TITLE

PROCESS FOR PREPARING SILANIZED TiO_2 PIGMENTS USING A MEDIA MILL

BACKGROUND OF THE INVENTION

The present invention relates to an improved process for preparing TiO_2 pigment for plastic and coating applications using a TiO_2 slurry as a feedstock. More particularly, this invention relates to a slurry process for preparing a silanized TiO_2 pigment for plastic and coating applications.

TiO_2 is generally produced by hydrolyzing an aqueous solution of titanium sulfate and calcining the hydrolyzate at 750° to 1000°C, or oxidizing titanium tetrachloride at elevated temperatures followed by cooling to temperatures below 600°C. A resulting slurry is formed by the addition of water to the TiO_2 pigment. Certain finishing steps are required to be performed on the resulting slurries such as filtering, washing, drying and fluid energy milling. A fluid energy mill, also referred to as a micronizer, involves introducing dry TiO_2 pigment and a fluid, e.g., air or steam into the outer portion of an inwardly spiraling vortex so as to convey the TiO_2 at high velocity against the housing of the spiral vortex to fracture agglomerates as described in U.S. Patent 4,427,451. Nonetheless, such milling is expensive and energy intensive. Fluid energy milling requires high energy input and intensive agitation.

U.S. 3,834,924 discloses surface modified pigments produced by adding amino organosilane to a pigment dispersion directly in a suitable solids mixing apparatus. The process therein eliminates the need for filtration, however, conventional finishing steps such as fluid energy milling are not mentioned.

U.S. 4,061,503 and U.S. 4,151,154 describe enhanced dispersibility of TiO_2 in paints and plastics. Therein, the TiO_2 is surface treated with a silane possessing at least two hydrolyzable groups bonded to silicon and an organic group containing a polyalkylene oxide group. In a U.S. 4,061,503 Example, the use of silane reduced the grinding time of TiO_2 pigment for use in a water reducible enamel and post treatment of silane to TiO_2. Each of the prior art processes suffers from various deficiencies and further improvements are desirable.

This invention provides a step forward in preparing TiO_2 for pigmenting plastics and coatings. The present invention provides numerous advantages. Mechanical handling of the high solids slurry is made easier by

lowering its viscosity, and eliminating the need for fluid energy milling results in a more economical, less energy intensive process. In addition, media milling eliminates the need for an additional step after drying to reduce the particle size further.

SUMMARY OF THE INVENTION

In accordance with this invention, there is provided an improved process for preparing a silanized TiO_2 pigment by media milling. The resultant pigment is particularly suitable for use in plastics and surface coatings. This improved process comprises first reducing the viscosity of a high solids TiO_2 pigment slurry. This may be accomplished by either adjusting the pH in the range of about 7.5 to about 11 with caustic or the like, or contacting the slurry with a reducent. Next, the slurry is treated with an organosilicon reagent. This step is preceded and/or followed by media milling the high solids slurry to reduce the TiO_2 particle size. The slurry is then dried as a product; hence no post drying manipulation to control pigment properties such as particle size distribution is required.

DETAILED DESCRIPTION OF THE INVENTION

The TiO_2 pigment useful in the process of this invention generally are in the rutile or anatase crystalline form and can be produced by a chloride process or sulfate process. Both the sulfate and chloride processes are described in greater detail in "The Pigment Handbook", Vol. 1, 2nd Ed., John Wiley & Sons, NY (1988) the teachings of which are incorporated herein by reference. The invention relates to a high solids aqueous TiO_2 slurry. "High solids" refers herein to a solids content typically greater than about 30% by weight based on the total weight of the slurry. Preferably, the TiO_2 solids content of the slurry will be from about 30 to about 85 wt.%.

A typical overall process of the present invention is as follows:

a base TiO_2 pigment→slurry(about 30-about 85% solids)→reduce viscosity→optional media mill→organosilicon reagent treatment→media mill→improved slurry→drying.

The TiO_2 employed in the preparation of the slurry will preferably have a narrow particle size range with at least 95 wt.% in the form of particle agglomerates having an equivalent spherical diameter less than about 7 microns, and an average primary particle size less than about 0.4 microns.

The TiO_2 pigments may also contain ingredients added thereto to improve dispersibility characteristics or other properties such as durability. Thus, by way of example, but not limited thereto, the pigment may contain additives and/or inorganic oxides, such as aluminum, silicon, tin, as well as triethanol amine, trimethylolpropane, phosphates, etc.

First, the base pigmentary TiO_2 is dispersed in an aqueous slurry and the viscosity of the slurry is reduced to a minimum of about 2000 centipoise (cps). Sufficiently low viscosity is required in order for the slurry to be fed into a media mill without significant plugging. This may be accomplished by adjusting the pH within the range of about 7.5 to about 11 by adding caustic or the like, e.g., dilute NaOH. A preferable pH range is about 9 to about 11. Alternatively, the slurry may be treated with a reducent. By way of example, but not limited thereto, reducents include triethanol amine (TEA), 2-amino-2-methyl-1-propanol (AMP), trimethylol propane (TMP), tetrapotassium pyrophosphate (TKPP) or the like and mixtures thereof. "Reducent" is used herein to refer to a dispersant which when added to a slurry reduces the viscosity of the slurry sufficiently to avoid significantly plugging a media mill. Typically, the amount of reducent is in the range of about 0.1 to 5% by weight, based on the weight of TiO_2. It will be appreciated by those skilled in the art that the reducent is used advantageously when there is no need otherwise to filter or wash the slurry.

Next, the slurry is treated with at least one organosilicon reagent having the general formula:

$$R_xSi(R')_{4-x}$$

wherein

R is nonhydrolyzable aliphatic, cycloaliphatic or aromatic group having at least 1 to about 50 carbon atoms;

R′ is a hydrolyzable group such as an alkoxy, halogen, acetoxy, hydroxy or mixtures thereof; and

x = 1 to 3.

By way of example, but not limited thereto, suitable silanes include vinyltriethoxy silane, butyltrimethoxysilane, hexyltrimethoxysilane, octyltriethoxysilane, nonyltriethoxysilane, etc. Additional examples of silanes include R=8-18 carbon

atoms; R' = chloro, methoxy, hydroxy or mixtures thereof; and x = 1 to 3. It is believed that the present invention is also applicable to fluoroorganosilicon compounds, i.e., wherein R is fluorine substituted, such as C_nF_{2n+1} wherein n = 8, 10, 12 or mixtures thereof; R' is a hydrolyzable group such as an alkoxy, halogen, acetoxy, hydroxy or mixtures thereof; and x = 1 to 3. For example, suitable fluoroorganosilicon compounds include, but are not limited thereto, trichloroperfluoroethylsilane, trichloroperfluorodecylsilane, and trichloroperfluorododecylsilane.

Alternatively, at least one polysiloxane can be useful in carrying out the invention. Polysiloxanes having the formula:

$$(R_nSiO_{\frac{4-n}{2}})_m$$

wherein

R is organic or inorganic groups;

n = 0-3; and

$m \geq 2$ are suitable.

For example, but not limited thereto, polydimethylsiloxane (PDMS) vinylphenylmethyl terminated dimethylsiloxanes, divinylmethyl terminated, polydimethylsiloxane and the like are suitable polysiloxanes. Mixtures of organosilicon compounds are contemplated equivalents. "Silanized" TiO_2 is defined herein to refer to TiO_2 treated with at least one silane and/or fluoroorganosilane, or a mixture of at least one silane and/or fluoroorganosilanes and at least one polysiloxane (collectively referred herein as organosilicon compounds).

The TiO_2 surface in current commercially available slurries is not generally water repellent, i.e., hydrophobic. It is desirable to have the TiO_2 particle surface hydrophobic for use in plastics and surface coatings when the pigment is pre-wetted with an organosilicon reagent for end-use in organic matrices such as plastics and coatings. It is believed that the organosilicon reagent renders the TiO_2 particulate surface hydrophobic.

Typically, the amount of organosilicon reagent suitable for processing TiO_2 in plastics or surface coatings is in the range of about 0.1 to 5% by weight, based on the weight of silanized TiO_2 pigment. Preferably, about 0.5 to about 3 wt.% is suitable. In excess of 5 wt.% may be used but no particular advantage is observed.

The organosilicon reagent is commercially available or can be prepared by processes known in the art such as those described in "Organosilicon

Compounds", S. Pawlenko, New York (1980), the teachings of which are incorporated herein by reference. The organosilicon reagent treatment can be carried out by any suitable means such as by injecting a solution into the slurry, by dripping with agitation or the like. If present as a mixture, the polysiloxane addition can be made in conjunction with the silane or post addition to the silane.

Media milling the slurry can be done either before and/or after the organosilicon reagent is added. The media milling of the slurry is done in a continuous or batch mode. The titanium dioxide slurry having particle agglomerates less than 50 microns is fed into a grind chamber which is packed with media beads. Media of different types and sizes may be used, with one of ordinary skill in the art being able to adjust the media to produce the desired result based on the size distribution of the particles in the starting material according to conventional protocols. Typically, the media is forced to move around a grind chamber by a series of discs attached to a rotating shaft. The motion of the media is perpendicular to the direction in which the slurry is pumped. Therefore, the TiO_2 particle agglomerates are sheared by the media. Typically, a set of screens keeps the media inside the grind chamber but allows the smaller TiO_2 particles to exit out of the mill. Optionally, the product of the mill can be further screened. The grinding residence time (flow rate of the slurry) will vary depending on the size of the media mill. For example, the slurry is processed through the media mill at about 0 to 7 gallons per minute (gpm) [about 0 to 26.5 liter per minute (lpm)] preferably about 1/2 to 3 gpm [about 1.9 to 11.4 lpm] for a 60 liter media mill to achieve the desired particle size reduction. The desired particle size reduction will depend on the end use for the pigment. For example, the slurry is media milled until the diameter of TiO_2 particle agglomerates having a size of about 1-10 microns is reduced to 5 wt.% for use in a high gloss coating application, and the slurry is media milled until the diameter of TiO_2 particle agglomerates having a size of about 1-10 microns is reduced to 3 wt.% for use in plastics applications. Current industrial manufacture of TiO_2 pigment typically requires particle size reduction by fluid energy milling, e.g., micronizing. The present invention achieves particle size reduction with a media mill and obviates the need for the fluid energy mill.

Finally, the slurry is dried by any suitable means, such as flash drying, spray drying or an oven, to less than 1 wt.% water, preferably 0.7% or lower. The slurry can be packaged as a product for use in plastics and surface coatings.

The following examples are merely illustrative and not intended to limit the disclosure. Viscosity was measured on a Brookfield® Viscometer (Brookfield Engineering Laboratories, Inc., Stoughton, Mass.).

EXAMPLES

EXAMPLE 1

A TiO_2 pigment slurry, with 30 to 60 wt.% solids, and a viscosity of 2200 centipoise (cps), was treated with dilute NaOH to adjust the pH to 9 to 11, and slurry viscosity was thereby reduced to about 120 cps.

The slurry was then processed through a 60 liter media mill at 3 gpm (11.4 lpm) to achieve the desired particle size reduction; e.g., % mass coarser than 1.0 micron. The media mill's grind chamber was charged to about 85% capacity with 250 lbs. (93 kg) ZrO_2/SiO_2 media. The media nominal size range is 0.60-0.80 mm in diameter. The milling of the slurry was done in a continuous fashion. After passing through the grind chamber, the slurry is separated from the grinding media by a set of screens. At the discharge of the mill, the slurry was treated with 1 wt.% octyltriethoxysilane, and dried to less than 1 wt.% water. The diameter of the TiO_2 particle agglomerates having a size of about 1 micron was reduced by about 91% after media milling.

Other property improvements determined were tinting strength (TS) and undertone (UT). The TiO_2 pigment product was tested for TS and UT which are measures of optical properties in plastics applications. For these tests, the pigment was dispersed in black vinyl compound on a two-roll mill. The tristimulus values, X, Y, Z of the vinyl sheet were measured with a Hunterlab Labscan spectrocolorimeter (Hunter Associates Laboratory, Inc., Reston, VA), and TS and UT were calculated versus standards prepared at the same time. TS and UT were derived from Y, and Z/X respectively. L*, a*, and b*, the color space coordinates defined by CIE (Commission Internationale de l'Eclairage) in 1976, were read directly on the spectrocolorimeter. The TS range for commercial TiO_2 pigments was about 80 to 120. The UT range was about -0.070 to +0.050. Averages for this example were:

$$TS = 107\ (+/-2)$$

$$UT = 0.034\ (+/-0.001)$$

These results were comparable to those for untreated TiO_2, which had been micronized, except that the TiO_2 from the example gave a slightly bluer undertone.

EXAMPLE 2

A TiO_2 pigment slurry, with 53 wt.% solids, and a viscosity of 8500 cps was treated with 0.2 ml of an organic dispersant, AMP (0.1 % by weight) at room temperature and the slurry viscosity was thereby reduced to 20 cps.

The slurry was then processed through a 60 liter media mill at 3 gpm (11.4 lpm) to achieve the desired particle size reduction, e.g., % mass courser than 1.0 micron as in Example 1.

At the discharge of the mill, the slurry was treated with 0.8 % by weight octyltriethoxysilane, stirred for 10 minutes at room temperature and dried to less than 1 wt.% water. The diameter of the TiO_2 agglomerates having a size of about 1 micron was reduced by about 91% after media milling. The treated, media milled TiO_2 pigment product was tested as in Example 1 for plastic applications. These results were comparable to those for untreated TiO_2 which had been micronized.

EXAMPLE 3

A TiO_2 pigment slurry, with 50 wt.% solids, and an unmeasurable viscosity (too high to be measured by the Brookfield® viscometer) is treated with caustic to adjust the pH to greater than 8.5 and the slurry viscosity is thereby reduced to 26-75 cps.

The slurry is then processed through a 60 liter media mill at 1 gpm (3.8 lpm) to achieve the desired particle size reduction, e.g., % mass courser than 1.0 micron as in Example 1.

At the discharge of the mill, the slurry is treated with 1% by weight butyltrimethoxysilane, stirred for 10 minutes at room temperature and dried to less than 1 wt.% water. The diameter of the TiO_2 agglomerates having a size of about 1 micron is reduced by about 91% after media milling. The treated, media milled TiO_2 pigment product is tested as in Example 1 for plastic applications. It is believed that these results would be comparable to those for untreated TiO_2 which are micronized.

EXAMPLE 4

Same as Example 3 except the organosilicon compound is a mixture of 1 wt% PDMS and 1 wt% octyltriethoxysilane. These results would be comparable to those for untreated TiO_2 which are micronized.

Having thus described and exemplified the invention with a certain degree of particularity, it should be appreciated that the following claims are not to be so limited but are to be afforded a scope commensurate with the wording of each element of the claim and equivalent thereof.

CLAIMS

What is claimed is:

1. A process for preparing a high solids TiO_2 pigment comprising the steps of:
   (a) reducing the viscosity of a high solids TiO_2 pigment slurry by adjusting the pH in the range of about 7.5 to about 11;
   (b) media milling the slurry;
   (c) contacting the slurry with an organosilicon reagent; and
   (d) drying the slurry to less than 1 wt.% water.

2. The process of Claim 1, wherein the viscosity is reduced by contacting the slurry with a reducent selected from the group consisting of triethanol amine, 2-amino-2-methyl-1-propanol, trimethylol propane and tetrapotassium pyrophosphate and mixtures thereof.

3. The process of Claim 1 or Claim 2, wherein the organosilicon reagent has the formula:

$$R_xSi(R')_{4-x}$$

wherein

R is nonhydrolyzable aliphatic, cycloaliphatic or aromatic group having at least 1 to about 50 carbon atoms;

R′ is a hydrolyzable group selected from alkoxy, halogen, acetoxy, hydroxy and mixtures thereof; and

x = 1 to 3,

and is present in the amount of about 0.1 to about 5% by weight, based on the weight of TiO_2.

4. The process of Claim 3 wherein the organosilicon reagent is fluorine substituted and $R = C_nF_{2n+1}$ wherein n=8, 10, 12 or mixtures thereof.

5. The process of Claim 3 or Claim 4 wherein the organosilicon reagent further comprises a polysiloxane having the formula:

$$(R_nSiO_{\frac{4-n}{2}})_m$$

wherein

R is organic or inorganic group;

n = 0-3; and

$m \geq 2$.

6. The process of Claim 3 or Claim 4 wherein the organosilicon reagent is selected from the group consisting of vinyltriethoxysilane, butyltrimethoxysilane, hexyltrimethoxysilane, octyltriethoxysilane, nonyltriethoxysilane, trichloroperfluoroethylsilane, trichloroperfluorodecylsilane and trichloroperfluorododecylsilane.

7. The process of Claim 5 wherein the organosilicon reagent is selected from the group consisting of polydimethylsiloxane, vinylphenylmethyl terminated dimethylsiloxanes, divinylmethyl terminated and polydimethylsiloxane.

8. The process of Claim 3, further comprising:

(e) media milling the slurry after step (c).

* C L M S *

SG 9611251-1

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 : C09C 1/36 — A1

(11) International Publication Number: WO 95/23194

(43) International Publication Date: 31 August 1995 (31.08.95)

(21) International Application Number: PCT/US95/02813

(22) International Filing Date: 28 February 1995 (28.02.95)

(30) Priority Data:

08/203,144	28 February 1994 (28.02.94)	US
08/392,706	23 February 1995 (23.02.95)	US

(71) Applicant: E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US).

(72) Inventors: NIEDENZU, Philipp, Martin; 502 Ashe Avenue, New Johnsonville, TN 37134-2354 (US). HERKIMER, Scott, Matthew; 101 Red Oak Circle, Dickson, TN 37055 (US). CHANEY, Ronald, Lee; Route 3, Box 121D, McEwen, TN 37101-9122 (US).

(74) Agents: YUN, Caroline, J. et al.; E.I. du Pont de Nemours and Company, Legal/Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).

(81) Designated States: AM, AU, BB, BG, BR, BY, CA, CN, CZ, EE, FI, GE, HU, JP, KG, KP, KR, KZ, LK, LR, LT, LV, MD, MG, MN, MX, NO, NZ, PL, RO, RU, SD, SI, SK, TJ, TT, UA, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ, UG).

Published

With international search report.

Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.

RMP

(54) Title: PROCESS FOR PREPARING SILANIZED TiO_2 PIGMENTS USING A MEDIA MILL

(57) Abstract

Disclosed is an improved process for preparing a silanized TiO_2 pigment by media milling.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgystan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo			SE	Sweden
CH	Switzerland	KR	Republic of Korea	SI	Slovenia
CI	Côte d'Ivoire	KZ	Kazakhstan	SK	Slovakia
CM	Cameroon	LI	Liechtenstein	SN	Senegal
CN	China	LK	Sri Lanka	TD	Chad
CS	Czechoslovakia	LU	Luxembourg	TG	Togo
CZ	Czech Republic	LV	Latvia	TJ	Tajikistan
DE	Germany	MC	Monaco	TT	Trinidad and Tobago
DK	Denmark	MD	Republic of Moldova	UA	Ukraine
ES	Spain	MG	Madagascar	US	United States of America
FI	Finland	ML	Mali	UZ	Uzbekistan
FR	France	MN	Mongolia	VN	Viet Nam
GA	Gabon				

96112511

16 SEP 1996