

## CLAIMS

1. A quantum computing device, comprising:
  - a device region located on a superconductor layer above a first surface of a semiconductor layer;
  - a sensing region located within the device region, the sensing region comprising a portion of the device region including no superconductor layer;
  - a sensing region contact comprising a first metal coupled to the first surface of the semiconductor layer within the sensing region;
  - a nanorod contact comprising the first metal coupled to the superconductor layer within the portion of the device region outside the sensing region;
  - a tunnel junction gate comprising a second metal within the sensing region, the tunnel junction gate disposed on a second surface of the semiconductor layer; and
  - a chemical potential gate comprising the second metal within a portion of the device region outside the sensing region, the chemical potential gate disposed on the second surface of the semiconductor layer.
2. The quantum computing device of claim 1, wherein the first device region comprises a first nanorod region, a second nanorod region substantially parallel to the first nanorod region, and the sensing region, the sensing region connecting the first nanorod region and the second nanorod region.
3. The quantum computing device of any one of the preceding claims, further comprising:
  - a buffer layer formed on a first surface of a substrate;
  - a first protective layer formed below the second surface of the semiconductor layer;and
  - the semiconductor layer formed on the first protective layer
4. The quantum computing device of claim 3, wherein the buffer layer comprises indium aluminum arsenide.
5. The quantum computing device of any one of claims 3 to 4, wherein the first protective layer comprises indium gallium arsenide.

6. The quantum computing device of any one of the preceding claims, wherein the superconductor layer comprises aluminum.
7. The quantum computing device of any one of the preceding claims, further comprising:  
a second protective layer formed between the first surface of the semiconductor layer and the superconductor layer.
8. The quantum computing device of any one of the preceding claims, further comprising:  
an isolation region surrounding the device region, the isolation region comprising a region in which the superconductor layer has been removed and the semiconductor layer implanted
9. A computer-implemented method to fabricate a quantum computing device, the method comprising:  
forming, on a superconductor layer, a first resist pattern defining a device region and a sensing region within the device region;  
removing, using an etching process, the superconductor layer within the sensing region, the etching exposing a region of a first surface of an underlying semiconductor layer outside the device region unprotected by the first resist pattern;  
implanting the exposed region of the first surface of the semiconductor layer, the implanting forming an isolation region surrounding the device region;  
exposing, using an etching process subsequent to the implanting, the sensing region and a portion of the device region of the superconductor layer adjacent to the isolation region;  
forming a sensing region contact by coupling the first surface of the semiconductor layer with a first metal layer;  
forming a nanorod contact using the first metal coupled to the superconductor layer within the portion of the device region outside the sensing region; and  
forming, by depositing a second metal layer on a second surface of the semiconductor layer within the sensing region, a tunnel junction gate.

10. The computer-implemented method of claim 9, wherein the first device region comprises a first nanorod region, a second nanorod region substantially parallel to the first nanorod region, and the sensing region, the sensing region connecting the first nanorod region and the second nanorod region.
11. The computer-implemented method of any one of claims 9 to 10, further comprising:
- forming, on a first surface of a substrate, a buffer layer;
  - forming, on the buffer layer, a first protective layer;
  - forming, on a first protective layer, the semiconductor layer; and
  - forming, on the first surface of the semiconductor layer, the superconductor layer.
12. The computer-implemented method of claim 11, wherein the buffer layer comprises indium aluminum arsenide.
13. The computer-implemented method of any one of claims 11 to 12, wherein the first protective layer comprises indium gallium arsenide.
14. The computer-implemented method of any one of claims 9 to 13, wherein the superconductor layer comprises aluminum.
15. The computer-implemented method of any one of claims 9 to 14, further comprising:
- forming, between the first surface of the semiconductor layer and the superconductor layer, a second protective layer.
16. The computer-implemented method of any one of claims 9 to 15, further comprising:
- removing, prior to depositing the first metal layer, the first resist pattern.

17. The computer-implemented method of any one of claims 9 to 16, wherein depositing the first metal layer is performed in regions defined by a second resist pattern.

18. The computer-implemented method of any one of claims 9 to 17, further comprising, prior to depositing the second metal layer:

protecting the sensing region contact, the nanorod contact, and the superconductor layer using an encapsulation film; and

depositing, above the encapsulation film, a carrier wafer.

19. The computer-implemented method of any one of claims 9 to 18, further comprising forming, by depositing the second metal layer on the second surface of the semiconductor layer.

20. A superconductor fabrication system comprising a lithography component, the superconductor fabrication system when operated on at least one die to fabricate a quantum computing device performing operations comprising:

forming, on a superconductor layer, a first resist pattern defining a device region and a sensing region within the device region;

removing, using an etching process, the superconductor layer within the sensing region, the etching exposing a region of a first surface of an underlying semiconductor layer outside the device region unprotected by the first resist pattern;

implanting the exposed region of the first surface of the semiconductor layer, the implanting forming an isolation region surrounding the device region;

exposing, using an etching process subsequent to the implanting, the sensing region and a portion of the device region of the superconductor layer adjacent to the isolation region;

forming a sensing region contact by coupling the first surface of the semiconductor layer with a first metal layer;

forming a nanorod contact using the first metal coupled to the superconductor layer within the portion of the device region outside the sensing region; and

forming, by depositing a second metal layer on a second surface of the semiconductor layer within the sensing region, a tunnel junction gate.