

THIS SHEET HAS BEEN
REPLACED

1

HIGH CAPACITY RECHARGEABLE CELL HAVING MANGANESE DIOXIDE ELECTRODE

FIELD OF THE INVENTION:

This invention relates to rechargeable cells having a manganese dioxide positive electrode, a potassium hydroxide or zinc chloride/ammonium chloride electrolyte and metallic zinc as the negative electrode material. The theoretical discharge capacity of the zinc contained in the negative electrode is in the range of from 65% to 110% of the theoretical one electron discharge capacity of the MnO_2 in the positive electrode. The usual embodiment may be the typical "bobbin" type cylindrical cell, however spirally wound cells, button or coin cells, and flat plate cells may be provided in keeping with the present invention.

BACKGROUND OF THE INVENTION:

For purposes of the present discussion, the capacity on the first discharge of the MnO_2 contained in the positive electrode between the MnO_2 status and the MnOOH status is termed or designated as the theoretical one electron discharge capacity of the manganese dioxide electrode, which is 308 m Ah/g of manganese dioxide. If the discharge process of the MnO_2 positive electrode continues beyond the MnOOH level, an irreversible phase change has been reported to occur, so that the manganese dioxide electrode is no longer fully rechargeable.


Specifically, the following equation is descriptive of the discharge reaction which takes place as the MnO_2 discharges towards its MnOOH status in the presence of an aqueous electrolyte.



Discharge according to this reaction occurs with essentially no phase change. If the discharge process of the manganese dioxide positive electrode continues beyond the MnOOH level, an irreversible phase change has been reported to occur, so that the manganese dioxide electrode is no longer fully rechargeable. Such phase change must be avoided. Responsible for the phase change is the following reaction:

This Sheet Has Been Replaced





However, particularly with reference to practical aqueous manganese dioxide/zinc cells, discharge according to this reaction occurs at a voltage which is too low to contribute to the useful service life of the cell, since it occurs below
5 0.8 volts.

To provide rechargeable alkaline manganese dioxide/zinc cells, there have been a number of steps taken to ensure rechargeability; and specifically, steps have been taken to severely limit the discharge of the MnO_2 to a fraction of the one electron discharge by limiting the capacity of the zinc electrode accordingly.

10 Historically, rechargeable alkaline MnO_2/Zn cells that have been brought to the market in the late 1960's and early 1970's were not successful because of the constraints placed upon them. Those constraints included the use of electronic controls to cut off the discharge after a certain time of use to not permit discharge beyond the MnOOH level. In general, such cells were merely modified primary
15 alkaline manganese dioxide/zinc cells, and generally they had the same ratio of Zn metal in the negative electrode to MnO_2 in the positive electrode as primary cells and, therefore, had a very limited cycle life. Once a battery of cells in series had been discharged to 0 Volt, the cells were no longer rechargeable. Such cells were also quite low in respect of their energy densities: For example, a
20 rechargeable D cell may have been rated at only 2 Ah. A more full discussion of the above is found in FALK and SALKIND Alkaline Storage Batteries, published by John Wiley & Sons, New York, 1969, at pages 180 to 185, and also pages 367 to 370.

So as to overcome the recharge problems of the MnO_2 , as noted above,
25 cells were developed by which the discharge capacity of the cell was limited by imposing a zinc negative electrode limitation -- by which it was made impossible to discharge the MnO_2 to more than a fraction of the one electron discharge capacity of the negative electrode. For example, the discharge capacity of the zinc negative electrode was limited by design to be no more than about 30% of
30 the one electron discharge capacity of the MnO_2 in the positive electrode. This preserved the rechargeable characteristics of the cell, but resulted in a cell having

quite low deliverable energy capacity and density. Those limitations, understandably, mitigated against the commercial acceptability of such cells.

Reference is made to AMANO *et al* U.S. Patent 3,530,496, issued September 22, 1970. AMANO *et al* make a very strong statement of their intent to limit the depth of discharge of the MnO_2 electrode by providing a zinc electrode that has its capacity limited to between 20% to 30% of the one electron discharge capacity of the MnO_2 in the positive electrode. It should be noted that the concept of electrode balance is well known, and for the cells discussed it is the ratio of the theoretical discharge capacity of the metallic zinc in the negative electrode with respect to the theoretical one electron discharge capacity of the manganese dioxide in the positive electrode. AMANO *et al* shows, in Figure 8 of that patent, the capacity decay vs. cycle of "D" size cells in cases where the depth of discharge of the MnO_2 electrode is set at 100%, 50%, 30%, 20% and 10% of the theoretical one electron MnO_2 discharge capacity. The target depth of discharge of the MnO_2 electrode is set by varying the theoretical capacity of the negative electrode. All "D" size test cells were cycled until their discharge capacity fell below 0.5 Ah, that is below an energy density of about 4 Wh/kg of cell weight. Using a 50% electrode balance, AMANO *et al* report an initial cell capacity of 4.5 Ah, which degrades to 0.5 Ah within 15 cycles. In other words, the 15th cycle capacity represents 11% of the first cycle capacity. Based on the negative findings of this experiment, AMANO *et al* conclude that an electrode balance exceeding 30% of the theoretical one electron MnO_2 discharge capacity produces a cell with a cycle life which is too low to be commercially viable. In their Table 1, AMANO *et al* list the number of cycles achieved in their experiments to an end of life discharge capacity of 0.5 Ah -- that is, 3.6 Ah/kg - as a function of the cell balance. They report the service life of the cell as being only 6 cycles at 100% balance, 15 cycles at 50% balance, 35 cycles at 30% balance, 84 cycles at 20% balance, and over 99 cycles at 10% balance. These results have led AMANO *et al* to the conclusion that an electrode balance exceeding 30% of the theoretical one electron MnO_2 discharge capacity results in a cell that has poor performance characteristics.

OGAWA *et al*, in U.S. Patent 3,716,411, issued February 13, 1973, teach a rechargeable alkaline manganese cell with the discharge capacity of the zinc electrode controlled within a range so as to ensure the recharge capability of the MnO_2 electrode. The zinc electrode and MnO_2 electrode face each other through a gas permeable and dendrite impermeable separator. However, the OGAWA *et al* cell is strictly negative electrode limited in that the capacity of the zinc electrode is held to be not more than about 40% of the theoretical one electron discharge capacity of the manganese dioxide in the positive electrode. OGAWA *et al* discuss the fact that if a manganese dioxide/zinc cell is discharged to below 0.9 volts and down to about 0.75 volts, and where the capacity of the zinc negative electrode is about the same or slightly smaller than that of the manganese dioxide positive electrode, then the recharge capability of the manganese dioxide strongly deteriorates. OGAWA *et al* provide that under no conditions should the depth of discharge of the zinc electrode be permitted to exceed 60% of the theoretical one electron discharge capacity of the manganese dioxide positive electrode.

KORDESCH, in U.S. Patent 4,091,178, issued May 23, 1978, also provides a rechargeable MnO_2/Zn cell where the theoretical discharge capacity of the zinc negative electrode is specifically limited to about 33% of the one electron discharge capacity of the positive electrode. However, KORDESCH also provides what he calls a "charge reserve mass", in which a quantity of zinc oxide is placed that is equal to at least 50% of the discharge capacity of the metallic zinc in the negative electrode. The energy density of the KORDESCH cell is quite low.

Tomantschger *et al*, in a commonly owned U.S. Patent Application No. 07/893,793 filed June 4, 1992, provide rechargeable alkaline manganese zinc cells that utilize an MnO_2 positive electrode and a zinc negative electrode, wherein the discharge capacity of the zinc electrode is limited to from greater than 60% and up to 100% of the theoretical one electron discharge capacity of the MnO_2 . That provides a rechargeable alkaline manganese cell having higher capacity and higher energy density than has been available from the prior art cells.

OBJECTIVE OF THE INVENTION:

The purpose of this invention is to provide a rechargeable alkaline manganese dioxide-zinc cell which has the following features:

- a high discharge capacity on its first discharge;
- 5 a long cycle life;
- the ability to recuperate from overdischarge without an excessive performance loss on further cycling; and
- the ability to be used as power source in appliances without the requirement to employ devices for cutting off discharge of the cell or batteries at
- 10 a predetermined limit.

The present invention accomplishes these objectives by determining the optimum electrode balance range where the electrode balance is defined as the ratio of the theoretical discharge capacity of the Zn active material of the negative electrode to the theoretical one electron discharge capacity of the MnO_2 active

15 material contained in the positive electrode. The influence of various electrode balances on the initial discharge capacity and the cycle life as well as the ability to recuperate following an overdischarge were determined. the reason for this determination was the fact that users of batteries sometimes forget to switch off a battery powered device so that current will flow until the battery voltage reaches

20 zero Volts. A battery generally consists of a series of connected cells; e.g. four cells in series for a 6 volt battery. On overdischarge of a 6 Volt battery, current is driven through a weak cell (or cells) with the result of oxygen evolution on the totally discharged zinc electrode and/or hydrogen evolution on the overdischarged manganese dioxide electrode. The consequence of such an overdischarge is

25 typically bulging and/or leakage and/or the loss of cycle life.

What the present invention provides is rechargeable manganese dioxide/zinc cells with an aqueous electrolyte which have a high capacity relative to prior art cells. A separator between the zinc electrode and the manganese dioxide electrode, and appropriate terminal means contacting the zinc electrode

30 and manganese dioxide electrode are provided. As noted above, the discharge

THIS SHEET HAS BEEN
REPLACED

6

capacity of the manganese dioxide electrode between the MnO_2 status and the MnOOH status is termed the theoretical one electron discharge capacity of that electrode.

5 The present invention also contemplates an aqueous electrolyte containing potassium hydroxide or a mixture of zinc chloride and ammonium chloride.

To reduce the mobility of zincate in the alkaline electrolyte by precipitation, the negative electrode may contain between .5% and 25% of an additive chosen from the group consisting of magnesium, barium and calcium, their oxides and hydroxides.

10 In keeping with the provisions of the present invention, the theoretical discharge capacity of the zinc negative electrode is in the range of from 65% and up to 110% of the theoretical one electron discharge capacity of the manganese dioxide electrode.

15 In a typical embodiment of cells according to the present invention, where the cells are intended for commercial exploitation, the electrolyte is a 4N to 12N aqueous solution of potassium hydroxide.

Cells according to the present invention may have a number of additives for purposes of enhancing the conductivity and the structural integrity of the MnO_2 positive electrode, or for inhibiting oxygen evolution or hydrogen evolution. For example, the MnO_2 electrode may include at least one additive which is chosen from the group consisting of 5% to 15% by weight of graphite, 0.1% to 15% by weight of carbon black, an inorganic binder, and/or an organic binder. The binder materials may be present in the range of from 0.1% to 15% by weight of the MnO_2 electrode. The carbon black may be present as a porous additive in the MnO_2 electrode in the range of from 0.1% to 15% by weight thereof.

30 Generally, the positive electrode of cells in keeping with present invention will include a barium-based additive in an amount of from about 3.0% to about 25% by weight of the positive electrode. The addition of a barium compound has been found to have a beneficial effect on the cycle life of the cell. Typically, such barium compounds may be such as BaSO_4 , BaO , and Ba(OH)_2 .

This Sheet Has Been Replaced



To promote hydrogen gas recombination within the positive electrode, the positive electrode composition may include hydrogen recombination catalysts such as those taught in commonly owned U.S. Patent 5,162,169, issued November 10, 1992. Still further, so as to provide for overcharge capability, oxygen
5 recombination techniques such as those taught in commonly owned U.S. Patent 5,043,234, issued August 27, 1991, to Tomantschger *et al*, may be utilized. To enhance the overcharge capability of the manganese dioxide electrode, catalysts may be added to it to facilitate oxygen evolution. Any catalyst must be stable over a wide voltage range -- typically from 0.9 volts versus Zn to 2.0 volts versus
10 Zn -- and also over a wide temperature range -- typically from -40°C to +70°C - - without any significant deterioration in performance of the cell. Such catalysts may be at least one of an oxide, spinel, or perovskite of nickel, cobalt, aluminum, zinc, iron, manganese, chromium, vanadium, titanium, and silver.

Still further, for purposes of improved hydrogen transfer, the positive
15 electrode composition may further comprise from about 0.1% to 15% of a hydrophobic additive such as PTFE, polyethylene, or polypropylene, together with an additional porous additive such as from about 0.1% to 15% of carbon black. Such additives improve the gas transport characteristics of the positive electrode, and thereby enhance the hydrogen recombination rate.

20 The manganese dioxide electrode may comprise from 0.1% to 5% of a hydrogen recombination catalyst such as one chosen from the group consisting of silver, oxides of silver, and compounds of silver, as described in U.S. Patent 5,162,169, issued November 10, 1992, to Tomantschger *et al*.

Depending on the nature of the cell, the positive electrode may be molded
25 into pellets and inserted into the can, followed optionally by recompaction. Otherwise, the positive electrode may be extruded directly into the can, or it may be rolled or cast as a flat positive electrode for use in flat plate cells, button or coin cells.

THIS SHEET HAS BEEN
REPLACED

BRIEF DESCRIPTION OF THE DRAWINGS:

The present invention is described hereafter, in association with the accompanying drawings, in which:

Figure 1 is a typical cylindrical cell in which the present invention may be embodied.

DESCRIPTION OF THE PREFERRED EMBODIMENTS:

Referring to Figure 1, a typical cylindrical cell is shown at 10. The cell comprises a container 12, within which is a manganese dioxide positive electrode 14 and a zinc negative electrode 16. The container 12 is a nickel plated deep drawn steel can, although other suitable metal cans may be used. So as to improve the contact and conductivity between the positive electrode 14 and the can 12, and thereby so as to reduce the internal resistance of the cell, the internal surface of the container 12 may be coated with a conductive carbon coating such as LONZA™.

The manganese dioxide positive electrode 14 may be placed into the container 12 by such ordinary cell manufacturing techniques as by being molded into discrete pellets, and then placed in the container 12, or by being extruded into the container. It is generally comprised of manganese dioxide, to which a variety of optional additives may be mixed, as discussed hereafter. Typically the MnO_2 is electrolytic manganese dioxide to which optionally at least one hydrogen recombination catalyst has been added. Chemically synthesized MnO_2 may also be used.

A suitable manganese oxide positive electrode for use in a rechargeable cell is described in U.S. Patent No. 5,300,371 issued April 5, 1994 (unconstrained balance CIP). Suitable active materials utilizing manganese oxides comprise e.g. electrolytically or chemically synthesized manganese dioxide containing typically over 90% of four valent manganese and minor amounts of lower valance oxides. Alternatively manganese oxides can comprise a mixture of manganese dioxide and MnOOH or comprise bismuth modified manganese oxides. In the case manganese oxides are used as active material in the positive electrode typically



1 to 15% of graphite or carbon black are added to the electrode as well as minor amounts of a hydrophobic lubricant such as polytetrafluoroethylene or a stearate. To improve the cycling performance of the manganese oxide electrode the addition of various compounds such as barium oxide, hydroxide or sulphate in the range from 3% to 15% are desired.

For the purpose of hydrogen recombination typically 0.01% to 10% of suitable hydrogen recombination catalyst can be added to the positive electrode. Effective catalysts include silver, its oxides, and compounds as well as alloys of metals capable of absorbing hydrogen such as nickel, iron, lanthanum, titanium.

Between the positive electrode and the negative electrode there is located a separator 18. The cell is closed by the closure member 20, through which a current collector 22 extends into the negative electrode 16. The current collector or nail 22 contacts a metal negative cap 24 which is placed or welded across the head of the nail, and across the closure member 20, thereby providing a negative terminal for the cell 10. At the other end of the cell there is formed a pip 26, and it provides the positive terminal for the cell. It is evident that the can 12 contacts the positive electrode 14 whereas only the cap 24 through nail 22 contacts the negative electrode 16. To preclude short circuit within the cell, the pip 26 is insulated from the negative electrode 16 by an insulating washer or bottom cup 28.

The closure member 20 is normally formed of a plastic material, and contains a safety vent (not shown) which may be simply a rupturable membrane, or a resealable vent. The plastic closure member is moulded from a thermoplastic material such as polyethylene and/or polypropylene, talc filled polypropylene, polysulfone, nylon, and the like.

It is evident that similar or appropriate structures, providing negative and positive electrodes respectively connected to negative and positive terminals for the cell, and separated by an appropriate separator, may be provided in spirally wound cells, flat plate cells, and button or coin cells.

Within the cell, an aqueous electrolyte provides ionic paths so that the cell may be charged and discharged.

The separator 18 is generally a complex flexible structure which is impermeable to zinc dendrites, but which is permeable to ions and which may be permeable to the passage of gases such as hydrogen or oxygen that are produced within the cell on overcharge, standby, or overdischarge conditions. The separator
5 may comprise an absorber made from cellulose, rayon, polyamide polypropylene, or polyvinylalcohol fibres, and a barrier which may consist of an ion permeable membranes made of cellulose, CELLOPHANE™, or radiation grafted polyethylene, polypropylene, or the like. The ion permeable membrane prevents zinc dendrite growth that may short the electrodes. Other appropriate separator
10 materials such as those sold in association with the trademarks CELGARD™, ZAMM™, and PERMION™ may be used, as well as multi-component designs that include an absorber and a barrier, laminated structures having several laminates, and so on.

The negative electrode 16 comprises powdered metallic zinc together with
15 a suitable gelling agent such as carboxymethyl cellulose, polyacrylic acid, starches, and their derivatives. A charge reserve mass of ZnO -- usually solid zinc oxide -- and generally in the amount of from 1% to 20% by weight of the negative electrode, may optionally be used to compensate for losses due to the migration zincates from the negative to the positive electrode compartment of the
20 cell.

Until recently, hydrogen generation of the zinc electrode was suppressed by amalgamating the zinc powder with up to 3% of mercury. However, demand is now created for environmentally friendly cells, whereby the amount of mercury employed is reduced to below 0.025% based on the cell weight. Indeed, it is
25 desirable to ultimately eliminate the use of mercury altogether. To minimize the evolution of hydrogen gas, a low pollution negative electrode contains at least one additive in the range of 0.01% to 0.5% based on the weight of the zinc powder, which additive is selected from the group consisting of lead, gallium, bismuth, cadmium and indium metals or their compounds. These metals can be provided
30 in a suitable zinc alloy, or alternatively the zinc powder can be treated to provide a surface deposit of the desired metals. Still further, the selected metal or metals,

and/or their compounds may be added to the negative electrode composition during the gel processing step. Further yet, the selected metal compounds may be introduced via the electrolyte. Optionally, organic additives as surfactants in range of 0.01% to 0.5% may be employed to reduce dendrite formation and/or hydrogen gassing of the zinc electrode.

Zincate mobility within the cell may be reduced by the use of additives to the negative electrode mix such as 1% to 15% of compounds of magnesium, barium, and calcium, typically their oxides, or their hydroxides, or mixtures thereof. Oxygen gas recombining agents may also be added to the zinc negative electrode as are taught in commonly owned United States Patent 5,043,234 issued August 27, 1991.

The electrolyte is an aqueous alkali solution of usually 4N to 12N potassium hydroxide. The electrolyte may contain additives such as dissolved zinc oxide so as to reduce the gassing of the active zinc within the negative electrode, and so as to permit overcharge of the cell without damage to it. Also, as noted earlier, from 1% to 20% ZnO can optionally be included in the cell, as a charge reserve mass.

Other electrolytes effective with zinc electrodes are potassium hydroxide or a mixture of ZnCl_2 and NH_4Cl .

The electrical performance of cells is frequently compared in amperehours of discharge capacity delivered per cell of equal size at a specified discharge rate such as e.g. a 10 hour discharge rate. Frequently, the performance is compared in Wh of energy delivered by cells of equal size. To compare performance of cells of different size Wh of energy per kilogram of cell weight or Wh per litre of cell volume are compared.

Example I:

Test cells were constructed using the following electrode compositions:

	<u>Positive electrode Composition</u>		<u>Negative electrode Composition</u>	
	MnO ₂	79.01	Zn	56.95
5	Graphite,	14.49	CARBOPOL™	0.52
	Carbon PTFE, Ag ₂ O		ZnO	9.00
	9N KOH	6.50	9N KOH, 5% ZnO	33.53

10

The negative electrode according to the composition noted above is conveniently produced in the form of a gel containing metallic zinc powder and zinc oxide. The zinc oxide is introduced into the gel, either up to 10% dissolved in electrolyte and/or in an amount up to 20% by weight of the negative electrode as solid zinc oxide powder.

15

Groups of various different cylindrical AA alkaline manganese dioxide/zinc cells were manufactured in a way that the theoretical discharge capacity of the zinc electrode was 65%, 80%, 90%, 100%, 110%, 120%, or 130% of the theoretical one electron capacity of the manganese dioxide electrode. To accommodate the various electrode balances in the constant cell volume, the weights of the manganese dioxide and the zinc electrode were varied accordingly.

20

Then, one set of control cells from each of the balance sets was tested by continuously discharging the cell on a 10 ohm load resistor -- representing a drain rate of about 15 mA/g of the MnO₂ -- to a cutoff voltage of 0.9 volts. After discharge, the control cells were recharged immediately.

25

A second set of cells was assembled into a four cell battery pack, in series. The battery pack was connected to a 39 ohm load resistor for one week. It should be noted that in general the useful cell capacity of the cells is exhausted within the first 15 hours of discharge when the battery pack voltage reaches 3.6 Volts. However, if the user forgets to switch off the device, the battery continues to discharge until its voltage reaches 0 Volt. Because all of the cells are not exactly equal in discharge capacity, one of the cells within the battery pack is driven to a negative voltage by the other cells which are still discharging. The weak cell is overdischarged.

30

After one week the four cell battery pack is disassembled, and each of the cells is recharged individually and then cycled on a ten ohm load to 0.9 volts cutoff, to determine to what degree cells of the various balance groups have retained their cycling capability.

5 Table 1 shows the average discharge capacity of the test cells on the initial discharge, the second discharge without and with overdischarge in a 6 Volt battery pack for one week as described above. The last column E contains the capability of cycling after overdischarge calculated as column D as a percentage of C.

10

TABLE 1: Performance Comparison of AA Test Cells Ranging in Electrode Balance from 65% to 130% with and without an Overdischarge on the Walkman Test (10 Ω to .9V).

15	A Electrode Balance [Zn:MnO ₂]e]	B Initial Discharge Capacity to .9V [mAh]	C Second Discharge Capacity to .9V [mAh] Without Overdischarge	D Second Discharge Capacity to .9V After Overdischarge [mAh]	E Retention of Electrical Cycling Capability
20					
	130%	1614	1143	165	14%
	120%	1583	1113	262	24%
25	110%	1571	1139	800	70%
	100%	1547	1135	1310	115%
	90%	1473	1079	1048	97%
	80%	1353	998	862	86%
30	65%	1250	1125	1120	100%

From a review of Table 1 above it is evident that up to an electrode balance of 110%, a 70% to 115% retention of the cycling capability of cells following an overdischarge is observed. There is only very limited recovery when the electrode balance is above 110%, e.g. 14% and 24%.

35 Thus, it is apparent that substantially up to and including an electrode balance of 110% theoretical discharge capacity of the negative electrode with respect to the theoretical one electron discharge capacity of the manganese dioxide

electrode, cells according to the present invention provide useful capacity, and are rechargeable and capable of retaining their cycling capability following an overdischarge.

Example II:

5 An important comparison between rechargeable cell designs is in respect of the theoretical energy capacities of the electrodes. Therefore, various designs of AA (LR06) cells according to the teachings in three prior art patents were compared with results of tests on cells constructed according to this invention. The theoretical energy densities were calculated as shown in Table 2. It should
10 be noted that the comparisons are made on the basis of each of the cells having a total volume of 7.5 ml, a weight of 22.5 g, and an average discharge voltage of 1.25 volts. The theoretical capacities are in practise, achievable only at low discharge rates. Table 2 provides both the theoretical gravimetric and volumetric energy densities of the respective prior art cells; and included in Table 2 in all
15 categories shown are cells in keeping with the present invention and as described in Example I.

TABLE 2: AA Cell Design Comparisons
Prior Art Versus This Invention

	AMANO 3,530,496	KORDESCH 4,091,178	OGAWA 3,716,411	This Invention	This Invention
20 MnO ₂ {Ah} 1e ⁻	2.234	2.261	2.136	2.760	2.136
25 Zn{Ah} 2e ⁻	0.670	0.746	1.282	1.930	2.136
Cell{Ah}	0.670	0.746	1.282	1.930	2.136
30 Electrode Ratio	30%	33%	60%	70%	100%
Theoretical Energy per Cell(Wh)	.877	.933	1.602	2.413	2.670
35 theor. Energy Density (Wh/kg)	39	41	71	107	119
40 (Wh/l)	117	124	214	322	356

It is clearly evident from Table 2 that cells according to the present invention have substantially improved energy density when compared to AMANO, KORDESCH and OGAWA.

5 Example III:

Using the positive electrode and negative electrode compositions as described above with respect to Example I, the present invention was applied to AAA, AA, C, and D cells having conventional cylindrical cell configurations. The capacity in ampere-hours of cells in each size was determined, as noted
10 below in Table 4, and the cells were optimized having the respective ratios of the zinc in the negative electrode to the MnO_2 in the positive electrode as noted in line 2 of Table 4. The ratios are stated with respect to the theoretical one electron discharge capacity of the MnO_2 present in the positive electrode.

It is seen from Table 3 that the gravimetric energy densities generally
15 range from about 115 Wh/kg to about 120 Wh/kg; and that the volumetric energy densities generally range from about 300 Wh/litre. Comparing with the respective values in Table 2 of example 2, cells of the present invention have the gravimetric energy density improved by more than 50%, and the volumetric energy density by more than 43%. Four cells of each cell size AAA, AA, C, and D were
20 connected in series into battery packs and each pack was discharged through a resistor of 39 ohms for seven days. All cells were recharged and then submitted to discharge-charge cycling. The retention of electrical cycling capability calculated as in example 1 exceeded 70% for all packs; this being further proof of utility of the present invention.

TABLE 3: Energy Densities of Cylindrical RAM Cells According to the Present Invention

	AAA	AA	C	D
5 Capacity [Ah]	1.02	2.14	5.67	13.30
Zn:1e ⁻ MnO ₂ Ratio	0.95	1.00	0.80	0.65
10 theor. Energy Density {Wh/kg}	116	118	115	121
{Wh/l}	364	357	308	346

Example IV:

To demonstrate the cycling capability of cells in keeping with the present invention and having positive electrode and negative electrode compositions as noted below in Table 4 were constructed. However, one set of AA cells was constructed having a Zn to one electron MnO₂ discharge capacity ratio of about 65%; and the other set of AA cells was constructed having a negative electrode to one electron MnO₂ discharge capacity ration of about 110%. Those cells were then subjected to deep discharge tests at 3.9 Ohms -- representing a six hour discharge rate -- to a 0.8 volt cutoff. In each case, the cells were immediately recharged after discharge.

TABLE 4: Composition of Present Design Test Cells used in Example IV

	<u>Positive electrode Composition</u>	<u>Negative electrode Composition</u>
	MnO ₂ 83.03	Zn, ZnO 65.00
	Graphite, Carbon,	CARBOPOL 0.50
35 PTFE, Ag ₂ O 10.47		9N KOH, 5% ZnO 34.50
9N KOH 6.50		

Table 5 indicates the cycling performance obtained with the respective "AA" test cells on a 3.9Ω load resistance to a cut off of .80V.

TABLE 5: 3.9 Ω Cycling Performance Comparison of AA Test Cells
Having an Electrode Balance of 70% and 110% respectively.

5		TEST CELL 1 70% ELECTRODE BALANCE [mAh]	TEST CELL 2 110% ELECTRODE BALANCE [mAh]
	CYCLE 1	1169	1536
10	CYCLE 5	943	980
	CYCLE 10	767	790
	CYCLE 15	680	650
	CYCLE 20	436	511

15

On their 15th discharge, the cells show a discharge capacity greater than 20% of their initial discharge capacity -- well above the 11% landmark set by AMANO *et al.*

20

As noted, the present invention is applicable not only to conventional bobbin type cells, but it may also be applied to button or coin cells, and to flat plate cells.

**WHAT IS CLAIMED IS:**

THIS SHEET HAS BEEN
REPLACED

1. A rechargeable electrochemical cell (10) comprising a zinc negative electrode (16), a manganese dioxide positive electrode (14), a separator (18) between said zinc negative electrode and said manganese dioxide positive electrode, terminal means (24,26) contacting said negative electrode and said manganese dioxide electrode to provide respective negative and positive terminals for said cell, and an aqueous electrolyte; wherein the principal active component of said manganese dioxide electrode is manganese dioxide having a first discharge capacity of up to 308 mAh per gram thereof, which discharge capacity is the theoretical one electron discharge capacity of said principal active manganese dioxide component; wherein the separator is a semipermeable membrane impermeable to zinc dendrites; and wherein the principal component of said negative electrode is metallic zinc having at least one of the group consisting of mercury, indium, lead, bismuth, and gallium alloyed with said metallic zinc or deposited at the surface thereof; said rechargeable cell being characterized in that:

the theoretical discharge capacity of said metallic zinc contained in the negative electrode is controlled so as to be in the range of 65% to 110% of said theoretical one electron discharge capacity of manganese dioxide contained in said positive electrode, whereby said rechargeable cell retains its ability to deliver at least 50% of the electrical discharge capacity that it had just prior to an overdischarge to substantially zero Volts or below zero Volts, after said overdischarge;

said rechargeable cell has a discharge capacity on its 15th discharge which is greater than 20% of the discharge capacity delivered in the first discharge, when the cell is discharged at a six hour discharge rate, and when said cell has been recharged immediately after discharge in each of its first to 14th discharge/charge cycles; and

This Sheet Has Been Replaced





THIS SHEET HAS BEEN
REPLACED

the solute of said aqueous electrolyte is selected from the group consisting of potassium hydroxide, and a mixture of zinc chloride with ammonium chloride.

- 5 2. The rechargeable electrochemical cell of claim 1, wherein said aqueous electrolyte is 4N to 12N potassium hydroxide.
3. The rechargeable electrochemical cell of claim 1, wherein said positive electrode includes from about 3% to about 25% by weight thereof of a
10 barium compound.
4. The rechargeable electrochemical cell of claim 2, wherein said manganese dioxide electrode includes at least one additive selected from the group consisting of 5% to 15% by weight of graphite, 0.1% to 15% by weight of carbon
15 black, an inorganic binder, and an organic binder.
5. The rechargeable electrochemical cell of claim 2 when of cylindrical shape, wherein said manganese dioxide positive electrode is obtained by pressing discrete rings, inserting the rings into close contact with the inner
20 surface of a cylindrical metal can and then optionally recompacting the pellets with the metal can, or wherein a granulated electrode material is molded directly into the can to obtain a similarly shaped electrode.
6. The rechargeable electrochemical cell of claim 4, wherein said
25 manganese dioxide electrode includes from 0.1% to 10% of said organic material selected from the group consisting of PTFE, polypropylene, and polyethylene.
7. The rechargeable electrochemical cell of claim 2, wherein said manganese dioxide electrode further comprises from 0.1% to 5% of a hydrogen
30 recombination catalyst selected from the group consisting of silver, oxides of silver, and compounds of silver.

This Sheet Has Been Replaced





8. The rechargeable electrochemical cell of claim 2, wherein said electrolyte has from 1% to 20% of zinc oxide therein.
9. The rechargeable electrochemical cell of claim 2, wherein said metal container is a nickel plated steel can.
10. The rechargeable electrochemical cell of claim 2, wherein said container is coated on its interior surface with a conductive carbon coating.
11. The rechargeable electrochemical cell of claim 2, wherein said negative electrode comprises a gel which includes metallic zinc powder and optionally zinc oxide powder, a gelling agent, and said aqueous electrolyte, so as to form a gelled powdered zinc negative electrode.
12. The rechargeable electrochemical cell of claim 2, wherein said mercury, indium, lead, bismuth, and gallium is present in the range of 0.01% to 0.5% based on the zinc weight; and wherein said cell optionally contains an organic additive in the range of 0.01% to 0.5% based on the zinc weight, so as to retard zinc dendrite growth.
13. The rechargeable electrochemical cell of claim 11, wherein said gelling agent is selected from the group consisting of carboxymethyl cellulose, modified starches, polymethacrylates, polyacrylates, and mixtures or derivatives thereof.
14. The rechargeable electrochemical cell of claim 1, wherein said negative electrode further contains 1 to 15% of an additive chosen from the group consisting of hydroxides or oxides of magnesium, barium, and calcium, or mixtures thereof.



15. The rechargeable electrochemical cell of claim 1, wherein said separator comprises at least one barrier layer which is impermeable to zinc dendrites; wherein said barrier layer is an ion permeable membrane selected from the group consisting of cellulose, polyvinylalcohol, polypropylene, polyethylene, and combinations thereof.
- 5
16. The rechargeable electrochemical cell of claim 15, wherein said separator is a laminated separator having at least one electrolyte absorbent layer laminated to said barrier layer.
- 10
17. The rechargeable cell of claim 1, wherein said positive electrode further contains oxygen evolution catalysts including oxides, spinels or perovskites of nickel, cobalt, aluminium, zinc, iron, manganese, chromium, vanadium, titanium and silver.

1 / 1




FIG. 1

HIGH CAPACITY RECHARGEABLE CELL HAVING MANGANESE DIOXIDE ELECTRODE


FIELD OF THE INVENTION:

This invention relates to rechargeable cells having a manganese dioxide positive electrode, a potassium hydroxide or zinc chloride/ammonium chloride electrolyte and metallic zinc as the negative electrode material. The theoretical discharge capacity of the zinc contained in the negative electrode is in the range of from 65% to 110% of the theoretical one electron discharge capacity of the MnO_2 in the positive electrode. The usual embodiment may be the typical "bobbin" type cylindrical cell, however spirally wound cells, button or coin cells, and flat plate cells may be provided in keeping with the present invention.

BACKGROUND OF THE INVENTION:

For purposes of the present discussion, the capacity on the first discharge of the MnO_2 contained in the positive electrode between the MnO_2 status and the MnOOH status is termed or designated as the theoretical one electron discharge capacity of the manganese dioxide electrode, which is 308 m Ah/g of manganese dioxide. If the discharge process of the MnO_2 positive electrode continues beyond the MnOOH level, an irreversible phase change has been reported to occur, so that the manganese dioxide electrode is no longer fully rechargeable.

Specifically, the following equation is descriptive of the discharge reaction which takes place as the MnO_2 discharges towards its MnOOH status in the presence of an aqueous electrolyte.



Discharge according to this reaction occurs with essentially no phase change. If the discharge process of the manganese dioxide positive electrode continues beyond the MnOOH level, an irreversible phase change has been reported to occur, so that the manganese dioxide electrode is no longer fully rechargeable. Such phase change must be avoided. Responsible for the phase change is the following reaction:

capacity of the manganese dioxide electrode between the MnO_2 status and the MnOOH status is termed the theoretical one electron discharge capacity of that electrode.

5 The present invention also contemplates an aqueous electrolyte containing potassium hydroxide or a mixture of zinc chloride and ammonium chloride.

To reduce the mobility of zincate in the alkaline electrolyte by precipitation, the negative electrode may contain between 1% and 15% of an additive chosen from the group consisting of magnesium, barium and calcium, their oxides and hydroxides.

10 In keeping with the provisions of the present invention, the theoretical discharge capacity of the zinc negative electrode is in the range of from 65% and up to 110% of the theoretical one electron discharge capacity of the manganese dioxide electrode.

15 In a typical embodiment of cells according to the present invention, where the cells are intended for commercial exploitation, the electrolyte is a 4N to 12N aqueous solution of potassium hydroxide.

Cells according to the present invention may have a number of additives for purposes of enhancing the conductivity and the structural integrity of the MnO_2 positive electrode, or for inhibiting oxygen evolution or hydrogen evolution. For example, the MnO_2 electrode may include at least one additive which is chosen from the group consisting of 5% to 15% by weight of graphite, 0.1% to 15% by weight of carbon black, an inorganic binder, and/or an organic binder. The binder materials may be present in the range of from 0.1% to 15% by weight of the MnO_2 electrode. The carbon black may be present as a porous additive in the MnO_2 electrode in the range of from 0.1% to 15% by weight thereof.

30 Generally, the positive electrode of cells in keeping with present invention will include a barium-based additive in an amount of from about 3.0% to about 25% by weight of the positive electrode. The addition of a barium compound has been found to have a beneficial effect on the cycle life of the cell. Typically, such barium compounds may be such as BaSO_4 , BaO , and Ba(OH)_2 .

BRIEF DESCRIPTION OF THE DRAWINGS:

The present invention is described hereafter, in association with the accompanying drawings, in which:

Figure 1 is a typical cylindrical cell in which the present invention may be embodied.

DESCRIPTION OF THE PREFERRED EMBODIMENTS:

Referring to Figure 1, a typical cylindrical cell is shown at 10. The cell comprises a container 12, within which is a manganese dioxide positive electrode 14 and a zinc negative electrode 16. The container 12 is a nickel plated deep drawn steel can, although other suitable metal cans may be used. So as to improve the contact and conductivity between the positive electrode 14 and the can 12, and thereby so as to reduce the internal resistance of the cell, the internal surface of the container 12 may be coated with a conductive carbon coating such as LONZA™.

The manganese dioxide positive electrode 14 may be placed into the container 12 by such ordinary cell manufacturing techniques as by being molded into discrete pellets, and then placed in the container 12, or by being extruded into the container. It is generally comprised of manganese dioxide, to which a variety of optional additives may be mixed, as discussed hereafter. Typically the MnO_2 is electrolytic manganese dioxide to which optionally at least one hydrogen recombination catalyst has been added. Chemically synthesized MnO_2 may also be used.

A suitable manganese oxide positive electrode for use in a rechargeable cell is described in U.S. Patent No. 5,300,371 issued April 5, 1994. Suitable active materials utilizing manganese oxides comprise e.g. electrolytically or chemically synthesized manganese dioxide containing typically over 90% of four valent manganese and minor amounts of lower valance oxides. Alternatively manganese oxides can comprise a mixture of manganese dioxide and $MnOOH$ or comprise bismuth modified manganese oxides. In the case manganese oxides are used as active material in the positive electrode typically 1 to 15% of graphite or

18(replacement)

WHAT IS CLAIMED IS:

1. A rechargeable electrochemical cell (10) comprising a metallic zinc negative electrode (16), a manganese dioxide positive electrode (14), a separator (18) between said zinc negative electrode and said manganese dioxide positive electrode, terminal means (24,26) contacting said negative electrode and said manganese dioxide electrode to provide respective negative and positive terminals for said cell, and an aqueous electrolyte; wherein the principal active component of said manganese dioxide electrode is manganese dioxide having a first discharge capacity of up to 308 mAh per gram thereof, which discharge capacity is the theoretical one electron discharge capacity of said principal active manganese dioxide component; and wherein the separator is a semipermeable membrane impermeable to zinc dendrites; said rechargeable cell being characterized in that:
 - 15 the theoretical discharge capacity of said metallic zinc contained in the negative electrode is controlled so as to be in the range of 65% to 110% of said theoretical one electron discharge capacity of manganese dioxide contained in said positive electrode;
wherein said rechargeable cell retains its ability to deliver at least
20 50% of the electrical discharge capacity that it had just prior to an overdischarge to substantially zero Volts or below zero Volts, after said overdischarge;
said rechargeable cell has a discharge capacity on its 15th discharge which is greater than 20% of the discharge capacity delivered in the first discharge, when the cell is discharged at a six hour discharge rate, and when said
25 cell has been recharged immediately after discharge in each of its first to 14th discharge/charge cycles; and

AMENDED SHEET

19(replacement)

the solute of said aqueous electrolyte is selected from the group consisting of potassium hydroxide, and a mixture of zinc chloride with ammonium chloride.

5 2. The rechargeable electrochemical cell of claim 1, wherein said aqueous electrolyte is 4N to 12N potassium hydroxide.

3. The rechargeable electrochemical cell of claim 1, wherein said positive electrode includes from about 3% to about 25% by weight thereof of a
10 barium compound.

4. The rechargeable electrochemical cell of claim 2, wherein said manganese dioxide electrode includes at least one additive selected from the group consisting of 5% to 15% by weight of graphite, 0.1% to 15% by weight of carbon
15 black, an inorganic binder, and an organic binder.

5. The rechargeable electrochemical cell of claim 2 when of cylindrical shape, wherein said manganese dioxide positive electrode is obtained by pressing discrete rings, inserting the rings into close contact with the inner
20 surface of a cylindrical metal can and then optionally recompacting the pellets with the metal can, or wherein a granulated electrode material is molded directly into the can to obtain a similarly shaped electrode.

6. The rechargeable electrochemical cell of claim 4, wherein said
25 manganese dioxide electrode includes from 0.1% to 10% of said organic material selected from the group consisting of PTFE, polypropylene, and polyethylene.

7. The rechargeable electrochemical cell of claim 2, wherein said manganese dioxide electrode further comprises from 0.1% to 5% of a hydrogen
30 recombination catalyst selected from the group consisting of silver, oxides of silver, and compounds of silver other than oxides.

OBJECTIVE OF THE INVENTION:

The purpose of this invention is to provide a rechargeable alkaline manganese dioxide-zinc cell which has the following features:

a high discharge capacity on its first discharge;


a long cycle life;

the ability to recuperate from overdischarge without an excessive performance loss on further cycling; and

the ability to be used as power source in appliances without the requirement to employ devices for cutting off discharge of the cell or batteries at a predetermined limit.

According to the invention in a first aspect, there is provided a rechargeable electrochemical cell comprising a zinc negative electrode, a manganese dioxide positive electrode, a separator between said zinc negative electrode and said manganese dioxide positive electrode, terminal means contacting said negative electrode and said manganese dioxide electrode to provide respective negative and positive terminals for said cell, and an aqueous electrolyte; wherein the principal active component of said manganese dioxide electrode is manganese dioxide having a first discharge capacity of up to 308 mAh per gram thereof, which discharge capacity is the theoretical one electron discharge capacity of said principal active manganese dioxide component; wherein the separator is a semipermeable membrane impermeable to zinc dendrites; and wherein the principal component of said negative electrode is metallic zinc having at least one of the group consisting of mercury, indium, lead, bismuth, and gallium alloyed with said metallic zinc or deposited at the surface thereof; said rechargeable cell being characterized in that:

the theoretical discharge capacity of said metallic zinc contained in the negative electrode is controlled so as to be in the range 65% to 110% of said theoretical one electron discharge capacity of manganese dioxide contained in said positive electrode, whereby said rechargeable cell retains its ability to deliver at least 50% of the electrical discharge capacity that it had just prior to an overdischarge to substantially zero Volts or below zero Volts, after said overdischarge;



said rechargeable cell has a discharge capacity on its 15th discharge which is greater than 20% of the discharge capacity delivered in the first discharge, when the cell is discharged at a six hour discharge rate, and when said cell has been recharged immediately after discharge in each of its first to 14th discharge/charge cycles; and

the solute of said aqueous electrolyte is selected from the group consisting of potassium hydroxide, and a mixture of zinc chloride with ammonium chloride.

According to the the invention in a second aspect, there is provided a rechargeable electrochemical cell comprising a metallic zinc negative electrode, a manganese dioxide positive electrode, a separator between said zinc negative electrode and said MnO_2 positive electrode, terminal means contacting said negative electrode and said MnO_2 electrode to provide respective negative and positive terminals for said cell, and an aqueous electrolyte;

wherein the principal active component of said MnO_2 electrode is manganese dioxide having a first discharge capacity of up to 308 mAh per gram thereof, which discharge capacity is the theoretical one electron discharge capacity of said active MnO_2 electrode;


wherein the separator is a semipermeable membrane impermeable to zinc dendrites;

wherein the solute of said aqueous electrolyte is selected from the group consisting of potassium hydroxide, and a mixture of zinc chloride with ammonium chloride;

wherein the theoretical discharge capacity of said metallic zinc contained in the negative electrode is in the range of 65% to 120% of the theoretical one electron discharge capacity of MnO_2 contained in said positive electrode;


wherein said rechargeable cell has a discharge capacity on its 15th discharge which is greater than 20% of the discharge capacity delivered in the first discharge when the cell is discharged at a six hour discharge rate, and when said cell has been recharged immediately after discharge in each of its first to 14th discharge/charge cycle; and


wherein said rechargeable cell retains at least 30% of its electrical cycling capability after an overdischarge to substantially zero Volts.



The present invention accomplishes the objectives by determining the optimum electrode balance range where the electrode balance is defined as the ratio of the theoretical discharge capacity of the Zn active material of the negative electrode to the theoretical one electron discharge capacity of the MnO_2 active material contained in the positive electrode. The influence of various electrode balances on the initial discharge capacity and the cycle life as well as the ability to recuperate following an overdischarge were determined. The reason for this determination was the fact that users of batteries sometimes forget to switch off a battery powered device so that current will flow until the battery voltage reaches zero Volts. A battery generally consists of a series of connected cells; e.g. four cells in series for a 6 volt battery. On overdischarge of a 6 Volt battery, current is driven through a weak cell (or cells) with the result of oxygen evolution on the totally discharged zinc electrode and/or hydrogen evolution on the overdischarged manganese dioxide electrode. The consequence of such an overdischarge is typically bulging and/or leakage and/or the loss of cycle life.

What the present invention provides is rechargeable manganese dioxide/zinc cells with an aqueous electrolyte which have high capacity relative to prior art cells. A separator between the zinc electrode and the manganese dioxide electrode, and appropriate terminal means contacting the zinc electrode and manganese dioxide electrode are provided. As noted above, the discharge





18. A rechargeable electrochemical cell comprising a metallic zinc negative electrode, a manganese dioxide positive electrode, a separator between said zinc negative electrode and said MnO_2 positive electrode, terminal means contacting said negative electrode and said MnO_2 electrode to provide respective negative and positive terminals for said cell, and an aqueous electrolyte;

wherein the principal active component of said MnO_2 electrode is manganese dioxide having a first discharge capacity of up to 308 mAh per gram thereof, which discharge capacity is the theoretical one electron discharge capacity of said active MnO_2 electrode;

wherein the separator is a semipermeable membrane impermeable to zinc dendrites;

wherein the solute of said aqueous electrolyte is selected from the group consisting of potassium hydroxide, and a mixture of zinc chloride with ammonium chloride;

wherein the theoretical discharge capacity of said metallic zinc contained in the negative electrode is in the range of 65% to 120% of the theoretical one electron discharge capacity of MnO_2 contained in said positive electrode;

wherein said rechargeable cell has a discharge capacity on its 15th discharge which is greater than 20% of the discharge capacity delivered in the first discharge when the cell is discharged at a six hour discharge rate, and when said cell has been recharged immediately after discharge in each of its first to 14th discharge/charge cycles; and

wherein said rechargeable cell retains at least 30% of its electrical cycling capability after an overdischarge to substantially zero Volts.

19. The rechargeable electrochemical cell of claim 18, wherein said theoretical discharge capacity of zinc in said negative electrode is in the range of from about 70% to about 110% of the theoretical one electron discharge capacity of manganese dioxide in said positive electrode.

20. The rechargeable electrochemical cell of claim 18, wherein said aqueous electrolyte is 4N to 12N potassium hydroxide.

21. The rechargeable electrochemical cell of claim 18, wherein said positive electrode includes from about 3% to about 25% by weight thereof of a barium compound.

09 SEP 1997

22. The rechargeable electrochemical cell of claim 20, wherein said MnO_2 electrode includes at least one additive selected from the group consisting of 5% to 15% by weight of graphite, 0.1% to 15% by weight of carbon black, an inorganic binder, and an organic binder.
23. The rechargeable electrochemical cell of claim 20 when of cylindrical shape, wherein said manganese dioxide positive electrode is obtained by pressing discrete rings, inserting the rings into close contact with the inner surface of a cylindrical metal can and then optionally recompacting the pellets with the metal can, or wherein a granulated electrode material is molded directly into the can to obtain a similarly shaped electrode.
24. The rechargeable electrochemical cell of claim 22, wherein said MnO_2 electrode includes from 0.1% to 10% of said organic material selected from the group consisting of PTFB, polypropylene, and polyethylene.
25. The rechargeable electrochemical cell of claim 20, wherein said MnO_2 electrode further comprises from 0.1% to 5% of a hydrogen recombination catalyst selected from the group consisting of silver, oxides of silver, and compounds of silver.
26. The rechargeable electrochemical cell of claim 20, wherein said electrolyte has from 1% to 20% of zinc oxide dissolved therein.
27. The rechargeable electrochemical cell of claim 20, wherein said metal container is a nickel plated steel can.
28. The rechargeable electrochemical cell of claim 27, wherein said container is coated on its interior surface with a conductive carbon coating.
29. The rechargeable electrochemical cell of claim 20, wherein said negative electrode comprises a gel which includes metallic zinc powder and optionally zinc oxide powder, a gelling agent, and said aqueous electrolyte, so as to form a gelled powdered zinc negative electrode.

30. The rechargeable electrochemical cell of claim 29, wherein said negative electrode further comprises at least one additional metallic corrosion inhibitor in the range of 0.01% to 0.5% based on the zinc weight, wherein said metallic element is at least one element selected from the group consisting of mercury, lead, gallium and indium; and optionally 0.01% to 0.5% based on the zinc weight of an organic additive so as to retard zinc dendrite growth.


31. The rechargeable electrochemical cell of claim 29, wherein said gelling agent is selected from the group consisting of carboxymethyl cellulose, modified starches, polymethacrylates, polyacrylates, and mixtures or derivatives thereof.

32. The rechargeable electrochemical cell of claim 18, wherein said negative electrode further contains 1% to 15% of an additive chosen from the group consisting of hydroxides or oxides of magnesium, barium, and calcium, or mixtures thereof.

33. The rechargeable electrochemical cell of claim 18, wherein said separator comprises at least one barrier layer which is impermeable to zinc dendrites; wherein said barrier layer is an ion permeable membrane selected from the group consisting of cellulose, polyvinylalcohol, polypropylene, polyethylene, and combinations thereof.

34. The rechargeable electrochemical cell of claim 33, wherein said separator is a laminated separator having at least one electrolyte absorbent layer laminated to said barrier layer.

35. The rechargeable electrochemical cell of claim 18, wherein said positive electrode further contains oxygen evolution catalysts including oxides, spinels or perovskites of nickel, cobalt, aluminum, zinc, iron, manganese, chromium, vanadium, titanium and silver.



PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : H01M 10/24, 10/36		A1	(11) International Publication Number: WO 95/24742
			(43) International Publication Date: 14 September 1995 (14.09.95)
(21) International Application Number: PCT/CA95/00128		(81) Designated States: AM, AU, BB, BG, BR, BY, CA, CZ, EE, FI, GE, HU, JP, KG, KP, KR, KZ, LK, LR, LT, LV, MD, MG, MN, MX, NO, NZ, PL, RO, RU, SC SI, SK, TJ, TT, UA, UG, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ, UG).	
(22) International Filing Date: 8 March 1995 (08.03.95)			
(30) Priority Data: 08/207,629 9 March 1994 (09.03.94) US			
(71) Applicant: BATTERY TECHNOLOGIES INC. [CA/CA]; 30 Pollard Street, Richmond Hill, Ontario L4B 1C3 (CA).		Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	
(72) Inventors: TOMANISCHGER, Klaus; 6197 Montevideo Road, Mississauga, Ontario L5N 2E8 (CA). BOOK, R., James; 1771 Sherwood Forrest Circle, Mississauga, Ontario L5K 2H7 (CA). DANIEL-IVAD, Josef; 54 Old Hill Street, Richmond Hill, Ontario L4C 9T9 (CA).			
(74) Agent: HEWSON, Donald, E.; Suite 13, 2145 Dunwin Drive, Mississauga, Ontario L5L 4L9 (CA).			


SN 9611256-0

RTMP'S COPY

(54) Title: **HIGH CAPACITY RECHARGEABLE CELL HAVING MANGANESE DIOXIDE ELECTRODE**

(57) Abstract

A rechargeable manganese dioxide/zinc cell (10) is provided, where the cell has high capacity, high volumetric and gravimetric energy densities, high cycle life, and is capable of continued charge-discharge cycles following an overdischarge. The cell comprises a zinc negative electrode (16), a manganese dioxide positive electrode (14), a separator (18), and terminal means (24, 26). The cell has an aqueous electrolyte, wherein the solute may be potassium hydroxide, or the solute may also be a mixture of zinc chloride and ammonium chloride. The electrode balance as determined by the ratio of the theoretical discharge capacity of the zinc and the theoretical one electron discharge capacity of the manganese dioxide ranges from greater than 65 % up to 110 %. On the 15th discharge, a cell of the present invention will deliver a discharge capacity of at least 20 % of the discharge capacity delivered on the first discharge. A cell according to the present invention is capable of continued charge-discharge cycles after overdischarge or voltage reversal.



96112560

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

9611256-0