

SPECIFICATION

TITLE OF THE INVENTION

A liquid crystalline compound containing fluorine atom substituted alkyl group(s) and a liquid crystal composition

5 BACKGROUND OF THE INVENTION

1. Field of the Invention

This invention relates to a liquid crystalline compound effective as a component of liquid crystal composition, particularly a liquid crystalline compound
10 preferred to be used as a component for TFT liquid crystal composition, a liquid crystal composition containing the same and a liquid crystal display element constituted by using the composition.

2. Description of the Related Art

15 Liquid crystal display elements are materials utilizing the optical anisotropy and the dielectric anisotropy of liquid crystal substances. They are classified into various kinds of modes such as TN mode (twisted nematic mode), DS mode (dynamic scattering mode), guest-host mode,
20 DAP mode (deformation of aligned phase mode), STN mode, etc., depending upon the display mode of the element, and the properties of liquid crystal substances suitable to the respective uses therein are varied. Recently higher display grade of liquid crystal display elements has been
25 particularly required, and in order to comply with the requirement, demand upon display element of active






matrix mode represented by thin film transistor (TFT) has been increased. Liquid crystal substances used for display elements not only requires to be stable to moisture, air, heat, light, etc., but also they should exhibit liquid crystal phase within a temperature range as broad as possible, around room temperature, and also have a low viscosity, a superior compatibility, a large dielectric anisotropy value ($\Delta\epsilon$) and an optimum optical anisotropy value (Δn). However, at present, there is no single compound which satisfies all of such conditions. Thus, it is the present status that liquid crystal compositions obtained by blending several kinds of liquid crystal compounds or non-liquid crystal compounds have been used.

A characteristic particularly required for TFT mode liquid crystal display element is to retain a high contrast during a frame period; hence liquid crystal substances used for this object are required to exhibit a large specific resistance value in addition to the above described conditions. Further, recently, a low voltage drive has been sought for TFT mode liquid crystal display element; hence in order to comply with this requirement, a liquid crystalline compound or liquid crystal composition having a large $\Delta\epsilon$ than those of liquid crystal materials so far used for TFT mode liquid crystal display elements has been required.

General liquid crystalline compounds very often contain cyano group, and when liquid crystalline compounds containing cyano group are used in TFT mode liquid crystal display element, decomposition thereof occurs under high voltage; hence it is impossible to retain high specific resistance value during display operation. Thus, in spite of the fact that liquid crystalline compounds containing cyano group have a high $\Delta\epsilon$, it is impossible to use the compounds for TFT mode liquid crystal display element.

Thus, in order to overcome the defect, development of a liquid crystal material which exhibits a high specific resistance value and nevertheless has a high $\Delta\epsilon$ has been vigorously carried out. As liquid crystalline compounds having a high specific resistance value, fluorine-containing compounds are suitable. As these compounds, generally, liquid crystalline compounds containing fluorine atom as substituent group, the following compounds have been known:


For example, Japanese patent publication No. Hei 02-40048 discloses the following compound expressed by the formula (1):



The compound (1) has a high specific resistance as compared with compounds having cyano group; hence it has been industrially used, but its $\Delta\epsilon$ is as small as about 4;




hence a sufficient low voltage drive cannot be realized.

Japanese patent application laid-open No. Hei 02-233626 discloses, as a compound having a $\Delta\epsilon$ larger than that of the above compound (1), the following trifluorophenyl compound expressed by the following formula (2):




However, this compound nothing but exhibits an insufficient $\Delta\epsilon$ value to an extent of about 8 and further has a structure wherein a more number of fluorine atoms than those of the above compound (1) are introduced thereinto. Thus, the compound has a very narrow liquid crystal phase temperature range, so that it is unsuitable as a component constituting a liquid crystal composition. Further, even from the standpoint of N-I point, it has been confirmed that the compound an example of the compound of the formula (2), 1-(4-propylcyclohexyl)-4-(3,4,5-trifluorophenyl)cyclohexane has an N-I point lower by about 60°C than that of, an example of monofluoro compounds, 1-(4-propylcyclohexyl)-4-(4-fluorophenyl)cyclohexane, and also the compound has an N-I point lower by about 25°C than that of an example of difluoro compounds, 1-(4-propylcyclohexyl)-4-(3,4,-difluorophenyl)cyclohexane.

Further, Japanese patent application laid-open No. Hei 04-506361 discloses compounds expressed by the following formulas (3), (4) and (5):



These compounds each have relatively large $\Delta\epsilon$ (for example, compounds (4) and (5) have $\Delta\epsilon$ of about 7), but they have a far inferior compatibility with existing liquid crystalline compounds at low temperature, hence they have been unsuitable as a constituting component of liquid crystal compositions. In order to improve the compatibility, a compound having fluorine atom introduced into R as an alkyl group has been disclosed in Japanese patent application Hyo No. Hei 04-506817. This compound is compounds of two or three rings having cyclohexyl group and phenyl group at the terminal end thereof such as a compound expressed by the following formula (6):



However, this compound contains only a single bond at the central part of the molecule, but does not contain

another bonding group such as 1,2-ethylene group.

Further, the substituents on the phenyl group as the above terminal group are limited to fluorine atom, and other substituents such as fluoroalkyl group or fluoroalkoxy group are neither taught nor suggested.


However, these compounds do not improve the compatibility at all, and in particular, the compound of the formula (6) does not exhibit even any liquid crystal phase. As described above, a compound having a large $\Delta\epsilon$ and a superior compatibility has not yet been known. Thus, when a liquid crystalline compound having a large $\Delta\epsilon$ is used as a component of a composition, it is impossible to increase the mixing ratio of the compound; hence it is the present status that the $\Delta\epsilon$ value of the composition is restricted. Accordingly, appearance of a liquid crystalline compound having a high specific resistance value and a large $\Delta\epsilon$ and at the same time, having a superior compatibility with existing liquid crystalline compounds, has been awaited.

SUMMARY OF THE INVENTION

The object of the present invention is to provide a liquid crystalline compound having overcome the drawbacks of the prior art and having a large $\Delta\epsilon$ value, an electric and chemical stability, and a superior compatibility with existing liquid crystalline compounds, and a liquid crystal composition containing the same and further a liquid crystal display element constituted by using the same.

The present invention has the following constitutions
(1) to (17):



(1) A liquid crystalline compound expressed by
the formula (I):




wherein n represents an integer of 1 to 10; k, l and m
each independently represent an integer of 0 to 2;
ring E represents 1,4-cyclohexylene group or 1,4-phenylene
10 group wherein one or more hydrogen atoms on the six-
membered ring may be replaced by fluorine atom(s); G and
L each independently represent a covalent bond or
1,4-cyclohexylene group or 1,4-phenylene group wherein
one or more hydrogen atoms may be replaced by fluorine
15 atom(s), and in the case of covalent bond, G is
preferential; ring Z represents 1,4-phenylene group
wherein one or more hydrogen atoms on the 1,4-phenylene
group may be replaced by fluorine atom(s); Q represents
a covalent bond or -O-; Y represents a fluoroalkyl group
20 of 1 to 3 carbon atoms or fluorine atom; and when ring E
represents 1,4-cyclohexylene group and at least one of G
and L represents a covalent bond, $k+l+m \neq 0$ and when
Q represents -O-, Y does not represent fluorine atom.

- (2) A liquid crystalline compound according to item (1), wherein k, l and m each independently represent 0 or 1, and ring E represents 1,4-phenylene group or fluorine-substituted 1,4-phenylene group.
- 5 (3) A liquid crystalline compound according to item (1), wherein k, l and m each independently represent 0 or 1 and ring E represents 1,4-cyclohexylene group.
- (4) A liquid crystalline compound according to item (3), wherein k, l and m each are zero; G represents a covalent
10 bond; and L represents 1,4-cyclohexylene group, 1,4-phenylene group or fluorine-substituted 1,4-phenylene group.
- (5) A liquid crystalline compound according to item (4), wherein L represents 1,4-cyclohexylene group.
- 15 (6) A liquid crystalline compound according to item (4), wherein L represents 1,4-phenylene group or fluorine-substituted 1,4-phenylene group.
- (7) A liquid crystalline compound according to item (3), wherein k and l each represent 0; m represents 1;
20 G represents a covalent bond; and L represents 1,4-cyclohexylene group, 1,4-phenylene group or fluorine-substituted 1,4-phenylene group.
- (8) A liquid crystalline compound according to item (7) wherein L represents 1,4-cyclohexylene group.
- 25 (9) A liquid crystalline compound according to item (7), wherein L represents 1,4-phenylene group or fluorine-substituted 1,4-phenylene group.


- (10) A liquid crystalline compound according to item (3), wherein k and m each represent 1; l represents 0; G represents a covalent bond; and L represents 1,4-cyclohexylene group, 1,4-phenylene group or fluorine-substituted 1,4-phenylene group.
- (11) A liquid crystalline compound according to item (3), wherein k represents 1; l and m each represent 0; and G and L each represent a covalent bond.
- (12) A liquid crystalline compound according to item (1), wherein G and L each independently represent 1,4-cyclohexylene group, 1,4-phenylene group or fluorine-substituted phenylene group.
- (13) A liquid crystal composition containing at least one of liquid crystalline compounds according to items (1) to (12).
- (14) A liquid crystal composition characterized by containing at least one member of the liquid crystalline compounds set forth in either one of items (1) to (12), as a first component, and at least one member of compounds selected from the group consisting of compounds expressed by the following formulas (II), (III) and (IV), as a second component:






wherein R_1 represents an alkyl group of 1 to 10 carbon atoms; V represents F , Cl , CF_3 , OCF_3 , OCF_2H or an alkyl group of 1 to 10 carbon atoms; L_1 , L_2 , L_3 and L_4 each
 5 independently represent H or F ; Z_1 and Z_2 each independently represent $-(CH_2)_2-$, $-CH=CH-$ or a covalent bond; ring A represents trans-1,4-cyclohexylene group or 1,4-phenylene group; a represents 1 or 2; and b represents 0 or 1).

- 10 (15) A liquid crystal composition characterized by containing at least one member of the liquid crystalline compounds set forth in either one of items (1) to (12), as a first component, and at least one member of compounds selected from the group consisting of compounds
 15 expressed by the following formulas (V), (VI), (VII), (VIII) and (IX), as a second component:




wherein R_2 represents F , an alkyl group of 1 to 10 carbon atoms or an alkenyl group of 2 to 10 carbon atoms, and
 20 in either of the groups, an optional methylene group $(-CH_2-)$ in the groups may be replaced by oxygen atom $(-O-)$,

but two or more methylene groups therein are not success-
sively replaced by oxygen atom; Z_3 represents $-(CH_2)_2-$,
-COO or a covalent bond; L_5 and L_6 each independently
represent H or F; D_1 represents trans-1,4-cyclohexylene
5 group, 1,4-phenylene group or 1,3-dioxane-2,5-diyl group;
ring U represents trans-1,4-cyclohexylene group or 1,4-
phenylene group; and c and d each independently represent
0 or 1,



10 wherein R_3 represents an alkyl group of 1 to 10 carbon
atoms; L_7 represents H or F; and e represents 0 or 1,




wherein R_4 represents an alkyl group of 1 to 10 carbon
atoms; I represents trans-1,4-cyclohexylene group or
15 1,4-phenylene group; L_8 and L_9 each independently
represent H or F; Z_4 represents -COO- or a covalent bond;
 Z_5 represents -COO- or $-C\equiv C-$; and f and g each independ-
ently 0 or 1,



20 wherein R_5 and R_6 each independently represent an alkyl
group, an alkoxy group or an alkoxymethyl group, each

of 1 to 10 carbon atoms; W represents trans-1,4-cyclohexylene group, 1,4-phenylene group or 1,3-pyrimidine-2,5-diyl group; K represents trans-1,4-cyclohexylene group or 1,4-phenylene group; and Z₆ represents -C≡C-, -COO-,
 5 -(CH₂)₂- or a covalent bond,



wherein R₇ represents an alkyl group or an alkoxy group each of 1 to 10 carbon atoms; R₈ represents an alkyl group of 1 to 10 carbon atoms, and an optional methylene group (-CH₂-) in R₈ may be replaced by oxygen atom (-O-), but
 10 two or more methylene groups are not successively replaced by oxygen atom (-O-); M represents trans-1,4-cyclohexylene group or 1,3-pyrimidine-2,5-diyl group; rings N and P each independently represent trans-1,4-
 15 cyclohexylene group or 1,4-phenylene group; Z₇ represents -COO-, -(CH₂)₂-, -CH=CH- or a covalent bond; Z₈ represents -C≡C-, -COO- or a covalent bond; h represents 0 or 1; and L₁₀ represents H or F.

(16) A liquid crystal composition characterized by
 20 containing at least one member of the liquid crystalline compounds set forth in either one of items (1) to (12), as a first component, and at least one member of compounds selected from the group consisting of compounds

expressed by the formulas (II), (III) and (IV), as a part of the second component, and at least one member of compounds selected from the group consisting of compounds expressed by the formulas (V), (VI), (VII), (VIII) and
5 (IX), as another part of the second component.










(17) A liquid crystal display element constituted by using either one of the liquid crystal compositions set forth in either one of the items (13) to (16).









Detailed Description of the Invention









10 The liquid crystalline compound expressed by the formula (I) of the present invention is characterized in that the compound has a structure of 2 to 4 rings, having a group selected from the group consisting of fluorine atom, a fluoroalkyl group and a fluoroalkoxy
15 group, each of 1 to 3 carbon atoms, on a phenyl group which is a terminal ring on one side of the molecule, and having fluorine atom-containing group on another terminal ring of the molecule, and in the case of 2 to 3 ring structures, at least one of 1,2-
20 ethylene or 1,4-butylene bonding group is introduced into the central bonding part of the molecule. By having such a structure, the compound (I) of the present invention either exhibits a large $\Delta\epsilon$ and a superior compatibility and further exhibits a low viscosity and a high stability,
25 i.e. a high specific resistance value, and the most of

the compound exhibits a broad mesomorphic range. Thus, when such compounds of the present invention are used as a component of liquid crystal composition, a novel liquid crystal composition having
5 preferable characteristics can be provided.

As described above, any of the liquid crystalline compounds expressed by the formula (I) by the present invention exhibit superior characteristics, and among the compounds, those expressed by the following
10 formulas (1-1) to (1-25) are preferable in that they have a large $\Delta\epsilon$ and a superior compatibility. In addition, in the respective formulas, Q and Y each are as defined above; T_1 to T_8 each independently represent H or F; S_1 represents $(CH_2CH_2)_k$; S_2 represents $(CH_2CH_2)_l$;
15 S_3 represents $(CH_2CH_2)_m$; and k, l and m are as defined above.







In these compounds, compounds expressed by the bicyclic formulas (1-1), (1-2) and (1-17) exhibit superior characteristics of a very good compatibility and also a low viscosity. Among these, particularly those included
5 in the formulas (1-1) and (1-2) wherein two rings are both phenyl group, have also a characteristic of a large Δn . Thus, these bicyclic compounds are effective when they are used as a component of composition needing a low viscosity.

10 Tricyclic compounds (1-3) to (1-16) and tetracyclic compounds (1-18) to (1-25) both have a high clearing point; hence they are effective for broadening a mesomorphic range. In addition to this, particularly among the tricyclic compounds,
15 compounds having an ethylene bond between the rings, have a superior compatibility; hence they are effective as a component of a liquid crystal composition used in use applications needing the above characteristic, for example, in the liquid crystal display element of TFT mode
20 used in the television loaded on automobile. Further, the tetracyclic compounds are effective for elevating the upper limit of the clearing point of the compositions containing them even by using a small quantity thereof. When they are used, those having linear rings having the res-
25 pective rings bonded by covalent bonds are suitable to compositions needing a low viscosity, and on the other

hand, those having ethylene bonds between the respective rings, which have a further superior compatibility, are suitable to compositions needing a further broad mesomorphic range.

- 5 Among the substituent Q-Y, those having a particularly superior characteristic are CF_3 , OCF_3 , $-\text{OCF}_2\text{H}$, $\text{OCF}_2\text{CFHCF}_3$, $-\text{CF}_2\text{CF}_2\text{H}$ or F. However, in the case where the substituent is F, this F has a property of increasing $\Delta\epsilon$; hence substituent F other than the above F may be 3-position
- 10 substituent or 3-position and 5-position substituent. In the case where the substituent Q-Y is a substituent other than F, i.e. a fluoroalkyl group or fluoroalkoxy group of each 1 to 3 carbon atoms, the resulting liquid crystalline compound exhibits a particularly large $\Delta\epsilon$.
- 15 In particular, a compound wherein Q-Y is $-\text{CF}_3$, exhibits a very large $\Delta\epsilon$, and a compound wherein Q-Y is $-\text{OCF}_3$ exhibits a large $\Delta\epsilon$ and also a low viscosity. Further, a compound wherein Q-Y is $-\text{OCF}_2\text{CFHCF}_3$ or $\text{OCF}_2\text{CF}_2\text{H}$ exhibits a large $\Delta\epsilon$ and also a particularly large Δn . Namely, by
- 20 variously altering Q-Y as described above, it is possible to obtain a compound having desired characteristics.

In the case where a further large $\Delta\epsilon$ value is required, fluorine atom(s) may be further introduced into rings E, G, L and Z.

- 25 Further, in the case where a larger Δn is required, a compound containing a further more phenyl groups may be chosen.


The compound expressed by the formula (I) can be effectively prepared according to a known process, for example according to the following processes:

(Introduction of Q-Y group)

5 In the following description, T_1 and T_2 in the formulas are as defined above; r_1 represents an integer of 0 to 2, r_0 , r_2 and r_3 each represent an integer of 0 or 1.


A case where Q-Y represents perfluoroalkoxy group:

10 The compound of this case can be prepared according to a known process, for example according to a process described in "Japanese patent application Kai No. Hei 4-501575, pages 7-9", wherein CCl_4 and HF are reacted with a phenol.




A case where Q-Y represents perfluoroalkyl group:

20 The compound of this case can be prepared according to a known process, for example according to a process described in "Fourth edition, Lecture of Experimental Chemistry, 19, page 403", wherein copper powder is reacted with a perfluorohalide as a perfluoroalkylating agent in an aprotic solvent, followed by reacting an iodobenzene derivative with the resulting solution of $\text{CF}_3 \cdot \text{Cu}$ complex.




Further, according to a process described in "Fourth edition, Lecture of Experimental Chemistry, 19, page 390", a preferable result is also obtained by treating a carboxylic acid with SF_4 . In addition, as the perfluoroalkylating agent, besides the above, $\text{CF}_3\text{CO}_2\text{Na}$, $\text{FO}_2\text{SCF}_2\text{CO}_2\text{Me}$, $n\text{-Bu}_4\text{N}^+\text{H}_2\text{F}_3^-$, CF_3SiMe_3 , CF_2Br_2 , etc. can be preferably used.




10 A case where Q-Y represents a fluoroalkoxy group containing hydrogen atom(s):

In this case, the objective compound can be preferably prepared according to a known process, for example by using an unsaturated fluoroalkene. For example, it is possible to produce a fluoroalkoxy site containing hydrogen atom(s), using hexafluoropropene or tetrafluoroethylene, as follows:




Further, it can also be prepared by carrying out etherification reaction using a fluoroalkylhalide e.g. a fluoroalkyliodide, under basic condition:



5 A case where Q-Y represents a fluoroalkyl group containing hydrogen atom(s):

In this case, the compound can be prepared for example by treating a benzaldehyde derivative with diethylaminosulfur trifluoride (DAST), as described
 10 in "J.O.C., 40, 578 (1975), or by treating it by ultrasonic wave in the presence of a fluoroalkyl iodide and zinc, followed by treating the resulting material with DAST, as described in "Organosynthetic Chemistry, Vol. 41, No. 5, page 53", or by reacting a fluoroalkyl
 15 iodide with a phenyllithium derivative according to a known process:



Synthesis of the compound of the present invention:


Using the compounds having Q-Y group introduced as described above or a commercially available fluorine-substituted-phenyl derivative, it is possible to prepare
5 the compound of the present invention, for example, representative compounds shown in the formulas (1-1) to (1-25):

Firstly, preparation processes of bicyclic or tricyclic compounds will be described.

10 Compound of the formula (1-1):

The hydroxyl group of a normal alkane derivative substituted by hydroxyl group and a halogen such as bromine at both the respective ends is protected, followed by reacting the resulting compound with Mg in an aprotic
15 solvent such as ether or tetrahydrofuran (hereinafter abbreviated to THF), at a temperature of -50°C to room temperature, to obtain a Grignard agent, reacting this agent with a bromobenzene derivative (6) in the presence of a catalyst such as Ni acetylacetonate and then
20 deprotecting to prepare an alcohol derivative (7), and reacting this derivative (7) with DAST in a solvent such as chloroform, dichloromethane, etc. at a temperature of -50°C to the boiling point of the solvent, to prepare a fluoroalkyl derivative (8). With this derivative, alkyl
25 lithium like butyl lithium etc. is reacted in THF, at a temperature of -50°C to room temperature, to prepare compound (9). However, in the case where the benzene derivative (6) is bromobenzene, lithio-derivative reaction of (8) to (9) does not advance preferably. Thus, it is preferred that


bromine is reacted with the compound (8) in the presence of a catalyst such as aluminum chloride, etc. to once prepare 4-(ω-fluoroalkyl)bromobenzene, followed by subjecting this compound to lithio-derivation to obtain compound (9). The thus obtained compound (9) is reacted with zinc chloride in THF at a temperature of -50°C to room temperature, to prepare compound (10). To a THF solution of this compound (10) is added tetrakis(triphenylphosphine) palladium as a catalyst, followed by dropwise adding a bromobenzene derivative (11), stirring the mixture at room temperature or refluxing it, and recrystallizing to obtain compound (1-1).



Compound of the formula (1-2):

Firstly, a Grignard reagent (hereinafter referred to (11) - Mg) obtained from the above bromobenzene derivative (11) as raw material is prepared in an aprotic solvent such as ether, THF, etc. at a temperature of -50°C


to room temperature, followed by dropwise adding ethylene oxide to the resulting product at the above temperature, to obtain a phenethylalcohol derivative (12), and reacting this derivative with a brominating reagent such as HBr, tribromophosphine, etc., to prepare a phenethyl bromide derivative (13). On the other hand, iodine is reacted with the above compound (9) in THF, to prepare a compound (14), followed by adding this compound to a Grignard reagent (13)-Mg prepared by using the above phenethyl bromide derivative (13) in an aproic solvent such as ether, THF, etc., and reacting the mixture in the presence of a catalyst such as Ni acetylacetonate, etc. at a temperature of -50°C to room temperature, to prepare compound (1-2).




Compound the formula (1-3) or (1-5):

Bromine is reacted with the above compound (9) in THF, to prepare compound (15). But, in the case where 4-(ω-fluoroalkyl)bromobenzene is prepared, the fluoroalkyl derivative (8) is brominated in the presence of a catalyst


such as aluminum chloride, etc. to obtain compound (15).
 Thereafter, a Grignard reagent of the thus obtained
 compound (15) is prepared, followed by reacting the
 reagent with cyclohexanedione monoethylene ketal in THF,
 5 at a temperature of 0°C to room temperature, to prepare
 an alcohol derivative (17), reacting this compound (17)
 with ion-exchange resin or an organic acid such as
 paratoluenesulfonic acid, to carry out dehydration
 reaction and thereby prepare a cyclohexene derivative (18).
 10 This derivative (18) is subjected to catalytic hydrogenation
 in the presence of a heterogeneous catalyst such as Pd/C,
 Raney Ni, etc. to prepare a compound (19). The protective
 group of the compound (19) is removed by reacting with
 an acid. The thus obtained compound (20) is reacted with
 15 a Grignard reagent (11)-Mg or (13)-Mg prepared in an aprotic
 solvent such as ether, THF, etc., followed by carrying
 out dehydration and catalytic hydrogenation in the same
 manner as the reaction from the above compound (17) to
 (19), and further carrying out purification procedure such
 20 as recrystallization, etc., to obtain compound (1-3) or
 (1-5).






Compounds of formula (1-4) or (1-9):

A phenethylbromide derivative (22) is prepared in the same manner as in the process of obtaining compound (1-2), except that compound (11) is replaced by compound (15). Next, compound (1-4) or (1-9) can be obtained in the same manner as in the process of obtaining compound (1-3) or (1-5), except that compound (15) is replaced by its derivative (22).



Compound of formula (1-6):


To a THF solution of the above compound (10) is added tetrakis(triphenylphosphine) palladium as a catalyst, followed by dropwise adding the above bromobenzene derivative (6), stirring the mixture at room temperature or refluxing, to obtain compound (26). Compound (1-6) can be obtained in the same manner as in the process of obtaining compound (1-1) except that compound (8) is replaced by compound (26).



Compound of formula (1-7):

A Grignard reagent obtained using the above bromobenzene derivative (6) as a raw material is prepared in an aprotic solvent such as ether, THF, etc. at a temperature of -50°C to room temperature, followed by dropwise adding thereto ethylene oxide at the same temperature, to obtain a phenethyl alcohol derivative (29), reacting this derivative (29) with a brominating reagent such as HBr,


tribromophosphine, etc. to obtain a phenetyl bromide derivative (30), preparing a Grignard reagent thereof in an aproic solvent such as ether, THF, etc. at a temperature of -50°C to room temperature, and reacting the agent with the above compound (15) in the presence of a catalyst such as Ni acetylacetonate, to obtain compound (31). Compound (1-7) can be obtained in the same manner as in the process of obtaining compound (1-1), except that compound (8) is replaced by compound (31).



Compounds of the formula (1-8) or (1-10):


Bromine is reacted with the above compound (27) or (32) in THF, or bromine is reacted with the above compound (26) or (31) in the presence of aluminum chloride, etc., to prepare compound (33) or (34), followed by reacting therewith a Grignard reagent of the above compound (13) prepared in an aproic solvent such as ether THF, etc. at a temperature of -50°C to room

temperature, in the presence of a catalyst such as Ni acetyl acetonate, etc., to obtain compound (1-8) or (1-10).



Compound of formula (1-11):


Compound (35) obtained from 4-(2-(4-oxocyclohexyl)-ethyl)cyclohexanone is subjected to Wittig reaction using a suitable phosphonium salt, to prepare compound (36), followed by hydrogenating it in the presence of a heterogeneous catalyst such as Raney Ni, Pd/C, etc., to obtain compound (37). This compound is treated in the same manner as in the process of obtaining compound (1-4), except that compound (24) is replaced by compound (37), to obtain compound (1-11).



Compound of formula (1-12):

Compound (39) is prepared in the same manner as in the process of obtaining compound (1-11), except that the above compound (35) is replaced by compound (16), followed by reacting the compound (35) with a Grignard reagent of the above compound (30) prepared in an aprotic solvent such as ether, THF, etc. at a temperature of -50°C to room temperature, at the same temperature, successively carrying out dehydration reaction and hydrogenation reaction, to prepare compound (40).


Compound (1-12) is obtained in the same manner as in the process of obtaining compound (1-1), except that compound (8) is replaced by compound (40).



Compound of formula (1-13):


Compound (43) is prepared in the same manner as in the process of obtaining compound (1-11), except that the above compound (35) is replaced by compound (42). Compound (1-13) is obtained in the same manner as in

the process of obtaining compound (1-5), except that the above compound (20) is replaced by compound (43).




5 Compound of formula (1-14):

The above cyclohexanone derivative (39) is reacted with a Grignard reagent of the above compound (6) prepared in an aprotic solvent such as ether, THF, etc. at a temperature of -50°C to room temperature, at the same temperature, followed by successively carrying out dehydration reaction and hydrogenation, to prepare compound (44), reacting this compound with an alkyl-lithium such as butyllithium, etc. in THF at a temperature of -50°C to room temperature, to prepare compound (45), reacting this compound with bromine in THF, to obtain compound (46). However, in the case where compound (44) is a 1-fluoroalkyl-4-phenylcyclohexane, it is preferred that bromine is reacted therewith in the presence of a catalyst such as aluminum chloride, to prepare compound (46). Compound (1-14) can be obtained in the same manner as in the process of obtaining compound (1-8), except that compound (33) is replaced by compound (46).




Compound of formula (1-15):

- 5 Compound (1-15) can be obtained in the same manner as in the process of obtaining compound (1-5), except that the above compound (20) is replaced by the above cyclohexanone derivative (38).




Compound of formula (1-16):

Bromine is reacted with the above compound (41) in THF, or compound (40) is brominated in the presence of a catalyst such as aluminum chloride, etc., to prepare compound (47). Compound (1-16) can be obtained in the same manner as in the process of obtaining compound (1-10), except that the above compound (33) is replaced by compound (47).



Compound of formula (1-17):

Compound (1-17) can be obtained in the same manner
 5 as in the process of obtaining compound (1-5), except
 that the above compound (20) is replaced by the above
 cyclohexanone derivative (39).



Next, preparation process of tetracyclic compound
 10 will be described.

In addition, in the below description, when a lithio-
 deriving reagent such as alkyl lithium, etc. is reacted in THF
 with the above compounds (44), (40), (26) or (31), or
 bromine is reacted therewith in the presence of a catalyst
 15 such as aluminum chloride, etc., followed by reacting
 the reaction product with a lithio-deriving reagent,
 the resulting compounds (45), (41), (27) or (32) are

collectively referred to as Ar-Li, and the above cyclohexane derivatives (43), (38), (20) or (25) are collectively referred to as R=O.









Compounds of formula (1-19) to (1-21) or (1-24):

- 5 Firstly, using these compounds Ar-Li or R=O as starting materials, tetracyclic precursor compounds (49), (50), (51) or (52) are prepared. Namely, zinc chloride is reacted with Ar-Li in THF at a temperature of -50°C to room temperature to prepare compound (48), followed
- 10 by adding tetrakis(triphenylphosphine) palladium as catalyst to a THF solution of the compound (48), dropwise adding the above bromobenzene derivative (6) and stirring the mixture at room temperature or refluxing, to prepare compound (49).
- 15 Further, a Grignard reagent of compound (6) prepared in an aprotic solvent such as ether, THF, etc. at a temperature of -50°C to room temperature is reacted with a cyclohexanone derivative R=O, followed by successively carrying out dehydration reaction and hydrogenation,
- 20 to prepare compound (50).
- Further, a Grignard reagent of compound (30) prepared in an aprotic solvent such as ether, THF, etc. at a temperature of -50°C to room temperature is reacted with Ar-Li in the presence of a catalyst such as nickel
- 25 acetylacetonate, etc., to prepare compound (51).

Further, a Grignard reagent of compound (30) prepared in an aproic solvent such as ether, THF, etc. at a temperature of -50°C to room temperature is reacted with a cyclohexanone derivative $\text{R}=\text{O}$, followed by successively carrying out dehydration reaction and hydrogenation, to prepare compound (52).

An alkyllithium such as butyllithium is reacted with the precursor compounds (49) to (52) obtained above, in THF, to prepare compound (53), or bromine is reacted in a halide solvent such as methylene chloride in the presence of aluminum chloride to prepare compound (55), followed by reacting an alkyllithium such as butyllithium with the compound (55) in THF, to prepare compound (56). Compounds of (1 - 19) to (1-21) or (1-24) (in the case of $m=0$) can be obtained in the same manner as in the process of obtaining compound (1-1), except that compound (9) is replaced by compound (53) or (56).

In addition, when bromine is reacted with the above compound (53) in THF, it is possible to prepare (54). When the above phenetyl bromide derivative (13) is reacted with the compound (54) or the above compound (55) in an aproic solvent such as ether, THF, etc. at a temperature of -50°C to room temperature and in the presence of a catalyst such as Ni acetylacetonate, etc., it is possible to prepare compounds (1-19) to (1-21) or (1-24) (in the case of $m=1$).



Compounds of formula (1-18), (1-12), (1-23), or (1-25):











Firstly, using the above Ar-Li or R=O as starting material, cyclohexane derivatives (58), (63), (68) or (73) as tetracyclic precursor compounds are prepared. Namely,
5 the above cyclohexanedione monoethylene ketal (16) is reacted with Ar-Li in an aproic solvent such as ether, THF, etc. at a temperature of -50°C to room temperature, followed by successively carrying out dehydration with acid and hydrogenation reaction in the presence of
10 a catalyst such as Raney Ni or Pd/C, to prepare compound (57). By removing the protective group of this compound (57), a cyclohexanone derivative (58) is obtained.

Further, a Grignard reagent of 4-methoxybromobenzene (59) is reacted with R=O, followed by successively carrying
15 out dehydration with acid, and catalytic hydrogenation treatment in the presence of a catalyst of Pd/C, to prepare compound (60). This compound (60) is refluxed in the presence of an acid catalyst in toluene or xylene to obtain a phenol derivative (61), followed by nucleus-
20 hydrogenating in the presence of Pd/C catalyst, to obtain a cyclohexanol derivative (62). In addition, in this reaction, even in the case where phenyl group is contained in R, benzene ring having hydroxyl group bonded is almost selectively hydrogenated. When the above
25 cyclohexanol derivative (62) is oxydized with an oxydizing agent, cyclohexane derivative (63) is prepared.


Further, when ethylene oxide is reacted with Ar-Li, compound (64) is obtained, and when this compound is brominated with HBr or tribromophosphine, compound (65) is obtained. Next, when compound (16) is reacted with
5 a Grignard reagent (66) of the compound (65), compound (67) is obtained. When the protective group of the compound is removed with an acid, a cyclohexanone derivative (68) is obtained.

Further, when a Grignard reagent of the above
10 4-methoxybromobenzene (59) is reacted with ethylene oxide, followed by brominating with HBr or tribromophosphine, compound (69) is obtained. A cyclohexanone derivative (73) is prepared in the same manner as in the reaction of preparing compound (63), except that
15 compound (59) is replaced by compound (69).

A Grignard reagent of the above compound (11) or (13) is reacted with the above obtained precursor compounds (58), (63), (68) or (73), followed by successively carrying out dehydration with an acid and catalytic
20 hydrogenation treatment in the presence of a catalyst such as Raney Ni, Pd/C, etc., to prepare compounds (1-18), (1-22), (1-23) or (1-25).









However, in the case where Q-Y represents CF₂H, CF₂CF₂H, CF₂CFHCF₃, OCF₂H, OCF₂CFHCF₃ or OCF₂CF₂CF₂H, in the liquid crystalline compound expressed by the formula (I) of the present invention, it is preferred to introduce ring Z-Q-Y site by the following route, differently from the above:




























The liquid crystal composition provided by the present invention may be only a first component containing at least one member of the liquid crystalline compound expressed by the formula (I), but a blend of the first component and besides, as a second component, at least one member of compounds selected from the group consisting of the already mentioned formulas (II), (III) and (VI) (hereinafter referred to as the second component A) and/or at least one member of compounds selected from the group consisting of the formulas (V), (VI), (VII), (VIII) and (IX) (hereinafter referred to as the second component B) is preferred, and further, a known compound may be also blended as a third component, in order to adjust the threshold voltage, liquid crystal phase temperature range, Δn , $\Delta \epsilon$, viscosity, etc.













Among the second component A, the following (2-1) to (2-15) as preferable examples of compounds included in the formula (II), the following (3-1) to (3-48) as preferable examples of compounds included in the formula (III) and the following (4-1) to (4-41) as preferable examples of compounds included in the formula (IV), may be respectively mentioned:



























































































The compounds expressed by these formulas (II) to (IV) exhibit a positive $\Delta\epsilon$ and are far superior in the heat stability and chemical stability.

As to the quantities of the compounds used, a range of 1 to 99% by weight based upon the total weight of the liquid crystal composition is suitable, and the range is preferably 10 to 97% by weight, more preferably 40 to 95% by weight.



Next, among the compounds of the above second component B, as preferable examples of compounds included in the formulas (V), (VI) and (VII), (5-1) to (5-27), (6-1) to (6-3) and (7-1) to (7-13) can be mentioned.























(R' represents an alkylene.)



























The compounds expressed by these formulas (V) to (VII) have a large positive $\Delta\epsilon$ value; thus, they are used as a composition component particularly in order to lower the threshold voltage. Further, they are also
 5 used for adjusting the viscosity, adjusting the Δn , broadening the liquid crystal phase temperature range and so on, and further for improving the steepness.

Further, among the second component B, as preferable examples of compounds included in the formulas (VIII) and (IX), (8-1) to (8-15) and (9-1) to (9-14) are
 10 mentioned.







Compounds expressed by these formulas (VIII) and (IX) have negative or weakly positive $\Delta\epsilon$, and among these compounds, the compounds expressed by the formula (VIII) are used as composition components, mainly for lowering the viscosity and adjusting the Δn , and the compounds expressed by the formula (IX) are used for broadening the mesomorphic range and/or for adjusting the Δn .

Compounds expressed by the formulas (V) to (IX) are indispensable particularly in the case where a liquid crystal composition for STN mode display or conventional TN mode display are prepared. The quantity of the compounds used is suitable to be in the range of 1 to 99% by weight based upon the total weight of the liquid crystal composition when a liquid crystal composition for usual STN mode display or TN mode display is prepared, but the quantity is preferably in the range of 10 to 97% by weight, more preferably 40 to 95% by weight.

As to the liquid crystal composition provided by the present invention, it is preferred that the composition contains at least one member of the liquid crystalline compound expressed by the formula (I) in a ratio of 1 to 99% by weight, in order to exhibit superior characteristics.

The liquid crystal composition is generally prepared according to a process which is known, for example, according to a process of dissolving mutually various components at a high temperature, or other processes.

5 Further, if necessary, by adding a suitable additive, improvement in accordance with aimed use applications is made to perform optimization. Such an additive has been well known and described in literatures in details. Usually, a chiral doping agent or the like is added,

10 which induces the spiral structure of liquid crystal to adjust necessary twist angle, thereby preventing reverse twist.

Further, by adding a dichroic dyestuff such as those of merocyanine group, styryl group, azo group,

15 azomethine group, azoxy group, quinophthalone group, anthraquinone group, tetrazine group, etc., the composition can be also used as that for GH mode. The liquid crystal composition of the present invention can be used not only as those of NCAP mode prepared by microcapsulating nematic liquid crystal, polymer-dispersion mode

20 liquid crystal display element (PDLCD) prepared by forming a three-dimensional, reticulated, polymer substance, for example, polymer network liquid crystal display element (PNLCD), but also as those of birefringence control (ECB)

25 mode or DS mode.

As examples of the liquid crystal composition containing the compound of the present invention, the following can be mentioned, wherein compound numbers are the same as those shown in the below mentioned examples. Further, the double bond of 1,4-cyclohexylene and that in alkyl chain are all directed to a trans-form.

Composition example 1

FC_2H_4 -  -  -CH ₂ CH ₂ -  -OCF ₃	(Compound No. 17)	10%
FC_3H_9 -  -  -CH ₂ CH ₂ -  -OCF ₃	(Compound No. 19)	9%
C_2H_5 -  -  - 		10%
C_3H_7 -  -  - 		10%
C_5H_{11} -  -  - 		10%
C_7H_{15} -  - 		7%
C_2H_5 -  -CH ₂ CH ₂ -  - 		4%
C_3H_7 -  -CH ₂ CH ₂ -  - 		2%
C_5H_{11} -  -CH ₂ CH ₂ -  - 		4%
C_2H_5 -  -  - 		6%
C_3H_7 -  -  - 		6%
C_5H_{11} -  -  - 		12%
C_3H_7 -  -  - 		5%
C_3H_7 -  -  - 		5%





Composition example 2

FC_2H_4 -  -  - CH_2CH_2 -  - OCF_3	(Compound No. 17)	7%
FC_3H_6 -  -  - CH_2CH_2 -  - OCF_3	(Compound No. 19)	7%
FC_3H_6 -  -  - CH_2CH_2 -  - CF_3	(Compound No. 18)	7%
C_7H_{15} -  - 		2%
C_2H_5 -  -  - 		6%
C_3H_7 -  -  - 		6%
C_5H_{11} -  -  - 		6%
C_2H_5 -  -  - 		2%
C_3H_7 -  -  - 		2%
C_5H_{11} -  -  - 		4%
C_3H_7 -  -  - 		7%
C_3H_7 -  - CH_2CH_2 -  - 		7%
C_5H_{11} -  - CH_2CH_2 -  - 		7%
C_3H_7 -  -  - CH_2CH_2 - 		7%
C_5H_{11} -  -  - CH_2CH_2 - 		7%
C_3H_7 -  -  - 		5%
C_3H_7 -  - CH_2CH_2 -  - 		5%
C_3H_7 -  -  -  - 		3%
C_3H_7 -  -  - COO - 		3%

Composition example 3

<chem>FC3H8-C1CCC(CC1)-CH2CH2-c2cc(F)c(F)c(F)c2-c3cc(F)c(F)c(F)c3</chem>	(Compound No. 80)	10%
<chem>FC3H8-C1CCC(CC1)-CH2CH2-c2cc(F)c(F)c(F)c2-c3cc(F)c(F)c(OC(F)(F)F)c3</chem>	(Compound No. 77)	10%
<chem>C7H15-C1CCC(CC1)-c2cc(F)c(F)cc2</chem>		6%
<chem>C2H5-C1CCC(CC1)-C2CCC(CC2)-c3cc(F)c(F)cc3</chem>		5%
<chem>C3H7-C1CCC(CC1)-C2CCC(CC2)-c3cc(F)c(F)cc3</chem>		5%
<chem>C5H11-C1CCC(CC1)-C2CCC(CC2)-c3cc(F)c(F)cc3</chem>		5%
<chem>C2H5-C1CCC(CC1)-CH2CH2-C2CCC(CC2)-c3cc(F)c(F)cc3</chem>		8%
<chem>C3H7-C1CCC(CC1)-CH2CH2-C2CCC(CC2)-c3cc(F)c(F)cc3</chem>		4%
<chem>C5H11-C1CCC(CC1)-CH2CH2-C2CCC(CC2)-c3cc(F)c(F)cc3</chem>		8%
<chem>C2H5-C1CCC(CC1)-c2ccc(cc2)-c3cc(F)c(F)cc3</chem>		5%
<chem>C3H7-C1CCC(CC1)-c2ccc(cc2)-c3cc(F)c(F)cc3</chem>		5%
<chem>C5H11-C1CCC(CC1)-c2ccc(cc2)-c3cc(F)c(F)cc3</chem>		10%
<chem>C3H7-C1CCC(CC1)-c2ccc(cc2)-c3ccc(F)cc3</chem>		4%
<chem>C3H7-C1CCC(CC1)-C2CCC(CC2)-c3ccc(F)cc3</chem>		4%
<chem>C3H7-C1CCC(CC1)-C2CCC(CC2)-C(=O)Oc1ccc(F)cc1</chem>		4%
<chem>C3H7-C1CCC(CC1)-C2CCC(CC2)-c3ccc(Cl)cc3</chem>		4%
<chem>C5H11-C1CCC(CC1)-C2CCC(CC2)-c3ccc(Cl)cc3</chem>		3%

Composition example 4

FC_5H_{10} -  -  -CH ₂ CH ₂ - 	(Compound No. 30)	7%
FC_5H_{10} -  -  -CH ₂ CH ₂ - 	(Compound No. 31)	7%
FC_3H_8 -  -CH ₂ CH ₂ -  - 	(Compound No. 35)	8%
C_3H_7 -  - 		5%
C_5H_{11} -  - 		5%
C_7H_{15} -  - 		5%
C_2H_5 -  -  - 		5%
C_3H_7 -  -  - 		5%
C_5H_{11} -  -  - 		5%
C_2H_5 -  - 		7%
C_3H_7 -  - 		7%
C_5H_{11} -  - 		14%
C_3H_7 -  - 		6%
C_5H_{11} -  - 		6%
C_3H_7 -  -CH ₂ CH ₂ -  - 		4%
C_5H_{11} -  -CH ₂ CH ₂ -  - 		4%

Composition example 5

	(Compound No. 125)	6%
	(Compound No. 11)	6%
	(Compound No. 240)	4%
		5%
		10%
		10%
		10%
		6%
		3%
		6%
		4%
		4%
		4%
		4%
		3%
		3%
		3%
		3%
		4%
		4%

Composition example 6

	(Compound No. 19)	6%
	(Compound No. 18)	5%
	(Compound No. 80)	5%
		8%
		8%
		5%
		8%
		8%
		10%
		8%
		8%
		11%
		6%
		4%












Composition example 7

FC_3H_8 -  -  -CH ₂ CH ₂ -  -CF ₃	(Compound No. 18)	10%
FC_2H_4 -  -  -CH ₂ CH ₂ -  -OCF ₃	(Compound No. 17)	10%
C_2H_5 -  -  -CN		5%
C_3H_7 -  -  -CN		15%
$\text{C}_3\text{H}_7\text{OCH}_2$ -  -COO-  -F CN		5%
C_2H_5 -  -  -  -CN		5%
C_3H_7 -  -  -  -CN		5%
C_4H_9 -  -  -  -CN		5%
C_3H_7 -  -  -  -F		5%
C_3H_7 -  -  -  -CH ₃		5%
C_3H_7 -  -  -  -OCH ₃		3%
C_2H_5 -  -C≡C-  -OCH ₃		3%
C_3H_7 -  -C≡C-  -OCH ₃		3%
C_4H_9 -  -C≡C-  -OCH ₃		3%
C_4H_9 -  -C≡C-  -OC ₂ H ₅		3%
C_5H_{11} -  -C≡C-  -OCH ₃		3%
C_3H_7 -  -  -C ₄ H ₉		9%
C_3H_7 -  -  -C ₅ H ₁₁		3%




Composition example 8

<chem>FC3H8-C1CCC(CC1)-CH2CH2-C2=CC(=C(C=C2)F)-C3=CC(=C(C=C3)F)C(F)(F)F</chem>	(Compound No. 80) 11%
<chem>FC3H8-C1CCC(CC1)-CH2CH2-C2=CC(=C(C=C2)F)-C3=CC(=C(C=C3)OC(F)(F)F)F</chem>	(Compound No. 77) 10%
<chem>C3H7-C1CCC(CC1)-C2=CC=CC=C2C#N</chem>	7%
<chem>CH2=CHCH2CH2-C1CCC(CC1)-C2=CC=CC=C2C#N</chem>	9%
<chem>CH3CH=CHCH2CH2-C1CCC(CC1)-C2=CC=CC=C2C#N</chem>	9%
<chem>C3H7-C1CCC(CC1)-C2=CC=CC=C2C#N</chem>	5%
<chem>C3H7-C1=CN=CN=C1-C2=CC=CC=C2-C3=CC=CC=C3F</chem>	7%
<chem>C2H5-C1=CN=CN=C1-C2=CC=CC=C2-C3=CC=CC=C3C3H7</chem>	5%
<chem>C3H7-C1=CN=CN=C1-C2=CC=CC=C2-C3=CC=CC=C3C3H7</chem>	5%
<chem>C2H5-C1=CC=CC=C1C#CC2=CC=CC=C2C</chem>	4%
<chem>CH3-C1=CC=CC=C1C#CC2=CC=CC=C2C6H13</chem>	8%
<chem>C4H9-C1=CC=CC=C1C#CC2=CC=CC=C2C4H9</chem>	4%
<chem>CH3OCH2-C1CCC(CC1)-C2=CC=CC=C2C3H7</chem>	5%
<chem>C3H7-C1CCC(CC1)-C2=CC=CC=C2C4H9</chem>	8%
<chem>C3H7-C1CCC(CC1)-C2=CC=CC=C2C</chem>	3%

Composition example 9

FC_5H_{10} —  —  — CH_2CH_2 — 	(Compound No. 30)	10%
FC_3H_6 —  — CH_2CH_2 —  — 	(Compound No. 35)	10%
C_2H_5 —  —  —CN		7%
CH_3OCH_2 —  —  —CN		8%
$\text{C}_2\text{H}_5\text{OCH}_2$ —  —  —CN		8%
C_2H_5 —  — COO —  —CN		4%
C_5H_{11} —  —  —F		5%
C_3H_7 —  —  —  —F		6%
C_2H_5 —  —  — C_2H_5		3%
C_3H_7 —  —  — C_2H_5		3%
C_4H_9 —  —  — C_2H_5		3%
C_2H_5 —  —  —  — C_3H_7		4%
C_3H_7 —  —  —  — C_3H_7		4%
C_4H_9 —  —  —  — C_3H_7		4%
C_3H_7 —  —  — OC_2H_5		4%
C_2H_5 —  —  —  — CH_3		5%
C_3H_7 —  —  —  — CH_3		5%
C_3H_7 —  —  —  — C_3H_7		7%

Composition example 10

FC_5H_{10} —  —  — OCF_3	(Compound No. 11)	6%
FC_3H_6 —  —  —  — OCF_3	(Compound No. 240)	4%
FC_5H_{10} —  —  — CH_2CH_2 —  — CF_3	(Compound No. 31)	10%
$\text{C}_2\text{H}_5\text{OCH}_2$ —  — COO —  — CN		3%
$\text{C}_3\text{H}_7\text{OCH}_2$ —  — COO —  — CN		10%
C_2H_5 —  —  — CN		8%
C_3H_7 —  —  — CN		9%
C_3H_7 —  —  —  — CN		4%
C_2H_5 —  —  —  — F		3%
C_3H_7 —  —  —  — F		3%
C_5H_{11} —  —  —  — F		3%
C_3H_7 —  — CH_2CH_2 —  — $\text{C}\equiv\text{C}$ —  — C_2H_5		3%
C_3H_7 —  — CH_2CH_2 —  — $\text{C}\equiv\text{C}$ —  — C_3H_7		3%
C_3H_7 —  — CH_2CH_2 —  — $\text{C}\equiv\text{C}$ —  — C_4H_9		3%
C_3H_7 —  —  — $\text{C}\equiv\text{C}$ —  — C_2H_5		4%
C_3H_7 —  —  — $\text{C}\equiv\text{C}$ —  — C_3H_7		4%
C_3H_7 —  —  — $\text{C}\equiv\text{C}$ —  — C_4H_9		4%
C_3H_7 —  —  —  — CH_3		8%
C_3H_7 —  —  —  — C_3H_7		4%
C_3H_7 —  —  —  — OCH_3		4%

Composition example 11

<chem>FC2H4-C1CCC(CC1)-C2CCC(CC2)-CH2CH2-C3=CC=C(C=C3)OC(F)(F)F</chem>	(Compound No. 17)	7%
<chem>FC3H6-C1CCC(CC1)-C2=CC(=C(C=C2)F)F-CH2CH2-C3=CC=C(C=C3)OC(F)(F)F</chem>	(Compound No. 122)	6%
<chem>FC5H10-C1CCC(CC1)-C2CCC(CC2)-C3=CC(=C(C=C3)F)F-C4=CC=C(C=C4)OC(F)(F)F</chem>	(Compound No. 247)	3%
<chem>C2H5-C1CCC(CC1)-C2=CC(=C(C=C2)F)C#N</chem>		13%
<chem>C3H7-C1CCC(CC1)-C2=CC(=C(C=C2)F)C#N</chem>		13%
<chem>C3H7OCH2-C1=CC=C(C=C1)C(=O)OC2=CC(=C(C=C2)F)C#N</chem>		8%
<chem>C3H7-C1CCC(CC1)-C2CCC(CC2)C(=O)OC3=CC=C(C=C3)F</chem>		4%
<chem>C5H11-C1CCC(CC1)-C2CCC(CC2)C(=O)OC3=CC=C(C=C3)F</chem>		4%
<chem>C3H7-C1CCC(CC1)-C2CCC(CC2)C(=O)OC3=CC(=C(C=C3)F)F</chem>		12%
<chem>C5H11-C1CCC(CC1)-C2CCC(CC2)C(=O)OC3=CC(=C(C=C3)F)F</chem>		8%
<chem>C3H7-C1CCC(CC1)-C2=CC=C(C=C2)C(=O)OC3=CC(=C(C=C3)F)F</chem>		4%
<chem>C5H11-C1CCC(CC1)-C2=CC=C(C=C2)C(=O)OC3=CC(=C(C=C3)F)F</chem>		4%
<chem>C3H7-C1CCC(CC1)-C2CCC(CC2)-C3=CC=C(C=C3)C</chem>		7%
<chem>C3H7-C1CCC(CC1)-C2CCC(CC2)-C3=CC=C(C=C3)OC</chem>		4%
<chem>C3H7-C1CCC(CC1)-C2CCC(CC2)-C3=CC=C(C=C3)CC</chem>		3%















Composition example 12

FC_3H_6 -  -  -CH ₂ CH ₂ -  -OCF ₃	(Compound No. 19)	6%
FC_3H_6 -  -  -CH ₂ CH ₂ -  -CF ₃	(Compound No. 18)	6%
FC_3H_6 -  -CH ₂ CH ₂ -  -  -OCF ₃	(Compound No. 77)	7%
C_3H_7 -  -  -COO-  -  -CN		3%
C_5H_{11} -  -  -COO-  -  -CN		3%
C_3H_7 -  -  -COO-  -  -CN		3%
C_3H_7 -  - 		7%
C_3H_7 -  -  -  -F		5%
C_4H_9 -  -  -  -F		5%
C_5H_{11} -  -  -  -F		5%
C_2H_5 -  -  -C ₂ H ₅		5%
C_3H_7 -  -  -C ₂ H ₅		5%
C_4H_9 -  -  -C ₂ H ₅		5%
C_3H_7 -  -COO-  -OC ₄ H ₉		5%
C_4H_9 -  -COO-  -OC ₄ H ₉		5%
C_5H_{11} -  -COO-  -OC ₄ H ₉		5%
C_2H_5 -  -CH ₂ CH ₂ -  -C≡C-  -C ₄ H ₉		4%
C_3H_7 -  -CH ₂ CH ₂ -  -C≡C-  -C ₄ H ₉		5%
C_3H_7 -  -  -  -CH ₃		6%
C_3H_7 -  -  -  -C ₃ H ₇		5%






Composition example 13

FC_5H_{10} —  — CH_2CH_2 —  —  — OCF_3	(Compound No. 48)	7%
FC_5H_{10} —  — CH_2CH_2 —  —  — CF_3	(Compound No. 90)	8%
C_3H_7 —  —  — OCH_3		4%
C_3H_7 —  —  — OC_3H_7		4%
C_5H_{11} —  —  — OCH_3		6%
C_5H_{11} —  —  — F		6%
C_2H_5 —  —  —  — OCF_3		4%
C_3H_7 —  —  —  — OCF_3		4%
C_4H_9 —  —  —  — OCF_3		6%
C_5H_{11} —  —  —  — OCF_3		6%
C_3H_7 —  —  — CH_2CH_2 —  — F		6%
C_5H_{11} —  —  — CH_2CH_2 —  — F		6%
C_3H_7 —  —  —  — OCHF_2		10%
C_3H_7 —  —  — COO —  — F		5%
C_5H_{11} —  —  —  — F		3%
C_5H_{11} —  —  —  — C_2H_5		3%
C_3H_7 —  —  —  — OCHF_2		6%
C_5H_{11} —  —  —  — OCHF_2		6%



Composition example 14

FC_5H_{10} -  -  -CH ₂ CH ₂ - 	(Compound No. 134)	8%
FC_3H_6 -  -  -CH ₂ CH ₂ - 	(Compound No. 19)	8%
C_5H_{11} -  - 		8%
C_6H_{13} -  - 		8%
C_7H_{15} -  - 		8%
C_2H_5 -  -  - 		7%
C_3H_7 -  -  - 		7%
C_4H_9 -  -  - 		7%
C_5H_{11} -  -  - 		7%
C_3H_7 -  -  -CH ₂ CH ₂ - 		5%
C_5H_{11} -  -  -CH ₂ CH ₂ - 		5%
C_3H_7 -  - 		8%
C_5H_{11} -  - 		8%
C_3H_7 -  -  - 		3%
C_5H_{11} -  -  - 		3%

Composition example 15

FC_5H_{10} -  -  -CH ₂ CH ₂ - 	(Compound No. 30)	9%
FC_5H_{10} -  -CH ₂ CH ₂ -  - 	(Compound No. 48)	7%
CH ₂ =CHCH ₂ -  - 		5%
C ₄ H ₉ -  -  -C ₂ H ₅		4%
C ₃ H ₇ -  - 		6%
C ₅ H ₁₁ -  - 		6%
C ₂ H ₅ -  - 		6%
C ₃ H ₇ -  -CH ₂ CH ₂ - 		6%
C ₅ H ₁₁ -  -CH ₂ CH ₂ - 		8%
C ₃ H ₇ -  -COO- 		6%
C ₅ H ₁₁ -  -COO- 		11%
C ₅ H ₁₁ -  -COO- 		11%
C ₅ H ₁₁ -  -  - 		3%
C ₄ H ₉ -  -  - 		3%
C ₄ H ₉ -  -  - 		3%
C ₅ H ₁₁ -  -  -CH ₂ CH ₂ - 		3%
C ₅ H ₁₁ -  -  -CH ₂ CH ₂ - 		3%

Composition example 16

FC_5H_{10} -  - CH_2CH_2 -  -  - CF_3	(Compound No. 90) 7%
FC_5H_{10} -  - CH_2CH_2 -  - CF_3	(Compound No. 134) 7%
C_4H_9 -  - COO - 	6%
C_5H_{11} -  - COO - 	6%
C_2H_5 -  - COO -  - CN	5%
C_3H_7 -  - COO -  - CN	5%
C_4H_9 -  - COO -  - CN	6%
C_5H_{11} -  - COO -  - CN	6%
$\text{CH}_3\text{OC}_3\text{H}_7$ -  -  - CN	10%
C_3H_7 -  -  - COO - 	6%
C_5H_{11} -  -  - COO - 	6%
C_2H_5 -  -  - COO -  - CN	4%
C_3H_7 -  -  - COO -  - CN	4%
C_4H_9 -  -  - COO -  - CN	6%
C_5H_{11} -  -  - COO -  - CN	6%
C_3H_7 -  -  - $\text{C}\equiv\text{C}$ -  - C_2H_5	10%

Composition example 17

<chem>FC3H8-C1CCC(CC1)CCc2cc(F)c(cc2F)-c3ccc(OC(F)F)cc3</chem>	(Compound No. 74)	10%
<chem>FC3H8-C1CCC(CC1)CCc2cc(F)c(cc2F)-c3cc(F)c(OC(F)F)cc3</chem>	(Compound No. 77)	10%
<chem>FC3H7-C1CCC(CC1)CCc2cc(F)c(cc2)OC(F)F</chem>	(Compound No. 13)	6%
<chem>C2H5-C1CCC(CC1)CC2c3cc(F)c(cc3F)</chem>		5%
<chem>C3H7-C1CCC(CC1)CC2c3cc(F)c(cc3F)</chem>		5%
<chem>C5H11-C1CCC(CC1)CC2c3cc(F)c(cc3F)</chem>		5%
<chem>C2H5-C1CCC(CC1)CCc2cc(F)c(cc2F)-C3CCC(CC3)c4cc(F)c(cc4F)</chem>		8%
<chem>C3H7-C1CCC(CC1)CCc2cc(F)c(cc2F)-C3CCC(CC3)c4cc(F)c(cc4F)</chem>		4%
<chem>C5H11-C1CCC(CC1)CCc2cc(F)c(cc2F)-C3CCC(CC3)c4cc(F)c(cc4F)</chem>		8%
<chem>C2H5-C1CCC(CC1)Cc2ccc(cc2)-c3cc(F)c(cc3F)</chem>		5%
<chem>C3H7-C1CCC(CC1)Cc2ccc(cc2)-c3cc(F)c(cc3F)</chem>		5%
<chem>C5H11-C1CCC(CC1)Cc2ccc(cc2)-c3cc(F)c(cc3F)</chem>		10%
<chem>C3H7-C1CCC(CC1)Cc2ccc(cc2)-c3ccc(F)cc3</chem>		4%
<chem>C3H7-C1CCC(CC1)CC2c3cc(F)c(cc3F)-C(=O)Oc4ccc(F)cc4</chem>		4%
<chem>C3H7-C1CCC(CC1)CC2c3cc(F)c(cc3F)-c4ccc(Cl)cc4</chem>		4%
<chem>C5H11-C1CCC(CC1)CC2c3cc(F)c(cc3F)-c4ccc(Cl)cc4</chem>		3%

Composition example 18

	(Compound No. 86) 10%
	(Compound No. 19) 9%
	10%
	10%
	10%
	7%
	4%
	2%
	4%
	6%
	6%
	12%
	5%
	5%

Composition example 19

<chem>FC3H6-C1CCC(CC1)-C2CCC(CC2)-c3cc(F)c(F)c(c3)OC(F)(F)F</chem>	(Compound No. 240) 4%
<chem>C7H15-C1CCC(CC1)-c2ccc(F)cc2</chem>	3%
<chem>C7H15-C1CCC(CC1)-c2cc(F)c(F)cc2</chem>	4%
<chem>C2H5-C1CCC(CC1)-C2CCC(CC2)-c3cc(F)c(F)c(c3)</chem>	13%
<chem>C3H7-C1CCC(CC1)-C2CCC(CC2)-c3cc(F)c(F)c(c3)</chem>	13%
<chem>C5H11-C1CCC(CC1)-C2CCC(CC2)-c3cc(F)c(F)c(c3)</chem>	13%
<chem>C2H5-C1CCC(CC1)-CH2CH2-C2CCC(CC2)-c3cc(F)c(F)c(c3)</chem>	4%
<chem>C3H7-C1CCC(CC1)-CH2CH2-C2CCC(CC2)-c3cc(F)c(F)c(c3)</chem>	2%
<chem>C5H11-C1CCC(CC1)-CH2CH2-C2CCC(CC2)-c3cc(F)c(F)c(c3)</chem>	4%
<chem>C2H5-C1CCC(CC1)-c2ccc(cc2)-c3cc(F)c(F)c(c3)</chem>	3%
<chem>C3H7-C1CCC(CC1)-c2ccc(cc2)-c3cc(F)c(F)c(c3)</chem>	3%
<chem>C5H11-C1CCC(CC1)-c2ccc(cc2)-c3cc(F)c(F)c(c3)</chem>	6%
<chem>C3H7-C1CCC(CC1)-C2CCC(CC2)-c3ccc(CCC)cc3</chem>	8%
<chem>C3H7-C1CCC(CC1)-C2CCC(CC2)-C(=O)Oc3ccc(cc3)-c4ccc(F)cc4</chem>	3%
<chem>C5H11-C1CCC(CC1)-C2CCC(CC2)-C(=O)Oc3ccc(F)cc3</chem>	3%
<chem>C3H7-C1CCC(CC1)-C2CCC(CC2)-CH2CH2-c3ccc(OC(F)(F)F)cc3</chem>	3%
<chem>C3H7-C1CCC(CC1)-C2CCC(CC2)-c3ccc(OC(F)(F)F)cc3</chem>	5%
<chem>C3H7-C1CCC(CC1)-C2CCC(CC2)-CH2CH2-c3cc(F)c(F)c(c3)</chem>	6%

This composition exhibited a clearing point of 113.8°C, a threshold value in a cell thickness of 8.7 μm of 2.59 V, a $\Delta\epsilon$ of 4.5, a Δn of 0.090 and a viscosity at 20°C of 23.1 mPa·S.

Composition example 20

<chem>FC3H6-C1CCC(CC1)-C2CCC(CC2)-c3cc(F)c(F)c(F)c3-OC(F)(F)F</chem>	(Compound No. 240)	8%
<chem>FC3H7-C1CCC(CC1)-C2CCC(CC2)-CH2CH2-c3ccc(C(F)(F)F)cc3</chem>	(Compound No. 18)	8%
<chem>C7H15-C1CCC(CC1)-c2cc(F)c(F)c(F)c2</chem>		4%
<chem>C3H7-C1CCC(CC1)-CH2CH2-C2CCC(CC2)-c3cc(F)c(F)c(F)c3</chem>		10%
<chem>C5H11-C1CCC(CC1)-CH2CH2-C2CCC(CC2)-c3cc(F)c(F)c(F)c3</chem>		9%
<chem>C3H7-C1CCC(CC1)-C2CCC(CC2)-c3cc(F)c(F)c(F)c3</chem>		6%
<chem>C4H9-C1CCC(CC1)-C2CCC(CC2)-c3cc(F)c(F)c(F)c3</chem>		6%
<chem>C3H7-C1CCC(CC1)-C2CCC(CC2)-CH2CH2-c3cc(F)c(F)c(F)c3</chem>		6%
<chem>C5H11-C1CCC(CC1)-C2CCC(CC2)-CH2CH2-c3cc(F)c(F)c(F)c3</chem>		6%
<chem>C3H7-C1CCC(CC1)-c2ccc(cc2)-c3cc(F)c(F)c(F)c3</chem>		10%
<chem>C5H11-C1CCC(CC1)-c2ccc(cc2)-c3cc(F)c(F)c(F)c3</chem>		10%
<chem>C3H7-C1CCC(CC1)-C2CCC(CC2)-COO-c3cc(F)c(F)c(F)c3</chem>		9%
<chem>C4H9-C1CCC(CC1)-C2CCC(CC2)-COO-c3cc(F)c(F)c(F)c3</chem>		2%
<chem>C5H11-C1CCC(CC1)-C2CCC(CC2)-COO-c3cc(F)c(F)c(F)c3</chem>		2%
<chem>C2H5-C1CCC(CC1)-C2CCC(CC2)-c3ccc(cc3)-c4cc(F)c(F)c(F)c4</chem>		2%
<chem>C3H7-C1CCC(CC1)-C2CCC(CC2)-c3ccc(cc3)-c4cc(F)c(F)c(F)c4</chem>		2%

This composition exhibited a clearing point of 92.1°C, a threshold voltage in a cell thickness of 8.7 μm of 1.78 V, a $\Delta\epsilon$ of 9.1, a Δn of 0.093 and a viscosity at 20°C of 31.2 mPa·S.

Composition example 21

FC_3H_7 -  -  -CH ₂ CH ₂ -  -CF ₃	(Compound No. 18)	4%
C ₃ H ₇ -  -  -Cl		7%
C ₇ H ₁₅ -  - 		10%
C ₂ H ₅ -  -  - 		7.5%
C ₃ H ₇ -  -  - 		7.5%
C ₅ H ₁₁ -  -  - 		15%
C ₂ H ₅ -  -  -  -Cl		5%
C ₄ H ₉ -  -  -  -Cl		10%
C ₅ H ₁₁ -  -  -  -Cl		5%
C ₃ H ₇ -  -  - 		10%
C ₅ H ₁₁ -  -  - 		9%
C ₃ H ₇ -  -  -C(FH)=C(H)-  -C ₂ H ₅		5%
C ₃ H ₇ -  -  -C≡C-  -C ₃ H ₇		5%

This composition exhibited a clearing point of 89.5°C, a threshold voltage in a cell thickness of 8.7 μm of 2.09 V, a Δε of 5.5, a Δn of 0.128 and a viscosity at 20°C of 22.7 mPa·S.

Composition example 22

FC_3H_6 -  -  -  -  - OCF_3	(Compound No. 240) 2%
FC_3H_7 -  -  - CH_2CH_2 - 	(Compound No. 18) 4%
$\text{CH}_2=\text{CHC}_2\text{H}_4$ -  - 	9%
CH_3 - $\text{C}(\text{H})_2$ - C_2H_4 -  - 	9%
C_3H_7 -  - 	14%
CH_3OCH_2 -  - 	8%
$\text{C}_2\text{H}_5\text{OCH}_2$ -  - 	4%
C_3H_7 -  -  - 	4%
C_3H_7 -  -  - C_4H_9	5%
C_3H_7 -  -  - C_2H_4 - $\text{C}(\text{H})=\text{C}(\text{H})\text{CH}_3$	5%
CH_3OCH_2 -  -  - C_5H_{11}	8%
C_2H_5 -  - $\text{C}\equiv\text{C}$ -  - OCH_3	11%
C_3H_7 -  -  - 	4%
C_3H_7 -  -  - 	9%
$\text{H}-\text{C}(\text{H})_2$ - $\text{C}(\text{H})$ -  -  - 	4%

This composition exhibited a clearing point of 76.1°C, a threshold voltage in a cell thickness of 8.7 mm of 1.89 V, a $\Delta\epsilon$ of 7.6, a Δn of 0.124 and a viscosity at 20°C of 18.4 mPa·S.

Composition example 23

<chem>FC3H6-C1CCC(CC1)-C2CCC(CC2)-c3cc(F)c(F)c(c3)-c4cc(F)c(OC(F)(F)F)cc4</chem>	(Compound No. 240) 10%
<chem>CH3-C(=C)-C2H4-c1ccc(cc1)C(=O)Oc2cc(F)c(C#N)c(F)c2</chem>	11%
<chem>C2H5OCH2-c1ccc(cc1)C(=O)Oc2cc(F)c(C#N)c(F)c2</chem>	5%
<chem>C3H7OCH2-c1ccc(cc1)C(=O)Oc2cc(F)c(C#N)c(F)c2</chem>	9%
<chem>C3H7-C1CCC(CC1)-c2cc(F)c(C#N)cc2</chem>	15%
<chem>C3H7-C1CCC(CC1)-C2CCC(CC2)-C4H9</chem>	9%
<chem>CH3OCH2-C1CCC(CC1)-C2CCC(CC2)-C3H7</chem>	3%
<chem>C4H9-c1ccc(cc1)C#Cc2ccc(OC2H5)cc2</chem>	5%
<chem>C2H5-c1ccc(cc1)C#Cc2ccc(C)cc2</chem>	1%
<chem>CH3-c1ccc(cc1)C#Cc2ccc(C8H13)cc2</chem>	2%
<chem>C4H9-c1ccc(cc1)C#Cc2ccc(C4H9)cc2</chem>	1%
<chem>C2H5-C1CCC(CC1)-C2CCC(CC2)-c3cc(F)c(C#N)cc3</chem>	9%
<chem>C3H7-C1CCC(CC1)-C2CCC(CC2)-c3cc(F)c(C#N)cc3</chem>	8%
<chem>C3H7-C1CCC(CC1)CCc2ccc(cc2)C#Cc3ccc(C2H5)cc3</chem>	4%
<chem>C3H7-C1CCC(CC1)CCc2ccc(cc2)C#Cc3ccc(C3H7)cc3</chem>	4%
<chem>C3H7-C1CCC(CC1)CCc2ccc(cc2)C#Cc3ccc(C4H9)cc3</chem>	4%

This composition exhibited a clearing point of 77.0°C, a threshold voltage in a cell thickness of 8.7 μm of 0.96 V, a $\Delta\epsilon$ of 24.2, a Δn of 0.145 and a viscosity at 20°C of 39.8 mPa·S.

5 Preferred Embodiments of the Present Invention

The present invention will be described in more details. In the following Examples, C, S, N and I respectively represent crystal, smectic phase, nematic phase and isotropic phase. The units of the transition
10 points are all directed to °C.

Example 1

Preparation of 1-(2-(4-(3-fluoropropyl)cyclohexyl)-ethyl)-3,5-difluoro-4-(3,5-difluoro-4-trifluoromethylphenyl)benzene

15 (a compound No. 80)(in the formula (I), wherein $n=3$, ring E=1,4-cyclohexylene, G=covalent bond, L=ring Z=3,5-difluoro-1,4-phenylene, $k=1$, $l=0$, $m=0$, Q=covalent bond and $Y=\text{CF}_3$)

(First step)

20 A Grignard reagent was prepared from 3,5-dibromobenzene (150 g, 0.78 mol), and dried Mg (18.9 g, 0.78 mol) in ether (600 ml), followed by slowly dropwise adding a 100 ml ether solution of ethylene oxide (100 g, 2.27 mol) to the reagent under -50°C cooling, heating the mixture
25 up to room temperature, stirring the reaction solution for one hour, adding it into 6N hydrochloric acid (500 ml),

extracting the resulting product with toluene, washing the extraction solution successively with a saturated aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate, distilling off the solvent,

5 adding an aqueous HBr (47%) (500 ml) to the residue, refluxing the mixture for 7 hours, and distilling under reduced pressure using Vigoureaux tube, to obtain a colorless, transparent liquid, 3,5-difluorophenetylbromide (41 g, 0.19 mol) (b.p. 52° to 53°C under 2 Torr).

10 The yield of this product from 3,5-difluorobromobenzene was 23.8%. A Grignard reagent was prepared from the product (20.0 g, 90.5 mmol) and dried Mg (2.2 g, 90.5 mmol) in ether (150 ml), cooling the agent down to 0°C, dropwise adding thereto a 130 ml ether solution of commercially

15 available cyclohexanedione monoethylene ketal (14.2 g, 90.9 mmol), heating the reaction solution up to room temperature, stirring it for 3 hours, adding the reaction solution to 6N HCl (500 ml), extracting the product with toluene, washing the extract successively with a saturated,

20 aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate, distilling off the solvent, adding to the residue (20 g), toluene (100 ml) and Amberlist (1 g), refluxing the mixture for 5 hours while removing water formed by the reaction, by means of Dean Stark, adding

25 ethyleneglycol (2 g), further refluxing for 2 hours, adding water (100 ml) to the reaction solution, washing

the organic layer successively with a saturated aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate, distilling off the solvent, purifying the residue according to column chromatography using
5 toluene/ethyl acetate (4:1) as a developing solvent, hydrogenating the resulting purified substance in ethanol in the presence of 5% Pd/C catalyst (1.02 g), filtering off the catalyst, distilling off under reduced pressure, refluxing the resulting concentrate in formic acid
10 (80 ml) for 3 hours, adding water (200 ml), extracting the product with toluene, washing the extraction liquid successively with a saturated aqueous solution of sodium bicarbonate and water, drying the toluene layer over magnesium sulfate, and distilling off toluene to obtain
15 4-(3,5-difluorophenylethyl)-1-cyclohexanone (10.1 g, 42.4 mmol). The yield of this product from 3,5-difluorobromobenzene was 46.6%.

(Second step)

3-Fluorobromopropane (200.0 g, 1.42 mol) was dis-
20 solved in toluene (3 l), followed by adding to the solution, triphenylphosphine (37.2 g, 1.42 mol), refluxing the mixture for 15 hours, filtering off the resulting product, and suction-drying, to obtain 3-fluoropropyltriphenylphosphine bromide (486 g, 1.21 mol). Yield: 85.2%.

25

(Third step)

THF (100 ml) was added to the above 3-fluoropropyl-
triphenylphosphine bromide (22.0 g, 54.6 mmol), followed
by cooling the mixture down to -50°C in a nitrogen
5 atmosphere, adding to the mixture, a 70 ml THF solution
of potassium-t-butoxide (6.10 g, 54.5 mmol), stirring
the mixture for 3 hours, dropwise adding to the reaction
solution, a 80 ml THF solution of 4-(3,5-difluoro-
phenetyl)-1-cyclohexanone (10.0 g, 42.0 mmol), stirring
10 the mixture for one hour at the same temperature, and
heating it up to room temperature for 4 hours, adding
water (200 ml) to the resulting reaction solution,
extracting the resulting product with ethyl acetate,
washing the extraction solution successively with
15 a saturated aqueous solution of sodium bicarbonate and
water, drying the organic layer over magnesium sulfate,
distilling off the solvent under reduced pressure,
purifying the residue according to column chromatography
treatment using toluene as a developing solvent,
20 hydrogenating the resulting purified substance in the
presence of 5% Pd/C catalyst, in ethanol, and thereafter
filtering off the catalyst to obtain 4-(3,5-difluoro-
phenetyl)-1-(3-fluoropropyl)cyclohexane (2.51 g, 8.83 mmol).
Yield: 21.0%.

(Fourth step)

THF (30 mL) was added to the above 4-(3,5-difluoro-phenetyl)-1-(3-fluoropropyl)cyclohexane (2.51g, 8.83 mmol), followed by cooling the mixture down to -50°C in
5 a nitrogen gas atmosphere, dropwise adding thereto a hexane solution (7 mL, 11.4 mmol) of 1.63N n-butyl-lithium by means of a syringe, stirring the mixture for one hour at the same temperature, dropwise adding a 0.5 mol ZnCl₂ THF solution (22.8 mL, 11.4 mol),
10 heating the reaction substance up to room temperature, further stirring it for 2 hours, adding to the reaction solution, tetrakis(triphenylphosphine) palladium (250 mg) as a catalyst, dropwise adding 3,5-difluoro-4-trifluoromethylphenyl bromide (2.97 g, 11.4 mmol), refluxing the
15 mixture for 2 hours adding the reaction solution to cooled 6N-HCl, extracting the resulting product with toluene, washing the extraction solution successively with a saturated aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate, distilling off
20 the solvent, to obtain an orange color suspension (8.5 g), purifying it according to column chromatography treatment using a developing solvent of toluene/heptane (1/1), on silica gel, and recrystallization, to obtain trans-form of 1-(2-(4-(3-fluoropropyl)cyclohexyl)ethyl)-3,5-difluoro-
25 4-(3,5-difluoro-4-trifluoromethylphenyl)benzene (0.35 g, 0.75 mmol). Yield: 8.49%, C-I point: 83.7°C
1H-NMR (CDCl₃) δ (ppm): 7.10 (d, 2H), 6.84 (d, 2H),

4.69 (t, 1H), 4.16 (t, 1H), 2.66 (t, 2H), 1.84~0.88 (m, 18H).

Example 2

Preparation of 1-(2-(4-(4-(2-fluoroethyl)cyclohexyl)-cyclohexyl)ethyl-4-trifluoromethoxybenzene

5 (a compound No. 17) (in the formula (1), wherein
n=2, ring E=1,4-cyclohexylene, G=covalent bond,
L=1,4-cyclohexylene, ring Z=1,4-phenylene, k=l=0,
m=1, Q=-O- and Y=CF₃)

(First step)

10 THF (1 l) was added to ethoxycarbonylmethyldimethyl-
phosphonate (125 g, 0.556 mol), followed by cooling the
mixture down to -50°C in a nitrogen gas atmosphere,
followed by gradually adding to the mixture, potassium-
t-butoxide (62.3 g, 0.556 mol), stirring the mixture
15 at the same temperature for one hour, adding thereto,
a THF 400 ml solution of bicyclohexanedione monoethylene
ketal (117 g, 0.464 mol), stirring the mixture at room
temperature for 10 hours, adding water (500 ml) to the
reaction solution, extracting the resulting product with
20 toluene, washing the extraction solution successively with
a saturated aqueous solution of sodium bicarbonate and
water, drying over magnesium sulfate, distilling off the
solvent under reduced pressure to obtain a yellow liquid
(218.2 g), dissolving it in ethanol, hydrogenating in
25 the presence of Raney Ni catalyst, filtering off the
catalyst, distilling off ethanol under reduced pressure,

purifying the residue according to column chromatography using toluene as a developing solvent on silica gel, to isolate colorless, oily 4-(1,4-dioxaspiro[4.5]decyl)-cyclohexylmethanoic acid ethyl ester (183.2 g, 0.464 mol).

5 (Second step)

Dried THF (100 ml) was added to lithium aluminum hydride (17.6 g, 0.464 mol), followed by cooling the mixture down to 0°C, dropwise adding thereto a 800 ml THF solution of the above 4-(1,4-dioxaspiro[4.5]decyl)-cyclohexylmethanoic acid ethyl ester (183.2 g, 0.464 mol), stirring at 0°C for 3 hours, stirring at room temperature for 2 hours, washing the reaction solution successively with 3N HCl, a saturated aqueous solution of sodium bicarbonate and water, distilling off the solvent, and recrystallizing, to isolate colorless crystals of 2-(4-(1,4-dioxaspiro[4,5]decyl)cyclohexyl)ethanol (50.6 g, 0.179 mol). Yield from bicyclohexanedione monoethylene ketal was 38%.

(Third step)

The above 2-(4-(1,4-dioxaspiro[4,5]decyl)cyclohexyl)-ethanol (20 g, 70.8 mmol) was dissolved in dichloromethane (70 ml), followed by dropwise adding to the solution, DAST (13 g, 80.7 mmol), stirring at 0°C for one hour, adding water to the reaction solution, washing the resulting organic layer successively with a saturated aqueous solution of sodium bicarbonate and water, distilling off the solvent, purifying the residue

according to column chromatography using heptane/ethyl acetate as a developing solvent, on silica gel, to obtain 1-(4-(1,4-dioxaspiro[4,5]decyl)cyclohexyl)-2-fluoroethane, adding thereto formic acid (80 ml), refluxing
5 the mixture for 2 hours, extracting the resulting product with toluene, washing the extraction solution successively with a saturated aqueous solution of sodium bicarbonate, distilling off the solvent, to isolate 4-(4-(2-fluoroethyl)cyclohexyl)cyclohexanone (8.0 g,
10 35.3 mmol). The yield of this product from 2-(4-(1,4-dioxaspiro[4,5]decyl)cyclohexyl)ethanol was 49.9%.

(Fourth step)

A Grignard reagent prepared from 4-trifluoromethoxybromobenzene (54 g, 220 mmol) and dried Mg (5.4 g, 220
15 mmol) in 250 ml ether solvent was cooled down to -50°C, followed by gradually dropwise adding thereto ethylene oxide (29.3 g, 670 mmol), gradually heating the resulting reaction mixture up to room temperature, further stirring it for one hour at room temperature, adding the reaction
20 solution to 6N HCl (300 ml), extracting the resulting product with ethyl acetate, washing the extraction solution successively with a saturated aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate, distilling off the solvent, distilling the residue under
25 reduced pressure by means of a Vigoureaux tube, to isolate a colorless liquid, 2-(4-trifluoromethoxyphenyl)ethanol

(14.5 g, 70.3 mmol) having a b.p. of 82° to 84°C under 3.5 Torr, adding to this liquid, xylene (60 ml) and HBr aqueous solution (47%) (60 ml), refluxing the mixture for 9 hours, adding water to the reaction mixture, 5 extracting the resulting product with toluene, washing the reaction solution successively with a saturated aqueous solution of sodium bicarbonate and water, drying the resulting organic layer over magnesium sulfate, distilling off the solvent, distilling the residue under 10 reduced pressure using Vigoureaux tube, to isolate a colorless liquid, 2-(4-trifluoromethoxyphenyl)bromoethane (12.0 g, 51.9 mmol) having a b.p. of 74°C under 4 Torr. The yield of this product from 4-trifluoromethoxybromobenzene was 23.6%.

15 (Fifth step)

A Grignard reagent prepared from the above 2-(4-trifluoromethoxyphenyl)bromoethane (7.0 g, 30.3 mmol) and dried Mg (0.74 g, 30.4 mmol) in an ether solvent (40 ml) was cooled down to 0°C, followed by dropwise 20 adding thereto a 30 ml ether solution of 4-(4-(2-fluoroethyl)cyclohexyl)cyclohexanone (2.2 g, 9.7 mmol) prepared at the third step, stirring the mixture at 0°C for 3 hours, adding 6N HCl to the reaction solution, extracting the resulting product with toluene, washing the extraction 25 solution successively with a saturated aqueous solution of sodium bicarbonate and water, drying over magnesium

sulfate, distilling off the solvent, adding toluene (100 ml) and Amberlist (500 mg) to the resulting yellow oily substance, refluxing the mixture for 4 hours, while removing water formed by the reaction by means of Dean-Stark, filtering off Amberlist, distilling off the solvent, purifying the residue according to column chromatography treatment using toluene as a developing solvent, on silica gel, to isolate 4-(4-(2-fluoroethyl)-cyclohexyl)-1-(2-(4-trifluoromethoxyphenyl)ethyl)-1-cyclohexene (1.8 g, 4.5 mmol), hydrogenating this product (1.2 g, 3.0 mmol) in the presence of 5% Pd/C catalyst (0.12 g) in ethanol solution, filtering off the catalyst, distilling off the solvent under reduced pressure, and recrystallizing the residue, to isolate only trans-form of colorless 1-(2-(4-(4-(2-fluoroethyl)-cyclohexyl)cyclohexyl)ethyl-4-trifluoromethoxybenzene (0.37 g, 0.90 mmol) exhibiting smectic phase. The yield of this product from 4-(4-(2-fluoroethyl)chclohexyl)cyclohexanone was 9.3%.

S_B-N point 68.8°C, N-I point 103.5°C.
1H-NMR (CDCl₃) δ (ppm): 7.19 (t, 4H), 4.74 (t, 1H), 4.21 (t, 1H), 2.58 (t, 2H), 1.82~0.99 (m, 26H).

Example 3

Preparation of 1-(4-(3-fluoropropyl)cyclohexyl)-3,5-difluoro-4-(2-(3-fluoro-4-trifluoromethoxyphenyl)-ethyl)benzene

(in the formula (1), $n=3$, ring E=1,4-cyclohexylene, G=covalent bond, L=3,5-difluoro-1,4-phenylene, ring Z=3-fluoro-1,4-phenylene, $k=l=0$, $m=1$, Q=-O- and Y=CF₃) (Compound No. 122)

5 (First step)

A Grignard reagent prepared from 3,5-difluorophenyl-bromide (193.1 g, 1.00 mol) and dried Mg (24.3 g, 1.00 mol) in THF solvent was cooled down to 0°C, followed by dropwise adding to the agent, a 300 ml ether solution
10 of cyclohexanedione monoethyleneketal (156 g, 1.00 mol), heating the reaction solution up to room temperature, stirring the mixture for 3 hours, adding it to 6N HCl (1 l), extracting the resulting product with toluene, washing the extraction solution successively with
15 a saturated aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate, distilling off the solvent under reduced pressure, adding to the residue, Amberlist (8 g) and toluene (1,000 ml), refluxing for 7 hours while removing water formed by the reaction by
20 means of Dean-Stark, filtering off the Amberlist in the product, distilling off toluene under reduced pressure, purifying the residue according to column chromatography treatment using toluene as a developing agent, on silica gel, to obtain a cyclohexene derivative, adding
25 formic acid (500 ml) to the cyclohexene derivative (62 g), refluxing the mixture for 5 hours, adding water (500 ml)

to the reaction solution, extracting the resulting product with toluene, washing the toluene layer successively with a saturated aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate, distilling off
5 toluene under reduced pressure and distilling the residue under reduced pressure, to obtain 4-(3,5-difluorophenyl)-cyclohexanone (43.8 g, 20.8 mmol). Yield: 20.8%

(Second step)

THF (60 ml) was added to 3-fluoropropyltriphenyl-
10 phosphinebromide (10.3 g, 25.5 mmol) prepared at the second step of Example 1, followed by cooling the mixture down to -50°C in nitrogen atmosphere, adding to the mixture, a 40 ml THF solution of potassium-t-butoxide (2.86 g, 25.5 mmol), stirring the mixture at the same temperature
15 for 3 hours, dropwise adding to the reaction solution, a 100 ml THF solution of 4-(3,5-difluorophenyl)cyclohexanone (43.8 g, 20.8 mmol) prepared at the first step, stirring the mixture at the same temperature for one hour, stirring at room temperature for 3 hours, adding water
20 (200 ml) to the reaction solution, extracting the resulting product with ethyl acetate, washing the organic layer successively with a saturated aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate, purifying an yellow solution obtained by distilling off
25 the solvent, according to column chromatography treatment using toluene as a developing solvent, on silica gel,

hydrogenating the resulting cyclohexylidene derivative using a catalyst of Pd/C, in ethanol, filtering off the catalyst after the reaction, distilling off ethanol under reduced pressure and recrystallizing the resulting product using a mixed solvent of heptane with ethanol, to obtain 4-(3,5-difluorophenyl)-1-(3-fluoropropyl)cyclohexane (1.50 g, 6.14 mmol).
Yield: 29.5%.

(Third step)

THF (20 ml) was added to the above 4-(3,5-difluorophenyl)-1-(3-fluoropropyl)cyclohexane (1.50 g, 6.14 mmol), followed by cooling the mixture down to -50°C in a nitrogen atmosphere, dropwise adding thereto a hexane solution 4 ml (6.51 mmol) of 1.63 N normal butyllithium by means of a syringe, stirring the mixture at the same temperature for one hour, dropwise adding to the reaction solution, THF 10 ml solution of iodine (1.65 g, 6.51 mmol), stirring the mixture at the same temperature for 30 minutes, adding the reaction solution to 6N HCl, extracting the resulting product with toluene, washing the extraction solution successively with a saturated aqueous solution of sodium bicarbonate and water, drying the organic layer over magnesium sulfate, distilling off the solvent, and purifying the residue according to column chromatography treatment using heptane as a developing solvent, on silica gel, to obtain 4-(3,5-difluorophenyl-4-iodo)-1-3-fluoropropyl)cyclohexane (2.12 g, 5.73 mmol). Yield: 93.3%.

(Fourth step)

A Grignard reagent prepared from 3-fluoro-4-tri-
fluoromethoxyphenylbromide (200.0 g, 772 mmol) and dried
Mg (18.8 g, 774 mmol) in ether was cooled down to -50°C
5 in a nitrogen atmosphere, followed by dropwise adding
thereto a 100 ml ether solution of ethylene oxide (100 g,
2.27 mol), stirring the reaction solution at 0°C for
2 hours, adding the resulting reaction product to 6N HCl,
extracting the product with toluene, washing the extrac-
10 tion solution successively a saturated aqueous solution
of sodium bicarbonate and water, drying over the organic
layer over magnesium sulfate, distilling off the solvent,
adding to the residue, 47% hydrogen bromic acid (300 ml)
and xylene (300 ml), refluxing the mixture for 9 hours,
15 while removing water formed by the reaction by means of
Dean-Stark, adding water (500 ml) to the resulting reac-
tion product, extracting the resulting product with
toluene, washing the extraction solution successively
with a saturated aqueous solution of sodium bicarbonate
20 and water, distilling off the solvent, and distilling
the residue under reduced pressure, to obtain 3-fluoro-4-
trifluoromethoxyphenetylbromide (68.3 g, 238 mmol).
Yield: 30.7%.

(Fifth step)

25 A Grignard reagent prepared from the above 3-fluoro-
4-trifluoromethoxyphenetylbromide (1.64 g, 5.71 mmol) and

dried Mg (0.14 g, 5.76 mmol) in ether (10 ml) was cooled down to 0°C, followed by adding thereto Ni acetylacetonate (0.10 g, 0.39 mmol), dropwise adding a 20 ml ether solution of 4-(3,5-difluorophenyl-4-iodo)-1-(3-fluoropropyl)-cyclohexane (2.12 g, 5.73 mmol) prepared at the third step, stirring the reaction solution at 0°C for one hour, heating it up to room temperature, stirring it for 3 hours, adding the resulting reaction solution to 6N HCl, extracting the resulting product with toluene, washing the extraction solution successively with a saturated aqueous solution of sodium bicarbonate and water, drying the organic layer over magnesium sulfate, distilling off the solvent, purifying the residue according to column chromatography treatment using toluene as a developing solvent on silica gel, and recrystallizing from a mixed solvent of heptane with ethanol, to obtain 1-(4-(3-fluoropropyl)cyclohexyl)-3,5-difluoro-4-(2-(3-fluoro-4-trifluoromethoxyphenyl)ethyl)benzene (320 mg, 0.692 mmol). Yield: 12.0%. The data of 1H-NMR well supported its structure.

20 Example 4

Preparation of 1-(4-(4-(3-fluoropropyl)cyclohexyl)-cyclohexyl)-3,5-difluoro-4-(3-fluoro-4-trifluoromethoxyphenyl)benzene (in the formula (1), n=3, ring E=G=1,4-cyclohexylene, L=3,5-difluoro-1,4-phenylene, ring Z=3-fluoro-1,4-phenylene, k=l=m=0, Q= -O- and Y=CF₃) (Compound No. 240).



(First step)

A 500 ml THF solution of bicyclohexanedione mono-propyleneketal was dropwise added at room temperature to a Grignard reagent prepared from 3,5-difluorophenyl-
5 bromide (107.1 g, 555 mmol) and dried Mg (14.0 g, 575 mmol) in THF (600 ml), followed by stirring the mixture at the same temperature for 5 hours, cooling the reaction solution to 0°C, adding thereto a saturated aqueous solution of NH_4Cl , extracting the resulting product with ethyl
10 acetate, washing the extraction solution with water, drying the organic layer over magnesium sulfate, distilling off the solvent, to obtain yellow crystals (158 g), adding thereto toluene (700 ml) and 5% paratoluenesulfonic acid (7.9 g), refluxing the mixture for 9 hours, further
15 2 hours before completion of the reflux, adding propylene glycol (37 g) and 5% paratoluenesulfonic acid (8.3 g) into the system, washing the reaction solution successively with 6N HCl , a saturated aqueous solution of sodium bicarbonate and water, drying the organic layer over magnesium sulfate,
20 distilling off the solvent, and purifying the resulting residue (169 g) according to column chromatography treatment using toluene/ethyl acetate (1/9) as a developing solvent, on silica gel, to obtain 4-(3,5-difluorophenyl)-3-cyclohexenyl-1-cyclohexanone propyleneketal (114 g, 327
25 mmol). Yield: 56.9%.

(Second step)

The above 4-(3,5-difluorophenyl)-3-cyclohexenyl-1-cyclohexanone propyleneketal (114 g, 327 mmol) was hydrogenated in a mixed solvent of ethyl acetate with ethanol in the presence of Raney Ni catalyst (44.8 g), followed by filtering off the catalyst, distilling off the solvent under reduced pressure, adding to the residue, formic acid (50.0 g, 1.09 mol) and toluene (300 ml), refluxing the mixture for 4 hours, adding water to the reaction solution, washing the organic layer successively with a saturated aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate, distilling off toluene under reduced pressure, and purifying the residue according to column chromatography treatment using toluene as a developing solvent, on silica gel, to obtain 4-(3,5-difluorophenyl)cyclohexyl-1-cyclohexanone (56.8 g, 194 mmol). Yield: 59.3%.

(Third step)

THF (250 ml) was added to 3-fluoropropyltriphenylphosphine bromide (36.1 g, 89.5 mmol) prepared at the second step of Example 1, followed by cooling the mixture down to -50°C in nitrogen gas atmosphere, adding to the mixture, a 100 ml THF solution of potassium-t-butoxide (10.0 g, 89.5 mmol), stirring the mixture for 3 hours, dropwise adding to the reaction solution, a 200 ml THF solution of 4-(3,5-difluorophenyl)cyclohexyl-1-cyclohexanone

(20.0 g, 68.9 mmol) prepared at the second step, stirring the mixture at the same temperature for one hour, heating the mixture up to room temperature, stirring for 4 hours, adding water (1 l) to the reaction solution, extracting
5 the resulting product with toluene, washing the extraction solution with water, drying the organic layer over magnesium sulfate, distilling off the solvent, purifying the residue according to column chromatography treatment using toluene as a developing solvent, on silica gel,
10 to obtain an yellow solution (12.99 g), hydrogenating it in the presence of a 5% Pd/C catalyst (1.20 g) in ethanol, distilling off the solvent, and purifying the residue using toluene as a developing solvent on silica gel, to obtain 4-(3-fluoropropylcyclohexyl)cyclohexyl)-3,5-
15 difluorobenzene (8.33 g, 24.6 mmol). Yield: 35.7%.

(Fourth step)

THF (80 ml) was added to the above 4-(3-fluoropropylcyclohexyl)cyclohexyl)-3,5-difluorobenzene (8.10 g, 23.9 mmol), followed by cooling the mixture down to -50°C in
20 nitrogen gas atmosphere, dropwise adding thereto a hexane solution (16.9 ml, 28.7 mmol) of 1.63 N normal butyllithium by means of a syringe, stirring the mixture at the same temperature for one hour, further dropwise adding a THF solution (58.4 ml, 29.2 mol) of 0.5 mol zinc chloride,
25 heating the reaction solution up to room temperature, further stirring for 2 hours, adding to the reaction

solution, tetrakis(triphenylphosphine) palladium (0.72 g, 622 μ mol), dropwise adding 3-fluoro-4-trifluoromethoxyphenylbromide (7.44 g, 28.7 μ mol), refluxing the mixture for 2 hours, adding to the reaction solution, 6N HCl, extracting the product with ethyl acetate, washing the extraction solution successively with a saturated aqueous solution of sodium bicarbonate and water, drying the organic layer over magnesium sulfate, distilling off the solvent, purifying the residue (13.9 g) according to column chromatography treatment using heptane as a developing solvent on silica gel, and recrystallizing from a mixed solvent of heptane with ethanol, to obtain 1-(4-(4-(3-fluoropropyl)cyclohexyl)cyclohexyl)-3,5-difluoro-4-(3-fluoro-4-trifluoromethoxyphenyl)benzene (1.31 g, 2.54 μ mol). Yield: 10.6%. C-N point: 78.5°C. N-I point: 224.5°C.

$^1\text{H-NMR}(\text{CDCl}_3)$ δ (ppm): 7.37 (t, 3H), 6.85 (d, 2H), 4.69 (t, 1H), 4.16 (t, 1H), 2.46 (m, 1H), 2.02~0.81 (m, 23H).

Example 5

Preparation of 1-(2-(4-(3-fluoropropyl)cyclohexyl)-ethyl)-3,5-difluoro-4-(3-fluoro-4-trifluoromethoxyphenyl)benzene (in the formula (1), $n=3$, ring E = 1,4-cyclohexylene, G=covalent bond, L = 3,5-difluoro-1,4-phenylene, ring Z = 3-fluoro-1,4-phenylene, $k=1$, $l=0$, $m=0$, Q = -O-, Y=CF₃) (compound No. 77)

(First step)

THF (50 ml) was added to 4-(3,5-difluorophenetyl)-
1-(3-fluoropropyl)cyclohexane (5.0 g, 17.6 mmol) prepared
in the same manner as in Example 1, followed by cooling
5 the mixture down to -50°C in a nitrogen gas atmosphere,
dropwise adding thereto a hexane solution (13 ml, 21.8
mmol) of 1.68 N normal-butyllithium by means of a syringe,
stirring the mixture at the same temperature for one hour,
dropwise adding a THF solution (43.6 ml, 21.8 mmol) of
10 zinc chloride (0.5 mol/l), heating the reaction product
up to room temperature, further stirring it for 2 hours,
adding to the reaction solution, tetrakis(triphenyl)phosphine
palladium (500 mg) as a catalyst, dropwise adding 3-fluoro-
4-trifluoromethoxybromobenzene (5.64 g, 21.8 mmol),
15 refluxing the mixture for 2 hours, adding the reaction
solution to cooled 6N HCl, extracting the resulting product
with toluene, washing the extraction solution successively
with a saturated, aqueous solution of sodium bicarbonate,
and water, drying over magnesium sulfate, distilling off
20 the solvent, to obtain a yellow suspension (7.7 g),
purifying it according to column chromatography treatment
using toluene/heptane (1:1) as a developing solvent, on
silica gel, and recrystallizing to obtain trans form of
1-(2-(4-(3-fluoropropyl)cyclohexyl)ethyl)-3,5-difluoro-4-
25 (3-fluoro-4-trifluoromethoxyphenyl)benzene (0.58 g, 1.25
mmol). Yield: 7.1%, C-I point: 44.8°C, (N-I point:
13.6°C).

¹H-NMR (CDCl₃) δ (ppm): 7.38 ~ 6.77 (m, 5H),
4.69 (t, 1H), 4.16 (t, 1H), 2.65 (t, 2H),
1.84 ~ 0.93 (m, 16H).

Example 6

5 1-(2-(4-(4-(3-fluoropropyl)cyclohexyl)cyclohexyl)-
ethyl)-4-trifluoromethylbenzene (in the formula (1),
n=3, ring E = G = 1,4-cyclohexylene, L=covalent bond,
ring Z = 1,4-phenylene, k=l=0, m=1, Q=covalent bond,
Y=CF₃) (Compound No. 18).

10 (First step)

THF (1 l) was added to methoxymethyltriphenylphosphine
chloride (128 g, 370 mmol), followed by adding to the mix-
ture, potassium-t-butoxide (41.5 g, 370 mmol) at 0°C,
stirring the mixture at the same temperature for 3 hours,
15 dropwise adding to the reaction solution, a 500 ml THF
solution of commercially available 4-trifluoromethyl-
benzaldehyde (50.0 g, 287 mmol), stirring the mixture
at the same temperature for one hour, stirring it at
room temperature for 3 hours, adding water (1.5 l) to
20 the reaction solution, extracting the resulting product
with ethyl acetate, washing the organic layer successively
with a saturated aqueous solution of sodium bicarbonate
and water, drying over magnesium sulfate, distilling off
the solvent, purifying the resulting yellow solution
25 according to column chromatography treatment using
heptane/ethyl acetate (3:2) as a developing solvent,

on silica gel, and distilling the purified substance under reduced pressure by means of Vigoureux tube, to obtain 1-trifluoromethyl-4-(2-methoxyvinyl)benzene (19.5 g, 96.5 mmol) (b.p. 93.5°C under 9 Torr). Yield: 33.6%.

5 (Second step)

The above 1-trifluoromethyl-4-(2-methoxyvinyl)-benzene (19.5 g, 96.5 mmol) was dissolved in acetone (100 ml), followed by adding 6N HCl (100 ml) to the solution, stirring the mixture for 5 hours, extracting the
10 resulting product with ethyl acetate, washing the organic layer successively with a saturated, aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate and distilling off the solvent, to obtain 4-trifluoromethylbenzaldehyde (17.5 g, 93.0 mmol).
15 Yield: 96.4%.

(Third step)

Ethanol (200 ml) was added to the above 4-trifluoromethylbenzaldehyde (17.5 g, 93 mmol), followed by cooling the mixture down to 0°C in a nitrogen atmosphere, adding
20 thereto sodiumboronhydride (1.78 g, 47.1 mmol) so that the liquid temperature might not exceed 10°C, stirring the mixture at 0°C for 2 hours, extracting the resulting product with ethyl acetate, washing the organic layer successively with a saturated, aqueous solution of sodium
25 bicarbonate and water, drying over magnesium sulfate, distilling off the solvent, adding an aqueous solution

of HBr (47%) (100 ml) to the residue (about 18 g),
refluxing the mixture for 7 hours and distilling under
reduced pressure by means of Vigoureux tube, to obtain
2-(4-trifluoromethylphenyl)bromoethane (19.5 g, 77.1 mmol)
5 (b.p.: 94°C under 9 Torr). Yield: 82.9%.

(Fourth step)

A Grignard reagent prepared from the above 2-(4-
trifluoromethylphenyl)bromoethane (19.5 g, 77.1 mmol and
dried Mg (1.90 g, 78.2 mmol) in an ether solvent (100 ml),
10 was cooled down to 0°C, followed by dropwise adding to
the agent, a 100 ml ether solution of bicyclohexanedione
monopropylene ketal (19.4 g, 76.9 mmol), heating the mix-
ture up to room temperature, stirring it for 3 hours,
adding this reaction solution to 6N HCl (100 ml),
15 extracting the resulting product with toluene, washing
the extraction solution successively with a saturated,
aqueous solution of sodium bicarbonate and water, drying
over magnesium sulfate, distilling off the solvent, adding
toluene (300 ml) and Amberlist (1.5 g) to the resulting
20 pale-yellow, oily substance (about 30 g), refluxing the
mixture for 4 hours, while removing water formed by the
reaction by Dean-Stark, filtering off the solvent, purify-
ing the residue according to column chromatography treatment
using ethyl acetate/toluene (1/1) as a developing solvent, on
25 silica gel, to isolate 4-(4-oxocyclohexyl)-1-(2-(4-tri-
fluoromethylphenyl)ethyl)-1-cyclohexene propyleneacetal

(20.0 g, 48.9 mmol), hydrogenating the compound in the presence of a catalyst of 5% Pd/C (1.0 g) in ethanol solvent, filtering off the catalyst, distilling off the solvent under reduced pressure, adding formic acid
5 (20.0 g, 444 mmol) and toluene (100 ml), to the residue, refluxing the mixture for 5 hours, washing the organic layer successively with a saturated, aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate, purifying the residue according to column
10 chromatography treatment using ethyl acetate/toluene (1/3) as a developing solvent, on silica gel, recrystallizing the purified product from heptane, to isolate 4-(4-oxocyclohexyl)-1-(2-(4-trifluoromethylphenyl)ethyl)cyclohexane (2.7 g, 7.7 mmol). The yield of this product from
15 bicyclohexanedione monopropylene ketal was 10.0%.

(Fifth step)

THF (70 ml) was added to 1,3-dioxan-2-ylethyltriphenylphosphinebromide (6.80 g, 14.9 mmol), followed by adding to the mixture, potassium-t-butoxide (1.68 g,
20 14.9 mmol) at 0°C, stirring the mixture at the same temperature for 3 hours, dropwise adding to the reaction solution, a 10 ml THF solution of the above 4-(4-oxocyclohexyl)-1-(2-(4-trifluoromethylphenyl)ethyl)cyclohexane
(2.7 g, 7.7 mmol), stirring the mixture at the same
25 temperature for one hour, further stirring at room temperature for 3 hours, adding water (50 ml) to

the reaction solution, extracting the resulting product with ethyl acetate, washing the organic layer successively with a saturated, aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate, distilling off the solvent, purifying the resulting residue according to column chromatography treatment using heptane/ethyl acetate (3/1) as a developing solvent, on silica gel, distilling off the solvent, hydrogenating the residue (3.2 g) in the presence of a catalyst of 5% Pd/C (0.15 g), in ethanol solvent, filtering off the catalyst distilling off the solvent under reduced pressure, and recrystallizing the residue from heptane/ethanol (5/1), to obtain 4-(4-(1,3-dioxan-2-ylethyl)cyclohexyl)-1-(2-(4-trifluoromethylphenyl)ethyl)cyclohexane (1.46 g, 3.23 mmol). The yield of this product from 4-(4-oxocyclohexyl)-1-(2-(4-trifluoromethylphenyl)ethyl)cyclohexane was 42%.

(Sixth step)

Formic acid (1.5 g, 33 mmol) and toluene (10 ml) were added to the above 4-(4-(1,3-dioxan-2-ylethyl)cyclohexyl)-1-(2-(4-trifluoromethylphenyl)ethyl)cyclohexane (1.46 g, 3.23 mmol), followed by refluxing the mixture for 5 hours, washing the organic layer successively with a saturated, aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate, and distilling off the solvent, to obtain 3-(4-(4-(2-(4-trifluoromethylphenyl)ethyl)cyclohexyl)cyclohexyl)propanal (1.21 g, 3.07 mmol). Yield: 95.0%.

(Seventh step)

Ethanol (10 mL) was added to the above 3-(4-(4-(2-(4-trifluoromethylphenyl)ethyl)cyclohexyl)cyclohexyl)propanal (1.21 g, 3.07 mmol), followed by cooling the mixture down
5 to 0°C in a nitrogen gas atmosphere, adding thereto, sodiumboronhydride (0.13 g, 3.43 mmol) so that the solution temperature could not exceed 10°C, stirring the mixture at 0°C for 2 hours, extracting the resulting product with ethyl acetate, washing the organic layer
10 successively with a saturated, aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate, and distilling off the solvent, to obtain 3-(4-(4-(2-(4-trifluoromethylphenyl)ethyl)cyclohexyl)cyclohexyl)propanol (1.20 g, 3.03 mmol). The yield was 98.7%.

15 (Eighth step)

Dimethoxyethane (10 mL) was added to the above 3-(4-(4-(2-(4-trifluoromethylphenyl)ethyl)cyclohexyl)cyclohexyl)propanol (1.20 g, 3.03 mmol), followed by dropwise adding thereto diethylaminosulfur trifluoride (DAST)
20 (1.13 g, 7.01 mmol), refluxing the mixture for 5 hours, extracting the resulting product with toluene, washing the organic layer successively with a saturated, aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate, distilling off the solvent, purifying
25 the residue according to column chromatography treatment using heptane as a developing solvent, on silica gel,

distilling off the solvent, and recrystallizing the residue from ethanol/heptane (9/1), to isolate only trans-form of 1-(2-(4-(4-(3-fluoropropyl)cyclohexyl)cyclohexyl)ethyl)-4-trifluoromethylbenzene (0.60 g, 1.5 mmol).

5 Yield: 49.5%. Sp-I point: 118.9°C

1H-NMR (CDC 13) δ (ppm): 7.52 (d, 2H), 7.27 (d, 2H), 4.68 (t, 1H), 4.16 (t, 1H), 2.68 (t, 2H), 1.75~0.99 (m, 26H).

Example 7

10 Preparation of 1-(2-(4-(4-(3-fluoropropyl)cyclohexyl)-cyclohexyl)ethyl)-4-trifluoromethoxybenzene

(in the formula (1), n=3, ring E = 1,4-cyclohexylene, G = covalent bond, L = 1,4-cyclohexylene, ring Z = 1,4-phenylene, k=l=0, m=1, Q = -O-, Y=CF₃)

15 (Compound No. 19)

(First step)

THF (1.8 l) was added to methoxymethyltriphenylphosphine chloride (350 g, 1.02 mol), followed by adding to the mixture, potassium-t-butoxide (114 g, 1.02 mol),
20 stirring the mixture at the same temperature, for 3 hours, dropwise adding to the reaction solution, a 750 mL THF solution of commercially available 4-trifluoromethoxybenzaldehyde (150.0 g, 0.79 mol), stirring the mixture at the same temperature for one hour, further stirring
25 it at room temperature for 3 hours, adding water (1.5 l) to the reaction solution, extracting the resulting product

with ethyl acetate, washing the organic layer successively with a saturated, aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate, distilling off the solvent, purifying the resulting yellow solution
5 according to column chromatography treatment using heptane/ethyl acetate (3/2) as a developing solvent, on silica gel, and distilling the purified product under reduced pressure, by means of Vigoureaux tube, to obtain 1-trifluoromethoxy-4-(2-methoxyvinyl)benzene (138 g, 0.63 mol). (b.p. 91°C
10 under 9 Torr). Yield: 79.7%.

(Second step)

The above 1-trifluoromethoxy-4-(2-methoxyvinyl)-benzene (138 g, 0.63 mol) was dissolved in acetone (500 ml), followed by adding 6N HCl (500 ml) to the solution,
15 stirring the mixture for 5 hours, extracting the resulting product with ethyl acetate, washing the organic layer successively with a saturated aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate, and distilling off the solvent, to obtain 4-trifluoro-
20 methoxybenzylaldehyde (123 g, 0.60 mol). Yield: 95.2%.

(Third step)

Ethanol (1.5 l) was added to the above 4-trifluoromethoxybenzylaldehyde (123 g, 0.60 mol), followed by cooling the mixture down to 0°C in a nitrogen atmosphere,
25 adding thereto sodiumboronhydride (11.7 g, 0.31 mol) so that the liquid temperature might not exceed 10°C,

stirring the mixture at 0°C for 2 hours, extracting the resulting product with ethyl acetate, washing the organic layer successively with a saturated, aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate, distilling off the solvent, adding an aqueous solution of HBr (47%) (750 ml) to the residue, refluxing the mixture for 7 hours, and distilling it under reduced pressure by means of Vigoureux tube, to obtain 2-(4-trifluoromethoxyphenyl)bromoethane (52.8 g, 0.20 mol) (b.p.: 52.0°C under 1 Torr). Yield: 33.3%.

(Fourth step)

A Grignard reagent prepared from the above 2-(4-trifluoromethoxyphenyl)bromoethane (25.0 g, 92.9 mmol) and dried Mg (2.26 g, 93.0 mmol) in 100 ml ether solvent, was cooled down to 0°C, followed by dropwise adding there- to a 100 ml ether solution of bicyclohexanedione mono-propyleneketal (22.0 g, 87.2 mmol), heating the mixture up to room temperature, stirring it for 3 hours, adding the reaction solution to 6N HCl (100 ml), extracting the resulting product with toluene, washing the extraction solution successively with a saturated, aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate, distilling off the solvent, adding toluene (300 ml) and Amberlist (2.0 g) to the residue, refluxing for 5 hours, while removing water formed by the reaction by means of Dean-Stark, filtering off Amberlist,

distilling off the solvent, purifying the residue according to column chromatography treatment using ethyl acetate/toluene (1/2) as a developing solvent, on silica gel, to isolate 4-(4-oxocyclohexyl)-1-(2-(4-trifluoromethoxyphenyl)ethyl)-1-cyclohexene propylene acetal (22.2 g, 52.3 mmol), hydrogenating it in the presence of a 5% Pd/C catalyst (1.2 g) in ethanol solvent, filtering off the catalyst after the reaction, distilling off the solvent under reduced pressure, adding to the residue, formic acid (20.0 g, 444 mmol) and toluene (100 mL), refluxing the mixture for 5 hours, washing the organic layer successively with a saturated, aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate, distilling off the solvent, purifying the residue according to column chromatography treatment using ethyl acetate/toluene (1/3) as a developing solvent, on silica gel and recrystallizing the purified substance from heptane, to isolate 4-(4-oxocyclohexyl)-1-(2-(4-trifluoromethoxyphenyl)ethyl)cyclohexane (5.7 g, 15.6 mmol). The yield of this product from bicyclohexanedione monopropylene ketal was 17.9%.

(Fifth step)

THF (100 mL) was added to 1,3-dioxan-2-ylethyltriphenylphosphinebromide (10.0 g, 21.9 mmol), followed by adding thereto potassium-t-butoxide (2.46 g, 21.9 mmol), stirring the mixture at the same temperature for 3 hours,

dropwise adding to the reaction solution, a 20 ml THF solution of the above 4-(4-oxocyclohexyl)-1-(2-(4-trifluoromethoxyphenyl)ethyl)cyclohexane (5.7 g, 15.6 mmol), stirring the mixture at the same temperature for one hour, stirring for 3 hours at room temperature, adding water (100 ml) to the reaction solution, extracting the product with ethyl acetate, washing the organic layer successively with a saturated aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate, distilling off the solvent, purifying the resulting residue according to column chromatography treatment using heptane/ethyl acetate (3/1) as a developing solvent, on silica gel, distilling off the solvent, hydrogenating the residue (5.1 g) in the presence of a catalyst of 5% Pd/C (0.30 g) in an ethanol solution, filtering off the catalyst, distilling off the solvent under reduced pressure, and recrystallizing the residue from heptane/ethanol (5/1), to obtain 4-(4-(1,3-dioxan-2-ylethyl)cyclohexyl)-1-(2-(4-trifluoromethoxyphenyl)ethyl)cyclohexane (3.25 g, 6.94 mmol). The yield of this product from 4-(4-oxocyclohexyl)-1-(2-(4-trifluoromethoxyphenyl)ethyl)cyclohexane was 44.5%.

(Sixth step)

Formic acid (3.0 g, 66 mmol) and toluene (20 ml) were added to the above 4-(4-(1,3-dioxan-2-ylethyl)cyclohexyl)-1-(2-(4-trifluoromethoxyphenyl)ethyl)cyclohexane (3.25 g, 6.94 mmol), followed by refluxing the mixture for 5 hours,

washing the organic layer successively with a saturated, aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate, and distilling off the solvent, to obtain 3-(4-(4-(2-(4-trifluoromethoxyphenyl)ethyl)-cyclohexyl)cyclohexyl)propanal (2.70 g, 6.58 mmol).
5 Yield: 94.8%.

(Seventh step)

Ethanol (20 ml) was added to the above 3-(4-(4-(2-(4-trifluoromethoxyphenyl)ethyl)cyclohexyl)cyclohexyl)
10 propanal (2.70 g, 6.58 mmol), followed by cooling the mixture down to 0°C in a nitrogen gas atmosphere, adding thereto, sodiumboronhydride (0.13 g, 3.43 mmol) so that the liquid temperature could not exceed 10°C, stirring the mixture at 0°C for 2 hours, extracting the resulting
15 product with ethyl acetate, washing the organic layer successively with a saturated aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate, distilling off the solvent, and recrystallizing the residue from heptane, to obtain 3-(4-(4-(2-(4-trifluoro-
20 methoxyphenyl)ethyl)cyclohexyl)cyclohexyl)propanol (2.10 g, 5.09 mmol). Yield: 77.4%.

(Eighth step)

Dimethoxyethane (20 ml) was added to the above 3-(4-(4-(2-(4-trifluoromethoxyphenyl)ethyl)cyclohexyl)cyclo-
25 hexyl)propanol (2.10 g, 5.09 mmol), followed by dropwise adding thereto diethylaminosulfurtrifluoride (DAST)

(1.73 g, 10.7 mmol), refluxing the mixture for 5 hours, extracting the resulting product with toluene, washing the organic layer successively with a saturated, aqueous solution of sodium bicarbonate and water, drying over
5 magnesium sulfate, distilling off the solvent, purifying the residue according to column chromatography treatment using heptane/toluene (3/1) as a developing solvent, on silica gel, distilling off the solvent, and recrystallizing the residue from ethanol, to isolate only tran-form of
10 1-(2-(4-(4-(3-fluoropropyl)cyclohexyl)cyclohexyl)ethyl)-4-trifluoromethylbenzene (0.88 g, 2.12 mmol). Yield: 41.7%.
SB-N point: 73.8°C, N-I point: 131.8°C.

¹H-NMR (CDC 13) δ (ppm): 7.20 (d, 4H), 4.68 (t, 1H), 4.15 (t, 1H), 2.62 (t, 2H), 1.75-0.99 (m, 26H).

15 Example 8

Preparation of 1-(4-(3-fluoropropyl)cyclohexyl)-3-fluoro-4-trifluoromethoxybenzene (in the formula (1), n=3, ring E = 1,4-cyclohexylene, G, L = covalent bond, ring Z = 3-fluoro-1,4-phenylene, k=1, ℓ =m=0,

20 Q = -O-, Y=CF₃) (Compound No. 13)

(First step)

THF (3 l) was added to 1,3-dioxan-2-ylethyltriphenylphosphinebromide (500 g, 1.09 mol), followed by adding to the mixture, potassium-t-butoxide (122 g, 1.09 mol) at 0°C,
25 stirring the mixture at the same temperature for 3 hours, dropwise adding to the reaction solution, a 700 ml THF

solution of cyclohexanedionemonoethyleneketal (141.9 g, 0.91 mol), stirring the mixture at the same temperature for one hour, further stirring it at room temperature for 3 hours, adding water (2 l) to the reaction solution, 5 extracting the resulting product with ethyl acetate, washing the organic layer successively with a saturated, aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate, distilling off the solvent, purifying the residue according to column chromatography 10 treatment using heptane/ethyl acetate (1/1) as a developing solvent, on silica gel, distilling off the solvent, hydrogenating the residue in the presence of 5% Pd/C catalyst (3.0 g) in an ethanol solution, filtering off the catalyst and distilling off the solvent under reduced 15 pressure, to obtain 4-oxo-1-(1,3-dioxan-2-ylethyl)cyclohexane monoethyleneketal (98 g, 0.38 mol). The yield of this product from cyclohexanedionemonoethyleneketal was 42%.

(Second step)

20 3N HCl (200 ml) and acetone (200 ml) were added to the above 4-oxo-1-(1,3-dioxan-2-ylethyl)cyclohexane ethyleneacetal (60 g, 234 mmol), followed by stirring the mixture for 5 hours, extracting the resulting product with ethyl acetate, washing the organic layer successively 25 with a saturated, aqueous solution of sodium bicarbonate and water, drying over magnesium sulfate, distilling off

the solvent, purifying the residue according to column chromatography treatment using heptane/ethyl acetate (3/2) as a developing solvent, on silica gel, and distilling off the solvent, to obtain 4-oxo-1-(1,3-dioxan-2-ylethyl)cyclo-
5 hexane (35.5 g, 167 mmol). Yield: 71.3%.

(Third step)

60% Sodium hydride (7.12 g, 178 mmol) was added to dimethoxyethane (280 mL) in a nitrogen gas atmosphere, followed by stirring the mixture at room temperature
10 for 10 minutes, dropwise adding to the solution, diethylphosphonoacetic acid ethyl (40.0 g, 178 mmol), stirring the mixture at the same temperature till completion of evolution of hydrogen gas, dropwise adding the above
4-oxo-1-(1,3-dioxan-2-ylethyl)cyclohexane (30.0 g, 141
15 mmol) so that the liquid temperature might not exceed 30°C, stirring the mixture for 30 minutes, adding the reaction solution to water (300 mL), extracting the resulting product with ether, drying the organic layer over magnesium sulfate, distilling off the solvent,
20 hydrogenating the residue (36.6 g) in the presence of 5% Pd/C catalyst (1.8 g), in an ethanol solution, filtering off the catalyst, and distilling off the solvent under reduced catalyst, to obtain ethyl 2-(4-(1,3-dioxan-2-ylethyl)cyclohexylethanoate (30.2 g, 106 mmol). The
25 yield of this product from 4-oxo-1-(1,3-dioxan-2-ylethyl)-cyclohexane was 75.1%.

(Fourth step)

Toluene (450 ml) was added to the above ethyl 2-(4-(1,3-dioxan-2-ylethyl)cyclohexylethanoate (30.2 g, 106 mmol) in a nitrogen gas atmosphere, followed by cooling
5 the mixture down to -65°C, dropwise adding to the solution, a toluene solution of diisobutylaluminum hydride (1.01 mol/l) 120 ml (121 mmol), stirring the mixture at the same temperature for 45 minutes, dropwise adding a saturated aqueous solution of ammonium chloride (33 ml),
10 heating the mixture up to room temperature, adding ether (100 ml) to the reaction solution, stirring the mixture at the temperature for 1.5 hours, adding magnesium sulfate (10 g), stirring the mixture for one hour, filtering off the reaction solution, washing the filtrate with water,
15 drying over magnesium sulfate, and distilling off the solvent, to obtain 2-(4-(1,3-dioxan-2-ylethyl)cyclohexyl)-ethanol (22.0 g, 91.5 mmol). Yield: 86.3%.

(Fifth step)

A Grignard reagent prepared from 3-fluoro-4-trifluoromethoxybromobenzene (9.3 g, 38.7 mmol) and dried Mg (0.97 g
20 39.9 mmol) in a 50 ml ether solvent, was cooled down 0°C, followed by dropwise adding thereto, a 40 ml ether solution of the above 2-(4-(1,3-dioxan-2-ylethyl)cyclohexyl)ethanol (6.3 g, 26.2 mmol), heating the mixture up to room temper-
25 ature, stirring it for 3 hours, adding this reaction

solution to 6N HCl (100 ml), extracting the resulting product with ethyl acetate, washing the extraction solution successively with a saturated aqueous solution of sodium bicarbonate and water, drying over MgSO₄,
5 distilling off the solvent, adding toluene (150 ml) and Amberlist (3.0 g) to the residue, refluxing for 5 hours, while removing water formed by the reaction by means of Dean-Stark, adding trimethylene glycol (1.0 g, 13.1 mmol), further refluxing for one hour, filtering off Amberlist,
10 distilling off the solvent, purifying the residue according to column chromatography treatment using ethyl acetate/toluene (1/2) as a developing solvent, on silica gel, and distilling off the solvent, to isolate 1-(2-(4-(1,3-dioxan-2-ylethyl)cyclohexyl)vinyl-3-fluoro-4-trifluoro-
15 methoxybenzene (5.5 g, 13.7 mmol). The yield of this product from 2-(4-(1,3-dioxan-2-ylethyl)cyclohexyl)ethanol was 52.3%.

(Sixth step)

The above 1-(2-(4-(1,3-dioxan-2-ylethyl)cyclohexyl)-
20 vinyl-3-fluoro-4-trifluoromethoxybenzene (5.5 g, 13.7 mmol) was hydrogenated in the presence of 5% Pd/C catalyst (0.3 g) in an ethanol solution, followed by filtering off the catalyst, distilling off the solvent under reduced pressure, adding formic acid (2.8 g, 60.8 mmol) and
25 toluene (50 ml) to the residue, refluxing the mixture for 5 hours, washing the organic layer successively with

a saturated, aqueous solution of sodium bicarbonate and water, drying over MgSO_4 , and distilling off the solvent, to obtain 3-(4-(2-(3-fluoro-4-trifluoromethoxyphenyl)-ethyl)cyclohexyl)propanal (1.76 g, 5.1 mmol). The yield
5 of this product from 1-(2-(4-(1,3-dioxan-2-ylethyl)cyclohexyl)vinyl-3-fluoro-4-trifluoromethoxybenzene was 37.2%.

(Seventh step)

Ethanol (12 mL) was added to the above 3-(4-(2-(3-fluoro-4-trifluoromethoxyphenyl)ethyl)cyclohexyl)propanal
10 (1.76 g, 5.1 mmol), followed by cooling the mixture down to 0°C in a nitrogen gas atmosphere, adding to the mixture, sodiumboron hydride (0.19 g, 5.0 mmol) so that the liquid temperature might not exceed 10°C, stirring the mixture at 0°C for 2 hours, extracting the resulting product with
15 ethyl acetate, washing the organic layer successively with a saturated, aqueous solution of sodium bicarbonate and water, drying over MgSO_4 , distilling off the solvent, and recrystallizing the residue with heptane, to obtain 3-(4-(2-(3-fluoro-4-trifluoromethoxyphenyl)ethyl)cyclohexyl)-
20 propanol (1.52 g, 4.4 mmol). Yield: 86.3%.

(Eighth step)

Dimethoxyethane (15 mL) was added to the above 3-(4-(2-(3-fluoro-4-trifluoromethoxyphenyl)ethyl)cyclohexyl)-
propanol (1.52 g, 4.4 mmol), followed by dropwise adding
25 DAST (1.40 g, 8.7 mmol), refluxing the mixture for 5 hours, extracting the resulting product with toluene,

washing the organic layer successively with a saturated aqueous solution of sodium bicarbonate and water, drying over MgSO_4 , distilling off the solvent, purifying the residue according to column chromatography treatment using
5 heptane as a developing solvent, on silica gel, distilling off the solvent, and recrystallizing the residue from ethanol, to isolate 1-(3-fluoropropyl)cyclohexyl)-3-fluoro-4-trifluoromethoxybenzene (0.12 g, 0.34 mmol). Yield: 7.7%. Its clearing point measured by PERKIN-ELMER 7 series
10 Thermal Analysis System was -5.89°C .

$^1\text{H-NMR}$ (CDC 13) δ (ppm): 7.26~6.89 (m, 3H),
4.68 (t, 1H), 4.15 (t, 1H), 2.61 (t, 2H),
1.82~0.91 (m, 16H).

Example 9

15 Preparation of 1-(2-(4-(3-fluoropropyl)cyclohexyl)-ethyl)-3,5-difluoro-4-(4-(1,1,2,3,3,3-hexafluoropropoxy)phenyl)benzene (in the formula (1), $n=3$, ring E = 1,4-cyclohexylene, G = covalent bond, L = 3,5-difluoro-1,4-phenylene, ring Z = 1,4-phenylene,
20 $k=1$, $l=0$, $m=0$, Q = -O-, $Y=\text{CF}_2\text{CFHCF}_3$) (Compound No. 74)

(First step)


THF (50 mL) was added to 4-(3,5-difluorophenetyl)-1-(3-fluoropropyl)cyclohexane (5.0 g, 17.6 mmol) prepared in the same manner as the process carried out in Example 1,
25 followed by cooling the mixture down to -50°C in nitrogen gas atmosphere, dropwise adding thereto a hexane solution

(14 ml, 22.8 mmol) of 1.63 N normal butyllithium by means of a syringe, stirring the mixture at the same temperature for one hour, dropwise adding a THF solution (45.6 ml, 22.8 mmol) of 0.5 mol zinc chloride, heating the resulting reaction product up to room temperature, further stirring it for 2 hours, adding to the reaction solution, tetrakis-triphenylphosphinepalladium (500 g) as a catalyst, dropwise adding 4-(1,1,2,3,3,3-hexafluoropropoxy)bromobenzene (7.37 g, 22.8 mmol), refluxing the mixture for 2 hours, adding this reaction solution to cooled 6N HCl (50 ml), extracting the resulting product with toluene, washing the extraction liquid successively with a saturated, aqueous solution of sodium bicarbonate and water, drying over MgSO₄, distilling off the solvent, purifying the residue according to column chromatography treatment using toluene/heptane (1/1) as a developing solvent, on silica gel, and recrystallizing from ethanol, to obtain 1-(2-(4-(3-fluoropropyl)cyclohexyl)ethyl)-3,5-difluoro-4-(1,1,2,3,3,3-hexafluoropropoxy)phenyl)benzene (1.25 g, 2.37 mmol). Yield: 13.5%.

The results of 1H-NMR well supported the structure.

Based upon Examples 1 to 9 and the detailed description of the present invention, it is possible to prepare the following compounds No. 1 to No. 286. In addition, the respective compounds are designated by extracting n, ring E, k, G, l, L, m, ring Z and group Q-Y as parameters

in the compounds expressed by the formula (1). Further, designations H, B, M and D in the columns of ring E, G, L and ring Z among the parameters, respectively represent 1,4-cyclohexylene, 1,4-phenylene,



and the symbol, - in the columns of G and L represents covalent bond.

Parameter No.	n	Ring E	G	L	Ring Z	k	l	m	Q-Y
1	3	B	—	—	B	0	0	0	CF ₃
2	3	B	—	—	B	0	0	0	OCF ₃
3	3	B	—	—	M	0	0	0	CF ₃
4	3	B	—	—	M	0	0	0	OCF ₃
5	3	B	—	—	D	0	0	0	CF ₃
6	3	B	—	—	D	0	0	0	OCF ₃
7	3	B	—	—	B	0	0	0	OCF ₂ CFHCF ₃
8	3	B	—	—	B	0	0	0	CH ₂ CF ₃
9	3	B	—	—	M	0	0	0	OCH ₂ CF ₃
10	3	B	—	—	B	0	0	0	CF ₂ CF ₃
11	5	B	—	—	B	0	0	0	OCF ₃
12	3	H	—	—	B	1	0	0	CF ₃
13	3	H	—	—	M	1	0	0	OCF ₃
14	3	B	—	—	B	1	0	0	CF ₃
15	3	B	—	—	M	1	0	0	OCF ₃
16	2	H	—	H	B	0	0	1	CF ₃
17	2	H	—	H	B	0	0	1	OCF ₃ S _B 69 NI104
18	3	H	—	H	B	0	0	1	CF ₃ S _B I 120
19	3	H	—	H	B	0	0	1	OCF ₃ S _B N 74 NI 132
20	3	H	—	H	D	0	0	1	CF ₃
21	3	H	—	H	M	0	0	1	OCF ₃
22	3	H	—	H	M	0	0	1	F
23	3	H	—	H	D	0	0	1	F
24	3	H	—	H	B	0	0	1	OCF ₂ CFHCF ₃

25	3	H	—	H	M	0	0	1	OCF ₂ CFHCF ₃
26	3	H	—	H	D	0	0	1	OCF ₂ CFHCF ₃
27	3	H	—	H	M	0	0	2	OCF ₃
28	3	H	—	H	D	0	0	2	CF ₃
29	3	H	—	H	M	0	0	1	OCF ₂ H
30	5	H	—	H	M	0	0	1	OCF ₃
31	5	H	—	H	D	0	0	1	CF ₃
32	3	H	—	H	B	1	0	0	CF ₃
33	3	H	—	H	B	1	0	0	OCF ₃
34	3	H	—	H	M	1	0	0	CF ₃
35	3	H	—	H	M	1	0	0	OCF ₃
36	3	H	—	H	D	1	0	0	CF ₃
37	3	H	—	H	D	1	0	0	OCF ₃
38	3	H	—	H	M	1	0	0	F
39	3	H	—	H	D	1	0	0	F
40	3	H	—	H	B	1	0	0	OCF ₂ CFHCF ₃
41	3	H	—	H	M	1	0	0	OCF ₂ CFHCF ₃
42	3	H	—	H	D	1	0	0	OCF ₂ CFHCF ₃
43	3	H	—	H	B	1	0	0	CH ₂ CF ₃
44	3	H	—	H	M	1	0	0	OCH ₂ CF ₃
45	3	H	—	H	B	1	0	0	CF ₂ CF ₃
46	3	H	—	H	B	2	0	0	OCF ₃
47	3	H	—	H	M	2	0	0	OCF ₃
48	5	H	—	H	B	1	0	0	OCF ₃
49	3	H	—	B	B	1	0	0	CF ₃
50	3	H	—	B	B	1	0	0	OCF ₃
51	3	H	—	B	B	1	0	0	OCF ₂ CFHCF ₃

52	3	H	-	B	M	1	0	0	CF ₃
53	3	H	-	B	M	1	0	0	OCF ₃
54	3	H	-	B	M	1	0	0	OCF ₂ CFHCF ₃
55	3	H	-	B	M	1	0	0	F
56	3	H	-	B	D	1	0	0	CF ₃
57	3	H	-	B	D	1	0	0	OCF ₃
58	3	H	-	B	D	1	0	0	OCF ₂ CFHCF ₃
59	3	H	-	B	D	1	0	0	F
60	3	H	-	M	B	1	0	0	CF ₃
61	3	H	-	M	B	1	0	0	OCF ₃
62	3	H	-	M	B	1	0	0	OCF ₂ CFHCF ₃
63	3	H	-	M	B	1	0	0	F
64	3	H	-	M	M	1	0	0	CF ₃
65	3	H	-	M	M	1	0	0	OCF ₃
66	3	H	-	M	M	1	0	0	OCF ₂ CFHCF ₃
67	3	H	-	M	M	1	0	0	F
68	3	H	-	M	D	1	0	0	CF ₃
69	3	H	-	M	D	1	0	0	OCF ₃
70	3	H	-	M	D	1	0	0	OCF ₂ CFHCF ₃
71	3	H	-	M	D	1	0	0	F
72	3	H	-	D	B	1	0	0	CF ₃
73	3	H	-	D	B	1	0	0	OCF ₃
74	3	H	-	D	B	1	0	0	OCF ₂ CFHCF ₃
75	3	H	-	D	B	1	0	0	F
76	3	H	-	D	M	1	0	0	CF ₃
77	3	H	-	D	M	1	0	0	OCF ₃ CI 45 NI (13.6)
78	3	H	-	D	M	1	0	0	OCF ₂ CFHCF ₃
79	3	H	-	D	M	1	0	0	F
80	3	H	-	D	D	1	0	0	CF ₃ C184

81	3	H	-	D	D	1	0	0	OCF ₃
82	3	H	-	D	D	1	0	0	OCF ₂ CFHCF ₃
83	3	H	-	D	D	1	0	0	F
84	3	H	-	D	M	2	0	0	OCF ₃
85	3	H	-	M	D	2	0	0	F
86	3	H	-	M	M	1	0	0	OCF ₂ CF ₂ H
87	3	H	-	M	M	1	0	0	CH ₂ CF ₃
88	3	H	-	D	M	1	0	0	OCH ₂ CF ₃
89	3	H	-	M	B	1	0	0	CF ₂ CF ₃

90	5	H	-	D	B	1	0	0	CF ₃
91	5	H	-	D	M	1	0	0	OCF ₂ CFHCF ₃
92	5	H	-	D	M	1	0	0	F
93	5	H	-	D	M	1	0	0	OCF ₃
94	3	H	-	B	B	0	0	1	CF ₃
95	3	H	-	B	B	0	0	1	OCF ₃
96	3	H	-	B	B	0	0	1	OCF ₂ CFHCF ₃
97	3	H	-	B	M	0	0	1	CF ₃
98	3	H	-	B	M	0	0	1	OCF ₃
99	3	H	-	B	M	0	0	1	OCF ₂ CFHCF ₃
100	3	H	-	B	M	0	0	1	F
101	3	H	-	B	D	0	0	1	CF ₃
102	3	H	-	B	D	0	0	1	OCF ₃
103	3	H	-	B	D	0	0	1	OCF ₂ CFHCF ₃
104	3	H	-	B	D	0	0	1	F
105	3	H	-	M	B	0	0	1	CF ₃
106	3	H	-	M	B	0	0	1	OCF ₃
107	3	H	-	M	B	0	0	1	OCF ₂ CFHCF ₃

108	3	H	-	M	B	0	0	1	F
109	3	H	-	M	M	0	0	1	CF ₃
110	3	H	-	M	M	0	0	1	OCF ₃
111	3	H	-	M	M	0	0	1	OCF ₂ CFHCF ₃
112	3	H	-	M	M	0	0	1	F
113	3	H	-	M	D	0	0	1	CF ₃
114	3	H	-	M	D	0	0	1	OCF ₃
115	3	H	-	M	D	0	0	1	OCF ₂ CFHCF ₃
116	3	H	-	M	D	0	0	1	F
117	3	H	-	D	B	0	0	1	CF ₃
118	3	H	-	D	B	0	0	1	OCF ₃
119	3	H	-	D	B	0	0	1	OCF ₂ CFHCF ₃
120	3	H	-	D	B	0	0	1	F
121	3	H	-	D	M	0	0	1	CF ₃
122	3	H	-	D	M	0	0	1	OCF ₃
123	3	H	-	D	M	0	0	1	OCF ₂ CFHCF ₃
124	3	H	-	D	M	0	0	1	F
125	3	H	-	D	D	0	0	1	CF ₃
126	3	H	-	D	D	0	0	1	OCF ₃
127	3	H	-	D	D	0	0	1	OCF ₂ CFHCF ₃
128	3	H	-	D	D	0	0	1	F
129	3	H	-	M	M	0	0	1	CH ₂ CF ₃
130	3	H	-	D	M	0	0	1	OCH ₂ CF ₃
131	3	H	-	M	B	0	0	1	CF ₂ CF ₃
132	3	H	-	B	B	0	0	2	OCF ₃
133	3	H	-	D	M	0	0	2	OCF ₃
134	5	H	-	D	D	0	0	1	CF ₃

135	5	H	-	M	D	0	0	2	F
136	3	B	-	H	B	0	0	0	CF ₃
137	3	B	-	H	B	0	0	0	OCF ₃
138	3	B	-	H	B	0	0	0	OCF ₂ CFHCF ₃
139	3	M	-	H	B	0	0	0	CF ₃
140	3	M	-	H	B	0	0	0	OCF ₃
141	3	M	-	H	B	0	0	0	OCF ₂ CFHCF ₃
142	3	D	-	H	B	0	0	0	CF ₃
143	3	D	-	H	B	0	0	0	OCF ₃
144	3	D	-	H	B	0	0	0	OCF ₂ CFHCF ₃
145	3	B	-	H	D	0	0	0	CF ₃
146	3	B	-	H	M	0	0	0	OCF ₃
147	3	B	-	H	M	0	0	0	OCF ₂ CFHCF ₃
148	3	B	-	H	D	0	0	0	F
149	5	B	-	H	M	0	0	0	OCF ₃
150	3	B	-	H	B	0	0	1	CF ₃
151	3	B	-	H	B	0	0	1	OCF ₃
152	3	B	-	H	B	0	0	1	OCF ₂ CFHCF ₃
153	3	M	-	H	B	0	0	1	CF ₃
154	3	M	-	H	B	0	0	1	OCF ₃
155	3	M	-	H	B	0	0	1	OCF ₂ CFHCF ₃
156	3	D	-	H	B	0	0	1	CF ₃
157	3	D	-	H	B	0	0	1	OCF ₃
158	3	D	-	H	B	0	0	1	OCF ₂ CFHCF ₃
159	5	B	-	H	D	0	0	1	CF ₃
160	3	B	-	H	M	0	0	1	OCF ₃
161	3	B	-	H	M	0	0	1	OCF ₂ CFHCF ₃

162	3	B	-	H	D	0	0	1	F
163	3	B	-	H	M	0	0	2	OCF ₃
164	5	B	-	H	M	0	0	1	OCF ₃
165	3	B	-	H	B	0	0	1	CF ₃
166	3	B	-	H	B	0	0	1	OCF ₃
167	3	B	-	H	B	0	0	1	OCF ₂ CFHCF ₃
168	3	M	-	H	B	0	0	1	CF ₃
169	3	M	-	H	B	0	0	1	OCF ₃
170	3	M	-	H	B	0	0	1	OCF ₂ CFHCF ₃
171	3	D	-	H	B	0	0	1	CF ₃
172	3	D	-	H	B	0	0	1	OCF ₃
173	3	D	-	H	B	0	0	1	OCF ₂ CFHCF ₃
174	3	B	-	H	D	0	0	1	CF ₃
175	3	B	-	H	M	0	0	1	OCF ₃
176	3	B	-	H	M	0	0	1	OCF ₂ CFHCF ₃
177	3	B	-	H	D	0	0	1	F
178	3	B	-	H	M	0	0	2	OCF ₃
179	5	B	-	H	M	0	0	1	OCF ₃
180	3	B	-	H	B	1	0	1	CF ₃
181	3	B	-	H	B	1	0	1	OCF ₃
182	3	B	-	H	B	1	0	1	OCF ₂ CFHCF ₃
183	3	M	-	H	B	1	0	1	CF ₃
184	3	M	-	H	B	1	0	1	OCF ₃
185	3	M	-	H	B	1	0	1	OCF ₂ CFHCF ₃
186	3	D	-	H	B	1	0	1	CF ₃
187	3	D	-	H	B	1	0	1	OCF ₃
188	3	D	-	H	B	1	0	1	OCF ₂ CFHCF ₃

189	3	B	-	H	D	1	0	1	CF ₃
190	3	B	-	H	M	1	0	1	OCF ₃
191	3	B	-	H	M	1	0	1	OCF ₂ CFHCF ₃
192	3	B	-	H	D	1	0	1	F
193	3	B	-	H	M	1	0	2	OCF ₃
194	5	B	-	H	M	1	0	1	OCF ₃
195	3	H	-	H	B	1	0	1	CF ₃
196	3	H	-	H	M	1	0	1	OCF ₃
197	3	H	-	H	D	1	0	1	F
198	5	H	-	H	B	1	0	1	CF ₃
199	3	B	-	B	B	0	0	0	CF ₃
200	3	B	-	M	B	0	0	0	OCF ₃
201	3	B	-	B	B	0	0	0	OCF ₃
202	3	B	-	B	M	0	0	0	OCF ₃
203	5	B	-	B	B	0	0	0	OCF ₃
204	3	B	-	B	B	1	0	0	CF ₃
205	3	B	-	M	B	1	0	0	OCF ₃
206	3	B	-	B	B	1	0	0	OCF ₃
207	3	B	-	B	M	1	0	0	OCF ₃
208	5	B	-	B	B	1	0	0	OCF ₃
209	3	B	-	B	B	0	0	1	CF ₃
210	3	B	-	M	B	0	0	1	OCF ₃
211	3	B	-	B	B	0	0	1	OCF ₃
212	3	B	-	B	M	0	0	1	OCF ₃
213	5	B	-	B	B	0	0	1	OCF ₃

214	3	B	-	B	B	1	0	1	CF ₃
215	3	B	-	M	B	1	0	1	OCF ₃
216	3	B	-	B	B	1	0	1	OCF ₃
217	3	B	-	B	M	1	0	1	OCF ₃
218	5	B	-	B	B	1	0	1	OCF ₃
219	3	H	H	H	B	0	0	0	CF ₃
220	3	H	H	H	B	0	0	0	OCF ₃
221	3	H	H	H	B	0	0	0	OCF ₂ CFHCF ₃
222	3	H	H	H	M	0	0	0	CF ₃
223	3	H	H	H	M	0	0	0	OCF ₃
224	3	H	H	H	M	0	0	0	OCF ₂ CFHCF ₃
225	3	H	H	H	M	0	0	0	F
226	3	H	H	H	D	0	0	0	CF ₃
227	3	H	H	H	D	0	0	0	OCF ₃
228	3	H	H	H	D	0	0	0	OCF ₂ CFHCF ₃
229	3	H	H	H	D	0	0	0	F
230	3	H	H	H	B	0	0	0	CH ₂ CF ₃
231	3	H	H	H	B	0	0	0	OCH ₂ CF ₃
232	3	H	H	H	B	0	0	0	CF ₂ CF ₃
233	5	H	H	H	M	0	0	0	OCF ₃
234	3	H	H	H	M	1	0	0	OCF ₃
235	3	H	H	H	M	0	1	0	OCF ₃
236	3	H	H	H	M	0	0	1	OCF ₃
237	3	H	H	B	B	0	0	0	CF ₃
238	3	H	H	B	M	0	0	0	OCF ₃

239	3	H	H	M	M	0	0	0	OCF ₃
240	3	H	H	D	M	0	0	0	OCF ₃ CN79 NI225
241	3	H	H	D	B	0	0	0	OCF ₃
242	3	H	H	M	D	0	0	0	OCF ₃
243	3	H	H	B	M	0	0	0	OCF ₂ CFHCF ₃
244	3	H	H	M	M	0	0	0	OCF ₂ CFHCF ₃
245	3	H	H	D	M	0	0	0	OCF ₂ CFHCF ₃
246	3	H	H	M	D	0	0	0	F
247	5	H	H	D	B	0	0	0	OCF ₃
248	3	H	H	D	M	1	0	0	OCF ₃
249	3	H	H	D	M	0	1	0	OCF ₃
250	3	H	H	D	M	0	0	1	OCF ₃
251	3	H	B	B	B	0	0	0	CF ₃
252	3	H	B	B	B	0	0	0	OCF ₃
253	3	H	B	B	M	0	0	0	OCF ₃
254	3	H	B	B	B	1	0	0	OCF ₃
255	3	H	B	B	B	0	1	0	OCF ₃
256	3	H	B	B	B	0	0	1	OCF ₃
257	3	B	B	B	B	0	0	0	CF ₃
258	3	B	B	B	B	0	0	0	OCF ₃
259	3	B	B	B	M	0	0	0	OCF ₃
260	3	B	B	B	B	1	0	0	OCF ₃
261	3	B	B	B	B	0	1	0	OCF ₃
262	3	B	B	B	B	0	0	1	OCF ₃
263	3	H	B	H	B	0	0	0	CF ₃

264	3	H	B	H	B	0	0	0	OCF ₃
265	3	H	B	H	M	0	0	0	OCF ₃
266	3	H	B	H	B	1	0	0	OCF ₃
267	3	H	B	H	B	0	1	0	OCF ₃
268	3	H	B	H	B	0	0	1	OCF ₃
269	3	B	B	H	B	0	0	0	CF ₃
270	3	B	B	H	B	0	0	0	OCF ₃
271	3	B	B	H	M	0	0	0	OCF ₃
272	3	B	B	H	B	1	0	0	OCF ₃
273	3	B	B	H	B	0	1	0	OCF ₃
274	3	B	B	H	B	0	0	1	OCF ₃
275	3	B	H	B	B	0	0	0	CF ₃
276	3	B	H	B	B	0	0	0	OCF ₃
277	3	B	H	B	M	0	0	0	OCF ₃
278	3	B	H	B	B	1	0	0	OCF ₃
279	3	B	H	B	B	0	1	0	OCF ₃
280	3	B	H	B	B	0	0	1	OCF ₃
281	3	B	H	H	B	0	0	0	CF ₃
282	3	B	H	H	B	0	0	0	OCF ₃
283	3	B	H	H	M	0	0	0	OCF ₃
284	3	B	H	H	B	1	0	0	OCF ₃
285	3	B	H	H	B	0	1	0	OCF ₃
286	3	B	H	H	B	0	0	1	OCF ₃

Exempl 10 (Use example 1)

A liquid crystal composition (A1) consisting of

	4-(4-propylcyclohexyl)benzonitrile	24%
	4-(4-pentylcyclohexyl)benzonitrile	36%
5	4-(4-heptylcyclohexyl)benzonitrile	25% and
	4-(4-pentylphenyl)benzonitrile	15%

was prepared. This nematic liquid crystal composition exhibited a clearing point of 72.4°C, a threshold voltage in a cell thickness of 9 μm , of 1.78V, a $\Delta\epsilon$ of 11.0, a Δn of 0.137 and a viscosity at 20°C, of 27.0 mPa·S.

10 With this liquid crystal composition (85%) was blended 1-(2-(4-(3-fluoropropyl)cyclohexyl)ethyl)-3,5-difluoro-4-(3,5-difluoro-4-trifluoromethylphenyl)benzene of Example 1 of the present invention (15%), to prepare a liquid
15 crystal composition (B1). This composition exhibited a threshold voltage in a cell thickness of 8.8 μm , of 1.39 V, a $\Delta\epsilon$ of 12.0, a Δn of 0.131, and an elastic constant of K_{33}/K_{11} , of 2.13. Further, the extrapolated values calculated from the blending ratios were respec-
20 tively a $\Delta\epsilon$ of 17.7 and a Δn of 0.097. This composition was allowed to stand for 60 days in a breezer of -20°C, but no crystal deposition was observed.

Example 11 (Use example 2)

A liquid crystal composition (A2) consisting of

25	4-(4-propylcyclohexyl)benzonitrile	30%
	4-(4-pentylcyclohexyl)benzonitrile	40% and
	4-(4-heptylcyclohexyl)benzonitrile	30%

was prepared. This nematic liquid crystal composition exhibited a clearing point of 52.3°C, a threshold voltage in a cell thickness of 9 μm , of 1.60 V, a $\Delta\epsilon$ of 10.7 a Δn of 0.119, and a viscosity at 20°C, of 21.7 Pa·S.

- 5 With this liquid crystal composition (85%) was blended 1-(2-(4-(4-(2-fluoroethyl)cyclohexyl)cyclohexyl)ethyl-4-trifluoromethoxybenzene (a compound of Example 2 of the present invention) (15%), to prepare a liquid crystal composition (B2). This composition exhibited a clearing
10 point of 56.1°C, a threshold voltage in a cell thickness, of 8.8 μm , of 1.55 V, a $\Delta\epsilon$ of 10.2, a Δn of 0.112 and a viscosity at 20°C, of 22.3 mPa·S. Further, the extrapolated values calculated from the blending ratios were respectively a clearing point of 77.6°C, a $\Delta\epsilon$ of 7.4,
15 a Δn of 0.072, and a viscosity at 20°C, of 25.7 mPa·S. Further, this composition was allowed to stand 60 days in a freezer at -20°C, but no crystal deposition was observed.

Example 12 (Use example 3)

With the above liquid crystal composition (A2) (85%) was blended 1-(1-(4-(3-fluoropropyl)cyclohexyl)ethyl)-3,5-difluoro-4-(3-fluoro-4-trifluoromethoxyphenyl)benzene of a compound of Example 4 (15%), to prepare a liquid crystal composition (B3). This composition exhibited a clearing point of 64.5°C, a threshold voltage in a cell thickness of 8.8 μm , of 1.52 V, a $\Delta\epsilon$ of 11.1, a Δn of 0.122, and a viscosity at 20°C, 27.8 mPa·S. Further, the extrapolated values calculated from the blending ratios were respectively a clearing point of 133.6°C, a $\Delta\epsilon$ of 13.4, a Δn of 0.139, and a viscosity at 20°C, of 62.4 mPa·S. Further, this composition was allowed to stand for 60 days in a freezer at -20°C, but no crystal deposition was observed.

15 Example 13 (Use example 4)

With the above liquid crystal composition (A1) (85%) was blended 1-(2-(4-(3-fluoropropyl)cyclohexyl)ethyl)-3,5-difluoro-4-(3-fluoro-4-trifluoromethoxyphenyl)benzene of a compound of Example 5 (15%), to prepare a liquid crystal composition (B4). This composition exhibited a clearing point of 63.3°C, a threshold voltage in a cell thickness of 8.8 μm , of 1.47 V, a $\Delta\epsilon$ of 11.4, a Δn of

0.130, and a viscosity at 20°C, of 34.1 mPa·S. Further, the extrapolated values calculated from the blending ratios were respectively a clearing point of 15.7°C, a $\Delta\epsilon$ of 13.7, a Δn of 0.090, and a viscosity at 20°C, of 67.5 mPa·S. Further, this composition was allowed to stand for 60 days in a freezer at -20°C, but no crystal deposition was observed.

Example 14 (Use example 5)

With the above liquid crystal composition (A1) (85%) was blended 1-(2-(4-(4-(3-fluoropropyl)cyclohexyl)cyclohexyl)ethyl)-4-trifluoromethylbenzene of a compound of Example 6 of the present invention (15%), to prepare a liquid crystal composition (B5). This composition exhibited a clearing point of 74.9°C, a threshold voltage in a cell thickness of 8.9 μm , of 1.79 V, a $\Delta\epsilon$ of 10.6, a Δn of 0.130 and a viscosity at 20°C, of 29.7 mPa·S. Further, the extrapolated values calculated from the blending ratios were respectively a clearing point of 93.0°C, a $\Delta\epsilon$ of 8.3, a Δn of 0.090 and a viscosity at 20°C, of 46.7 mPa·S. Further, this composition was allowed to stand for 60 days in a freezer at -20°C, but no crystal deposition was observed.

Example 15 (Use example 6)

With the above composition (A1) (85%) was blended 1-(2-(4-(4-(3-fluoropropyl)cyclohexyl)cyclohexyl)ethyl)-4-trifluoromethoxybenzene of a compound of Example 7 (15%),

to prepare a liquid crystal composition (B6). This composition exhibited a clearing point of 77.1°C, a threshold voltage in a cell thickness of 8.7 μm , of 1.78 V, a $\Delta\epsilon$ of 10.2, a Δn of 0.130 and a viscosity at 20°C, of 27.8 mPa·S.

5 Further, the extrapolated values calculated from the blending ratios were respectively a clearing point of 107.7°C, a $\Delta\epsilon$ of 5.7, a Δn of 0.090 and a viscosity at 20°C, of 32.9 mPa·S. Further, this composition was allowed to stand for 60 days in a freezer at -20°C, but no crystal

10 deposition was observed.

Example 16 (Use example 7)

With the above liquid crystal composition (A1) (85%) was blended 1-(3-fluoropropyl)cyclohexyl)-3-fluoro-4-trifluoromethoxybenzene of a compound of Example 8 of

15 the present invention (B7) (15%), to prepare a liquid crystal composition (B7). This composition exhibited a $\Delta\epsilon$ of 9.9. Further, the $\Delta\epsilon$ calculated from the blending ratios was 3.7. Further, this composition was allowed to stand for 60 days in a freezer at -20°C, but no crystal

20 deposition was observed.

Example 17 (Comparative example 1)

With the above liquid crystal composition (A2) (50%) was blended a compound, 1-(4-(2-fluoroethyl)cyclohexyl)-4-(3,4,5-trifluorophenyl)benzene (50%), disclosed in

25 Japanese patent application Hyo No. Hei 04-506817, formula (5), to prepare a liquid crystal composition (B4).

On the other hand, with the liquid crystal composition (A2) (50%) was blended a compound of Example 2, 1-(4-(2-fluoroethyl)cyclohexyl)cyclohexyl)-4-(2-(4-trifluoromethoxyphenyl)ethyl)cyclohexane (50%), to prepare

5 a liquid crystal composition (B5). These liquid crystal compositions B4 and B5 were respectively allowed to stand for 60 days in a freezer at -20°C. In the case of B5, no crystal deposition was observed, but in the case of B4, crystal deposition was observed.

10 Example 18 (Comparative example 2)

A liquid crystal composition (A3) consisting of the following compounds were prepared:

	1-(4-(4-ethylcyclohexyl)cyclohexyl)-3,4-difluorobenzene	16.67%
15	1-(4-(4-propylcyclohexyl)cyclohexyl)-3,4-difluorobenzene	16.67%
	1-(4-(4-pentylcyclohexyl)cyclohexyl)-3,4-difluorobenzene	16.66%
	1-(4-(2-(4-ethylcyclohexyl)ethyl)cyclohexyl)-3,4-difluorobenzene	10.00%
20	1-(4-(2-(4-propylcyclohexyl)ethyl)cyclohexyl)-3,4-difluorobenzene	5.00%
	1-(4-(2-(4-pentylcyclohexyl)ethyl)cyclohexyl)-3,4-difluorobenzene	10.00%
25	1-(4-(4-ethylcyclohexyl)phenyl)-3,4-difluorobenzene	6.25%

1-(4-(4-propylcyclohexyl)phenyl)-3,4-

difluorobenzene

6.25%

1-(4-(4-pentylcyclohexyl)phenyl)-3,4-

difluorobenzene

12.50%.

5 With this liquid crystal composition (A3) (57%) was blended
a compound, (1-(2-(4-(4-propylcyclohexyl)cyclohexyl)ethyl)-
4-trifluoromethoxybenzene) (43%), to prepare a liquid
crystal composition (B9). On the other hand, with the
liquid crystal composition (A2) (50%) was blended (1-(2-
10 (4-(4-(3-fluoropropyl)cyclohexyl)cyclohexyl)ethyl)-4-
trifluoromethoxybenzene) (43%) of a compound of Example 7,
to prepare a liquid crystal composition (B10). These
liquid crystal compositions B9 and B10 were respectively
allowed to stand for 18 hours in a freezer at -40°C. In
15 the case of B10, no crystal deposition was observed, but
in the case of B9, crystal deposition was observed.

The compounds of the present invention have a very
large $\Delta\epsilon$ exceeding 20 in certain cases, and further,
20 overcome an inferior compatibility and a narrow liquid
crystal range which have been so far a problem common
to the compounds having a high $\Delta\epsilon$, and still further have
a low viscosity and a sufficient, chemical stability.

The liquid crystal compositions containing these
25 compounds as components are chemically very stable and
exhibit a large $\Delta\epsilon$, and further, have superior

characteristics of exhibiting nematic phase within a broad and practical temperature range, reflected from the superior compatibility and broad liquid crystal range of the compounds and the low viscosity thereof.

- 5 Thus, the compositions obtained by using these compounds are very useful when liquid crystal display elements are constructed.

For exmaple, as compared with the compound (1), compounds No. 17 and No. 19 both have the same extents
10 of the specific resistance value and the compatibility, but have a large $\Delta\epsilon$ and a far elevated clearing point, and on the other hand, a far reduced viscosity, and as compared with the compound (5), they have the same extents of the clearing point, viscosity, $\Delta\epsilon$ and Δn , but have a far
15 superior compatibility; hence they are useful as a composition component of TFT display element. Further, compounds No. 18, No. 70 and No. 80 each exhibit a large $\Delta\epsilon$, a superior compatibility, a large Δn and a high specific resistance value; hence they are useful as the composition
20 component of TFT display element. Compound No. 240 exhibits a large $\Delta\epsilon$, a large Δn and a property of far elevating the clearing point; hence it is very useful as a composition component.


Compound No. 74 has a large $\Delta\epsilon$ and a very large Δn
25 and a superior compatibility; hence it is useful as a composition component of TFT display element.

Bicyclic compound No. 13 has a somewhat low clearing point, but has a large $\Delta\epsilon$ and a very low viscosity; hence it is useful as a composition component of TFT display element.

WHAT WE CLAIM IS:



1. A liquid crystalline compound expressed by the formula (I):




wherein n represents an integer of 1 to 10; k , l and m each independently represent an integer of 0 to 2; E represents 1,4-cyclohexylene group or 1,4-phenylene group wherein one or more hydrogen atoms on a six-membered ring may be replaced by fluorine atom(s); G and L each independently represent a covalent bond or 1,4-cyclohexylene group or 1,4-phenylene group wherein one or more hydrogen atoms may be replaced by fluorine atom(s), and in the case of covalent bond, G is preferential; Z represents 1,4-phenylene group wherein one or more hydrogen atoms on the 1,4-phenylene group may be replaced by fluorine atom(s); Q represents a covalent bond or $-O-$; Y represents a fluoroalkyl group of 1 to 3 carbon atoms or fluorine atom; and when E represents 1,4-cyclohexylene group and at least one of G and L represents a covalent bond, $k+l+m \neq 0$ and when Q represents $-O-$, Y does not represent fluorine atom.




2. A liquid crystalline compound according to claim 1, wherein k, l and m each independently represent 0 or 1, and E represents 1,4-phenylene group of fluorine-substituted 1,4-phenylene group.
- 5 3. A liquid crystalline compound according to claim 1, wherein k, l and m each independently represent 0 or 1 and E represents 1,4-cyclohexylene group.
4. A liquid crystalline compound according to claim 3, wherein k, l and m each are zero; G represents a covalent
10 bond; and L represents 1,4-cyclohexylene group, 1,4-phenylene group or fluorine-substituted 1,4-phenylene group.
5. A liquid crystalline compound according to claim 4, wherein L represents 1,4-cyclohexylene group.
- 15 6. A liquid crystalline compound according to claim 4, wherein L represents 1,4-phenylene group or fluorine-substituted 1,4-phenylene group.
7. A liquid crystalline compound according to claim 3, wherein k and l each represent 0; m represents 1;
20 G represents a covalent bond; and L represents 1,4-cyclohexylene group, 1,4-phenylene group or fluorine-substituted 1,4-phenylene group.
8. A liquid crystalline compound according to claim 7, wherein L represents 1,4-cyclohexylene group.
- 25 9. A liquid crystalline compound according to claim 7, wherein L represents 1,4-phenylene group or fluorine-substituted 1,4-phenylene group.




10. A liquid crystalline compound according to claim 3,
wherein k and m each represent 1; l represents 0;
G represents a covalent bond; and L represents 1,4-
cyclohexylene group or fluorine-substituted 1,4-
phenylene group.
11. A liquid crystalline compound according to claim 3,
wherein k represents 1; l and m each represent 0; and
G and L each represent a covalent bond.
12. A liquid crystalline compound according to claim 1,
wherein G and L each independently represent 1,4-cyclo-
hexylene group, 1,4-phenylene group or fluorine-substituted
phenylene group.
13. A liquid crystal composition containing at least
one of liquid crystalline compounds according to claims 1
to 12.
14. A liquid crystal composition characterized by
containing at least one member of the liquid crystalline
compounds set forth in either one of claims 1 to 12,
as a first component, and at least one member of compounds
selected from the group consisting of compounds expressed
by the following formulas (II), (III) and (IV), as
a second component:




(II)



(III)




- wherein R_1 represents an alkyl group of 1 to 10 carbon atoms; V represents F , Cl , CF_3 , OCF_3 , OCF_2H or an alkyl group of 1 to 10 carbon atoms; L_1 , L_2 , L_3 and L_4 each independently represent H or F ; Z_1 and Z_2 each independently represent $-(CH_2)_2-$, $-CH=CH-$ or a covalent bond; ring A represents trans-1,4-cyclohexylene group or 1,4-phenylene group; a represents 1 or 2; and b represents 0 or 1).
15. A liquid crystal composition characterized by containing at least one member of the liquid crystalline compounds set forth in either one of claims 1 to 12, as a first component, and at least one member of compounds selected from the group consisting of compounds expressed by the following formulas (V), (VI), (VII), (VIII) and (IX), as a second component:




- wherein R_2 represents F , an alkyl group of 1 to 10 carbon atoms or an alkenyl group of 2 to 10 carbon atoms, and in either of the groups, an optional methylene group $(-CH_2-)$ in the groups may be replaced by oxygen atom $(-O-)$,



but two or more methylene groups therein are not continuously replaced by oxygen atom; Z_3 represents $-(CH_2)_2-$, $-COO-$ or a covalent bond; L_5 and L_6 each independently represent H or F; D_1 represents trans-1,4-cyclohexylene group, 1,4-phenylene group or 1,3-dioxane-2,5-diyl group; ring U represents trans-1,4-cyclohexylene group or 1,4-phenylene group; and c and d each independently represent 0 or 1,



wherein R_3 represents an alkyl group of 1 to 10 carbon atoms; L_7 represents H or F; and e represents 0 or 1,




wherein R_4 represents an alkyl group of 1 to 10 carbon atoms; I represents trans-1,4-cyclohexylene group or 1,4-phenylene group; L_8 and L_9 each independently represent H or F; Z_4 represents $-COO-$ or a covalent bond; Z_5 represents $-COO-$ or $-C\equiv C-$; and f and g each independently 0 or 1,



wherein R_5 and R_6 each independently represent an alkyl group, an alkoxy group or an alkoxymethyl group, each



of 1 to 10 carbon atoms; W represents trans-1,4-cyclohexylene group, 1,4-phenylene group or 1,3-pyrimidine-2,5-diyl group; K represents trans-1,4-cyclohexylene group or 1,4-phenylene group; and Z₆ represents -C≡C-, -COO-,
 5 -(CH₂)₂- or a covalent bond,



wherein R₇ represents an alkyl group or an alkoxy group each of 1 to 10 carbon atoms; R₈ represents an alkyl group of 1 to 10 carbon atoms, and an optional methylene group (-CH₂-) in R₈ may be replaced by oxygen atom (-O-), but
 10 two or more methylene groups are not continuously replaced by oxygen atom (-O-); M represents trans-1,4-cyclohexylene group or 1,3-pyrimidine-2,5-diyl group; rings N and P each independently represent trans-1,4-
 15 cyclohexylene group or 1,4-phenylene group; Z₇ represents -COO-, -(CH₂)₂-, -CH=CH- or a covalent bond; Z₈ represents -C≡C-, -COO- or a covalent bond; h represents 0 or 1; and L₁₀ represents H or F.

16. A liquid crystal composition characterized by
 20 containing at least one member of the liquid crystalline compounds set forth in either one of items (1) to (12), as a first component, and at least one member of compounds selected from the group consisting of compounds



expressed by the formulas (II), (III) and (IV), as a part of the second component, and at least one member of compounds selected from the group consisting of compounds expressed by the formulas (V), (VI), (VII), (VIII) and
5 (IX), as another part of the second component.

17. A liquid crystal display element constituted by using either one of the liquid crystal compositions set forth in either one of the claims 13 to 16.