

Claims

1. Catalytically active material, comprising grains of non-graphitizing carbon with cobalt nanoparticles dispersed therein,
- wherein
- d_p , the average diameter of cobalt nanoparticles in the non-graphitizing carbon grains, is in the range of 1 nm to 20 nm,
- D , the average distance between cobalt nanoparticles in the non-graphitizing carbon grains, is in the range of 2 nm to 150 nm, and
- ω , the combined total mass fraction of metal in the non-graphitizing carbon grains, is in the range of 30 wt% to 70 wt% of the total mass of the non-graphitizing carbon grains,
- wherein d_p and D are measured by TGZ-TEM as described herein,
- and wherein
- d_p , D and ω conform to the following relation:
- $$4.5 d_p / \omega > D \geq 0.25 d_p / \omega.$$
2. Material according to claim 1, wherein the non-graphitizing carbon grains exhibit the following particle size distribution: $d_{10} = 5 \mu\text{m}$, $d_{50} = 40 \mu\text{m}$, $d_{90} = 150 \mu\text{m}$
3. Material according to any one of claims 1 to 2, wherein the total mass fraction of nitrogen in the non-graphitizing carbon grains is less than 1 wt% of the total mass of the non-graphitizing carbon grains.
4. Material according to any one of claims 1 to 3, wherein d_p is in the range of 1 nm to 10 nm.
5. Material according to any one of claims 1 to 4, wherein d_p is in the range of 2 nm to 6 nm.
6. Material according to any one of claims 1 to 5, wherein the material has been doped with dopant metal,
- and wherein the dopant metal is selected from Mn, Cu or mixtures thereof,

and wherein the non-graphitizing carbon grains exhibit a molar ratio $RDM = n(\text{cobalt}) : n(\text{dopant metal})$ in the range of 2 to 15.

- 5 7. Material according to any one of claims 1 to 6, wherein the total mass fraction of Cu is less than 10^{-4} wt% of the total mass of the non-graphitizing carbon grains.
8. Process for the manufacture of material according to any one of claims 1 to 7, comprising the following steps:
- 10 (a) providing an aqueous solution comprising metal precursor and organic carbon source,
- wherein the metal precursor comprises one or a combination of more than one
- 15 organic, at least partially water soluble, salts of cobalt, and
- wherein the organic carbon source is one or a combination of more than one saturated, aliphatic di-, tri-, or polycarboxylic acids,
- 20 (b) spray drying or freeze drying the aqueous solution of metal precursor and organic carbon source and, thus, obtaining intermediate product P,
- (c) thermo-treating intermediate product P at a temperature in the range from 200 °C to 380 °C.
- 25 9. Process according to claim 8, wherein the organic carbon source is selected from malonic acid, tartaric acid, citric acid and mixtures thereof.
10. Process according to any one of claims 8 to 9, wherein intermediate product P is thermo-treated at a temperature in the range from 255 °C to 375 °C for 1 to 4 hours.
- 30 11. Process according to any one of claims 8 to 10, wherein intermediate product P is thermo-treated at a temperature in the range from 300 °C to 350 °C for 1 to 4 hours
- 35 12. Use of material according to any one of claims 1 to 7 as a catalyst.
13. Use according to claim 12, wherein the catalyst is a catalyst for the hydrogenation of organic compounds, the reductive amination of carbonyl compounds and/or the hydroformylation of organic compounds.

40

14. Use according to claim 12 wherein the catalyst is a catalyst for the conversion of carbon monoxide, carbon dioxide or mixtures thereof with hydrogen, to alcohols, alkenes, alkanes or mixtures thereof.