



(43) International Publication Date
24 April 2014 (24.04.2014)

(10) International Publication Number
WO 2014/060260 A1

- (51) International Patent Classification:
C01B 39/02 (2006.01) *B01J 21/00* (2006.01)
- (21) International Application Number:
PCT/EP2013/071041
- (22) International Filing Date:
9 October 2013 (09.10.2013)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
12189040.4 18 October 2012 (18.10.2012) EP
- (71) Applicant: **BASF SE** [DE/DE]; 67056 Ludwigshafen (DE).
- (72) Inventors: **MAURER, Stefan**; Emil-Nolde-Strasse 6, 67061 Ludwigshafen (DE). **ÖZKIRIM, Faruk**; Ellerstadterstrasse 43, 67071 Ludwigshafen (DE). **PAR-VULESCU, Andrei-Nicolae**; Theaterstrasse 14, 69117 Heidelberg (DE). **YANG, Jeff**; Maximilianstrasse 6, 68165 Mannheim (DE). **MÜLLER, Ulrich**; Am Stecken 14a, 67435 Neustadt (DE).
- (74) Agent: **ALTMANN, Andreas**; Herzog Fiesser & Partner, Patent Attorneys, Isartorplatz 1, 80331 Munich (DE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: POST-TREATMENT OF A ZEOLITIC MATERIAL

(57) Abstract: A process for the post-treatment of a zeolitic material, the process comprising (i) providing a zeolitic material, wherein the framework structure of the zeolitic material comprises YO_2 and X_2O_3 , wherein Y is a tetravalent element and X is a trivalent element; (ii) subjecting the zeolitic material provided in (i) to a method comprising (a) treating the zeolitic material with an aqueous solution having a pH of at most 5, (b) treating the zeolitic material obtained from (a) with a liquid aqueous system having a pH in the range of 5.5 to 8 and a temperature of at least 75 °C; wherein in (ii) and after (b), the zeolitic material is optionally subjected to at least one further treatment according to (a) and/or at least one further treatment according to (b).



WO 2014/060260 A1