

Description

The invention relates to a steam iron comprising a steam chamber which is provided with a hydrophilic coating. The invention further relates to a method of providing a hydrophilic coating in the steam chamber of a steam iron.

Present day steam irons comprise a water reservoir from which water is fed at an adjustable and regular rate to the steam chamber. Said steam chamber is partly located in the part of the steam iron to be heated, namely the soleplate of the iron. In the steam chamber the water is converted into steam after which said steam is fed outwards through steam ports in the soleplate of the iron.

In general, the steam chamber is bounded by metal walls which are generally composed of aluminium. When water is fed from the reservoir directly onto the hot metal bottom of the steam chamber the so-called "Leiden-frost" effect occurs: the water is not optimally distributed over the bottom surface and remains bouncing about on the surface in the form of large drops; it is even possible for these drops to fly off the surface, pass through the steam chamber and leave the iron through the steam ports. In such a situation, the formation of steam is not optimal. In order to preclude this undesirable effect a hydrophilic and somewhat heat-insulating coating is customarily applied to at least the bottom of the steam chamber. By virtue of the hydrophilic character of the steam chamber coating the water introduced spreads readily over the bottom of the steam chamber. The somewhat heatinsulating character of the layer ensures a gradual heat transfer from the soleplate of the iron to the water introduced. Both properties of the steam chamber coating contribute to the water being regularly and efficiently converted into steam.

A steam iron of the type described in the opening paragraph is known from, inter alia, British Patent Specification GB 773,741. The steam chamber coating used in said Specification is mainly composed of silica and fillers which are provided on the bottom of the steam chamber from an alkaline colloidal suspension, preferably, by means of a spraying process. According to said patent Specification, a steam chamber coating having optimum properties is obtained when the colloidal suspension is stabilised with NaOH in the range from pH 9.5 - 10.5.

Applicants have ascertained that the known steam iron has disadvantages. For example, it has been found that corrosion problems occur, in particular, in an environment having a high degree of humidity and a relatively high temperature. This causes flakes to break away from the steam chamber coating which can leave the iron through the

steam ports. This situation is found very disadvantageous.

One of the objects of the invention is to overcome the above-mentioned corrosion problem. For this purpose, it is an object of the invention to provide, in particular, a steam iron which is provided with a steam chamber coating which is not sensitive to corrosion in a warm and humid environment. A further object is to provide an inventive method of providing such a corrosion resistant coating in the steam chamber of a steam iron.

These and other objects are achieved by, a steam iron of the type described in the opening paragraph, which is characterized according to the invention in that the hydrophilic steam chamber coating comprises an acid phosphate, so that the coating is acid-resistant. In experiments leading to the invention it has been found that the corrosion problem of the known steam chamber coating is caused by a reaction of the alkaline stabiliser, for example the NaOH present in the silica layer, with the material of the soleplate of the iron, which is generally composed of aluminium. So far the exact mechanism is not clear. It has further been found that the known steam chamber coating is sensitive to acid attack. This acid may originate from the seals used for the steam chamber, which are customarily composed of a elastic silicone rubber in which a small quantity of acetic acid is present. This acid may escape from the seal, in particular in a warm environment, and subsequently bring about corrosion. Prolonged use of a diluted acetic acid solution as a decalcifier will considerably increase the corrosion problem. On the basis of the above experimental results Applicants have gained the insight that the presence of an acid-resistant steam chamber layer is of essential importance to overcome the above-mentioned corrosion problems.

According to the invention, the hydrophilic steam chamber coating comprises an acid phosphate compound. This is to be understood to mean a metal-phosphate compound in which the phosphate is at least singly protonated (HPO_4^{2-} or H_2PO_4^-). Examples of such compounds are MgHPO_4 and $\text{Zn}(\text{H}_2\text{PO}_4)_2$. It has been found that the presence of such an acid phosphate compound in the steam chamber coating obviates the corrosion problem to a large degree. As will be explained hereinafter, such an acid phosphate compound can be used as the stabiliser of an acid colloidal silica-suspension.

It has been demonstrated that in this respect aluminium-phosphate compounds, more particularly aluminium triphosphate ($\text{Al}(\text{H}_2\text{PO}_4)_3$) can be applied very advantageously. These compounds which are used as acid stabilisers of a colloidal silica suspension are thickened from the suspension, partly along with the silica, in the steam

chamber coating in which they then serve as binders. It has been found that the presence of aluminium phosphate in the steam chamber coating ensures that said coating is particularly insoluble in water and also very acid resistant.

The invention also relates to a method of providing a hydrophilic coating in the steam chamber of a steam iron, whereby a colloidal suspension comprising alumina, silica or magnesia, or mixtures thereof is introduced into the steam chamber and is thickened to form a hydrophilic steam chamber coating. Said method is characterized in that the suspension is acidified to a pH value of 1-3 by means of an acid phosphate compound which functions as an acid stabiliser. The suspension may alternatively comprise further fillers. A preferred embodiment of the method according to the invention is characterized in that an aluminium phosphate, in particular $\text{Al}(\text{H}_2\text{PO}_4)_3$, is used as the acid stabiliser.

The invention will be explained in greater detail by means of exemplary embodiments and with reference to the accompanying drawings, in which

Fig. 1 is a partly cross-sectional and partly elevational view of a steam iron according to the invention.

Fig. 2 is a top view of the soleplate of the steam iron according to the invention.

It is to be noted, that for clarity the absolute and relative dimensions of the various components are not drawn to scale, in every detail. In the Figures, identical parts bear the same reference numerals.

The steam iron shown in Fig. 1 is composed of a housing 1 which is closed on the bottom side by an aluminium soleplate 2 which is provided with a thin layer of stainless steel on the underside 3. The soleplate is provided with upright ribs 4 on the inside, on which ribs an aluminium plate 5 is provided in such a manner that a steam chamber 6 is formed between the inside of the soleplate 2 and the plate 5. The steam chamber 6 is sealed by an elastic silicone rubber 7. The steam iron further comprises a water reservoir 8. By means of a pumping mechanism 9, water from the reservoir 8 can be sprayed directly onto the clothes to be ironed. By means of a pumping mechanism 10, water can be pumped from the reservoir 8 into the steam chamber 5, thus increasing the steam output. This water passes through an aperture in plate 5 onto the bottom of the steam chamber 6. In GB-A 2,213,207, a more detailed description is given of the pumping mechanisms 9 and 10. The bottom of the steam chamber 6 is provided with a hydrophilic steam chamber coating 11.

Fig. 2 is a top view of the separate soleplate 2. The steam chamber 6 is bounded by a wall 12. The steam formed can leave the steam chamber

through apertures 13 and, subsequently, it can leave the iron through apertures in a soleplate 14, the so-called steam ports. The bottom of the steam chamber 6 and a portion of the wall 12 is covered with a hydrophilic coating.

The hydrophilic coating is manufactured and provided as described hereinbelow. An aqueous suspension of colloidal SiO_2 and a filler such as mullite ($3\text{Al}_2\text{O}_3 \cdot \text{SiO}_2$) are stabilised to a pH of 2.0 using $+10\%$ by weight of $\text{Al}(\text{H}_2\text{PO}_4)_3$. The suspension is subsequently applied to the bottom of the steam chamber 6 and then thickened. In this manner a hydrophilic steam chamber coating 11 is obtained. The mutual bond of the suspension particles and the adherence to the aluminium bottom of the steam chamber are enhanced in that the acid $\text{H}_2\text{PO}_4^{2-}$ ions react both with metals and oxides until stable, insoluble compounds are formed which do no longer react with water. It has been found that colloidal suspensions comprising alumina, silica, magnesia, or mixtures thereof, yield an acid-resistant steam chamber coating when they are applied by means of the method according to the invention. Further, it has been ascertained that, in order to produce a favourable effect, the quantity of acid phosphate in the steam chamber coating must amount to 1-40 % by weight. Preferably, the quantity of acid phosphate is 10 % by weight.

In an accelerated life test a number of steam irons according to the invention and a number of conventional irons were compared. The hydrophilic steam chamber coating of the conventional irons was composed of a silicate layer which was provided from an alkaline colloidal suspension as described in GB 773,741. The irons according to the invention were provided with an aluminium silicate layer which was provided from an acid colloidal suspension. The acidity of the latter colloidal solution was adjusted to pH 2.0 by means of $\pm 10\%$ by weight of $\text{Al}(\text{H}_2\text{PO}_4)_3$. Both types of steam irons were placed in a climatic chamber for 14 days at a temperature of 30°C and a relative humidity of 9 %. The known steam chamber coating exhibited a strong degree of flaking after the test whereas the steam chamber coating according to the invention was unaffected.

Claims

1. A steam iron comprising a steam chamber (6) which is provided with a hydrophilic coating (11), characterized in that the hydrophilic coating comprises an acid phosphate compound, so that the coating is acid resistant.
2. A steam iron as claimed in Claim 1, characterized in that the acid phosphate compound is an aluminium phosphate compound.

chamber coating in which they then serve as binders. It has been found that the presence of aluminium phosphate in the steam chamber coating ensures that said coating is particularly insoluble in water and also very acid resistant.

The invention also relates to a method of providing a hydrophilic coating in the steam chamber of a steam iron, whereby a colloidal suspension comprising alumina, silica or magnesia, or mixtures thereof is introduced into the steam chamber and is thickened to form a hydrophilic steam chamber coating. Said method is characterized in that the suspension is acidified to a pH value of 1-3 by means of an acid phosphate compound which functions as an acid stabiliser. The suspension may alternatively comprise further fillers. A preferred embodiment of the method according to the invention is characterized in that an aluminium phosphate, in particular $\text{Al}(\text{H}_2\text{PO}_4)_3$, is used as the acid stabiliser.

The invention will be explained in greater detail by means of exemplary embodiments and with reference to the accompanying drawings, in which

Fig. 1 is a partly cross-sectional and partly elevational view of a steam iron according to the invention.

Fig. 2 is a top view of the soleplate of the steam iron according to the invention.

It is to be noted, that for clarity the absolute and relative dimensions of the various components are not drawn to scale, in every detail. In the Figures, identical parts bear the same reference numerals.

The steam iron shown in Fig. 1 is composed of a housing 1 which is closed on the bottom side by an aluminium soleplate 2 which is provided with a thin layer of stainless steel on the underside 3. The soleplate is provided with upright ribs 4 on the inside, on which ribs an aluminium plate 5 is provided in such a manner that a steam chamber 6 is formed between the inside of the soleplate 2 and the plate 5. The steam chamber 6 is sealed by an elastic silicone rubber 7. The steam iron further comprises a water reservoir 8. By means of a pumping mechanism 9, water from the reservoir 8 can be sprayed directly onto the clothes to be ironed. By means of a pumping mechanism 10, water can be pumped from the reservoir 8 into the steam chamber 5, thus increasing the steam output. This water passes through an aperture in plate 5 onto the bottom of the steam chamber 6. In GB-A 2,213,207, a more detailed description is given of the pumping mechanisms 9 and 10. The bottom of the steam chamber 6 is provided with a hydrophilic steam chamber coating 11.

Fig. 2 is a top view of the separate soleplate 2. The steam chamber 6 is bounded by a wall 12. The steam formed can leave the steam chamber

through apertures 13 and, subsequently, it can leave the iron through apertures in a soleplate 14, the so-called steam ports. The bottom of the steam chamber 6 and a portion of the wall 12 is covered with a hydrophilic coating.

The hydrophilic coating is manufactured and provided as described hereinbelow. An aqueous suspension of colloidal SiO_2 and a filler such as mullite ($3 \text{ Al}_2\text{O}_3 \cdot \text{SiO}_2$) are stabilised to a pH of 2.0 using $\pm 10\%$ by weight of $\text{Al}(\text{H}_2\text{PO}_4)_3$. The suspension is subsequently applied to the bottom of the steam chamber 6 and then thickened. In this manner a hydrophilic steam chamber coating 11 is obtained. The mutual bond of the suspension particles and the adherence to the aluminium bottom of the steam chamber are enhanced in that the acid $\text{H}_2\text{PO}_4^{2-}$ ions react both with metals and oxides until stable, insoluble compounds are formed which do no longer react with water. It has been found that colloidal suspensions comprising alumina, silica, magnesia, or mixtures thereof, yield an acid-resistant steam chamber coating when they are applied by means of the method according to the invention. Further, it has been ascertained that, in order to produce a favourable effect, the quantity of acid phosphate in the steam chamber coating must amount to 1-40 % by weight. Preferably, the quantity of acid phosphate is 10 % by weight.

In an accelerated life test a number of steam irons according to the invention and a number of conventional irons were compared. The hydrophilic steam chamber coating of the conventional irons was composed of a silicate layer which was provided from an alkaline colloidal suspension as described in GB 773,741. The irons according to the invention were provided with an aluminium silicate layer which was provided from an acid colloidal suspension. The acidity of the latter colloidal solution was adjusted to pH 2.0 by means of $\pm 10\%$ by weight of $\text{Al}(\text{H}_2\text{PO}_4)_3$. Both types of steam irons were placed in a climatic chamber for 14 days at a temperature of 30°C and a relative humidity of 9 %. The known steam chamber coating exhibited a strong degree of flaking after the test whereas the steam chamber coating according to the invention was unaffected.

Claims

1. A steam iron comprising a steam chamber (6) which is provided with a hydrophilic coating (11), characterized in that the hydrophilic coating comprises an acid phosphate compound, so that the coating is acid resistant.
2. A steam iron as claimed in Claim 1, characterized in that the acid phosphate compound is an aluminium phosphate compound.



3. A steam iron as claimed in Claim 2, characterized in that the aluminium phosphate compound is $\text{Al}(\text{H}_2\text{PO}_4)_3$.
4. A method of providing a hydrophilic coating (11) in the steam chamber (6) of a steam iron, whereby a colloidal suspension comprising alumina, silica, magnesia, or mixtures thereof, is introduced into the steam chamber (11) and thickened to form a hydrophilic coating (6), characterized in that the suspension is acidified to a pH value of 1-3 by means of an acid phosphate compound, which functions as an acid stabiliser.
5. A method as claimed in Claim 4, characterized in that aluminiumphosphate is used as the acid stabiliser.

Patentansprüche

1. Dampfbügeleisen mit einer mit einer Hydrophilschicht (11) bedeckten Dampfkammer (6), dadurch gekennzeichnet, daß die hydrophile Deckschicht eine saure Phosphatverbindung aufweist, so daß die Schicht säurefest ist.
2. Dampfbügeleisen nach Anspruch 1, dadurch gekennzeichnet, daß die saure Phosphatverbindung eine Aluminiumphosphatverbindung ist.
3. Dampfbügeleisen nach Anspruch 2, dadurch gekennzeichnet, daß die Aluminiumphosphatverbindung $\text{Al}(\text{H}_2\text{PO}_4)_3$ ist.
4. Verfahren zum Anbringen einer Hydrophilschicht (11) in einer Dampfkammer (6) eines Dampfbügeleisens, wobei eine kolloidale Suspension mit Tonerde, Kiesel Erde, Magnesiumoxid oder Gemischen derselben in die Dampfkammer (11) gebracht und darin eingedickt wird zum Bilden einer Hydrophilschicht (6), dadurch gekennzeichnet, daß die Suspension mittels einer sauren Phosphatverbindung, die als saurer Stabilisator wirksam ist, auf einen pH-Wert von 1 - 3 gebracht wird.
5. Verfahren nach Anspruch 4, dadurch gekennzeichnet, daß Aluminiumphosphat als saurer Stabilisator verwendet wird.

Revendications

1. Fer à repasser à vapeur comportant une enceinte d'ébullition (6) munie d'un revêtement hydrophilique (11), caractérisé en ce que le revêtement hydrophilique comporte un composé de phosphate acide, de sorte que le revête-

ment résiste aux acides.

2. Fer à repasser à vapeur selon la revendication 1, caractérisé en ce que le composé de phosphate acide est un composé de phosphate d'aluminium.
3. Fer à repasser à vapeur selon la revendication 2, caractérisé en ce que le composé de phosphate d'aluminium est $\text{Al}(\text{H}_2\text{PO}_4)_3$.
4. Procédé pour fournir un revêtement hydrophilique (11) dans l'enceinte d'ébullition (6) d'un fer à repasser à vapeur, la suspension colloïdale comportant de l'alumine, de la silice, de la magnésie, ou des mélanges desdits matériaux, étant introduite dans l'enceinte d'ébullition (11) pour être épaissie afin de constituer un revêtement hydrophilique (6) caractérisé en ce que la suspension est acidifiée de manière à présenter un pH dont la valeur est comprise entre 1 et 3 au moyen d'un composé de phosphate acide fonctionnant comme stabilisateur acide.
5. Procédé selon la revendication 4, caractérisé en ce que l'on utilise le phosphate d'aluminium comme stabilisateur acide.

