

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
28 February 2002 (28.02.2002)

PCT

(10) International Publication Number
WO 02/16149 A1

(51) International Patent Classification⁷: **B44C 1/22**,
B44F 1/14

(21) International Application Number: PCT/JP01/07162

(22) International Filing Date: 21 August 2001 (21.08.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
2000-250941 22 August 2000 (22.08.2000) JP

(71) Applicants (for all designated States except US): **OSAKA PREFECTURE** [JP/JP]; 1-22, Otemae 2-chome, Chuo-ku, Osaka-shi, Osaka 540-0008 (JP). **SHOWA DENKO K.K.** [JP/JP]; 13-9, Shiba Daimon 1-chome, Minato-ku, Tokyo 105-8518 (JP).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **NAGATA, Itsuo** [JP/JP]; Technology Research Institute of Osaka Prefecture, 7-1, Ayumino 2-chome, Izumi-shi, Osaka 594-1157

(JP). **JOGAN, Shigetoshi** [JP/JP]; Sakai Regional Office, Showa Denko K.K., 224, Kaizancho 6-cho, Sakai-shi, Osaka 590-0982 (JP). **ENOMOTO, Masatoshi** [JP/JP]; Sakai Regional Office, Showa Denko K.K., 224, Kaizancho 6-cho, Sakai-shi, Osaka 590-0982 (JP).


(74) Agents: **SHIMIZU, Hisayoshi** et al.; Idemitsu Nagahori Building, 4-26, Minamisemba 3-chome, Chuo-ku, Osaka-shi, Osaka 542-0081 (JP).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

[Continued on next page]

(54) Title: PROCESSING METHOD OF CREATING RAINBOW COLOR, METHOD OF MANUFACTURING ARTICLE WHICH PRESENTS RAINBOW-COLOURED REFLECTIVE LUSTER, AND ARTICLE WHICH PRESENTS RAINBOW-COLOURED REFLECTIVE LUSTER



(57) Abstract: The present invention relates to a method of processing an article to be processed so as to cause the article to create rainbow color and a method of manufacturing an article made of aluminum or its alloy which presents rainbow-coloured reflective luster. An aluminum plate is prepared as a substrate (2) of an article (1) to be processed. A nickel-phosphorus alloy deposit (3) is formed on the surface of this aluminum substrate (2) by an electroless plating method. Subsequently, this article is heat-treated at the temperature of 150 to 600 °C for 5 seconds to 1 hour in an air atmosphere. Subsequently, pulsed laser light (10) is irradiated onto the surface of the deposit (3). By performing the aforementioned steps, diffraction gratings (5) which present beautiful rainbow-coloured reflective luster can be assuredly formed in the surface of article (1). Furthermore, the processing speed can be further increased.



Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.