

Preparation of amines and aminonitriles

- 5 The present invention relates to an improved process for preparing an NH_2 -containing compound by hydrogenating a compound containing at least one unsaturated carbon-nitrogen bond with hydrogen in the presence of a catalyst at temperatures not below room temperature and elevated hydrogen partial pressure in the presence or absence of a solvent.
- 10 The present invention further relates to a process for preparing specifically 6-aminocapronitrile (ACN) and hexamethylenediamine (HMD), a process wherein the hydrogenation of compounds
- 15 containing at least one unsaturated carbon-nitrogen bond is carried out in suspension or in a fixed-bed reactor in a downflow or upflow process, and a process for regenerating cobalt- and/or iron-containing catalysts.
- 20 The hydrogenation of unsaturated carbon-nitrogen bonds with hydrogen is described for example in Houben-Weyl, Vol. 11/1 (nitrogen compounds II, amines), pages 545-574, 4th edition, 1957.
- 25 US-A 2,257,814 discloses a process for preparing aminonitriles from dinitriles by conducting the hydrogenation in the liquid phase in the presence of cobalt- and optionally iron-containing catalysts. Furthermore, DE-A 848,654 describes the partial hydrogenation of adiponitrile (ADN) to ACN in the presence of
- 30 fixed-bed catalysts based on copper/cobalt/zinc and iron-cobalt spinels. DE-A 954,416 describes the use of cobalt on silica gel as a catalyst for preparing aminonitriles and diamines by hydrogenation of dinitriles with hydrogen. DE-A 4,235,466 describes a process for preparing cycloaliphatic and aliphatic
- 35 aminonitriles by catalytic hydrogenation in the presence of a catalyst prepared from iron sponge.
- The cobalt- and iron-containing catalysts used in the
- 40 hydrogenation of nitriles and imines lose activity in long runs and therefore have to be replaced with new catalysts once certain limits have been reached in respect of conversion and/or selectivity or by-product level.
- 45 The regeneration of catalysts coated with carbonaceous deposits is generally effected by burning off the organic coatings with nitrogen-air mixtures (Chem. Eng. Sci. 46 (1991), 11-21).

However, this method can be used only with catalysts which remain mechanically stable on reaction with air. Supported catalysts having a stable structure of oxidic material, such as SiO_2 , Al_2O_3 , TiO_2 , can be successfully regenerated by this method. For instance, GB-A 2,284,163 describes the regeneration of a supported catalyst with Pt, Pd, Ru, Rh, Os, Ir or Ni by treatment of [sic] a gas containing at least chlorine and oxygen.

Catalysts with very high metal contents become damaged on burning off the organic deposits with air, altering their mechanical properties (see EP-A 61,042, for example).

It is known from the Journal of Catalysis 143 (1993), 187-200, that a nickel catalyst (25% by weight of Ni on SiO_2) which is used for the hydrogenation of acetonitrile in the gas phase can be regenerated by treatment with hydrogen at temperatures above 200°C .

The cited references do not reveal whether it is also possible to regenerate cobalt- and/or iron-containing catalysts under these conditions.

It is an object of the present invention to provide a process whereby it is possible to regenerate the cobalt- and iron-containing catalysts used in the hydrogenation of a compound containing at least one unsaturated carbon-nitrogen bond in a simple way, without incurring long shutdown times during the regeneration of the catalysts. More particularly, the object is to raise catalyst activity in respect of conversion and selectivity in the hydrogenation of the compound containing at least one unsaturated carbon-nitrogen bond as closely as possible back to the level of the unused catalyst.

We have found that these objects are achieved by a process for preparing an NH_2 -containing compound by hydrogenating a compound containing at least one unsaturated carbon-nitrogen bond with hydrogen in the presence of a catalyst at temperatures not below room temperature and elevated hydrogen partial pressure in the presence or absence of a solvent, which comprises

a) using a catalyst comprising a cobalt- and/or iron-containing catalyst, and

- b) after the conversion based on the compound to be hydrogenated and/or the selectivity based on the desired product has or have dropped below a defined value or the amount of an unwanted by-product has risen beyond a defined value,
 5 interrupting the hydrogenation by stopping the feed of the compound to be hydrogenated and of the solvent, if used,
- c) treating the catalyst at from 150 to 400°C with hydrogen using a hydrogen pressure within the range from 0.1 to 30 MPa
 10 and a treatment time within the range from 2 to 48 h, and
- d) subsequently continuing the hydrogenation of the compound containing at least one unsaturated carbon-nitrogen bond.

15 We have also found a process wherein compounds containing at least one unsaturated carbon-nitrogen bond are hydrogenated in suspension or in a fixed-bed reactor in a downflow or upflow process; a process for preparing specifically 6-aminocapronitrile
 20 (ACN) and hexamethylenediamine (HMD); and also a process for regenerating cobalt- and iron-containing catalysts.

According to the invention, the starting compounds used are compounds containing at least one unsaturated carbon-nitrogen
 25 bond, such as a carbon-nitrogen double or triple bond. Preference is given to using a C₄-C₈-alkylnitrile or -dinitrile such as butanenitrile, pentanenitrile, hexanenitrile, heptanenitrile, octanenitrile, butanedinitrile (adiponitrile, short ADN), pentanedinitrile, hexanedinitrile, heptanedinitrile and
 30 octanedinitrile, especially adiponitrile, particularly preferably terminal C₄-C₈-dinitriles such as 1,4-dicyanobutane (adiponitrile), 1,5-dicyanopentane, 1,6-dicyanohexane, 1,7-dicyanoheptane and 1,8-dicyanooctane, especially adiponitrile, C₅-C₈-cycloalkylnitriles or -dinitriles such as
 35 cyclopentanecarbonitrile, cyclohexanecarbonitrile, cycloheptanecarbonitrile, cyclooctanecarbonitrile, cyclopentanedicarbonitrile, cyclohexanedicarbonitrile, and also aminonitriles containing from 4 to 8 carbon atoms, preferably a,w-aminonitriles such as 5-aminovaleronitrile and
 40 6-aminocapronitrile (ACN), especially ACN.

The nitriles, dinitriles and aminonitriles may also carry other functional groups as long as they do not impair the hydrogenation or their simultaneous or partial hydrogenation is desired.
 45 Examples are C₁-C₄-alkyl, aryl, especially phenyl, C₅-C₈-cycloalkyl, aminoalkyl, N-alkylaminoalkyl,

N-(cyanomethyl)aminoalkyl and imino ($C=NH$, $C=NR$), preferably imino.

- Particularly preferred compounds are ADN, ACN,
5 3-cyano-3,5,5-trimethylcyclohexylimine, $NC-(CH_2)_2-N(H)-(CH_2)_2-CN$,
 $NC-(CH_2)_2-N(H)-(CH_2)_2-N(H)-(CH_2)_2-CN$ and 1-cyano-2-aminoethane.

- The cobalt and/or iron catalysts can be used without support,
10 especially for a fixed-bed or suspension process, for example in
the form of Raney catalysts or in other customary unsupported
forms. The unsupported forms may comprise admixtures at low
levels compared with the high level of the active components.
These admixtures can have favorable effects on either the
15 catalytic activity and/or selectivity or else on properties such
as hardness, attrition, chemical or thermal stability of the
catalyst. Total admixtures are generally within the range from 0
to 20% by weight, based on the amount of active component.
Suitable mixtures are oxides, phosphates and sulfates of alkali
20 metal and alkaline earth metal compounds, thermally stable oxides
such as SiO_2 , Al_2O_3 , TiO_2 and ZrO_2 and also other transition metal
oxides. Use in the form of a supported catalyst is likewise
possible. The support used may typically be alumina, silica,
activated carbons, titania and zirconia. In supported catalysts,
25 the level of cobalt and/or iron relative to support is generally
within the range from 3 to 95, preferably from 30 to 95, % by
weight, depending on whether only one or both of cobalt and iron
are present.
- 30 The catalysts can also be modified, if desired, with metals of
group VIB (Cr, Mo, W), VIII of the periodic table of the elements
(Ru, Os, Rh, Ir, Pd, Pt) and also copper, manganese and rhenium,
in which case the cobalt and/or iron content of the catalyst is
generally within the range from 50 to 99.9, preferably from 80 to
35 99, % by weight, based on the active components (cobalt and/or
iron + modifier).

- Furthermore, the catalysts may be modified with a compound based
on an alkali metal or an alkaline earth metal such as lithium,
40 sodium, potassium, rubidium, cesium, magnesium, calcium,
strontium and barium, especially cesium. It is customary to use a
weight ratio within the range from 0 to 5, preferably from 0.1 to
3, % by weight of alkali metal or alkaline earth metal, based on
mass of cobalt and iron (one of which need not be present).

Preferred catalysts are unsupported iron and cobalt catalysts having an iron and/or cobalt content of at least 60% by weight, based on the mass of cobalt and/or iron and any modifier, if present.

5

Iron catalysts, which are chiefly used in ammonia synthesis, the Fischer-Tropsch reaction or as dehydrogenation catalyst for making styrene from ethylbenzene, may be prepared in various ways described in the literature. For instance, iron catalysts can be
10 prepared from naturally occurring iron oxides such as hematite or magnetite or metallurgically produced (by oxidation) iron (see Ullmann's Encyclopedia of Industrial Chemistry, 5th Ed., Vol. A2, pages 169-172). Modifiers (also known as promoters) are
15 customarily incorporated by conjoint melting of the oxides or applied to the inner surface by subsequent impregnation of the iron oxides. However, the iron oxide precursor may also be obtained by precipitation (see for example B.E. Leach, Applied Industrial Catalysis, 2 (1983), 177-180) or coprecipitation onto
20 inert oxidic materials from aqueous iron salt solutions as carbonates or hydroxides. These precursors may be brought into a technically usable form in a conventional manner by tableting or extrusion (A.B. Stiles, Catalyst manufacture, New York 1983, pages 137-138, or M. Sittig, Catalyst Manufacture, Recovery and Use, 1972, Noyes data corporation, pages 217-221).

25

A further way of preparing iron catalysts is, for example, the thermal decomposition of iron cyanides to iron carbides and iron nitrides, which can generally be converted into alpha-iron by
30 further heating (see Ullmann's Encyclopedia of Industrial Chemistry, 5th Ed., Vol. A2, pages 169-172).

Cobalt catalysts can be prepared by impregnating a ceramic support with aqueous or organic solutions of a cobalt-containing
35 compound. The impregnation can be carried out on the ready-produced extrudate of the support or else on the support powder. If the ceramic support is used as powder, the cobalt-impregnated powder is customarily shaped, for example by extrusion or tableting, preferably after calcination.

40

If an impregnating step has failed to put sufficient cobalt on the support, for example because of the solubility of the cobalt salts used or the surface area of the support, it is possible, from observations to date, to repeat the impregnating until the
45 desired amount of cobalt has been applied, in which case the

resulting mass is dried and calcined after each impregnating step before the next impregnation is carried out.

It is also possible to prepare cobalt-containing catalysts by precipitation from aqueous or organic solution, in which case the modifiers (or promoters) are customarily coprecipitated or may be applied subsequently by impregnation. It is preferred to precipitate cobalt hydroxide or the corresponding carbonate or other sparingly soluble cobalt compounds. After precipitation, it is customary to dry the precipitate and then process the dried mass, for example by extrusion or tableting, although, if desired, it is possible to precede the shaping into extrudates or tablets with a calcination at temperatures within the range from 200 to 700°C in order that certain, desirable solid-state phases may be obtained.

Before use as hydrogenation catalysts, the cobalt oxide and/or iron oxide precatalysts are advantageously reduced to the corresponding metals by means of a hydrogen treatment, in which case, in general, an oxide content of not more than 10% by weight, preferably of not more than 5% by weight, particularly preferably of not more than 1% by weight, based on the total mass of metal and oxide, is preferable from experience to date. This reduction of the oxide-containing materials to the corresponding active catalyst masses can be carried out under atmospheric or superatmospheric pressure at temperatures from 200°C in a conventional manner.

The hydrogenations can be carried out in upflow, downflow or suspension.

When the reaction is carried out in a suspension, it is customary to choose temperatures within the range from 40 to 150°C, preferably within the range from 50 to 100°C, particularly preferably within the range from 60 to 90°C; the pressure is generally chosen to be within the range from 2 to 20, preferably from 3 to 10, particularly preferably from 4 to 9, MPa. The residence times are essentially dependent on the desired yield, selectivity and the desired conversion; customarily, the residence time is selected so as to maximize the yield, for example within the range from 50 to 275, preferably within the range from 70 to 200, min.

In the suspension process, the solvent used is preferably ammonia, amines, diamines and triamines having from 1 to 6 carbon atoms such as trimethylamine, triethylamine, tripropylamine and

tributylamine or alcohols, especially methanol and ethanol, particularly preferably ammonia. It is advantageous to use a concentration of the compound to be hydrogenated within the range from 10 to 90, preferably from 30 to 80, particularly preferably
5 from 40 to 70, % by weight, based on the sum of compound to be hydrogenated and solvent.

The amount of catalyst used is generally within the range from 1 to 50, preferably from 5 to 20, % by weight, based on the amount
10 of compound to be hydrogenated used.

The suspension hydrogenation can be carried out batchwise or, preferably, continuously, generally in the liquid phase.

15 The hydrogenation may also be carried out batchwise or continuously in a fixed-bed reactor in a downflow or upflow process, in which case it is customary to employ a temperature within the range from 30 to 200°C, preferably within the range
20 from 50 to 150°C, and a pressure generally within the range from 2 to 30, preferably within the range from 3 to 20, MPa. The hydrogenation is preferably carried out in the presence of a solvent, preferably ammonia, amines, diamines and triamines having from 1 to 6 carbon atoms such as trimethylamine,
25 triethylamine, tripropylamine and tributylamine or alcohol, preferably methanol and ethanol, particularly preferably ammonia. In a preferred embodiment, the amount of ammonia used is within the range from 0.5 to 10, preferably from 1 to 6, g per g of compound to be hydrogenated, especially adiponitrile. Preference
30 is given to using a catalyst space velocity within the range from 0.1 to 2.0, preferably from 0.3 to 1.0, kg of the compound to be hydrogenated/l*h, especially adiponitrile/l*h. Here too it is possible to adjust the conversion and hence the selectivity in a specific manner by varying the residence time.

35 The hydrogenation can be carried out in a customary suitable reactor.

40 If the reaction is carried out in the gas phase, it is customary to use temperatures within the range from 100 to 250°C, preferably within the range from 160 to 200°C; the pressure employed is generally within the range from 0.01 to 3, preferably from 0.09 to 0.5, MPa. Furthermore, the molar ratio of hydrogen to compound containing at least one unsaturated carbon-nitrogen bond is
45 generally within the range from 2:1 to 300:1, preferably within the range from 10:1 to 200:1.

In a preferred embodiment, the hydrogenation of ADN is carried out in the presence of ammonia as solvent using fixed-bed catalysts by a process wherein, following the deactivation of the catalyst, ie. a decrease in the conversion of ADN and/or

- 5 selectivity based on ACN below a defined value, first the feed of adiponitrile and ammonia is switched off, then the temperature is brought to 200-250°C, and subsequently the catalyst is treated for from ten to twenty hours with from 200 to 800, preferably from 500 to 700, especially 600, l of hydrogen/l of cat. x h.
- 10 Thereafter the temperature is customarily brought back down to reaction temperature and the hydrogenation is continued.

- Prior to starting the regeneration, it is preferable to remove the hydrogenation mixture still present in the reactor. It may be
- 15 advantageous to wash the catalyst before the actual regeneration with the solvent present in the system, especially ammonia. The wash temperature employed is customarily within the range from 20 to 200°C, especially within the range from 20 to 100°C. It is generally advantageous to carry on the wash for a period of from
- 20 2 to 24 hours.

- According to the invention, the regeneration of the catalyst is carried out at temperatures within the range from 150 to 400°C, preferably within the range from 180 to 350°C, especially within
- 25 the range from 200 to 300°C, using a hydrogen pressure within the range from 0.1 to 30 MPa, preferably within the range from 0.1 to 20 MPa. A continuous process is customarily carried out with the hydrogen rate within the range from 100 to 1500, preferably within the range from 200 to 1000, l of hydrogen/l of reactor
- 30 volume x hour.

- The process of the invention makes it possible to achieve distinct improvements in the life and space-time yield of cobalt-
- 35 and/or iron-containing catalysts in the hydrogenation of compounds containing at least one unsaturated carbon-nitrogen bond, especially in the hydrogenation of adiponitrile to aminocapronitrile and hexamethylenediamine (nylon 6 and nylon 66 intermediates).

40 Examples

Example 1 - Preparation of an unsupported cobalt catalyst

- 45 20% strength by weight sodium carbonate solution was added a little at a time to an aqueous solution of cobalt nitrate, manganese nitrate and phosphoric acid in water containing 10% by

weight of cobalt (calculated on the basis of cobalt nitrate), 0.55% by weight of manganese (calculated from the amount of manganese nitrate) and 0.45% by weight of H_3PO_4 at 50°C in such a way as to always produce a pH of 6 on completion of the addition of the sodium carbonate solution; the corresponding carbonates were precipitated. On completion of the precipitation, discernible from the fact that the established pH of 6 did not change, further sodium carbonate solution was added until a pH of 7.5 was obtained. The resulting precipitate was washed with nitrate and sodium-free by washing the precipitate with water until a final conductivity of 20 msiemens was obtained and, according to Merckoquant® test strips for nitrate (from Merck), the nitrate content of the solution was less than 0.02% by weight. The precipitate thus washed was suspended in water and sprayed into a spray-tower (inlet temperature = 550°C). The sprayed material was dried at 500°C, milled and shaped in an extruder into extrudates 4 mm in diameter and 1 cm in length. The extrudates were dried at from 100 to 120°C, and calcined at 900°C for 1 h. The calcined product had a composition of 90% by weight of CoO , 5% by weight of Mn_2O_3 , 3% by weight of P_2O_5 and 2% by weight of Na_2O . The extrudates thus obtained were reduced at 320°C in a stream of hydrogen for 16 h and passivated at room temperature with a nitrogen-air mixture (5% by volume of air, 95% by volume of nitrogen).

25

Example 2 - Preparation of an unsupported iron catalyst

The method described in Catalyst Manufacture, A.B. Stiles, T.A. Koch (1995), pages 167/68, was followed to melt a mixture of iron oxide (magnetite) with the promoters Al_2O_3 , K_2CO_3 and calcium carbonate at from 1600 to 2000°C. The melt was subsequently cooled and comminuted. The material obtained (catalyst in the oxidic state) had the following composition: 1.1% by weight of K_2O , 3.0% by weight of Al_2O_3 , 2.3% by weight of CaO , remainder FeO and Fe_2O_3 . To obtain a usable catalyst, the material obtained was treated at 450°C with hydrogen at 3 MPa for 32 h and then passivated at room temperature with a nitrogen/air mixture (5% by volume of air, 95% by volume of nitrogen). The ratio of mass of metals to mass of oxides ("degree of reduction") was 9:1.

40

Example 3 - Fixed-bed hydrogenation in the liquid phase

A tubular reactor 2 m in length and 2.5 cm in internal diameter was packed with 750 ml (1534 g) of the passivated catalyst of Example 1. The passivated catalyst was then activated over 48 h in a stream of nitrogen (500 l/h) under atmospheric pressure by

raising the temperature from 30°C to 280°C (during which time previously unconverted CoO was reduced to Co).

After lowering the reactor inlet temperature to 45°C and the
5 reactor outlet temperature to 85°C, the reactor was supplied under
a total pressure of 20 MPa with a mixture of 400 ml/h of
adiponitrile, 600 ml/h of ammonia and 500 l/h of hydrogen. In
addition, to remove the heat, about four times the feed quantity
(4.2 l/h) was recycled via a heat exchanger. Under these
10 conditions, the adiponitrile conversion was 70%. The initial
reaction mixture contained 30% by weight of ADN, 35% by weight of
ACN and 34.5% of HMD (ACN selectivity: 50%, ACN + HMD
selectivity: > 99%). Following a run of 3,600 h, the ACN
selectivity dropped from an initial 50% to 23% while the
15 conversion remained unchanged.

Thereafter the dinitrile and ammonia feed was switched off and
the catalyst regenerated in the reactor over 12 hours at 200°C and
20 a total pressure of 200 bar (at 500 l/h of hydrogen). A renewed
startup under identical conditions (see above) produced an
increase in the selectivity to 50%; that is, the catalyst had
been restored to its initial selectivity.

25 Example 4 - Fixed-bed hydrogenation in the liquid phase

A tubular reactor 2 m in length and 2.5 cm in internal diameter
was packed with 800 ml (1598 g) of the passivated catalyst of
Example 1. The catalyst was then activated over 48 h under
30 atmospheric pressure in a stream of hydrogen (500 l/h) by raising
the temperature from 30°C to 320°C (in which period residual CoO
was reduced to Co).

After lowering the reactor inlet temperature to 120°C and the
35 reactor outlet temperature to 140°C, the reactor was supplied at
25 MPa in the downflow direction with a mixture of 180 ml/h of
3-cyano-3,5,5-trimethylcyclohexylimine, 1700 ml/h of ammonia and
500 ml/h of hydrogen. Under these conditions the imine conversion
was 100%. The yield of
40 3-aminomethyl-3,5,5-trimethylcyclohexylamine was 94%
(selectivity: 94%). 3-Cyano-3,5,5-trimethylcyclohexylamine was a
hydrogenation intermediate and hence an indicator of the catalyst
activity. The concentration of this compound rose from an initial
0 ppm to 1500 ppm (based on the reaction mixture) after 5700 h,
45 so that catalyst regeneration appeared to be necessary for
product specification reasons.

Thereafter the nitrile and ammonia feed was switched off and the catalyst regenerated in the reactor over 24 h at 300°C and a total pressure of 25 MPa (at 500 l/h of hydrogen). A renewed startup under identical conditions as above produced a drop in the intermediate concentration to 200 ppm; that is, the catalyst had been almost completely restored to its initial activity.

Example 5 - Fixed-bed hydrogenation in the liquid phase

10 A tubular reactor 7 m in length and 10.5 cm in internal diameter was packed with 60 l (130 kg) of the catalyst obtained in Example 2 (degree of reduction 9:1) and then the catalyst was activated over 72 h at 370°C and a total pressure of 15 MPa (reducing the remaining iron oxide to iron) by first passing nitrogen through
15 the reactor and then replacing the nitrogen step by step with hydrogen during the first 24 h.

After lowering the reactor inlet temperature to 110°C and the
20 reactor outlet temperature to 135°C, the reactor was supplied under a total pressure of 25 MPa with a mixture of 30 kg/h of ADN, 50 l/h of liquid ammonia and 40 standard m³/h of hydrogen. In addition, to remove the heat, five times the feed quantity (400 l/h) was recirculated via a heat exchanger (giving a recycle
25 stream temperature at the reactor inlet of 110°C). Under these conditions the ADN conversion was 70%. The initial reaction mixture contained 30% by weight of ADN, 35% by weight of ACN and 34.5% by weight of HMD (ACN selectivity: 50%, ACN + HMD selectivity: > 99%). After 800 h the catalyst was specifically
30 deactivated by switching off the feeds without rinsing.

For regeneration, the catalyst was treated in the reactor initially with nitrogen (80 m³/h) at a temperature within the range from 200 to 250°C and a pressure of 15 MPa, for 24 h. This
35 was followed by heating to 270°C and stepwise replacement of the nitrogen (80 m³/h) with hydrogen over 5 h. During the replacement of nitrogen with hydrogen the temperature was likewise increased stepwise to 380°C. Finally the reactor was maintained at a temperature within the range from 350 to 380°C and a hydrogen
40 pressure of 20 MPa for 24 h. On a renewed startup under the same conditions as indicated above the selectivity of the catalyst was back to its initial level.



We claim:

- 5 1. A process for preparing an NH_2 -containing compound by hydrogenating a compound containing at least one unsaturated carbon-nitrogen bond with hydrogen in the presence of a catalyst at temperatures not below room temperature and elevated hydrogen partial pressure in the presence or absence
10 of a solvent, which comprises
 - a) using a catalyst comprising a cobalt- and/or iron-containing catalyst, and
 - 15 b) after the conversion based on the compound to be hydrogenated and/or the selectivity based on the desired product has or have dropped below a defined value or the amount of an unwanted by-product has risen beyond a defined value, interrupting the hydrogenation by stopping
20 the feed of the compound to be hydrogenated and of the solvent, if used,
 - c) treating the catalyst at from 150 to 400°C with hydrogen using a hydrogen pressure within the range from 0.1 to 30
25 MPa and a treatment time within the range from 2 to 48 h, and
 - d) subsequently continuing the hydrogenation of the compound containing at least one unsaturated carbon-nitrogen bond.
30
2. A process as claimed in claim 1, wherein the compound containing at least one unsaturated carbon-nitrogen bond is a
35 C_4 - C_8 -alkylnitrile, a C_5 - C_8 -cycloalkylnitrile, a C_4 - C_8 -alkyldinitrile or a C_5 - C_8 -cycloalkyldinitrile.
3. A process as claimed in claim 1 or 2, wherein adiponitrile is used to obtain 6-aminocapronitrile and hexamethylenediamine.
- 40 4. A process as claimed in any of claims 1 to 3, wherein the hydrogenation of the compound containing at least one unsaturated carbon-nitrogen bond is carried out in suspension at a temperature within the range from 40 to 150°C and at a
45 pressure within the range from 2 to 20 MPa.



5. A process as claimed in any of claims 1 to 3, wherein the hydrogenation of the compound containing at least one unsaturated carbon-nitrogen bond is carried out in a fixed-bed reactor in a downflow or upflow process at a temperature within the range from 30 to 200°C and at a pressure within the range from 2 to 30 MPa.
6. A process for regenerating a cobalt- and/or iron-containing catalyst, which comprises treating the catalyst with hydrogen at from 150 to 400°C using a hydrogen pressure within the range from 0.1 to 30 MPa and a treatment time within the range from 2 to 48 h.

Preparation of amines and aminonitriles

5 Abstract

A process for preparing an NH_2 -containing compound by hydrogenating a compound containing at least one unsaturated carbon-nitrogen bond with hydrogen in the presence of a catalyst
10 at temperatures not below room temperature and elevated hydrogen partial pressure in the presence or absence of a solvent which comprises

- 15 a) using a catalyst comprising a cobalt- and/or iron-containing catalyst, and
- 20 b) after the conversion based on the compound to be hydrogenated and/or the selectivity based on the desired product has or have dropped below a defined value or the amount of an unwanted by-product has risen beyond a defined value, interrupting the hydrogenation by stopping the feed of the compound to be hydrogenated and of the solvent, if used,
- 25 c) treating the catalyst at from 150 to 400°C with hydrogen using a hydrogen pressure within the range from 0.1 to 30 MPa and a treatment time within the range from 2 to 48 h, and
- 30 d) subsequently continuing the hydrogenation of the compound containing at least one unsaturated carbon-nitrogen bond.

35

40

45