



(51) International Patent Classification:

C08K 3/26 (2006.01) C08K 5/526 (2006.01)

C08K 5/13 (2006.01) F16L 9/12 (2006.01)

C08K 5/3492 (2006.01)

(21) International Application Number:

PCT/EP2019/084689

(22) International Filing Date:

11 December 2019 (11.12.2019)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

18214993.0 21 December 2018 (21.12.2018) EP

(71) Applicant: BASF SE [DE/DE]; Carl-Bosch-Strasse 38,
67056 Ludwigshafen am Rhein (DE).(72) Inventors: WEYLAND, Tania; Hardmattstr. 434, 5082
Kaisten (CH). BERTET, Marie Laure; 49, Avenue
Georges Pompidou, 92593 Levallois-Perret Cedex (FR).
HERBST, Heinz; Hardmattstr. 434, 5082 Kaisten (CH).(74) Agent: BASF IP ASSOCIATION; BASF SE, G-FLP -
C006, 67056 Ludwigshafen (DE).(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ,


CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO,
DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN,
HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP,
KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME,
MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ,
OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA,
SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN,
TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ,
UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ,
TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK,
EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV,
MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM,
TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,
KM, ML, MR, NE, SN, TD, TG).


Published:

— with international search report (Art. 21(3))


(54) Title: A POLYPROPYLENE COMPOSITION




(A-I-1)




(A-I-2)



(A-I-3)



(A-III-1)



(A-IV-1)

(57) **Abstract:** A polypropylene composition comprising components A), B) and C), wherein component A) is a hindered amine light stabilizer selected from the group consisting of the compounds of formulae (A-I-1), (A-I-2), (A-I-3), (A-III-1) and (A-IV-1) as defined for the present invention, component B) is a natural or synthetic hydroxycitric acid, component C) is a phenolic antioxidant selected from the group consisting of 1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl)-2, 4, 6-trimethyl benzene, ethylene bis[3,3-bis(3-tert-butyl-4-hydroxyphenyl)butyrate], 1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl)-isocyanurate and 6-[3-(3-tert-butyl-4-hydroxy-5-methylphenyl)propoxy]-2, 4,8,10-tetra-tert-butylbenzo[d,f][1,3,2]dioxaphosphin, and wherein the weight ratio of component A) to component B) is 1:10 to 10:1.