

## Description

TITLE OF INVENTION: CURABLE RESIN COMPOSITION AND CURED PRODUCT  
OF SAME

## TECHNICAL FIELD

5 [0001]

The present invention relates to a curable resin composition containing a compound having a specific structure and a cured product thereof, and the composition is suitable for use in electric and electronic parts such as semiconductor encapsulants, printed wiring boards, and build-up laminates, lightweight and high-strength materials such as carbon fiber reinforced  
10 plastics and glass fiber reinforced plastics, and 3D printing applications.

## BACKGROUND ART

[0002]

In recent years, the laminates on which electric and electronic components are mounted have come to be used in a wider range of fields, and the required characteristics have  
15 become more extensive and sophisticated. Conventional semiconductor chips were mainly mounted on metal lead frames, but semiconductor chips with high processing power, such as central processing units (hereinafter referred to as CPUs), are increasingly being mounted on laminates made of polymer materials.

[0003]

20 The fifth generation communication system "5G", whose development is currently accelerating, is expected to further increase capacity and speed of communication. In 5G, the frequency used will become higher, but in order to realize high-speed communication using high frequencies, it is important to reduce transmission loss, and further reduction in dielectric tangent of the board material will be required. The transmission loss occurring on the printed  
25 circuit board is due to conductor loss and dielectric loss. As described in Non-Patent

Literature 1, the dielectric loss  $\alpha_D$  is proportional to the square root of the relative dielectric constant  $\epsilon_r$  of the dielectric and the dielectric tangent  $\tan\delta$ , so it can be said that improving the dielectric tangent  $\tan\delta$ , which has a higher contribution rate than the relative dielectric constant  $\epsilon_r$ , is effective in reducing transmission loss. Low-dielectric materials include thermoplastic materials such as PTFE (polytetrafluoroethylene) and LCP (liquid crystal polymer), but they are poor in moldability compared to thermosetting resins. In light of this, the development of thermosetting resins that exhibit low dielectric tangent is desired.

[0004]

In light of this background, thermosetting resins exhibiting low dielectric tangents have been studied. For example, Patent Literature 1 proposes a thermosetting resin composition containing an imide compound having a maleimide group and a phenol aralkyl resin having an aliphatic unsaturated bond. However, on the other hand, since phenolic hydroxy groups that do not participate in the reaction remain during the curing reaction, the electrical properties are not sufficient. Patent Literature 2 also discloses an allyl ether-modified biphenyl aralkyl novolac resin to which an allyl group is added together with a phenolic hydroxy group. However, it has been shown that the allyl ether-modified biphenyl aralkyl novolac resin undergoes Claisen rearrangement at 190°C, and at 200°C, which is the molding temperature of a general substrate, phenolic hydroxy groups that do not contribute to the curing reaction are generated, so the electrical properties are not satisfactory.

## CITATION LIST

### NON-PATENT LITERATURE

[0005]

Non-Patent Literature 1: "Consideration of signal loss factor in the high-speed Signal transmission on a printed Circuit board", 29th Spring Conference of the Japan Institute of Electronics Packaging, Session ID: 16P1-17, 2015

## PATENT LITERATURE

[0006]

Patent Literature 1: Japanese Patent Publication No. H04-359911

Patent Literature 2: International Publication No. 2016/002704

## 5 SUMMARY OF INVENTION

## TECHNICAL PROBLEM

[0007]

Furthermore, in recent years, there is a demand for excellent dielectric properties over a long period of time, not just at the initial values. Specifically, there is a demand for  
10 excellent dielectric properties even after exposure to high temperatures and after water absorption tests.

[0008]

The present invention has been made in view of the above circumstances, and an object of the present invention is to provide a curable resin composition exhibiting a low  
15 dielectric tangent, and a cured product thereof.


## Solution to Problem

[0009]

That is, the present invention relates to the following [1] to [5]. In the present application, "(Numerical value 1) to (Numerical value 2)" indicates that the upper and lower  
20 limits are included.

[1] A curable resin composition containing: a compound represented by the following formula (1); and a compound having one ethylenically unsaturated double bond in the molecule.

[Chem. 1]



In formula (1), plural R each independently represent a hydrogen atom, a hydrocarbon group having 1 to 10 carbon atoms, or a halogenated alkyl group having 1 to 10 carbon atoms. p and r each represent integers of 0 to 4, q represents an integer of 0 to 3, and n represents the average number of repetitions, and satisfies  $1 \leq n \leq 20$ .

[2] The curable resin composition according to the preceding item [1], in which the compound having one ethylenically unsaturated double bond in the molecule is a compound having a maleimide structure or an acenaphthylene structure in the molecule.

[3] The curable resin composition according to the preceding item [1] or [2], further containing a polymerization initiator.

[4] The curable resin composition according to any one of the preceding items [1] to [3], further comprising at least one selected from the group consisting of a maleimide compound having two or more maleimide groups in the molecule, a polyphenylene ether compound, a compound having two or more ethylenically unsaturated bonds in the molecule, a cyanate ester resin, polybutadiene and modified products thereof, polystyrene and modified products thereof, and polyethylene and modified products thereof.

[5] A cured product obtained by curing the curable resin composition according to any one of the preceding items [1] to [4].

#### ADVANTAGEOUS EFFECTS OF INVENTION

[0010]

The curable resin composition of the present invention and its cured product exhibit a low dielectric tangent.

## BRIEF DESCRIPTION OF DRAWINGS

[0011]

[Figure 1] shows a GPC chart of Synthesis Example 1.

[Figure 2] shows a GPC chart of Synthesis Example 2.

5 [Figure 3] shows a  $^1\text{H}$ -NMR chart of Synthesis Example 2.


## DESCRIPTION OF EMBODIMENTS

[0012]

The curable resin composition of the present embodiment contains a compound represented by the following formula (1) as an essential component.

10 [0013]

[Chem. 2]



[0014]

In formula (1), plural R each independently represent a hydrogen atom, a hydrocarbon group having 1 to 10 carbon atoms, or a halogenated alkyl group having 1 to 10 carbon atoms, preferably a hydrogen atom or a hydrocarbon group having 1 to 10 carbon atoms, and more preferably a hydrogen atom or a hydrocarbon group having 1 to 3 carbon atoms. Hydrocarbons having 10 or less carbon atoms are less likely to undergo molecular vibration when exposed to high frequency waves, and therefore have particularly excellent electrical properties.

20

[0015]

In formula (1), p and r are integers of 0 to 4, preferably integers of 0 to 2. q is an


integer of 0 to 3, preferably integers of 0 to 2.  $n$  is the average number of repetitions, and is preferably  $1 \leq n \leq 20$ , more preferably  $1.1 \leq n \leq 20$ , particularly preferably  $1.1 \leq n \leq 10$ , and most preferably  $1.1 \leq n \leq 5$ . The value of  $n$  can be calculated from the value of the number average molecular weight ( $M_n$ ) obtained by measuring the compound represented by formula (1) by gel permeation chromatography (GPC). The number average molecular weight is preferably 200 or more and less than 5000, more preferably 300 or more and less than 3000, and particularly preferably 400 or more and less than 2000. If the number average molecular weight is less than 5000, purification by washing with water becomes easy, and if it is 200 or more, the target compound does not volatilize in the solvent distillation step.

[0016]

The compound represented by the formula (1) is derived from a compound represented by the following formula (1-1).

[0017]

[Chem. 3]



15

[0018]

In formula (1-1),  $R$  is the same as in formula (1). The values and preferred ranges of  $p$ ,  $r$ ,  $q$ , and  $n$  are the same as in formula (1).  $X$  represents a halogen atom, and from the viewpoints of reactivity and stability of the raw materials, a bromine atom is preferable, and a bromine atom is particularly preferable.

20

[0019]

The compound represented by the formula (1) can be obtained, for example, by a

method of subjecting the compound represented by the formula (1-1) to a dehydrohalogenation reaction in a solvent in the presence of a basic catalyst. Examples of the solvent to be used include, but are not limited to, water-insoluble solvents such as aromatic solvents such as toluene and xylene, aliphatic solvents such as cyclohexane and n-hexane, ethers such as diethyl ether and diisopropyl ether, ester solvents such as ethyl acetate and butyl acetate, and ketone solvents such as methyl isobutyl ketone and cyclopentanone. Two or more of these may be used in combination. In addition to the water-insoluble solvent, an aprotic polar solvent may also be used in combination. Examples include dimethyl sulfone, dimethyl sulfoxide, dimethylformamide, dimethylacetamide, 1,3-dimethyl-2-imidazolidinone, and N-methylpyrrolidone, and two or more of these may be used in combination. When an aprotic polar solvent is used, it is preferable to use one having a boiling point higher than that of the water-insoluble solvent to be used in combination. The catalyst is not particularly limited, and examples thereof include basic catalysts such as sodium hydroxide, potassium hydroxide, and potassium carbonate. Since it is difficult to completely proceed with the dehydrohalogenation reaction, the aprotic polar solvent may be used in large excess relative to the substrate, and the dehydrohalogenation reaction may be repeated two or more times. For example, the dehydrohalogenation reaction of the compound represented by the formula (1-1) may be carried out in an organic solvent in the presence of a base catalyst, and the resulting solution may be washed with water and then returned to the reaction vessel, and the base catalyst may be added to cause the reaction again. This can increase the progress of the dehydrohalogenation reaction. That is, it is possible to reduce the amount of residual halogen contained in the target compound. The amount of residual halogen is preferably 1 to 10,000 ppm in the target product, more preferably 1 to 1,000 ppm, and even more preferably 1 to 750 ppm. If the amount of residual halogen contained in the compound represented by the formula (1) is large, molecular vibration occurs when exposed to high frequency, which adversely

affects electrical properties, particularly dielectric loss tangent. Furthermore, if the amount of residual halogen is large, the risk of problems such as metal corrosion and ion migration increases in environmental tests such as HAST (High Accelerated Stress Test), so the above-mentioned halogen content is preferable.

5 [0020]

The method for producing the compound represented by the formula (1-1) is not particularly limited, and for example, a compound having a (2-bromoethyl)benzene structure may be reacted with a bishalogenated methylaryl compound (or a bishydroxymethylaryl compound, etc.) in the presence of an acid catalyst such as hydrochloric acid, sulfonic acid, or  
 10 activated clay, or a compound having a (2-bromoethyl)benzene structure may be reacted with a bishydroxymethylaryl compound in the presence of an acid catalyst such as hydrochloric acid, sulfonic acid, or activated clay. When sulfonic acid or the like is used as a catalyst, the mixture may be neutralized with an alkali metal such as sodium hydroxide or potassium hydroxide before proceeding to the extraction step. In the extraction step, an aromatic  
 15 hydrocarbon solvent such as toluene or xylene may be used alone, or a non-aromatic hydrocarbon such as cyclohexane or toluene may be used in combination. After extraction, the organic layer is washed with water until the wastewater becomes neutral, and the solvent and the excess compound having a (2-bromoethyl)benzene structure are distilled off using an evaporator or the like, thereby obtaining a compound having at least two or more 2-  
 20 bromoethylethylbenzene structures in the target molecule.

[0021]

Examples of compounds having a (2-bromoethyl)benzene structure include, but are not limited to, (2-bromoethyl)benzene, 1-(2-bromoethyl)-2-methylbenzene, 1-(2-bromoethyl)-3-methylbenzene, 1-(2-bromoethyl)-4-methylbenzene, 1-(2-bromoethyl)-2,3-  
 25 dimethylbenzene, 1-(2-bromoethyl)-2,4-dimethylbenzene, 1-(2-bromoethyl)-2,5-

dimethylbenzene, and 1-(2-bromoethyl)-2,6-dimethylbenzene. These may be used alone or in combination of two or more. A large carbon number improves solvent solubility, but reduces heat resistance, so it is preferably unsubstituted or substituted with an alkyl group having 1 to 3 carbon atoms, more preferably unsubstituted or substituted with an alkyl group having 1 to 2 carbon atoms, and most preferably unsubstituted or substituted with a methyl group.

[0022]

Examples of the bishalogenated methylaryl compound include, but are not limited to, o-xylylene difluoride, m-xylylene difluoride, p-xylylene difluoride, o-xylylene dichloride, m-xylylene dichloride, p-xylylene dichloride, o-xylylene dibromide, m-xylylene dibromide, p-xylylene dibromide, o-xylylene diiodide, m-xylylene diiodide, and p-xylylene diiodide. These may be used alone or in combination of two or more. From the viewpoint of the reactivity of the raw material during synthesis, chloride-based compounds, bromide-based compounds, and iodide-based compounds are preferred, and chloride-based compounds and bromide-based compounds are more preferred.

[0023]

Examples of bishydroxymethylaryl compounds include, but are not limited to, o-benzenedimethanol, m-benzenedimethanol, and p-benzenedimethanol. These may be used alone or in combination of two or more. The amount of these compounds used is preferably 0.05 to 0.8 parts by mass, more preferably 0.1 to 0.6 parts by mass, per part by mass of the compound having a (2-bromoethyl)benzene structure.

[0024]

In the reaction of a compound having a (2-bromoethyl)benzene structure with a halogenated methylaryl compound or the like, as well as hydrochloric acid, phosphoric acid, sulfuric acid, formic acid, p-toluenesulfonic acid, methanesulfonic acid, Lewis acids such as aluminum chloride and zinc chloride, activated clay, acidic clay, white carbon, zeolite, silica,

alumina, and the like, and acidic ion exchange resins can be used as catalysts as necessary. These can be used alone or in combination of two or more. The amount of catalyst used is 0.05 to 0.8 mol, preferably 0.1 to 0.7 mol, per mol of the compound having a (2-bromoethyl)benzene structure used. If the amount of catalyst used is too large, the viscosity of the reaction solution may be too high, making stirring difficult, and if the amount is too small, the reaction may proceed slowly. The reaction may be carried out using an organic solvent such as hexane, cyclohexane, octane, toluene, or xylene, as necessary, or may be carried out without a solvent. For example, after adding an acidic catalyst to a mixed solution of a compound having a (2-bromoethyl)benzene structure, a halogenated methylaryl compound, and a solvent, if the catalyst contains water, the water is removed from the system by azeotropy. Thereafter, the reaction is carried out at 40 to 180°C, preferably 50 to 170°C, for 0.5 to 20 hours. After the reaction is completed, the acidic catalyst may be neutralized with an alkaline aqueous solution, but it is also possible to proceed to the water washing step without neutralizing it. In the water washing step, a water-insoluble organic solvent is added to the oil layer and water washing is repeated until the wastewater becomes neutral.

[0025]

The softening point of the compound represented by formula (1-1) is preferably 80°C or lower, more preferably 70°C or lower. When the softening point is 80°C or lower, the viscosity when induced into the compound represented by formula (1) is low. This makes it easy to ensure fluidity, does not impair the ability to impregnate glass cloth or carbon fiber, and facilitates B-stage formation such as prepreg formation. If the viscosity is reduced by increasing the dilution solvent, there is a possibility that the resin will not sufficiently adhere to the fibrous material in the impregnation step.

[0026]

The curable resin composition of the present embodiment further contains, as an

essential component, a compound having one ethylenically unsaturated double bond in the molecule. The ethylenically unsaturated double bond in the present embodiment refers to an ethylenically unsaturated bond that can be polymerized by heat or light, and examples thereof include a vinyl group, a styryl group, an allyl group, a 1-propenyl group, a 2-propenyl group, an acryl group, a methacryl group, an acenaphthyl group, a maleimide group, a citraconic imide group, an itaconimide group, a nadiimide group, and an allylnadiimide group. Of these, a vinyl group, a styryl group, an acryl group, a methacryl group, an acenaphthyl group, and a maleimide group are preferred; a styryl group, a methacryl group, an acenaphthyl group, and a maleimide group are more preferred; and an acenaphthyl group and a maleimide group are even more preferred.

[0027]

The compound having one ethylenically unsaturated double bond in the molecule may be any compound having one ethylenically unsaturated double bond in the molecule, and contributes to the curing reaction as a monofunctional component. When the molecule has two or more functional groups, the distance between crosslinking points increases as the molecular weight increases, and the free volume increases. In this case, when the cured product is exposed to high frequency waves, the molecule vibrates, which is a factor in transmission loss. On the other hand, a compound having one functional group can reduce the free volume, and is effective in suppressing molecular vibration and reducing transmission loss. That is, it is possible to obtain a cured product with excellent low dielectric properties (low dielectric tangent).

[0028]



Examples of compounds having one ethylenically unsaturated double bond in the molecule include styrene, 2-vinylbiphenyl, 3-vinylbiphenyl, 4-vinylbiphenyl, 1-vinylnaphthalene, 2-vinylnaphthalene,  $\alpha$ -methylstyrene,  $\alpha$ -ethylstyrene,  $\alpha$ -propylstyrene,  $\alpha$ -n-

- butylstyrene,  $\alpha$ -isobutylstyrene,  $\alpha$ -t-butylstyrene,  $\alpha$ -n-pentylstyrene,  $\alpha$ -2-methylbutylstyrene,  $\alpha$ -3-methylbutyl-2-styrene,  $\alpha$ -3-methylbutylstyrene,  $\alpha$ -t-pentylstyrene,  $\alpha$ -n-hexylstyrene,  $\alpha$ -2-methylpentylstyrene,  $\alpha$ -3-methylpentylstyrene,  $\alpha$ -1-methylpentylstyrene,  $\alpha$ -2,2-dimethylbutylstyrene,  $\alpha$ -2,3-dimethylbutylstyrene,  $\alpha$ -2,4-dimethylbutylstyrene,  $\alpha$ -3,3-dimethylbutylstyrene,  $\alpha$ -3,4-dimethylbutylstyrene,  $\alpha$ -4,4-dimethylbutylstyrene,  $\alpha$ -2-ethylbutylstyrene,  $\alpha$ -1-ethylbutylstyrene,  $\alpha$ -cyclohexylstyrene, o-ethylvinylbenzene, m-ethylvinylbenzene, p-ethylvinylbenzene, 2-vinyl-2'-ethylbiphenyl, 2-vinyl-3'-ethylbiphenyl, 2-vinyl-4'-ethylbiphenyl, 3-vinyl-2'-ethylbiphenyl, 3-vinyl-3'-ethylbiphenyl, 3-vinyl-4'-ethylbiphenyl, 4-vinyl-2'-ethylbiphenyl, 4-vinyl-3'-ethylbiphenyl, 4-vinyl-4'-ethylbiphenyl, 1-vinyl-2-ethylnaphthalene, 1-vinyl-3-ethylnaphthalene, 1-vinyl-4-ethylnaphthalene, 1-vinyl-5-ethylnaphthalene, 1-vinyl-6-ethylnaphthalene, 1-vinyl-7-ethylnaphthalene, 1-vinyl-8-ethylnaphthalene, 2-vinyl-1-ethylnaphthalene, 2-vinyl-3-ethylnaphthalene, 2-vinyl-4-ethylnaphthalene, 2-vinyl-5-ethylnaphthalene, 2-vinyl-6-ethylnaphthalene, 2-vinyl-7-ethylnaphthalene, 2-vinyl-8-ethylnaphthalene, m-methylstyrene, p-methylstyrene, m-propylstyrene, p-propylstyrene, m-n-butylstyrene, p-n-butylstyrene, m-t-butylstyrene, p-t-butylstyrene, m-n-hexylstyrene, p-n-hexylstyrene, m-cyclohexylstyrene, p-cyclohexylstyrene, 2-vinyl-2'-propylbiphenyl, 2-vinyl-3'-propylbiphenyl, 2-vinyl-4'-propylbiphenyl, 3-vinyl-2'-propylbiphenyl, 3-vinyl-3'-propylbiphenyl, 3-vinyl-4'-propylbiphenyl, 4-vinyl-2'-propylbiphenyl, 4-vinyl-3'-propylbiphenyl, 4-vinyl-4'-propylbiphenyl, 1-vinyl-2-propylnaphthalene, 1-vinyl-3-propylnaphthalene, 1-vinyl-4-propylnaphthalene, 1-vinyl-5-propylnaphthalene, 1-vinyl-6-propylnaphthalene, 1-vinyl-7-propylnaphthalene, 1-vinyl-8-propylnaphthalene, 2-vinyl-1-propylnaphthalene, 2-vinyl-3-propylnaphthalene, 2-vinyl-4-propylnaphthalene, 2-vinyl-5-propylnaphthalene, 2-vinyl-6-propylnaphthalene, 2-vinyl-7-propylnaphthalene, 2-vinyl-8-propylnaphthalene, o-ethoxystyrene, m-ethoxystyrene, p-ethoxystyrene, o-propoxystyrene, m-propoxystyrene, p-propoxystyrene, o-n-butoxystyrene,

m-n-butoxystyrene, p-n-butoxystyrene, o-isobutoxystyrene, m-isobutoxystyrene, p-isobutoxystyrene, o-t-butoxystyrene, m-t-butoxystyrene, p-t-butoxystyrene, o-n-pentoxystyrene, m-n-pentoxystyrene, p-n-pentoxystyrene,  $\alpha$ -methyl-o-butoxystyrene,  $\alpha$ -methyl-m-butoxystyrene,  $\alpha$ -methyl-p-butoxystyrene, o-t-pentoxystyrene, m-t-pentoxystyrene, p-t-pentoxystyrene, o-n-hexoxystyrene, m-n-hexoxystyrene, p-n-hexoxystyrene,  $\alpha$ -methyl-o-pentoxystyrene,  $\alpha$ -methyl-m-pentoxystyrene,  $\alpha$ -methyl-p-pentoxystyrene, o-cyclohexoxystyrene, m-cyclohexoxystyrene, p-cyclohexoxystyrene, o-phenoxy styrene, m-phenoxy styrene, p-phenoxy styrene, indene, methyl indene, ethyl indene, propyl indene, butyl indene, t-butyl indene, sec-butyl indene, n-pentyl indene, 2-methyl-butyl indene, 3-methyl-butyl indene, n-hexyl indene, 2-methyl-pentyl indene, 3-methyl-pentyl indene, 4-methyl-pentyl indene, methoxy indene, ethoxy indene, propoxyindene, butoxyindene, t-butoxyindene, sec-butoxyindene, n-pentoxyindene, 2-methyl-butoxyindene, 3-methyl-butoxyindene, n-hexoxyindene, 2-methyl-pentoxyindene, 3-methyl-pentoxyindene, 4-methyl-pentoxyindene, and compounds having one maleimide structure in the molecule represented by the following formula (A) or (B), and compounds having an acenaphthylene structure in the molecule.

[0029]

[Chem. 4]



20 [0030]

In the formulas (A) and (B), Ra is each independently a hydrocarbon group having 1 to 12 carbon atoms, preferably a hydrocarbon group having 1 to 10 carbon atoms, more

preferably a hydrocarbon group having 1 to 5 carbon atoms, and even more preferably a hydrocarbon group having 1 to 3 carbon atoms. When it is a hydrocarbon group having 1 to 12 carbon atoms, low dielectric properties can be exhibited without significantly impairing heat resistance. m is each independently an integer of 0 to 5, preferably an integer of 0 to 3, more preferably an integer of 0 to 2, even more preferably an integer of 0 to 1, and most preferably 0.

[0031]

From the viewpoints of curability, heat resistance, and dielectric properties, the compound having one ethylenically unsaturated double bond in the molecule is preferably a compound having a maleimide structure or an acenaphthylene structure in the molecule. Particularly preferred compounds having a maleimide structure in the molecule are compounds represented by formula (A) or (B), and the most preferred compounds are N-phenylmaleimide or N-cyclohexylmaleimide.

[0032]

Examples of compounds having an acenaphthylene structure in the molecule include acenaphthylene, 1-methylacenaphthylene, 3-methylacenaphthylene, 4-methylacenaphthylene, 5-methylacenaphthylene, 1-ethylacenaphthylene, 3-ethylacenaphthylene, 4-ethylacenaphthylene, 5-ethylacenaphthylene, 5-propylacenaphthylene, 3,8-dimethylacenaphthylene, 5,6-dimethylacenaphthylene, 1-chloroacenaphthylene, 3-chloroacenaphthylene, 4-chloroacenaphthylene, 5-chloroacenaphthylene, 1-bromoacenaphthylene, 3-bromoacenaphthylene, 4-bromoacenaphthylene, 5-bromoacenaphthylene, 1-phenylacenaphthylene, 3-phenylacenaphthylene, 4-phenylacenaphthylene, 5-phenylacenaphthylene, 3-methoxyacenaphthylene, 3-ethoxyacenaphthylene, 3-butoxyacenaphthylene, 4-methoxyacenaphthylene, 4-ethoxyacenaphthylene, 4-butoxyacenaphthylene, 5-methoxyacenaphthylene, 5-

ethoxyacenaphthylene, 5-butoxyacenaphthylene, etc. The most preferred compound having an acenaphthylene structure in the molecule is acenaphthylene.

[0033]

The compound having one ethylenically unsaturated double bond in the molecule is preferably 0.01 to 100 parts by mass, more preferably 0.1 to 75 parts by mass, and even more preferably 1 to 50 parts by mass, relative to 100 parts by mass of the compound represented by formula (1). Below the lower limit, the curing improvement effect and low dielectric properties obtained by adding the compound having one ethylenically unsaturated bond in the molecule may not be sufficiently obtained. Above the upper limit, the high heat resistance obtained by adding the compound represented by formula (1) may be impaired.

[0034]

In addition to the compound represented by formula (1) and the compound having one ethylenically unsaturated double bond in the molecule, various materials may be added to the curable resin composition of the present embodiment to improve performance.

[0035]

[Curing Accelerator]

The curing property of the curable resin composition of the present embodiment can be improved by adding a curing accelerator. As the curing accelerator, an anionic curing accelerator that accelerates the curing reaction by generating anions upon irradiation with ultraviolet light or visible light or heating, or a cationic curing accelerator that accelerates the curing reaction by generating cations upon irradiation with ultraviolet light or visible light or heating, is preferable.

[0036]

Examples of the anionic curing accelerator include: imidazoles such as 2-methylimidazole, 2-ethylimidazole, and 2-ethyl-4-methylimidazole; trialkylamines such as

triethylamine and tributylamine; 4-dimethylaminopyridine, benzyldimethylamine, 2,4,6-tris(dimethylaminomethyl)phenol, and 1,8-diazabicyclo(5,4,0)-undecene, with 4-dimethylaminopyridine and 1,8-diazabicyclo(5,4,0)-undecene being preferred. Other examples include phosphines such as triphenylphosphine, quaternary ammonium salts such as

5 tetrabutylammonium salts, triisopropylmethylammonium salts, trimethyldecanylammonium salts, cetyltrimethylammonium salts, and hexadecyltrimethylammonium hydroxide, but are not limited thereto. These may be used alone or in combination.

[0037]

Examples of the cationic curing accelerator include quaternary phosphonium salts

10 such as triphenylbenzylphosphonium salt, triphenylethylphosphonium salt, and tetrabutylphosphonium salt (the counter ion of the quaternary salt may be a halogen, an organic acid ion, a hydroxide ion, or the like, and is not particularly specified, but an organic acid ion or a hydroxide ion is particularly preferred); transition metal compounds (transition metal salts) such as tin octylate, zinc carboxylate (zinc 2-ethylhexanoate, zinc stearate, zinc

15 behenate, zinc myristate), and zinc phosphate (zinc octylphosphate, zinc stearylphosphate), but are not limited thereto. Furthermore, these may be used alone or in combination.

[0038]

The curing accelerator is used in an amount of 0.01 to 5.0 parts by mass based on 100 parts by mass of the curable resin composition, as required.

20 [0039]

[Inorganic filler]

The curable resin composition of the present embodiment may contain an inorganic filler. Examples of inorganic fillers include fused silica, crystalline silica, porous silica, alumina, zircon, calcium silicate, calcium carbonate, quartz powder, silicon carbide, silicon

25 nitride, boron nitride, zirconia, aluminum nitride, graphite, forsterite, steatite, spinel, mullite,

titania, talc, clay, iron oxide, asbestos, glass powder, and other powders, or inorganic fillers obtained by making these into a spherical or crushed shape, but are not limited thereto. In addition, these may be used alone or in combination.

[0040]

5           When a curable resin composition for semiconductor encapsulation is obtained, the amount of the inorganic filler used is preferably 80 to 92 parts by mass, and more preferably 83 to 90 parts by mass, based on 100 parts by mass of the curable resin composition. When a curable resin composition for interlayer insulating layer forming materials, copper-clad laminates, prepregs, RCCs, and other substrate materials is obtained, the amount of the  
10   inorganic filler used is preferably 5 to 80 parts by mass, and more preferably 10 to 60 parts by mass, based on 100 parts by mass of the curable resin composition.

[0041]

[Polymerization initiator]

          The curable resin composition of the present embodiment can also improve the  
15   curability by adding a polymerization initiator. The polymerization initiator is a compound capable of polymerizing an olefin functional group such as an ethylenically unsaturated double bond, and examples of the polymerization initiator include an olefin metathesis polymerization initiator, an anionic polymerization initiator, a cationic polymerization initiator, and a radical polymerization initiator. Among these, it is preferable to use a radical  
20   polymerization initiator having curability and moderate stability. The radical polymerization initiator is a compound that generates radicals by irradiation with ultraviolet light or visible light or by heating, and starts a chain polymerization reaction. Examples of radical polymerization initiators that can be used include organic peroxides, azo compounds, and benzopinacoles, and it is preferable to use an organic peroxide because it has little effect on  
25   curing temperature control, outgassing suppression, and electrical properties of decomposition

products.

[0042]

Examples of the organic peroxides include: ketone peroxides such as methyl ethyl ketone peroxide and acetylacetone peroxide; diacyl peroxides such as benzoyl peroxide; 5 dialkyl peroxides such as dicumyl peroxide and 1,3-bis-(t-butylperoxyisopropyl)-benzene; peroxyketals such as t-butylperoxybenzoate and 1,1-di-t-butylperoxycyclohexane; alkyl peresters such as  $\alpha$ -cumylperoxynodecanoate, t-butylperoxynodecanoate, t-butylperoxypivalate, 1,1,3,3-tetramethylbutylperoxy-2-ethylhexanoate, t-amylperoxy-2-ethylhexanoate, t-butylperoxy-2-ethylhexanoate, t-amylperoxy-3,5,5-trimethylhexanoate, t- 10 butylperoxy-3,5,5-trimethylhexanoate, t-amylperoxybenzoate; peroxycarbonates such as di-2-ethylhexyl peroxydicarbonate, bis(4-t-butylcyclohexyl)peroxydicarbonate, t-butylperoxyisopropyl carbonate, 1,6-bis(t-butylperoxycarbonyloxy)hexane; t-butyl hydroperoxide, cumene hydroperoxide, t-butyl peroxyoctoate, lauroyl peroxide, etc. These may be used alone or in combination. Among the above organic peroxides, ketone peroxides, 15 diacyl peroxides, hydroperoxides, dialkyl peroxides, peroxyketals, alkyl peresters, peroxycarbonates, etc. are preferred, and dialkyl peroxides are more preferred.

[0043]

Examples of the azo-based compound include, but are not limited to, azobisisobutyronitrile, 4,4'-azobis(4-cyanovaleric acid), 2,2'-azobis(2,4- 20 dimethylvaleronitrile), etc. These may be used alone or in combination.

[0044]

The amount of the polymerization initiator added is preferably 0.01 to 5 parts by mass, particularly preferably 0.01 to 3 parts by mass, in 100 parts by mass of the curable resin composition. If the amount of the polymerization initiator used is less than 0.01 part by mass, 25 the molecular weight may not be sufficiently extended during the polymerization reaction,

and if it is more than 5 parts by mass, the dielectric properties such as the dielectric constant and the dielectric loss tangent may be impaired.

[0045]

[Polymerization inhibitor]

5           The curable resin composition of the present embodiment may contain a polymerization inhibitor. By containing a polymerization inhibitor, storage stability is improved and the reaction initiation temperature can be controlled. By controlling the reaction initiation temperature, it becomes easy to ensure fluidity, impregnation into glass cloth and the like is not impaired, and B-stage such as prepreg formation is facilitated. If the polymerization  
10 reaction proceeds too much during prepreg formation, problems such as difficulty in lamination during the lamination process are likely to occur.

[0046]

          The polymerization inhibitor may be added during or after the synthesis of the compound represented by the formula (1). The amount of the polymerization inhibitor used is  
15 0.008 to 1 part by mass, preferably 0.01 to 0.5 parts by mass, based on 100 parts by mass of the compound represented by the formula (1).

[0047]

          Examples of the polymerization inhibitor include phenol-based, sulfur-based, phosphorus-based, hindered amine-based, nitroso-based, and nitroxyl radical-based. The  
20 polymerization inhibitor may be used alone or in combination. Among these, in the present embodiment, the phenol-based, hindered amine-based, nitroso-based, and nitroxyl radical-based are preferred.

[0048]

          Examples of the phenol-based polymerization inhibitor include: monophenols such  
25 as 2,6-di-t-butyl-p-cresol, butylated hydroxyanisole, 2,6-di-t-butyl-p-ethylphenol, stearyl- $\beta$ -

(3,5-di-*t*-butyl-4-hydroxyphenyl)propionate, isooctyl-3-(3,5-di-*t*-butyl-4-hydroxyphenyl)propionate, 2,4-bis-(*n*-octylthio)-6-(4-hydroxy-3,5-di-*t*-butylanilino)-1,3,5-triazine, and 2,4-bis[(octylthio)methyl]-*o*-cresol; bisphenols such as 2,2'-methylenebis(4-methyl-6-*t*-butylphenol), 2,2'-methylenebis(4-ethyl-6-*t*-butylphenol), 4,4'-thiobis(3-methyl-6-*t*-butylphenol), 4,4'-butylidenebis(3-methyl-6-*t*-butylphenol), triethylene glycol-bis[3-(3-*t*-butyl-5-methyl-4-hydroxyphenyl)propionate], 1,6-hexanediol-bis[3-(3,5-di-*t*-butyl-4-hydroxyphenyl)propionate], *N,N'*-hexamethylenebis(3,5-di-*t*-butyl-4-hydroxyhydrocinnamamide), 2,2'-thio-diethylenebis[3-(3,5-di-*t*-butyl-4-hydroxyphenyl)propionate, 3,5-di-*t*-butyl-4-hydroxybenzylphosphonate-diethyl ester, 3,9-bis[1,1-dimethyl-2- $\beta$ -(3-*t*-butyl-4-hydroxy-5-methylphenyl)propionyloxy}ethyl]2,4,8,10-tetraoxaspiro[5,5]undecane, bis(3,5-di-*t*-butyl-4-hydroxybenzylsulfonate ethyl)calcium; and polymeric phenols such as 1,1,3-tris(2-methyl-4-hydroxy-5-*t*-butylphenyl)butane, 1,3,5-trimethyl-2,4,6-tris(3,5-di-*t*-butyl-4'-hydroxybenzyl)benzene, tetrakis-[methylene-3-(3',5'-di-*t*-butyl-4'-hydroxyphenyl)propionate]methane, bis[3,3'-bis-(4'-hydroxy-3'-*t*-butylphenyl)butyric acid]glycol ester, tris-(3,5-di-*t*-butyl-4-hydroxybenzyl)-isocyanurate, 1,3,5-tris(3',5'-di-*t*-butyl-4'-hydroxybenzyl)-*S*-triazine-2,4,6-(1*H*,3*H*,5*H*)trione, tocopherol, but are not limited thereto.

[0049]

Examples of the sulfur-based polymerization inhibitor include, but are not limited to, dilauryl-3,3'-thiodipropionate, dimyristyl-3,3'-thiodipropionate, and distearyl-3,3'-thiodipropionate.

[0050]

Examples of the phosphorus-based polymerization inhibitor include, but are not limited to: phosphites such as triphenyl phosphite, diphenyl isodecyl phosphite, phenyl diisodecyl phosphite, tris(nonylphenyl)phosphite, diisodecyl pentaerythritol phosphite, tris(2,4-di-*t*-butylphenyl)phosphite, cyclic neopentane tetrayl bis(octadecyl)phosphite, cyclic

neopentane tetrayl bis(2,4-di-t-butylphenyl)phosphite, cyclic neopentane tetrayl bis(2,4-di-t-butyl-4-methylphenyl)phosphite, bis[2- t-butyl-6-methyl-4- {2-(octadecyloxycarbonyl)ethyl} phenyl]hydrogen phosphite; and oxaphosphaphenanthrene oxides such as 9,10-dihydro-9-oxa-10-phosphaphenanthrene-10-oxide, 10-(3,5-di-t-butyl-4-hydroxybenzyl)-9,10-dihydro-9-oxa-10-phosphaphenanthrene-10-oxide, and 10-decyloxy-9,10-dihydro-9-oxa-10-phosphaphenanthrene-10-oxide.

[0051]

Examples of the hindered amine-based polymerization inhibitor include, but are not limited to: ADK STAB (registered trademark) LA-40MP, ADK STAB LA-40Si, ADK STAB LA-402AF, ADK STAB LA-87, ADK STAB LA-82, ADK STAB LA-81, ADK STAB LA-77Y, ADK STAB LA-77G, ADK STAB LA-72, ADK STAB LA-68, ADK STAB LA-63P, ADK STAB LA-57, and ADK STAB LA-52 (all manufactured by ADEKA Corporation); Chimassorb (registered trademark) 2020FDL, Chimassorb 944FDL, Chimassorb 944LD, Tinuvin (registered trademark) 622SF, Tinuvin PA144, Tinuvin 765, Tinuvin 770DF, Tinuvin XT55FB, Tinuvin 111FDL, Tinuvin 783FDL, and Tinuvin 791FB (all manufactured by BASF Corporation).

[0052]

Examples of the nitroso-based polymerization inhibitor include, but are not limited to, p-nitrosophenol, N-nitrosodiphenylamine, and N-nitrosophenylhydroxyamine (cupferron), etc. Among these, N-nitrosophenylhydroxyamine ammonium salt (cupferron) is preferred.

[0053]

Examples of the nitroxyl radical polymerization inhibitor include, but are not limited to: di-tert-butyl nitroxide, 2,2,6,6-tetramethylpiperidine-1-oxyl, 4-hydroxy-2,2,6,6-tetramethylpiperidine-1-oxyl, 4-oxo-2,2,6,6-tetramethylpiperidine-1-oxyl, 4-amino-2,2,6,6-tetramethylpiperidine-1-oxyl, 4-methoxy-2,2,6,6-tetramethylpiperidine-1-oxyl, 4-acetoxy-

2,2,6,6-tetramethylpiperidine-1-oxyl, 4-benzoyloxy-2,2,6,6-tetramethylpiperidine-1-oxyl, and the like.

[0054]

[Flame retardant]

5           The curable resin composition of the present embodiment may contain a flame retardant. Examples of the flame retardant include halogen-based flame retardants, inorganic flame retardants (antimony compounds, metal hydroxides, nitrogen compounds, boron compounds, etc.), and phosphorus-based flame retardants. From the viewpoint of achieving halogen-free flame retardancy, phosphorus-based flame retardants are preferred.

10           The phosphorus-based flame retardant may be either a reactive type or an additive type. Specific examples include, but are not limited to: phosphoric acid esters such as trimethyl phosphate, triethyl phosphate, tricresyl phosphate, trixylyleneyl phosphate, cresyl diphenyl phosphate, cresyl-2,6-dixylyleneyl phosphate, 1,3-phenylene bis(dixylyleneyl phosphate), 1,4-phenylene bis(dixylyleneyl phosphate), and 4,4'-biphenyl(dixylyleneyl phosphate); phosphanes such as 9,10-dihydro-9-oxa-10-phosphaphenanthrene-10-oxide and 15 10-(2,5-dihydroxyphenyl)-10H-9-oxa-10-phosphaphenanthrene-10-oxide; as well as phosphorus-containing epoxy compounds obtained by reacting an epoxy resin with the active hydrogen of the phosphanes, red phosphorus, and the like. These may be used alone or in combination. Of the above-listed substances, phosphates, phosphanes, or phosphorus- 20 containing epoxy compounds are preferred, with 1,3-phenylenebis(dixylilenyl phosphate), 1,4-phenylenebis(dixylilenyl phosphate), 4,4'-biphenyl(dixylilenyl phosphate) or phosphorus-containing epoxy compounds being particularly preferred.

[0055]

          The content of the flame retardant is preferably in the range of 0.1 to 0.6 parts by 25 mass per 100 parts by mass of the curable resin composition. If the content is less than 0.1

part by mass, the flame retardancy may be insufficient, and if the content is more than 0.6 part by mass, the moisture absorption and dielectric properties of the cured product may be adversely affected.

[0056]

5 [Light Stabilizer]

The curable resin composition of the present embodiment may contain a light stabilizer. As the light stabilizer, a hindered amine light stabilizer (Hindered Amine Light Stabilizers, HALS) or the like is preferable. Examples of HALS include, but are not limited to: reaction products of dibutylamine, 1,3,5-triazine, N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)-1,6-hexamethylenediamine and N-(2,2,6,6-tetramethyl-4-piperidyl)butylamine, reaction products of dimethyl succinate-1-(2-hydroxyethyl)-4-hydroxy-2,2,6,6-tetramethylpiperidine, poly[ {6-(1,1,3,3-tetramethylbutyl)amino-1,3,5-triazine-2,4-diyl} {(2,2,6,6-tetramethyl-4-piperidyl)imino} hexamethylene {(2,2,6,6-tetramethyl-4-piperidyl)imino} ], bis(1,2,2,6,6-pentamethyl-4-piperidyl)[[3,5-bis(1,1-dimethylethyl)-4-hydroxyphenyl]methyl]butyl malonate, bis(2,2,6,6-tetramethyl-4-piperidyl)sebacate, bis(1,2,2,6,6-pentamethyl-4-piperidyl)sebacate, bis(1-octyloxy-2,2,6,6-tetramethyl-4-piperidyl)sebacate, 2-(3,5-di-t-butyl-4-hydroxybenzyl)-2-n-butylmalonate bis(1,2,2,6,6-pentamethyl-4-piperidyl), and the like. These may be used alone or in combination.

[0057]

20 The content of the light stabilizer is preferably in the range of 0.001 to 0.1 parts by mass in 100 parts by mass of the curable resin composition. If the content is less than 0.001 part by mass, the light stabilizing effect may be insufficient, and if the content is more than 0.1 part by mass, the moisture absorption and dielectric properties of the cured product may be adversely affected.

25 [0058]

#### [Binder Resin]

The curable resin composition of the present embodiment may use a binder resin. Examples of binder resins include, but are not limited to, butyral resins, acetal resins, acrylic resins, epoxy-nylon resins, NBR-phenol resins, epoxy-NBR resins, and silicone resins. These may be used alone or in combination.

[0059]

The amount of the binder resin is preferably within a range that does not impair the flame retardancy and heat resistance of the cured product, and is preferably 0.05 to 50 parts by mass, and more preferably 0.05 to 20 parts by mass, per 100 parts by mass of the curable resin composition, as needed.

[0060]

#### [Additives]

The curable resin composition of the present embodiment may contain additives. Examples of the additives include modified acrylonitrile copolymers, polyethylene, fluororesins, silicone gels, silicone oils, surface treatment agents for fillers such as silane coupling agents, release agents, and colorants such as carbon black, phthalocyanine blue, and phthalocyanine green.

[0061]

The amount of the additive is preferably 30 parts by mass or less, more preferably 20 parts by mass or less, and particularly preferably 10 parts by mass or less, based on 100 parts by mass of the curable resin composition.

[0062]

The curable resin composition of the present embodiment may further include epoxy resins, active ester compounds, phenolic resins, polyphenylene ether compounds, amine resins, compounds having two or more ethylenically unsaturated double bonds in the

molecule, isocyanate resins, polyamide resins, maleimide compounds having two or more maleimide groups in the molecule, cyanate ester resins, polyimide resins, polybutadiene and modified products thereof, polystyrene and modified products thereof, polyethylene and modified products thereof, etc., which may be used alone or in combination. Among these compounds, from the perspective of the balance of heat resistance, adhesion, and dielectric properties, it is preferable to contain maleimide compounds having two or more maleimide groups in the molecule, polyphenylene ether compounds, compounds having two or more ethylenically unsaturated double bonds in the molecule, cyanate ester resins, polybutadiene and modified products thereof, polystyrene and modified products thereof, and polyethylene and modified products thereof. By containing these compounds, the brittleness of the cured product can be improved and adhesion to metals can be improved, and cracks in the package during reliability tests such as solder reflow and thermal cycles can be suppressed. The total amount of the above compounds used is preferably 10 times by mass or less, more preferably 5 times by mass or less, and particularly preferably 3 times by mass or less, relative to the mixture of this embodiment, unless otherwise specified. The preferred lower limit is 0.1 times by mass or more, more preferably 0.25 times by mass or more, and even more preferably 0.5 times by mass or more. By being within the above range, the effect of each compound added can be added while taking advantage of the effect of the low dielectric characteristic (low dielectric tangent) of the compound represented by the formula (1). As these components, the following examples can be used.

[0063]

[Epoxy resin]

Preferred examples of the epoxy resin are shown below, but are not limited to these.

The epoxy resin may be liquid or solid, and may be used alone or in combination.

[0064]

Examples of liquid epoxy resins include bisphenol A type epoxy resins, bisphenol F type epoxy resins, bisphenol AF type epoxy resins, naphthalene type epoxy resins, glycidyl ester type epoxy resins, glycidyl amine type epoxy resins, phenol novolac type epoxy resins, alicyclic epoxy resins having an ester skeleton, cyclohexane type epoxy resins, cyclohexane dimethanol type epoxy resins, and epoxy resins having a butadiene structure. Specific examples include "RE310S", "RE410S" (all manufactured by Nippon Kayaku Co., Ltd., bisphenol A type epoxy resin), "RE303S", "RE304S", "RE403S", "RE404S" (all manufactured by Nippon Kayaku Co., Ltd., bisphenol F type epoxy resin), "HP-4032", "HP-4032D", "HP-4032SS" (all manufactured by DIC Corporation, naphthalene type epoxy resin), "jER (registered trademark) 828US", "jER828EL", "jER825" (all manufactured by Mitsubishi Chemical Corporation, bisphenol A type epoxy resin), "jER807", "jER1750" (all manufactured by Mitsubishi Chemical Corporation, bisphenol F type epoxy resin), "jER152" (manufactured by Mitsubishi Chemical Corporation, phenol novolac type epoxy resin), "jER630", "jER630LSD" (all manufactured by Mitsubishi Chemical Corporation, glycidylamine type epoxy resin), "ZX1059" (manufactured by Nippon Steel & Sumitomo Metal Chemical Co., Ltd., a mixture of bisphenol A type epoxy resin and bisphenol F type epoxy resin), "EX-721" (manufactured by Nagase ChemteX Corporation, glycidyl ester type epoxy resin), "Celloxide (registered trademark) 2021P" (manufactured by Daicel Corporation, alicyclic epoxy resin having an ester skeleton), "PB-3600" (manufactured by Daicel Corporation, epoxy resin having a butadiene structure), "ZX1658", "ZX1658GS" (all manufactured by Nippon Steel & Sumitomo Metal Chemical Co., Ltd., liquid 1,4-glycidylcyclohexane type epoxy resin), and the like. These may be used alone or in combination of two or more.

[0065]

Examples of solid epoxy resins include bixylenol type epoxy resins, naphthalene type

epoxy resins, naphthalene type tetrafunctional epoxy resins, cresol novolac type epoxy resins, dicyclopentadiene type epoxy resins, trisphenol type epoxy resins, naphthol type epoxy resins, biphenyl type epoxy resins, naphthylene ether type epoxy resins, anthracene type epoxy resins, bisphenol A type epoxy resins, bisphenol AF type epoxy resins, and tetraphenylethane

5 type epoxy resins, and naphthol type epoxy resins, bisphenol AF type epoxy resins, naphthalene type epoxy resins, and biphenyl type epoxy resins are preferred. Specific examples include "HP4032H" (manufactured by DIC Corporation, naphthalene type epoxy resin), "HP-4700", and "HP-4710" (all manufactured by DIC Corporation, naphthalene type tetrafunctional epoxy resin), "N-690" (manufactured by DIC Corporation, cresol novolac type

10 epoxy resin), "N-695" (manufactured by DIC Corporation, cresol novolac type epoxy resin), "HP-7200", "HP-7200HH", and "HP-7200H" (all manufactured by DIC Corporation, dicyclopentadiene type epoxy resin). epoxy resin), "EXA-7311", "EXA-7311-G3", "EXA-7311-G4", "EXA-7311-G4S", "HP-6000" (all manufactured by DIC Corporation, naphthylene ether type epoxy resin), "EPPN-502H" (manufactured by Nippon Kayaku Co., Ltd., trisphenol

15 type epoxy resin), "NC-7000L", "NC-7300" (all manufactured by Nippon Kayaku Co., Ltd., naphthol-cresol novolac type epoxy resin), "NC-3000H", "NC-3000", "NC-3000L", "NC-3100" (all manufactured by Nippon Kayaku Co., Ltd., biphenyl aralkyl type epoxy resin), "XD-1000-2L", "XD-1000-L", "XD-1000-H" (all manufactured by Nippon Kayaku Co., Ltd., dicyclopentadiene type epoxy resin), "ESN475V" (manufactured by Nippon Steel & Sumikin

20 Chemical Co., Ltd., naphthol type epoxy resin), "ESN485" (manufactured by Nippon Steel & Sumikin Chemical Co., Ltd., naphthol novolac type epoxy resin), "YX-4000H", "YX-4000", "YL6121" (all manufactured by Mitsubishi Chemical Corporation, biphenyl type epoxy resin), "YX-4000HK" (manufactured by Mitsubishi Chemical Corporation, bixyl olefin type epoxy resin), "YX-8800" (manufactured by Mitsubishi Chemical Corporation, anthracene

25 type epoxy resin), "PG-100", "CG-500" (manufactured by Osaka Gas Chemical Co., Ltd.,

fluorene type epoxy resin), "YL-7760" (manufactured by Mitsubishi Chemical Corporation, bisphenol AF type epoxy resin), "YL-7800" (manufactured by Mitsubishi Chemical Corporation, fluorene type epoxy resin), "jER1010" (manufactured by Mitsubishi Chemical Corporation, solid bisphenol A type epoxy resin), "jER1031S" (manufactured by Mitsubishi Chemical Corporation, tetraphenylethane type epoxy resin), etc. These may be used alone or in combination of two or more.

[0066]

[Active ester compound]

The active ester compound refers to a compound that contains at least one ester bond in the structure and has an aliphatic chain, an aliphatic ring, or an aromatic ring bonded to both sides of the ester bond. Examples of the active ester compound include compounds having two or more highly reactive ester groups in one molecule, such as phenol esters, thiophenol esters, N-hydroxyamine esters, and esters of heterocyclic hydroxy compounds, and are obtained by a condensation reaction between at least one compound of a carboxylic acid compound, an acid chloride, or a thiocarboxylic acid compound and at least one compound of a hydroxy compound or a thiol compound. In particular, from the viewpoint of improving heat resistance, it is preferable to obtain the active ester compound from a carboxylic acid compound or an acid chloride and a hydroxy compound, and the hydroxy compound is preferably a phenol compound or a naphthol compound. The active ester compound may be used alone or in combination of two or more types.

[0067]

Examples of the carboxylic acid compound include benzoic acid, acetic acid, succinic acid, maleic acid, itaconic acid, phthalic acid, isophthalic acid, terephthalic acid, and pyromellitic acid.

[0068]

Examples of the acid chloride include acetyl chloride, acrylic acid chloride, methacrylic acid chloride, malonyl chloride, succinic acid dichloride, diglycolyl chloride, glutaric acid dichloride, suberic acid dichloride, sebacic acid dichloride, adipic acid dichloride, dodecandioyl dichloride, azelaic acid chloride, 2,5-furandicarbonyl dichloride, phthaloyl chloride, isophthaloyl chloride, terephthaloyl chloride, trimesic acid chloride, bis(4-chlorocarbonylphenyl) ether, 4,4'-diphenyldicarbonyl chloride, and 4,4'-azodibenzoyl dichloride.

[0069]

Examples of the phenol compound and naphthol compound include hydroquinone, resorcin, bisphenol A, bisphenol F, bisphenol S, phenolphthalein, methylated bisphenol A, methylated bisphenol F, methylated bisphenol S, phenol, o-cresol, m-cresol, p-cresol, catechol,  $\alpha$ -naphthol,  $\beta$ -naphthol, 1,5-dihydroxynaphthalene, 1,6-dihydroxynaphthalene, 2,6-dihydroxynaphthalene, dihydroxybenzophenone, trihydroxybenzophenone, tetrahydroxybenzophenone, phloroglucin, benzenetriol, dicyclopentadiene-type diphenol compound, phenol novolak, and phenol resins described below. Here, the term "dicyclopentadiene-type diphenol compound" refers to a diphenol compound obtained by condensing one molecule of dicyclopentadiene with two molecules of phenol.

[0070]

Preferred specific examples of the active ester compound include an active ester compound containing a dicyclopentadiene-type diphenol structure, an active ester compound containing a naphthalene structure, an active ester compound containing an acetylated product of phenol novolak, an active ester compound containing a benzoylated product of phenol novolak, a compound described in Example 2 of WO 2020/095829, and a compound disclosed in WO 2020/059625. Among them, an active ester compound containing a naphthalene structure and an active ester compound containing a dicyclopentadiene-type

diphenol structure are more preferred. The dicyclopentadiene-type diphenol structure refers to a divalent structural unit consisting of phenylene-dicyclopentylene-phenylene.

[0071]

Commercially available active ester compounds include, for example: active ester  
5 compounds containing a dicyclopentadiene-type diphenol structure such as "EXB9451",  
"EXB9460", "EXB9460S", "HPC-8000-65T", "HPC-8000H-65TM", "EXB-8000L-65TM",  
and "EXB-8150-65T" (manufactured by DIC Corporation); active ester compounds  
containing a naphthalene structure such as "EXB9416-70BK" (manufactured by DIC  
Corporation); active ester compounds containing an acetylated product of phenol novolac  
10 such as "DC808" (manufactured by Mitsubishi Chemical Corporation); active ester  
compounds containing a benzoylated product of phenol novolac such as "YLH1026",  
"YLH1030", and "YLH1048" (manufactured by Mitsubishi Chemical Corporation); active  
ester-based hardeners which are acetylated products of phenol novolac such as "DC808"  
(manufactured by Mitsubishi Chemical Corporation); and active ester-based hardeners  
15 containing a phosphorus atom such as "EXB-9050L-62M" (manufactured by DIC  
Corporation).

[0072]

Regarding the compounding ratio of the active ester compound and the epoxy resin,  
the ratio ( $\alpha/\beta$ ) of the active ester equivalent ( $\alpha$ ) to the epoxy equivalent ( $\beta$ ) is preferably 0.5 to  
20 1.5, more preferably 0.8 to 1.2, and even more preferably 0.90 to 1.10. If it is out of the above  
range, there is a risk that excess epoxy groups or active ester groups will remain in the  
system, and the characteristics may deteriorate in a high-temperature storage test (e.g., 150°C,  
1000 hours) or a long-term reliability test under high-temperature and high-humidity  
conditions (e.g., temperature: 85°C, humidity: 85%).

25 [0073]

### [Phenol resin]

Phenol resin is a compound having two or more phenolic hydroxy groups in the molecule. Examples of phenol resin include, but are not limited to, reaction products of phenols and aldehydes, reaction products of phenols and diene compounds, reaction products of phenols and ketones, reaction products of phenols and substituted biphenyls, reaction products of phenols and substituted phenyls, reaction products of bisphenols and aldehydes, etc. Furthermore, these may be used alone or in combination.

Specific examples of the above raw materials are shown below, but are not limited to these.

#### <Phenols>

- 10 Phenol, alkyl-substituted phenol, aromatic-substituted phenol, hydroquinone, resorcin, naphthol, alkyl-substituted naphthol, dihydroxybenzene, alkyl-substituted dihydroxybenzene, dihydroxynaphthalene, etc.

#### <Aldehydes>

- 15 Formaldehyde, acetaldehyde, alkyl aldehyde, benzaldehyde, alkyl-substituted benzaldehyde, hydroxybenzaldehyde, naphthaldehyde, glutaraldehyde, phthalaldehyde, crotonaldehyde, cinnamaldehyde, furfural, etc.

#### <Diene compounds>

- 20 Dicyclopentadiene, terpenes, vinylcyclohexene, norbornadiene, vinylnorbornene, tetrahydroindene, divinylbenzene, divinylbiphenyl, diisopropenylbiphenyl, butadiene, isoprene, etc.

#### <Ketones>

Acetone, methyl ethyl ketone, methyl isobutyl ketone, acetophenone, benzophenone, fluorenone, etc.

#### <Substituted biphenyls>

- 25 4,4'-bis(chloromethyl)-1,1'-biphenyl, 4,4'-bis(methoxymethyl)-1,1'-biphenyl, 4,4'-

bis(hydroxymethyl)-1,1'-biphenyl, etc.

<Substituted phenyls>

1,4-bis(chloromethyl)benzene, 1,4-bis(methoxymethyl)benzene, 1,4-bis(hydroxymethyl)benzene, etc.

5 [0074]

[Polyphenylene ether compound]

From the viewpoint of heat resistance and electrical properties, the polyphenylene ether compound is preferably a polyphenylene ether compound having two or more ethylenically unsaturated double bonds in the molecule, and more preferably a polyphenylene ether compound having an acrylic group, a methacrylic group, or a styrene structure. Commercially available products include SA-9000 (manufactured by SABIC, a polyphenylene ether compound having a methacrylic group) and OPE-2St 1200 (manufactured by Mitsubishi Gas Chemical Co., Ltd., a polyphenylene ether compound having a styrene structure).

15 The number average molecular weight (Mn) of the polyphenylene ether compound is preferably 500 to 5000, more preferably 2000 to 5000, and more preferably 2000 to 4000. If the molecular weight is less than 500, the heat resistance of the cured product tends to be insufficient. In addition, if the molecular weight is more than 5000, the melt viscosity becomes high and sufficient fluidity cannot be obtained, which tends to cause molding defects. In addition, the reactivity is also reduced, the curing reaction takes a long time, and the amount of unreacted compounds not incorporated into the curing system increases, which leads to a decrease in the glass transition temperature of the cured product and a decrease in the heat resistance of the cured product.

25 If the number average molecular weight of the polyphenylene ether compound is 500 to 5000, excellent heat resistance and moldability can be achieved while maintaining excellent

dielectric properties. The number average molecular weight here can be specifically measured using gel permeation chromatography or the like.

[0075]

The polyphenylene ether compound may be one obtained by a polymerization  
5 reaction, or one obtained by a redistribution reaction of a high molecular weight  
polyphenylene ether compound having a number average molecular weight of about 10,000 to  
30,000. In addition, these may be used as raw materials and reacted with a compound having  
an ethylenically unsaturated double bond, such as methacryl chloride, acrylic chloride, or  
chloromethylstyrene, to impart radical polymerizability. The polyphenylene ether compound  
10 obtained by the redistribution reaction is obtained, for example, by heating a high molecular  
weight polyphenylene ether compound in a solvent such as toluene in the presence of a  
phenolic compound and a radical initiator to cause a redistribution reaction. The  
polyphenylene ether compound obtained by the redistribution reaction in this way has  
hydroxy groups derived from a phenolic compound that contributes to curing at both ends of  
15 the molecular chain, and is therefore preferable in that it can maintain even higher heat  
resistance, and that functional groups can be introduced at both ends of the molecular chain  
even after modification with a compound having an ethylenically unsaturated double bond. In  
addition, the polyphenylene ether compound obtained by the polymerization reaction is  
preferable in that it exhibits excellent fluidity.

20 [0076]

The molecular weight of the polyphenylene ether compound can be adjusted by  
adjusting the polymerization conditions, etc., in the case of a polyphenylene ether compound  
obtained by a polymerization reaction. In addition, in the case of a polyphenylene ether  
compound obtained by a redistribution reaction, the molecular weight of the obtained  
25 polyphenylene ether compound can be adjusted by adjusting the conditions, etc., of the

redistribution reaction. More specifically, it is possible to adjust the amount of the phenolic compound used in the redistribution reaction. That is, the greater the amount of the phenolic compound, the lower the molecular weight of the obtained polyphenylene ether compound. In this case, poly(2,6-dimethyl-1,4-phenylene ether) or the like can be used as the high molecular weight polyphenylene ether compound that undergoes the redistribution reaction. In addition, the phenolic compound used in the redistribution reaction is not particularly limited, but for example, a polyfunctional phenolic compound having two or more phenolic hydroxy groups in the molecule, such as bisphenol A, phenol novolac, cresol novolac, etc., is preferably used. These may be used alone or in combination of two or more.

10 [0077]

#### [Amine resin]

Amine resin is a compound having two or more amino groups in the molecule. Examples of amine resins include, but are not limited to: diaminodiphenylmethane, diaminodiphenylsulfone, isophoronediamine, naphthalenediamine, aniline novolak (a reaction product of aniline and formalin), N-methylaniline novolak (a reaction product of N-methylaniline and formalin), orthoethylaniline novolak (a reaction product of orthoethylaniline and formalin), a reaction product of 2-methylaniline and formalin, a reaction product of 2,6-diisopropylaniline and formalin, a reaction product of 2,6-diethylaniline and formalin, a reaction product of 2-ethyl-6-ethylaniline and formalin, a reaction product of 2,6-dimethylaniline and formalin, and a reaction product obtained by reacting aniline and xylylene chloride, a reaction product of aniline disclosed in Japanese Patent No. 6429862 and a substituted biphenyl (4,4'-bis(chloromethyl)-1,1'-biphenyl and 4,4'-bis(methoxymethyl)-1,1'-biphenyl, etc.), a reaction product of aniline and a substituted phenyl (1,4-bis(chloromethyl)benzene, 1,4-bis(methoxymethyl)benzene, 1,4-bis(hydroxymethyl)benzene, etc.), 4,4'-(1,3-phenylenediisopropylidene)bisaniline, 4,4'-(1,4-

15

20

25

phenylenediisopropylidene)bisaniline, a reaction product of aniline and diisopropenylbenzene, dimer diamine, etc. Furthermore, these may be used alone or in combination.

[0078]

- 5 [Compound containing two or more ethylenically unsaturated double bonds in the molecule]

The compound containing two or more ethylenically unsaturated double bonds in the molecule is a compound having two or more ethylenically unsaturated double bonds in the molecule that can be polymerized by heat or light.

- Examples of the compound containing two or more ethylenically unsaturated double bonds in the molecule include, but are not limited to: reaction products of the phenol resin described above with halogen-based compounds containing ethylenically unsaturated double bonds (chloromethylstyrene, allyl chloride, methallyl chloride, acrylic acid chloride, methacrylic acid chloride, etc.); reaction products of phenols containing ethylenically unsaturated double bonds (2-allylphenol, 2-propenylphenol, 4-allylphenol, 4-propenylphenol, eugenol, isoeugenol, etc.), with halogen-based compounds (1,4-bis(chloromethyl)benzene, 4,4'-bis(chloromethyl)biphenyl, 4,4'-difluorobenzophenone, 4,4'-dichlorobenzophenone, 4,4'-dibromobenzophenone, cyanuric chloride, etc.); in addition to the polyphenylene ether compound having two or more ethylenically unsaturated double bonds in the molecule reaction products of epoxy resins or alcohols with (meth)acrylic acids (acrylic acid, methacrylic acid, etc.) and acid-modified products thereof. These may be used alone or in combination.

[0079]

[Isocyanate Resin]

- An isocyanate resin is a compound having two or more isocyanate groups in the molecule. Examples of the isocyanate resin include, but are not limited to: aromatic

diisocyanates such as p-phenylene diisocyanate, m-phenylene diisocyanate, p-xylylene diisocyanate, m-xylylene diisocyanate, 2,4-tolylene diisocyanate, 2,6-tolylene diisocyanate, 4,4'-diphenylmethane diisocyanate, and naphthalene diisocyanate; aliphatic or alicyclic diisocyanates such as isophorone diisocyanate, hexamethylene diisocyanate, 4,4'-dicyclohexylmethane diisocyanate, hydrogenated xylene diisocyanate, norbornene diisocyanate, and lysine diisocyanate; one or more biuret forms of isocyanate monomers; or polyisocyanates such as isocyanate forms obtained by trimerizing the diisocyanate compounds; and polyisocyanates obtained by a urethanization reaction between the isocyanate compounds and polyol compounds. These may be used alone or in combination.

10 [0080]

[Polyamide resin]

Examples of polyamide resins include reaction products of one or more of diamines, diisocyanates, and oxazolines with dicarboxylic acids, reaction products of diamines with acid chlorides, and ring-opening polymers of lactam compounds. These may be used alone or in combination.

15

Specific examples of the above-mentioned raw materials are shown below, but are not limited to these.

<Diamines>

Ethylenediamine, trimethylenediamine, tetramethylenediamine, pentamethylenediamine, hexamethylenediamine, heptamethylenediamine, octamethylenediamine, nonamethylenediamine, decanediamine, undecanediamine, dodecanediamine, tridecanediamine, tetradecanediamine, pentadecanediamine, hexadecanediamine, heptadecanediamine, octadecanediamine, nonadecanediamine, eicosanediamine, 2-methyl-1,5-diaminopentane, 2-methyl-1,8-diaminooctane, dimer diamine, cyclohexane diamine, bis-(4-aminocyclohexyl)methane, bis-(3-methyl-4-

25

aminocyclohexyl)methane, xylylene diamine, norbornane diamine, isophorone diamine, bisaminomethyltricyclodecane, phenylenediamine, diethyltoluenediamine, naphthalenediamine, diaminodiphenylmethane, bis(4-amino-3,5-dimethylphenyl)methane, bis(4-amino-3,5-diethylphenyl) methane, 4,4'-methylenebis-o-toluidine, 4,4'-methylenebis-o-ethylaniline, 4,4'-methylenebis-2-ethyl-6-methylaniline, 4,4'-methylenebis-2,6-diisopropylaniline, 4,4'-ethylenedianiline, diaminodiphenyl sulfone, diaminodiphenyl ether, 1,3-bis(3-aminophenoxy)benzene, 1,3-bis(4-aminophenoxy)benzene, 4,4-bis(4-aminophenoxy)biphenyl, 2,2-bis[4-(4-aminophenoxy)phenyl]propane, bis[4-(4-aminophenoxy)phenyl]sulfone, 2,2-bis(3-amino-4-hydroxyphenyl)propane, 2,2-bis(4-aminophenyl)hexafluoropropane, 4,4'-(1,3-phenylenediisopropylidene)bisaniiline, 4,4'-(1,4-phenylenediisopropylidene)bisaniiline, 9,9-bis(4-aminophenyl)fluorene, 2,7-diaminofluorene, aminobenzylamine, diaminobenzophenone, and the like.

#### <Diisocyanates>

Benzene diisocyanate, toluene diisocyanate, 1,3-bis(isocyanatomethyl)benzene, 1,3-bis(isocyanatomethyl)cyclohexane, bis(4-isocyanatophenyl)methane, isophorone diisocyanate, 1,3-bis(2-isocyanato-2-propyl)benzene, 2,2-bis(4-isocyanatophenyl)hexafluoropropane, dicyclohexylmethane-4,4'-diisocyanate, and the like.

#### <Dicarboxylic acids>

Oxalic acid, malonic acid, succinic acid, glutaric acid, adipic acid, suberic acid, azelaic acid, sebacic acid, undecanedioic acid, dodecanedioic acid, terephthalic acid, isophthalic acid, 5-hydroxyisophthalic acid, 2-chloroterephthalic acid, 2-methylterephthalic acid, 5-methylisophthalic acid, 5-sodium sulfoisophthalic acid, hexahydroterephthalic acid, hexahydroisophthalic acid, cyclohexanedicarboxylic acid, biphenyldicarboxylic acid, naphthalenedicarboxylic acid, benzophenonedicarboxylic acid, furandicarboxylic acid, 4,4'-dicarboxydiphenyl ether, 4,4'-dicarboxydiphenyl sulfide, and the like.

## &lt;Acid chlorides&gt;

Acetyl chloride, acrylic acid chloride, methacrylic acid chloride, malonyl chloride, succinic acid dichloride, diglycolyl chloride, glutaric acid dichloride, suberic acid dichloride, sebacic acid dichloride, adipic acid dichloride, dodecandioyl dichloride, azeloyl chloride, 2,5-furandicarbonyl dichloride, phthaloyl chloride, isophthaloyl chloride, terephthaloyl chloride, trimesic acid chloride, bis(4-chlorocarbonylphenyl) ether, 4,4'-diphenyldicarbonyl chloride, 4,4'-azodibenzoyl dichloride, etc.

## &lt;Lactams&gt;

$\epsilon$ -caprolactam,  $\omega$ -undecanelactam,  $\omega$ -laurolactam, etc.

10 [0081]

## [Polyimide resin]

Examples of polyimide resins include, but are not limited to, reaction products of the diamines described above with the following tetracarboxylic dianhydrides. These may be used alone or in combination.

15 <Tetracarboxylic dianhydrides>

4,4'-(hexafluoroisopropylidene)diphthalic anhydride, 5-(2,5-dioxotetrahydro-3-furanyl)-3-methyl-cyclohexene-1,2 dicarboxylic anhydride, pyromellitic dianhydride, 1,2,3,4-benzenetetracarboxylic dianhydride, 3,3',4,4'-benzophenonetetracarboxylic dianhydride, 2,2',3,3'-benzophenonetetracarboxylic dianhydride, 3,3',4,4'-biphenyltetracarboxylic dianhydride, 3,3',4,4'-diphenylsulfonate tetracarboxylic dianhydride, 2,2',3,3'-biphenyltetracarboxylic dianhydride, methylene-4,4'-diphthalic dianhydride, 1,1-ethylidene-4,4'-diphthalic dianhydride, 2,2'-propylidene-4,4'-diphthalic dianhydride, 1,2-ethylene-4,4'-diphthalic dianhydride, 1,3-trimethylene-4,4'-diphthalic dianhydride, 1,4-tetramethylene-4,4'-diphthalic dianhydride, 1,5-pentamethylene-4,4'-diphthalic dianhydride, 4,4'-oxydiphthalic dianhydride Anhydride, thio-4,4'-diphthalic dianhydride, sulfonyl-4,4'-diphthalic dianhydride,

20

25

- 1,3-bis(3,4-dicarboxyphenyl)benzene dianhydride, 1,3-bis(3,4-dicarboxyphenoxy)benzene dianhydride, 1,4-bis(3,4-dicarboxyphenoxy)benzene dianhydride, 1,3-bis[2-(3,4-dicarboxyphenyl)-2-propyl]benzene dianhydride, 1,4-bis[2-(3,4-dicarboxyphenyl)-2-propyl]benzene dianhydride, bis[3-(3,4-dicarboxyphenoxy)phenyl]methane dianhydride,
- 5 bis[4-(3,4-dicarboxyphenoxy)phenyl]methane dianhydride, 2,2-bis[3-(3,4-dicarboxyphenoxy)phenyl]propane dianhydride, 2,2-bis[4-(3,4-dicarboxyphenoxy)phenyl]propane dianhydride, bis(3,4-dicarboxyphenoxy)dimethylsilane dianhydride, 1,3-bis(3,4-dicarboxyphenyl)-1,1,3,3-tetramethyldisiloxane dianhydride, 2,3,6,7-Naphthalene tetracarboxylic dianhydride, 1,4,5,8-naphthalene tetracarboxylic dianhydride,
- 10 1,2,5,6-naphthalene tetracarboxylic dianhydride, 3,4,9,10-perylene tetracarboxylic dianhydride, 2,3,6,7-anthracene tetracarboxylic dianhydride, 1,2,7,8-phenanthrene tetracarboxylic dianhydride, ethylene tetracarboxylic dianhydride, 1,2,3,4-butane tetracarboxylic dianhydride, 1,2,3,4-cyclobutane tetracarboxylic dianhydride, cyclopentane tetracarboxylic dianhydride, cyclohexane-1,2,3,4-tetracarboxylic acid dianhydride,
- 15 cyclohexane-1,2,4,5-tetracarboxylic acid dianhydride, 3,3',4,4'-bicyclohexyltetracarboxylic acid dianhydride, carbonyl-4,4'-bis(cyclohexane-1,2-dicarboxylic acid) dianhydride, methylene-4,4'-bis(cyclohexane-1,2-dicarboxylic acid) dianhydride, 1,2-ethylene-4,4'-bis(cyclohexane-1,2-dicarboxylic acid) dianhydride, 1,1-ethylidene-4,4'-bis(cyclohexane-1,2-dicarboxylic acid) dianhydride, 2,2-propylidene-4,4'-bis(cyclohexane-1,2-dicarboxylic acid)
- 20 dianhydride, oxy-4,4'-bis(cyclohexane-1,2-dicarboxylic acid) dianhydride, thio-4,4'-bis(cyclohexane-1,2-dicarboxylic acid) dianhydride, sulfonyl-4,4'-bis(cyclohexane-1,2-dicarboxylic acid) dianhydride, bicyclo[2,2,2]oct-7-ene-2,3,5,6-tetracarboxylic acid dianhydride, rel-[1S,5R,6R]-3-oxabicyclo[3,2,1]octane-2,4-dione-6-spiro-3'-(tetrahydrofuran-2',5'-dione), 4-(2,5-dioxotetrahydrofuran-3-yl)-1,2,3,4-tetrahydronaphthalene-1,2-dicarboxylic
- 25 anhydride, ethylene glycol-bis-(3,4-dicarboxylic anhydride phenyl)ether, 4,4'-biphenyl

bis(trimellitic acid monoester acid anhydride), 9,9'-bis(3,4-dicarboxyphenyl)fluorene dianhydride, and the like.

[0082]

[Maleimide compound having two or more maleimide groups in the molecule]

5           The curable resin composition of the present embodiment may contain a maleimide compound having two or more maleimide groups in the molecule, and examples of such a maleimide compound include 4,4'-diphenylmethane bismaleimide, polyphenylmethane maleimide, m-phenylene bismaleimide, 2,2'-bis[4-(4-maleimidophenoxy)phenyl]propane, 3,3'-dimethyl-5,5'-diethyl-4,4'-diphenylmethane bismaleimide, 4-methyl-1,3-phenylene  
10   bismaleimide, 4,4'-diphenylether bismaleimide, 4,4'-diphenylsulfone bismaleimide, 1,3-bis(3-maleimidophenoxy)benzene, 1,3-bis(4-maleimidophenoxy)benzene, Xylok-type maleimide compounds (anilix maleimide, manufactured by Mitsui Chemicals Fine Co., Ltd.), biphenylaralkyl-type maleimide compound (solidified by distilling off the solvent under reduced pressure from a resin solution containing the maleimide compound (M2) described in  
15   Example 4 of JP 2009-001783 A), bisaminocumylbenzene-type maleimide (maleimide compound described in WO 2020/054601 A), maleimide compounds having an indane structure described in JP 6629692B or WO 2020/217679 A, and maleimide compounds described in MATERIAL STAGE Vol. 18, No. 12, 2019 "Sequel Epoxy Resin CAS Number Story – Hardener CAS Number Memorandum, No. 31 Bismaleimide (1)" and MATERIAL  
20   STAGE Vol. 19, No. 2, 2019 "Sequel Epoxy Resin CAS Number Story - Hardener CAS Number Memorandum, No. 32 Bismaleimide (2)". These compounds may be used alone or in combination.

[0083]

[Cyanate ester resin]

25           Cyanate ester resin is a cyanate ester compound obtained by reacting a phenol resin

with a cyanogen halide. Specific examples include dicyanatobenzene, tricyanatobenzene, dicyanatonaphthalene, dicyanatobiphenyl, 2,2'-bis(4-cyanatophenyl)propane, bis(4-cyanatophenyl)methane, bis(3,5-dimethyl-4-cyanatophenyl)methane, 2,2'-bis(3,5-dimethyl-4-cyanatophenyl)propane, 2,2'-bis(4-cyanatophenyl)ethane, 2,2'-bis(4-cyanatophenyl)hexafluoropropane, bis(4-cyanatophenyl)sulfone, bis(4-cyanatophenyl)thioether, phenol novolac cyanate, and phenol-dicyclopentadiene co-condensates in which the hydroxy groups have been converted to cyanate groups, but are not limited thereto. These may be used alone or in combination.

The cyanate ester compound, the synthesis method of which is described in JP-A-2005-264154, is particularly preferred as the cyanate ester compound, since it has low moisture absorption, flame retardancy, and excellent dielectric properties.

The cyanate ester resin may contain a catalyst such as zinc naphthenate, cobalt naphthenate, copper naphthenate, lead naphthenate, zinc octylate, tin octylate, lead acetylacetonate, or dibutyltin maleate, in order to trimerize the cyanate group to form a sym-triazine ring, as necessary.

[0084]

The catalyst is preferably used in an amount of 0.0001 to 0.10 parts by mass, and more preferably 0.00015 to 0.0015 parts by mass, per 100 parts by mass of the cyanate ester resin and the curable resin composition.

[0085]

[Polybutadiene and its modified products]

Polybutadiene and its modified products are compounds having polybutadiene or a structure derived from polybutadiene in the molecule. The structure derived from polybutadiene may have some or all of the unsaturated bonds converted to single bonds by hydrogenation.

Examples of polybutadiene and its modified products include, but are not limited to, polybutadiene, hydroxy-terminated polybutadiene, (meth)acrylate-terminated polybutadiene, carboxylic acid-terminated polybutadiene, amine-terminated polybutadiene, styrene butadiene rubber, etc. Also, these may be used alone or in combination. Of these, polybutadiene or  
5 styrene butadiene rubber is preferred from the viewpoint of dielectric properties. Examples of styrene butadiene rubber (SBR) include RICON-100, RICON-181, and RICON-184 (all manufactured by Cray Valley Corporation), and 1,2-SBS (manufactured by Nippon Soda Co., Ltd.). Examples of polybutadiene include B-1000, B-2000, and B-3000 (all manufactured by Nippon Soda Co., Ltd.). The molecular weight of polybutadiene and styrene butadiene rubber  
10 is preferably a weight average molecular weight of 500 to 10,000, more preferably 750 to 7,500, and even more preferably 1,000 to 5,000. Below the lower limit of the above range, the amount of volatilization is large, making it difficult to adjust the solid content when preparing the prepreg, and above the upper limit of the above range, the compatibility with other curable resins is deteriorated. In general, in the case of compounds containing heteroatoms such as  
15 oxygen and nitrogen, such as bismaleimide and polymaleimide, it is difficult to ensure compatibility with low-polarity compounds such as compounds mainly composed of hydrocarbons or compounds composed only of hydrocarbons due to their polarity. On the other hand, the compound of the present embodiment does not have a skeleton design in which heteroatoms such as oxygen and nitrogen are actively introduced, and therefore has  
20 excellent compatibility with materials exhibiting low polarity and low dielectric tangent, and with compounds composed only of hydrocarbons.

[0086]

[Polystyrene and modified products thereof]

Polystyrene and modified products thereof are polystyrene or compounds having a  
25 structure derived from polystyrene in the molecule.

Examples of polystyrene and modified products thereof include, but are not limited to: polystyrene, styrene-2-isopropenyl-2-oxazoline copolymers (Epocross RPS-1005, RP-61, both manufactured by Nippon Shokubai Co., Ltd.), SEP (styrene-ethylene-propylene copolymer: Septon (registered trademark) 1020, manufactured by Kuraray Co., Ltd.), SEPS (styrene-ethylene-propylene-styrene copolymer: Septon 2002, Septon 2004F, Septon 2005, Septon 2006, Septon 2063, Septon 2104, all manufactured by Kuraray Co., Ltd.), SEEPS (styrene-ethylene/ethylene-propylene-styrene block copolymer: Septon 4003, Septon 4044, Septon 4055, Septon 4077, Septon 4099, all manufactured by Kuraray Co., Ltd.), and SEBS (styrene-ethylene-butylene-styrene block copolymer: Septon 8004, Septon 8006, Septon 8007L, all manufactured by Kuraray Co., Ltd.), SEEPS-OH (a styrene-ethylene/ethylene propylene-styrene block copolymer having a hydroxy group at the end: SEPTON HG252, manufactured by Kuraray Co., Ltd.), SIS (styrene-isoprene-styrene block copolymer: SEPTON 5125, SEPTON 5127, manufactured by Kuraray Co., Ltd.), hydrogenated SIS (hydrogenated styrene-isoprene-styrene block copolymer: HYBLER (registered trademark) 7125F, HYBLER 7311F, manufactured by Kuraray Co., Ltd.), SIBS (styrene-isobutylene-styrene block copolymer: SIBSTAR (registered trademark) 073T, SIBSTAR 102T, SIBSTAR 103T (all manufactured by Kaneka Corporation), SEPTON V9827 (manufactured by Kuraray Co., Ltd.)). These may be used alone or in combination. Polystyrene and modified products thereof have higher heat resistance and are less susceptible to oxidative deterioration, so it is preferable that they do not have unsaturated bonds. The weight-average molecular weight of polystyrene and modified products thereof is not particularly limited as long as it is 10,000 or more, but if it is too large, the compatibility with not only polyphenylene ether compounds but also low molecular weight components with a weight-average molecular weight of about 50 to 1,000 and oligomer components with a weight-average molecular weight of about 1,000 to 5,000 deteriorates, making it difficult to ensure mixing and solvent stability, so it is

preferably about 10,000 to 300,000.

[0087]

[Polyethylene and modified products thereof]

Polyethylene and modified products thereof are compounds having polyethylene or a  
5 structure derived from polyethylene in the molecule. Examples of polyethylene and modified  
products thereof include ethylene-propylene copolymers, ethylene-styrene copolymers,  
ethylene-propylene-ethylidene norbornene copolymers (EBT: K-8370EM, K-9330M, etc.,  
manufactured by Mitsui Chemicals, Inc.), ethylene-propylene-vinyl norbornene copolymers  
(VNB-EPT: PX-006M, PX-008M, PX-009M, etc., manufactured by Mitsui Chemicals, Inc.),  
10 ethylene-vinyl alcohol copolymers, ethylene-vinyl acetate copolymers, etc., but are not  
limited thereto. From the viewpoint of improving heat resistance, it is preferable to use  
ethylene-propylene-ethylidene norbornene copolymers and ethylene-propylene-vinyl  
norbornene copolymers containing a crosslinkable structure. In addition, these may be used  
alone or in combination. The weight average molecular weight of the polyethylene and  
15 modified products thereof is not particularly limited as long as it is 10,000 or more. However,  
if it is too large, compatibility with not only the polyphenylene ether compound but also low  
molecular weight components having a weight average molecular weight of about 50 to 1,000  
and oligomer components having a weight average molecular weight of about 1,000 to 5,000  
deteriorates, making it difficult to ensure mixing and solvent stability. Therefore, it is  
20 preferably about 10,000 to 300,000.

[0088]

The curable resin composition of the present embodiment can be obtained by  
preparing the above-mentioned components in a predetermined ratio, pre-curing at 130 to  
180°C for 30 to 500 seconds, and then post-curing at 150 to 200°C for 2 to 15 hours, whereby  
25 a sufficient curing reaction proceeds to obtain a cured product of the present embodiment.

Alternatively, the components of the curable resin composition can be uniformly dispersed or dissolved in a solvent or the like, and cured after removing the solvent.

[0089]

The method for preparing the curable resin composition of the present embodiment is not particularly limited, but each component may be mixed uniformly or may be prepolymerized. For example, a mixture containing the compound of the present embodiment is heated in the presence or absence of a curing accelerator or a polymerization initiator, and in the presence or absence of a solvent to form a prepolymer. Similarly, an amine compound, a compound having an ethylenically unsaturated bond, a maleimide compound, a cyanate ester compound, polybutadiene and its modified products, polystyrene and its modified products, inorganic fillers, and other additives may be added to form a prepolymer. The mixing or prepolymerization of each component is carried out using, for example, an extruder, a kneader, a roll, or the like in the absence of a solvent, and a reaction kettle with a stirrer in the presence of a solvent.

[0090]

As a method of uniform mixing, the materials are mixed at a temperature in the range of 50 to 100°C by kneading with a device such as a kneader, roll, or planetary mixer to obtain a uniform resin composition. The obtained resin composition is crushed and then molded into a cylindrical tablet shape using a molding machine such as a tablet machine, or into a granular powder or powder molded body, or these compositions can be melted on a surface support and molded into a sheet shape with a thickness of 0.05 mm to 10 mm to obtain a molded curable resin composition. The obtained molded body is a non-sticky molded body at 0 to 20°C, and even if stored at -25 to 0°C for one week or more, the flowability and curability are hardly reduced.

The obtained molded body can be molded into a cured product using a transfer

molding machine or a compression molding machine.

[0091]

The curable resin composition of the present embodiment can be made into a varnish-like composition (hereinafter, simply referred to as varnish) by adding an organic solvent. The curable resin composition of the present embodiment can be dissolved in a solvent such as toluene, xylene, acetone, methyl ethyl ketone, methyl isobutyl ketone, dimethylformamide, dimethylacetamide, or N-methylpyrrolidone as necessary to form a varnish, which is then impregnated into a substrate such as glass fiber, carbon fiber, polyester fiber, polyamide fiber, alumina fiber, or paper, and dried by heating to obtain a prepreg, which is then hot-press molded to obtain a cured product of the curable resin composition of the present embodiment. The solvent used in this case is in an amount that occupies 10 to 70% by weight, preferably 15 to 70% by weight, in the mixture of the curable resin composition of the present embodiment and the solvent. In addition, if the composition is in a liquid state, a cured product of the curable resin containing carbon fiber can be obtained as it is, for example, by the RTM method.

[0092]

The curable resin composition of the present embodiment can also be used as a modifier for a film-type composition. Specifically, it can be used to improve flexibility and the like in the B-stage. Such a film-type resin composition can be obtained as a sheet-like adhesive by applying the curable resin composition of the present embodiment as a varnish onto a release film, removing the solvent under heating, and then performing B-stage formation. This sheet-like adhesive can be used as an interlayer insulating layer in a multilayer substrate or the like.

[0093]

The curable resin composition of the present embodiment can be heated and melted

to reduce the viscosity, and impregnated into reinforced fibers such as glass fibers, carbon fibers, polyester fibers, polyamide fibers, and alumina fibers to obtain a prepreg. Specific examples thereof include glass fibers such as E glass cloth, D glass cloth, S glass cloth, Q glass cloth, spherical glass cloth, NE glass cloth, and T glass cloth, inorganic fibers other than glass, and organic fibers such as polyparaphenylene terephthalamide (Kevlar (registered trademark), manufactured by DuPont), wholly aromatic polyamide, polyester, polyparaphenylene benzoxazole, polyimide, and carbon fibers, but are not particularly limited thereto. The shape of the substrate is not particularly limited, but examples thereof include woven fabric, nonwoven fabric, roving, chopped strand mat, and the like. In addition, as the weaving method of the woven fabric, plain weave, saddle weave, twill weave, and the like are known, and these known weaves can be appropriately selected and used depending on the intended use and performance. In addition, woven fabrics that have been subjected to fiber opening treatment and glass woven fabrics that have been surface-treated with a silane coupling agent or the like are preferably used. The thickness of the substrate is not particularly limited, but is preferably about 0.01 to 0.4 mm. A prepreg can also be obtained by impregnating reinforcing fibers with the varnish and drying the fibers by heating.

[0094]

Moreover, a laminate can be manufactured using the prepreg. The laminate is not particularly limited as long as it has one or more prepregs, and may have any other layer. The manufacturing method of the laminate can be appropriately applied by a generally known method, and is not particularly limited. For example, when molding a metal foil-clad laminate, a multi-stage press machine, a multi-stage vacuum press machine, a continuous molding machine, an autoclave molding machine, etc. can be used, and the prepregs are laminated together and heated and pressurized to obtain a laminate. At this time, the heating temperature is not particularly limited, but is preferably 65 to 300 °C, and more preferably

120 to 270 °C. In addition, the pressure to be applied is not particularly limited, but if the pressure is too high, it is difficult to adjust the solid content of the resin of the laminate, and the quality is not stable, and if the pressure is too low, air bubbles and adhesion between the laminates are deteriorated, so that 2.0 to 5.0 MPa is preferable, and 2.5 to 4.0 MPa is more preferable. The laminate of this embodiment can be suitably used as a metal foil-clad laminate described later by providing a layer made of metal foil.

The prepreg is cut into a desired shape and laminated with copper foil or the like as necessary. The laminate is then heated and cured while applying pressure thereto by press molding, autoclave molding, sheet winding molding or the like, to obtain an electrical and electronic laminate (printed wiring board) or a carbon fiber reinforced material.

[0095]

The curable resin composition of this embodiment can also be made into a resin sheet. As a method for obtaining a resin sheet from the curable resin composition of this embodiment, for example, a method of applying the curable resin composition onto a support film (support), drying it, and forming a resin composition layer on the support film can be mentioned. When the curable resin composition of this embodiment is used for a resin sheet, it is essential that the film softens under the temperature conditions (70 °C to 140 °C) of lamination in the vacuum lamination method, and simultaneously with lamination of the circuit board, exhibits a fluidity (resin flow) that allows resin filling in via holes or through holes present in the circuit board, and it is preferable to blend each of the components so as to express such characteristics. In addition, in the obtained resin sheet or circuit board (copper-clad laminate, etc.), a phenomenon that locally different characteristic values are exhibited due to phase separation or the like is not caused, and a certain performance is expressed at any part, so that a uniform appearance is required.

[0096]

Here, the diameter of the through-holes in the circuit board is 0.1 to 0.5 mm, and the depth is 0.1 to 1.2 mm, and it is preferable to make it possible to fill the resin within this range. When laminating both sides of the circuit board, it is preferable to fill about 1/2 of the through-holes.

5 [0097]

A specific method for producing the resin sheet includes preparing a resin composition varnished by blending an organic solvent, applying the varnished resin composition to the surface of a support film (Y), and then drying the organic solvent by heating or blowing hot air or the like to form a resin composition layer (X).

10 [0098]

The organic solvent used here is preferably, for example: ketones such as acetone, methyl ethyl ketone, and cyclohexanone; acetate esters such as ethyl acetate, butyl acetate, cellosolve acetate, propylene glycol monomethyl ether acetate, carbitol acetate; carbitols such as cellosolve and butyl carbitol; aromatic hydrocarbons such as toluene and xylene; dimethylformamide, dimethylacetamide, N-methylpyrrolidone, etc. It is also preferable to use an organic solvent in such a proportion that the nonvolatile content is 30 to 60 mass % of the total.

[0099]

The thickness of the resin composition layer (X) to be formed must be equal to or greater than the thickness of the conductor layer of the circuit board to which the resin composition layer (X) is laminated. Since the thickness of the conductor layer of the circuit board is in the range of 5 to 70  $\mu\text{m}$ , the thickness of the resin composition layer (X) is preferably 10 to 100  $\mu\text{m}$ . The resin composition layer (X) in this embodiment may be protected with a protective film to be described later. By protecting the resin composition layer (X) with a protective film, it is possible to prevent the adhesion of dirt and the like to the

20

25

surface of the resin composition layer (X) and scratches.

[0100]

The support film and the protective film may be made of: polyolefins such as polyethylene, polypropylene, or polyvinyl chloride; polyesters such as polyethylene terephthalate (PET) or polyethylene naphthalate; a polycarbonate, or a polyimide, or may be a release paper or a metal foil such as a copper foil or an aluminum foil. The support film and the protective film may be subjected to a release treatment in addition to a matte treatment or a corona treatment. The thickness of the support film is not particularly limited, but is in the range of 10 to 150  $\mu\text{m}$ , and preferably 25 to 50  $\mu\text{m}$ . The thickness of the protective film is preferably 1 to 40  $\mu\text{m}$ .

[0101]

The support film (Y) is peeled off after laminating the resin composition layer (X) on a circuit board, or after forming an insulating layer by heat-curing the resin composition layer (X). If the support film (Y) is peeled off after the resin composition layer (X) constituting the resin sheet is heat-cured, adhesion of dust and the like during the curing process can be prevented. When the support film (Y) is peeled off after the resin composition layer (X) is cured, the support film (Y) is previously subjected to a release treatment.

[0102]

A multilayer printed circuit board can be manufactured from the resin sheet obtained as described above. For example, when the resin composition layer (X) is protected by a protective film, the protective film is peeled off from the resin composition layer (X), and then the resin composition layer (X) is laminated on one or both sides of the circuit board so as to be in direct contact with the circuit board, for example, by a vacuum lamination method. The lamination method may be a batch type or a continuous type using a roll. If necessary, the resin sheet and the circuit board may be heated (preheated) before lamination. The lamination

conditions are preferably a pressure bonding temperature (lamination temperature) of 70 to 140°C, a pressure bonding pressure of 1 to 11 kgf/cm<sup>2</sup> ( $9.8 \times 10^4$  to  $107.9 \times 10^4$  N/m<sup>2</sup>), and lamination is preferably performed under reduced pressure of 20 mmHg (26.7 hPa) or less.

[0103]

5           The curable resin composition of the present embodiment can be used to manufacture a semiconductor device. Examples of the semiconductor device include: a dual in-line package (DIP), a quad flat package (QFP), a ball grid array (BGA), a chip size package (CSP), a small outline package (SOP), a thin small outline package (TSOP), a thin quad flat package (TQFP).

10   [0104]

          The curable resin composition of the present embodiment and its cured product can be used in a wide range of fields. Specifically, it can be used in various applications such as molding materials, adhesives, composite materials, and paints. The cured product of the curable resin composition described in this embodiment exhibits excellent heat resistance and

15   dielectric properties, and is therefore suitable for use in electrical and electronic components such as semiconductor element encapsulants, liquid crystal display element encapsulants, organic EL element encapsulants, laminates (printed wiring boards, BGA substrates, build-up substrates, etc.), carbon fiber reinforced plastics, glass fiber reinforced plastics, and other lightweight and high-strength structural composite materials, 3D printing, and the like.

20   Examples

[0105]

          The present invention will now be described in more detail with reference to examples. Unless otherwise specified, all parts are by weight. However, the present invention is not limited to these examples.

25   [0106]

The various analytical methods used in the examples are described below.

GPC (gel permeation chromatography) analysis

Equipment: online degassing unit (DGU-20A), liquid delivery unit (LC-20AD), autosampler (SIL-20A), photodiode array detector (SPD-M40), column oven (CTO-20A), system

5 controller (CBM-20A), all manufactured by Shimadzu Corporation

Columns: SHODEX GPC KF-601 (2 columns), KF-602, KF-602.5, KF-603

Flow rate: 1.5 ml/min.

Column temperature: 40°C

Solvent used: THF (tetrahydrofuran)

10 Detector: differential refractometer (RID-20A, manufactured by Shimadzu Corporation)


[0107]

[Synthesis Example 1]

A thermometer, a cooling tube, and a stirrer were attached to the flask, and a base trap and an aspirator were connected to the cooling tube. 370.1 parts of 2-bromoethylbenzene  
 15 (manufactured by Tokyo Chemical Industry Co., Ltd.), 175.1 parts of  $\alpha,\alpha'$ -dichloro-p-xylene (manufactured by Tokyo Chemical Industry Co., Ltd.), and 27.3 parts of methanesulfonic acid (manufactured by Tokyo Chemical Industry Co., Ltd.) were charged into this flask, and the reaction was carried out at 130 °C for 6 hours while collecting the generated hydrogen chloride with a base trap. Then, 100 parts of toluene and 600 parts of cyclohexane were added  
 20 to the flask to extract the product, and the organic layer was washed five times with 100 parts of water. By distilling off the solvent and excess 2-bromoethylbenzene under heating and reduced pressure, 380 parts of a compound (BEB-1) having a 2-bromoethylbenzene structure represented by the following formula (2) was obtained as a liquid resin (Mn: 938, Mw: 1290). The GPC chart of the obtained compound is shown in Figure 1. The average number of  
 25 repetitions, n, calculated from the area % of the GPC chart was 2.2.

[0108]

[Chem. 5]



[0109]

## 5 [Synthesis Example 2]

300 parts of BEB-1 obtained in Synthesis Example 1, 245 parts of toluene, 735 parts of dimethyl sulfoxide, 0.15 parts of 4-hydroxy-2,2,6,6-tetramethylpiperidine-1-oxyl free radical, and 146.4 parts of 50 wt% aqueous sodium hydroxide solution were added to a flask equipped with a thermometer, a cooling tube, and a stirrer, and the reaction was continued for


10 6 hours at 40 °C. 100 parts of water were added to the flask, the organic layer was washed, and the organic layer was returned to the flask. 735 parts of dimethyl sulfoxide and 9.8 parts of 50 wt% aqueous sodium hydroxide solution were added to the organic layer, and the reaction was continued for 1 hour at 40 °C, 300 parts of toluene were added, and the organic layer was repeatedly washed with 100 parts of water until the wastewater became neutral. The

15 mixture was concentrated under reduced pressure using an evaporator, and 180 parts of a compound (O-1) having two or more styrene structures in the molecule represented by the following formula (3) was obtained. The GPC chart of the obtained compound is shown in FIG. 2. The  $^1\text{H}$ -NMR data (deuterated chloroform) of the obtained compound is shown in Figure 3. Signals derived from vinyl groups were observed at 5.10-5.30 ppm, 5.50-5.85 ppm,

20 and 6.60-6.80 ppm in the  $^1\text{H}$ -NMR chart. The average repeat number  $n$  calculated from the area % of the GPC chart was 2.2 (the molecular weight of the resin component was  $M_n$ : 797,  $M_w$ : 1187).

[0110]

[Chem. 6]



[0111]

[Examples 1-2, Comparative Example 1]

5           Compound (O-1) obtained in Synthesis Example 2 as a compound represented by formula (1), a compound having one ethylenically unsaturated double bond in the molecule (acenaphthylene: manufactured by JFE Chemical Corporation, phenylmaleimide: manufactured by TCI Corporation), a polyphenylene ether compound (SA-9000: manufactured by SABIC Corporation), a radical polymerization initiator (dicumyl peroxide),  
 10   and toluene were dissolved and mixed in the amounts shown in Table 1, and coated on a mirror-finished copper foil so as to have a wet film thickness of 200  $\mu\text{m}$ , pre-dried in a vacuum oven at 60°C for 30 minutes, and cured at 220°C for 1 hour. After curing, the copper foil was etched using ferric chloride to obtain a cured film. If necessary, a test piece of the desired size was cut using a laser cutter, and evaluation was performed.

15   [0112]

&lt;Dielectric constant test/dielectric loss tangent test&gt;

Using a 10 GHz cavity resonator manufactured by AET Co., Ltd., the test was performed by the cavity resonator perturbation method at 25°C. The size of the test piece was 1.7 mm wide x 100 mm long x 0.1 mm thick, and the test was performed. The dielectric properties  
 20   (dielectric constant/dielectric loss tangent) at this time were evaluated as initial values.

[Water absorption test]

The values of the dielectric constant (after water absorption) and the dielectric loss tangent (after water absorption) measured after the water absorption test in which the test

piece after the initial value measurement was immersed in water at 25°C for 24 hours were taken as the dielectric properties after water absorption.

[High temperature storage test]

The values of the dielectric constant (after high temperature storage) and the dielectric loss tangent (after high temperature storage) were measured after the high temperature storage test in which the test piece after the initial value measurement was left at 150°C for 24 hours, which were taken as the dielectric properties after high temperature storage. The evaluation results are shown in Table 1.

[0113]

10 [Table 1]

|                                                                           |                  | Example 1 | Example 2 | Comparative Example 1 |
|---------------------------------------------------------------------------|------------------|-----------|-----------|-----------------------|
| Compound represented by formula (1)                                       | O-1              | 25        | 25        | 25                    |
| Polyphenylene ether compound                                              | SA-9000          | 65        | 65        | 75                    |
| Compound having one ethylenically unsaturated double bond in the molecule | Acenaphthylene   | 10        |           |                       |
|                                                                           | Phenylmaleimide  |           | 10        |                       |
| Radical polymerization initiator                                          | Dicumyl peroxide | 1         | 1         | 1                     |
| Solvent                                                                   | Toluene          | 100       | 100       | 100                   |
| Evaluation results                                                        |                  |           |           |                       |
| Dielectric constant                                                       |                  | 2.24      | 2.35      | 2.47                  |
| Dielectric constant (after water absorption)                              |                  | 2.23      | 2.36      | 2.47                  |
| Dielectric constant (after high temperature storage)                      |                  | 2.22      | 2.36      | 2.45                  |
| Dielectric loss tangent                                                   |                  | 0.00206   | 0.00127   | 0.00205               |
| Dielectric loss tangent (after water absorption)                          |                  | 0.00197   | 0.00161   | 0.00205               |
| Dielectric loss tangent (after high temperature storage)                  |                  | 0.00199   | 0.00162   | 0.00243               |

[0114]

From the results in Table 1, it was confirmed that the curable resin composition of the present invention exhibits low dielectric properties (low dielectric constant and low

dielectric tangent) not only initially but also after a water absorption test and a high temperature storage test.

This application claims priority based on Japanese Patent Application No. 2023-069238 filed on April 20, 2023.

## 5 Industrial Applicability

[0115]

The curable resin composition of the present invention is suitably used for electric and electronic parts such as semiconductor encapsulants, printed wiring boards, and build-up laminates.

## Claims


## [Claim 1]

A curable resin composition comprising:

a compound represented by the following formula (1); and

5 a compound having one ethylenically unsaturated double bond in the molecule:

## [Chem. 1]



in formula (1), a plurality of R each independently represent a hydrogen atom, a hydrocarbon group having 1 to 10 carbon atoms, or a halogenated alkyl group having 1 to 10 carbon atoms,

p and r each represent an integer of 0 to 4,

q represents an integer of 0 to 3, and

n represents the average number of repetitions, and satisfies  $1 \leq n \leq 20$ .

## [Claim 2]

15 The curable resin composition according to claim 1, wherein the compound having one ethylenically unsaturated double bond in the molecule is a compound having a maleimide structure or an acenaphthylene structure in the molecule.

## [Claim 3]

20 The curable resin composition according to claim 1, further comprising a polymerization initiator.

## [Claim 4]

The curable resin composition according to claim 1, further comprising at least one

selected from the group consisting of: a maleimide compound having two or more maleimide groups in the molecule, a polyphenylene ether compound, a compound having two or more ethylenically unsaturated bonds in the molecule, a cyanate ester resin, polybutadiene and modified products thereof, polystyrene and modified products thereof, and polyethylene and  
5 modified products thereof.

[Claim 5]

A cured product obtained by curing the curable resin composition according to any one of claims 1 to 4.