Claims

[Claim 1] A resin composition comprising the following components (A) to (C):

a saponified ethylene-vinyl ester-based copolymer (A)

cinnamic acids (B), and

at least either one (C) of an alkali metal salt (C1) and an alkaline earth metal salt (C2) wherein the component (C) excludes a salt of cinnamic acid.

[Claim 2] The resin composition according to claim 1,

wherein cinnamic acids (B) is at least one selected from the group consisting of cinnamic acid itself and cinnamic acid derivatives.

[Claim 3] The resin composition according to claim 1 or 2,

wherein a content of the cinnamic acids (B) is from 0.0005 to 0.1 parts by weight per 100 parts by weight of the saponified ethylene-vinyl ester-based copolymer (A).

[Claim 4] The resin composition according to claim 1 to 3,

wherein a content of the at least either one (C) of the alkali metal salt (C1) and the alkaline earth metal salt (C2) is, in terms of metal, from 0.001 to 0.1 parts by weight per 100 parts by weight of the saponified ethylene-vinyl ester-based copolymer (A).

[Claim 5] The resin composition according to any one of claims 1 to 4,

wherein a weight ratio (B/C) of the cinnamic acids (B) and the at least either one (C) of the alkali metal salt (C1) and the alkaline earth metal salt (C2) is from 0.01 to 100.

[Claim 6] A melt-molded article obtained by melt-molding the resin composition according to any one of claims 1 to 5.

[Claim 7] A multilayer structure comprising at least one resin composition layer composed of the resin composition according to any one of claims 1 to 5.