



159159



G00002

3-Arylbenzofuranones as stabilisers


The present invention relates to novel 3-arylbenzofuranones, to compositions comprising an organic material, preferably a polymer or a lubricant, and to the novel stabilisers, as well as to the use thereof for stabilising organic materials against oxidative, thermal or light-induced degradation.

Individual 3-arylbenzofuran-2-ones are known in the literature and have been described, inter alia, by J. Morvan et al., Bull. Soc. Chim. Fr. 1979, 583.

The use of some 3-phenyl-3H-benzofuran-2-ones as stabilisers for organic polymers is disclosed, inter alia, in US-A-4 325 863; US-A-4 338 244 and US-A-5 175 312.

It has now been found that a selected group of 3-arylbenzofuran-2-ones is particularly suitable for use as stabilisers for organic materials that are susceptible to oxidative, thermal or light-induced degradation.

Accordingly, the invention relates to compounds of formula I




wherein, when n is 1,

R₁ is naphthyl, phenanthryl, anthryl, 5,6,7,8-tetrahydro-2-naphthyl, 5,6,7,8-tetrahydro-1-naphthyl, thienyl, benzo[b]thienyl, naphtho[2,3-b]thienyl, thiathrenyl, dibenzofuryl, chromenyl, xanthenyl, phenoxathiinyl, pyrrolyl, imidazolyl, pyrazolyl, pyrazinyl, pyrimidinyl, pyridazinyl, indolizinyll, isoindolyl, indolyl, indazolyl, purinyl, quinolizinyll, isoquinolyl, quinolyl, phthalazinyl, naphthyridinyl, quinoxalinyll, quinazolinyl, cinnolinyl, pteridinyl, carbazolyl, β-carbolinyl, phenanthridinyl, acridinyl, perimidinyl, phenanthrolinyl, phenazinyll, isothiazolyl, phenothiazinyl, isoxazolyl, furazanyl, biphenyl, terphenyl, fluorenyll

THIS SHEET HAS BEEN
REPLACED

or phenoxazinyl, each unsubstituted or substituted by C₁-C₄alkyl, C₁-C₄alkoxy, C₁-C₄alkylthio, hydroxy, halogen, amino, C₁-C₄alkylamino, phenylamino or di(C₁-C₄alkyl)-amino, or R₁ is a radical of formula II




and

when n is 2,


R₁ is phenylene or naphthylene which is unsubstituted or substituted by C₁-C₄alkyl or hydroxy; or is -R₁₂-X-R₁₃-,

R₂, R₃, R₄ and R₅ are each independently of one another hydrogen, chloro, hydroxy, C₁-C₂₅alkyl, C₇-C₉phenylalkyl, unsubstituted or C₁-C₄alkyl-substituted phenyl, unsubstituted or C₁-C₄alkyl-substituted C₅-C₈cycloalkyl; C₁-C₁₈alkoxy, C₁-C₁₈alkylthio, C₁-C₄alkylamino, di(C₁-C₄alkyl)amino, C₁-C₂₅alkanoyloxy, C₁-C₂₅alkanoylamino, C₃-C₂₅alkanoyloxy, C₃-C₂₅alkanoyloxy which is interrupted by oxygen, sulfur or >N-R_{14} ; C₆-C₉-cycloalkylcarbonyloxy, benzoyloxy or C₁-C₁₂alkyl-substituted benzoyloxy; with the proviso that, when R₂ is hydrogen or methyl, R₇ or R₉ is not hydroxy or C₁-C₂₅alkanoyloxy; or each pair of substituents R₂ and R₃ or R₃ and R₄ or R₄ and R₅, together with the linking carbon atoms, forms a benzene ring; R₄ is additionally -(CH₂)_p-COR₁₅ or -(CH₂)_qOH, or when R₃, R₅ and R₆ are hydrogen, R₄ is additionally a radical of formula III



THIS SHEET HAS BEEN
REPLACED

wherein R_1 is as defined above for $n = 1$,
 R_6 is hydrogen or a radical of formula IV



in which R_4 is not a radical of formula III and R_1 is as defined above for $n = 1$,
 R_7 , R_8 , R_9 and R_{10} are each independently of one another hydrogen, halogen, hydroxy,
 C_1 - C_{25} alkyl, C_2 - C_{25} alkyl which is interrupted by oxygen, sulfur or >N-R_{14} ; C_1 - C_{25} -
alkoxy, C_2 - C_{25} alkoxy which is interrupted by oxygen, sulfur or >N-R_{14} ; C_1 - C_{25} alkyl-
thio, C_3 - C_{25} alkenyl, C_3 - C_{25} alkenyloxy, C_3 - C_{25} alkynyl, C_3 - C_{25} alkynyloxy, C_7 - C_9 phenyl-
alkyl, C_7 - C_9 phenylalkoxy, unsubstituted or C_1 - C_4 alkyl-substituted phenyl; unsubstituted
or C_1 - C_4 alkyl-substituted phenoxy; unsubstituted or C_1 - C_4 alkyl-substituted C_5 - C_8 cyclo-
alkyl; unsubstituted or C_1 - C_4 alkyl-substituted C_5 - C_8 cycloalkoxy; C_1 - C_4 alkylamino, di-
(C_1 - C_4 alkyl)amino, C_1 - C_{25} alkanoyl, C_3 - C_{25} alkanoyl which is interrupted by oxygen, sul-
fur or >N-R_{14} ; C_1 - C_{25} alkanoyloxy, C_3 - C_{25} alkanoyloxy which is interrupted by oxygen,
sulfur or >N-R_{14} ; C_1 - C_{25} alkanoylamino, C_3 - C_{25} alkenoyl, C_3 - C_{25} alkenoyl which is
interrupted by oxygen, sulfur or >N-R_{14} ; C_3 - C_{25} alkenoyloxy, C_3 - C_{25} alkenoyloxy
which is interrupted by oxygen, sulfur or >N-R_{14} ; C_6 - C_9 cycloalkylcarbonyl, C_6 - C_9 -
cycloalkylcarbonyloxy, benzoyl or C_1 - C_{12} alkyl-substituted benzoyl; benzoyloxy or
 C_1 - C_{12} alkyl-substituted benzoyloxy; $\text{—O—}\overset{\overset{R_{18}}{|}}{\underset{\underset{R_{19}}{|}}{C}}\text{—}\overset{\overset{O}{||}}{C}\text{—}R_{15}$ or $\text{—O—}\overset{\overset{R_{20}}{|}}{\underset{\underset{H}{|}}{C}}\text{—}\overset{\overset{R_{21}}{|}}{\underset{\underset{R_{22}}{|}}{C}}\text{—O—}R_{23}$,
or also in formula II each pair of substituents R_7 and R_8 or R_8 and R_{11} , together with the
linking carbon atoms, forms a benzene ring,
 R_{11} is hydrogen, C_1 - C_{25} alkyl, C_1 - C_{25} alkylthio, C_3 - C_{25} alkenyl, C_3 - C_{25} alkynyl, C_7 - C_9 phe-

nylalkyl, unsubstituted or C₁-C₄alkyl-substituted phenyl; unsubstituted or C₁-C₄alkyl-substituted C₅-C₈cycloalkyl; C₁-C₄alkylamino, di(C₁-C₄alkyl)amino, C₁-C₂₅alkanoyl,

C₃-C₂₅alkanoyl which is interrupted by oxygen, sulfur or >N-R_{14} ; C₁-C₂₅alkanoyl-amino, C₃-C₂₅alkenoyl, C₃-C₂₅alkenoyl which is interrupted by oxygen, sulfur or

>N-R_{14} ; C₆-C₉cycloalkylcarbonyl, benzoyl or C₁-C₁₂alkyl-substituted benzoyl; with

the proviso that at least one of R₇, R₈, R₉, R₁₀ or R₁₁ is not hydrogen,

R₁₂ and R₁₃ are each independently of the other unsubstituted or C₁-C₄alkyl-substituted phenylene or naphthylene,

R₁₄ is hydrogen or C₁-C₈alkyl,

R₁₅ is hydroxy, $[\text{-O}^{\ominus} \frac{1}{r} \text{M}^{r+}]$, C₁-C₁₈alkoxy or $\text{-N} \begin{matrix} \text{R}_{24} \\ \text{R}_{25} \end{matrix}$,

R₁₆ and R₁₇ are each independently of the other hydrogen, CF₃, C₁-C₁₂alkyl or phenyl, or R₁₆ and R₁₇, together with the linking carbon atom, form a C₅-C₈cycloalkylidene ring which is unsubstituted or substituted by 1 to 3 C₁-C₄alkyl groups;

R₁₈ and R₁₉ are each independently of the other hydrogen, C₁-C₄alkyl or phenyl,




R₂₀ is hydrogen or C₁-C₄alkyl,

R₂₁ is hydrogen, unsubstituted or C₁-C₄alkyl-substituted phenyl; C₁-C₂₅alkyl, C₂-C₂₅alkyl which is interrupted by oxygen, sulfur or >N-R_{14} ; C₇-C₉phenylalkyl which is unsubstituted or substituted in the phenyl moiety by 1 to 3 C₁-C₄alkyl groups; C₇-C₂₅phenylalkyl

which is interrupted by oxygen, sulfur or >N-R_{14} and which is unsubstituted or substituted in the phenyl moiety by 1 to 3 C₁-C₄alkyl groups; or R₂₀ and R₂₁, together with the linking carbon atoms, form a C₅-C₁₂cycloalkylene ring which is unsubstituted or substituted by 1 to 3 C₁-C₄alkyl groups;

R₂₂ is hydrogen or C₁-C₄alkyl,

R₂₃ is hydrogen, C₁-C₂₅alkanoyl, C₃-C₂₅alkenoyl, C₃-C₂₅alkanoyl which is interrupted by oxygen, sulfur or >N-R_{14} ; C₂-C₂₅alkanoyl which is substituted by a di(C₁-C₆alkyl)-phosphonate group; C₆-C₉cycloalkylcarbonyl, thenoyl, furoyl, benzoyl or C₁-C₁₂alkyl-




R₂₄ and R₂₅ are each independently of the other hydrogen or C₁-C₁₈alkyl,

R₂₆ is hydrogen or C₁-C₈alkyl,

R₂₇ is a direct bond, C₁-C₁₈alkylene, C₂-C₁₈alkylene which is interrupted by oxygen, sul-

fur or N—R₁₄; C₂-C₁₈alkenylene, C₂-C₂₀alkylidene, C₇-C₂₀phenylalkylidene, C₅-C₈-cycloalkylene, C₇-C₈bicycloalkylene, unsubstituted or C₁-C₄alkyl-substituted phenylene,



R_{28} is hydroxy, $[-O^{\ominus} \cdot \frac{1}{r} M^{r+}]$, C_1 - C_{18} alkoxy or $-N \begin{matrix} R_{24} \\ R_{25} \end{matrix}$,

R_{29} is oxygen, -NH- or $\begin{array}{c} \diagup \\ \text{N} - \text{C}(=\text{O}) - \text{NH} - R_{30} \\ \diagdown \end{array}$,

R₃₀ is C₁-C₁₈alkyl or phenyl,

R₃₁ is hydrogen or C₁-C₁₈alkyl,

M is a metal cation of valency r,

X is a direct bond, oxygen, sulfur or -NR₃₁-,

n is 1 or 2,

$p = 0, 1$ or 2 ,

q is 1, 2, 3, 4, 5 or 6,

r is 1, 2 or 3, and

THIS SHEET HAS BEEN
REPLACED

s is 0, 1 or 2.

Naphthyl, phenanthryl, anthryl, 5,6,7,8-tetrahydro-2-naphthyl, 5,6,7,8-tetrahydro-1-naphthyl, thienyl, benzo[b]thienyl, naphtho[2,3-b]thienyl, thiathrenyl, dibenzofuryl, chromenyl, xanthenyl, phenoxathiinyl, pyrrolyl, imidazolyl, pyrazolyl, pyrazinyl, pyrimidinyl, pyridazinyl, indoliziny, isoindolyl, indolyl, indazolyl, purinyl, quinoliziny, isoquinolyl, quinolyl, phthalazinyl, naphthyridinyl, quinoxaliny, quinazolinyl, cinnolinyl, pteridinyl, carbazolyl, β -carbolinyl, phenanthridinyl, acridinyl, perimidinyl, phenanthrolinyl, phenazinyl, isothiazolyl, phenothiazinyl, isoxazolyl, furazanyl, biphenyl, terphenyl, fluorenyl or phenoxazinyl, each unsubstituted or substituted by C_1 - C_4 alkyl, C_1 - C_4 alkoxy, C_1 - C_4 alkylthio, hydroxy, halogen, amino, C_1 - C_4 alkylamino, phenylamino or di(C_1 - C_4 alkyl)amino, will typically be 1-naphthyl, 2-naphthyl, 1-phenylamino-4-naphthyl, 1-methylnaphthyl, 2-methylnaphthyl, 1-methoxy-2-naphthyl, 2-methoxy-1-naphthyl, 1-dimethylamino-2-naphthyl, 1,2-dimethyl-4-naphthyl, 1,2-dimethyl-6-naphthyl, 1,2-dimethyl-7-naphthyl, 1,3-dimethyl-6-naphthyl, 1,4-dimethyl-6-naphthyl, 1,5-dimethyl-2-naphthyl, 1,6-dimethyl-2-naphthyl, 1-hydroxy-2-naphthyl, 2-hydroxy-1-naphthyl, 1,4-dihydroxy-2-naphthyl, 7-phenanthryl, 1-anthryl, 2-anthryl, 9-anthryl, 3-benzo[b]thienyl, 5-benzo[b]thienyl, 2-benzo[b]thienyl, 4-dibenzofuryl, 4,7-dibenzofuryl, 4-methyl-7-dibenzofuryl, 2-xanthenyl, 8-methyl-2-xanthenyl, 3-xanthenyl, 2-phenoxathiinyl, 2,7-phenoxathiinyl, 2-pyrrolyl, 3-pyrrolyle, 5-methyl-3-pyrrolyl, 2-imidazolyl, 4-imidazolyl, 5-imidazolyl, 2-methyl-4-imidazolyl, 2-ethyl-4-imidazolyl, 2-ethyl-5-imidazolyl, 3-pyrazolyl, 1-methyl-3-pyrazolyl, 1-propyl-4-pyrazolyl, 2-pyrazinyl, 5,6-dimethyl-2-pyrazinyl, 2-indoliziny, 2-methyl-3-isoindolyl, 2-methyl-1-isoindolyl, 1-methyl-2-indolyl, 1-methyl-3-indolyl, 1,5-dimethyl-2-indolyl, 1-methyl-3-indazolyl, 2,7-dimethyl-8-purinyl, 2-methoxy-7-methyl-8-purinyl, 2-quinoliziny, 3-isoquinolyl, 6-isoquinolyl, 7-isoquinolyl, isoquinolyl, 3-methoxy-6-isoquinolyl, 2-quinolyl, 6-quinolyl, 7-quinolyl, 2-methoxy-3-quinolyl, 2-methoxy-6-quinolyl, 6-phthalazinyl, 7-phthalazinyl, 1-methoxy-6-phthalazinyl, 1,4-dimethoxy-6-phthalazinyl, 1,8-naphthyridin-2-yl, 2-quinoxaliny, 6-quinoxaliny, 2,3-dimethyl-6-quinoxaliny, 2,3-dimethoxy-6-quinoxaliny, 2-quinazolinyl, 7-quinazolinyl, 2-dimethylamino-6-quinazolinyl, 3-cinnolinyl, 6-cinnolinyl, 7-cinnolinyl, 3-methoxy-7-cinnolinyl, 2-pteridinyl, 6-pteridinyl, 7-pteridinyl, 6,7-dimethoxy-2-pteridinyl, 2-carbazolyl, 3-carbazolyl, 9-methyl-2-carbazolyl, 9-methyl-3-carbazolyl, β -carbolin-3-yl, 1-methyl- β -carbolin-3-yl, 1-methyl- β -carbolin-6-yl, 3-phenanthridinyl, 2-acridinyl, 3-acridinyl, 2-perimidinyl, 1-methyl-5-perimidinyl, 5-phenanthrolinyl, 6-phenanthrolinyl, 1-phenazinyl, 2-phenazinyl, 3-isothiazolyl, 4-isothiazolyl, 5-isothiazolyl, 2-phenothiazinyl, 3-phenothiazinyl, 10-methyl-3-phenothiazinyl, 3-isoxazolyl, 4-isoxazolyl, 5-isoxazolyl, 4-methyl-3-furazanyl, 2-phenoxazinyl or

10-methyl-2-phenoxazinyl.

Particularly preferred above substituents are naphthyl, phenanthryl, anthryl, 5,6,7,8-tetrahydro-2-naphthyl, 5,6,7,8-tetrahydro-1-naphthyl, thienyl, benzo[b]thienyl, naphtho[2,3-b]thienyl, thiathrenyl, dibenzofuryl, chromenyl, xanthenyl, phenoxathiinyl, pyrrolyl, isoindolyl, indolyl, phenothiazinyl, biphenyl, terphenyl, fluorenyl or phenoxazinyl, each unsubstituted or substituted by C₁-C₄alkyl, C₁-C₄alkoxy, C₁-C₄alkylthio, hydroxy, phenylamino or di(C₁-C₄alkyl)amino, typically 1-naphthyl, 2-naphthyl, 1-phenylamino-4-naphthyl, 1-methylnaphthyl, 2-methylnaphthyl, 1-methoxy-2-naphthyl, 2-methoxy-1-naphthyl, 1-dimethylamino-2-naphthyl, 1,2-dimethyl-4-naphthyl, 1,2-dimethyl-6-naphthyl, 1,2-dimethyl-7-naphthyl, 1,3-dimethyl-6-naphthyl, 1,4-dimethyl-6-naphthyl, 1,5-dimethyl-2-naphthyl, 1,6-dimethyl-2-naphthyl, 1-hydroxy-2-naphthyl, 2-hydroxy-1-naphthyl, 1,4-dihydroxy-2-naphthyl, 7-phenanthryl, 1-anthryl, 2-anthryl, 9-anthryl, 3-benzo[b]thienyl, 5-benzo[b]thienyl, 2-benzo[b]thienyl, 4-dibenzofuryl, 4,7-dibenzofuryl, 4-methyl-7-dibenzofuryl, 2-xanthenyl, 8-methyl-2-xanthenyl, 3-xanthenyl, 2-pyrrolyl, 3-pyrrolyl, 2-phenothiazinyl, 3-phenothiazinyl, 10-methyl-3-phenothiazinyl.

Halogen substituents will conveniently be chloro, bromo or iodo. Chloro is preferred.

Alkanoyl of up to 25 carbon atoms inclusive is a branched or unbranched radical, typically including formyl, acetyl, propionyl, butanoyl, pentanoyl, hexanoyl, heptanoyl, octanoyl, nonanoyl, decanoyl, undecanoyl, dodecanoyl, tridecanoyl, tetradecanoyl, pentadecanoyl, hexadecanoyl, heptadecanoyl, octadecanoyl, eicosanoyl or docosanoyl. Alkanoyl of 2 to 18, most preferably 2 to 12, e.g. 2 to 6, carbon atoms, is preferred. Acetyl is particularly preferred.

C₂-C₂₅Alkanoyl substituted by a di(C₁-C₆alkyl)phosphonate group will typically be (CH₃CH₂O)₂POCH₂CO-, (CH₃O)₂POCH₂CO-, (CH₃CH₂CH₂CH₂O)₂POCH₂CO-, (CH₃CH₂O)₂POCH₂CH₂CO-, (CH₃O)₂POCH₂CH₂CO-, (CH₃CH₂CH₂CH₂O)₂POCH₂CH₂CO-, (CH₃CH₂O)₂PO(CH₂)₄CO-, (CH₃CH₂O)₂PO(CH₂)₈CO- or (CH₃CH₂O)₂PO(CH₂)₁₇CO-.

Alkanoyloxy of up to 25 carbon atoms is an unbranched or branched radical and is typically formyloxy, acetoxo, propionyloxy, butanoyloxy, pentanoyloxy, hexanoyloxy, heptanoyloxy, octanoyloxy, nonanoyloxy, decanoyloxy, undecanoyloxy, dodecanoyloxy, tridecanoyloxy, tetradecanoyloxy, pentadecanoyloxy, hexadecanoyloxy, heptadecanoyloxy, octa-

THIS SHEET HAS BEEN
REPLACED

decanoyloxy, eicosanoyloxy or docosanoyloxy. Alkanoyloxy of 2 to 18, preferably 2 to 12, e.g. 2 to 6, carbon atoms is preferred. Acetoxy is particularly preferred.

Alkenoyl of 3 to 25 carbon atoms is a branched or unbranched radical, typically including propenoyl, 2-butenoyl, 3-butenoyl, isobutenoyl, n-2,4-pentadienoyl, 3-methyl-2-butenoyl, n-2-octenoyl, n-2-dodecenoyl, isododecenoyl, oleoyl, n-2-octadecenoyl or n-4-octadecenoyl. Alkenoyl of 3 to 18, preferably 3 to 12, e.g. 3 to 6, most preferably 3 to 4, carbon atoms is preferred.

C₃-C₂₅Alkenoyl interrupted by oxygen, sulfur or $\text{N}-\text{R}_{14}$ is typically CH₃OCH₂CH₂CH=CHCO- or CH₃OCH₂CH₂OCH=CHCO-.

Alkenoyloxy of 3 to 25 carbon atoms is a branched or unbranched radical, typically including propenoyloxy, 2-butenoyloxy, 3-butenoyloxy, isobutenoyloxy, n-2,4-pentadienoyloxy, 3-methyl-2-butenoyloxy, n-2-octenoyloxy, n-2-dodecenoyloxy, isododecenoyloxy, oleoyloxy, n-2-octadecenoyloxy or n-4-octadecenoyloxy. Alkenoyloxy of 3 to 18, preferably 3 to 12, typically 3 to 6, most preferably 3 to 4, carbon atoms is preferred.

C₃-C₂₅Alkenoyloxy interrupted by oxygen, sulfur or $\text{N}-\text{R}_{14}$ will typically be CH₃OCH₂CH₂CH=CHCOO- or CH₃OCH₂CH₂OCH=CHCOO-.

C₃-C₂₅-Alkanoyl interrupted by oxygen, sulfur or $\text{N}-\text{R}_{14}$ will typically be CH₃-O-CH₂CO-, CH₃-S-CH₂CO-, CH₃-NH-CH₂CO-, CH₃-N(CH₃)-CH₂CO-, CH₃-O-CH₂CH₂-O-CH₂CO-, CH₃-(O-CH₂CH₂)₂O-CH₂CO-, CH₃-(O-CH₂CH₂)₃O-CH₂CO- or CH₃-(O-CH₂CH₂)₄O-CH₂CO-.

C₃-C₂₅-Alkanoyloxy interrupted by oxygen, sulfur or $\text{N}-\text{R}_{14}$ will typically be CH₃-O-CH₂COO-, CH₃-S-CH₂COO-, CH₃-NH-CH₂COO-, CH₃-N(CH₃)-CH₂COO-, CH₃-O-CH₂CH₂-O-CH₂COO-, CH₃-(O-CH₂CH₂)₂O-CH₂COO-, CH₃-(O-CH₂CH₂)₃O-CH₂COO- or CH₃-(O-CH₂CH₂)₄O-CH₂COO-.

C₆-C₉Cycloalkylcarbonyl is typically cyclopentylcarbonyl, cyclohexylcarbonyl, cycloheptylcarbonyl or cyclooctylcarbonyl. Cyclohexylcarbonyl is preferred.

C₆-C₉Cycloalkylcarbonyloxy is typically cyclopentylcarbonyloxy, cyclohexylcarbonyloxy, cycloheptylcarbonyloxy or cyclooctylcarbonyloxy. Cyclohexylcarbonyloxy is preferred.

C₁-C₁₂Alkyl-substituted benzoyl which preferably carries 1 to 3, most preferably 1 or 2, alkyl groups, is typically o-, m- or p-methylbenzoyl, 2,3-dimethylbenzoyl, 2,4-dimethylbenzoyl, 2,5-dimethylbenzoyl, 2,6-dimethylbenzoyl, 3,4-dimethylbenzoyl, 3,5-dimethylbenzoyl, 2-methyl-6-ethylbenzoyl, 4-tert-butylbenzoyl, 2-ethylbenzoyl, 2,4,6-trimethylbenzoyl, 2,6-dimethyl-4-tert-butylbenzoyl or 3,5-di-tert-butylbenzoyl. Preferred substituents are C₁-C₈alkyl, most preferably C₁-C₄alkyl.

C₁-C₁₂Alkyl-substituted benzoyloxy which preferably carries 1 to 3, most preferably 1 or 2, alkyl groups, is typically o-, m- or p-methylbenzoyloxy, 2,3-dimethylbenzoyloxy, 2,4-dimethylbenzoyloxy, 2,5-dimethylbenzoyloxy, 2,6-dimethylbenzoyloxy, 3,4-dimethylbenzoyloxy, 3,5-dimethylbenzoyloxy, 2-methyl-6-ethylbenzoyloxy, 4-tert-butylbenzoyloxy, 2-ethylbenzoyloxy, 2,4,6-trimethylbenzoyloxy, 2,6-dimethyl-4-tert-butylbenzoyloxy or 3,5-di-tert-butylbenzoyloxy. Preferred substituents are C₁-C₈alkyl, preferably C₁-C₄alkyl.

Alkyl of up to 25 carbon atoms is a branched or unbranched radical and is typically methyl, ethyl, propyl, isopropyl, n-butyl, sec-butyl, isobutyl, tert-butyl, 2-ethylbutyl, n-pentyl, isopentyl, 1-methylpentyl, 1,3-dimethylbutyl, n-hexyl, 1-methylhexyl, n-heptyl, isoheptyl, 1,1,3,3-tetramethylbutyl, 1-methylheptyl, 3-methylheptyl, n-octyl, 2-ethylhexyl, 1,1,3-trimethylhexyl, 1,1,3,3-tetramethylpentyl, nonyl, decyl, undecyl, 1-methylundecyl, dodecyl, 1,1,3,3,5-hexamethylhexyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, eicosyl or docosyl. A preferred meaning of R₂ and R₄ is typically C₁-C₁₈alkyl. A particularly preferred meaning of R₄ is C₁-C₄alkyl.

Alkenyl of 3 to 25 carbon atoms is a branched or unbranched radical, typically including propenyl, 2-butenyl, 3-butenyl, isobutenyl, n-2,4-pentadienyl, 3-methyl-2-butenyl, n-2-octenyl, n-2-dodecenyl, isododecenyl, oleyl, n-2-octadecenyl or n-4-octadecenyl. Alkenyl of 3 to 18, preferably 3 to 12, typically 3 to 6, most preferably 3 to 4, carbon atoms is preferred.

Alkenyloxy of 3 to 25 carbon atoms is a branched or unbranched radical, typically including propenyloxy, 2-butenyloxy, 3-butenyloxy, isobutenyloxy, n-2,4-pentadienyloxy, 3-

methyl-2-butenyloxy, n-2-octenyloxy, n-2-dodecenyloxy, isododecenyloxy, oleyloxy, n-2-octadecenyloxy or n-4-octadecenyloxy. Alkenyloxy of 3 to 18, preferably 3 to 12, typically 3 to 6, most preferably 3 to 4, carbon atoms is preferred.

Alkynyl of 3 to 25 carbon atoms is a branched or unbranched radical, typically including propynyl ($-\text{CH}_2-\text{C}\equiv\text{CH}$), 2-butylnyl, 3-butylnyl, n-2-octynyl or n-2-dodecynyl. Alkynyl of 3 to 18, preferably 3 to 12, typically 3 to 6, most preferably 3 to 4, carbon atoms is preferred.

Alkynyloxy of 3 to 25 carbon atoms is a branched or unbranched radical, typically including propynyloxy ($-\text{OCH}_2-\text{C}\equiv\text{CH}$), 2-butyntyloxy, 3-butyntyloxy, n-2-octynyloxy, or n-2-dodecynyloxy. Alkynyloxy of 3 to 18, preferably 3 to 12, typically 3 to 6, most preferably 3 to 4, carbon atoms is preferred.

$\text{C}_2\text{-C}_{25}$ Alkyl interrupted by oxygen, sulfur or $\text{N}-\text{R}_{14}$ will typically be $\text{CH}_3\text{-O-CH}_2\text{-}$, $\text{CH}_3\text{-S-CH}_2\text{-}$, $\text{CH}_3\text{-NH-CH}_2\text{-}$, $\text{CH}_3\text{-N(CH}_3\text{)-CH}_2\text{-}$, $\text{CH}_3\text{-O-CH}_2\text{CH}_2\text{-O-CH}_2\text{-}$, $\text{CH}_3\text{-(O-CH}_2\text{CH}_2\text{)}_2\text{O-CH}_2\text{-}$, $\text{CH}_3\text{-(O-CH}_2\text{CH}_2\text{)}_3\text{O-CH}_2\text{-}$ or $\text{CH}_3\text{-(O-CH}_2\text{CH}_2\text{)}_4\text{O-CH}_2\text{-}$.

$\text{C}_7\text{-C}_9$ Phenylalkyl may typically be benzyl, α -methylbenzyl, α,α -dimethylbenzyl or 2-phenylethyl. Benzyl and α,α -dimethylbenzyl are preferred.

$\text{C}_7\text{-C}_9$ -Phenylalkyl which is unsubstituted or substituted in the phenyl moiety by 1 to 3 $\text{C}_1\text{-C}_4$ alkyl groups will typically be benzyl, α -methylbenzyl, α,α -dimethylbenzyl, 2-phenylethyl, 2-methylbenzyl, 3-methylbenzyl, 4-methylbenzyl, 2,4-dimethylbenzyl, 2,6-dimethylbenzyl or 4-tert-butylbenzyl. Benzyl is preferred.

$\text{C}_7\text{-C}_{25}$ Phenylalkyl which is interrupted by oxygen, sulfur or $\text{N}-\text{R}_{14}$ and is unsubstituted or substituted in the phenyl moiety by 1 to 3 $\text{C}_1\text{-C}_4$ alkyl groups is a branched or unbranched radical such as phenoxymethyl, 2-methylphenoxymethyl, 3-methylphenoxy-methyl, 4-methylphenoxymethyl, 2,4-dimethylphenoxymethyl, 2,3-dimethylphenoxy-methyl, phenylthiomethyl, N-methyl-N-phenyl-methyl, N-ethyl-N-phenylmethyl, 4-tert-butylphenoxymethyl, 4-tert-butylphenoxyethoxymethyl, 2,4-di-tert-butylphenoxymethyl, 2,4-di-tert-butylphenoxyethoxymethyl, phenoxyethoxyethoxyethoxymethyl, benzyloxy-methyl, benzyloxyethoxymethyl, N-benzyl-N-ethylmethyl or N-benzyl-N-isopropyl-

methyl.

C₇-C₉Phenylalkoxy is typically benzyloxy, α-methylbenzyloxy, α,α-dimethylbenzyloxy or 2-phenylethoxy. Benzyloxy is preferred.

C₁-C₄Alkyl-substituted phenyl that preferably contains 1 to 3, preferably 1 or 2, alkyl groups, will typically be o-, m- or p-methylphenyl, 2,3-dimethylphenyl, 2,4-dimethylphenyl, 2,5-dimethylphenyl, 2,6-dimethylphenyl, 3,4-dimethylphenyl, 3,5-dimethylphenyl, 2-methyl-6-ethylphenyl, 4-tert-butylphenyl, 2-ethylphenyl or 2,6-diethylphenyl.

C₁-C₄Alkyl-substituted phenoxy which preferably contains 1 to 3, most preferably 1 or 2, alkyl groups, is typically o-, m- or p-methylphenoxy, 2,3-dimethylphenoxy, 2,4-dimethylphenoxy, 2,5-dimethylphenoxy, 2,6-dimethylphenoxy, 3,4-dimethylphenoxy, 3,5-dimethylphenoxy, 2-methyl-6-ethylphenoxy, 4-tert-butylphenoxy, 2-ethylphenoxy or 2,6-diethylphenoxy.

Unsubstituted or C₁-C₄alkyl-substituted C₅-C₈cycloalkyl is typically cyclopentyl, methylcyclopentyl, dimethylcyclopentyl, cyclohexyl, methylcyclohexyl, dimethylcyclohexyl, trimethylcyclohexyl, tert-butylcyclohexyl, cycloheptyl or cyclooctyl. Cyclohexyl and tert-butylcyclohexyl are preferred.

Unsubstituted or C₁-C₄alkyl-substituted C₅-C₈cycloalkoxy is typically cyclopentoxo, methylcyclopentoxo, dimethylcyclopentoxo, cyclohexoxo, methylcyclohexoxo, dimethylcyclohexoxo, trimethylcyclohexoxo, tert-butylcyclohexoxo, cycloheptoxo or cyclooctoxo. Cyclohexoxo and tert-butylcyclohexoxo are preferred.

Alkoxy of up to 25 carbon atoms is a branched or unbranched radical and is typically methoxy, ethoxy, propoxy, isopropoxy, n-butoxy, isobutoxy, pentoxy, isopentoxy, hexoxy, heptoxy, octoxy, decyloxy, tetradecyloxy, hexadecyloxy or octadecyloxy. Alkoxy of 1 to 12, preferably 1 to 8, e.g. 1 to 6, carbon atoms is preferred.

C₂-C₂₅Alkoxy interrupted by oxygen, sulfur or $\text{N}-\text{R}_{14}$ is typically CH₃-O-CH₂CH₂O-, CH₃-S-CH₂CH₂O-, CH₃-NH-CH₂CH₂O-, CH₃-N(CH₃)-CH₂CH₂O-, CH₃-O-CH₂CH₂-O-CH₂CH₂O-, CH₃-(O-CH₂CH₂)₂O-CH₂CH₂O-, CH₃-(O-CH₂CH₂)₃O-CH₂CH₂O- or CH₃-(O-CH₂CH₂)₄O-CH₂CH₂O-.

THIS SHEET HAS BEEN
REPLACED

Alkylthio of up to 25 carbon atoms is a branched or unbranched radical and is typically methylthio, ethylthio, propylthio, isopropylthio, n-butylthio, isobutylthio, pentylthio, isopentylthio, hexylthio, heptylthio, octylthio, decylthio, tetradecylthio, hexadecylthio or octadecylthio. Alkylthio of 1 to 12, preferably 1 to 8, e.g. 1 to 6, carbon atoms is preferred.

Alkylamino of up to 4 carbon atoms is a branched or unbranched radical and is typically methylamino, ethylamino, propylamino, isopropylamino, n-butylamino, isobutylamino or tert-butylamino.

Di(C₁-C₄)alkylamino also signifies that the two moieties, each independently of the other, are branched or unbranched, and is typically dimethylamino, methylethylamino, diethylamino, methyl-n-propylamino, methylisopropylamino, methyl-n-butylamino, methylisobutylamino, ethylisopropylamino, ethyl-n-butylamino, ethylisobutylamino, ethyl-tert-butylamino, diethylamino, diisopropylamino, isopropyl-n-butylamino, isopropylisobutylamino, di-n-butylamino or diisobutylamino.

Alkanoylamino of up to 25 carbon atoms is an unbranched or branched radical and is typically formylamino, acetylamino, propionylamino, butanoylamino, pentanoylamino, hexanoylamino, heptanoylamino, octanoylamino, nonanoylamino, decanoylamino, undecanoylamino, dodecanoylamino, tridecanoylamino, tetradecanoylamino, pentadecanoylamino, hexadecanoylamino, heptadecanoylamino, octadecanoylamino, eicosanoylamino oder docosanoylamino. Alkanoylamino of 2 to 18, preferably 2 to 12, e.g. 2 to 6, carbon atoms is preferred.

C₁-C₁₈Alkylene is a branched or unbranched radical, typically methylene, ethylene, propylene, trimethylene, tetramethylene, pentamethylene, hexamethylene, heptamethylene, octamethylene, decamethylene, dodecamethylene or octadecamethylene. C₁-C₁₂Alkylene is preferred, and C₁-C₈alkylene is particularly preferred.

A C₁-C₄alkyl-substituted C₅-C₁₂cycloalkylene ring which preferably contains 1 to 3, preferably 1 or 2 branched or unbranched alkyl groups will typically be cyclopentylene, methylcyclopentylene, dimethylcyclopentylene, cyclohexylene, methylcyclohexylene, dimethylcyclohexylene, trimethylcyclohexylene, tert-butylcyclohexylene, cycloheptylene, cyclooctylene or cyclodecylene. Cyclohexylene and tert-butylcyclohexylene.

THIS SHEET HAS BEEN REPLACED

C₂-C₁₈Alkylene which is interrupted by oxygen, sulfur or $\text{N}-\text{R}_{14}$ will typically be
-CH₂-O-CH₂-, -CH₂-S-CH₂-, -CH₂-NH-CH₂-, -CH₂-N(CH₃)-CH₂-,
-CH₂-O-CH₂CH₂-O-CH₂-, -CH₂-(O-CH₂CH₂)₂-O-CH₂-, -CH₂-(O-CH₂CH₂)₃-O-CH₂-,
-CH₂-(O-CH₂CH₂)₄-O-CH₂- or -CH₂CH₂-S-CH₂CH₂-.

C₂-C₁₈Alkenylene is typically vinylene, methylvinylene, octenylethylene or dodecenylethylene. C₂-C₈Alkenylene is preferred.

Alkylidene of 2 to 20 carbon atoms may typically be ethylidene, propyliden, butylidene, pentylidene, 4-methylpentylidene, heptylidene, nonylidene, tridecylidene, nonadecylidene, 1-methylethylidene, 1-ethylpropylidene or 1-ethylpentylidene. C₂-C₈Alkylidene is preferred.

Phenylalkylidene of 7 to 20 carbon atoms may typically be benzylidene, 2-phenylethylidene or 1-phenyl-2-hexylidene. C₇-C₉Phenylalkylidene is preferred.

C₅-C₈Cycloalkylene is a saturated hydrocarbon group having two free valences and at least one ring unit and is typically cyclopentylene, cyclohexylene, cycloheptylene or cyclooctylene. Cyclohexylene is preferred.

C₇-C₈Bicycloalkylene may be bicycloheptylene or bicyclooctylene.

Unsubstituted or C₁-C₄alkyl-substituted phenylene or naphthylene is typically 1,2-, 1,3-, 1,4-phenylene, 1,2-, 1,3-, 1,4-, 1,6-, 1,7-, 2,6- or 2,7-naphthylene. 1,4-phenylene is preferred.

A C₁-C₄alkyl-substituted C₅-C₈cycloalkylidene ring that preferably contains 1 to 3, most preferably 1 or 2, branched or unbranched alkyl groups, is typically cyclopentylidene, methylcyclopentylidene, dimethylcyclopentylidene, cyclohexylidene, methylcyclohexylidene, dimethylcyclohexylidene, trimethylcyclohexylidene, tert-butylcyclohexylidene, cycloheptylidene or cyclooctylidene. Cyclohexylidene and tert-butylcyclohexylidene are preferred.

A mono-, di- or trivalent metal cation is preferably an alkali metal cation, an alkaline earth metal cation or an aluminium cation, typically Na⁺, K⁺, Mg⁺⁺, Ca⁺⁺ or Al⁺⁺⁺.

THIS SHEET HAS BEEN REPLACED

Interesting compounds of formula I are those wherein, when n is 1,

R₁ is phenyl which is unsubstituted or substituted in para-position by C₁-C₁₈alkylthio or di(C₁-C₄-alkyl)amino; mono- to penta-substituted alkylphenyl containing together a maximum number of 18 carbon atoms in the 1 to 5 alkyl substituents; naphthyl, biphenyl, terphenyl, phenanthryl, anthryl, fluorenyl, carbazolyl, thienyl, pyrrolyl, phenothiazinyl or 5,6,7,8-tetrahydronaphthyl, each unsubstituted or substituted by C₁-C₄alkyl, C₁-C₄alkoxy, C₁-C₄alkylthio, hydroxy or amino.

Preferred compounds of formula I are those wherein, when n is 2,

R₁ is -R₁₂-X-R₁₃-,


R₁₂ and R₁₃ are phenylene,

X is oxygen or -NR₃₁-, and

R₃₁ is C₁-C₄alkyl.

Further preferred compounds of formula I are those wherein, when n is 1,

R₁ is naphthyl, phenanthryl, thienyl, dibenzofuryl, carbazolyl, fluorenyl, each unsubstituted or substituted by C₁-C₄alkyl, C₁-C₄alkoxy, C₁-C₄alkylthio, hydroxy, halogen, amino, C₁-C₄alkylamino or di(C₁-C₄-alkyl)amino, or is a radical of formula II



R₇, R₈, R₉ and R₁₀ are each independently of one another hydrogen, chloro, bromo, hydroxy, C₁-C₁₈alkyl, C₂-C₁₈alkyl which is interrupted by oxygen or sulfur; C₁-C₁₈-alkoxy, C₂-C₁₈alkoxy which is interrupted by oxygen or sulfur; C₁-C₁₈alkylthio, C₃-C₁₂-alkenyloxy, C₃-C₁₂alkynyloxy, C₇-C₉phenylalkyl, C₇-C₉phenylalkoxy, unsubstituted or C₁-C₄alkyl-substituted phenyl; phenoxy, cyclohexyl, C₅-C₈cycloalkoxy; C₁-C₄alkyl-amino, di(C₁-C₄alkyl)amino, C₁-C₁₂alkanoyl, C₃-C₁₂alkanoyl which is interrupted by oxygen or sulfur; C₁-C₁₂alkanoyloxy, C₃-C₁₂alkanoyloxy which is interrupted by oxygen or sulfur; C₁-C₁₂alkanoylamino, C₃-C₁₂alkenoyl, C₃-C₁₂alkenoyloxy, cyclohexylcarbonyl, cyclohexylcarbonyloxy, benzoyl or C₁-C₄alkyl-substituted benzoyl; benzoyloxy or C₁-C₄-

alkyl substituted benzoyloxy; $\text{---O---}\overset{\overset{\text{R}_{18}}{\text{|}}}{\underset{\underset{\text{R}_{19}}{\text{|}}}{\text{C}}}\text{---}\overset{\overset{\text{O}}{\text{||}}}{\text{C}}\text{---R}_{15}$ or $\text{---O---}\overset{\overset{\text{R}_{20}}{\text{|}}}{\underset{\underset{\text{H}}{\text{|}}}{\text{C}}}\text{---}\overset{\overset{\text{R}_{21}}{\text{|}}}{\underset{\underset{\text{R}_{22}}{\text{|}}}{\text{C}}}\text{---O---R}_{23}$, or in

formula II each pair of substituents R_7 and R_8 or R_8 and R_{11} , together with the linking carbon atoms, forms a benzene ring,

R_{11} is hydrogen, $\text{C}_1\text{--C}_{18}$ alkyl, $\text{C}_1\text{--C}_{18}$ alkylthio, $\text{C}_7\text{--C}_9$ phenylalkyl, unsubstituted or $\text{C}_1\text{--C}_4$ -alkyl-substituted phenyl; cyclohexyl, $\text{C}_1\text{--C}_4$ alkylamino, di($\text{C}_1\text{--C}_4$ -alkyl)amino, $\text{C}_1\text{--C}_{12}$ -alkanoyl, $\text{C}_3\text{--C}_{12}$ alkanoyl which is interrupted by oxygen or sulfur; $\text{C}_1\text{--C}_{12}$ alkanoylamino, $\text{C}_3\text{--C}_{12}$ alkenoyl, cyclohexylcarbonyl, benzoyl or $\text{C}_1\text{--C}_4$ alkyl-substituted benzoyl; with the proviso that at least one of R_7 , R_8 , R_9 , R_{10} or R_{11} is not hydrogen;

R_{15} is hydroxy, $\text{C}_1\text{--C}_{12}$ alkoxy or $\text{---N}\overset{\overset{\text{R}_{24}}{\text{|}}}{\underset{\underset{\text{R}_{25}}{\text{|}}}{\text{---}}}$,



R_{18} and R_{19} are each independently of the other hydrogen or $\text{C}_1\text{--C}_4$ alkyl,

R_{20} is hydrogen,


R_{21} is hydrogen, phenyl, $\text{C}_1\text{--C}_{18}$ alkyl, $\text{C}_2\text{--C}_{18}$ alkyl which is interrupted by oxygen or sulfur, $\text{C}_7\text{--C}_9$ phenylalkyl, $\text{C}_7\text{--C}_{18}$ phenylalkyl which is interrupted by oxygen or sulfur and which is unsubstituted or substituted in the phenyl moiety by 1 to 3 $\text{C}_1\text{--C}_4$ alkyl groups, and R_{19} and R_{20} , together with the linking carbon atoms, form a cyclohexylene ring which is unsubstituted or substituted by 1 to 3 $\text{C}_1\text{--C}_4$ alkyl groups,

R_{22} is hydrogen or $\text{C}_1\text{--C}_4$ alkyl,

R_{23} is hydrogen, $\text{C}_1\text{--C}_{18}$ alkanoyl, $\text{C}_3\text{--C}_{12}$ alkenoyl, $\text{C}_3\text{--C}_{12}$ alkanoyl which is interrupted by oxygen or sulfur; $\text{C}_2\text{--C}_{12}$ alkanoyl which is substituted by a di($\text{C}_1\text{--C}_6$ -alkyl)phosphonate



THIS SHEET HAS BEEN
REPLACED



R₂₄ and R₂₅ are each independently of the other hydrogen or C₁-C₁₂alkyl,

R₂₆ is hydrogen or C₁-C₄alkyl,

R₂₇ is C₁-C₁₂alkylene, C₂-C₈alkenylene, C₂-C₈alkylidene, C₇-C₁₂phenylalkylidene, C₅-C₈cycloalkylene or phenylene,

R₂₈ is hydroxy, C₁-C₁₂alkoxy or $\text{---N}\begin{matrix} \text{R}_{24} \\ \text{R}_{25} \end{matrix}$,


R₂₉ is oxygen or -NH-,

R₃₀ is C₁-C₁₈alkyl or phenyl, and

s is 1 or 2.

Also preferred are compounds of formula I, wherein, when n is 1,

R₁ is phenanthryl, thienyl, dibenzofuryl, unsubstituted or C₁-C₄alkyl-substituted carbazoyl; or fluorenyl, or R₁ is a radical of formula II



R₇, R₈, R₉ and R₁₀ are each independently of one another hydrogen, chloro, hydroxy, C₁-C₁₈alkyl, C₁-C₁₈alkoxy, C₁-C₁₈alkylthio, C₃-C₄alkenyloxy, C₃-C₄-alkynyloxy, phenyl,

benzoyl, benzoyloxy or $\text{---O---}\overset{\text{R}_{20}}{\underset{\text{H}}{\text{C}}}\text{---}\overset{\text{R}_{21}}{\underset{\text{R}_{22}}{\text{C}}}\text{---O---R}_{23}$,

R₁₁ is hydrogen, C₁-C₁₈alkyl, C₁-C₁₈alkylthio, phenyl or cyclohexyl; with the proviso that at least one of R₇, R₈, R₉, R₁₀ or R₁₁ is not hydrogen,

R₂₀ is hydrogen,

R₂₁ is hydrogen, phenyl or C₁-C₁₈alkyl, or R₂₀ and R₂₁, together with the linking carbon atoms, form a cyclohexylene ring which is unsubstituted or substituted by 1 to 3 C₁-C₄-alkyl groups,

R₂₂ is hydrogen or C₁-C₄alkyl, and

R₂₃ is hydrogen, C₁-C₁₂alkanoyl or benzoyl.

THIS SHEET HAS BEEN
REPLACED

Compounds of formula I are especially preferred, wherein, when n is 1, R₇, R₈, R₉ and R₁₀ are each independently of one another hydrogen or C₁-C₄alkyl, and R₁₁ is hydrogen, C₁-C₁₂alkyl, C₁-C₄alkylthio or phenyl; with the proviso that at least one of R₇, R₈, R₉, R₁₀ or R₁₁ is not hydrogen.

Particularly interesting compounds of formula I are those wherein R₂, R₃, R₄ and R₅ are each independently of one another hydrogen, chloro, C₁-C₁₈alkyl, benzyl, phenyl, C₅-C₈-cycloalkyl, C₁-C₁₈alkoxy, C₁-C₁₈alkylthio, C₁-C₁₈alkanoyloxy, C₁-C₁₈alkanoylamino, C₃-C₁₈alkenoyloxy or benzoyloxy; with the proviso that, when R₂ is hydrogen or methyl, R₇ or R₉ is not hydroxy or C₁-C₂₅alkanoyloxy; or each pair of substituents R₂ and R₃ or R₃ and R₄ or R₄ and R₅, together with the linking carbon atoms, forms a benzene ring, R₄ is additionally -(CH₂)_p-COR₁₅ or -(CH₂)_qOH or, if R₃, R₅ and R₆ are hydrogen, R₄ is additionally a radical of formula III,

R₁₅ is hydroxy, C₁-C₁₂alkoxy or $\text{---N} \begin{matrix} \text{R}_{24} \\ \text{R}_{25} \end{matrix}$,

R₁₆ and R₁₇ are methyl groups or, together with the linking carbon atom, form a C₅-C₈-cycloalkylidene ring which is unsubstituted or substituted by 1 to 3 C₁-C₄alkyl groups, R₂₄ and R₂₅ are each independently of the other hydrogen or C₁-C₁₂alkyl, p is 1 or 2, and q is 2, 3, 4, 5 or 6.

Particularly interesting compounds of formula I are also those wherein at least two of R₂, R₃, R₄ and R₅ are hydrogen.

Compounds of formula I of very particular interest are those wherein R₃ and R₅ are hydrogen.

Very particularly preferred compounds of formula I are those wherein

R₂ is C₁-C₄alkyl,

R₃ is hydrogen,

R₄ is C₁-C₄alkyl or, if R₆ is hydrogen, R₄ is additionally a radical of formula III,



R₅ is hydrogen, and

R₁₆ and R₁₇, together with the linking carbon atom, form a cyclohexylidene ring.

THIS SHEET HAS BEEN
REPLACED

The compounds of formula I can be prepared in per se known manner.

Conveniently, a phenol of formula V



wherein R_2 , R_3 , R_4 and R_5 have the given meanings, is reacted with a mandelic acid derivative of formula VI which is substituted at the phenyl ring, wherein R_7 , R_8 , R_9 , R_{10} and R_{11} have the given meanings, at elevated temperature, preferably in the temperature range from 130 to 200°C, in the melt or in a solvent, under normal pressure or a slight vacuum, to the novel compounds of formula I, wherein R_6 is hydrogen.

To prepare the novel compounds of formula I, wherein n is 2, R_6 is hydrogen and R_1 is e.g. $-R_{12}-X-R_{13}-$, and R_{12} , R_{13} and X have the given meanings, 2 equivalents of the phenol of formula V are used.


It is preferred to carry out the reaction in the presence of a solvent such as acetic acid, propionic acid or formic acid, in the temperature range from 50 to 130°C. The reaction can be catalysed by the addition of an acid such as hydrochloric acid, sulfuric acid or methanesulfonic acid. The reaction may conveniently be carried out as described in the references cited at the outset, in particular according to US-A-4 325 863, Example 1, column 8, lines 35-45.

The drawback of this process for the preparation of compounds of formula I is that it is necessary to use mandelic acids that are substituted at the phenyl ring or heterocyclic mandelic acids. However, not very many of these acids are known in the literature and the known syntheses for the preparation of these mandelic acids are quite troublesome.

A novel process for the preparation of compounds of formula I, which is also the subject matter of a parallel application, is therefore preferred.

THIS SHEET HAS BEEN
REPLACED

Typically, a compound of formula VII



wherein R₂, R₃, R₄ and R₅ have the given meanings, is reacted with a compound of formula VIII, wherein R₁ has the given meaning, to compounds of formula I.

The reaction conditions of the inventive process are the following:

The reaction can be carried out at elevated temperature, preferably in the range from 70 to 200°C, in the melt or in a solvent and under normal pressure or slight vacuum.

It is particularly preferred to carry out the reaction in the boiling range of the compound of formula VIII.

The preferred solvent is the compound of formula VIII, which is simultaneously the reactant.

Suitable solvents are those which do not participate in the reaction, typically halogenated hydrocarbons, hydrocarbons, ethers or deactivated aromatic hydrocarbons.

Preferred halogenated hydrocarbons are dichloromethane, 1,2-dichloroethane, chloroform or carbon tetrachloride.

Preferred hydrocarbons are typically octane and the commercially available isomeric fractions such as the hexane fraction, white spirit or ligroin.

Preferred ethers are typically dibutyl ether, methyl tert-butyl ether or diethylene glycol dimethyl ether.

Illustrative examples of deactivated aromatic hydrocarbons are nitrobenzene or pyridine.

The water of reaction is preferably removed continuously, preferably by adding an agent that absorbs water, for example a molecular sieve. Most preferably the water is removed continuously as an azeotrope by distillation via a water separator.

This process for the preparation of compounds of formula I is preferably carried out in the presence of a catalyst.

Suitable catalysts are protonic acids, Lewis acids, aluminium silicates, ion exchange resins, zeolites, naturally occurring sheet silicates or modified sheet silicates.

Suitable protonic acids are typically acids of inorganic or organic salts, for example hydrochloric acid, sulfuric acid, phosphoric acid, methanesulfonic acid, p-toluenesulfonic acid or carboxylic acids such as acetic acid. p-Toluenesulfonic acid is particularly preferred.

Illustrative examples of suitable Lewis acids are tin tetrachloride, aluminium chloride, zinc chloride or borotrifluoride etherate. Tin tetrachloride and aluminium chloride are especially preferred.

Illustrative examples of suitable aluminium silicates are those that are widely used in the petrochemical industry and are also known as amorphous aluminium silicates. These compounds contain c. 10-30 % of silicon monoxide and 70-90 % of aluminium oxide. A particularly preferred aluminium silicate is HA-HPV[®] available from Ketjen (Akzo).

Illustrative examples of suitable ion exchange resins are styrene-divinylbenzene resins which additionally carry sulfonic acid groups, for example Amberlite 200[®] and Amberlyst[®] available from Rohm and Haas, or Dowex 50[®] available from Dow Chemicals; perfluorinated ion exchange resins such as Nafion H[®] sold by DuPont; or other superacid ion exchange resins such as those as described by T. Yamaguchi, Applied Catalysis, 61, 1-25 (1990) or M. Hino et al., J. Chem. Soc. Chem. Commun. 1980, 851-852.

Suitable zeolites are typically those widely used in petrochemistry as cracking catalysts and known as crystalline silicon-aluminium oxides of different crystal structure. Particularly preferred zeolites are the Faujasites available from Union Carbide, for example Zeolith X[®], Zeolith Y[®] and ultrastabile Zeolith Y[®]; Zeolith Beta[®] and Zeolith ZSM-12[®]

THIS SHEET HAS BEEN REPLACED

available from Mobil Oil Co.; and Zeolith Mordenit[®] available from Norton.

Suitable naturally occurring sheet silicates are termed "acid clays" and typically include bentonites or montmorillonites, which are degraded, ground, treated with mineral acids and calcined industrially. Particularly suitable naturally occurring sheet silicates are the Fulcat[®] types available from Laporte Adsorbents Co., for example Fulcat 22A[®], Fulcat 22B[®], Fulcat 20[®], Fulcat 30[®] or Fulcat 40[®]; or the Fulmont[®] types available from Laporte Adsorbents Co., for example Fulmont XMP-3[®] or Fulmont XMP-4[®]. A particularly preferred catalyst is Fulcat 22B[®]. The other Fulcat[®] types and Fulmont[®] types also belong to this preferred class, because there are only minor differences between the individual types, as for example in the number of acid centres.

Modified sheet silicates are also termed "pillared clays" and are derived from the above described naturally occurring sheet silicates by additionally containing between the silicate layers oxides of e.g. zirconium, iron, zinc, nickel, chromium, cobalt or magnesium. This type of catalyst is widely used, as described in the literature, inter alia by J. Clark et al., J. Chem. Soc. Chem. Commun. 1989, 1353-1354, but is available from only a very few firms. Particularly preferred modified sheet silicates typically include Envirocat EPZ-10[®], Envirocat EPZG[®] or Envirocat EPIC[®] available from Contract Chemicals.

Preferred catalysts are naturally occurring sheet silicates or modified sheet silicates.

Especially preferred is the process for the preparation of compounds of formula I, wherein the reaction is carried out in the presence of a catalyst of the Fulcat[®] type.


The catalyst is conveniently added in an amount of 1 to 60 % by weight and, if a particularly preferred catalyst of the Fulcat[®] type is used, in an amount of 1 to 30 % by weight, with respect to the compound of formula VII.

A particularly interesting process is also that for the preparation of compounds of formula I, wherein, when n is 1, the molar ratio of the compound of formula VII to the compound of formula VIII is 1:1 to 1:20, and, when n is 2, the molar ratio of the compound of formula VII to the compound of formula VIII is 3:1 to 2:1.

Before the reaction with a compound of formula VIII, the compounds of formula VII can be subjected to an additional reaction step by substituting the hydroxyl group in the com-

THIS SHEET HAS BEEN
REPLACED

pound of formula VII by halogen or activating said hydroxyl group with a leaving group. The reaction to give the compounds of formula IX



wherein R_{32} is halogen or $-OR'_{32}$, and R'_{32} is typically C_1-C_{25} alkanoyl, C_3-C_{25} alkenoyl, C_3-C_{25} alkanoyl which is interrupted by oxygen, sulfur or $\text{N}-R_{14}$; C_6-C_9 cycloalkylcarbonyl, thenoyl, furoyl, benzoyl or C_1-C_{12} alkyl-substituted benzoyl; naphthoyl or C_1-C_{12} alkyl-substituted naphthoyl; C_1-C_{25} alkanesulfonyl, fluoro-substituted C_1-C_{25} alkanesulfonyl; phenylsulfonyl or C_1-C_{12} alkyl-substituted phenylsulfonyl, can be carried out in accordance with known substitution reactions described, inter alia, in Organikum 1986, pages 186-191; or by esterification reactions described, inter alia, in Organikum 1986, pages 402-408.

Halogen substituents will conveniently be chloro, bromo or iodo. Chloro is preferred.

Alkanoyl of up to 25 carbon atoms inclusive is a branched or unbranched radical, typically including formyl, acetyl, propionyl, butanoyl, pentanoyl, hexanoyl, heptanoyl, octanoyl, nonanoyl, decanoyl, undecanoyl, dodecanoyl, tridecanoyl, tetradecanoyl, pentadecanoyl, hexadecanoyl, heptadecanoyl, octadecanoyl, eicosanoyl or docosanoyl. R'_{32} defined as alkanoyl preferably contains 2 to 18, most preferably 2 to 12, e.g. 2 to 6, carbon atoms. Acetyl is particularly preferred.

Alkenoyl of 3 to 25 carbon atoms is a branched or unbranched radical, typically including propenoyl, 2-butenoyl, 3-butenoyl, isobutenoyl, n-2,4-pentadienoyl, 3-methyl-2-butenoyl, n-2-octenoyl, n-2-dodecenoyl, isododecenoyl, oleoyl, n-2-octadecenoyl or n-4-octadecenoyl. Alkenoyl of 3 to 18, preferably 3 to 12, e.g. 3 to 6, most preferably 3 to 4, carbon atoms is preferred.

THIS SHEET HAS BEEN
REPLACED

C_3-C_{25} -Alkanoyl interrupted by oxygen, sulfur or $\text{N}-R_{14}$ will typically be $\text{CH}_3\text{-O-CH}_2\text{CO-}$, $\text{CH}_3\text{-S-CH}_2\text{CO-}$, $\text{CH}_3\text{-NH-CH}_2\text{CO-}$, $\text{CH}_3\text{-N(CH}_3\text{)-CH}_2\text{CO-}$, $\text{CH}_3\text{-O-CH}_2\text{CH}_2\text{-O-CH}_2\text{CO-}$, $\text{CH}_3\text{-(O-CH}_2\text{CH}_2\text{)}_2\text{O-CH}_2\text{CO-}$, $\text{CH}_3\text{-(O-CH}_2\text{CH}_2\text{)}_3\text{O-CH}_2\text{CO-}$ or $\text{CH}_3\text{-(O-CH}_2\text{CH}_2\text{)}_4\text{O-CH}_2\text{CO-}$.

C_6-C_9 Cycloalkylcarbonyl is typically cyclopentylcarbonyl, cyclohexylcarbonyl, cycloheptylcarbonyl or cyclooctylcarbonyl. Cyclohexylcarbonyl is preferred.

C_1-C_{12} Alkyl-substituted benzoyl which preferably carries 1 to 3, most preferably 1 or 2 alkyl groups, is typically o-, m- or p-methylbenzoyl, 2,3-dimethylbenzoyl, 2,4-dimethylbenzoyl, 2,5-dimethylbenzoyl, 2,6-dimethylbenzoyl, 3,4-dimethylbenzoyl, 3,5-dimethylbenzoyl, 2-methyl-6-ethylbenzoyl, 4-tert-butylbenzoyl, 2-ethylbenzoyl, 2,4,6-trimethylbenzoyl, 2,6-dimethyl-4-tert-butylbenzoyl or 3,5-di-tert-butylbenzoyl. Preferred substituents are C_1-C_8 alkyl, most preferably C_1-C_4 alkyl.

C_1-C_{12} Alkyl-substituted naphthoyl, which is 1-naphthoyl or 2-naphthoyl and preferably contains 1 to 3, most preferably 1 or 2 alkyl groups, will typically be 1-, 2-, 3-, 4-, 5-, 6-, 7- or 8-methylnaphthoyl, 1-, 2-, 3-, 4-, 5-, 6-, 7- or 8-ethylnaphthoyl, 4-tert-butylnaphthoyl or 6-tert-butylnaphthoyl. Particularly preferred substituents are C_1-C_8 alkyl, most preferably C_1-C_4 alkyl.


C_1-C_{25} Alkanesulfonyl is a branched or unbranched radical, typically methanesulfonyl, ethanesulfonyl, propanesulfonyl, butanesulfonyl, pentanesulfonyl, hexanesulfonyl, heptanesulfonyl, octanesulfonyl, nonanesulfonyl or docosanesulfonyl. Alkanesulfonyl of 1 to 18, preferably 1 to 12, e.g. 2 to 6, carbon atoms is preferred. Methanesulfonyl is particularly preferred.

Fluoro-substituted C_1-C_{25} alkanesulfonyl is typically trifluoromethanesulfonyl.

C_1-C_{12} Alkyl-substituted phenylsulfonyl which carries preferably 1 to 3, most preferably 1 or 2, alkyl groups is typically o-, m- or p-methylphenylsulfonyl, p-ethylphenylsulfonyl, p-propylphenylsulfonyl or p-butylphenylsulfonyl. Preferred substituents are C_1-C_8 alkyl, most preferably C_1-C_4 alkyl. p-Methylphenylsulfonyl is particularly preferred.

Thus, for example, the reaction of compounds of formula VII with a hydrohalic acid, a


halide of an oxysulfuric acid, a halide of phosphoric acid, a halide of a phosphorous acid, an acid of formula X




an acid halide of formula XI,




an ester of formula XII



a symmetrical or unsymmetrical anhydride of formula XIII



or an isocyanate of formula XIV



wherein R'_{32} in formula XIII may be different or identical,

Y is fluoro, chloro, bromo or iodo,

R_{33} is C_1 - C_8 alkyl, and

R_{34} is C_1 - C_{25} alkyl, unsubstituted or C_1 - C_4 alkyl-substituted phenyl, gives the compounds of formula IX in good yield.

Suitable hydrohalic acids are typically hydrochloric acid, hydrobromic acid or hydriodic acid. Hydrochloric acid is preferred.

Suitable halides of an oxysulfuric acid are typically thionyl chloride, sulfuryl chloride or thionyl bromide. Thionyl chloride is preferred.

Suitable halides of phosphoric acid and phosphorous acid typically include phosphorus tri-chloride, phosphorus tribromide, phosphorus triiodide, phosphorus pentachloride, phosphoroxy chloride or phosphorus pentafluoride. Phosphoroxy chloride is particularly pre-

THIS SHEET HAS BEEN REPLACED

ferred.

A preferred meaning of Y is chloro.

Preferred leaving groups are typically carboxylates such as acetates; alkanesulfonates such as mesylates; or arylsulfonates such as tosylates.

In this reaction step it is preferred to use a halide of an oxysulfuric acid such as thionyl chloride; an acid halide of formula XI; an ester of formula XII; or a symmetrical anhydride of formula XIII.

When using a halide of an oxysulfuric acid such as thionyl chloride, it is preferred to carry out the reaction of a compound of formula VII without a solvent and in the temperature range from 0 to 40°C, preferably at room temperature. The thionyl chloride is conveniently used in a 2- to 10-fold excess, preferably in a 2- to 6-fold excess, with respect to the compound of formula VII. The reaction can also be carried out in the presence of a catalyst such as dimethyl formamide.

When using an acid of formula X (R'_{32} -OH), the reaction is preferably carried out with a compound of formula VII in the presence of an inert organic solvent such as dichloromethane, dioxane, diethyl ether or tetrahydrofuran, and in the presence of a reagent that bonds water physically or chemically, conveniently a molecular sieve or dicyclohexylcarbodiimide.

If an acid halide of formula XI (R'_{32} -Y), wherein Y is preferably chloro or bromo, most preferably chloro, is used in process step b), it is preferred to carry out the reaction of the compound of formula VII in the presence of a solvent and a base.

The base can be used in varying amounts, from catalytic through stoichiometric amounts to the multiple molar excess with respect to the compound of formula VII. The hydrogen chloride formed during the reaction may be converted by the base into the chloride, which can be removed by filtration and/or washing with a suitable aqueous or solid phase, in which case a second water-immiscible solvent can also be used. The product is conveniently purified by recrystallising the residue of the organic phase, which is concentrated or evaporated to dryness.

THIS SHEET HAS BEEN
REPLACED

Suitable solvents for carrying out the reaction include hydrocarbons (typically toluene, xylene, hexane, pentane or further petroleum ether fractions), halogenated hydrocarbons (typically di- or trichloromethane, 1,2-dichloroethane, 1,1,1-trichloroethane), ethers (e.g. diethyl ether, dibutyl ether or tetrahydrofuran), and also acetonitrile, dimethyl formamide, dimethyl sulfoxide, N-methylpyrrolidone.

Suitable bases include tertiary amines, e.g. trimethylamine, triethylamine, tributylamine, N,N-dimethylaniline, N,N-diethylaniline; pyridines; hydrides (e.g. lithium, sodium or potassium hydride) or alcoholates (e.g. sodium methylate).

If an ester of formula XII ($R'_{32}-O-R_{33}$), wherein R_{33} is preferably C_1-C_4 alkyl, most preferably methyl or ethyl, is used in process step b), it is preferred to carry out the reaction of the compound of formula VII in the presence of a solvent that forms an azeotropic mixture with alcohols. The alcohol ($R_{33}-OH$) that forms during the reaction can be removed continuously by distillation.

Suitable solvents that form an azeotropic mixture with alcohols do not participate in the reaction and typically include hydrocarbons such as cyclohexane; aromatic hydrocarbons such as benzene or toluene; halogenated hydrocarbons such as 1,2-dichloroethane; or ethers such as methyl tert-butyl ether.

The reaction can be catalysed with a minor amount of a protonic acid such as p-toluenesulfonic acid, methanesulfonic acid, sulfuric acid or hydrochloric acid; as well as of a Lewis acid such as boron trifluoride etherate or aluminium chloride.


If a symmetrical anhydride of formula XIII ($R'_{32}-O-R'_{32}$), wherein R'_{32} is preferably C_2-C_6 alkanoyl, preferably acetyl, is used in process step b), it is preferred to carry out the reaction with a compound of formula VII without the addition of a further solvent and in the temperature range from 20 to 200°C, e.g. the boiling temperature of the anhydride of formula XIII, preferably from 60 to 180°C.

If an isocyanate of formula XIV ($R_{34}-N=C=O$) is used, it is preferred to carry out the reaction with a compound of formula VII without the addition of a further solvent and in the temperature range from 20 to 200°C, e.g. the boiling temperature of the isocyanate of formula XIV, preferably from 60 to 180°C.


THIS SHEET HAS BEEN
REPLACED

The reaction with an isocyanate is likewise preferably carried out in the presence of a catalyst. Preferred catalysts correspond to those referred to above previously in connection with the reaction of the alcohol of formula VII with the compound of formula VIII above.


In the process of this invention for the preparation of the novel compounds of formula I, wherein R_6 is hydrogen, the compounds of formula VIII, which also yield mixtures of isomers in other known electrophilic substitution reactions, likewise give compounds of formula I in the form of mixtures of isomers. The relative distribution of the isomers will depend on the commonly known basic rules of organic chemistry for electrophilic aromatic substitution reactions.



(105)



(105A)



(105B)

As described in Example 4, reaction of e.g. 5,7-di-tert-butyl-3-hydroxy-3H-benzofuran-2-one (compound (201), Table 2) with ethyl benzene, using Fulcat 22B as catalyst, gives 59.2 % of the para-isomer (compound (105). Table 1), 10.8 % of the meta-isomer (compound (105A) and 21.1 % of the ortho-isomer (compound (105B).

The isomers can be purified and separated by fractional crystallisation or chromatography on e.g. silica gel. It is preferred to use the mixtures of isomers as stabilisers for organic materials.


THIS SHEET HAS BEEN
REPLACED

The compounds of formula I can be obtained in different crystal modifications.


The compounds of formula VIII are novel and some are commercially available or can be prepared by per se known methods.

Some of the compounds of formula VII are known in the literature, and have been mentioned, inter alia, in Beilstein 18, 17 and Beilstein E III/IV, 18, 154-166, or described by Th. Kappe et al., Monatshefte für Chemie 99, 990 (1968); J. Morvan et al., Bull. Soc. Chim. Fr. 1979, 583; L. F. Clarke et al., J. Org. Chem. 57, 362 (1992); M. Julia et al., Bull. Soc. Chim. Fr. 1965, 2175, or by H. Sterk et al., Monatshefte für Chemie 99, 2223 (1968). Novel compounds of formula VII can be prepared by methods analogous to those described in these references.

Preferred, however, is a novel process for the preparation of compounds of formula VII



which process is the subject matter of a parallel patent application, wherein the general symbols are as defined for formula I, which comprises reacting 1 equivalent of the phenol of formula V



wherein the general symbols are as defined in connection with the novel compounds of formula I, with 0.8 to 2.0 equivalents, preferably 0.8 to 1.2 equivalents, of glyoxylic acid.

THIS SHEET HAS BEEN
REPLACED

The glyoxylic acid can be used either in crystalline form or, conveniently, in the form of a commercial aqueous solution, usually a 40 to 60 % aqueous solution.

The water present in the glyoxylic acid and the water of reaction is removed by distillation during the reaction, conveniently using a solvent that forms an azeotropic mixture with water.

Suitable solvents that form an azeotropic mixture with water do not participate in the reaction and typically include hydrocarbons such as cyclohexane; aromatic hydrocarbons such as benzene or toluene; halogenated hydrocarbons such as 1,2-dichloroethane; or ethers such as methyl tert-butyl ether.



When carrying out the reaction of the phenol of formula V with glyoxylic acid without a solvent to give the compounds of formula VII in the melt, the water of reaction is conveniently distilled off under normal pressure, preferably under a slight vacuum.

It is preferred to carry out the reaction at elevated temperature, preferably in the range from 60 to 120°C. A particularly preferred temperature range is from 60 to 90°C.

The reaction can be catalysed by the addition of a minor amount of a protonic acid such as p-toluenesulfonic acid, methanesulfonic acid, sulfuric acid or hydrochloric acid; or of a Lewis acid such as boron trifluoride etherate or aluminium chloride.

The amount of catalyst is 0.01 to 5 mol %, preferably 0.1 to 1.0 mol %, based on the phenol of formula V.


The compounds of formula VII can be obtained in their tautomeric forms of formula VIIa or formula VIIb



THIS SHEET HAS BEEN
REPLACED

as described by H. Sterk et al., Monatshefte für Chemie 99, 2223 (1968). Within the scope of this application, formula VII will always be understood as also embracing the two tautomeric formulae VIIa and VIIb.

Bisphenols of formula XIV



can be prepared in accordance with Houben-Weyl, Methoden der organischen Chemie, Vol. 6/1c, 1030.

The compounds of formula I, wherein R_6 is hydrogen, can also be prepared by a so-called one-pot process starting from the phenols of formula V, which comprises reacting one equivalent of the phenol of formula VII with 0.8 to 2.0 equivalents of glyoxylic acid to a compound of formula VII, and subsequently reacting said compound of formula VII, without isolation, with a compound of formula VIII.


The definitions of the general symbols in connection with the inventive one-pot process are the same as for the inventive processes discussed previously.

The preferred reaction parameters for the one-pot process correspond to those previously discussed in detail in connection with the two single steps.

Prior to the further reaction with a compound of formula VIII, the 3-hydroxy-3H-benzofuran-2-ones of formula VII initially formed in the one-pot process can be subjected to an additional reaction step by substituting the hydroxyl group with halogen or activating it with a leaving group.

A special one-pot process for the preparation of compounds of formula I comprises using a compound of formula V that differs from the compound of formula VIII.

THIS SHEET HAS BEEN
REPLACED



The dimerisation of the compounds of formula XVI for the preparation of compounds of formula I, wherein R_6 is a radical of formula IV [compounds of formula XVII] is carried out by oxidation with e.g. iodine under basic conditions in an organic solvent at room temperature. A particularly suitable base is sodium ethylate, and a particularly suitable solvent is ethanol or diethyl ether.

The compounds of formula I are suitable for stabilising organic materials against thermal, oxidative or light-induced degradation.

Illustrative examples of such materials are:

1. Polymers of monoolefins and diolefins, for example polypropylene, polyisobutylene, polybut-1-ene, poly-4-methylpent-1-ene, polyisoprene or polybutadiene, as well as polymers of cycloolefins, for instance of cyclopentene or norbornene, polyethylene (which optionally can be crosslinked), for example high density polyethylene (HDPE), low density polyethylene (LDPE), linear low density polyethylene (LLDPE), branched low density polyethylene (BLDPE).

Polyolefins, i.e. the polymers of monoolefins exemplified in the preceding paragraph, preferably polyethylene and polypropylene, can be prepared by different, and especially by the following, methods:

- a) radical polymerisation (normally under high pressure and at elevated temperature).
- b) catalytic polymerisation using a catalyst that normally contains one or more than one metal of groups IVb, Vb, VIb or VIII of the Periodic Table. These

metals usually have one or more than one ligand, typically oxides, halides, alcoholates, esters, ethers, amines, alkyls, alkenyls and/or aryls that may be either π - or σ -coordinated. These metal complexes may be in the free form or fixed on substrates, typically on activated magnesium chloride, titanium(III) chloride, alumina or silicon oxide. These catalysts may be soluble or insoluble in the polymerisation medium. The catalysts can be used by themselves in the polymerisation or further activators may be used, typically metal alkyls, metal hydrides, metal alkyl halides, metal alkyl oxides or metal alkyloxanes, said metals being elements of groups Ia, IIa and/or IIIa of the Periodic Table. The activators may be modified conveniently with further ester, ether, amine or silyl ether groups. These catalyst systems are usually termed Phillips, Standard Oil Indiana, Ziegler (-Natta), TNZ (DuPont), metallocene or single site catalysts (SSC).

2. Mixtures of the polymers mentioned under 1), for example mixtures of polypropylene with polyisobutylene, polypropylene with polyethylene (for example PP/HDPE, PP/LDPE) and mixtures of different types of polyethylene (for example LDPE/HDPE).
3. Copolymers of monoolefins and diolefins with each other or with other vinyl monomers, for example ethylene/propylene copolymers, linear low density polyethylene (LLDPE) and mixtures thereof with low density polyethylene (LDPE), propylene/but-1-ene copolymers, propylene/isobutylene copolymers, ethylene/but-1-ene copolymers, ethylene/hexene copolymers, ethylene/methylpentene copolymers, ethylene/heptene copolymers, ethylene/octene copolymers, propylene/butadiene copolymers, isobutylene/isoprene copolymers, ethylene/alkyl acrylate copolymers, ethylene/alkyl methacrylate copolymers, ethylene/vinyl acetate copolymers and their copolymers with carbon monoxide or ethylene/acrylic acid copolymers and their salts (ionomers) as well as terpolymers of ethylene with propylene and a diene such as hexadiene, dicyclopentadiene or ethylidene-norbornene; and mixtures of such copolymers with one another and with polymers mentioned in 1) above, for example polypropylene/ethylene-propylene copolymers, LDPE/ethylene-vinyl acetate copolymers (EVA), LDPE/ethylene-acrylic acid copolymers (EAA), LLDPE/EVA, LLDPE/EAA and alternating or random polyalkylene/carbon monoxide copolymers and mixtures thereof with other polymers, for example polyamides.
4. Hydrocarbon resins (for example C_5 - C_9) including hydrogenated modifications thereof (e.g. tackifiers) and mixtures of polyalkylenes and starch.

5. Polystyrene, poly(p-methylstyrene), poly(α -methylstyrene).
6. Copolymers of styrene or α -methylstyrene with dienes or acrylic derivatives, for example styrene/butadiene, styrene/acrylonitrile, styrene/alkyl methacrylate, styrene/butadiene/alkyl acrylate, styrene/butadiene/alkyl methacrylate, styrene/maleic anhydride, styrene/acrylonitrile/methyl acrylate; mixtures of high impact strength of styrene copolymers and another polymer, for example a polyacrylate, a diene polymer or an ethylene/propylene/diene terpolymer; and block copolymers of styrene such as styrene/butadiene/styrene, styrene/isoprene/styrene, styrene/ethylene/butylene/styrene or styrene/ethylene/propylene/styrene.
7. Graft copolymers of styrene or α -methylstyrene, for example styrene on polybutadiene, styrene on polybutadiene-styrene or polybutadiene-acrylonitrile copolymers; styrene and acrylonitrile (or methacrylonitrile) on polybutadiene; styrene, acrylonitrile and methyl methacrylate on polybutadiene; styrene and maleic anhydride on polybutadiene; styrene, acrylonitrile and maleic anhydride or maleimide on polybutadiene; styrene and maleimide on polybutadiene; styrene and alkyl acrylates or methacrylates on polybutadiene; styrene and acrylonitrile on ethylene/propylene/diene terpolymers; styrene and acrylonitrile on polyalkyl acrylates or polyalkyl methacrylates, styrene and acrylonitrile on acrylate/butadiene copolymers, as well as mixtures thereof with the copolymers listed under 6), for example the copolymer mixtures known as ABS, MBS, ASA or AES polymers.
8. Halogen-containing polymers such as polychloroprene, chlorinated rubbers, chlorinated or sulfochlorinated polyethylene, copolymers of ethylene and chlorinated ethylene, epichlorohydrin homo- and copolymers, especially polymers of halogen-containing vinyl compounds, for example polyvinyl chloride, polyvinylidene chloride, polyvinyl fluoride, polyvinylidene fluoride, as well as copolymers thereof such as vinyl chloride/vinylidene chloride, vinyl chloride/vinyl acetate or vinylidene chloride/vinyl acetate copolymers.
9. Polymers derived from α,β -unsaturated acids and derivatives thereof such as polyacrylates and polymethacrylates; polymethyl methacrylates, polyacrylamides and polyacrylonitriles, impact-modified with butyl acrylate.
10. Copolymers of the monomers mentioned under 9) with each other or with other unsaturated monomers, for example acrylonitrile/butadiene copolymers, acrylonitrile/-

THIS SHEET HAS BEEN REPLACED

alkyl acrylate copolymers, acrylonitrile/alkoxyalkyl acrylate or acrylonitrile/vinyl halide copolymers or acrylonitrile/ alkyl methacrylate/butadiene terpolymers.

11. Polymers derived from unsaturated alcohols and amines or the acyl derivatives or acetals thereof, for example polyvinyl alcohol, polyvinyl acetate, polyvinyl stearate, polyvinyl benzoate, polyvinyl maleate, polyvinyl butyral, polyallyl phthalate or polyallyl melamine; as well as their copolymers with olefins mentioned in 1) above.

12. Homopolymers and copolymers of cyclic ethers such as polyalkylene glycols, polyethylene oxide, polypropylene oxide or copolymers thereof with bisglycidyl ethers.

13. Polyacetals such as polyoxymethylene and those polyoxymethylenes which contain ethylene oxide as a comonomer; polyacetals modified with thermoplastic polyurethanes, acrylates or MBS.

14. Polyphenylene oxides and sulfides, and mixtures of polyphenylene oxides with styrene polymers or polyamides.

15. Polyurethanes derived from hydroxyl-terminated polyethers, polyesters or polybutadienes on the one hand and aliphatic or aromatic polyisocyanates on the other, as well as precursors thereof.

16. Polyamides and copolyamides derived from diamines and dicarboxylic acids and/or from aminocarboxylic acids or the corresponding lactams, for example polyamide 4, polyamide 6, polyamide 6/6, 6/10, 6/9, 6/12, 4/6, 12/12, polyamide 11, polyamide 12, aromatic polyamides starting from m-xylene diamine and adipic acid; polyamides prepared from hexamethylenediamine and isophthalic or/and terephthalic acid and with or without an elastomer as modifier, for example poly-2,4,4-trimethylhexamethylene terephthalamide or poly-m-phenylene isophthalamide; and also block copolymers of the aforementioned polyamides with polyolefins, olefin copolymers, ionomers or chemically bonded or grafted elastomers; or with polyethers, e.g. with polyethylene glycol, polypropylene glycol or polytetramethylene glycol; as well as polyamides or copolyamides modified with EPDM or ABS; and polyamides condensed during processing (RIM polyamide systems).

17. Polyureas, polyimides, polyamide-imides and polybenzimidazoles.

THIS SHEET HAS BEEN
REPLACED

18. Polyesters derived from dicarboxylic acids and diols and/or from hydroxycarboxylic acids or the corresponding lactones, for example polyethylene terephthalate, polybutylene terephthalate, poly-1,4-dimethylolcyclohexane terephthalate and polyhydroxybenzoates, as well as block copolyether esters derived from hydroxyl-terminated polyethers; and also polyesters modified with polycarbonates or MBS.

19. Polycarbonates and polyester carbonates.

20. Polysulfones, polyether sulfones and polyether ketones.

21. Crosslinked polymers derived from aldehydes on the one hand and phenols, ureas and melamines on the other hand, such as phenol/formaldehyde resins, urea/formaldehyde resins and melamine/formaldehyde resins.

22. Drying and non-drying alkyd resins.

23. Unsaturated polyester resins derived from copolyesters of saturated and unsaturated dicarboxylic acids with polyhydric alcohols and vinyl compounds as crosslinking agents, and also halogen-containing modifications thereof of low flammability.

24. Crosslinkable acrylic resins derived from substituted acrylates, for example epoxy acrylates, urethane acrylates or polyester acrylates.

25. Alkyd resins, polyester resins and acrylate resins crosslinked with melamine resins, urea resins, polyisocyanates or epoxy resins.

26. Crosslinked epoxy resins derived from polyepoxides, for example from bisglycidyl ethers or from cycloaliphatic diepoxides.

27. Natural polymers such as cellulose, rubber, gelatin and chemically modified homologous derivatives thereof, for example cellulose acetates, cellulose propionates and cellulose butyrates, or the cellulose ethers such as methyl cellulose; as well as rosins and their derivatives.

28. Blends of the aforementioned polymers (polyblends), for example PP/EPDM, Polyamide/EPDM or ABS, PVC/EVA, PVC/ABS, PVC/MBS, PC/ABS, PBTP/ABS,

THIS SHEET HAS BEEN
REPLACED

PC/ASA, PC/PBT, PVC/CPE, PVC/acrylates, POM/thermoplastic PUR, PC/thermoplastic PUR, POM/acrylate, POM/MBS, PPO/HIPS, PPO/PA 6.6 and copolymers, PA/HDPE, PA/PP, PA/PPO.

29. Naturally occurring and synthetic organic materials which are pure monomeric compounds or mixtures of such compounds, for example mineral oils, animal and vegetable fats, oil and waxes, or oils, fats and waxes based on synthetic esters (e.g. phthalates, adipates, phosphates or trimellitates) and also mixtures of synthetic esters with mineral oils in any weight ratios, typically those used as spinning compositions, as well as aqueous emulsions of such materials.

30. Aqueous emulsions of natural or synthetic rubber, e.g. natural latex or latices of carboxylated styrene/butadiene copolymers.

Further objects of the invention are therefore also compositions comprising an organic material that is susceptible to oxidative, thermal or light-induced degradation, and at least one compound of formula I.

Preferred organic materials are natural, semi-synthetic or, preferably, synthetic polymers.

Particularly preferred organic materials are synthetic polymers, most preferably thermoplastic polymers. Especially preferred organic materials are polyacetals or polyolefins such as polypropylene or polyethylene.

To be singled out for special mention is the efficacy of the novel compounds against thermal and oxidative degradation, especially under the action of heat which occurs during the processing of thermoplasts. The compounds of this invention are therefore admirably suited for use as processing stabilisers.

The compounds of formula I will preferably be added to the organic material to be stabilised in concentrations of 0.0005 to 5 %, preferably 0.001 to 2 %, typically 0.01 to 2 %, based on the weight of said material.

In addition to comprising the compounds of formula I, the inventive compositions may comprise further co-stabilisers, typically the following:

THIS SHEET HAS BEEN
REPLACED

1. Antioxidants

1.1. Alkylated monophenols, for example 2,6-di-tert-butyl-4-methylphenol, 2-tert-butyl-4,6-dimethylphenol, 2,6-di-tert-butyl-4-ethylphenol, 2,6-di-tert-butyl-4-n-butylphenol, 2,6-di-tert-butyl-4-isobutylphenol, 2,6-dicyclopentyl-4-methylphenol, 2-(α -methylcyclohexyl)-4,6-dimethylphenol, 2,6-dioctadecyl-4-methylphenol, 2,4,6-tricyclohexylphenol, 2,6-di-tert-butyl-4-methoxymethylphenol, 2,6-di-nonyl-4-methylphenol, 2,4-dimethyl-6-(1'-methylundec-1'-yl)phenol, 2,4-dimethyl-6-(1'-methylheptadec-1'-yl)phenol, 2,4-dimethyl-6-(1'-methyltridec-1'-yl)phenol and mixtures thereof.

1.2. Alkylthiomethylphenols, for example 2,4-dioctylthiomethyl-6-tert-butylphenol, 2,4-dioctylthiomethyl-6-methylphenol, 2,4-dioctylthiomethyl-6-ethylphenol, 2,6-di-dodecylthiomethyl-4-nonylphenol.

1.3. Hydroquinones and alkylated hydroquinones, for example 2,6-di-tert-butyl-4-methoxyphenol, 2,5-di-tert-butylhydroquinone, 2,5-di-tert-amylhydroquinone, 2,6-di-phenyl-4-octadecyloxyphenol, 2,6-di-tert-butylhydroquinone, 2,5-di-tert-butyl-4-hydroxyanisole, 3,5-di-tert-butyl-4-hydroxyanisole, 3,5-di-tert-butyl-4-hydroxyphenyl stearate, bis-(3,5-di-tert-butyl-4-hydroxyphenyl) adipate.

1.4. Tocopherols, for example α -tocopherol, β -tocopherol, γ -tocopherol, δ -tocopherol and mixtures thereof (Vitamin E).

1.5. Hydroxylated thiodiphenyl ethers, for example 2,2'-thiobis(6-tert-butyl-4-methylphenol), 2,2'-thiobis(4-octylphenol), 4,4'-thiobis(6-tert-butyl-3-methylphenol), 4,4'-thiobis(6-tert-butyl-2-methylphenol), 4,4'-thiobis-(3,6-di-sec-amylphenol), 4,4'-bis-(2,6-dimethyl-4-hydroxyphenyl) disulfide.

1.6. Alkylidenebisphenols, for example 2,2'-methylenebis(6-tert-butyl-4-methylphenol), 2,2'-methylenebis(6-tert-butyl-4-ethylphenol), 2,2'-methylenebis[4-methyl-6-(α -methylcyclohexyl)phenol], 2,2'-methylenebis(4-methyl-6-cyclohexylphenol), 2,2'-methylenebis(6-nonyl-4-methylphenol), 2,2'-methylenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(6-tert-butyl-4-isobutylphenol), 2,2'-methylenebis[6-(α -methylbenzyl)-4-nonylphenol], 2,2'-methylenebis[6-(α,α -dimethylbenzyl)-4-nonylphenol], 4,4'-methylenebis(2,6-di-tert-butylphenol), 4,4'-methylenebis(6-tert-butyl-2-methylphenol), 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 2,6-bis(3-

tert-butyl-5-methyl-2-hydroxybenzyl)-4-methylphenol, 1,1,3-tris(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)-3-n-dodecylmercaptobutane, ethylene glycol bis[3,3-bis(3'-tert-butyl-4'-hydroxyphenyl)butyrate], bis(3-tert-butyl-4-hydroxy-5-methylphenyl)dicyclopentadiene, bis[2-(3'-tert-butyl-2'-hydroxy-5'-methylbenzyl)-6-tert-butyl-4-methylphenyl]terephthalate, 1,1-bis-(3,5-dimethyl-2-hydroxyphenyl)butane, 2,2-bis-(3,5-di-tert-butyl-4-hydroxyphenyl)propane, 2,2-bis-(5-tert-butyl-4-hydroxy-2-methylphenyl)-4-n-dodecylmercaptobutane, 1,1,5,5-tetra-(5-tert-butyl-4-hydroxy-2-methylphenyl)pentane.

1.7. O-, N- and S-benzyl compounds, for example 3,5,3',5'-tetra-tert-butyl-4,4'-dihydroxy-dibenzyl ether, octadecyl-4-hydroxy-3,5-dimethylbenzylmercaptoacetate, tris-(3,5-di-tert-butyl-4-hydroxybenzyl)amine, bis(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)dithio-terephthalate, bis(3,5-di-tert-butyl-4-hydroxybenzyl)sulfide, isooctyl-3,5-di-tert-butyl-4-hydroxybenzylmercaptoacetate.

1.8. Hydroxybenzylated malonates, for example dioctadecyl-2,2-bis-(3,5-di-tert-butyl-2-hydroxybenzyl)-malonate, di-octadecyl-2-(3-tert-butyl-4-hydroxy-5-methylbenzyl)-malonate, di-dodecylmercaptoethyl-2,2-bis-(3,5-di-tert-butyl-4-hydroxybenzyl)malonate, bis-[4-(1,1,3,3-tetramethylbutyl)phenyl]-2,2-bis(3,5-di-tert-butyl-4-hydroxybenzyl)malonate.

1.9. Aromatic hydroxybenzyl compounds, for example 1,3,5-tris-(3,5-di-tert-butyl-4-hydroxybenzyl)-2,4,6-trimethylbenzene, 1,4-bis(3,5-di-tert-butyl-4-hydroxybenzyl)-2,3,5,6-tetramethylbenzene, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxybenzyl)phenol.

1.10. Triazine Compounds, for example 2,4-bis(octylmercapto)-6-(3,5-di-tert-butyl-4-hydroxyanilino)-1,3,5-triazine, 2-octylmercapto-4,6-bis(3,5-di-tert-butyl-4-hydroxyanilino)-1,3,5-triazine, 2-octylmercapto-4,6-bis(3,5-di-tert-butyl-4-hydroxyphenoxy)-1,3,5-triazine, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxyphenoxy)-1,2,3-triazine, 1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl)isocyanurate, 1,3,5-tris(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)isocyanurate, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxyphenylethyl)-1,3,5-triazine, 1,3,5-tris(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)-hexahydro-1,3,5-triazine, 1,3,5-tris(3,5-dicyclohexyl-4-hydroxybenzyl)isocyanurate.

1.11. Benzylphosphonates, for example dimethyl-2,5-di-tert-butyl-4-hydroxybenzylphosphonate, diethyl-3,5-di-tert-butyl-4-hydroxybenzylphosphonate, dioctadecyl-3,5-di-tert-butyl-4-hydroxybenzylphosphonate, dioctadecyl-5-tert-butyl-4-hydroxy-3-methylbenzyl-

phosphonate, the calcium salt of the monoethyl ester of 3,5-di-tert-butyl-4-hydroxybenzyl-phosphonic acid.

1.12. Acylaminophenols, for example 4-hydroxylauranilide, 4-hydroxystearanilide, octyl N-(3,5-di-tert-butyl-4-hydroxyphenyl)carbamate.

1.13. Esters of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl) isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.14. Esters of β -(5-tert-butyl-4-hydroxy-3-methylphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl) isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.15. Esters of β -(3,5-dicyclohexyl-4-hydroxyphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl) isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.16. Esters of 3,5-di-tert-butyl-4-hydroxyphenyl acetic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl) isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.17. Amides of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid e.g. N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hexamethylenediamine, N,N'-bis(3,5-di-tert-butyl-

4-hydroxyphenylpropionyl)trimethylenediamine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hydrazine.

2. UV absorbers and light stabilisers

2.1. 2-(2'-Hydroxyphenyl)benzotriazoles, for example 2-(2'-hydroxy-5'-methylphenyl)-benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(5'-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(2'-hydroxy-5'-(1,1,3,3-tetramethylbutyl)phenyl)benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)-5-chloro-benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-methylphenyl)-5-chloro-benzotriazole, 2-(3'-sec-butyl-5'-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(2'-hydroxy-4'-octyloxyphenyl)benzotriazole, 2-(3',5'-di-tert-amyl-2'-hydroxyphenyl)benzotriazole, 2-(3',5'-bis-(α,α -dimethylbenzyl)-2'-hydroxyphenyl)benzotriazole, mixture of 2-(3'-tert-butyl-2'-hydroxy-5'-(2-octyloxycarbonyl)phenyl)-5-chloro-benzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethylhexyloxy)-carbonyl]phenyl)-5-chloro-benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-methoxycarbonyl)phenyl)-5-chloro-benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-methoxycarbonyl)phenyl)benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-octyloxycarbonyl)phenyl)benzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethylhexyloxy)carbonyl]phenyl)-2'-hydroxyphenyl)benzotriazole, 2-(3'-dodecyl-2'-hydroxy-5'-methylphenyl)benzotriazole, and 2-(3'-tert-butyl-2'-hydroxy-5'-(2-isooctyloxycarbonyl)phenyl)benzotriazole, 2,2'-methylene-bis[4-(1,1,3,3-tetramethylbutyl)-6-benzotriazole-2-ylphenol]; the transesterification product of 2-[3'-tert-butyl-5'-(2-methoxycarbonyl)phenyl]-2H-benzotriazole with polyethylene glycol 300; $[R-CH_2CH_2-COO(CH_2)_3]_2$, where R = 3'-tert-butyl-4'-hydroxy-5'-2H-benzotriazol-2-ylphenyl.

2.2. 2-Hydroxybenzophenones, for example the 4-hydroxy, 4-methoxy, 4-octyloxy, 4-decyloxy, 4-dodecyloxy, 4-benzyloxy, 4,2',4'-trihydroxy and 2'-hydroxy-4,4'-dimethoxy derivatives.

2.3. Esters of substituted and unsubstituted benzoic acids, as for example 4-tertbutylphenyl salicylate, phenyl salicylate, octylphenyl salicylate, dibenzoyl resorcinol, bis(4-tert-butylbenzoyl) resorcinol, benzoyl resorcinol, 2,4-di-tertbutylphenyl 3,5-di-tert-butyl-4-hydroxybenzoate, hexadecyl 3,5-di-tert-butyl-4-hydroxybenzoate, octadecyl 3,5-di-tert-butyl-4-hydroxybenzoate, 2-methyl-4,6-di-tert-butylphenyl 3,5-di-tert-butyl-4-hydroxybenzoate.

2.4. Acrylates, for example ethyl α -cyano- β,β -diphenylacrylate, isooctyl α -cyano- β,β -diphenylacrylate, methyl α -carbomethoxycinnamate, methyl α -cyano- β -methyl-p-methoxycinnamate, butyl α -cyano- β -methyl-p-methoxycinnamate, methyl α -carbomethoxy-p-methoxycinnamate and N-(β -carbomethoxy- β -cyanovinyl)-2-methylindoline.

2.5. Nickel compounds, for example nickel complexes of 2,2'-thio-bis-[4-(1,1,3,3-tetramethylbutyl)phenol], such as the 1:1 or 1:2 complex, with or without additional ligands such as n-butylamine, triethanolamine or N-cyclohexyldiethanolamine, nickel dibutyldithiocarbamate, nickel salts of the monoalkyl esters, e.g. the methyl or ethyl ester, of 4-hydroxy-3,5-di-tert-butylbenzylphosphonic acid, nickel complexes of ketoximes, e.g. of 2-hydroxy-4-methylphenyl undecylketoxime, nickel complexes of 1-phenyl-4-lauroyl-5-hydroxypyrazole, with or without additional ligands.

2.6. Sterically hindered amines, for example bis(2,2,6,6-tetramethyl-piperidyl)sebacate, bis(2,2,6,6-tetramethyl-piperidyl)succinate, bis(1,2,2,6,6-pentamethylpiperidyl)sebacate, bis(1,2,2,6,6-pentamethylpiperidyl) n-butyl-3,5-di-tert-butyl-4-hydroxybenzylmalonate, the condensate of 1-(2-hydroxyethyl)-2,2,6,6-tetramethyl-4-hydroxypiperidine and succinic acid, the condensate of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-tert-octylamino-2,6-dichloro-1,3,5-triazine, tris(2,2,6,6-tetramethyl-4-piperidyl) nitrilotriacetate, tetrakis(2,2,6,6-tetramethyl-4-piperidyl)-1,2,3,4-butane-tetracarboxylate, 1,1'-(1,2-ethanediyl)bis(3,3,5,5-tetramethylpiperazinone), 4-benzoyl-2,2,6,6-tetramethylpiperidine, 4-stearyloxy-2,2,6,6-tetramethylpiperidine, bis(1,2,2,6,6-pentamethylpiperidyl)-2-n-butyl-2-(2-hydroxy-3,5-di-tert-butylbenzyl)malonate, 3-n-octyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decan-2,4-dione, bis(1-octyloxy-2,2,6,6-tetramethylpiperidyl)sebacate, bis(1-octyloxy-2,2,6,6-tetramethylpiperidyl)succinate, the condensate of N,N'-bis-(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-morpholino-2,6-dichloro-1,3,5-triazine, the condensate of 2-chloro-4,6-bis(4-n-butylamino-2,2,6,6-tetramethylpiperidyl)-1,3,5-triazine and 1,2-bis(3-aminopropylamino)ethane, the condensate of 2-chloro-4,6-di-(4-n-butylamino-1,2,2,6,6-pentamethylpiperidyl)-1,3,5-triazine and 1,2-bis-(3-aminopropylamino)ethane, 8-acetyl-3-dodecyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decane-2,4-dione, 3-dodecyl-1-(2,2,6,6-tetramethyl-4-piperidyl)pyrrolidin-2,5-dione, 3-dodecyl-1-(1,2,2,6,6-pentamethyl-4-piperidyl)pyrrolidine-2,5-dione.

2.7. Oxamides, for example 4,4'-dioctyloxyoxanilide, 2,2'-diethoxyoxanilide, 2,2'-dioctyloxy-5,5'-di-tert-butoxanilide, 2,2'-didodecyloxy-5,5'-di-tert-butoxanilide, 2-ethoxy-2'-

ethyloxanilide, N,N'-bis(3-dimethylaminopropyl)oxamide, 2-ethoxy-5-tert-butyl-2'-ethoxyanilide and its mixture with 2-ethoxy-2'-ethyl-5,4'-di-tert-butoxanilide and mixtures of ortho- and para-methoxy-disubstituted oxanilides and mixtures of o- and p-ethoxy-disubstituted oxanilides.

2.8. 2-(2-Hydroxyphenyl)-1,3,5-triazines, for example 2,4,6-tris(2-hydroxy-4-octyloxyphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2,4-dihydroxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2,4-bis(2-hydroxy-4-propyloxyphenyl)-6-(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(4-methylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-dodecyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2hydroxy-3-butyloxy-propoxy)phenyl]-4,6-bis(2,4-dimethyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-octyloxy-propyloxy)phenyl]-4,6-bis(2,4-dimethyl)-1,3,5-triazine.

3. Metal deactivators, for example N,N'-diphenyloxamide, N-salicylal-N'-salicyloyl hydrazine, N,N'-bis(salicyloyl) hydrazine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl) hydrazine, 3-salicyloylamino-1,2,4-triazole, bis(benzylidene)oxalyl dihydrazide, oxanilide, isophthaloyl dihydrazide, sebacoyl bisphenylhydrazide, N,N'-diacetyl adipoyl dihydrazide, N,N'-bis(salicyloyl)oxalyl dihydrazide, N,N'-bis(salicyloyl)-thiopropionyl dihydrazide.

4. Phosphites and phosphonites, for example triphenyl phosphite, diphenyl alkyl phosphites, phenyl dialkyl phosphites, tris(nonylphenyl) phosphite, trilauryl phosphite, trioctadecyl phosphite, distearyl pentaerythritol diphosphite, tris(2,4-di-tert-butylphenyl) phosphite, diisodecyl pentaerythritol diphosphite, bis(2,4-di-tert-butylphenyl) pentaerythritol diphosphite, bis(2,6-di-tert-butyl-4-methylphenyl)-pentaerythritol diphosphite, diisodecyl pentaerythritol diphosphite, bis(2,4-di-tert-butyl-6-methylphenyl)pentaerythritol diphosphite, bis(2,4,6-tris(tert-butylphenyl)pentaerythritol diphosphite, tristearyl sorbitol triphosphite, tetrakis(2,4-di-tert-butylphenyl) 4,4'-biphenylene diphosphonite, 6-isooctyloxy-2,4,8,10-tetra-tert-butyl-12H-dibenz[d,g]-1,3,2-dioxaphosphocin, 6-fluoro-2,4,8,10-tetra-tert-butyl-12-methyl-dibenz[d,g]-1,3,2-dioxaphosphocin, bis(2,4-di-tert-butyl-6-methylphenyl)methylphosphite, bis(2,4-di-tert-butyl-6-methylphenyl)ethylphosphite.

5. Peroxide scavengers, for example esters of β -thiodipropionic acid, for example the lauryl, stearyl, myristyl or tridecyl esters, mercaptobenzimidazole or the zinc salt of 2-mercaptobenzimidazole, zinc dibutyldithiocarbamate, dioctadecyl disulfide, penta-

erythritol tetrakis(β -dodecylmercapto)propionate.

6. Polyamide stabilisers, for example, copper salts in combination with iodides and/or phosphorus compounds and salts of divalent manganese.

7. Basic co-stabilisers, for example, melamine, polyvinylpyrrolidone, dicyandiamide, tri-allyl cyanurate, urea derivatives, hydrazine derivatives, amines, polyamides, polyurethanes, alkali metal salts and alkaline earth metal salts of higher fatty acids for example calcium stearate, zinc stearate, magnesium behenate, magnesium stearate, sodium ricinoleate and potassium palmitate, antimony pyrocatecholate or tin pyrocatecholate.

8. Nucleating agents, for example, 4-tert-butylbenzoic acid, adipic acid, diphenylacetic acid.

9. Fillers and reinforcing agents, for example, calcium carbonate, silicates, glass fibres, asbestos, talc, kaolin, mica, barium sulfate, metal oxides and hydroxides, carbon black, graphite.

10. Other additives, for example, plasticisers, lubricants, emulsifiers, pigments, optical brighteners, flameproofing agents, antistatic agents and blowing agents.

The co-stabilisers are typically used in concentrations of 0.01 to 10 %, based on the total weight of the material to be stabilised.

The novel compounds of formula I can be used in particular together with phenolic antioxidants, light stabilisers and/or processing stabilisers.

It is particularly preferred to use the novel compounds of formula I together with phenolic antioxidants. The novel compositions therefore preferably comprise, in addition to compounds of formula I, phenolic antioxidants, preferably those listed in items 1.1 to 1.17 of the above list.

Other preferred compositions comprise, in addition to compounds of formula I, a compound of the organic phosphite or phosphonite type.

The compounds of formula I and other optional additives are incorporated into the organic

THIS SHEET HAS BEEN
REPLACED

polymeric material by known methods, conveniently before or during shaping to moulded articles or alternatively by coating the organic polymeric material with a solution or dispersion of the compounds and subsequently evaporating the solvent. The compounds of formula I can also be added to the materials to be stabilised in the form of a masterbatch which contains these compounds, typically in a concentration of 2.5 to 25 % by weight.

The compounds of formula I can also be added before or during polymerisation or before crosslinking.

In this connection, particular attention is drawn to the surprising feature that the novel compounds of formula I inhibit discolouration, especially so-called "pinkings", in the manufacture of e.g. polyurethane foams.

The compounds of formula I can be incorporated into the material to be stabilised in pure form or in waxes, oils or polymer encapsulations.

The compounds of formula I can also be sprayed on to the polymer to be stabilised. They are able to dilute other additives (typically the conventional additives listed above) or melts thereof, so that they can also be sprayed together with these additives on to the polymer to be stabilised. Application by spraying during deactivation of the polymerisation catalysts is especially advantageous, in which case spraying is conveniently effected with the vapour used for deactivation.

It may be expedient to spray the compounds of formula I, with or without other additives, on to spherical polymerised polyolefins.

A preferred embodiment of this invention is therefore the use of compounds of formula I for stabilising organic materials against oxidative, thermal or light-induced degradation.

The stabilised materials may be in any form of presentation, typically sheets, filaments, ribbons, mouldings, profiles or binders for coating compositions, adhesives or putties.

The invention also relates to a process for stabilising an organic material against oxidative, thermal or light-induced degradation, which comprises incorporating therein or applying thereto at least one compound of formula I.

THIS SHEET HAS BEEN
REPLACED

As already emphasised, the novel compounds are used with particular advantage as stabilisers in polyolefins, preferably as heat stabilisers. Excellent stabilisation is achieved when the compounds are used in conjunction with organic phosphites or phosphonites. The novel compounds have in this case the advantage that they are effective in exceedingly low concentration, typically in concentrations from 0.0001 to 0.050 % by weight, preferably from 0.0001 to 0.015 % by weight, based on the polyolefin. The organic phosphite or phosphonite is conveniently used in a concentration of 0.01 to 2 % by weight, preferably of 0.01 to 1 % by weight, based on the polyolefin. It is preferred to use the organic phosphites and phosphonites disclosed in DE-A-4 202 276. Attention is drawn in particular to the claims, to the Examples and to pages 5, last paragraph, to 8. Particularly suitable phosphites and phosphonites will also be found under item 4 of the above list of co-stabilisers.

Some of the novel compounds of formula I, when incorporated in polyolefins, induce slight yellowing. This yellowing of polyolefins can be substantially inhibited by a combination of the novel compounds of formula I with phosphites or phosphonites.

Further objects of the invention are compositions comprising a functional fluid, preferably of the series of the lubricants, hydraulic fluids and metal processing fluids as well as fuels for driving motors of the Otto 4-stroke, Otto 2-stroke, diesel, Wankel and orbital type, and at least one compound of formula I.

Particularly preferred lubricants are the mineral oils, the synthetic oils or mixtures thereof.

Suitable functional fluids of the series of the lubricants, hydraulic fluids and metal processing fluids are per se known products.

The suitable lubricants and hydraulic fluids are known to the skilled person and are described in the relevant literature, inter alia in Dieter Klamann, "Schmierstoffe und verwandte Produkte" (Lubricants and Related Products) (Verlag Chemie, Weinheim, 1982), in Schewe-Kobek, "Das Schmiermittel-Taschenbuch" (Handbook of Lubricants) (Dr. Alfred Hüthig-Verlag, Heidelberg, 1974), and in "Ullmanns Enzyklopädie der technischen Chemie" (Ullmann's Encyclopedia of Industrial Chemistry), Vol. 13, pages 85-94 (Verlag Chemie, Weinheim, 1977).

Illustrative examples are lubricants and hydraulic fluids based on mineral oils or synthetic lubricants or hydraulic fluids, especially those that are carboxylic acid derivatives and are

THIS SHEET HAS BEEN REPLACED

used at temperatures of 200°C and above.

Synthetic lubricants typically comprise lubricants based on a diester of a divalent acid with a monohydric alcohol, typically dioctyl sebacate or dinonyl adipate, on a triester of trimethylolpropane with a monovalent acid or with a mixture of acids, conveniently trimethylolpropane tripelargonate, trimethylolpropane tricaprylate or mixtures thereof, on a tetraester of pentaerythritol with a monovalent acid or with a mixture of such acids, typically pentaerythritol tetracaprylate, or on a complex ester of monovalent and divalent acids with polyhydric alcohols, for example a complex ester of trimethylolpropane with caprylic and sebacic acid or of a mixture thereof.

Especially suitable lubricants are, in addition to mineral oils, typically poly- α -olefins, ester-based lubricants, phosphates, glycols, polyglycols and polyalkylene glycols and mixtures thereof with water.

The compounds of formula I are readily soluble in lubricants and are therefore especially suitable for use as additives for lubricants. Their surprisingly good antioxidative and anti-corrosive properties merit special mention.

In lubricants for combustion engines, as in combustion engines that operate according to the Otto principle, the novel compounds of formula I are able to exert their surprising properties. Thus the compounds of formula I inhibit in lubricant oils the formation of deposits (sludge) or reduce such deposits in surprising manner.

It is also possible to prepare masterbatches.

The compounds of formula I act as additives in lubricants even in very minor amounts. They are conveniently added to the lubricants in an amount of 0.01 to 5 % by weight, preferably of 0.05 to 3 % by weight and, most preferably, of 0.1 to 2 % by weight, based in each case on the lubricant.

The lubricants may also contain other additives which are added for further enhancement of the basic properties. These further additives comprise antioxidants, metal deactivators, rust inhibitors, viscosity improvers, pour-point depressants, dispersants, detergents, other extreme-pressure and antiwear additives.

THIS SHEET HAS BEEN
REPLACED

A number of such compounds will be found in the above list under item "1. Antioxidants", especially under 1.1 to 1.17. Illustrative examples of such further additives are:

Examples of aminic antioxidants:

N,N'-diisopropyl-p-phenylenediamine, N,N'-di-sec-butyl-p-phenylenediamine, N,N'-bis-(1,4-dimethylpentyl)-p-phenylenediamine, N,N'-bis(1-ethyl-3-methylpentyl)-p-phenylenediamine, N,N'-bis(1-methylheptyl)-p-phenylenediamine, N,N'-dicyclohexyl-p-phenylenediamine, N,N'-diphenyl-p-phenylenediamine, N,N'-bis(2-naphthyl)-p-phenylenediamine, N-isopropyl-N'-phenyl-p-phenylenediamine, N-(1,3-dimethyl-butyl)-N'-phenyl-p-phenylenediamine, N-(1-methylheptyl)-N'-phenyl-p-phenylenediamine, N-cyclohexyl-N'-phenyl-p-phenylenediamine, 4-(p-toluenesulfamoyl)diphenylamine, N,N'-dimethyl-N,N'-di-sec-butyl-p-phenylenediamine, diphenylamine, N-allyldiphenylamine, 4-isopropoxydiphenylamine, N-phenyl-1-naphthylamine, N-phenyl-2-naphthylamine, octylated diphenylamine, for example p,p'-di-tert-octyldiphenylamine, 4-n-butylaminophenol, 4-butylaminophenol, 4-nonanoylaminophenol, 4-dodecanoylaminophenol, 4-octadecanoylaminophenol, bis(4-methoxyphenyl)amine, 2,6-di-tert-butyl-4-dimethylaminomethylphenol, 2,4'-diaminodiphenylmethane, 4,4'-diaminodiphenylmethane, N,N,N',N'-tetramethyl-4,4'-diaminodiphenylmethane, 1,2-bis[(2-methyl-phenyl)amino]ethane, 1,2-bis(phenylamino)propane, (o-tolyl)biguanide, bis[4-(1',3'-dimethylbutyl)phenyl]amine, tert-octylated N-phenyl-1-naphthylamine, a mixture of mono- and dialkylated tert-butyl/tert-octyldiphenylamines, a mixture of mono- and dialkylated isopropyl/isohexyldiphenylamines, mixtures of mono- and dialkylated tert-butyldiphenylamines, 2,3-dihydro-3,3-dimethyl-4H-1,4-benzothiazine, phenothiazine, N-allylphenothiazine, N,N,N',N'-tetraphenyl-1,4-diaminobut-2-ene, N,N-bis(2,2,6,6-tetramethylpiperid-4-yl)-hexamethylenediamine, bis(2,2,6,6-tetramethylpiperid-4-yl) sebacate, 2,2,6,6-tetramethylpiperidin-4-one and 2,2,6,6-tetramethylpiperidin-4-ol.

Examples of other antioxidants:

Aliphatic or aromatic phosphites, esters of thiodipropionic acid or of thiodiacetic acid, or salts of dithiocarbamic or dithiophosphoric acid, 2,2,12,12-tetramethyl-5,9-dihydroxy-3,7,11-trithiatridecane and 2,2,15,15-tetramethyl-5,12-dihydroxy-3,7,10,14-tetrathiahexadecane.

Examples of metal deactivators, for example for copper, are:

- a) Benzotriazoles and derivatives thereof, for example 4- or 5-alkylbenzotriazoles (e.g. tolutriazole) and derivatives thereof, 4,5,6,7-tetrahydrobenzotriazole and 5,5'-

THIS SHEET HAS BEEN
REPLACED

methylenebisbenzotriazole; Mannich bases of benzotriazole or tolutriazole, e.g. 1-[bis(2-ethylhexyl)aminomethyl]tolutriazole and 1-[bis(2-ethylhexyl)aminomethyl]benzotriazole; and alkoxyalkylbenzotriazoles such as 1-(nonyloxymethyl)benzotriazole, 1-(1-butoxyethyl)benzotriazole and 1-(1-cyclohexyloxybutyl)tolutriazole.

- b) 1,2,4-Triazoles and derivatives thereof, for example 3-alkyl(or aryl)-1,2,4-triazoles, and Mannich bases of 1,2,4-triazoles, such as 1-[bis(2-ethylhexyl)aminomethyl]-1,2,4-triazole; alkoxyalkyl-1,2,4-triazoles such as 1-(1-butoxyethyl)-1,2,4-triazole; and acylated 3-amino-1,2,4-triazoles.
- c) Imidazole derivatives, for example 4,4'-methylenebis(2-undecyl-5-methylimidazole) and bis[(N-methyl)imidazol-2-yl]carbinol octyl ether.
- d) Sulfur-containing heterocyclic compounds, for example 2-mercaptobenzothiazole, 2,5-dimercapto-1,3,4-thiadiazole and derivatives thereof; and 3,5-bis[di(2-ethylhexyl)aminomethyl]-1,3,4-thiadiazolin-2-one.
- e) Amino compounds, for example salicylidenepropylenediamine, salicylamino-guanidine and salts thereof.

Examples of rust inhibitors are:

- a) Organic acids, their esters, metal salts, amine salts and anhydrides, for example alkyl- and alkenylsuccinic acids and their partial esters with alcohols, diols or hydroxycarboxylic acids, partial amides of alkyl- and alkenylsuccinic acids, 4-nonylphenoxyacetic acid, alkoxy- and alkoxyethoxycarboxylic acids such as dodecyloxyacetic acid, dodecyloxy(ethoxy)acetic acid and the amine salts thereof, and also N-oleoylsarcosine, sorbitan monooleate, lead naphthenate, alkenylsuccinic anhydrides, for example dodecenylsuccinic anhydride, 2-(carboxyethyl)-1-dodecyl-3-methylglycerol and the amine salts thereof.
- b) Nitrogen-containing compounds, for example:
 - I. Primary, secondary or tertiary aliphatic or cycloaliphatic amines and amine salts of organic and inorganic acids, for example oil-soluble alkylammonium carboxylates, and also 1-[N,N-bis(2-hydroxyethyl)amino]-3-(4-nonylphenoxy)propan-2-ol.

THIS SHEET HAS BEEN
REPLACED

- II. Heterocyclic compounds, for example: substituted imidazolines and oxazolines, and 2-heptadecenyl-1-(2-hydroxyethyl)imidazoline.
- c) Phosphorus-containing compounds, for example: Amine salts of phosphoric acid partial esters or phosphonic acid partial esters, and zinc dialkyldithiophosphates.
- d) Sulfur-containing compounds, for example: barium dinonylnaphthalenesulfonates, calcium petroleum sulfonates, alkylthio-substituted aliphatic carboxylic acids, esters of aliphatic 2-sulfocarboxylic acids and salts thereof.
- e) Glycerol derivatives, for example: glycerol monooleate, 1-(alkylphenoxy)-3-(2-hydroxyethyl)glycerols, 1-(alkylphenoxy)-3-(2,3-dihydroxypropyl)glycerols and 2-carboxyalkyl-1,3-dialkylglycerols.

Examples of viscosity index improvers are:

Polyacrylates, polymethacrylates, vinylpyrrolidone/methacrylate copolymers, polyvinylpyrrolidones, polybutenes, olefin copolymers, styrene/acrylate copolymers and polyethers.

Examples of pour-point depressants are:

Polymethacrylate and alkylated naphthalene derivatives.

Examples of dispersants/surfactants are:

Polybutenylsuccinic amides or -imides, polybutenylphosphonic acid derivatives and basic magnesium, calcium and barium sulfonates and phenolates.

Examples of antiwear additives are:

Sulfur- and/or phosphorus- and/or halogen-containing compounds, e.g. sulfurised olefins and vegetable oils, zinc dialkyldithiophosphates, alkylated triphenyl phosphates, tritolyl phosphate, tricresyl phosphate, chlorinated paraffins, alkyl and aryl di- and trisulfides, amine salts of mono- and dialkyl phosphates, amine salts of methylphosphonic acid, diethanolaminomethyltolyltriazole, bis(2-ethylhexyl)aminomethyltolyltriazole, derivatives of 2,5-dimercapto-1,3,4-thiadiazole, ethyl 3-[(diisopropoxyphosphinothioyl)thio]propionate, triphenyl thiophosphate (triphenylphosphorothioate), tris(alkylphenyl) phosphorothioate and mixtures thereof (for example tris(isononylphenyl) phosphorothioate), diphenyl monononylphenyl phosphorothioate, isobutylphenyl diphenyl phosphorothioate,

the dodecylamine salt of 3-hydroxy-1,3-thiaphosphetane 3-oxide, trithiophosphoric acid 5,5,5-tris[isooctyl 2-acetate], derivatives of 2-mercaptobenzothiazole such as 1-[N,N-bis-(2-ethylhexyl)aminomethyl]-2-mercapto-1H-1,3-benzothiazole, and ethoxycarbonyl-5-octyldithiocarbamate.

The invention is illustrated in more detail by the following Examples, in which parts and percentages are by weight.

Example 1: Preparation of 5,7-di-tert-butyl-3-(2,5-dimethylphenyl)-3H-benzofuran-2-one (compound (101), Table 1) starting from 5,7-di-tert-butyl-3-hydroxy-3H-benzofuran-2-one (compound (201), Table 2) with p-xylene, as well as Fulcat 22B as catalyst.

a) Preparation of 5,7-di-tert-butyl-3-hydroxy-3H-benzofuran-2-one (compound (201), Table 2).

A mixture of 212.5 g (1.00 mol) of 2,4-di-tert-butylphenol (97 %), 163.0 g (1.10 mol) of 50 % aqueous glyoxylic acid and 0.5 g (2.6 mmol) of p-toluenesulfonic acid monohydrate in 300 ml of 1,2-dichloroethane is refluxed under nitrogen for 3.5 hours on a water separator. Afterwards the reaction mixture is concentrated on a vacuum rotary evaporator. The residue is taken up in 800 ml of hexane and washed three times with water. The aqueous phases are separated in the separating funnel and further extracted with 300 ml of hexane. The organic phases are combined, dried over magnesium sulfate and concentrated on a vacuum rotary evaporator. The residue yields 262.3 g (~100 %) of analytically pure 5,7-di-tert-butyl-3-hydroxy-3H-benzofuran-2-one in the form of a thick yellowish resin (compound (201), Table 2).

In analogy to Example 1a, compounds (202), (203), (204), (205), (209), (210) and (211) are prepared from the corresponding phenols such as 2-tert-butyl-4-methylphenol, 4-tert-butyl-2-methylphenol, 2,4-dicyclohexylphenol, 2-(hexadec-2-yl)-4-methylphenol, 3-[3-tert-butyl-4-hydroxyphenyl]propionic acid, 2,4-bis(α,α -dimethylbenzyl)phenol and 4-methyl-2-(1,1,3,3-tetramethylbut-1-yl)phenol with glyoxylic acid. To prepare compound (207), 2 equivalents of glyoxylic acid are used starting from 1,1-bis(3-tert-butyl-4-hydroxyphenyl)cyclohexane.

b) Preparation of 5,7-di-tert-butyl-3-(2,5-dimethylphenyl)-3H-benzofuran-2-one (compound (101), Table 1)

THIS SHEET HAS BEEN REPLACED

To a solution of 262.3 g (1.00 mol) of 5,7-di-tert-butyl-3-hydroxy-3H-benzofuran-2-one (compound (201), Table 2, Example 1a) in 500 ml (4.05 mol) of p-xylene are added 40 g of Fulcat 22B and the mixture is refluxed for 1.5 hours on a water separator. The Fulcat 22B catalyst is then removed by filtration and excess p-xylene is removed by distillation on a vacuum rotary evaporator. Crystallisation of the residue from 400 ml of methanol yields 280.6 g (80 %) of 5,7-di-tert-butyl-3-(2,5-dimethylphenyl)-3H-benzofuran-2-one, m.p. 93-97°C (compound (101), Table 1).

Example 2: Preparation of 5,7-di-tert-butyl-3-(2,5-dimethylphenyl)-3H-benzofuran-2-one (compound (101), Table 1) starting from 3-acetoxy-5,7-di-tert-butyl-3H-benzofuran-2-one (compound (206), Table 2) with p-xylene, as well as Fulcat 22B as catalyst.

a) Preparation of 3-acetoxy-5,7-di-tert-butyl-3H-benzofuran-2-one (compound (206), Table 2).

A mixture of 21.2 g (0.10 mol) of 2,4-di-tert-butylphenol (97 %), 16.3 g (0.11 mol) of 50 % aqueous glyoxylic acid and 0.05 g (0.26 mmol) of p-toluenesulfonic acid monohydrate in 30 ml of 1,2-dichloroethane is refluxed under nitrogen for 3.5 hours on a water separator. Afterwards the reaction mixture is concentrated on a vacuum rotary evaporator. The residue is taken up in 9.9 ml (0.105 mol) of acetic anhydride and the solution is refluxed for 90 minutes. The reaction mixture is then cooled to room temperature, diluted with 100 ml of tert-butyl methyl ether and washed in succession with water and dilute sodium hydrogencarbonate solution. The aqueous phases are separated and extracted with 50 ml of tert-butyl methyl ether. The organic phases are combined, dried over magnesium sulfate and concentrated on a vacuum rotary evaporator. Chromatography of the residue on silica gel with the solvent system dichloromethane/hexane = 2:1 yields 28.0 g (92 %) of 3-acetoxy-5,7-di-tert-butyl-3H-benzofuran-2-one (compound (206), Table 2) as a thick reddish resin.

b) Preparation of 5,7-di-tert-butyl-3-(2,5-dimethylphenyl)-3H-benzofuran-2-one (compound (101), Table 1)

To a solution of 15.3 g (50.0 mmol) of 3-acetoxy-5,7-di-tert-butyl-3H-benzofuran-2-one (compound (206), Table 2, Example 2a) in 25 ml (0.20 mol) of p-xylene is added 1.0 g of Fulcat 22B and the mixture is refluxed for 17 hours on a water separator. The Fulcat 22B

THIS SHEET HAS BEEN
REPLACED

catalyst is then removed by filtration and excess p-xylene is removed by distillation on a vacuum rotaray evaporator. Crystallisation of the residue from 20 ml of methanol yields 10.5 g (60 %) of 5,7-di-tert-butyl-3-(2,5-dimethylphenyl)-3H-benzofuran-2-one, m.p. 93-97°C (compound (101), Table 1).

Example 3: Preparation of 3-(3,4-dimethylphenyl)-5,7-di-tert-butyl-3H-benzofuran-2-one (compound (103), Table 1) starting from 5,7-di-tert-butyl-3-hydroxy-3H-benzofuran-2-one (compound (201), Table 2) with o-xylene, as well as Fulcat 22B as catalyst.

To a solution of 262.3 g (1.00 mol) of 5,7-di-tert-butyl-3-hydroxy-3H-benzofuran-2-one (compound (201), Table 2, Example 1a) in 500 ml (4.05 mol) of o-xylene are added 40 g of Fulcat 22B and the mixture is refluxed for 1.5 hours on a water separator. The Fulcat 22B catalyst is then removed by filtration and excess p-xylene is removed by distillation on a vacuum rotary evaporator. Crystallisation of the residue from 500 ml of methanol yields 244 g (69 %) of 3-(3,4-dimethylphenyl)-5,7-di-tert-butyl-3H-benzofuran-2-one, m.p. 130-132°C (compound (103), Table 1), which additionally contains c. 1.3 % of the structural isomer [3-(2,3-dimethylphenyl)-5,7-di-tert-butyl-3H-benzofuran-2-one, compound (103A)]. The mother liquor yields a further 42.4 g of product which, according to GC-MS analysis, consists of 12.3 % of the compound (103) and 87.7 % of the isomeric compound (103A).

Example 4: Preparation of 5,7-di-tert-butyl-3-(4-ethylphenyl)-3H-benzofuran-2-on (compound (105), Table 1) starting from 5,7-di-tert-butyl-3-hydroxy-3H-benzofuran-2-one (compound (201), Table 2, with ethyl benzene, as well as Fulcat 22B as catalyst.

To a solution of 262.3 g (1.00 mol) of 5,7-di-tert-butyl-3-hydroxy-3H-benzofuran-2-one (compound (201), Table 2, Example 1a) in 500 ml (4.08 mol) of ethyl benzene are added 40 g of Fulcat 22B and the mixture is refluxed for 1.5 hours on a water separator. The Fulcat 22B catalyst is then removed by filtration and excess ethyl benzene is removed by distillation on a vacuum rotary evaporator. GC-MS analysis shows the residue to consist of a mixture of 59.2 % of the para-isomer (compound (105). Table 1), 10.8 % of the meta-isomer (compound (105A) and 21.1 % of the ortho-isomer(compound (105B). Crystallisation of the residue from 400 ml of methanol yields 163.8 g (47 %) of 5,7-di-tert-butyl-3-(4-ethylphenyl)-3H-benzofuran-2-one (compound (105), Table 1) (para-isomer), which additionally contains 5.6 % of the meta-isomer 5,7-di-tert-butyl-3-(3-ethylphenyl)-3H-benzofuran-2-one (compound (105A) and 1.3 % of the ortho-isomer 5,7-di-tert-butyl-

3-(2-ethylphenyl)3H-benzofuran-2-one (compound (105B)). Further crystallisation from methanol yields the almost pure para-isomer (compound (105), Table 1), m.p. 127-132°C.

In accordance with the general procedure described in this Example, compounds (102), (106), (107), (114), (115), (116), (117), (118) and (119) are prepared from 5,7-di-tert-butyl-3-hydroxy-3H-benzofuran-2-one (compound (201), Table 2, Example 1a) and the corresponding aromatic hydrocarbons, typically including m-xylene, isopropylbenzene (cumene), tert-butylbenzene, biphenyl, thiophene, p-xylene, dibenzofuran, phenanthrene and diphenyl ether. To prepare compound (119), 2 equivalents of 5,7-di-tert-butyl-3-hydroxy-3H-benzofuran-2-one are used starting from diphenyl ether.

Example 5: Preparation of 5,7-di-tert-butyl-3-(2,3,4,5,6-pentamethylphenyl)-3H-benzofuran-2-one (compound (111), Table 1) starting from 5,7-di-tert-butyl-3-hydroxy-3H-benzofuran-2-one (compound (201), Table 2) with pentamethylbenzene, as well as tin tetrachloride as catalyst.

11.5 g (77.5 mmol) of pentamethylbenzene and 10 ml (85.0 mmol) of tin tetrachloride are added to a solution of 19.7 g (75.0 mmol) of 5,7-di-tert-butyl-3-hydroxy-3H-benzofuran-2-one (compound (201), Table 2, Example 1a) in 50 ml of 1,2-dichloroethane and the reaction mixture is refluxed for 1 hour. The reaction mixture is diluted with water and extracted three times with toluene. The organic phases are combined, washed with water, dried over sodium sulfate and concentrated on a vacuum rotary evaporator. Crystallisation of the residue from ethanol yields 26.3 g (89 %) of 5,7-di-tert-butyl-3-(2,3,4,5,6-pentamethylphenyl)-3H-benzofuran-2-one, m.p. 185-190°C (compound (111), Table 1).

In accordance with the general procedure of this Example, compounds (109) and (110) are prepared from 5,7-di-tert-butyl-3-hydroxy-3H-benzofuran-2-one (compound (201), Table 2, Example 1a) and the corresponding aromatic hydrocarbons, for example n-dodecylbenzene and 1,2,3-trimethylbenzene.

Example 6: Preparation of 5,7-di-tert-butyl-3-(4-methylthiophenyl)-3H-benzofuran-2-one (compound (108), Table 1) starting from 5,7-di-tert-butyl-3-hydroxy-3H-benzofuran-2-one (compound (201), Table 2) with thioanisole, as well as aluminium trichloride as catalyst.

A solution of 26.2 g (0.10 mol) of 5,7-di-tert-butyl-3-hydroxy-3H-benzofuran-2-one (compound (201), Table 2, Example 1a) in 25 ml (0.21 mol) of thioanisole is added dropwise to

a solution of 14.7 g (0.11 mol) of aluminium chloride in 15 ml (0.13 mol) of thioanisole at 35-40°C. The reaction mixture is thereafter stirred for 30 minutes at 30°C and for 2 hours at 80°C, and then after cooling, c. 50 ml of water and then concentrated hydrochloric acid and methylene chloride are added cautiously in sufficient amount to form a homogeneous two-phase mixture. The organic phase is separated, washed with water, dried over sodium sulfate and concentrated on a vacuum rotary evaporator. Crystallisation of the residue from ethanol yields 6.7 g (18 %) of 5,7-di-tert-butyl-3-(4-methylthiophenyl)-3H-benzofuran-2-one, m.p. 125-131°C (compound (108), Table 1).

Example 7: Preparation of 5,7-di-tert-butyl-3-(4-methylphenyl)-3H-benzofuran-2-one (compound (104), Table 1) starting from 2,4-di-tert-butylphenol, without isolation of 5,7-di-tert-butyl-3-hydroxy-3H-benzofuran-2-one (compound (201), Table 2), with glyoxylic acid and toluene, as well as Fulcat 22B as catalyst.

A mixture of 21.2 g (0.10 mol) of 2,4-di-tert-butylphenol (97 %), 16.3 g (0.11 mol) of 50 % aqueous glyoxylic acid, 2.0 g of Fulcat 22B and 50 ml of toluene is refluxed for 8 hours under nitrogen on a water separator. The Fulcat 22B catalyst is then removed by filtration and excess toluene is distilled off on a vacuum rotary evaporator. Crystallisation of the residue from 40 ml of ethanol yields 14.2 g (42 %) of 5,7-di-tert-butyl-3-(4-methylphenyl)-3H-benzofuran-2-one, m.p. 130-133°C (compound (104), Table 1).

In accordance with the general procedure of this Example, the compound (112) is prepared starting from 2-tert-butyl-4-methylphenol instead of from 2,4-di-tert-butylphenol.

Example 8: Preparation of 4,4'-di-(5,7-di-tert-butyl-3H-benzofuran-2-on-3-yl)-N-methyldiphenylamine (compound (113), Table 1) starting from 5,7-di-tert-butyl-3-hydroxy-3H-benzofuran-2-one (compound (201), Table 2) with N-methyl-diphenylamine, as well as p-toluenesulfonic acid as catalyst.

30.2 g (115.0 mmol) of 5,7-di-tert-butyl-3-hydroxy-3H-benzofuran-2-one (compound (201), Table 2, Example 1a) are added over 2 hours to a boiling solution of 9.20 g (50.0 mmol) of N-methyl-diphenylamine and 0.20 g of p-toluenesulfonic acid monohydrate in 50 ml of ligroin (mixture of alkanes with a boiling range of 140-160°C). The reaction mixture is then refluxed for 4 hours on a water separator, then cooled and concentrated on a vacuum rotary evaporator. Crystallisation of the residue from isopropanol/water = 9:1 yields 18.9 g (56 %) of 4,4'-bis(5,7-di-tert-butyl-3H-benzofuran-2-on-3-yl)-N-

methyl-diphenylamine, m.p. 135-145°C (compound (113), Table 1).

Example 9: Preparation of 7-tert-butyl-5-methyl-3-(9-methyl-9H-carbazol-3-yl)-3H-benzofuran-2-one (compound (120), Table 1) starting from 7-tert-butyl-3-hydroxy-5-methyl-3H-benzofuran-2-one (compound (202), Table 2) with N-methylcarbazole and n-octane, as well as Fulcat 22B as catalyst.

A mixture of 2.2 g (10.0 mmol) of 7-tert-butyl-3-hydroxy-5-methyl-3H-benzofuran-2-one (compound (202), Example 1a, Table 2), 1.8 g (10.0 mmol) of N-methylcarbazole and 0.2 g of Fulcat 22B and 20 ml of n-octane is refluxed for 5 hours under nitrogen. The Fulcat 22B catalyst is subsequently removed by filtration and excess n-octane is distilled off on a vacuum rotary evaporator. Chromatography of the residue on silica gel with the solvent system dichloromethane/hexane = 1:2 to 1:1 and subsequent crystallisation of the pure fractions from methanol yields 0.70 g (10 %) of 7-tert-butyl-5-methyl-3-(9-methyl-9H-carbazol-3-yl)-3H-benzofuran-2-one, m.p. 84-90°C (compound (120), Table 1). The product may additionally contain minor amounts of other structural isomers in accordance with the substitution at the carbazole ring.

Example 10: Preparation of 5,7-di-tert-butyl-3-(9H-fluoren-3-yl)-3H-benzofuran-2-one (compound (121), Table 1) starting from 2,4-di-tert-butylphenol, without isolation of 5,7-di-tert-butyl-3-hydroxy-3H-benzofuran-2-one (compound (201), Table 2), with glyoxylic acid and fluorene, as well as p-toluenesulfonic and Fulcat 22B as catalyst.

A mixture of 15.9 g (75 mmol) of 2,4-di-tert-butylphenol (97 %), 12.2 g (82 mmol) of 50 % aqueous glyoxylic acid, 40 mg (0.20 mmol) of p-toluenesulfonic acid monohydrate and 25 ml of 1,2-dichloroethane is refluxed for 3.5 hours under nitrogen on a water separator. The reaction mixture is thereafter concentrated on a vacuum rotary evaporator. The residue is dissolved in 30 ml of n-octane and 12.5 g (75 mmol) of fluorene and 3 g of Fulcat 22B are added to the solution. This reaction mixture is refluxed for 3.5 hours under nitrogen on a water separator, then cooled and filtered. The filtrate is concentrated on a vacuum rotary evaporator. Chromatography of the residue on silica gel with the solvent system dichloromethane/hexane = 2:1 and subsequent crystallisation of the pure fractions from methanol yields 5.28 g (17 %) of 5,7-di-tert-butyl-3-(9H-fluoren-3-yl)-3H-benzofuran-2-one, m.p. 140-153°C (compound (121), Table 1). The product may additionally contain minor amounts of other structural isomers in accordance with the substitution at the fluorene ring.

THIS SHEET HAS BEEN REPLACED

Example 11: Preparation of a c. 5.7:1 mixture of 3-(3,4-dimethylphenyl)-5,7-di-tert-butyl-3H-benzofuran-2-one (compound (103), Table 1) and 3-(2,3-dimethylphenyl)-5,7-di-tert-butyl-3H-benzofuran-2-one (compound (103A)) isomers starting from 2,4-di-tert-butylphenol with glyoxylic acid and o-xylene, as well as Fulcat or Fulmont as catalyst.

To a 1500 ml double-walled reactor with water separator are charged 206.3 g (1.0 mol) of 2,4-di-tert-butylphenol, 485 g (5.5 mol) of o-xylene, 0.5 g (2.6 mmol) of p-toluenesulfonic acid monohydrate and 163 g (1.1 mol) of 50 % aqueous glyoxylic acid. With stirring, the mixture is heated to 85-90°C and the apparatus is simultaneously evacuated to c. 450 mbar. As soon as the temperature in the reactor is 85-90°C, a mixture of o-xylene/-water begins to distill from the mixture, the o-xylene being refluxed and the water removed from the system. The vacuum is then raised continuously so that the temperature in the reactor can be kept at 85-90°C. Altogether c. 98-100 ml of water are distilled over 3 to 4 hours. The vacuum is then released with nitrogen and 40 g of catalyst (Fulcat 30 or 40, Fulmont XMP-3 or XMP-4) are added to the clear yellow solution. The apparatus is evacuated to a pressure of 700 mbar and the suspension is stirred at a heating bath temperature of 165°C. The water of reaction begins to distill from the system as an azeotrope from a temperature of c. 128°C. The temperature in the apparatus rises towards the end to a maximum of 140°C. A total amount of c. 20 ml of water distills from the system over 1 to 2 hours. The vacuum is then released with nitrogen. The reaction mixture is cooled to 90-100°C and filtered. The apparatus and the filter residue are rinsed with 100 g of o-xylene. The filtrate is transferred to a 1500 ml double-walled reactor and concentrated under vacuum and 360 g of o-xylene are recovered. The reddish-yellow residue is cooled to 70°C and 636 g of methanol are added cautiously from a dropping funnel, while keeping the temperature at 60-65°C. The solution is seeded and stirred for c. 30 minutes at 60-65°C to effect crystallisation. The crystalline slurry is then cooled over 2 hours to -5°C and stirring is continued at this temperature for a further 1 hour. The crystals are collected by suction filtration and the residue is washed with 400 g of cold (-5°C) methanol in 5 portions. The well dry-pressed product is dried in a vacuum drier at 50-60°C, yielding 266 g of a white solid. Analysis by gas chromatography shows this material to consist of c. 85 % of 3-(3,4-dimethylphenyl)-5,7-di-tert-butyl-3H-benzofuran-2-one (compound (103), Table 1) as well as of c. 15 % of the 3-(2,3-dimethylphenyl)-5,7-di-tert-butyl-3H-benzofuran-2-one isomer (compound (103A)).

Example 12: Preparation of 3-(N-methylcarbamoyloxy)-5-methyl-7-tert-butyl-3H-benzo-

THIS SHEET HAS BEEN
REPLACED

furan-2-one (compound (212), Table 2).





A mixture of 5.5 g (25.0 mmol) of 7-tert-butyl-3-hydroxy-5-methyl-3H-benzofuran-2-one (compound (202), Example 1a), 3 ml (50.0 mmol) of methyl isocyanate and 2 drops of methanesulfonic acid are refluxed for 3 1/4 hours. Then a further 3 ml (50.0 mmol) of methyl isocyanate and 2 drops of methanesulfonic acid are added. The reaction mixture is refluxed for another 16 hours, then cooled, diluted with dichloromethane and washed with water and a 5 % aqueous solution of sodium hydrogencarbonate. The organic phases are combined, dried over magnesium sulfate and concentrated on a vacuum rotary evaporator. Crystallisation of the residue from toluene yields 4.45 g (65 %) of 3-(N-methylcarbamoyloxy)-5-methyl-7-tert-butyl-3H-benzofuran-2-one (compound (212), Table 2), m.p. 138-143°C (compound (212), Table 2).

Example 13: Preparation of 7-tert-butyl-3-chloro-5-methyl-3H-benzofuran-2-one (compound (208), Table 2).

To a suspension of 2.2 g (10.0 mmol) of 7-tert-butyl-3-hydroxy-5-methyl-3H-benzofuran-2-one (compound (202), Example 1a, Table 2) in 2.4 ml (55.0 mmol) of thionyl chloride is added one drop of dimethyl formamide and the mixture is stirred for 2 hours at room temperature. Excess thionyl chloride is afterwards distilled off on a vacuum rotary evaporator. Chromatography of the residue on silica gel with the solvent system dichloromethane/hexane = 1:1 and crystallisation of the pure fractions from methanol yields 0.30 g (13 %) of 7-tert-butyl-3-chloro-5-methyl-3H-benzofuran-2-one, m.p. 81-86°C (compound (208), Table 2).

THIS SHEET HAS BEEN
REPLACED

Table 1:

No.	Compound	m.p. (°C)	C (%), H (%) (calcd/found)	Yield (%)
101		93-97	82.24 8.63 82.10 8.66	80
102		92-96	82.24 86.3 82.19 8.78	52 ^{a)}
103		130-132	82.24 8.63 82.36 8.62	69 ^{a)}
104		130-133	82.10 8.39 82.13 8.31	42 ^{a)}

a) The product may additionally contain minor amounts of other structural isomers in accordance with the substitution at the phenyl ring in 3-position of the benzofuran-2-one.





THIS SHEET HAS BEEN
REPLACED

Table 1: (continuation)

No.	Compound	m.p. (°C)	C (%), H (%) (calcd/found)	Yield (%)
105		127-132	82.24 8.63 82.39 8.65	47 ^{a)}
106		109-115	82.37 8.85 82.24 8.91	41 ^{a)}
107		110-115	82.49 9.05 82.49 9.03	68 ^{a)}
108		125-131	characterised by ¹ H-NMR (CDCl ₃) δ(H*) = 4.79 ppm	18 ^{a)}

a) The product may additionally contain minor amounts of other structural isomers in accordance with the substitution at the phenyl ring in 3-position of the benzofuran-2-one.





Table 1: (continuation)

No.	Compound	m.p. (°C)	C (%), H (%) (calcd/found)	Yield (%)
109		oil	characterised by ¹ H-NMR (CDCl ₃) δ(H*) = 4.84 ppm	66 ^a
110		118-122	82.37 8.85 82.31 8.84	74 ^a
111		185-190	82.61 9.24 82.41 9.43	89
112		69-80	81.60 7.53 81.42 7.57	70 ^a

a) The product may additionally contain minor amounts of other structural isomers in accordance with the substitution at the phenyl ring in 3-position of the benzofuran-2-one.

THIS SHEET HAS BEEN
REPLACED





Table 1: (continuation)

No.	Compound	m.p. (°C)	C (%), H (%), N (%) (calcd/found)	Yield (%)
113		135-145	80.44 7.95 2.08 80.20 8.06 1.96	56 ^{a)}
114		168-170	84.38 7.57 84.23 7.66	25 ^{a)}
115		86-93	C (%), H (%), S (%) 73.13 7.37 9.76 73.10 7.38 9.69	11 ^{a)}
116		220-228	82.60 7.84 82.58 7.85	40

a) The product may additionally contain minor amounts of other structural isomers in accordance with the substitution at the phenyl ring in 3-position of the benzofuran-2-one.

THIS SHEET HAS BEEN
REPLACED


Table 1: (continuation)

No.	Compound	m.p. (°C)	C (%), H (%) (calcd/found)	Yield (%)
117		142-154	81.52 6.84 80.97 6.5	33 ^{a)}
118		186-189	85.27 7.16 85.15 7.20	17 ^{a)}
119		resin	characterised by ¹ H-NMR (CDCl ₃) δ(H*) = 4.82 ppm	31 ^{a)}
120		84-90	81.43 6,57 81.37 6,72	10 ^{a)}

a) The product may additionally contain minor amounts of other structural isomers in accordance with the substitution at the aryl ring in 3-position of the benzofuran-2-one.

THIS SHEET HAS BEEN
REPLACED

Table 1: (continuation)

No.	Compound	m.p. (°C)	C (%), H (%) (calcd/found)	Yield (%)
121		140-153	84.84 7.37 84.66 7.52	17 ^{a)}

a) The product may additionally contain minor amounts of other structural isomers in accordance with the substitution at the fluorene ring in 3-position of the benzofuran-2-one.

THIS SHEET HAS BEEN
REPLACED

Table 2:





No.	Compound	m.p. (°C)	C (%), H (%) (calcd/found)	Yield (%)
201		resin	73.25 8.45 73.33 8.50	100
202		152-160	70.89 7.32 70.40 7.40	82
203		resin	characterised by ¹ H-NMR (CDCl ₃) δ(H*) = 5.33 ppm a) chromatographed on silica gel (CH ₂ Cl ₂ /hexane = 4 : 1)	45 ^a)
204		resin	characterised by ¹ H-NMR (CDCl ₃) δ(H*) = 5.30 ppm	~100

Table 2: (continuation)









No.	Compound	m.p. (°C)	C (%), H (%) (calcd(found))	Yield (%)				
205		resin	characterised by $^1\text{H-NMR}$ (CDCl_3) $\delta(\text{H}^*) = 5.31 \text{ ppm}$	98				
206		resin	<table><tr><td>71.03</td><td>7.95</td></tr><tr><td>71.10</td><td>7.98</td></tr></table>	71.03	7.95	71.10	7.98	92
71.03	7.95							
71.10	7.98							
207		resin	characterised by $^1\text{H-NMR}$ (CDCl_3) $\delta(\text{tert-butyl}) = 1.34 \text{ ppm}$	~100				
208		81-86	characterised by $^1\text{H-NMR}$ (CDCl_3) $\delta(\text{H}^*) = 5.34 \text{ ppm}$	13				

Table 2: (continuation)

No.	Compound	m.p. (°C)	C (%), H (%) (calcd/found)	Yield (%)
209		resin	characterised by ¹ H-NMR (CDCl ₃) δ(H*) = 5.29 ppm	~100
210		resin	characterised by ¹ H-NMR (CDCl ₃) δ(H*) = 5.08 ppm	38
211		100-103	73.88 8.75 73.73 8.75	61
212		138-143	64.97 6.91 65.02 6.89	65

Example 14: Stabilisation of multiple-extruded polypropylene

1.3 kg of polypropylene powder (Profax 6501), which has been prestabilised with 0.025 % of Irganox[®] 1076 (n-octadecyl 3-[3,5-di-tert-butyl-4-hydroxyphenyl]propionate (melt

THIS SHEET HAS BEEN
REPLACED

index 3.2 g/10 min, measured at 230°C/2.16 kg) are blended with 0.05 % of Irganox[®] 1010 (pentaerythritol tetrakis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate], 0.05 % of calcium stearate, 0.03 % of DHT 4A[®] (Kyowa Chemical Industry Co., Ltd., [Mg_{4.5}Al₂(OH)₁₃CO₃•3,5 H₂O]) and 0.05 % of compound of Table 1. This blend is then extruded in an extruder having a cylinder diameter of 20 mm and a length of 400 mm at 100 rpm, the 3 heating zones being adjusted to the following temperatures: 260, 270, 280°C. The extrudate is cooled by drawing it through a water bath and is then granulated. This granulate is repeatedly extruded. After 3 extrusions, the melt index is measured (at 230°C/2.16 kg). A substantial increase in the melt index denotes pronounced chain degradation, i.e. poor stabilisation. The results are shown in Table 3.

Table 3:

Compound of Table 1	Melt index after 3 extrusions
—	17.1
103	4.8
104	5.0
105	4.9
106	4.9

Example 15: Stabilisation of polyethylene during processing

100 parts of polyethylene powder (Lupolen[®] 5260 Z) are blended with 0.05 part of Irganox[®] 1010 (pentaerythritol tetrakis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate]) and 0.05 part of a compound of Table 1 and the blend is kneaded in a Brabender plastograph at 220°C and 50 rpm. During this time the kneading resistance is recorded continuously as torque. In the course of the kneading time the polymer begins to crosslink after prolonged constancy, as can be determined by the rapid increase in torque. The time taken until a marked increase in torque is shown in Table 4 as a measure of the stabilising action. The longer this time is the better the stabilising action.

Table 4:

Compound of Table 1	Time until increase in torque (min)
—	9.5
103	27.0
107	26.0

Example 16: Stabilisation of multiple-extruded polypropylene at high temperature.

1.5 kg of polypropylene powder (Profax 6501), which has been prestabilised with 0.008 % of Irganox[®] 1076 (n-octadecyl 3-[3,5-di-tert-butyl-4-hydroxyphenyl]propionate (melt index 3.2 g/10 min, measured at 230°C/2.16 kg) are blended with 0.05 % of Irganox[®] 1010 (pentaerythritol tetrakis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate), 0.10 % of calcium stearate and 0.015 to 0.100 % of stabiliser or stabiliser mixture according to Table 5. This blend is then extruded in an extruder having a cylinder diameter of 20 mm and a length of 400 mm at 100 rpm, the 3 heating zones being adjusted to the following temperatures: 280, 320, 340°C. The extrudate is cooled by drawing it through a water bath and is then granulated. This granulate is repeatedly extruded. After 5 extrusions, the melt index is measured (at 230°C/2.16 kg). A substantial increase in the melt index denotes pronounced chain degradation, i.e. poor stabilisation. The results are shown in Table 5.

THIS SHEET HAS BEEN
REPLACED

Table 5:


Stabiliser or mixture of stabilisers	Concentration in %by weight	Melt index after 5 extrusions		
		280°C	320°C	340°C
® Irgafos 168 ^{a)}	0.100	9.2	43.7	79.3
® Irgafos P-EPQ ^{b)}	0.050	6.1	23.4	61.0
Example 11 ^{c)}	0.015	8.5	19.7	23.6
® Irgafos 168 ^{a)}	0.045	7.3	24.4	26.7
Example 11 ^{c)}	0.005			
® Irgafos P-EPQ ^{b)}	0.045	5.6	15.7	23.6
Example 11 ^{c)}	0.005			

- a) ® Irgafos 168 is tris(2,4-di-tert-butylphenyl)phosphite.
- b) ® Irgafos P-EPQ is tetrakis(2,4-di-tert-butylphenyl)4,4'-biphenylene diphosphonite.
- c) Example 11 of the present application describes a mixture of c. 85 % of 3-(3,4-dimethylphenyl)-5,7-di-tert-butyl-3H-benzofuran-2-one (compound (103), Table 1) as well as c. 15 % of the 3-(2,3-dimethylphenyl)-5,7-di-tert-butyl-3H-benzofuran-2-one isomer (compound (103A)).

THIS SHEET HAS BEEN
REPLACED


What is claimed is:

1. A compound of formula I



wherein, when n is 1,

R₁ is naphthyl, phenanthryl, anthryl, 5,6,7,8-tetrahydro-2-naphthyl, 5,6,7,8-tetrahydro-1-naphthyl, thienyl, benzo[b]thienyl, naphtho[2,3-b]thienyl, thiathrenyl, dibenzofuryl, chromenyl, xanthenyl, phenoxathiinyl, pyrrolyl, imidazolyl, pyrazolyl, pyrazinyl, pyrimidinyl, pyridazinyl, indoliziny, isoindolyl, indolyl, indazolyl, purinyl, quinoliziny, isoquinolyl, quinolyl, phthalazinyl, naphthyridinyl, quinoxalinyl, quinazolinyl, cinnolinyl, pteridinyl, carbazolyl, β-carbolinyl, phenanthridinyl, acridinyl, perimidinyl, phenanthrolinyl, phenazinyl, isothiazolyl, phenothiazinyl, isoxazolyl, furazanyl, biphenyl, terphenyl, fluorenyl or phenoxazinyl, each unsubstituted or substituted by C₁-C₄alkyl, C₁-C₄alkoxy, C₁-C₄alkylthio, hydroxy, halogen, amino, C₁-C₄alkylamino, phenylamino or di(C₁-C₄alkyl)-amino, or R₁ is a radical of formula II




and


when n is 2,

THIS SHEET HAS BEEN
REPLACED

R_1 is phenylene or naphthylene which is unsubstituted or substituted by C_1 - C_4 alkyl or hydroxy; or is $-R_{12}-X-R_{13}-$,
 R_2, R_3, R_4 and R_5 are each independently of one another hydrogen, chloro, hydroxy, C_1 - C_{25} alkyl, C_7 - C_9 phenylalkyl, unsubstituted or C_1 - C_4 alkyl-substituted phenyl, unsubstituted or C_1 - C_4 alkyl-substituted C_5 - C_8 cycloalkyl; C_1 - C_{18} alkoxy, C_1 - C_{18} alkylthio, C_1 - C_4 alkylamino, di(C_1 - C_4 alkyl)amino, C_1 - C_{25} alkanoyloxy, C_1 - C_{25} alkanoylamino, C_3 - C_{25} alkanoyloxy, C_3 - C_{25} alkanoyloxy which is interrupted by oxygen, sulfur or >N-R_{14} ; C_6 - C_9 -cycloalkylcarbonyloxy, benzoyloxy or C_1 - C_{12} alkyl-substituted benzoyloxy; with the proviso that, when R_2 is hydrogen or methyl, R_7 or R_9 is not hydroxy or C_1 - C_{25} alkanoyloxy; or each pair of substituents R_2 and R_3 or R_3 and R_4 or R_4 and R_5 , together with the linking carbon atoms, forms a benzene ring; R_4 is additionally $-(CH_2)_p-COR_{15}$ or $-(CH_2)_qOH$, or when R_3, R_5 and R_6 are hydrogen, R_4 is additionally a radical of formula III



wherein R_1 is as defined above for $n = 1$,
 R_6 is hydrogen or a radical of formula IV



in which R_4 is not a radical of formula III and R_1 is as defined above for $n = 1$,
 R_7, R_8, R_9 and R_{10} are each independently of one another hydrogen, halogen, hydroxy, C_1 - C_{25} alkyl, C_2 - C_{25} alkyl which is interrupted by oxygen, sulfur or >N-R_{14} ; C_1 - C_{25} -

THIS SHEET HAS BEEN
REPLACED

alkoxy, C₂-C₂₅alkoxy which is interrupted by oxygen, sulfur or $\text{N}-\text{R}_{14}$; C₁-C₂₅alkylthio, C₃-C₂₅alkenyl, C₃-C₂₅alkenyloxy, C₃-C₂₅alkynyl, C₃-C₂₅alkynyloxy, C₇-C₉phenylalkyl, C₇-C₉phenylalkoxy, unsubstituted or C₁-C₄alkyl-substituted phenyl; unsubstituted or C₁-C₄alkyl-substituted phenoxy; unsubstituted or C₁-C₄alkyl-substituted C₅-C₈cycloalkyl; unsubstituted or C₁-C₄alkyl-substituted C₅-C₈cycloalkoxy; C₁-C₄alkylamino, di(C₁-C₄alkyl)amino, C₁-C₂₅alkanoyl, C₃-C₂₅alkanoyl which is interrupted by oxygen, sulfur or $\text{N}-\text{R}_{14}$; C₁-C₂₅alkanoyloxy, C₃-C₂₅alkanoyloxy which is interrupted by oxygen,

sulfur or $\text{N}-\text{R}_{14}$; C₁-C₂₅alkanoylamino, C₃-C₂₅alkenoyl, C₃-C₂₅alkenoyl which is interrupted by oxygen, sulfur or $\text{N}-\text{R}_{14}$; C₃-C₂₅alkenoyloxy, C₃-C₂₅alkenoyloxy

which is interrupted by oxygen, sulfur or $\text{N}-\text{R}_{14}$; C₆-C₉cycloalkylcarbonyl, C₆-C₉cycloalkylcarbonyloxy, benzoyl or C₁-C₁₂alkyl-substituted benzoyl; benzoyloxy or

C₁-C₁₂alkyl-substituted benzoyloxy; $\text{—O—}\overset{\text{R}_{18}}{\underset{\text{R}_{19}}{\text{C}}}\text{—}\overset{\text{O}}{\underset{\text{||}}{\text{C}}}\text{—R}_{15}$ or $\text{—O—}\overset{\text{R}_{20}}{\underset{\text{H}}{\text{C}}}\text{—}\overset{\text{R}_{21}}{\underset{\text{R}_{22}}{\text{C}}}\text{—O—R}_{23}$,

or also in formula II each pair of substituents R₇ and R₈ or R₈ and R₁₁, together with the linking carbon atoms, forms a benzene ring,

R₁₁ is hydrogen, C₁-C₂₅alkyl, C₁-C₂₅alkylthio, C₃-C₂₅alkenyl, C₃-C₂₅alkynyl, C₇-C₉phenylalkyl, unsubstituted or C₁-C₄alkyl-substituted phenyl; unsubstituted or C₁-C₄alkyl-substituted C₅-C₈cycloalkyl; C₁-C₄alkylamino, di(C₁-C₄alkyl)amino, C₁-C₂₅alkanoyl,

C₃-C₂₅alkanoyl which is interrupted by oxygen, sulfur or $\text{N}-\text{R}_{14}$; C₁-C₂₅alkanoylamino, C₃-C₂₅alkenoyl, C₃-C₂₅alkenoyl which is interrupted by oxygen, sulfur or

$\text{N}-\text{R}_{14}$; C₆-C₉cycloalkylcarbonyl, benzoyl or C₁-C₁₂alkyl-substituted benzoyl; with

the proviso that at least one of R₇, R₈, R₉, R₁₀ or R₁₁ is not hydrogen,

R₁₂ and R₁₃ are each independently of the other unsubstituted or C₁-C₄alkyl-substituted phenylene or naphthylene,

R₁₄ is hydrogen or C₁-C₈alkyl,

R₁₅ is hydroxy, $[-\text{O}^{\ominus} \frac{1}{r} \text{M}^{r+}]$, C₁-C₁₈alkoxy or $-\text{N}(\text{R}_{24})(\text{R}_{25})$,

R₁₆ and R₁₇ are each independently of the other hydrogen, CF₃, C₁-C₁₂alkyl or phenyl, or R₁₆ and R₁₇, together with the linking carbon atom, form a C₅-C₈cycloalkylidene ring

which is unsubstituted or substituted by 1 to 3 C₁-C₄alkyl groups;

R₁₈ and R₁₉ are each independently of the other hydrogen, C₁-C₄alkyl or phenyl,

R₂₀ is hydrogen or C₁-C₄alkyl,




R₂₁ is hydrogen, unsubstituted or C₁-C₄alkyl-substituted phenyl; C₁-C₂₅alkyl, C₂-C₂₅alkyl

which is interrupted by oxygen, sulfur or $\text{N}-\text{R}_{14}$; C₇-C₉phenylalkyl which is unsubstituted or substituted in the phenyl moiety by 1 to 3 C₁-C₄alkyl groups; C₇-C₂₅phenylalkyl

which is interrupted by oxygen, sulfur or $\text{N}-\text{R}_{14}$ and which is unsubstituted or substituted in the phenyl moiety by 1 to 3 C₁-C₄alkyl groups; or R₂₀ and R₂₁, together with the linking carbon atoms, form a C₅-C₁₂cycloalkylene ring which is unsubstituted or substituted by 1 to 3 C₁-C₄alkyl groups;

R₂₂ is hydrogen or C₁-C₄alkyl,

R₂₃ is hydrogen, C₁-C₂₅alkanoyl, C₃-C₂₅alkenoyl, C₃-C₂₅alkanoyl which is interrupted by oxygen, sulfur or $\text{N}-\text{R}_{14}$; C₂-C₂₅alkanoyl which is substituted by a di(C₁-C₆alkyl)-phosphonate group; C₆-C₉cycloalkylcarbonyl, thenoyl, furoyl, benzoyl or C₁-C₁₂alkyl-





R₂₄ and R₂₅ are each independently of the other hydrogen or C₁-C₁₈alkyl,

R₂₆ is hydrogen or C₁-C₈alkyl,


R₂₇ is a direct bond, C₁-C₁₈alkylene, C₂-C₁₈alkylene which is interrupted by oxygen,

sulfur or $\text{N}-\text{R}_{14}$; C₂-C₁₈alkenylene, C₂-C₂₀alkylidene, C₇-C₂₀phenylalkylidene,

C₅-C₈cycloalkylene, C₇-C₈bicycloalkylene, unsubstituted or C₁-C₄alkyl-substituted

phenylene,  or ,

R₂₈ is hydroxy, $\left[-O^{\ominus} \frac{1}{r} M^{r+} \right]$, C₁-C₁₈alkoxy or $-N \begin{matrix} R_{24} \\ R_{25} \end{matrix}$,

R₂₉ is oxygen, -NH- or  -NH-R₃₀,

R₃₀ is C₁-C₁₈alkyl or phenyl,

R₃₁ is hydrogen or C₁-C₁₈alkyl,

M is a metal cation of valency r,

X is a direct bond, oxygen, sulfur or -NR₃₁-,

n is 1 or 2,

p 0, 1 or 2,

q is 1, 2, 3, 4, 5 or 6,

r is 1, 2 or 3, and

s is 0, 1 or 2.

2. A compound according to claim 1, wherein, when n is 2,

R₁ is -R₁₂-X-R₁₃-,


R₁₂ and R₁₃ are phenylene,

X is oxygen or -NR₃₁-, and

R₃₁ is C₁-C₄alkyl.

3. A compound according to claim 1, wherein, when n is 1,

R₁ is naphthyl, phenanthryl, thienyl, dibenzofuryl, carbazolyl, fluorenyl, each unsubstituted or substituted by C₁-C₄alkyl, C₁-C₄alkoxy, C₁-C₄alkylthio, hydroxy, halogen, amino, C₁-C₄alkylamino or di(C₁-C₄-alkyl)amino, or is a radical of formula II



THIS SHEET HAS BEEN
REPLACED

R₇, R₈, R₉ und R₁₀ are each independently of one another hydrogen, chloro, bromo, hydroxy, C₁-C₁₈alkyl, C₂-C₁₈alkyl which is interrupted by oxygen or sulfur; C₁-C₁₈alkoxy, C₂-C₁₈alkoxy which is interrupted by oxygen or sulfur; C₁-C₁₈alkylthio, C₃-C₁₂alkenyloxy, C₃-C₁₂alkynyloxy, C₇-C₉phenylalkyl, C₇-C₉phenylalkoxy, unsubstituted or C₁-C₄alkyl-substituted phenyl; phenoxy, cyclohexyl, C₅-C₈cycloalkoxy; C₁-C₄alkyl-amino, di(C₁-C₄alkyl)amino, C₁-C₁₂alkanoyl, C₃-C₁₂alkanoyl which is interrupted by oxygen or sulfur; C₁-C₁₂alkanoyloxy, C₃-C₁₂alkanoyloxy which is interrupted by oxygen or sulfur; C₁-C₁₂alkanoylamino, C₃-C₁₂alkenoyl, C₃-C₁₂alkenoyloxy, cyclohexylcarbonyl, cyclohexylcarbonyloxy, benzoyl or C₁-C₄alkyl-substituted benzoyl; benzoyloxy or C₁-C₄-

alkyl substituted benzoyloxy; $\text{---O---}\overset{\overset{\text{R}_{18}}{\text{|}}}{\underset{\underset{\text{R}_{19}}{\text{|}}}{\text{C}}}\text{---}\overset{\overset{\text{O}}{\text{||}}}{\text{C}}\text{---R}_{15}$ or $\text{---O---}\overset{\overset{\text{R}_{20}}{\text{|}}}{\underset{\underset{\text{H}}{\text{|}}}{\text{C}}}\text{---}\overset{\overset{\text{R}_{21}}{\text{|}}}{\underset{\underset{\text{R}_{22}}{\text{|}}}{\text{C}}}\text{---O---R}_{23}$, or in

formula II each pair of substituents R₇ and R₈ or R₈ and R₁₁, together with the linking carbon atoms, forms a benzene ring,

R₁₁ is hydrogen, C₁-C₁₈alkyl, C₁-C₁₈alkylthio, C₇-C₉phenylalkyl, unsubstituted or C₁-C₄alkyl-substituted phenyl; cyclohexyl, C₁-C₄alkylamino, di(C₁-C₄alkyl)amino, C₁-C₁₂alkanoyl, C₃-C₁₂alkanoyl which is interrupted by oxygen or sulfur; C₁-C₁₂alkanoylamino, C₃-C₁₂alkenoyl, cyclohexylcarbonyl, benzoyl or C₁-C₄alkyl-substituted benzoyl; with the proviso that at least one of R₇, R₈, R₉, R₁₀ or R₁₁ is not hydrogen;

R₁₅ is hydroxy, C₁-C₁₂alkoxy or $\text{---N---}\overset{\overset{\text{R}_{24}}{\text{|}}}{\underset{\underset{\text{R}_{25}}{\text{|}}}{\text{C}}}$,

R₁₈ and R₁₉ are each independently of the other hydrogen or C₁-C₄alkyl,


R₂₀ is hydrogen,

R₂₁ is hydrogen, phenyl, C₁-C₁₈alkyl, C₂-C₁₈alkyl which is interrupted by oxygen or sulfur, C₇-C₉phenylalkyl, C₇-C₁₈phenylalkyl which is interrupted by oxygen or sulfur and which is unsubstituted or substituted in the phenyl moiety by 1 to 3 C₁-C₄alkyl groups, and R₁₉ and R₂₀, together with the linking carbon atoms, form a cyclohexylene ring which is unsubstituted or substituted by 1 to 3 C₁-C₄alkyl groups,

R₂₂ is hydrogen or C₁-C₄alkyl,

R₂₃ is hydrogen, C₁-C₁₈alkanoyl, C₃-C₁₂alkenoyl, C₃-C₁₂alkanoyl which is interrupted by oxygen or sulfur; C₂-C₁₂alkanoyl which is substituted by a di(C₁-C₆alkyl)phosphonate

THIS SHEET HAS BEEN REPLACED



R₂₄ and R₂₅ are each independently of the other hydrogen or C₁-C₁₂alkyl,

R₂₆ is hydrogen or C₁-C₄alkyl,

R₂₇ is C₁-C₁₂alkylene, C₂-C₈alkenylene, C₂-C₈alkylidene, C₇-C₁₂phenylalkylidene, C₅-C₈cycloalkylene or phenylene,

R₂₈ is hydroxy, C₁-C₁₂alkoxy or $\text{---}\text{N}\begin{matrix} \text{R}_{24} \\ \text{R}_{25} \end{matrix}$,


R₂₉ is oxygen or -NH-,

R₃₀ is C₁-C₁₈alkyl or phenyl, and

s is 1 or 2.

4. A compound according to claim 1, wherein, when n is 1,

R₁ is phenanthryl, thienyl, dibenzofuryl, unsubstituted or C₁-C₄alkyl-substituted carbazoyl; or fluorenyl, or R₁ is a radical of formula II



THIS SHEET HAS BEEN
REPLACED

R₇, R₈, R₉ und R₁₀ are each independently of one another hydrogen, chloro, hydroxy, C₁-C₁₈alkyl, C₁-C₁₈alkoxy, C₁-C₁₈alkylthio, C₃-C₄alkenyloxy, C₃-C₄-alkynyloxy, phenyl,

benzoyl, benzoyloxy or
$$\text{---O---}\overset{\overset{\text{R}_{20}}{|}}{\underset{\underset{\text{H}}{|}}{\text{C}}}\text{---}\overset{\overset{\text{R}_{21}}{|}}{\underset{\underset{\text{R}_{22}}{|}}{\text{C}}}\text{---O---R}_{23},$$

R₁₁ is hydrogen, C₁-C₁₈alkyl, C₁-C₁₈alkylthio, phenyl or cyclohexyl; with the proviso that at least one of R₇, R₈, R₉, R₁₀ or R₁₁ is not hydrogen,

R₂₀ is hydrogen,

R₂₁ is hydrogen, phenyl or C₁-C₁₈alkyl, or R₂₀ and R₂₁, together with the linking carbon atoms, form a cyclohexylene ring which is unsubstituted or substituted by 1 to 3 C₁-C₄-alkyl groups,

R₂₂ is hydrogen or C₁-C₄alkyl, and

R₂₃ is hydrogen, C₁-C₁₂alkanoyl or benzoyl.

5. A compound according to claim 4, wherein, when n is 1,

R₇, R₈, R₉ and R₁₀ are each independently of one another hydrogen or C₁-C₄alkyl, and R₁₁ is hydrogen, C₁-C₁₂alkyl, C₁-C₄alkylthio or phenyl; with the proviso that at least one of R₇, R₈, R₉, R₁₀ or R₁₁ is not hydrogen.

6. A compound according to claim 1, wherein

R₂, R₃, R₄ and R₅ are each independently of one another hydrogen, chloro, C₁-C₁₈alkyl, benzyl, phenyl, C₅-C₈cycloalkyl, C₁-C₁₈alkoxy, C₁-C₁₈alkylthio, C₁-C₁₈alkanoyloxy, C₁-C₁₈alkanoylamino, C₃-C₁₈alkenyloxy or benzoyloxy; with the proviso that, when R₂ is hydrogen or methyl, R₇ or R₉ is not hydroxy or C₁-C₂₅alkanoyloxy; or each pair of substituents R₂ and R₃ or R₃ and R₄ or R₄ and R₅, together with the linking carbon atoms, forms a benzene ring, R₄ is additionally -(CH₂)_p-COR₁₅ or -(CH₂)_qOH or, if R₃, R₅ and R₆ are hydrogen, R₄ is additionally a radical of formula III,

R₁₅ is hydroxy, C₁-C₁₂alkoxy or
$$\text{---N}\overset{\overset{\text{R}_{24}}{|}}{\underset{\underset{\text{R}_{25}}{|}}{}} ,$$

R₁₆ and R₁₇ are methyl groups or, together with the linking carbon atom, form a C₅-C₈-cycloalkylidene ring which is unsubstituted or substituted by 1 to 3 C₁-C₄alkyl groups,

R₂₄ and R₂₅ are each independently of the other hydrogen or C₁-C₁₂alkyl,

p is 1 or 2, and

q is 2, 3, 4, 5 or 6.

THIS SHEET HAS BEEN
REPLACED

7. A compound according to claim 1, wherein at least two of R_2 , R_3 , R_4 and R_5 are hydrogen.
8. A compound according to claim 1, wherein R_3 and R_5 are hydrogen.
9. A compound according to claim 1, wherein
 R_2 is C_1 - C_4 alkyl,
 R_3 is hydrogen,
 R_4 is C_1 - C_4 alkyl or, if R_6 is hydrogen, R_4 is additionally a radical of formula III,
 R_5 is hydrogen, and
 R_{16} and R_{17} , together with the linking carbon atom, form a cyclohexylidene ring.
10. A composition comprising
- a) an organic material which is susceptible to oxidative, thermal or light-induced degradation, and
 - b) at least one compound of formula I according to claim 1.
11. A composition according to claim 10, wherein component (a) is selected from the group consisting of a lubricant, a hydraulic fluid, a metal processing fluid and a natural, semisynthetic or synthetic polymer.
12. A composition according to claim 10, wherein component (a) is a lubricant of the series of the mineral oils, the synthetic oils or a mixture thereof.
13. A composition according to claim 10, wherein component (a) is a synthetic polymer.
14. A composition according to claim 10, wherein component (a) is a polyolefin.
15. A composition according to claim 10, wherein component (a) is polyethylene or polypropylene.
16. A composition according to claim 10, which contains component (b) in an amount of 0.0005 to 5 % by weight, based on the weight of component a).
17. A composition according to claim 10, which comprises further additives in addition to components (a) and (b).

THIS SHEET HAS BEEN REPLACED

18. A composition according to claim 17, which comprises as further additives phenolic antioxidants, light stabilisers and/or processing stabilisers.
19. A composition according to claim 18, which comprises as further additive at least one compound of the organic phosphite or phosphonite type.
20. Use of a compound of formula I as defined in claim 1 for stabilising organic materials against oxidative, thermal or light-induced degradation.
21. A process for stabilising an organic material against oxidative, thermal or light-induced degradation, which comprises incorporating therein or applying thereto at least one compound of formula I as defined in claim 1.

THIS SHEET HAS BEEN
REPLACED