

Product containing epichlorohydrin, its preparation and its use in various applications

The present patent application claims the benefit of the United States Provisional patent application USP 61/007,661 filed on 14 December 2007, of the French Patent applications FR 07/55696 filed on 12 June 2007, FR 07/57751 filed on 21 September 2007, and of the United States Provisional Patent
5 Application USP 61/013672 filed on 14 December 2007, the content of all of which is incorporated here by reference.

The present invention relates to an epichlorohydrin-based product, to a process for its preparation and to the use of the product in various applications.

Epichlorohydrin is a reaction intermediate in the manufacture of various
10 products like for instance epoxy resins, synthetic elastomers, glycidyl ethers, polyamide resins, etc. (Ullmann's Encyclopedia of Industrial Chemistry, Fifth Edition, Vol. A9, p.539).

Epichlorohydrin can be obtained by several routes, like for instance, epoxidation of allyl chloride with hydrogen peroxide or dehydrochlorination of
15 dichloropropanol.

The dichloropropanol route presents the advantage that dichloropropanol can be obtained by hydrochlorination of glycerol. This glycerol can be obtained from fossil raw materials or from renewable raw materials, e.g., from fats or oils of animal or plant origin by transesterification processes.

20 In some cases the epichlorohydrin thus obtained is contaminated with impurities which render them unsuitable for certain applications.

The goal of the invention is to solve those problems by providing a new product containing epichlorohydrin suitable in all known applications.

The invention therefore relates in a first embodiment to a product
25 containing epichlorohydrin and at least one alkyl glycidyl ether in an amount of less than 0.1 g/kg of product.

One of the essential characteristics of the present invention resides in the identification of unwanted impurities. Glycidyl alkyl ethers have indeed been identified as unwanted impurities. They are very difficult to separate from
30 epichlorohydrin because of similar boiling points. The presence of glycidyl alkyl ethers in epichlorohydrin may prove troublesome in some of these

applications for various reasons. Glycidyl ethers are suspected to have reproductive toxicity, immunotoxicity and toxicity to the skin. Glycidyl methyl ether is also suspected to be mutagenic. Those ethers can interfere in the synthesis processes as the molecules could be inserted for example in a polymeric chain through the opening of the epoxide ring. They can remain in the final products and possibly degrade with a concomitant deterioration of the properties of the final products. They can exhibit or degrade in compounds exhibiting some toxicity leading to safety issues especially when the final products are intended to be in contact with food and drink. Moreover, they can accumulate in and contaminate industrial waters such as wastewaters for instance or water containing pulp that is recycled in the pulp and paper industry. In the latter case, their higher concentration can increase contamination of the paper made using the recycled water.

The content of alkyl glycidyl ether, in the product of the invention is preferably lower than or equal to 0.08 g/kg, more preferably lower than or equal to 0.06 g/kg, still more preferably lower than or equal to 0.04 g/kg, yet preferably lower than or equal to 0.020 g/kg, most preferably lower than or equal to 0.01 g/kg and particularly most preferably lower than or equal to 0.005 g/kg. This content is usually higher than or equal to 0.0005 g/kg.

The product according to the invention has an epichlorohydrin content which is generally higher than or equal to 900 g/kg of product, preferably higher than or equal to 950 g/kg, more preferably higher than or equal to 990 g/kg, yet more preferably higher than or equal to 999 g/kg and most preferably higher than 999.5 g/kg.

The alkyl group of the alkyl glycidyl ether can be a linear or branched or alicyclic aliphatic alkyl group and is preferably a linear or branched aliphatic group.

The alkyl group of the alkyl glycidyl ether contains a number of carbon atoms which is generally higher than or equal to 1, often higher than or equal to 2 and frequently higher than or equal to 3. That number of carbon atoms is generally lower than or equal to 10, often lower than or equal to 8 and frequently lower than or equal to 6.

The alkyl group is preferably selected from the methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl and octyl groups and more preferably from the methyl, ethyl, propyl and butyl groups and particularly preferably from the methyl and ethyl groups. Very particularly preferably, the alkyl group is a methyl group. The

propyl group can be chosen from the n-propyl and isopropyl groups and is preferably an isopropyl group. The butyl group can be chosen from the 1-butyl, 2-butyl, isobutyl and tert-butyl groups, preferably from the isobutyl and tert-butyl groups.

5 The product according to the invention may contain in addition to alkyl glycidyl ether and epichlorohydrin, at least one halogenated hydrocarbon. The halogenated hydrocarbon may be an aliphatic or an aromatic halogenated hydrocarbon, optionally containing oxygen. It is often an aliphatic halogenated hydrocarbon and frequently an aromatic hydrocarbon.

10 The content of the halogenated hydrocarbon in the product is usually of less than 1 g/kg of product, preferably less than or equal to 0.8 g/kg of product, preferably less than or equal to 0.6 g/kg, more preferably less than or equal to 0.5 g/kg, yet more preferably less than or equal to 0.4 g/kg, still more preferably less than or equal to 0.2 g/kg, most preferably less than or equal to 0.1 g/kg, yet
15 most preferably less than or equal to 0.05 g/kg, still most preferably less than or equal to 0.01 g/kg, and most particularly preferably less than or equal to 0.001 g/kg. This content is generally greater than or equal to 0.001 mg/kg.

 That halogenated hydrocarbon can be chosen from chloropropene, trichloropropene, trichloropropane, chloropropanol, chloropropenol,
20 dichloropropene, dichloropropane, dichloropropanol, monochloropropanediol, chloroethers, monochlorobenzene, and any mixture of at least two of them.

 The halogenated hydrocarbon can be chosen from aliphatic halogenated hydrocarbons such as

- chloropropene, often 2-chloro-1-propene, frequently 1-chloro-1-propene cis,
25 usually 1-chloro-1-propene trans and specifically 3-chloro-1-propene, and any mixture of at least two of them
- chloropropane, often 2-chloropropane, frequently 1-chloropropane, and any mixture of at least two of them
- chloromethane, often dichloromethane, frequently trichloromethane, usually
30 tetrachloromethane and any mixture of at least two of them
- dichloroethane, often 1,2-dichloroethane,
- chloroethanol, often 2-chloroethanol,
- trichloropropene, often 1,3,3-trichloro-1-propene-cis, frequently 1,3,3-
trichloro-1-propene-trans, usually 1,2,3-trichloropropene-cis (?), specifically
35 1,2,3-trichloropropene-trans and any mixture of at least two of them

- trichloropropane, often 1,2,3-trichloropropane, frequently 1,1,1-trichloropropane, usually 1,1,3-trichloropropane, commonly 1,1,2-trichloropropane and any mixtures of at least two of them.
 - chloropropanol, often 3-chloro-1-propanol,
 - 5 ▪ chloropropenol, often 2-chloro-2-propen-1-ol, frequently 3-chloro-2-propene-1-ol *cis* and specifically 3-chloro-2-propene-1-ol *trans*, and any mixture of at least two of them
 - dichloropropene, often *cis*-1,3-dichloropropene, frequently *trans*-1,3-dichloropropene, usually 3,3-dichloro-1-propene, frequently 2,3-dichloro-1-propene, usually 1,3-dichloro-1-propene-*cis*, specifically 1,3-dichloro-1-propene-*trans*, and any mixture of at least two of them,
 - 10 ▪ dichloropropane, preferably 1,3-dichloropropane, 1,2-dichloropropane, 2,2-dichloropropane, and any mixture of at least two of them
 - dichloropropanol, often 1,3-dichloropropan-2-ol, 2,3-dichloropropan-1-ol, and mixtures thereof,
 - 15 ▪ monochloropropanediol, often 3-chloro-1,2-propanediol, frequently 2-chloro-1,3-propanediol, and mixtures thereof, and
 - chloroethers, preferably chosen from chloroethers of crude formula:
 $C_6H_{10}Cl_2O_2$, $C_6H_{12}Cl_2O$, $C_6H_9Cl_3O_2$, $C_6H_{11}Cl_3O_2$, and mixtures of at least two of them,
 - 20 ▪ compounds of crude formula $C_4H_7ClO_2$, $C_6H_9Cl_3$, $C_6H_9Cl_3O_2$, $C_9H_{17}Cl_3O_4$, $C_9H_{15}Cl_5O$, $C_3H_3Cl_3$, and mixtures of at least two of them
 - dichloroepoxypropane,
and any mixture of at least two of them.
- 25 Aromatic halogenated hydrocarbons comprise at least one ring of aromatic nature and a halogen atom. The halogen atom is preferably directly attached to the aromatic ring. The halogen may be chosen from fluorine, chlorine, bromine, iodine and mixtures thereof. Chlorine is preferred. The aromatic ring may be mononuclear or polynuclear, and is preferably mononuclear. The aromatic
- 30 halogenated hydrocarbons may be chosen from mono-, di-, tri-, tetra-, penta- and hexachloro- benzenes and/or naphthalenes. Monochlorobenzene is particularly preferred.
- Without wishing to be tied to one theoretical explanation, it is believed that monochlorobenzene may come from the process for manufacturing
- 35 epichlorohydrin, in particular when this is obtained by dehydrochlorination of dichloropropanol. More specifically, it is believed that monochlorobenzene may

be present in the dichloropropanol, in particular when this is obtained by a process for chlorinating glycerol using a chlorinating agent containing hydrogen chloride. More specifically still, it is believed that chlorobenzene may be present in the hydrogen chloride, in particular when this comes from another manufacturing process, such as the manufacture of isocyanates, diisocyanates or polyisocyanates, such as for example 4,4-methylenediphenyl diisocyanate (MDI) or toluene diisocyanate (TDI) or hexamethylene-1,6-diisocyanate (HDI).

The product according to the invention can contain chloropropene, in a content usually less than or equal to 0.8 g/kg of product, often less than or equal to 0.6 g/kg, frequently less than or equal to 0.5 g/kg, more often less than or equal to 0.4 g/kg, more frequently less than or equal to 0.2 g/kg, yet more often less than or equal to 0.1 g/kg, yet more frequently less than or equal to 0.05 g/kg, still more often less than or equal to 0.01 g/kg, and in particular less than or equal to 0.001 g/kg. That content is usually of at least 0.001 mg/kg. The chloropropene may be selected from 2-chloro-1-propene, 1-chloro-1-propene cis, 1-chloro-1-propene trans, 3-chloro-1-propene, and any mixture of at least two of them.

The product according to the invention can contain trichloropropane, in a content usually less than or equal to 0.8 g/kg of product, often less than or equal to 0.6 g/kg, frequently less than or equal to 0.5 g/kg, more often less than or equal to 0.4 g/kg, more frequently less than or equal to 0.2 g/kg, yet more often less than or equal to 0.1 g/kg, yet more frequently less than or equal to 0.05 g/kg, still more often less than or equal to 0.01 g/kg, and in particular less than or equal to 0.001 g/kg, in an amount of commonly less than or equal to 0.008 g/kg of product, more commonly of less than or equal to 0.006 g/kg, yet more often of less than or equal to 0.004 g/kg, still more often of less than or equal to 0.002 g/kg, most frequently of less than or equal to 0.001 g/kg, yet most frequently of less than or equal to 0.0005 g/kg. That content is usually of at least 0.001 mg/kg.

The product according to the invention can contain trichloropropene, in an amount a content usually less than or equal to 0.8 g/kg of product, often less than or equal to 0.6 g/kg, frequently less than or equal to 0.5 g/kg, more often less than or equal to 0.4 g/kg, more frequently less than or equal to 0.2 g/kg, yet more often less than or equal to 0.1 g/kg, yet more frequently less than or equal to 0.05 g/kg, still more often less than or equal to 0.01 g/kg, and in particular less than or equal to 0.001 g/kg. That content is usually of at least 0.001 mg/kg.

This content is at least 0.001 g/kg. The trichloropropene may be selected from 1,3,3-trichloro-1-propene-cis, 1,3,3-trichloro-1-propene-trans, 1,2,3-trichloropropene-cis, specifically 1,2,3-trichloropropene-trans and any mixtures of at least two of them.

5 The product according to the invention can contain chloropropenol, in a content a content usually less than or equal to 0.8 g/kg of product, often less than or equal to 0.6 g/kg, frequently less than or equal to 0.5 g/kg, more often less than or equal to 0.4 g/kg, more frequently less than or equal to 0.2 g/kg, yet more often less than or equal to 0.1 g/kg, yet more frequently less than or equal to
10 0.05 g/kg, still more often less than than or equal to 0.01 g/kg, and in particular less than or equal to 0.001 g/kg. That content is usually of at least 0.001 mg/kg. The chloropropenol may be selected from 2-chloro-2-propen-1-ol, 3-chloro-2-propene-1-ol cis, 3-chloro-2-propene-1-ol trans and any mixtures of at least two of them.

15 The product according to the invention may contain dichloropropene, in a content a content usually less than or equal to 0.8 g/kg of product, often less than or equal to 0.6 g/kg, frequently less than or equal to 0.5 g/kg, more often less than or equal to 0.4 g/kg, more frequently less than or equal to 0.2 g/kg, yet more often less than or equal to 0.1 g/kg, yet more frequently less than or equal to
20 0.05 g/kg, still more often less than than or equal to 0.01 g/kg, and in particular less than or equal to 0.001 g/kg. That content is usually of at least 0.001 mg/kg.. The dichloropropene may be selected from 3,3-dichloro-1-propene, 2,3-dichloro-1-propene, 1,3-dichloro-1-propene-cis, 1,3-dichloro-1-propene-trans, and any mixtures of at least two of them.

25 The product according to the invention can contain dichloropropane, in a content usually less than or equal to 0.8 g/kg of product, often less than or equal to 0.6 g/kg, frequently less than or equal to 0.5 g/kg, more often less than or equal to 0.4 g/kg, more frequently less than or equal to 0.2 g/kg, yet more often less than or equal to 0.2 g/kg, yet more frequently less than or equal to 0.05 g/kg, still
30 more often less than than or equal to 0.01 g/kg, and in particular less than or equal to 0.001 g/kg. That content is usually of at least 0.001 mg/kg... The dichloropropane may be selected from 1,3-dichloropropane, 1,2-dichloropropane, 2,2-dichloropropane, and any mixture of at least two of them.

 The product according to the invention can contain dichloropropanol, in a
35 content usually less than or equal to 0.8 g/kg of product, often less than or equal to 0.6 g/kg, frequently less than or equal to 0.5 g/kg, more often less than or equal

to 0.4 g/kg, more frequently less than or equal to 0.2 g/kg, yet more often less than or equal to 0.1 g/kg, yet more frequently less than or equal to 0.05 g/kg, still more often less than or equal to 0.01 g/kg, and in particular less than or equal to 0.001 g/kg. That content is usually of at least 0.001 mg/kg. The
5 dichloropropanol may be selected from 1,3-dichloropropan-2-ol, 2,3-dichloropropan-1-ol and any mixtures thereof.

The product according to the invention can contain monochloropropanediol, in a content usually less than or equal to 0.8 g/kg of product, often less than or equal to 0.6 g/kg, frequently less than or equal to
10 0.5 g/kg, more often less than or equal to 0.4 g/kg, more frequently less than or equal to 0.2 g/kg, yet more often less than or equal to 0.1 g/kg, yet more frequently less than or equal to 0.05 g/kg, still more often less than or equal to 0.01 g/kg, and in particular less than or equal to 0.001 g/kg. That content is usually of at least 0.001 mg/kg. The monochloropropanediol may be selected
15 from 3-chloro-1,2-propanediol, 2-chloro-1,3-propanediol and any mixtures thereof.

The product according to the invention usually can contain chloroethers in a content usually less than or equal to 0.8 g/kg of product, often less than or equal to 0.6 g/kg, frequently less than or equal to 0.5 g/kg, more often less than or
20 equal to 0.4 g/kg, more frequently less than or equal to 0.2 g/kg, yet more often less than or equal to 0.1 g/kg, yet more frequently less than or equal to 0.05 g/kg, still more often less than or equal to 0.01 g/kg, and in particular less than or equal to 0.001 g/kg. That content is usually of at least 0.001 mg/kg.. The chloroethers may be selected from chloroethers of crude formula $C_6H_{10}Cl_2O_2$,
25 $C_6H_{12}Cl_2O$, $C_6H_9Cl_3O_2$, $C_6H_{11}Cl_3O_2$, and any mixtures thereof.

The product according to the invention usually contains chlorobenzene, often monochlorobenzene, in an amount in a content usually less than or equal to 0.8 g/kg of product, often less than or equal to 0.6 g/kg, frequently less than or
30 equal to 0.5 g/kg, more often less than or equal to 0.4 g/kg, more frequently less than or equal to 0.2 g/kg, yet more often less than or equal to 0.1 g/kg, yet more frequently less than or equal to 0.05 g/kg, still more often less than or equal to 0.01 g/kg, and in particular less than or equal to 0.001 g/kg. That content is usually of at least 0.001 mg/kg.

The product according to the invention may also contain in addition to
35 epichlorohydrin, alkyl glycidyl ethers and halogenated hydrocarbons, compounds such as for example :

- aldehydes, like acetaldehyde, acrolein, isobutanal, isopentanal, and any mixture of at least two of them,
- ketones, like acetone, chloroacetone, cyclopentanone, 2-butanone, cyclohexanone, 2-methyl-2-cyclopentene-1-one, 3,5-dimethyl-2-cyclohexene-1-one ketone of crude formula $C_5H_{10}O$, $C_6H_{12}O$, and any mixture of at least two of them,
- aliphatic alcohols, like isopropanol, allyl alcohol, glycerol, and any mixture of at least two of them,
- aromatic alcohols like phenol,
- hydroxyketones like hydroxyacetone,
- epoxides different from epichlorohydrin, like propylene oxide, 1,2-epoxyhexane, glycidol, and any mixture of at least two of them
- hydrocarbons like methylcyclopentane, ethylbenzene, and any mixture of at least two of them
- compounds of crude formula $C_6H_{10}O$, $C_7H_{10}O$, $C_7H_{14}O_2$, $C_6H_8O_2$, $C_9H_{10}O_2$, and any mixture of at least two of them.

The product according to the invention can contain at least one aldehyde, in a content usually less than or equal to 0.8 g/kg of product, often less than or equal to 0.6 g/kg, frequently less than or equal to 0.5 g/kg, more often less than or equal to 0.4 g/kg, more frequently less than or equal to 0.2 g/kg, yet more often less than or equal to 0.1 g/kg, yet more frequently less than or equal to 0.05 g/kg, still more often less than or equal to 0.01 g/kg, and in particular less than or equal to 0.001 g/kg. That content is usually of at least 0.001 mg/kg. The aldehyde may be selected from acetaldehyde, acrolein, isobutanal, isopentanal and any mixtures of at least two of them.

The product according to the invention usually can contain acrolein in an amount usually of less than 0.07 g/kg of product, preferably at most 0.01 g/kg and more preferably at most 0.005 g/kg. This content is at least 0.001 g/kg.

The product according to the invention can contain ketones, in a content usually less than or equal to 0.8 g/kg of product, often less than or equal to 0.6 g/kg, frequently less than or equal to 0.5 g/kg, more often less than or equal to 0.4 g/kg, more frequently less than or equal to 0.2 g/kg, yet more often less than or equal to 0.1 g/kg, yet more frequently less than or equal to 0.05 g/kg, still more often less than or equal to 0.01 g/kg, and in particular less than or equal to 0.001 g/kg. That content is usually of at least 0.001 mg/kg.. The ketones may be selected from acetone, chloroacetone, 2-butanone, cyclopentanone,

cyclohexanone, 2-methyl-2-cyclopentene-1-one, 3,5-dimethyl-2-cyclohexene-1-one, ketones of crude formula $C_5H_{10}O$, $C_6H_{12}O$, and any mixtures of at least two of them.

The product according to the invention can contain cyclopentanone in an amount usually higher than or equal to 0.001 mg/kg, often higher than or equal to 0.01 mg/kg, frequently higher than or equal to 0.1 mg/kg and in particular higher than or equal to 0.001 g/kg. That content is usually lower than or equal to 0.5 g/kg, often lower than or equal to 0.3 g/kg, frequently lower than or equal to 0.1 g/kg, more often lower than or equal to 0.05 g/kg, more frequently lower than or equal to 0.01 g/kg and particularly lower than or equal to 0.005 g/kg. That content is usually higher than or equal to 0.001 mg/kg, often higher than or equal to 0.01 mg/kg, frequently higher than or equal to 0.1 mg/kg, more often higher than or equal to 0.5 mg/kg and in particular higher than or equal to 1 mg/kg

The product according to the invention can contain chloroacetone in an amount usually of less than 0.05 g/kg of product, preferably at most 0.03 g/kg and more preferably at most 0.01 g/kg. This content is at least 0.001 g/kg

The product according to the invention can contain aliphatic alcohols, in a content usually in a content usually less than or equal to 0.8 g/kg of product, often less than or equal to 0.6 g/kg, frequently less than or equal to 0.5 g/kg, more often less than or equal to 0.4 g/kg, more frequently less than or equal to 0.2 g/kg, yet more often less than or equal to 0.1 g/kg, yet more frequently less than or equal to 0.05 g/kg, still more often less than or equal to 0.01 g/kg, and in particular less than or equal to 0.001 g/kg. That content is usually of at least 0.001 mg/kg.. The aliphatic alcohols may be selected from isopropanol, allyl alcohol, glycerol, and any mixtures of at least two of them.

The product according to the invention can contain hydroxyketones, in a content in a content usually less than or equal to 0.8 g/kg of product, often less than or equal to 0.6 g/kg, frequently less than or equal to 0.5 g/kg, more often less than or equal to 0.4 g/kg, more frequently less than or equal to 0.2 g/kg, yet more often less than or equal to 0.2 g/kg, yet more frequently less than or equal to 0.05 g/kg, still more often less than than or equal to 0.01 g/kg, and in particular less than or equal to 0.001 g/kg. That content is usually of at least 0.001 mg/kg. The hydroxyketone is often hydroxyacetone.

The product according to the invention can contain epoxides different from epichlorohydrin, in a content in a content usually less than or equal to 0.8 g/kg of product, often less than or equal to 0.6 g/kg, frequently less than or equal to

0.5 g/kg, more often less than or equal to 0.4 g/kg, more frequently less than or equal to 0.2 g/kg, yet more often less than or equal to 0.2 g/kg, yet more frequently less than or equal to 0.05 g/kg, still more often less than or equal to 0.01 g/kg, and in particular less than or equal to 0.001 g/kg. That content is usually of at least 0.001 mg/kg. The epoxide may be selected from propylene oxide, 1,2-epoxyhexane, glycidol, and any mixtures of at least two of them.

The product according to the invention can contain glycidol in an amount in a content usually of at most 0.5 g/kg of product, generally of at most 0.2 g/kg, frequently of at most 0.10 g/kg of product, commonly of at most 0.05 g/kg of product, often of at most 0.01 g/kg and frequently of at most 0.005 g/kg.

The product according to the invention usually contains glycerol, hydroxyacetone and glycidol, of which the sum of the contents is less than 0.1 g/kg of product, preferably at most 0.01 g/kg and more preferably at most 0.005 g/kg. This content is at least 0.001 g/kg.

The product according to the invention can be obtained by dehydrochlorination of a composition containing dichloropropanol and at least one chloro alkoxy propanol in an amount usually of less than or equal to 0.1 g/kg of composition.

The alkoxy group of the chloro alkoxy propanol contains a number of carbon atoms which is generally higher than or equal to 1, often higher than or equal to 2 and frequently higher than or equal to 3. That number of carbon atoms is generally lower than or equal to 10, often lower than or equal to 8 and frequently lower than or equal to 6.

The alkoxy group of the chloro alkoxy propanol can be a linear or branched or alicyclic aliphatic alkoxy group and is preferably a linear or branched aliphatic group. The alkoxy group is preferably selected from the methoxy, ethoxy, propoxy, butoxy, pentoxyl, hexoxy, heptoxy and octoxy groups and more preferably from the methoxy, ethoxy, propoxyl and butoxy groups and particularly preferably from the methoxy and ethoxy groups. Very particularly preferably, the alkoxy group is a methoxy group. The propoxy group can be chosen from the n-propoxy and isopropoxy groups and is preferably an isopropoxy group. The butoxy group can be chosen from the 1-butoxy, 2-butoxy, isobutoxy and tert-butoxy groups, preferably from the isobutoxy and tert-butoxy groups.

Preferably the alkyl group of the alkyl glycidyl ether is a methyl group and the alkoxy group of the chloro alkoxy propanol is a methoxy group.

The product according to the invention can be obtained from a composition containing dichloropropanol wherein the content of chloro alkoxy propanol, preferably chloro methoxy propanol is preferably lower than or equal to 0.08 g/kg, more preferably lower than or equal to 0.06 g/kg, still more preferably
5 lower than or equal to 0.04 g/kg, yet preferably lower than or equal to 0.05 g/kg, most preferably lower than or equal to 0.01 g/kg and particularly most preferably lower than or equal to 0.005 g/kg . This content is usually higher than or equal to 0.0005 g/kg.

The chloro methoxy propanol can be selected from 2-chloro-3-methoxy-
10 propane-1-ol, 1-chloro-3-methoxy-propane-2-ol and mixtures thereof.

Without being bound by any theory, it is believed that, when the dichloropropanol is contaminated by various isomers of chloroalkoxypropanol, the dehydrochlorination of dichloropropanol into epichlorohydrin is accompanied by the dehydrochlorination of chloro alkoxy propanol into alkyl glycidyl ethers.
15 Those alkyl glycidyl ethers exhibit usually boiling points very close to that of epichlorohydrin and are, for this reason, very difficult to separate from it.

The chloro alkoxy propanols can be produced during the manufacture of dichloropropanol, especially when the dichloropropanol is obtained by hydrochlorination of a compound containing glycerol and at least one alkyl ether
20 of glycerol. The glycerol alkyl ethers can originate in the process for manufacturing glycerol especially when glycerol is obtained from trans esterification of oils and/or fats of animal and/or plant origin.

The composition containing dichloropropanol according to the invention can be obtained by hydrochlorination of a compound containing glycerol and at least one glycerol alkyl ether in an amount that is usually lower than or equal to
25 0.6 g/kg, preferably lower than or equal to 0.1 g/kg, more preferably lower than or equal to 0.02 g/kg, yet preferably lower than or equal to 0.015 g/kg and most preferably lower than or equal to 0.01 g/kg. This content is usually higher than or equal to 0.0005 g/kg of compound. The alkyl group in the glycerol alkyl ether is
30 as defined above and is preferably a methyl group.

The invention relates, in a second embodiment, to a process for obtaining a product containing epichlorohydrin and at least one alkyl glycidyl ether in an amount of less than 0.1 g/kg of product. The product can be obtained by dehydrochlorination of a composition containing dichloropropanol and at least
35 one chloro alkoxy propanol in an amount usually of less than or equal to 0.1 g/kg of composition. The composition containing dichloropropanol and at least one

chloro alkoxy propanol can be obtained by hydrochlorination of a compound containing glycerol and at least one glycerol alkyl ether in an amount of less than or equal to 0.6 g/kg of compound.

5 The process for producing the product according to the invention comprises the following steps:

- (a) a compound containing glycerol and at least one glycerol alkyl ether in an amount of less than or equal to 0.6 g/kg of compound is reacted with hydrogen chloride in the presence of a carboxylic acid, in order to obtain a composition containing dichloropropanol and at least one chloro alkoxy
10 propanol in an amount of less than or equal to 0.1 g/kg of composition
- (b) the composition containing dichloropropanol obtained in step (a) is further reacted with a basic agent in order to obtain a product containing epichlorohydrin and at least one alkyl glycidyl ether in an amount of less than 0.1 g/kg of product.

15 The process comprises optionally the following steps:

- (c) a vegetable fat or oil is reacted with an alcohol to obtain the compound containing glycerol, under such conditions that ethers of glycerol are formed and are not separated from glycerol,
- (d) the compound containing glycerol obtained in step (c) is further subjected to
20 at least one treatment, optionally under reduced pressure, of evaporative concentration, of evaporative crystallization, of distillation, of fractional distillation, of stripping or of liquid-liquid extraction, in order to obtain a compound containing glycerol and at least one glycerol alkyl ether in an amount that is preferably lower than or equal to 0.6 g/kg.

25 The conditions of step (a) of the process are such as described in the patent application PCT/EP2007/055742 filed in the name of SOLVAY SA, the content of which is incorporated herein by reference, more specifically the passages from page 18, lines 17 to 25, and page 19, line 4 to 19.

30 The conditions of step (a) of the process are such as described in the patent application PCT/EP2007/055742 filed in the name of SOLVAY SA, the content of which is incorporated herein by reference, more specifically the passages from page 11, line 12, to page 17, line 24, and page 17, lines 31 to 35. The catalyst can be based on dodecanoic acid.

35 The conditions of steps (c) and (d) of the process are such as described in the patent application PCT/EP2007/055742 filed in the name of SOLVAY SA,

the content of which is incorporated herein by reference, more specifically the passages from page 6, line 18, to page 11, line 11.

The invention also relates, in a third embodiment, to the use of the product of the invention described above containing epichlorohydrin and at least one alkyl glycidyl ether in an amount of less than or equal to 0.1 g/kg of product, in the manufacture of epoxy derivatives such epoxy resins, of products which will be used in food and drink applications, of cationization agents, of flame retardants, of products which will be used as detergent ingredients, and of epichlorohydrin elastomers.

10 Brief Description of the Figures

Figure 1 : examples of chemical formula of epoxy resins

Figure 2 : examples of chemical formula of compounds having at least one aromatic hydroxyl group

15 Figure 3 : examples of chemical formula of compounds having at least one aromatic hydroxyl or aromatic amine group per molecule

Figure 4 : examples of chemical formula of polycyclopentadiene polyphenols or aromatic polyamines

Figure 5 : example of chemical formula of a coagulant molecule

Figure 6 : example of chemical formula of wet-strength resin polymers

20 Figure 7 : example of chemical formula of compounds used as phosphorus containing flame retardants.

1. EPOXY DERIVATIVES

1.1. General

25 Epoxy derivatives are for example, epoxy resins, glycidyl ethers, glycidyl esters and glycidyl amides and imides. Examples of glycidyl esters are glycidyl acrylate and glycidyl methacrylate.

By epoxy resin, one intends to denote a polymer, the chemical formula of which contains at least one oxirane group, preferably one 2,3-epoxypropyloxy group.

30 By polymer, one intends to denote molecules with many units joined to each other through chemical covalent bonds, often in a repeating manner, those units being referred as repeat units. The number of repeat units is higher than zero. A polymer contains at least one type of repeat units. When the polymer contains only one type of repeat units, it is called a homopolymer. When the
35 polymer contains more than one type of repeat units, it is called a copolymer. The copolymers can be of the random type, of the alternating type or of the block

type, such as described in "Polymer Science Dictionary, M.S.M., Elsevier Applied Science, London and New York 1989, page 86".

Examples of chemical formulas of epoxy resins are presented in Figure 1, where n is not zero.

5 By glycidyl ether, one intends to denote an ether, the chemical formula of which contains at least one glycidyl (2,3-epoxypropyl) group and which is not a polymer. Examples of glycidyl ethers are N-butyl glycidyl ether, C₁₂-C₁₄ aliphatic glycidyl ethers, o-Cresol glycidyl ether, neopentylglycol diglycidyl ether and butanediol diglycidyl ether.

10 By glycidyl ester, one intends to denote an ester, the chemical formula of which contains at least one glycidyl (2,3-epoxypropyl) group and which is not a polymer. Examples of glycidyl ester are diglycidyl ester of hexahydrophthalic acid, glycidyl ester of neodecanoic acid, glycidyl acrylate and glycidyl methacrylate.

15 By glycidyl amides and imides, one intends to denote an amide or an imide, the chemical formula of which contains at least one glycidyl (2,3-epoxypropyl) group and which is not a polymer. Examples of glycidyl amide and imide 1,3,5—tris(2,3-epoxypropyl)-1,3,5-perhydrotriazine-2,4,6-trione and 5,5-dimethyl-1,3-bis(2,3-epoxypropyl)-2,4-imidazolidinedione.

20 1.2. Co-reactants

When, the product containing epichlorohydrin according to the invention is used in the manufacture of epoxy derivatives, the product containing epichlorohydrin is usually subjected to a reaction with at least one compound containing at least one active hydrogen atom, preferably at least two active
25 hydrogen atoms, followed by dehydrochlorination as described in Ullmann's Encyclopedia of Industrial Chemistry, 5th Edition, 1987, Vol. A9, pp. 547-553).

The compound containing one active hydrogen atom can be selected from mono alcohol, preferably from 1-butanol, a C₁₂ to C₁₄ primary alcohol or a cresol, and mixtures thereof, mono carboxylic acids, like for instance neodecanoic acid,
30 acrylic acid, methacrylic acid, or mixtures thereof.

The compound containing at least two active hydrogen atoms can be selected from polyols, polyamines, amino alcohols, polyimides and amides, polycarboxylic acids, and mixtures thereof.

The polyols can be aromatic or aliphatic. Aromatic polyols are preferred.

35 Preferred aliphatic polyols are aliphatic diols, more preferably selected from butanediol, neopentyl glycol, hydrogenated Bisphenol A (4,4'-dihydroxy-

2,2-dicyclohexylpropane), and aliphatic triols, preferably glycerol, poly(oxypropylene) glycol, and mixtures thereof.

Aromatic polyols can be selected from polyhydroxy benzenes, polyphenolic compounds, and mixtures thereof.

5 Poly hydroxybenzenes are preferably selected from dihydroxy benzenes, trihydroxy benzene, and mixtures thereof. Dihydroxy benzenes are more preferably selected from 1,2-, 1,3-, 1,4-dihydroxy benzenes and mixture thereof.

Trihydroxy benzene is preferably 1,3,5-trihydroxy benzene.

10 Polyphenolic compounds are generally compounds the molecule of which contains at least one aromatic hydroxyl group.

Suitable compounds having at least one aromatic hydroxyl group which can be employed herein are such as described in US 4,499,255, the content of which is incorporated herein by reference and include, for example, phenols, bisphenols, novolac resins, polyvinyl phenols, the corresponding amine compounds and the like, such as those represented by the formulas I to V of Figure 2 wherein, each A is independently a divalent hydrocarbon group having from 1 to about 12, preferably from 1 to about 6 carbon atoms, -O-, -S-, -S-S-,

15 $-(S=O)_2-$, $-(S=O)-$ or $-(C=O)-$, A' is a trivalent hydrocarbon group having from 1 to about 12, preferably from 1 to about 6, carbon atoms; each R is independently hydrogen, a hydrocarbyl group having from 1 to about 10, preferably from 1 to about 4, carbon atoms, a halogen atom, preferably chlorine or bromine or a hydroxyl group or an amino group; each Z is independently -OH or NH₂; p has a value of from about 1 to about 100, preferably from about 2 to about 50; m has a value from about 1.00 to about 6 and n has a value of zero or 1.

25 Also suitable as compounds having at least one aromatic hydroxyl or aromatic amine group per molecule are those represented by the formulas VI to VIII of Figure 3, wherein each R is a divalent hydrocarbyl group having from 1 to about 18, preferably from about 2 to about 12 and most preferably from about 2 to about 6 carbon atoms, a group represented by the formulas IX, X, XI or XII of Figure 2, or R can combine with R¹ so as to form a stable heterocyclic ring with the nitrogen atoms; each A is independently a divalent hydrocarbyl group having from 1 to about 10, preferably from 1 to about four carbon atoms, -O-, -S-, -S-S-, $-(S=O)_2-$, $-(S=O)-$ or $-(C=O)-$, each R¹ is independently hydrogen, a 2,3-epoxypropyl group, a 2-alkyl-2,3-epoxypropyl group, a monovalent hydrocarbyl group or a hydroxyl substituted monovalent hydrocarbyl group, said hydrocarbyl groups having from 1 to about 9 carbon atoms, said alkyl having from 1 to about

4, preferably 1 to about 3 carbon atoms; each R^2 is independently hydrogen or an alkyl group having from 1 to about 4, preferably 1 to about 3 carbon atoms; each R^3 is independently hydrogen or an alkyl group having from 1 to about 4 carbon atoms; each R^4 is independently hydrogen, a hydrocarbyl or halogen substituted hydrocarbyl group having from 1 to about 9, preferably from 1 to about 2 carbon atoms; each R^8 is independently selected from the group represented by formula XIV or the same groups as R^1 except that R^8 cannot be a hydrogen; each R^9 is independently a divalent hydrocarbyl group having from 2 to about 4, preferably 2 carbon atoms; each Z is independently -OH or -NH₂; each X is independently hydrogen, chlorine, bromine or a hydrocarbyl or a hydrocarbyloxy group having from 1 to about 9, preferably 1 to about 6 carbon atoms; each m independently has a value of zero or 1; n has an average value of from about 0.01 to about 6, preferably 0.1 to about 4; p has an average value of from 1 to about 10, preferably from 1 to about 3; q has an average value of at least 1, preferably from 1 to about 150, most preferably from 1 to about 100 and usually from 1 to about 10 and each y and z independently has a value of 1 or 2.

Also suitable are polycyclopentadiene polyphenols or aromatic polyamines represented by the formula XIII of Figure 4, wherein Z is -OH or -NH₂ and n has a value from 1 to about 5; n' has a value of from about 1 to about 10, preferably from 3 to about 6; each R is independently hydrogen, a hydrocarbyl group having from 1 to about 10, preferably from 1 to about 4 carbon atoms, a halogen atom, preferably chlorine or bromine or a hydroxyl group or an amino group.

Suitable such polycyclopentadiene polyphenols and methods for their preparation can be found in U.S. Pat. No. 4,390,680 issued to Donald L. Nelson on June 28, 1983 which is incorporated herein by reference. The polycyclopentadiene aromatic polyamines can be prepared in a similar manner by substituting an aromatic amine for the phenolic compound.

Also suitable are compounds containing both at least one aromatic hydroxyl group and at least one aromatic amine group such as, for example, hydroxy aniline, aminoxylene and the like.

The polyphenolic compound is preferably selected from Bisphenol A (4,4'-dihydroxy-2,2-diphenylpropane, 4,4'-isopropylidenediphenol), tetrabromo Bisphenol A (4,4'-isopropylidenebis(2,6-dibromophenol)), Bisphenol AF (4,4'-[2,2,2-trifluoro-1-(trifluoromethyl)ethylidene]bisphenol) = hexafluorobisphenol A (4,4'-dihydroxy-2,2-diphenyl-1,1,1,3,3,3-hexafluoropropane), 1,1,2,2-tetra(p-hydroxyphenyl)ethane, hexafluorobisphenol A, tetramethylbisphenol (4,4'-

5 dihydroxy-3,3',5,5'-tetramethyl bisphenol), 1,5-dihydroxynaphthalene, 1,1',7,7'-tetrahydroxy-dinaphthyl methane, 4,4'-dihydroxy- α -methylstilbene, a condensation product of Bisphenol A with formaldehyde (Bisphenol A novolac), a condensation product of phenol with formaldehyde, preferably Bisphenol F
10 (mixture of o,o', o,p' and p,p' isomers of dihydroxy diphenylmethane), a condensation product of cresol with formaldehyde (mixtures of o,o', o,p' and p,p' isomers of methyl hydroxy diphenylmethane), an alkylation product of phenol and dicyclopentadiene (2,5-bis[(hydroxy phenyl]octahydro-4,7-methano-5H-indene), a condensation product of phenol and glyoxal (tetrakis(4-hydroxy-phenyl)ethane), a condensation product of phenol and a hydroxybenzaldehyde
15 (e.g., tris(4-hydroxyphenyl)methane), 1,1,3-tris-(p-hydroxyphenyl)-propane, and mixtures thereof.

The polyamines can be aliphatic or aromatic. Aromatic diamines are preferred, like for instance 4,4'-diamino diphenyl methane.

15 The amino alcohol can be aliphatic or aromatic. Aromatic amino alcohol are preferred like for instance, p-aminophenol.

The imides and amides can be aliphatic or aromatic. Heterocyclic imides and amides are preferred, like for instance 1,3,5-triazinetriol and imidazolidine-2,4-dione.

20 Polycarboxylic acids can be aliphatic or aromatic. An example of dimeric fatty acid is linoleic dimer acid. The polycarboxylic acid is preferably an aromatic dicarboxylic acid like for instance hexahydrophthalic acid.

1.3. Processes for making epoxy derivatives

25 The process for making epoxy resins, glycidyl ethers and glycidyl esters generally involve a reaction of the product containing epichlorohydrin and the compound containing at least one active hydrogen atom, followed by dehydrochlorination with a basic agent

The process for making epoxy resin usually involves two steps: the preparation of an uncured epoxy resin followed by a curing step.

30 1.3.1. Uncured ER

The reaction between the product containing epichlorohydrin and the compound containing at least one, preferably two active hydrogen atoms can be carried out by any process known in the art like for instance the Caustic Coupling Process and the phase-transfer catalyst process, for making Liquid Epoxy Resins
35 (LER), the Taffy and the Advancement or Fusion process for making Solid Epoxy Resins (SER).

Caustic Coupling Process

In the caustic process, caustic is used as a catalyst for the nucleophilic ring-opening (coupling reaction) of the epoxide group on the primary carbon atom of epichlorohydrin by the phenolic hydroxyl group and as a dehydrochlorinating agent for conversion of the chlorohydrin to the epoxide group. Caustic (NaOH) can however be substituted by any basic compound.

The epichlorohydrin and the compound with active hydrogen atom, preferably an aromatic hydroxyl or aromatic amine compound, are employed in a molar ratio of from about 2:1 to about 10:1, preferably from about 2:1 to about 6:1, respectively.

The basic compound may be an organic or inorganic basic compound. Organic basic compounds are for example amines, phosphines and ammonium, phosphonium or arsonium hydroxides. Inorganic basic compounds are preferred. The expression "inorganic compounds" is understood to mean compounds which do not contain a carbon-hydrogen bond. The inorganic basic compound may be chosen from alkali and alkaline-earth metal oxides, hydroxides, carbonates, hydrogencarbonates, phosphates, hydrogenphosphates and borates, and mixtures thereof. Alkali and alkaline-earth metal oxides and hydroxides are preferred. Preferred alkali metal hydroxides which can be employed herein include, for example, sodium hydroxide, potassium hydroxide, lithium hydroxide or mixtures thereof. Sodium hydroxide is especially preferred.

In the process according to the invention, the basic compound may be in the form of a liquid, an essentially anhydrous solid, a hydrated solid, an aqueous and/or organic solution or an aqueous and/or organic suspension. The basic compound is preferably in the form of an essentially anhydrous solid, a hydrated solid, an aqueous solution or an aqueous suspension. It is preferred to use a solution or a suspension, preferably a solution of the basic compound, preferably sodium hydroxide, in water.

The content of the basic agent in the solution or suspension is generally higher than or equal to 5 % by weight, preferably higher than or equal to 10 % by weight, preferably higher than or equal to 20 % by weight, and most preferably higher than or equal to 30 % by weight. That content is usually lower than or equal to 70 % by weight, preferably lower than or equal to 60 % by weight, preferably lower than or equal to 50 % by weight, and most preferably lower than or equal to 40 % by weight.

The alkali metal hydroxide is preferably employed as an aqueous solution, usually at a concentration of from about 20 to about 50, preferably from about 40 to about 50 percent by weight.

5 The amount of basic compound, preferably alkali metal hydroxide, which is employed in the process of the present invention is from about 0.80 mole to about 1.2 mole of basic agent, preferably from about 0.90 mole to 1.0 mole per each, preferably aromatic, hydroxyl group and, preferably aromatic, amine hydrogen.

10 The basic agent, epichlorohydrin and the compound containing active hydrogen atom can be mixed in any order. It is preferred to add the basic compound to a mixture of the two other reactants. The basic agent, preferably, alkali metal hydroxide can be added either continuously or incrementally, but never is all of the alkali metal hydroxide added in one increment.

15 The reaction can be carried out in a solvent. Suitable solvents which can be employed include any solvent which does not react with any component in the reaction mixture. Preferably such solvent is partially or wholly miscible with water, forms a codistillate with the epichlorohydrin and water and the distillate has a boiling point below that of the lowest boiling component of the reaction mixture at the pressure employed. Suitable such solvents include primary and secondary alcohols such as, for example, 1-methoxy-2-hydroxy propane, 1-
20 butoxy-2-hydroxy ethane, cyclohexanol. The secondary alcohols are preferred.

25 When a solvent is used, the amount of solvent which is employed will depend on the particular solvent and the compound containing active hydrogen atom being employed. The solvent generally ranges from about 5 to about 50 weight percent, preferably from about 10 to about 40 weight percent based on the total weight of reactants.

The pressure can be equal to 1 bar absolute, lower than 1 bar absolute or higher than 1 bar absolute. When a solvent is used, suitable pressures which can be employed are those which will provide the codistillate with a boiling point of from about 45 °C to about 80 °C, preferably from about 55 °C to about 70 °C.

30 The temperature of the reaction is usually greater than or equal to 25 °C, preferably greater than or equal to 50 °C, more preferably greater than or equal to 90 °C, and most preferably greater than or equal to 95 °C. The temperature of the reaction is usually lower than or equal to 200 °C, preferably lower than or equal to 150 °C, more preferably lower than or equal to 125 °C, and most preferably
35 lower than or equal to 120 °C.

The reaction is usually conducted for a length of time such that the quantity of groups containing active hydrogen atom remaining in the reaction mixture is not greater than about 0.5, preferably not greater than about 0.2 percent by weight. That time is usually greater than or equal to 0.5 h, frequently greater than
5 or equal to 1.0 h, often greater than or equal to 2.0 h, and most particularly greater than or equal to 3.0 h. The time of reaction is usually lower than or equal to 20 h, often lower than or equal to 10 h, frequently lower than or equal to 5 h, and most particularly lower than or equal to 4 h.

Upon completion of the reaction, the resultant epoxy resin is finished in any
10 of the methods normally employed. The excess epichlorohydrin is usually removed by distillation and the salt removed by filtration, centrifugation and/or water washing.

The epichlorohydrin distillation is generally carried out in two steps. The first step is carried out generally at atmospheric pressure (1 bar absolute), at a
15 temperature usually greater than or equal to 100 °C, preferably greater than or equal to 120 °C, more preferably greater than or equal to 130 °C, and most preferably greater than or equal to 145 °C and usually lower than or equal to 200 °C, preferably lower than or equal to 180 °C, more preferably lower than or equal to 175 °C, and most preferably lower than or equal to 155 °C. The second
20 step is carried out usually at a subatmospheric pressure, usually lower than or equal to 0.1 bar absolute, preferably lower than or equal to 0.01 bar, more preferably lower than or equal to 0.005 bar, and most preferably lower than or equal to 0.002 bar, at a temperature usually greater than or equal to 150 °C, preferably greater than or equal to 170 °C, more preferably greater than or equal
25 to 190 °C, and most preferably greater than or equal to 195 °C and usually lower than or equal to 300 °C, preferably lower than or equal to 250 °C, more preferably lower than or equal to 220 °C, and most preferably lower than or equal to 215 °C.

The salt which is formed can be separated from the crude product through
30 addition of a solvent, e.g. toluene, followed by filtration and distillation to remove the solvent.

Phase-Transfer Catalytic Process

Alternatively, in the Phase-Transfer Catalyst Process, the coupling reaction and dehydrochlorination can be performed separately by using phase-transfer
35 coupling catalysts, such as quaternary ammonium salts, which are not strong enough bases to promote dehydrochlorination. Once the coupling reaction is

completed, caustic is added to carry out the dehydrochlorination step. Via this method, higher yields of for example the monomeric diglycidyl ether of Bisphenol A (DGEBA) (> 90 %) are readily available.

Batch methods and preferably continuous or semi continuous processes can be used.

Taffy Process

The Taffy method is used to prepare higher molecular weight solid resins. It is directly from epichlorohydrin, the compound containing active hydrogen atoms, and a stoichiometric amount of NaOH. This process is very similar to the caustic coupling process used to prepare liquid epoxy resins. Lower epichlorohydrin to compound containing active hydrogen atoms ratios are used to promote formation of high molecular weight resins. Upon completion of the polymerization, the mixture consists of an alkaline brine solution and a water-resin emulsion. The product is recovered by separating the phases, washing the resin with water, and removing the water under vacuum.

The epichlorohydrin and the compound with active hydrogen atom, preferably an aromatic hydroxyl or aromatic amine compound, are employed in a molar ratio of from about 1:1 to about 2:1, preferably from about 1.3:1 to about 1.8:1, respectively.

The alkali metal hydroxide is preferably employed as an aqueous solution, usually at a concentration of from about 1 to about 20, preferably from about 5 to about 15 percent by weight.

The amount of basic compound, preferably alkali metal hydroxide, which is employed in the process of the present invention is from about 0.05 mole to about 2 mole of basic agent, preferably from about 0.1 mole to 0.5 mole per each, preferably aromatic, hydroxyl group and, preferably aromatic, amine hydrogen.

The temperature of the reaction is usually greater than or equal to 25 °C, preferably greater than or equal to 50 °C, more preferably greater than or equal to 90 °C, and most preferably greater than or equal to 95 °C. The temperature of the reaction is usually lower than or equal to 200 °C, preferably lower than or equal to 150 °C, more preferably lower than or equal to 125 °C, and most preferably lower than or equal to 120 °C.

The time of reaction is usually greater than or equal to 0.1 h, frequently greater than or equal to 0.5 h, often greater than or equal to 1.0 h, and most particularly greater than or equal to 1.5 h. The time of reaction is usually lower

than or equal to 20 h, often lower than or equal to 10 h, frequently lower than or equal to 5 h, and most particularly lower than or equal to 4 h.

The basic agent, epichlorohydrin and the compound containing active hydrogen atom can be mixed in any order. It is preferred to add epichlorohydrin to a mixture of the two other reactants.

The reaction is usually carried out under vigorous agitation.

At the end of the reaction, the mixture separates into two layers. The heavier aqueous layer is drawn off and the molten, taffy-like product is washed with hot water until the wash water is neutral. The taffy-like product is dried at a temperature generally higher than or equal to 100 °C, preferably higher than or equal to 120 °C.

Alternatively, epichlorohydrin and water can be removed by distillation at temperatures up to 180 °C under vacuum. The crude resin/salt mixture can then be dissolved in a secondary solvent to facilitate water washing and salt removal. The secondary solvent can then be removed via vacuum distillation to obtain the product.

The advancement or fusion process is an alternative method for making solid epoxy resin and is based on the chain-extension reaction of liquid epoxy resin (for example, crude DGEBA) with bisphenol A.

1.3.2. Curing agents

The curing of Epoxy Resins can be carried out using classical curing agents. The cure can be done with coreactive curing agents, or it can be catalytic or photoinitiated cationic.

The coreactive curing agents can be selected from amine functional curing agents, carboxylic functional polyester and anhydride curing agents, phenolic-terminated curing agents, melamine-, urea-, and phenol-formaldehyde resins, mercaptans (polysulfides and polymercaptans) curing agents, cyclic amidines curing agents, isocyanate curing agents and cyanate ester curing agents

The amine functional curing agents can be primary and secondary amines, polyamides, amidoamines and dicyandiamide.

The amines can be aliphatic, cycloaliphatic, aromatic amines or aryl amines.

The aliphatic amines can be selected from liquid aliphatic polyamines, such as polyethylene polyamines, hexamethylene diamine, polyether amines (polyglycol-based polyamines), ketimines (reaction products of ketones and primary aliphatic amines), mannich base adducts (reaction products of amine,

phenol and formaldehyde), polyetheramines (reaction product of polyols derived from ethylene or propylene oxide with amines) and mixtures thereof.

The cycloaliphatic amines can be selected from isophorone diamine, bis(4-amino-cyclohexyl)methane, 1,2-diamino-cyclohexane, trihexylmethylene
5 diamines, metaxylylenediamine, and mixtures thereof.

The aromatic amines can be selected from meta-phenylenediamine, methylene dianiline, alkyl (tetraethyl-)substituted methylene dianiline, 4,4'-diaminodiphenylmethane, 4,4'-diamino diphenyl sulfone, diethylenetoluenediamine

10 The aryl amines can be selected from meta xylylenediamine, 1,3-bis(aminomethyl cyclohexane).

The amine can be more specifically selected from diethylenetriamine, triethylenetetramine, Poly(oxypropylene diamine), poly(oxypropylene triamine), poly(glycol amine), N-aminoethylpiperazine, isophorone diamine, 1,2-
15 diaminocyclohexane, bis(4-aminocyclohexyl)methane, 4,4'-diamino-diphenylmethane, 4,4'-diaminodiphenyl sulfone, m-phenylenediamine, diethyltoluenediamine, meta-xylene diamine, 1,3-bis(aminomethyl cyclohexane, and mixtures thereof.

The polyamides can be obtained by reaction of dimerized and trimerized
20 vegetable oil fatty acids (9,12 and 9,11-linoleic acids) with polyamines (diethylene triamine) or from polyamines and phenolic-containing carboxylic acids (phenalkamines).

The amidoamines can be obtained by reaction of mono functional acid like tall-oil fatty acid with a polyamine such diethylenediamine.

25 The carboxylic functional polyester can be obtained by reaction of terphthalic acid, trimellitic anhydride and neopentyl alcohol

The acid anhydrides can be phthalic anhydride, tetrahydrophthalic anhydride, methyltetrahydrophthalic anhydride, methyl hexahydrophthalic anhydride, hexahydrophthalic anhydride, nadic methyl anhydride or methyl himic
30 anhydride, benzophenonetetracarboxylic dianhydride, tetrachlorophthalic anhydride, and mixtures thereof.

The phenolic-terminated curing agents are products that can be obtained by reaction of phenol, creseol or bisphenol a with formaldehydes.

35 The mercaptans (polysulfides and polymercaptans) curing agents generally contain terminal thiols.

The cyclic amidines curing agents can be for instance 2-phenyl imidazolidine.

The cyanate ester curing agents can be for instance bisphenol a dicyante ester.

5 The catalytic cure can be carried out with Lewis bases or Lewis acids.

 The Lewis bases are for instance tertiary amine, like 2-diethylamino-methylphenol, 2,4,6-tris(dimethylaminomethyl)phenol and imidazoles such as 2-methylimidazole and 2-phenylimidazole, cyclic amidines like 2-phenylimidazoline, substituted ureas like 3-phenyl-1,1-dimethylurea and
10 quaternary ammonium salt like tetralkyl- and alkyl-triphenyl phosphonium salts.

 The Lewis acid can be selected from boron trihalides, preferably boron trifluoride.

 The Photoinitiated Cationic Cure can be carried out with photoinitiators like aryldiazonium salts, diaryldiazonium salts, diaryldiionium salts and onium
15 salts of Group VIa elements, such as triarylsulfonium salt, dialkylphenacyl sulfonium salts.

1.4 Uses of epoxy resins

 The epoxy resins can be used in coating applications and in structural applications. The coating applications can be in the fields of marine and
20 industrial maintenance (corrosion-resistant coatings for ships, shipping containers, offshore oil rigs and platforms, transportation infrastructures such as bridges, rail car coatings, coatings for industrial storage tanks, and primers for light industrial and agricultural equipment), metal container (aluminum and steel food and beverage cans) and coil coatings (metal can ends, can bodies, building
25 products, appliance panels, transportation, and metal furniture applications), automotive coatings (primer surface coatings) and inks and resists. Coating can be done using various technologies like low solids solventborne coating, high solid solventborne coating, solvent-free coating, waterborne coating, powder coating and radiation-curable coating.

30 The structural applications can be in the field of structural composites (fiber reinforcing materials based on glass, boron, graphite and aromatic polyaramides), of civil engineering, flooring (floor paints, self-leveling floors, trowelable floors, and pebble-finished floors) and construction, of electrical laminates, of electrical laminates (printed wiring boards and printed circuit boards), of other electrical
35 and electronic applications, like casting, potting, encapsulation (switchgear components, transformers, insulators, high voltage cable accessories, and similar

devices) and transfer molding (encapsulation of electronic components such as semiconductor chips, passive devices, and integrated circuits), of adhesives (cohesion between similar and dissimilar materials such as metals, glass, ceramics, wood, cloth, and many types of plastics) and of tooling (prototypes, master models, molds and other parts for aerospace, automotive, foundry, boat building, and various industrial molded items).

1.5 Uses of Glycidyl Ethers and Esters

These products are used for applications such as coatings, adhesives and reactive diluents.

1.6 Uses of Glycidyl amides and imides

These products are used for applications such as outdoor powder coatings with polyesters, or in applications in which a non-yellowing epoxy resin is desirable.

2. PRODUCTS FOR FOOD-DRINK APPLICATIONS - COAGULANTS

2.1. General

The product containing epichlorohydrin according to the invention can be used for the manufacture of products that will be used in applications where they will come in contact with food and drink, more specifically for the manufacture of synthetic organic coagulants.

Coagulation refers to the reduction or elimination of electrostatic repulsion forces between particles via addition of certain coagulants, and in technical terms, the first phase of floc formation after chemical mixing and destabilization, but before dosing of flocculants.

Coagulants are generally polymers with a high cationic charge density to neutralize negative charges of colloids and initiate the formation of flocs. They generally exhibit a relatively low molecular weight in order to permit a good diffusion of the charges around the particles and a low viscosity to allow a good distribution of the polymer in the effluents.

By coagulant, one intends to denote a polymer, comprising at least one repeat unit containing at least one 2-hydroxypropyldialkylammonium group.


An example of a coagulant molecule is presented in Figure 5.

2.2. Co-reactants

In the application according to the invention, the product containing epichlorohydrin is usually subjected to a reaction with ammonia, an amine, a polyaminoamide or a polyimine.

The amine can be a mono-, a di- or a polyamine. The amine can be aliphatic, alicyclic or aromatic, saturated or unsaturated, linear or substituted. The amine has preferably at least one, more preferably at least two primary amino hydrogens.

5 The amine can be represented by the general formula:



wherein R^{22} and R^{24} can be equal, except when equal to H, or different and can independently be selected from H, alkyl or alkenyl radical, linear, branched or carbocyclic, having from 1 to 30 carbon atoms, R^{21} and R^{23} can be equal or
 10 different, preferably equal, divalent aliphatic radical aromatic radicals having from 2 to 12 carbon atoms, each of r and s is an integer of from 0 to 6, r plus s equals 0 to 6.

Amines include lower alkyl and lower alkenyl primary monoamines, such as methylamine, ethylamine, isopropylamine, tertbutylamine, mixed amylamines,
 15 n-octylamine, branched-chain nonylamine, secondary amines such as dimethylamine, ethylmethylamine, diethylamine, propylmethylamine, propylethylamine, dipropylamine, dibutylamine, propylbutylamine, ethylbutylamine, methylbutylamine, pentylethylamine, pentylethylamine, and pentylpropylamine, tertiary amines, as well as alkylenediamines, triamines and
 20 polyamines, with or without an alkenyl or alkyl substituent bonded to nitrogen, such as ethylenediamine, propylenediamine, butylenediamine, pentylenediamine, hexylenediamine, octylenediamine, dodecylenediamine, cyclohexylenediamine, diethylenetriamine, dipropylenetriamine, dipentylenetriamine, triethylene tetramine, tributylenetetramine, trihexylenetetramine, tetraethylenepentamine,
 25 tetrapropylenepentamine, pentaheylenehexamine, pentapropylenhexamine, N-ethyl-1,2-ethylenediamine, N-(2-propenyl)-1,3-propanediamine, N-hexyl-1,4-butanediamine, N-2ethylhexyl-1,3-propanediamine, N-(5-octenyl)-1,6-hexanediamine, N-butyltriethylenetriamine, N-hexyltripropylenetetramine, N-nonyltetrabutylene pentamine and N-(oleyl)-hexaethyleneheptamine, N-alkyl-1,3-
 30 diaminopropane, butane and hexane, where the radical alkyl can be hexyl, heptyl, octyl, nonyl, decyl, undecyl, , dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, nonadecyl, eicosyl, heneicosyl, docosyl, tricosyl, and tetracosyl.

The monoamine is preferably a secondary amine, more preferably
 35 dimethylamine.

The diamine is more preferably selected from 1,2-diaminoethane, 1,2-diaminopropane, 1,3-diaminopropane, a N-substituted diaminopropane, more preferably, 1-amino-3-dimethylaminopropane, 1-amino-3-diethylaminopropane, 1-amino-3-cyclohexylaminopropane, N,N,N',N'-tetramethyl-1,3-propanediamine, 1,3-diaminobutane, 1,5-diaminopentane, 1,8-diaminooctane, 1,10-diaminodecane, 1,12-diaminododecane, 2-(diethylamino)ethylamine, 1-diethylamino-4-aminopentane, 3-aminomethyl-3,5,5-trimethylcyclohexylamine and N,N,N',N',-tetramethyl-1,6-hexanediamine.

Polyaminoamides are generally obtained from polyamide, preferably polyacrylamide, formaldehyde and an amine, preferably a secondary amine. Poly[N-(dialkylaminoalkyl)acrylamide] is particularly preferred.

Polyimines are usually obtained by ring opening polymerization of alkylene imine, preferably ethylene imine.

2.3. Processes

The reaction between the product containing epichlorohydrin and the compound containing at least one, preferably two primary amino hydrogens can be carried out by any process known in the art.

The reaction is generally carried out in the liquid phase, possibly in the presence of a solvent. The solvent may be selected from water, an organic solvent, preferably miscible with water, or mixtures thereof. Water is preferred. Monoalcohols, like methanol, ethanol, n-propanol, isopropanol and butanol are preferred organic solvents

When a solvent is used, the ammonia or amine content in the solvent-ammonia or amine mixture is usually higher than or equal to 5 % by weight (% wt), preferably higher than or equal to 10 wt %, more preferably higher than or equal to 20 wt % and most preferably higher than or equal to 45 wt %. That content is usually lower than or equal to 90 wt %, preferably lower than or equal to 75 wt % , more preferably lower than or equal to 60 wt %, and most preferably lower than or equal to 55 wt %.

The molar ratio between epichlorohydrin and ammonia or amine is generally higher than or equal to 0.1, preferably higher than or equal to 0.5, more preferably higher than or equal to 0.75 and most preferably higher than or equal to 1. That ratio is usually lower than or equal to 10, preferably lower than or equal to 5, more preferably lower than or equal to 3, and most preferably lower than or equal to 2.

The temperature at which the reaction is carried out is generally higher than or equal to 10 °C, preferably higher than or equal to 25 °C, more preferably higher than or equal to 50 °C and most preferably higher than or equal to 60 °C. That temperature is usually lower than or equal to 120 °C, preferably lower than
5 or equal to 110 °C, more preferably lower than or equal to 100 °C, and most preferably lower than or equal to 90 °C.

The pressure at which the reaction is carried out is generally higher than or equal to 0.1 bar absolute, preferably higher than or equal to 0.2 bar, more preferably higher than or equal to 0.5 bar and most preferably higher than or
10 equal to 1 bar. That pressure is usually lower than or equal to 20 bar, preferably lower than or equal to 10 bar, more preferably lower than or equal to 5 bar, and most preferably lower than or equal to 2 bar.

The duration of the reaction is generally higher than or equal to 10 min absolute, preferably higher than or equal to 20 min, more preferably higher than
15 or equal to 30 min and most preferably higher than or equal to 60 min. That duration is usually lower than or equal to 10 h, preferably lower than or equal to 5 h, more preferably lower than or equal to 3 h, and most preferably lower than or equal to 2 h.

The manufacturing procedure usually involves the dissolution of the amines
20 or ammonia in the solvent, followed by a slow addition of the epichlorohydrin, itself possibly dissolved in a solvent, possibly cooling in order to keep the temperature of the reaction between 10 and 50 °C, often between 25 and 40 °C, then after the epichlorohydrin addition is complete, raising the temperature to between 60 and 90 °C.

25 The reaction product can be recovered as an aqueous solution, or a solid after further treatments, e.g. distillation of the solvents under vacuum, treatment of the solution with an acid or a base.

These reactions lead to the formation of the monomer. For example a reaction between epichlorohydrin and dimethylamine produces the
30 epichlorohydrin dimethylamine monomer. This is then homopolymerized to the corresponding quaternary ammonium compound which is a low molecular weight cationic polymer used as a coagulant. Such polymerization usually takes place under alkaline conditions.

The monomer can also be copolymerized with acrylamide to produce
35 higher molecular weight polymers also used for water treatment.

2.4. Products characteristics

The obtained polymers usually exhibit a molecular weight that is higher than or equal to 5 000, often higher than or equal to 10 000, and frequently higher than or equal to 50 000. That molecular weight is usually lower than or equal to 500 000, often lower than or equal to 400 000, and frequently lower than or equal to 300 000. They can be obtained as aqueous solution containing from 40 to 50 % by weight of polymers and exhibiting viscosities from 40 to 11 000 centipoise.

2.5. Uses

These polymers can be used for treatment of raw water for conversion to drinking water, for recycling paper of water in Pulp & Paper Industry, for paint detackification, for breaking oil emulsions, for oil and grease removal, and for sludge dewatering. They can also be used for sugar refining.

3. PRODUCTS FOR FOOD-DRINK APPLICATIONS – WET-STRENGTH RESINS

3.1. General

The product containing epichlorohydrin according to the invention can be used for the manufacture of products that will be used in applications where they will come in contact with food and drink, more specifically for the manufacture of wet-strength resins.

By wet-strength resin one intends to denote a polyaminoamide polymer, the chemical formula of which contains at least one group selected from 2,3-epoxypropylamine, 2,3-epoxypropylammonium, 3-chloro-2-hydroxypropylamine, 3-chloro-2-hydroxypropylammonium, 3-hydroxyazetidinium, and any combination of at least two of them.

Examples of chemical formulas of such a polymer are presented in Figure 6.

3.2. Co-reactants

In the application according to the invention, the product containing epichlorohydrin is usually subjected to a reaction with a polyamine or a polyamide.

The polyamine and the reactions conditions are as described above for the manufacture of coagulants.

The polyamide is usually obtained by reacting an amine, preferably a polyalkylene polyamine (in this case the polyamide is generally referred as a polyaminamide) and a dicarboxylic acid, preferably a saturated aliphatic dicarboxylic acid, as described in US 865,727, the content of which is

incorporated herein by reference. The polyamide may be represented by the general formula



where R^{21} , R^{22} , R^{23} , r and s are as described above, and R^{24} is the divalent hydrocarbon radical of the dibasic carboxylic acid, preferably selected from phenylene, naphthalene, methylene, ethylene, propylene, butylenes, pentylene, hexylene, octylene and nonylene.

Preferably, the polyamide may be represented by the general formula



- 10 wherein t and x are each 2 or more and wherein the $-\text{NH}(\text{C}_t\text{H}_{2t}\text{HN})_x-$ group is derived from the polyamines described above, preferably containing from 2 to 8 alkylene groups, more preferably from diethylenetriamine, triethylenetetramine, tetraethylenepentamine, dipropylenetriamine and N-bis(aminopropyl)methylamine
- 15 the $-\text{COR}^{24}\text{CO}-$ group is derived from dibasic carboxylic acid containing from 2 to 12 carbon atoms, preferably selected from phenylene, naphthalene, methylene, ethylene, propylene, butylenes, pentylene, hexylene, octylene and nonylene. The acid is more preferably selected from malonic, succinic, glutaric, adipic, diglycolic, sebacic or azelaic acid, and mixtures thereof.

20 3.3. Processes

- The reaction between the polyamide and epichlorohydrin is usually carried out at a temperature generally higher than or equal to 45 °C. That temperature is usually lower than or equal to 100 °C, preferably lower than or equal to 70 °C. The temperature at which the reaction is conducted is preferably selected in two
- 25 stages. In the first stage, the reaction mixture is maintained at 30 °C -50 °C., preferably 39 ° - 41 °C. Reaction time for the first stage is preferably about 90-190 minutes to form an intermediate polyaminochlorohydrin. Then the reaction temperature is gradually increased to 55 ° -75 °C. such that the intermediate polyaminochlorohydrin is controllably cross-linked to a determined
- 30 level. The second stage is continued until the viscosity of the reaction mixture reaches the desired level (preferably level M to N on a Gardner-Holdt viscosity scale).

- Broadly speaking, the reaction can be carried out neat or in an aqueous solution of up to 57 wt % in water. Preferably, the polyaminoamide is reacted
- 35 with epichlorohydrin in an aqueous solution of 52-57 wt % in water that is, a solution of 43-48 wt % total solids (the weight percentage of the solution that is

solubilized solid material), more preferably about 45 wt % total solids. Reaction time varies depending on the temperature, with lower temperatures taking longer times. The typical composition of these resins is 12.5% (10-40% solids).

However, due to the cost of transporting water, companies have tried to produce resin solutions of higher concentration. It appears that at least one of the main issues making such concentrated solutions difficult to prepare is their high content of dichloropropanol so the level of this impurity is exceeded in the final application.

Reaction is preferably carried out until all, or substantially all of the available amine groups on the polyaminoamide are reacted with epichlorohydrin. Generally, reaction times vary between about 1 and 19 hours, preferably between 3 and 6 hours. Because the reaction is exothermic, the epichlorohydrin is added slowly over time to the polyaminoamide to allow for more effective heat transfer from the reaction medium. Heat transfer from the reaction medium can be accomplished according to known procedures, such as immersing the reaction vessel in a refrigerated environment, e.g., an ice bath, or passing refrigerated coils inside the reaction vessel.

The reaction is usually carried out in aqueous solution to moderate the reaction. The pH adjustment is usually not necessary but since the pH decreases during the reaction, it may be desirable in some cases, to add alkali to combine with at least some of the acid formed.

In the reaction, it is preferred to use sufficient epichlorohydrin to convert the entire secondary amine group to tertiary amine groups. The molar ratio between epichlorohydrin and the secondary amine groups is usually higher than or equal to 0.1, preferably higher than or equal to 0.5, and more preferably higher than or equal to 1. That molar ratio is usually lower than or equal to 10, preferably lower than or equal to 5, and more preferably lower than or equal to 2.

The reaction between the polyamide and epichlorohydrin can also be carried in the presence of a quaternizing agent, the conditions of reaction and the reactants, except for the inclusion of the quaternizing agent, being essentially the same as described above. In a preferred procedure, the epichlorohydrin is first added to an aqueous solution of the polyamide at a temperature from 45 to 55 °C. The reaction mixture is then heated to a temperature from about 60 to 100 °C, and preferably from about 50 to 80 °C, depending on the rate of the polymerization desired. After a suitable time at that temperature, i.e., 0 to 100 min, a time after which the epoxy group of the epichlorohydrin have reacted with the secondary

amine groups of the polyamide, the quaternizing agent is added and the reaction mixture heated, preferably at a temperature from 60 °C to 80 °C. The pH of the reaction mixture is then reduced to 4, preferably between 2 and 3 with any suitable acid such as sulphuric, hydrochloric formic and the like. The amount of quaternizing agent should be sufficient to convert from 25 % to 75 %, preferably 50 % of the tertiary amine group to quaternary group.

The quaternizing agent may be any compound capable of quaternizing a tertiary nitrogen atom in an aqueous medium. In general these compounds are characterized by having as a principal part of their structure an alkyl group or substituted alkyl group which is readily available for alkylation under the conditions herein described. These include the lower alkyl esters of mineral acids such the halides, sulfates and phosphates, and substituted alkyl halides. Illustrative of these compounds which may be used are dimethyl, diethyl and dipropylsulfate, methyl chloride, methyl iodide, methyl bromide, ethyl bromide, propyl bromide, the mono-, di- or tri-methyl, ethyl and propyl phosphates, 1,3-dichloropropanol-2 and 1-chloroglycerol. Certain aromatic compounds may also be used like benzyl chloride and methyl p-toluene sulfonate.

The above products resulting from the reaction between epichlorohydrin and the polyamide can be further cross polymerized by treatment with a sodium carbonate or sodium hydroxide solution at a pH between 10.5 and 12.

3.4. Uses

These resins are used in papers that will get wet such as paper towels, tea bags, coffee filters, milk cartons, meat wrapping, wallpaper. They can also be used in the production of high fructose corn syrup and to prevent wool from shrinking.

4. CATIONIZATION AGENTS

4.1. General

The product containing epichlorohydrin according to the invention can be used for the manufacture of cationization agents.

By cationization agent, one intends to denote a quaternary ammonium salt, the chemical formula of which contains at least one group selected from 2,3-epoxypropyl, 3-chloro-2-hydroxypropyl, and their combination, and which is not a polymer.

Cationization agents are often quaternary ammonium salt containing a glycidyl or a 3-chloro-2-hydroxypropyl group attached to the nitrogen atom. The

cationization agent can be isolated as solids or as solution in water or in organic solvents.

Examples of cationization agents are 3-chloro-2-hydroxypropyl trimethylammonium chloride and glycidyl trimethyl ammonium chloride.

5 4.2. Co-reactants

In the application according to the invention, the product containing epichlorohydrin is usually subjected to a reaction with an amine, an amine salt, or a mixture thereof.

10 The amine is preferably a tertiary amine and the amine salt is preferably a tertiary amine salt.

The tertiary amine salt is for instance a salt obtained by treating an amine with an acid, preferably an inorganic acid, like for instance hydrochloric or sulphuric acid.

15 The tertiary amine may be represented by the formula
$$R^{31}-N(R^{32})-R^{33} \quad (XVII)$$

wherein R^{31} , R^{32} and R^{33} can be selected from the group consisting of alkyl, cycloalkyl, alkene, aryl, aralkyl, alkylaryl, two of them being possibly joined to form a ring and containing from 1 to 25 carbon atoms. The group attached to the nitrogen can be linear or substituted, saturated or unsaturated.

20 If all three of R^{31} , R^{32} and R^{33} are the same, they preferably each should not contain more than 4 carbon atoms. If all three of R^{31} , R^{32} and R^{33} are not the same and if R^{33} contains up to 18 carbon atoms, the R^{31} and R^{32} should preferably be of the group consisting of methyl and ethyl. If R^{31} and R^{32} are joined to form a ring, then R^{33} should preferably be from the group consisting of methyl and
25 ethyl.

Examples of suitable tertiary amines are triethylamine, N-methyl and N-ethylmorpholine, N-ethyl and N-methylpiperidine and methyl diallylamine, trimethylamine, dimethylbenzylamine, dimethyldodecylamine, dimethylstearylamine, dimethylaniline, tri-npropylamine.

30 It is particularly preferred that the tertiary amine possess two methyl groups attached to the nitrogen, like for instance, trimethylamine, dimethylbenzylamine, dimethyldodecylamine, dimethylstearylamine, and dimethylaniline.

The amine salt is preferably a salt obtained by reaction between the above described amines with hydrochloric or sulfuric acid, preferably with hydrochloric
35 acid.

4.3. Processes

The reaction between the product containing epichlorohydrin and the amine or the amine salt can be carried out by any process known in the art such as those described in US 2,876,217 the content of which is incorporated herein by
5 reference.

The reaction is generally carried out in the liquid phase, possibly in the presence of a solvent. The solvent may be selected from water, an organic solvent e.g. an alcohol, a ketone, an ester or an aliphatic hydrocarbon, preferably miscible with water, or mixtures thereof. Water is preferred. Monoalcohols, like
10 methanol, ethanol, n-propanol, isopropanol and butanol are preferred organic solvents, with methanol being particularly preferred.

The content of epichlorohydrin in the solvent is usually higher than or equal to 0.1 mol/l, often higher than or equal to 0.5 mol/l, frequently higher than or equal to 1.0 mol/l, particularly higher than or equal to 2 mol/l, specifically higher
15 than or equal to 5 mol/l and sometimes higher than or equal to 10 mol/l. That epichlorohydrin content is usually lower than 20 mol/l.

The content of amine or amine salt in the solvent is usually higher than or equal to 0.1 mol/l, often higher than or equal to 0.5 mol/l, frequently higher than or equal to 1.0 mol/l, particularly higher than or equal to 2 mol/l, specifically
20 higher than or equal to 5 mol/l and sometimes higher than or equal to 10 mol/l. That amine or amine salt content is usually lower than 20 mol/l.

The molar epichlorohydrine/amine or amine salt ratio is usually higher than or equal to 0.1, preferably higher than or equal to 0.5, more preferably higher than or equal to 1 and most preferably higher than or equal to 1.2. That ratio is
25 usually lower than or equal to 10, more preferably lower than or equal to 5 and most preferably lower than or equal to 2.

The temperature at which the reaction is carried out is generally higher than or equal to 0 °C, preferably higher than or equal to 10 °C, more preferably higher than or equal to 25 °C and most preferably higher than or equal to 40 °C. That
30 temperature is usually lower than or equal to 100 °C, preferably lower than or equal to 80 °C, more preferably lower than or equal to 60 °C, and most preferably lower than or equal to 50 °C.

The pressure at which the reaction is carried out is generally higher than or equal to 0.1 bar absolute, preferably higher than or equal to 0.2 bar, more
35 preferably higher than or equal to 0.5 bar and most preferably higher than or equal to 1 bar. That pressure is usually lower than or equal to 20 bar, preferably

lower than or equal to 10 bar, more preferably lower than or equal to 5 bar, and most preferably lower than or equal to 2 bar.

The duration of the reaction is generally higher than or equal to 10 min absolute, preferably higher than or equal to 20 min, more preferably higher than or equal to 30 min and most preferably higher than or equal to 60 min. That duration is usually lower than or equal to 72 h, preferably lower than or equal to 60 h, more preferably lower than or equal to 48 h, and most preferably lower than or equal to 10 h.

When an amine salt or a mixture of an amine and of an amine salt is used, the pH of the reaction is usually at least 5, and preferably at least 6. That pH is usually at most 9, preferably at most 8.

In a first embodiment, the manufacturing procedure usually involves the mixing of the amine, epichlorohydrin and water, followed by heating at the desired temperature for the desired duration. The aqueous solution is further concentrated by vacuum distillation. The temperature of distillation is as described for the reaction. The distillation pressure is usually lower than or equal to 100 mbar absolute, preferably lower than or equal to 75 mbar and most preferably lower than or equal to 50 mbar. That pressure is usually higher than or equal to 1 mbar absolute.

In a second embodiment, an aqueous solution of the amine is first added to hydrochloric acid until a pH between 8 and 9 is obtained. Epichlorohydrin is further added to the resulting solution and the mixture stirred at the desired temperature for the desired duration. The solution is further distilled under vacuum to the solid 3-chloro-2-trialkylammonium chloride. The solid can be used as such or further cyclized into the glycidyl derivative by reaction with sodium hydroxide in aqueous solution.

In a third embodiment, an amine hydrochloride is dispersed in water. Sufficient sodium hydroxide is added to raise the pH from around 3 to around 8. Epichlorohydrin is further added to the resulting solution and the mixture stirred at the desired temperature for the desired duration. The chlorohydrin group is further cyclized into the glycidyl derivative by reaction with sodium hydroxide in aqueous solution.

In the various embodiments, the aqueous solution obtained at the end of the reaction can be further concentrated by vacuum evaporation or distillation at a temperature of less than 50 °C in order to obtain a slurry containing at least 90 % by weight of solid, preferably at least 95 % by weight. A water miscible alcohol

having 3 to 4 carbon atoms, such as isopropanol, n-propanol, and tert-butanol, preferably isopropanol, is added to the slurry, such as to obtain an alcohol content from 10 to 70 % wt, preferably from 25 to 50 % wt, based on the total weight of the resulting alcohol-water slurry. The precipitated solids are then recovered by
5 filtration or by other means suitable for removing solids from liquid. The solid may optionally be washed with additional volumes of alcohol or another non-solvent and/or dried to remove any trace of water and alcohol.

The reaction product can be recovered as an aqueous solution, or a solid after further treatments, e.g. distillation of the solvents under vacuum, treatment
10 of the solution with an acid or a base.

4.4. Uses

Cationization agents are mainly used in the cationization of starch to be utilized by the paper industry for processing of high quality paper grades or for cationization of textile for dye fixing.

15 5. FLAME RETARDANTS

5.1. General

The product containing epichlorohydrin according to the invention can be used for the manufacture of flame retardants additives.

The product containing epichlorohydrin according to the invention can
20 preferably be used for the manufacture of phosphorus containing flame retardants additives.

By phosphorus containing flame retardants, one intends to denote a compound, the chemical formula of which contains at least one phosphorus atom and at least one group selected from 2,3-epoxypropyloxy, 3-chloro-2-
25 hydroxypropyl, and the combination of at least two of them.

Examples of chemical formulas for such compounds are presented in Figure 7.

5.2. Co-reactants

In the application according to the invention, the product containing
30 epichlorohydrin is usually subjected to a reaction with an inorganic or organic compound containing phosphorus. Such inorganic compounds are for instance a phosphoric acid (ortho, pyro and polyphosphoric acid), a phosphoric acid salt and a phosphorus oxychloride. Examples of organic compounds containing phosphorus are for instance phosphoric acid esters (of ortho, pyro and
35 polyphosphoric acid), phosphonic acids, their esters or their salts, phosphinic acids, their esters or their salts and phosphine oxides.

The compounds containing phosphorus may be represented by the general formula



or



wherein X^1 , X^2 , X^3 can independently be selected from a halogen, H, OH, OR^{41} , R^{41} , $\text{OR}^{42}(\text{OH})_n$ and $\text{R}^{42}(\text{OH})_n$

wherein the halogen is preferably selected from bromine and chlorine and is preferably chlorine

wherein R^{41} is an alkyl, an aryl, an alkylaryl, an arylalkyl, a cycloalkyl radical containing from 1 to 20 carbon atoms, often from 3 to 12 carbon atoms wherein R^{42} is an alkylene, arylene, alkylarylene, arylalkylene, cycloalkylene radical containing from 1 to 20 carbon atoms, often from 3 to 12 carbon atoms wherein n is an integer equal to 1 or 2

wherein at least two of X^1 , X^2 , X^3 can be joined to form a ring, preferably with the phosphorus atom.

Examples of phosphorus containing compounds are tris(1,3-dichloro-2-propyl) phosphate, tris(1-chloro-2-propyl) phosphate, tris(2,3-dichloropropyl) phosphate, isobutylbis(hydroxypropyl)phosphine oxide, 10-(2',5'-dihydroxyphenyl)-9,10-dihydro-9-oxa-10-phosphaphenanthrene-10-oxide (DHQEP), 9,10-dihydro-9-oxa-10-phosphaphenanthrene-10-oxide (DOPO), the reaction products of DOPO and 4,4'-dihydroxybenzophenone (DOPO2OH and 2DOPO-PhOH,II as represented in Liu Y.L., Journal of Polymer Science: Part A: Polymer Chemistry, 2002, Vol. 40, 359-368 and Journal of Applied Polymer Science, 2002, Vol. 83, 1697-1701).

5.3. Processes

The reaction between the product containing epichlorohydrin and the phosphorus containing compound is carried out by any process known in the art such as those described in Journal of Applied Polymer Science, 2002, Vol. 83, 1697-1701).

The reaction is generally carried out in the liquid phase, possibly in the presence of a solvent. The solvent may be selected from water, an organic solvent e.g. an alcohol, or mixtures thereof. An alcohol is preferred. Monoalcohols, like methanol, ethanol, n-propanol, isopropanol and butanol are preferred organic solvents, with ethanol being particularly preferred.

The content of epichlorohydrin in the reaction mixture is usually higher than or equal to 0.1 mol/l, often higher than or equal to 1.0 mol/l, frequently higher than or equal to 2 mol/l and particularly higher than or equal to 5 mol/l. That epichlorohydrin content is usually lower than 20 mol/l.

5 The content of the phosphorus containing compound in the reaction mixture is usually higher than or equal to 0.1 mol/l, often higher than or equal to 0.2 mol/l and frequently higher than or equal to 0.5 mol/l. That content is usually lower than 2 mol/l.

10 The molar epichlorohydrin/ phosphorus containing compound ratio is usually higher than or equal to 1, preferably higher than or equal to 2, more preferably higher than or equal to 5 and most preferably higher than or equal to 10. That ratio is usually lower than or equal to 50, more preferably lower than or equal to 30 and most preferably lower than or equal to 20.

15 The temperature at which the reaction is carried out is generally higher than or equal to 0 °C, often higher than or equal to 5 °C, frequently higher than or equal to 10 °C, particularly higher than or equal to 20 °C and more specifically higher than or equal to 50 °C. That temperature is usually lower than or equal to 100 °C, preferably lower than or equal to 80 °C, more preferably lower than or equal to 60 °C, and most preferably lower than or equal to 30 °C.

20 The pressure at which the reaction is carried out is generally higher than or equal to 0.1 bar absolute, preferably higher than or equal to 0.2 bar, more preferably higher than or equal to 0.5 bar and most preferably higher than or equal to 1 bar. That pressure is usually lower than or equal to 20 bar, preferably lower than or equal to 10 bar, more preferably lower than or equal to 5 bar, and
25 most preferably lower than or equal to 2 bar.

30 The duration of the reaction depends on the temperature at which the reaction is carried out. That duration is generally higher than or equal to 10 min absolute, preferably higher than or equal to 1 h, more preferably higher than or equal to 10 min and most preferably higher than or equal to 24 h. That duration is usually lower than or equal to 72 h, preferably lower than or equal to 60 h, more preferably lower than or equal to 48 h, and most preferably lower than or equal to 30 h.

35 A basic compound, e.g., potassium hydroxide can be present in the reaction medium. This is generally the case when the phosphorus containing compound includes OH groups in the molecule. The molar basic compound/ phosphorus containing compound ratio is usually higher than or equal to 0.1, preferably

higher than or equal to 0.15, and most preferably higher than or equal to 0.2.
That ratio is usually lower than or equal to 5, more preferably lower than or equal to 3 and most preferably lower than or equal to 1.

An onium salt, preferably a quaternary ammonium or phosphonium salt,
5 more preferably a quaternary ammonium chloride, like for instance
benzyltrimethylammonium chloride, can be present in the reaction medium. This
is generally the case when the phosphorus containing compound is a phosphine
oxide. The onium/phosphorus containing compound ratio is usually higher than
or equal to 0.01, preferably higher than or equal to 0.05, and most preferably
10 higher than or equal to 0.1. That ratio is usually lower than or equal to 1, more
preferably lower than or equal to 0.5 and most preferably lower than or equal to
0.2.

The product of the reaction can be recovered by any means, e.g., filtration
and submitted to washing operations before being submitted to evaporation under
15 reduced pressure.

5.4. Uses

Flame retardants are usually used to inhibit the evolution of combustible
gases in various materials such as polymers, in particular in polyurethane foams.

6. DETERGENT INGREDIENTS

20 6.1. General

The product containing epichlorohydrin according to the invention can be
used for the manufacture of detergent ingredients. By detergent ingredient, one
intends to denote a compound, the chemical formula of which contains at least
one 3-sulfonate-2-hydroxy-propyloxy group. The compound can be an oligomer
25 or a polymer. An oligomer is a polymer with a number of repeat units in each
polymer molecule of less than 20.

By detergent ingredient, one intends to denote a polymer, at least one repeat
unit of which comprises at least one 2-hydroxypropylammonium group,
preferably a 2-hydroxypropylimidazolidium group.

30 The product containing epichlorohydrin according to the invention can
preferably be used for the manufacture of cationic monomers, polymers or
oligomers, anionic surfactants, for instance sulfonates based surfactants,
preferably alkyl glyceryl ether sulfonate surfactants, monomeric or oligomeric or
cationic cyclic amine based polymers.

6.2. Co-reactants

In the application according to the invention, when the detergent auxiliary is a sulfonate based surfactant, the product containing epichlorohydrin is usually subjected to a reaction with an aliphatic alcohol containing from 10 to 40 carbon atoms, preferably from 10 to 22 carbon atoms more preferably from 14 to 18 carbon atoms and most preferably from 16 to 18 carbon atoms. The alkyl chain may be branched or linear or ethoxylated, wherein when present, the branches comprise an alkyl moiety containing from 1 to 4 carbon atoms, such as methyl or ethyl.

In the application according to the invention, when the detergent ingredient is a cationic amine based polymer, the product containing epichlorohydrin is usually subjected to a reaction with an amine selected from the group consisting of linear alkylamines, branched alkylamines, cycloalkylamines, alkoxyamines, amino alcohols, cyclic amines containing at least one nitrogen atom in a ring structure, alkylenediamines, polyetherdiamines, polyalkylenepolyaminesamine.

Specific examples of the said amines are given above.

Cyclic amines containing at least one nitrogen atom in a ring structure are for example monoaminoalkylpiperazines, bis(aminoalkyl)piperazines, monoaminoalkylimidazoles, aminoalkylmorpholines, aminoalkylpiperidines and aminoalkylpyrrolidines. The monoaminoalkylpiperazines are for example 1-(2-aminoethyl)piperazine and 1-(3-aminopropyl)piperazine. Preferred monoaminoalkylimidazoles have 2 to 8 carbon atoms in the alkyl group. Examples of suitable compounds are 1-(2-aminoethyl)imidazole and 1-(3-aminopropyl)imidazole. Suitable bis(aminoalkyl)piperazines are for example 1,4-bis(2-aminoethyl)piperazine and 1,4-bis(3-aminopropyl)-piperazine. Preferred aminoalkylmorpholines are aminoethylmorpholine and 4-(3-aminopropyl)-morpholine. Other preferred compounds of this group are aminoethylpiperidine, aminopropylpiperidine and aminopropylpyrrolidine.

Cyclic amines with at least two reactive nitrogen atoms in the ring are for example imidazole, C-alkyl substituted imidazoles having 1 to 25 carbon atoms in the alkyl group such as 2-methylimidazole, 2-ethylimidazole, 2-propylimidazole, 2-isopropylimidazole and 2-isobutylimidazole, imidazoline, C-alkyl substituted imidazolines having 1 to 25 carbon atoms in the alkyl group and arylimidazolines such as 2-phenylimidazoline and 2-tolylimidazoline, piperazine, N-alkylpiperazines having 1 to 25 carbon atoms in the alkyl group such as 1-ethylpiperazine, 1-(2-hydroxy-1-ethyl)piperazine, 1-(2-hydroxy-1-

propyl)piperazine, 1-(2-hydroxy-1-butyl)piperazine, 1-(2-hydroxy-1-pentyl)piperazine, 1-(2,3-dihydroxy-1-propyl)piperazine, 1-(2-hydroxy-3-phenoxyethyl)piperazine, 1-(2-hydroxy-2-phenyl-1-ethyl)piperazine,

5 N,N'-dialkylpiperazines having 1 to 25 carbon atoms in the alkyl group for example 1,4-dimethylpiperazine, 1,4-diethylpiperazine, 1,4-dipropylpiperazine, 1,4-dibenzylpiperazine, 1,4-bis(2-hydroxy-1-ethyl)piperazine, 1,4-bis(2-hydroxy-1-propyl)piperazine, 1,4-bis(2-hydroxy-1-butyl)piperazine, 1,4-bis(2-hydroxy-1-pentyl)piperazine, and 1,4-bis(2-hydroxy-2-phenyl-1-ethyl)piperazine. Other cyclic amines with at least two reactive nitrogen atoms are melamine and
10 benzimidazoles such as 2-hydroxybenzimidazole and 2-aminobenzimidazole.

6.3. Processes

The reaction between the product containing epichlorohydrin and the alcohol is carried out by any process known in the art such as those described in US 5,567,359 and US 2006/0079433, the contents of which are incorporated
15 herein by reference.

The reaction is usually carried out at a temperature between 65 and 90 °C.

Typical molar ratios of alcohol:epichlorohydrin range from 1:1.24 to 1:4.02.

A catalyst is usually used when carrying out the reaction, for instance
20 stannic chloride. The mass ratio of initial alcohol:stannic chloride is generally of 100:0.67.

The duration of the reaction is usually between 0.25 and 1 h.

The epichlorohydrin/alcohol ratio and the duration can be adapted to the required degree of oligomerisation

25 Epichlorohydrin is usually slowly added to the alcohol-catalyst mixture.

The product of the reaction is a monomeric or oligomeric alkyl chloroglyceryl ether.

The alkyl chloroglyceryl ether is further converted into an alkyl glycidyl ether by reaction with a basic compound, preferably sodium hydroxide. That
30 reaction is usually carried out with a 35 % aqueous solution of sodium hydroxide at a temperature higher than 90 °C and for a molar ratio alcohol:NaOH of 1:1.5.

The alkyl glycidyl ether is further converted into an alkyl glyceryl surfactant by reaction usually with a mixture of sodium bisulfite and sodium sulfite, generally obtained by combining sodium meta-bisulfite with sodium
35 hydroxide.

The reaction between the product containing epichlorohydrin and the amine is carried out by any process known in the art such as those described in US 6,740,633 and US 2006/0052272, the contents of which are incorporated herein by reference.

5 The reaction is usually carried out at a temperature between 25 and 90 °C, in two steps the first one at a temperature between 40 and 60 °C and the second one between 90 and 100 °C.

Typical molar ratios of amine:epichlorohydrin range from 1:1 to 1:1.4.

The duration of the reaction is usually between 0.25 and 1 h.

10 The condensation product between the amine and epichlorohydrin is usually further quaternarized using alkyl halides, epoxides, chloroacetic acid, 2-chloroethanesulfonic acid, chloropropionic acid, epoxysuccinic acid, propane sulfone, 3-chloro-2-hydroxypropanesulfonic acid, dimethyl sulfate and/or diethyl sulfate, or oxidized by oxidation of the tertiary nitrogen atoms of the
15 condensation products to N-oxides.

6.4. Uses

Examples of detergent ingredients are surfactants or surface deposition enhancing materials. They are usually used as components of cleaning compositions for instance dishwashing, laundry compositions, shampoos and
20 synbars.

7. EPICHLOROHYDRIN ELASTOMERS

7.1. General

The product containing epichlorohydrin according to the invention can be used for the manufacture of epichlorohydrin elastomers.

25 By epichlorohydrin elastomer, one intends to denote a polymer, containing at least one type of repeat units, at least one type of repeat units containing at least one 2-chloromethylethoxy group. The polymer can be a homopolymer or a copolymer.

Examples of epichlorohydrin elastomers are homopolymers of
30 epichlorohydrin, copolymers of epichlorohydrin with an alkylene or phenylene oxide, and terpolymers of epichlorohydrin with an alkylene or phenylene oxide, and a glycidyl ether.

The alkylene oxide can be selected from styrene oxide, propylene oxide, ethylene oxide, butene-1 oxide, dodecene-1-oxide, and is preferably ethylene
35 oxide.

The glycidyl ether can be selected from alkyl and haloalkyl glycidyl ethers, for instance, 2-chloroethyl glycidyl ether and allyl glycidyl ether.

7.2. Co-reactants

5 In the application according to the invention, the product containing epichlorohydrin is usually subjected to a reaction with an alkylene or phenylene oxide or with an alkylene or phenylene oxide and a glycidyl ether or the epichlorohydrin is homopolymerized.

7.3. Processes

10 The reaction is carried out by any process known in the art such as those described in US 3,135,705, US 3,158,580, US 3,158,581, US 3,026,270 and US 3,341,491, the contents of which are incorporated herein by reference.

The reaction is usually carried out in solution in aliphatic or aromatic hydrocarbons, chlorinated hydrocarbons, or ether.

15 The weight ratio between epichlorohydrin and the alkylene oxide is usually between 20:80 and 90:10.

The reaction is preferably carried out in the presence of a catalyst formed by reacting R^{51}_3Al and water (thought to be $R^{51}_2Al-O-AlR^{51}_2$), where R^{51} can be selected from alkyl, cycloalkyl, aryl or alkaryl radical. The catalyst activity can be improved by the addition of acetylacetone. Some combinations of organozinc
20 and organomagnesium compounds, as well as other additives and chelating agents in combination with alkylaluminum compounds, are also effective catalysts.

The reaction can be carried out in a continuous process using a back-mixed reactor.

25 The temperature at which the reaction can be carried out is usually comprised between $-80\text{ }^{\circ}\text{C}$ and $250\text{ }^{\circ}\text{C}$, preferably between -80 and $150\text{ }^{\circ}\text{C}$, more preferably between -30 and $100\text{ }^{\circ}\text{C}$. A temperature between 25 and $50\text{ }^{\circ}\text{C}$ is particularly convenient

The homopolymer of epichlorohydrin and the copolymers can be further
30 cross-linked, e.g, by further reacting with a polyamine, or an amine in the presence of at least one agent from the group of sulfur, dithiocarbamates, thiuram sulfides and thiazoles, or with a metal compound selected from the group consisting of salts of aromatic carboxylic acids, aliphatic carboxylic acids, carbonic acid, phosphorous acid, silicic acid, and oxides of the metals of
35 Groups IIA, IIB and IVA of the periodic Table and at least one heterocyclic

compound selected from the group consisting of 2-mercaptoimidazolines and 2-mercaptopyrimidine.

7.4. Uses

- 5 The epichlorohydrin elastomers are generally used in specialty applications, like for instance automotive components (fuel pump diaphragms, emission control hoses, motor mounts, gaskets, seals and portable fuel tanks), in the aircraft industry, for specialty roofing membranes, coated fabrics, solvent storage containers, paper mill and printing roll and in a variety of oil specialties.

Examples

- 10 Five epichlorohydrin (ECH) samples have been used. Their compositions obtained by gas chromatography analysis are presented in Table 1.

Table 1

Component (g/kg)	ECH 1	ECH 2	ECH3	ECH4	ECH5
acetaldehyde	0.004	n.d	n.d	n.d.	n.d.
acrolein	< 0.001	0.003	0.003	n.d.	n.d.
2-propanol	< 0.001	n.d.	n.d.	n.d.	n.d.
3-chloro-1-propene	n.d.	n.d.	n.d.	n.d.	n.d.
allyl alcohol	0.001	< 0.001	< 0.001	n.d.	0.003
hydroxyacetone	0.094	0.018	0.018	0.006	0.006
chloroacetone + (3,3-dichloro-1-propene)	0.033	0.038	0.040	n.d.	0.024
1,2-dichloropropane	0.042	n.d.	n.d.	0.001	n.d.
2,3-dichloro-1-propene	0.005	n.d.	n.d.	0.004	n.d.
1-chloro-2, 3-epoxypropane (*)	> 998.464	> 999.474	> 999.045	> 999.503	> 999.865
1,3-dichloro-1-propene cis maj. + (C ₆ H ₁₄ O min.)	0.219	0.008	0.008	0.032	0.004
2-chloro-2-propene-1-ol	0.348	0.016	0.016	0.14	0.012
1,3-dichloro-1-propene trans	0.035	0.010	0.010	0.008	0.009
C ₅ H ₁₀ O / C ₄ H ₇ ClO	n.d.	n.d.	n.d.	0.014	0.001
C ₆ H ₁₂ O	n.d.	n.d.	n.d.	0.011	< 0.001
1,3-dichloropropane	0.002	0.34	0.34	0.005	0.030
Cyclopentanone	0.001	0.004	0.004	n.d.	0.004
dibromochloromethane	0.004	n.d.	n.d.	0.084	n.d.
C ₆ H ₁₀ O iso 1	0.003	n.d.	n.d.	0.009	< 0.001

Component (g/kg)	ECH 1	ECH 2	ECH3	ECH4	ECH5
C ₆ H ₁₀ O iso 2	0.012	n.d.	n.d.	0.009	0.001
1,2-epoxyhexane + (1,2,2-trichloropropane)	0.030	0.002	0.002	n.d.	0.001
C ₆ H ₁₀ O iso 3	0.004	n.d.	n.d.	0.031	0.001
dichloroepoxypropane	0.003	n.d.	n.d.	0.006	n.d.
1,3,3-trichloro-1-propene cis + 1,1,3- trichloropropene	0.012	n.d.	n.d.	0.004	n.d.
1,1,2-trichloropropane	0.211	0.001	0.001	0.025	0.007
chlorobenzene	0.011	< 0.001	< 0.001	0.001	0.007
1,3,3-trichloro-1-propene trans	0.015	n.d.	n.d.	0.012	0.001
1,2,3-trichloropropene trans	0.016	< 0.001	< 0.001	0.003	0.001
1,3-dichloro-2-propanol	0.111	0.023	0.024	0.017	0.008
1,2,3-trichloropropane	0.014	n.d.	n.d.	0.024	n.d.
1,2,3-trichloropropene cis	0.002	n.d.	n.d.	n.d.	n.d.
3-chloro-1,2-propanediol + 2,3-dichloro-1-propanol	0.13	< 0.001	0.001	n.d.	0.001
C ₆ H ₁₃ Br	n.d.	n.d.	n.d.	0.005	n.d.
C ₆ H ₁₀ Cl ₂ iso 1	n.d.	n.d.	n.d.	0.005	n.d.
C ₆ H ₁₀ Cl ₂ iso 2	n.d.	n.d.	n.d.	0.004	n.d.
methyl glycidyl ether	0.007	0.054	0.48	n.m.	n.m.
Unknowns (sum)	0.170	0.007	0.008	0.087	0.024

n.d. : not detected, n.m. : not measured

* : 1-chloro-2, 3-epoxypropane amount calculated on the basis of the total content of other organic components

Examples 1 to 10 (homopolymerization of ECH)

5 The tests have been carried out according to the following procedure with epichlorohydrin sample ECH1 (examples 1 to 3), ECH 2 (examples 4 to 6) and ECH 3 (examples 7 to 10). The quantities of chemicals are indicated in Table 2.

10 The polymerization of epichlorohydrin (ECH) has been carried out in the presence of the system tetraoctylammonium bromide(Noct₄Br)/triisobutyl aluminium (TiBA).

The epichlorohydrin has been dried over calcium hydride under vacuum for 24 h at 25 °C and further distilled.

The polymerization reactions have been carried out in pyrex vessels fitted with polytetrafluorethylene valves. The vessels have been evacuated under flame heating to remove residual moisture. After cooling to room temperature, the vessels have been cooled to $-30\text{ }^{\circ}\text{C}$ (ethanol/liquid nitrogen cooling bath) and toluene and epichlorohydrin, have been added under vacuum. After those additions, argon has been introduced in the vessel and tetraoctylammonium bromide and triisobutyl aluminium have been added to the vessel. This addition constituted the time zero of the reaction. After a given time under magnetic stirring at $-30\text{ }^{\circ}\text{C}$, the reaction has been stopped by adding 1-2 ml of ethanol to the vessel. Half of the volume of the reaction medium has then been submitted to evaporation after which the polymer has been recovered from the vessel.

The conversion has been obtained by comparing the weight of recovered polymer with the weight of added epichlorohydrin.

The theoretical molar weight (M_n th.) has been calculated on the basis of the quantity of tetraoctylammonium bromide.

The measured polymer molar weight (M_n exp) and the molar weight dispersion have been obtained by Gel Permeation Chromatography.

The tacticity of the polymer has been obtained by ^{13}C and ^1H NMR.

The results of the tests are summarized in Table 3.

Table 2

Example n°	ECH (ml)	Toluene (ml)	Noct ₄ Br (ml)	TiBA (ml)
1	4	10.2	2.15	0.71
2	4	10.2	2.15	0.71
3	3.4	9.9	0.91	0.30
4	4	10.2	2.15	0.71
5	4	10.2	2.15	0.71
6	4	11.6	1.08	0.35
7	4	10.2	2.15	0.71
8	4	10.2	2.15	0.71
9	3.6	11.4	0.97	0.43
10	4	11.6	1.08	0.35

Table 3

Example	Reaction time (h)	Con-version (mol %)	Mn th. (g/mol)	Mn exp. (g/mol)	Dis-persion	Tacticity
1	1	100	10000	10700	1.17	atactic
2	1	100	10000	10100	1.23	n.m.
3	2	100	20000	20200	1.17	n.m.
4	1	100	10000	16400	1.22	n.m.
5	1	100	10000	11200	1.20	atactic
6	1	100	20000	77700 (20%) 22200 (80%)	1.40 1.20	n.m.
7	1	80	8000	6800	1.17	n.m.
8	2	95	9500	12100	1.17	atactic
9	2	90	18000	24700	1.18	n.m.
10	6	94	18800	17650	1.17	n.m.

n.m. : not measured

Examples 13 to 15 (homopolymerization of ECH)

The tests have been carried out according to the following procedure with epichlorohydrin sample ECH1 (example 13), ECH 2 (example 14) and ECH 3 (example 15). The quantities of chemicals are indicated in Table 4.

The polymerization of epichlorohydrin (ECH) has been carried out in the presence of the system water/triethyl aluminium (TEA).

The procedure of example 1 has been followed except that TEA in solution in toluene and water have been added under argon to the vessel first evacuated and dried, left under magnetic stirring under vacuum for 30 min, before ECH in toluene has been added (time zero of the reaction). The polymerization has been carried out at a temperature of 25 °C for 12 h. The results have been summarized in Table 5

Table 4

Example n°	ECH (ml)	Toluene (ml)	H ₂ O (μl)	TEA (ml)
13	4	10	23	0.67
14	4	10	23	0.67
15	4	10	23	0.67

Table 5

Example	Reaction time (h)	Conversion (mol %)	Mn exp. (g/mol)	Dispersion	Tacticity
13	12	47	216000 7000	2.02 1.04	n.m.
14	12	50	285200 5850	3.51 1.08	atactic
15	12	55	357600 8100	3.45 1.31	atactic

n.m. : not measured

Example 16

Preparation of a product consisting predominantly in diglycidyl diether of Bisphenol A according to US 2,811,227

The apparatus employed was a thermostatised flask equipped with a mechanical stirrer, with a jacket containing a thermocouple and with a Dean-Stark separator surmounted by a water-cooled condenser. A pump was used to inject a caustic soda aqueous solution at a constant rate in the flask.

The reaction flask was initially charged with a mixture of bisphenol A (68.4 g, 0.3 mol) and the epichlorohydrin sample ECH4 coming from a propylene-chlorine plant (277.5 g, 3.0 mol). The analysis of the epichlorohydrin is given in Table 1. The trichloropropane content is of 0.049 g/kg. The mixture was heated at reflux under stirring to a temperature of 111°C. A 40 % aqueous solution of caustic soda (60.8 g, 0.6 mol) was introduced at a rate of 12 ml/h during 3.5 hour. The temperature of the mixture in the flask was maintained in the range 100 °C - 115 °C in order to assure a constant reflux. The epichlorohydrin rich organic phase decanted during the reaction as a lower phase in the separator was recycled regularly in the reaction flask and the aqueous rich phase collected as an upper phase in the separator was regularly drawn off. The heating was maintained for 15 min after the total introduction of the caustic soda solution to achieve the collect of the water phase in the decantor. 29.7 g of aqueous phase was collected with a composition given in Table 6.

The epichlorohydrin in excess was removed from the reaction mixture by distillation under a vacuum of 30 mbar and by a progressive heating of the mixture to 109°C. 156.1 g (1.7 mol) of epichlorohydrin was recovered in this step. The composition of the distillate is given in Table 6.

The salt was separated from the crude product (45.5 g) after addition of 567.2 g of toluene under agitation and by filtration. The cake of filtration was washed with 124.4 g of toluene. The toluene solutions were mixed and evaporated at 185°C under a pressure of 1 mbar.

5 659.4 g of toluene was recovered as the condensate of the evaporated fraction with a composition given in Table 6. The residual product of the evaporation (100.5 g) contained the diglycidyl ether of bis-phenol A as a major product and no trace of unconverted bis-phenol A (< 5 mg/kg). The residue contained 4.98 mol epoxy per kg and 1.52 % of hydrolysable chlorine.

10 Example 17

The trial was realized in the apparatus described in example 16.

The reaction flask was initially charged with a mixture of bisphenol A (68.4 g, 0.3 mol) and epichlorohydrin sample ECH 5 (277.5 g, 3.0 mol). The analysis of the epichlorohydrin is given in Table 1. The trichloropropane content is of 0.007 g/kg. The mixture was heated at reflux under stirring to a temperature of 119°C. A 40 % aqueous solution of caustic soda (60.8 g, 0.6 mol) was introduced at a rate of 12 ml/h during 3.5 hour. The temperature of the mixture in the flask was maintained in the range 102 °C – 119 °C in order to assure a constant reflux. The epichlorohydrin rich organic phase decanted during the reaction as a lower phase in the separator was recycled regularly in the reaction flask and the aqueous rich phase collected as an upper phase in the separator was regularly drawn off. The heating was maintained for 15 min after the total introduction of the caustic soda solution to achieve the collect of the water phase in the decantor. 54.5 g of aqueous phase was collected with a composition given in Table 6.

25 The epichlorohydrin in excess was removed from the reaction mixture by distillation under a vacuum of 30 mbar and by a progressive heating of the mixture to 118°C. 148.2 g (1.5 mol) of epichlorohydrin was recovered in this step. The composition of the distillate is given in Table 6.

30 The salt was separated from the crude product (47.8 g) after addition of 228.4 g of toluene under agitation and by filtration. The cake of filtration was washed with 97.3 g of toluene. The toluene solutions were mixed and evaporated at 180°C under a pressure of 1 mbar.

35 305.0 g of toluene was recovered as the condensate of the evaporation with a composition given in Table 6. The residual product of the evaporation (99.8 g) contained the diglycidyl ether of bis-phenol A as a major product and no trace of

unconverted bis-phenol A (< 5 mg/kg). The residue contained 4.93 mol epoxy per kg and 0.49 % of hydrolysable chlorine.

The High Performance Liquid Chromatography analyses of the residual products obtained in examples 16 and 17 are similar.

Table 6

Component	Example 16				Example 17		
	Epichlorohydrin evaporated (g/kg)	Water evaporated (mg/l)	Toluene evaporated (g/kg)		Epichlorohydrin evaporated (g/kg)	Water evaporated (mg/l)	Toluene evaporated (g/kg)
acetaldehyde	n.d.	2.9	n.d.		n.d.	1.3	n.d.
acrolein	n.d.	0.58	n.d.		0.002	0.42	n.d.
2-propanol	n.d.	< 0.05	n.d.		n.d.	0.3	n.d.
3-chloro-1-propene	0.001	n.d.	n.d.		n.d.	n.d.	n.d.
allyl alcohol	n.d.	n.d.	n.d.		0.001	0.2	n.d.
hydroxyacetone	0.016	n.d.	n.d.		0.002	n.d.	n.d.
chloroacetone + (3,3- dichloro-1-propene)	0.003	0.65	n.d.		0.002	0.53	n.d.
1,2-dichloropropane			n.d.		n.d.	n.d.	n.d.
2,3-dichloro-1-propene	0.005	0.07	n.d.		n.d.	n.d.	n.d.
1-chloro-2, 3-epoxypropane	principal product	(45g/kg)	1.6		principal product	(46g/kg)	3.3
1,3-dichloro-1-propene cis maj. + (C6H14O min.)	0.026	0.36	n.d.		0.003	n.d.	n.d.
2-chloro-2-propene-1-ol	0.19	0.12	n.d.		0.016	< 0.05	n.d.
1,3-dichloro-1-propene trans	0.007	< 0.05	n.d.		0.008	n.d.	n.d.
C ₅ H ₁₀ O / C ₄ H ₇ ClO	0.019	0.05	n.d.		0.001	n.d.	n.d.
C ₆ H ₁₂ O	0.022	0.28	n.d.		0.021	n.d.	n.d.
1,3-dichloropropane	0.001	n.d.	n.d.		0.03	< 0.05	n.d.
Cyclopentanone	n.d.	n.d.	n.d.		0.006	n.d.	n.d.
dibromochloromethane	0.080	n.d.	n.d.		n.d.	n.d.	n.d.

Component	Example 16					Example 17				
C ₆ H ₁₀ O iso 1	0.033	0.11	n.d.	n.d.	0.038	n.d.	n.d.	n.d.	n.d.	n.d.
C ₆ H ₁₀ O iso 2	0.040	0.31	n.d.	n.d.	0.001	n.d.	n.d.	n.d.	n.d.	n.d.
1,2-epoxyhexane + (1,2,2-trichloropropene)	n.d.	n.d.	n.d.	n.d.	0.001	n.d.	n.d.	n.d.	n.d.	n.d.
C ₆ H ₁₀ O iso 3	0.036	0.21	n.d.	n.d.	0.002	n.d.	n.d.	n.d.	n.d.	n.d.
dichloroepoxypropane	0.006	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.
1,3,3-trichloro-1-propene cis + 1,1,3-trichloropropene	0.006	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.
1,1,2-trichloropropene	0.005	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.
chlorobenzène	0.001	n.d.	n.d.	n.d.	0.008	n.d.	n.d.	n.d.	n.d.	n.d.
1,3,3-trichloro-1-propene trans	0.009	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.
1,2,3-trichloropropene trans	0.003	n.d.	n.d.	n.d.	0.001	n.d.	n.d.	n.d.	n.d.	n.d.
1,3-dichloro-2-propanol	3.4	143	0.38	0.002	2.5	111	0.074	n.d.	n.d.	n.d.
1,2,3-trichloropropene	0.022	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.
1,2,3-trichloropropene cis	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.
3-chloro-1,2-propanediol + 2,3-dichloro-1-propanol	0.13	5.9	0.064	0.071	4.1	0.033	n.d.	n.d.	n.d.	n.d.
C ₆ H ₁₃ Br	n.d.	< 0.05	0.005	n.d.	< 0.05	n.d.	n.d.	n.d.	n.d.	n.d.
C ₆ H ₁₀ Cl ₂ iso 1	0.009	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.
C ₆ H ₁₀ Cl ₂ iso 2	0.007	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.
methyl glycidyl ether	n.m.	n.m.	n.m.	n.m.	n.m.	n.m.	n.m.	n.m.	n.m.	n.m.
Unknowns (sum)	0.299	10.00	1.31	0.213	1.3	1.373	n.d.	n.d.	n.d.	n.d.

n.d. : not detected, n.m. : not measured

Example 18

A glass thermostated jacketed reactor having a working volume of 305 ml was supplied continuously with 47.2 wt% sodium hydroxide and with an aqueous mixture of dichloropropanol, a mixture prepared from glycerol and concentrated hydrochloric acid in the presence of an organic acid according to the International Application WO 2005/054167 filed by Solvay SA. The mixture contained 575 g of water/kg, 404.6 g of 1,3-dichloro-2-propanol/kg, 20.1 g of 2,3-dichloro-1-propanol/kg, 0.14 g of acrolein/kg, 0.13 g of epichlorohydrin/kg, 0.04 g of 1,2,3-trichloropropane/kg, 0.04 g of chloroacetone/kg and 0.03 g of an ether of crude formula $C_6H_{10}O_2Cl_2$ /kg. The sodium hydroxide was introduced at a flow rate of 262 g/h and the aqueous dichloropropanol mixture was introduced at a flow rate of 1180 g/h. The reaction medium was constantly maintained at 25°C with vigorous stirring. The liquid mixture exiting the reactor by continuous overflow was collected and then separated in batch mode in a glass funnel so as to obtain a first separated fraction and a second separated fraction. 3753 g of first separated fraction (MEL1) were subjected to a batch distillation under a vacuum of 193 mbar. The batch distillation was carried out using a round-bottomed flask equipped with a magnetic stirrer bar, a thermocouple to measure the temperature of the liquid and a plate distillation column surmounted by a device enabling part of the distillate to be refluxed at the top of the column. The glass plate column comprised 5 plates having a diameter of 30 mm, pierced by an internal aperture 10 mm diameter central hole for the flow of liquid and three rows of small holes having a diameter of around 0.8 mm, spaced at regular intervals of less than 1 mm between each hole, placed in an arc over three quarters of the circumference. The spacing between the plates was 30 mm. The column was adiabatic (glass jacket under vacuum). A thermocouple placed in the top of the distillation column enabled the temperature of the gas phase distilled to be measured. The distillate was collected in a funnel with a stopcock. A first distillation fraction was collected between 49°C and 67°C and gave, after separation, 425 g of an organic phase (D1 org) and 159 g of an aqueous phase (D1 aq). The organic phase (D1 org) was combined with the contents of the boiler to give the mixture (MEL2) which was then distilled at a temperature of 187°C. A second distillation fraction was collected between 66°C and 67°C and resulted, after separation, in 244 g of an organic phase (D2 org) and 11.5 g of an aqueous phase (D2 aq). A main distillate of 2082 g of epichlorohydrin at

999.5 g/kg was then collected (D3) at a temperature of 67°C. The mixture constituting the final boiler (MEL3) weighed 1226 g and only contained a very low fraction of epichlorohydrin implemented. The organic phase D2 org and the boiler MEL3 could be recycled to the distillation operations in order to recover, 5 for enhanced value, epichlorohydrin and a mixture of 1,3-dichloro-2-propanol and 2,3-dichloro-1-propanol respectively. The compositions (g/kg) used and obtained in the distillation operations are described in Table 7.

Table 7

	MEL1	D1 org	D1 aq	MEL2	D2 org	D2 aq	D3	MEL3
Acrolein	0.2	0.61	0.13	0.076	0.99	0.12	0.050	0.006
Acetone	0.006	0.024	0.02	< 0.005	0.027	0.01	< 0.01	< 0.005
Isopropanol	0.032	0.124	n.d.	0.014	0.15	n.d.	< 0.005	n.d.
2-Chloropropane	0.047	0.021	n.d.	< 0.005	0.012	n.d.	n.d.	n.d.
Allyl alcohol		0.003	n.d.	n.d.	0.003	n.d.	n.d.	n.d.
2,3-Epoxybutane	< 0.005	0.008	n.d.	n.d.	0.010	n.d.	n.d.	n.d.
C ₄ H ₈ O	< 0.005	0.010	n.d.	n.d.	0.012	n.d.	n.d.	n.d.
2-Butanone	< 0.005	0.003	n.d.	n.d.	0.005	n.d.	n.d.	n.d.
Hydroxyacetone	n.d.		n.d.	n.d.	0.001	n.d.	n.d.	n.d.
Chloroethanol	n.d.	0.005	n.d.	n.d.	0.001	n.d.	n.d.	n.d.
Chloroacetone	0.039	0.025	n.d.	0.039	0.034	0.03	0.05	0.019
Epichlorohydrin	653	982	46	666	989	36	999.5	29
Glycidol	0.06	0.000	n.d.	0.07	n.d.	n.d.	n.d.	0.24
2-chloro-2-propen-1-ol	< 0.005	0.005	0.16	< 0.005	0.008	0.04	< 0.01	0.005
cis-1,3-Dichloropropene	n.d.	0.003	0.03	< 0.005	0.003	0.02	< 0.01	< 0.005
trans-1,3-Dichloropropene	n.d.	0.005	n.d.	< 0.005	0.009	n.d.	< 0.01	< 0.005
1,1,1-Trichloropropane	< 0.005	n.d.	n.d.	< 0.005	n.d.	n.d.	n.d.	0.002
Cyclopentanone	0.021	n.d.	n.d.	0.023	n.d.	n.d.	< 0.01	0.021
3-Chloro-1-propanol	0.013	0.000	n.d.	0.020	n.d.	n.d.	n.d.	0.016
cis-1,3,3-Trichloropropene	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	n.d.	< 0.005
C ₄ H ₇ ClO ₂	n.d.	0.000	n.d.	n.d.	n.d.	n.d.	n.d.	< 0.005
Ethylbenzene	< 0.005	0.000	n.d.	n.d.	n.d.	n.d.	n.d.	< 0.005
1,3-Dichloropropan-2-ol	251	0.364	0.27	271	0.013	0.82	0.010	789
2-Methyl-2-cyclopenten-1-one	n.d.	n.d.	n.d.	< 0.005	n.d.	n.d.	n.d.	< 0.005

	MEL1	D1 org	D1 aq	MEL2	D2 org	D2 aq	D3	MEL3
1,2,3-Trichloropropane	0.16	n.d.	n.d.	0.018	n.d.	n.d.	n.d.	0.015
2,3-Dichloro-1-propanol + 3-chloro-1,2-propanediol	56	1.94	36.42	61	0.046	21	n.d.	174
Phenol	0.011	n.d.	n.d.	0.012	n.d.	n.d.	n.d.	0.035
C ₆ H ₈ O ₂	< 0.005	n.d.	n.d.	< 0.005	n.d.	n.d.	< 0.01	0.008
C ₆ H ₁₂ OC ₂	0.056	n.d.	n.d.	0.060	n.d.	n.d.	n.d.	0.051
3,5-Dimethyl-2-cyclohexen-1-one	0.011	n.d.	n.d.	0.012	n.d.	n.d.	n.d.	0.035
C ₆ H ₉ Cl ₃ O ₂	0.031	n.d.	n.d.	0.034	n.d.	n.d.	n.d.	0.102
1-Phenoxy-2-propanone	0.88	n.d.	n.d.	0.078	n.d.	n.d.	n.d.	1.754
C ₆ H ₁₀ Cl ₂ O ₂	0.076	0.002	n.d.	0.101	n.d.	n.d.	n.d.	0.325
C ₉ H ₉ Cl ₃	< 0.005	n.d.	n.d.	< 0.005	n.d.	n.d.	n.d.	0.012
C ₆ H ₁₁ O ₂ Cl ₃	0.74	n.d.	n.d.	0.81	n.d.	n.d.	n.d.	2.95
C ₉ H ₁₅ O ₂ Cl ₂ +C ₉ H ₁₇ O ₄ Cl ₃	< 0.005	n.d.	n.d.	< 0.005	n.d.	n.d.	n.d.	0.56
Sum of unknowns	0.27	0.07	0.16	0.31	0.08	n.d.	n.d.	1.07
Methyl glycidyl ether	0.02	n.d.	n.d.	0.03	0.03	n.d.	0.04	
H ₂ O	37	14.0	n.d.	2.32	9.9	n.d.	0.32	0.33

n.d. = not detected

C L A I M S

1. Product containing epichlorohydrin and at least one alkyl glycidyl ether in an amount of less than 0.1 g/kg of product.
2. Product according to claim 1 wherein the content of epichlorohydrin is
5 higher than or equal to 900 g/kg of product.
3. Product according to claim 1 or 2, wherein the alkyl glycidyl ether is methyl glycidyl ether.
4. Product according to any of claims 1 to 3 being obtained by
dehydrochlorination of a composition containing dichloropropanol and at least
10 one chloroalkoxypropanol in an amount of less than or equal to 0.1 g/kg of composition.
5. Product according to claim 4 wherein the chloro alkoxy propanol is selected from 2-chloro-3-alkoxy-propane-1-ol, 1-chloro-3-alkoxy-propane-2-ol and mixtures thereof.
- 15 6. Product according to claims 4 or 5 wherein the composition containing dichloropropanol is obtained by hydrochlorination of a compound containing glycerol and at least one glycerol alkyl ether in an amount of less than or equal to 0.6 g/kg of compound.
7. Process for producing the product according to any of claims 1 to 6
20 comprising the following steps:
 - (a) the compound containing glycerol is reacted with hydrogen chloride in the presence of a carboxylic acid, in order to obtain a composition containing dichloropropanol and at least one chloro alkoxy propanol in an amount of less than or equal to 0.1 g/kg of composition
 - 25 (b) the composition containing dichloropropanol obtained in step (a) is further reacted with a basic agent in order to obtain a product containing epichlorohydrin and at least one alkyl glycidyl ether in an amount of less than 0.1 g/kg of product.
8. Process according to claim 7 comprising in addition the following steps:

(c) a vegetable fat or oil is reacted with an alcohol to obtain the compound containing glycerol, under such conditions that ethers of glycerol are formed and are not separated from glycerol,

5 (d) the compound containing glycerol obtained in step (a) is further subjected to at least one treatment, optionally under reduced pressure, of evaporative concentration, of evaporative crystallization, of distillation, of fractional distillation, of stripping or of liquid-liquid extraction, in order to obtain a compound containing glycerol and at least one glycerol alkyl ether in an amount that is preferably lower than or equal to 0.6 g/kg.

10 9. Use of the product containing epichlorohydrin according to any of claims 1 to 6 in the manufacture of epoxy derivatives such as epoxy resins, glycidyl ethers, glycidyl esters, glycidyl amides and imides, of products which will be used in food and drink applications such as coagulants and wet-strength resins, of cationization agents, of flame retardants, of products which will be used as
15 detergent ingredients, and of epichlorohydrin elastomers.

10. Use according to claim 9 wherein the product containing epichlorohydrin is subjected to a reaction with a compound containing at least one active hydrogen atom, selected from monoalcohols, monocarboxylic acids, polyols, polyamines, amino alcohols, polyimides and amides, polycarboxylic
20 acids, and mixtures thereof, in order to obtain an epoxy resin or a glycidyl ether or a glycidyl ester or a glycidyl amide or a glycidyl imide.

11. Use according to claim 9 wherein the product containing epichlorohydrin is reacted with ammonia, an amine, a polyaminoamide or a polyimine in order to obtain a product used as a coagulant ; or wherein the
25 product containing epichlorohydrin is reacted with a polyamine, a polyamide or a polyaminoamide in order to obtain a wet-strength resin.

12. Use according to claim 9 wherein the product containing epichlorohydrin is reacted with an amine, an amine salt, or a mixture thereof in order to obtain a cationization agent.

30 13. Use according to claim 9 wherein the product containing epichlorohydrin is reacted with a compound selected from phosphoric acid, a phosphoric acid salt, a phosphorus oxychloride, a phosphoric acid ester, a

phosphonic acid, a phosphonic acid ester, a phosphonic acid salt, a phosphinic acid, a phosphinic acid ester, a phosphinic acid salt, a phosphine oxide, a phosphine, or a mixture thereof, in order to obtain a flame retardant.

14. Use according to claim 9 wherein the product containing
- 5 epichlorohydrin is reacted with a monoalcohol containing from 12 to 16 carbon atoms or an ethoxylated alcohol or with an amine selected from the group consisting of linear alkylamines, branched alkylamines, cycloalkylamines, alkoxyamines, amino alcohols, cyclic amines containing at least one nitrogen atom in a ring structure, alkylenediamines, polyetherdiamines,
- 10 polyalkylenepolyaminesamine in order to produce a detergent ingredient.

15. Use according to claim 9 wherein the product containing epichlorohydrin is reacted with an alkylene or phenylene oxide or with an alkylene or phenylene oxide and a glycidyl ether or homopolymerized in order to obtain an epichlorohydrin elastomer.