

[DESCRIPTION]

[TITLE OF INVENTION]

LOW WATER CONTENT SOFT LENS FOR EYE, AND METHOD FOR PRODUCING
THE SAME

[Technical Field]

[0001]

The present invention relates to a low water content soft lens for eye and a method for producing the same.

[Background Art]

[0002]

Typical examples of a commercially available soft lens for eye include a soft contact lens. A hydrogel material having a water content of about 25 to 80% is commonly used in the commercially available soft contact lens. However, since the low water content soft contact lens made of the hydrogel material contains water, there arises a phenomenon in which water is vaporized from the contact lens. Thereby, certain fixed proportions of contact lens wearers feel dry more strongly as compared with the case of the naked eye, and thus feel uncomfortable. Among these contact lens wearers, some persons complain a condition of so-called contact lens-related dry eye. Since a water-containing soft contact lens made of a hydrogel material is likely to be contaminated with components in a lacrimal fluid and also contains a large amount of water, there was also a risk of the growth of bacteria.

[0003]

There has been known as, a highly oxygen permeable low water content soft contact lens, for example, a silicone rubber lens obtained by a method of adding a platinum-based catalyst to a mixture of polydimethylsiloxane in which both ends of the molecular chain are blocked with a vinylmethylsilyl group, and methyl hydrogen polysiloxane, followed by heat-curing using a molding method (Patent Literature 1). Patent Literatures 2 to 6 disclose a highly oxygen permeable contact lens material composed mainly of polysiloxane having a plurality of polymerizable functional groups.

[0004]

Patent Literature 6 discloses a contact lens material made of a polymer obtained by polymerizing a difunctional organosiloxane macromer alone, or a polymer obtained by copolymerizing a difunctional organosiloxane macromer with the other monomers, and also discloses, as a monomer to be used in copolymerization, an acrylic acid fluoroalkyl ester or a methacrylic acid fluoroalkyl ester, and an acrylic acid alkyl ester or a methacrylic acid alkyl ester.

[0005]

However, the following problems also lie in a conventional highly oxygen permeable low water content soft contact lens. First, a silicone rubber lens has such a drawback that a hydrophilized layer formed so as to improve hydrophobicity of

the surface of the lens is peeled, or adhesion of the lens to the cornea occurs due to too large resilience, and thus the silicone rubber lens had not widely been put into practice.

[0006]

A material composed mainly of polysiloxane having a plurality of polymerizable functional groups has high oxygen permeability and also has flexibility, and the material is considered to be one of materials which are suitable for a contact lens. However, since tackiness is left on the surface of the lens after polymerization, the lens may adhere to the cornea and is also insufficient in balance between flexibility of the lens and mechanical properties such as folding resistance.

[0007]

There have been known various methods for modification of a surface of a soft lens for eye. Among these methods, there is known a method in which layers of two or more kinds of polymer materials are coated and accumulated in a layer by layer fashion (Patent Literatures 7 to 9). Among these methods, a method of alternately forming layers made of two polymer materials, each having an opposite electric charge, in a layer by layer fashion by coating is called an LbL method, and it is considered that each layer of the material is noncovalently bonded to the other layer made of a different material. However, the highly oxygen permeable soft lens for eye in which utility of this method is clearly shown is made only of a silicone hydrogel material, and

utility to the low water content soft lens for eye has not been known. Conventional LbL coating was carried out to obtain a multi-layered structure constituted from about 4 to 20 layers, and thus the production process may increase, to cause an increase in production costs.

[Citation List]

[Patent Literature]

[0008]

[Patent Literature 1]

Japanese Unexamined Patent Publication (Kokai) No.

54-81363

[Patent Literature 2]

Japanese Unexamined Patent Publication (Kokai) No.

54-24047

[Patent Literature 3]

Japanese Unexamined Patent Publication (Kokai) No.

56-51715

[Patent Literature 4]

Japanese Unexamined Patent Publication (Kokai) No.

59-229524

[Patent Literature 5]

Japanese Unexamined Patent Publication (Kokai) No.

2-188717

[Patent Literature 6]

Japanese Unexamined Patent Publication (Kokai) No. 5-5861

[Patent Literature 7]

Kohyo (National Publication of Translated Version) No. 2002-501211

[Patent Literature 8]

Kohyo (National Publication of Translated Version) No. 2005-538418

[Patent Literature 9]

Kohyo (National Publication of Translated Version) No. 2009-540369

[Summary]

[Technical Problem]

[0009]

An object of the embodiments disclosed herein is to solve the above-mentioned various problems and to provides a low water content soft lens for eye, wherein a phenomenon of adhesion of the lens to the cornea during wear, which has hitherto been regarded as a problem in a conventional low water content soft lens for eye, has been remarkably reduced or avoided. Another object of the embodiments disclosed herein is to produce an excellent low water content soft lens for eye by a simple process at low costs.

[Solution to Problem]

[0010]

In order to achieve the above objects, the present disclosure includes the following constitutions.

[0011]

The present disclosure is directed to a low water content soft lens for eye, including a base material, a layer made of an acidic polymer and a basic polymer being formed on at least a part of a surface of the base material.

In a first aspect, there is provided a low water content soft lens for eye, comprising a base material, a layer made of an acidic polymer and a basic polymer being formed on at least a part of a surface of the base material, wherein water content of the lens is 1% or less.

[0012]

In the above low water content soft lens for eye, the base material preferably contain, as a main component, a polymer of the following component A, or a copolymer of the following components A and B:

component A: a polysiloxane compound which has a plurality of polymerizable functional groups per molecule, and also has a number average molecular weight of 6,000 or more, and

component B: a polymerizable monomer having a fluoroalkyl group.

[0013]

The present disclosure is also directed to a method for producing a low water content soft lens for eye, which includes the following steps 1 to 3 in this order:

<Step 1>

Step of polymerizing a mixture of a component A which is polysiloxane compound having a plurality of polymerizable functional groups per molecule, and also having a number average molecular weight of 6,000 or more, and a component B which is a polymerizable monomer having a fluoroalkyl group, to obtain a lens-shaped molding;

<Step 2>

Step of bringing the molding obtained in the step 1 into contact with a basic polymer solution, and then washing the molding, to remove the surplus basic polymer solution; and

<Step 3>

Step of bringing the molding obtained in the step 2 into contact with an acidic polymer solution, and then washing the molding, to remove the surplus acidic polymer solution.

In a second aspect, there is provided a method for producing a low water content soft lens for eye, which comprises the following steps 1 to 3 in this order, wherein water content of the lens is 1% or less:

<Step 1>

Step of polymerizing a mixture of a component A which is polysiloxane compound having a plurality of polymerizable functional groups per molecule, and also having a number average molecular weight of 6,000 or more, and a component B which is a polymerizable monomer having a fluoroalkyl group, to obtain a lens-shaped molding;

<Step 2>

Step of bringing the molding obtained in the step 1 into contact with a basic polymer solution, and then washing the molding, to remove the surplus basic polymer solution; and

<Step 3>

Step of bringing the molding obtained in the step 2 into contact with an acidic polymer solution, and then washing the molding, to remove the surplus acidic polymer solution.

[Advantageous Effects of Invention]

[0014]

According to the low water content soft lens for eye of the present disclosure, it is possible to remarkably reduce or avoid a phenomenon of adhesion of the lens to the cornea during wear, which has hitherto been regarded as a problem in a conventional low water content soft lens for eye. The low water content soft lens for eye of the present disclosure can reduce a risk of the growth of bacteria because of its low water content. According to preferred embodiment of the present disclosure, it is possible to provide a low water content soft lens for eye, which has high oxygen permeability and is excellent in water wettability, and which is flexible and is therefore excellent in comfort, and is also excellent in mechanical properties such as folding resistance. The low water content soft lens for eye of the present disclosure has a merit capable of producing by a simple process at low costs.

[Brief Description of Drawings]

[0015]

Fig. 1 is a schematic view showing dynamic friction between a sample film and an artificial leather.

[Description of Embodiments]

[0016]

In the low water content soft lens for eye of the present invention, "low water content" means that water content is 10% by weight or less. "Soft" means that tensile elastic modulus is 10 MPa or less.

[0017]

The low water content soft lens for eye of the present invention has features such as less feeling of dryness of eyes of wearers and excellent comfort because of its low water content. The low water content soft lens for eye of the present invention has a merit such as low risk of the growth of bacteria because of its low water content. The water content is more preferably 5% or less, still more preferably 2% or less, and most preferably 1% or less. Too high water content is not preferred since feeling of dryness of eyes of ophthalmic lens wearers may increase or risk of the growth of bacteria may become higher.

[0018]

Tensile elastic modulus of the low water content soft lens for eye of the present invention is preferably from 0.01 to 5 MPa, more preferably from 0.1 to 3 MPa, still more preferably

from 0.1 to 2 MPa, even more preferably from 0.1 to 1 MPa, and most preferably from 0.1 to 0.6 MPa. When the tensile elastic modulus is too small, it may become difficult to handle since the lens is too soft. When the tensile elastic modulus is too large, comfort may become worse since the lens is too hard. It is preferred that the tensile elastic modulus becomes 2 MPa or less since satisfactory comfort is obtained, and that the tensile elastic modulus becomes 1 MPa or less since more satisfactory comfort is obtained. The tensile elastic modulus is measured by a specimen in a wet state.

[0019]

Tensile elongation the low water content soft lens for eye of the present invention is preferably from 100% to 1,000%, and more preferably from 200% to 700%. It is not preferred that the tensile elongation is too small since the low water content soft lens for eye is likely to be broken. It is not preferred that the tensile elongation is too large since the low water content soft lens for eye is likely to be deformed. The tensile elongation is measured by a specimen in a wet state.

[0020]

Dynamic contact angle (advancing angle, immersion rate of 0.1 mm/sec) of the lens for eye is preferably 100° or less, more preferably 90° or less, and still more preferably 80° or less. From the viewpoint of preventing adhesion to the cornea of the wearer, the dynamic contact angle is preferably lower, and is

preferably 65° or less, more preferably 60° or less, still more preferably 55° or less, even more preferably 50° or less, and most preferably 45° or less.

[0021]

From the viewpoint of preventing adhesion to the cornea of the wearer, liquid film retention time of a surface of a lens for eye is preferably long. As used herein, the liquid film retention time is the time during which a liquid film on a surface of a lens for eye is held without being broken, when the lens for eye immersed in a borate buffer is pulled up and then held in air so that a diameter direction becomes vertical. The liquid film retention time is preferably 5 seconds or more, more preferably 10 seconds or more, and most preferably 20 seconds or more.

[0022]

From the viewpoint of preventing adhesion to the cornea of the wearer, the surface of the lens for eye preferably has excellent lubricity. As an indicator representing the lubricity, friction measured by the method mentioned in Examples of the present description is preferably smaller. The friction is preferably 60 gf or less, more preferably 50 gf or less, still more preferably 40 gf or less, and most preferably 30 gf or less. When the friction is extremely small, it may become difficult to handle when wearing and removing. Therefore, the friction is 5 gf or more, and preferably 10 gf or more.

[0023]

Anti-fouling property of the lens for eye can be evaluated by adhesion of mucin, adhesion of lipid (methyl palmitate), and an artificial lacrimal fluid immersion test. The amount of adhesion determined by these evaluations is preferably as small as possible since the lens for eye is excellent in comfort, and also a risk of the growth of bacteria is reduced. The amount of adhesion of mucin is preferably $5\mu\text{g}/\text{cm}^2$ or less, more preferably $4\mu\text{g}/\text{cm}^2$ or less, and most preferably $3\mu\text{g}/\text{cm}^2$ or less.

[0024]

From the viewpoint of supply of oxygen from atmospheric air to an eye of a wearer of the lens for eye, it is required for a low water content soft lens for eye to have high oxygen permeability. The oxygen permeability [$\times 10^{-11}$ (cm^2/sec) $\text{mLO}_2/(\text{mL}\cdot\text{hPa})$] is preferably from 50 to 2,000, more preferably from 100 to 1,500, still more preferably from 200 to 1,000, and most preferably from 300 to 700. It is not preferred that the oxygen permeability is excessively increased since an adverse influence may be sometimes exerted on other physical properties such as mechanical properties. The oxygen permeability is measured by a specimen in a dry state.

[0025]

The low water content soft lens for eye of the present invention is a low water content soft lens for eye, including a lens-shaped molding (hereinafter referred to as a base material)

in which a layer made of acidic and basic polymers is formed on at least a part of a surface of the base material.

[0026]

The base material preferably contains 5% by weight or more of silicon atoms in order to have high oxygen permeability, and to obtain strong adhesion with a polymer to be coated on a surface without involving in a covalent bond. The content (% by weight) of silicon atoms is calculated based on the weight of the base material in a dry state (100% by weight). The content of silicon atoms of the base material is preferably from 5% by weight to 36% by weight, more preferably from 7% by weight to 30% by weight, still more preferably from 10% by weight to 30% by weight, and most preferably from 12% by weight to 26% by weight. It is not preferred that the content of silicon atoms is too large since tensile elastic modulus may sometimes increase.

[0027]

The content of silicon atoms in the base material can be measured by the following method. After weighing sufficiently dried base material in a platinum crucible, sulfuric acid is added then the base material is incinerated by heating using a hot plate and a burner. The obtained ash is melted with sodium carbonate and water is added. After dissolving by heating, nitric acid is added and the volume is fixed by water. Regarding this solution, silicon atoms are measured by ICP emission spectrometry and the content in the base material is determined.

[0028]

The base material preferably contains, as a main component, a polymer of a component A: a polysiloxane compound which has a plurality of polymerizable functional groups per molecule, and also has a number average molecular weight of 6,000 or more, or a copolymer of the above component A and a compound which has a polymerizable functional group and is different from the component A. As used herein, the main component means a component which is contained in the amount of 50% by weight or more based on the weight of the base material in a dry state (100% by weight).

[0029]

Number average molecular weight of the component A is preferably 6,000 or more. The present inventors have found that it is possible to obtain a low water content soft lens for eye, which is flexible and is excellent in comfort, and is also excellent in mechanical properties such as folding resistance, when the number average molecular weight of the component A is within the above range. The number average molecular weight of the polysiloxane compound as the component A is preferably 8,000 or more since it is possible to obtain a low water content soft lens for eye, which is more excellent in mechanical properties such as folding resistance. The number average molecular weight of the component A is preferably within a range from 8,000 to 100,000, more preferably from 9,000 to 70,000, and still more preferably from 10,000 to 50,000. When the number average

molecular weight of the component A is too small, mechanical properties such as folding resistance may deteriorate. In particular, when the number average molecular weight is less than 6,000, folding resistance deteriorates. It is not preferred that the number average molecular weight of the component A is too large since flexibility and transparency may deteriorate.

[0030]

It is preferred that the low water content soft lens for eye of the present invention has high transparency since it is an optical product. Regarding criteria of transparency, it is preferred that the soft lens is transparent with no turbidity when visually observed. Furthermore, when the lens for eye is observed by a lens projector, it is preferred that turbidity is scarcely or not observed, and it is most preferred that no turbidity is observed.

[0031]

Dispersion degree (value obtained by dividing weight average molecular weight by number average molecular weight) of the component A is preferably 6 or less, more preferably 3 or less, still more preferably 2 or less, and most preferably 1.5 or less. When the dispersion degree of the component A is low, it is possible to achieve such benefits that compatibility with other components is improved and thus transparency of the obtained lens is improved; extractable components contained in the obtained lens reduce; and a ratio of shrinkage associated

with lens molding decreases. The ratio of shrinkage associated with lens molding can be evaluated by a molding ratio of lens = [diameter of lens] / [diameter of cavity portion of mold] . As the molding ratio of lens approaches 1, it becomes easier to stably produce a high-quality lens. The molding ratio is preferably within a range from 0.85 to 2.0, more preferably from 0.9 to 1.5, and most preferably from 0.91 to 1.3.

[0032]

In the present invention, number average molecular weight of the component A is polystyrene-equivalent number average molecular weight to be measured by a gel permeation chromatographic method (GPC method) using chloroform as a solvent. Weight average molecular weight and dispersion degree (value obtained by dividing weight average molecular weight by number average molecular weight) are also measured by a similar method.

[0033]

In the present description, the weight average molecular weight is sometimes represented by M_w , and the number average molecular weight is sometimes represented by M_n . The molecular weight of 1,000 is sometimes written as 1 kD. For example, " M_w 33 kD" means "weight average molecular weight of 33,000".

[0034]

The component A is a polysiloxane compound which has plurality of polymerizable functional groups. The number of polymerizable functional groups of the component A may be 2 or

more per molecule, and preferably 2 per molecule from the viewpoint of easily obtaining more flexible (low elastic modulus) lens for eye. Particularly preferred is a structure having a polymerizable functional group at both ends of the molecular chain.

[0035]

The polymerizable functional group of the component A is preferably a radical polymerizable functional group, and more preferably a radical polymerizable functional group having a carbon-carbon double bond. Examples of preferable polymerizable functional group include a vinyl group, an allyl group, a (meth)acryloyl group, an α -alkoxymethylacryloyl group, a maleic acid residue, a fumaric acid residue, an itaconic acid residue, a crotonic acid residue, an isocrotonic acid residue, an citraconic acid residue and the like. Among these polymerizable functional groups, a (meth)acryloyl group is most preferable since it has high polymerizability.

[0036]


In the present description, the term "(meth)acryloyl" represents both methacryloyl and acryloyl, and the same shall apply to terms such as (meth)acryl and (meth)acrylate.

[0037]

The component A preferably has a structure of the following formula (A1).

[0038]

[Chemical Formula 1]



[0039]

In the formula (A1), X^1 and X^2 each independently represents a polymerizable functional group. R^1 to R^8 each independently represents a substituent selected from hydrogen, an alkyl group having 1 to 20 carbon atoms, a phenyl group and a fluoroalkyl group having 1 to 20 carbon atoms. L^1 and L^2 each independently represents a divalent group. a and b each independently represents the number of the respective repeating units.

[0040]

X^1 and X^2 are preferably radical polymerizable functional groups, and radical polymerizable functional groups having a carbon-carbon double bond are preferable. Examples of preferable polymerizable functional group include a vinyl group, an allyl group, a (meth)acryloyl group, an α -alkoxymethylacryloyl group, a maleic acid residue, a fumaric acid residue, an itaconic acid residue, a crotonic acid residue, an isocrotonic acid residue, a citraconic acid residue and the like. Among these polymerizable functional groups, a (meth)acryloyl group is most preferable since it has high polymerizability.

[0041]

Suitable specific examples of R^1 to R^8 include hydrogen; an alkyl group having 1 to 20 carbon atoms, such as a methyl

group, an ethyl group, a propyl group, an isopropyl group, a butyl group, a t-butyl group, a decyl group, a dodecyl group or an octadecyl group; a phenyl group; and a fluoroalkyl group having 1 to 20 carbon atoms, such as a trifluoromethyl group, a trifluoroethyl group, a trifluoropropyl group, a tetrafluoropropyl group, a hexafluoroisopropyl group, a pentafluorobutyl group, a heptafluoropentyl group, a nonafluorohexyl group, a hexafluorobutyl group, a heptafluorobutyl group, an octafluoropentyl group, a nonafluoropentyl group, a dodecafluoroheptyl group, a tridecafluoroheptyl group, a dodecafluorooctyl group, a tridecafluorooctyl group, a hexadecafluorodecyl group, a heptadecafluorodecyl group, a tetrafluoropropyl group, a pentafluoropropyl group, a tetradecafluorooctyl group, a pentadecafluorooctyl group, an octadecafluorodecyl group or a nonadecafluorodecyl group. Among these groups, hydrogen and a methyl group are more preferable from the viewpoint of imparting satisfactory mechanical properties and high oxygen permeability to the lens for eye, and a methyl group is most preferable.












[0042]

L^1 and L^2 are preferably divalent groups having 1 to 20 carbon atoms. Among these groups, groups represented by the following formulas (LE1) to (LE12) are preferable since a compound of the formula (A1) has an advantage of easily obtaining with high purity. Among these, L^1 and L^2 are more preferably groups

represented by the following formulas (LE1), (LE3), (LE9) and (LE11), still more preferably groups represented by the following formulas (LE1) and (LE3), and most preferably a group represented by the following formula (LE1). In the following formulas (LE1) to (LE12), left side is drawn as an end which is bonded to a polymerizable functional group X^1 or X^2 , while right side is drawn as an end which is bonded to a silicon atom.

[0043]

[Chemical Formula 2]



[0044]

In the formula (A1), a and b each independently represents the number of the respective repeating units. Preferably, a and

b each independently within a range from 0 to 1,500. The total value (a + b) of a and b is preferably 80 or more, more preferably 100 or more, still more preferably from 100 to 1400, even more preferably from 120 to 950, and yet more preferably from 130 to 700.

[0045]

When all of R^1 to R^8 are methyl groups, $b = 0$, and a is preferably from 80 to 1,500, more preferably from 100 to 1400, still more preferably from 120 to 950, and even more preferably from 130 to 700. In this case, the value of a is determined by the molecular weight of the polysiloxane compound as the component A.

[0046]

The component A of the present invention may be used alone, or two or more kinds may be used in combination.

[0047]

The other compound to be copolymerized with the component A is preferably a component B which is a polymerizable monomer having a fluoroalkyl group. The component B has properties of water and oil repellency due to a decrease in critical surface tension caused by a fluoroalkyl group, thereby exerting the effect of suppressing a surface of a lens for eye from being contaminated with components such as protein and lipid in a lacrimal fluid. The component B also has the effect of giving a low water content soft lens for eye, which is flexible and is excellent in comfort,

and is also excellent in mechanical properties such as folding resistance. Suitable specific examples of the fluoroalkyl group of the component B include fluoroalkyl groups having 1 to 20 carbon atoms, such as a trifluoromethyl group, a trifluoroethyl group, a trifluoropropyl group, a tetrafluoropropyl group, a hexafluoroisopropyl group, a pentafluorobutyl group, a heptafluoropentyl group, a nonafluorohexyl group, a hexafluorobutyl group, a heptafluorobutyl group, an octafluoropentyl group, a nonafluoropentyl group, a dodecafluoroheptyl group, a tridecafluoroheptyl group, a dodecafluorooctyl group, a tridecafluorooctyl group, a hexadecafluorodecyl group, a heptadecafluorodecyl group, a tetrafluoropropyl group, a pentafluoropropyl group, a tetradecafluorooctyl group, a pentadecafluorooctyl group, an octadecafluorodecyl group and a nonadecafluorodecyl group. The fluoroalkyl group is more preferably a fluoroalkyl group having 2 to 8 carbon atoms, for example, a trifluoroethyl group, a tetrafluoropropyl group, a hexafluoroisopropyl group, an octafluoropentyl group or a dodecafluorooctyl group, and most preferably a trifluoroethyl group.

[0048]

The polymerizable functional group of the component B is preferably a radical polymerizable functional group, and more preferably a radical polymerizable functional group having a carbon-carbon double bond. Examples of preferable

polymerizable functional group include a vinyl group, an allyl group, a (meth)acryloyl group, an α -alkoxymethylacryloyl group, a maleic acid residue, a fumaric acid residue, an itaconic acid residue, a crotonic acid residue, an isocrotonic acid residue, a citraconic acid residue and the like. Among these polymerizable functional groups, a (meth)acryloyl group is most preferable since it has high polymerizability.

[0049]

The component B is most preferably a (meth)acrylic acid fluoroalkyl ester since it exerts a remarkable effect of obtaining a low water content soft lens for eye, which is flexible and is excellent in comfort, and is also excellent in mechanical properties such as folding resistance. Specific examples of the (meth)acrylic acid fluoroalkyl ester include trifluoroethyl (meth)acrylate, tetrafluoroethyl (meth)acrylate, trifluoropropyl (meth)acrylate, tetrafluoropropyl (meth)acrylate, pentafluoropropyl (meth)acrylate, hexafluorobutyl (meth)acrylate, hexafluoroisopropyl (meth)acrylate, heptafluorobutyl (meth)acrylate, octafluoropentyl (meth)acrylate, nonafluoropentyl (meth)acrylate, dodecafluoropentyl (meth)acrylate, dodecafluoroheptyl (meth)acrylate, dodecafluorooctyl (meth)acrylate and tridecafluoroheptyl (meth)acrylate. Trifluoroethyl (meth)acrylate, tetrafluoroethyl (meth)acrylate, hexafluoroisopropyl (meth)acrylate, octafluoropentyl

(meth)acrylate and dodecafluorooctyl (meth)acrylate, which are preferably used. Trifluoroethyl (meth)acrylate is most preferable.

[0050]

The component B of the present invention may be used alone, or two or more kinds may be used in combination.

[0051]

The content of the component B in the copolymer is preferably from 10 to 500 parts by weight, more preferably from 20 to 400 parts by weight, and still more preferably from 20 to 200 parts by weight, based on 100 parts by weight of the component A. When the use amount of the component B is too small, white turbidity may arise in the obtained lens for eye, or mechanical properties such as folding resistance may become insufficient.

[0052]

It is possible to use, as the copolymer to be used in the base material, a copolymer obtained by copolymerizing a component which is different from the components A and B (hereinafter referred to as a component C), in addition to the components A and B.

[0053]

The component C may be a component which decreases a glass transition point of a copolymer to room temperature or 0°C or lower. The component decreases cohesive energy and therefore exerts the effect of imparting rubber elasticity and flexibility

to the copolymer.

[0054]

The polymerizable functional group of the component C is preferably a radical polymerizable functional group, and more preferably a radical polymerizable functional group having a carbon-carbon double bond. Examples of preferable polymerizable functional group include a vinyl group, an allyl group, a (meth)acryloyl group, an α -alkoxymethylacryloyl group, a maleic acid residue, a fumaric acid residue, an itaconic acid residue, a crotonic acid residue, an isocrotonic acid residue, a citraconic acid residue and the like. Among these polymerizable functional groups, a (meth)acryloyl group is most preferable since it has high polymerizability.

[0055]

The component C, which is suitable for the improvement of mechanical properties such as flexibility and folding resistance, is a (meth)acrylic acid alkyl ester, and preferably a (meth)acrylic acid alkyl ester whose alkyl group has 1 to 20 carbon atoms, and specific examples thereof include methyl (meth)acrylate, ethyl (meth)acrylate, n-propyl (meth)acrylate, n-butyl (meth)acrylate, tert-butyl (meth)acrylate, isobutyl (meth)acrylate, n-hexyl (meth)acrylate, n-octyl (meth)acrylate, 2-ethylhexyl (meth)acrylate, n-heptyl (meth)acrylate, n-nonyl (meth)acrylate, n-decyl (meth)acrylate, isodecyl (meth)acrylate, n-lauryl (meth)acrylate, tridecyl

(meth)acrylate, n-dodecyl (meth)acrylate, cyclopentyl (meth)acrylate, cyclohexyl (meth)acrylate, n-stearyl (meth)acrylate and the like. The (meth)acrylic acid alkyl ester is more preferably n-butyl (meth)acrylate, n-octyl (meth)acrylate, n-lauryl (meth)acrylate or n-stearyl (meth)acrylate. Among these, a (meth)acrylic acid alkyl ester whose alkyl group has 1 to 10 carbon atoms is more preferable. It is not preferred that the number of carbon atoms of the alkyl group is too large since transparency of the lens may sometimes deteriorate. Monofunctional (meth)acrylates having a siloxanyl group are also suitable for the improvement of oxygen permeability. As used herein, a siloxanyl group means a group having a Si-O-Si bond.

[0056]

Furthermore, in order to improve mechanical properties, surface wettability, dimensional stability of the lens and the like, the below-mentioned monomer can be optionally copolymerized.

[0057]

Examples of the monomer for the improvement of mechanical properties include an aromatic vinyl compound such as styrene, tert-butylstyrene and α -methylstyrene.

[0058]

Examples of the monomer for the improvement of surface wettability include methacrylic acid, acrylic acid, itaconic

acid, 2-hydroxyethyl methacrylate, 2-hydroxyethyl acrylate, 2-hydroxypropyl methacrylate, 2-hydroxypropyl acrylate, glycerol methacrylate, polyethylene glycol methacrylate, N,N-dimethylacrylamide, N-methyl acrylamide, dimethylaminoethyl methacrylate, methylenebisacrylamide, diacetone acrylamide, N-vinylpyrrolidone, N-vinylcaprolactam, N-vinyl acetamide, N-vinyl-N-methyl acetamide and the like. Among these monomers, an amide bond-containing monomer such as N,N-dimethylacrylamide, N-methyl acrylamide, dimethylaminoethyl methacrylate, methylenebisacrylamide, diacetone acrylamide, N-vinylpyrrolidone, N-vinylcaprolactam, N-vinyl acetamide or N-vinyl-N-methyl acetamide is preferable.

[0059]

Examples of the monomer for the improvement of dimensional stability of the lens include ethylene glycol dimethacrylate, diethylene glycol dimethacrylate, triethylene glycol dimethacrylate, polyethylene glycol dimethacrylate, trimethylolpropane trimethacrylate, pentaerythritol tetramethacrylate, bisphenol A dimethacrylate, vinyl methacrylate, acryl methacrylate, and acrylates corresponding to these methacrylates, divinylbenzene, triallyl isocyanurate and the like.

[0060]

The component C may be used alone, or two or more kinds may be used in combination.

[0061]

The use amount of the component C is preferably from 0.001 to 400 parts by weight, more preferably from 0.01 to 300 parts by weight, still more preferably from 0.01 to 200 parts by weight, and most preferably from 0.01 to 30 parts by weight, based on 100 parts by weight of the component A. When the use amount of the component C is too small, it may become difficult to obtain the effect which is expected to the component C. When the use amount of the component C is too large, white turbidity may arise in the obtained lens for eye, or mechanical properties such as folding resistance may become insufficient.

[0062]

The low water content soft lens for eye of the present invention may further contain a component such as an ultraviolet absorber, a pigment, a colorant, a humectant, a slip agent, a pharmaceutical and a nutritional supplementary component, a compatibilizing component, an antibacterial component, a mold release agent and the like. Any of the above-mentioned components can be contained in a non-reactive form or a copolymerization foam.

[0063]

In the case of containing an ultraviolet absorber, it is possible to protect eyes of ophthalmic lens wearers from harmful ultraviolet rays. In the case of containing a colorant, the lens for eye is colored, results in easy identification and an

improvement in convenience during handling.

[0064]

Any of the above-mentioned components can be contained in the form of a non-reactive form or a copolymerization form. It is preferred that the above components are copolymerized, that is, an ultraviolet absorber having a polymerizable group or a colorant having a polymerizable group is used since the component is copolymerized with a base material and immobilized, and thus elution may scarcely occur.

[0065]

The base material is preferably composed of components to be selected from an ultraviolet absorber and a colorant, and two or more kinds of components C other than these components (hereinafter referred to as a component C_k). In that case, it is preferred that at least one kind of the component C_k is selected from a (meth)acrylic acid alkyl ester having 1 to 10 carbon atoms, and at least one kind of the component C_k is selected from a monomer for the improvement of surface wettability. Use of two or more kinds of components C_k enhances affinity with an ultraviolet absorber or a colorant, and thus it becomes possible to obtain a transparent base material.

[0066]

In the case of using an ultraviolet absorber, the use amount thereof is preferably from 0.01 to 20 parts by weight, more preferably from 0.05 to 10 parts by weight, and still more

preferably from 0.1 to 2 parts by weight, based on 100 parts by weight of the component A. In the case of using a colorant, the use amount thereof is preferably from 0.00001 to 5 parts by weight, more preferably from 0.0001 to 1 part by weight, and still more preferably from 0.0001 to 0.5 part by weight, based on 100 parts by weight of the component A. When the content of the ultraviolet absorber or colorant is too small, it may become difficult to obtain the ultraviolet absorption effect or coloration effect. In contrast, when the content is too large, it may become difficult to dissolve these components in the base material. The use amount of the component Ck is preferably from 0.1 to 100 parts by weight, more preferably from 1 to 80 parts by weight, and still more preferably from 2 to 50 parts by weight, based on 100 parts by weight of the component A. When the use amount of the component Ck is too small, it may become difficult to obtain a transparent base material because of lack of affinity with the ultraviolet absorber or colorant. It is not preferred that the use amount of the component Ck is too large since white turbidity may arise in the obtained lens for eye, or mechanical properties such as folding resistance may become insufficient.

[0067]

It is possible to use, as a method for producing a base material of a low water content soft lens for eye, that is, a lens-shaped molding, a known method. For example, it is possible to use a method in which a round bar- or plate-shaped polymer

is once obtained and then processed into a desired shape by cutting or the like, a mold polymerization method, a spin-cast polymerization method and the like. In the case of obtaining a lens by cutting, freeze-cutting at low temperature is suitable. [0068]

A method of polymerizing a raw material composition containing a component A by a mold polymerization method to produce a lens for eye will be described below as an example. First, a gap between two mold members each having a fixed shape is filled with a raw material composition. Examples of the material of the mold member include resin, glass, ceramics, metal and the like. In the case of performing photopolymerization, since an optically transparent material is preferable, the resin or glass is preferably used. Depending on the shape of the mold member or properties of the raw material composition, a gasket may be used so as to impart a fixed thickness to the lens for eye, and to prevent liquid leakage of the raw material composition filled in the gap. The mold with the gap filled with raw material composition is subsequently irradiated with active rays such as ultraviolet rays, visible rays or a combination thereof, or heating in an oven or a liquid bath, thereby polymerizing the raw material composition filled in the mold. It is also possible to employ a method using two types of polymerization methods. That is, it is also possible to perform heat polymerization after photopolymerization, or perform photopolymerization after heat

polymerization. In a specific aspect of photopolymerization, for example, light including ultraviolet rays such as light of a mercury lamp or an ultraviolet lamp (for example, FL15BL, Toshiba Corporation) are irradiated within a short time (usually 1 hour or less). In the case of performing heat polymerization, conditions of gradually raising a temperature of the composition from about room temperature and raising to the temperature of 60°C to 200°C over several hours to several tens of hours are preferably used so as to maintain optical uniformity and grade of a lens for eye, and to enhance reproducibility.

[0069]

In the polymerization, a heat polymerization initiator typified by a peroxide or an azo compound, or a photopolymerization initiator is preferably added so as to facilitate the polymerization. In the case of performing heat polymerization, an initiator having optimum decomposition characteristics at a desired reaction temperature is selected. Commonly, an azo-based initiator and a peroxide-based initiator, each having a ten-hour half-life temperature of 40 to 120°C, are suitable. Examples of the photoinitiator in the case of performing photopolymerization include a carbonyl compound, a peroxide, an azo compound, a sulfur compound, a halogen compound, a metal salt and the like. These polymerization initiators are used alone or in combination. The amount of the polymerization initiator is preferably up to 5% by weight based on a polymerization mixture.

[0070]

In the case of performing polymerization, a polymerization solvent can be used. Organic and inorganic various solvents can be applied as the solvent. Examples of the solvent include water; alcohol-based solvents such as methyl alcohol, ethyl alcohol, normal propyl alcohol, isopropyl alcohol, normal butyl alcohol, isobutyl alcohol, t-butyl alcohol, t-amyl alcohol, tetrahydrolinalool, ethylene glycol, diethylene glycol, triethylene glycol, tetraethylene glycol and polyethylene glycol; glycol ether-based solvents such as methyl cellosolve, ethyl cellosolve, isopropyl cellosolve, butyl cellosolve, propylene glycol monomethyl ether, diethylene glycol monomethyl ether, triethylene glycol monomethyl ether, polyethylene glycol monomethyl ether, ethylene glycol dimethyl ether, diethylene glycol dimethyl ether, triethylene glycol dimethyl ether and polyethylene glycol dimethyl ether; ester-based solvents such as ethyl acetate, butyl acetate, amyl acetate, ethyl lactate and methyl benzoate; aliphatic hydrocarbon-based solvents such as normal hexane, normal heptane and normal octane; alicyclic hydrocarbon-based solvents such as cyclohexane and ethylcyclohexane; ketone-based solvents such as acetone, methyl ethyl ketone and methyl isobutyl ketone; aromatic hydrocarbon-based solvents such as benzene, toluene and xylene; and petroleum-based solvents. These solvent may be used alone, or two or more kinds may be used in combination.

[0071]

It is necessary that a layer made of an acidic polymer and a basic polymer (hereinafter referred to as a coating layer) is formed on at least a part of a surface of a base material in the low water content soft lens for eye of the present invention. Inclusion of a coating layer imparts satisfactory wettability and lubricity to the surface of the lens, and thus imparting excellent comfort.

[0072]

The present inventors have found that, even if the low water content soft lens for eye of the present invention has low water content and is soft, and also the base material is neutral, it is possible to impart sufficient wettability, lubricity and anti-fouling property to the surface of the lens by forming a coating layer made of an acidic polymer and a basic polymer on the surface. Thereby, according to the low water content soft lens for eye of the present invention, it is possible to remarkably reduce or avoid a phenomenon of adhesion of the lens to the cornea during wear, which has hitherto been regarded as a problem in a conventional low water content soft lens for eye.

[0073]

It is not necessary to have a covalent bond between the coating layer and the base material. It is preferred to have no covalent bond between the coating layer and the base material since it becomes possible to produce by a simple and easy step.

The coating layer has practical durability even in the case of having no covalent bond between the coating layer and the base material.

[0074]

The coating layer is preferably made of one or more kinds of acidic polymers and one or more kinds of basic polymers. Use of two or more kinds of acidic polymers or two or more kinds of basic polymers are more preferable since it is easy to develop properties such as lubricity and anti-fouling property to the surface of the lens for eye. In particular, use of two or more kinds of acidic polymers and one or more kinds of basic polymers are more preferable since this tendency is to be further increased.

[0075]

The coating layer preferably includes one or more layers made of an acidic polymer (acidic polymer layer), and one or more layers made of a basic polymer (basic polymer layer).

[0076]

The number of the acidic and basic polymer layers to be formed on the surface of the base material is preferably from 1 to 5, more preferably from 1 to 3, and still more preferably from 1 to 2. The number of the acidic polymer layer may be different from that of basic polymer layer.

[0077]

The present inventors have found that excellent wettability and lubricity can be imparted by very small number of layers

(total number of acidic and basic polymer layers is 2 or 3) in the low water content soft lens for eye of the present invention. This fact is crucially important for industry from the viewpoint of shortening of the production process. In that sense, in the low water content soft lens for eye of the present invention, the total number of acidic and basic polymer layers is preferably 2 or 3, and not preferably 2.

[0078]

The present inventors have also confirmed that wettability and lubricity are scarcely developed even if the coating layer only contains any one of acidic and basic polymers.

[0079]

From the viewpoint of wettability, lubricity and shortening of the production process, the low water content soft lens for eye of the present invention preferably includes constitution selected from the following layer constitutions 1 to 4. In the following notations, molding means a lens-shaped molding, that is, a base material. The following notation shows layer constitution in which the respective layers are sequentially accumulated on a base material from left to right.

[0080]

Layer constitution 1: Molding/basic polymer layer/acidic polymer layer

Layer constitution 2: Molding/acidic polymer layer/basic polymer layer

Layer constitution 3: Molding/basic polymer layer/acidic polymer layer/basic polymer layer

Layer constitution 4: Molding/acidic polymer layer/basic polymer layer/acidic polymer layer

Among these layer constitutions, layer constitution 1 and layer constitution 4 are more preferable since they exhibit particularly excellent wettability, and layer constitution 1 is most preferable from the viewpoint of production-related simplicity.

It is possible to suitably use, as the basic polymer, a homopolymer or copolymer having a plurality of groups having basicity along a polymer chain. An amino group and salts thereof are suitable as the group having basicity. Suitable examples of the basic polymer include an amino group-containing (meth)acrylate polymer such as poly(allylamine), poly(vinylamine), poly(ethyleneimine), poly(vinylbenzyltrimethylamine), polyaniline, poly(aminostyrene) or poly(N,N-dialkylaminoethyl methacrylate); an amino group-containing (meth)acrylamide polymer such as poly(N,N-dimethylaminopropyl acrylamide); and salts thereof. Although the followings are examples of a homopolymer, these copolymers (i.e., a copolymer of basic monomers composing the basic polymer, or a copolymer of a basic monomer and the other monomer) can also be suitably used.

When the basic polymer is a copolymer, the basic monomer composing the copolymer is preferably a monomer having an allyl group, a vinyl group and a (meth)acryloyl group from the viewpoint of high polymerizability, and most preferably a monomer having a (meth)acryloyl group. Suitable examples of the basic monomer composing the copolymer include allylamine, vinylamine (N-vinylcarboxylic acid amide as a precursor), vinylbenzyltrimethylamine, amino group-containing styrene, amino group-containing (meth)acrylate, amino group-containing (meth)acrylamide, and salts thereof. Among these monomers, amino group-containing (meth)acrylate, amino group-containing (meth)acrylamide, and salts thereof are more preferably from the viewpoint of high polymerizability, and N,N-dimethylaminoethyl methacrylate, N,N-dimethylaminopropyl acrylamide, and salts thereof are most preferable.

[0082]

The basic polymer may be a polymer having a quaternary ammonium structure. The polymer having a quaternary ammonium structure compound can impart antimicrobial properties to a soft lens for eye when used for coating of the soft lens for eye.

[0083]

It is possible to suitably use, as the acidic polymer, a homopolymer or copolymer having a plurality of groups having acidity along a polymer chain. The group having acidity is suitably a carboxyl group, a sulfonic acid group and salts thereof,

and most suitably a carboxyl group and salts thereof. Examples of suitable acidic polymer include polymethacrylic acid, polyacrylic acid, poly(vinylbenzoic acid), poly(thiophene-3-acetic acid), poly(4-styrenesulfonic acid), polyvinylsulfonic acid, poly(2-acrylamide-2-methylpropanesulfonic acid) and salts thereof. Although the above polymers are examples of a homopolymer, these copolymers (i.e., a copolymer of basic monomers composing the basic polymer, or a copolymer of a basic monomer and the other monomer) can also be suitably used.

[0084]

When the acidic polymer is a copolymer, the acidic monomer composing the copolymer is preferably a monomer having an allyl group, a vinyl group and a (meth)acryloyl group from the viewpoint of high polymerizability, and most preferably a monomer having a (meth)acryloyl group. Suitable examples of the acidic monomer composing the copolymer include (meth)acrylic acid, vinylbenzoic acid, styrenesulfonic acid, vinylsulfonic acid, 2-acrylamide-2-methylpropanesulfonic acid and salts thereof. Among these monomers, (meth)acrylic acid, 2-acrylamide-2-methylpropanesulfonic acid, and salts thereof are more preferable, and (meth)acrylic acid, and salts thereof are most preferable.

[0085]

It is preferred that at least one kind of basic and acidic

polymers is a polymer having a group selected from an amide bond and a hydroxyl group. It is preferred that a basic polymer and/or an acidic polymer has/have an amide bond since a surface having not only wettability but also lubricity can be formed. It is preferred that a basic polymer and/or an acidic polymer has/have a hydroxyl group since a surface having not only excellent wettability but also excellent anti-fouling property against a lacrimal fluid can be formed.

[0086]

More preferably, two or more kinds of the acidic polymer and basic polymer are polymers having a group selected from a hydroxyl group and an amide bond. That is, the low water content soft lens for eye preferably contains two or more kinds selected from an acidic polymer having a hydroxyl group, a basic polymer having a hydroxyl group, an acidic polymer having an amide bond and a basic polymer having an amide bond. In this case, it is preferred since the effect of forming a surface having lubricity, or the effect capable of forming a surface having excellent anti-fouling property against a lacrimal fluid can be more remarkably exerted.

[0087]

More preferably, the coating layer contains at least one kind selected from an acidic polymer having a hydroxyl group and a basic polymer having a hydroxyl group, and at least one kind selected from an acidic polymer having an amide bond and

a basic polymer having an amide bond. In this case, it is preferred since both the effect of forming a surface having lubricity, and the effect capable of forming a surface having excellent anti-fouling property against a lacrimal fluid can be exerted.

[0088]

Examples of the basic polymer having an amide bond include polyamides having an amino group, partially hydrolyzed chitosan, a copolymer of a basic monomer and a monomer having an amide bond and the like.

[0089]

Examples of the acidic polymer having an amide bond include polyamides having a carboxyl group, a copolymer of an acidic monomer and a monomer having an amide bond and the like.

[0090]

Examples of the basic polymer having a hydroxyl group include amino-polysaccharides such as chitin, a copolymer of a basic monomer and a monomer having a hydroxyl group and the like.

[0091]

Examples of the acidic polymer having a hydroxyl group include polysaccharides having an acidic group such as hyaluronic acid, chondroitin sulfate, carboxymethyl cellulose and carboxypropyl cellulose, a copolymer of an acidic monomer and a monomer having an amide bond and the like.

[0092]

The monomer having an amide bond is preferably a monomer having a (meth)acrylamide group and N-vinylcarboxylic acid amide (including a cyclic monomer) from the viewpoint of ease of polymerization. Suitable examples of the monomer include N-vinylpyrrolidone, N-vinylcaprolactam, N-vinyl acetamide, N-methyl-N-vinyl acetamide, N-vinylformamide, N,N-dimethylacrylamide, N,N-diethyl acrylamide, N-isopropyl acrylamide, N-(2-hydroxyethyl)acrylamide, acryloylmorpholine and acrylamide. Among these monomers, N-vinylpyrrolidone and N,N-dimethylacrylamide are preferable from the viewpoint of lubricity, and N,N-dimethylacrylamide is most preferable.

[0093]

Suitable examples of the monomer having a hydroxyl group include hydroxyethyl (meth)acrylate, hydroxypropyl (meth)acrylate, hydroxybutyl (meth)acrylate, hydroxyethyl (meth)acrylamide, glycerol (meth)acrylate, caprolactone-modified 2-hydroxyethyl (meth)acrylate, N-(4-hydroxyphenyl)maleimide, hydroxystyrene and vinyl alcohol (carboxylic acid vinyl ester as a precursor). The monomer having a hydroxyl group is preferably a monomer having a (meth)acryloyl group from the viewpoint of ease of polymerization, and more preferably a (meth)acrylic acid ester monomer. Among these monomers, hydroxyethyl (meth)acrylate, hydroxypropyl (meth)acrylate and glycerol (meth)acrylate are preferable from the viewpoint of anti-fouling property against a lacrimal fluid,

and hydroxyethyl (meth)acrylate is most preferable.

[0094]

Specific examples of preferable copolymer of a basic monomer and a monomer having an amide bond include an N,N-dimethylaminoethyl methacrylate/N-vinylpyrrolidone copolymer, an N,N-dimethylaminoethyl methacrylate/N,N-dimethylacrylamide copolymer, an N,N-dimethylaminopropyl acrylamide/N-vinylpyrrolidone copolymer and an N,N-dimethylaminopropyl acrylamide/N,N-dimethylacrylamide copolymer. An N,N-dimethylaminopropyl acrylamide/N,N-dimethylacrylamide copolymer is most preferable.

[0095]

Specific examples of preferable copolymer of an acidic monomer and a monomer having an amide bond include a (meth)acrylic acid/N-vinylpyrrolidone copolymer, a (meth)acrylic acid/N,N-dimethylacrylamide copolymer, a 2-acrylamide-2-methylpropanesulfonic acid/N-vinylpyrrolidone copolymer and a 2-acrylamide-2-methylpropanesulfonic acid/N,N-dimethylacrylamide copolymer. A (meth)acrylic acid/N,N-dimethylacrylamide copolymer is most preferable.

[0096]

Specific examples of preferable copolymer of a basic monomer and a monomer having a hydroxyl group include an N,N-dimethylaminoethyl methacrylate/hydroxyethyl

(meth)acrylate copolymer, an N,N-dimethylaminoethyl methacrylate/glycerol (meth)acrylate copolymer, an N,N-dimethylaminopropyl acrylamide/hydroxyethyl (meth)acrylate and an N,N-dimethylaminopropyl acrylamide/glycerol (meth)acrylate copolymer. An N,N-dimethylaminoethyl methacrylate/hydroxyethyl (meth)acrylate copolymer is most preferable.

[0097]

Specific examples of preferable copolymer of an acidic monomer and a monomer having an amide bond include a (meth)acrylic acid/hydroxyethyl (meth)acrylate copolymer, a (meth)acrylic acid/glycerol (meth)acrylate copolymer, a 2-acrylamide-2-methylpropanesulfonic acid/hydroxyethyl (meth)acrylate copolymer and a 2-acrylamide-2-methylpropanesulfonic acid/glycerol (meth)acrylate copolymer. A (meth)acrylic acid/hydroxyethyl (meth)acrylate copolymer is most preferable.

[0098]

In the case of using a copolymer of the basic monomer or acidic monomer and the other monomer, the copolymerization ratio [weight of basic monomer or acidic monomer] / [weight of the other monomer] is preferably from 1/99 to 99/1, more preferably from 2/98 to 90/10, and still more preferably from 10/90 to 80/20. When the copolymerization ratio is within the above range, functions such as lubricity and anti-fouling property against

a lacrimal fluid are likely to be developed.

[0099]

In order to change various characteristics, for example, thickness of the coating layer, it is possible to change molecular weights of an acidic polymer and a basic polymer. Specifically, when the molecular weight is increased, the thickness of the coating layer commonly increases. However, when the molecular weight is too large, it may become difficult to handle due to an increase in viscosity. Therefore, acidic and basic polymers to be used in the present invention preferably have a molecular weight of 2,000 to 150,000. The molecular weight is more preferably from 5,000 to 100,000, and still more preferably from 75,000 to 100,000. The molecular weight of the acidic and basic polymers is a polyethylene glycol-equivalent weight average molecular weight measured by a gel permeation chromatographic method (aqueous solvent).

[0100]

Coating of the coating layer can be achieved by various methods disclosed, for example, in WO 99/35520, WO 01/57118 or U.S. Patent No. 2001-0045676.

[0101]

The method for producing a low water content soft lens for eye of the present invention will be described below. The low water content soft lens for eye of the present invention is obtained by respectively coating a surface of a lens-shaped molding (base

material) with an acidic polymer solution and a basic polymer solution 1 to 5 times, more preferably 1 to 3 times, and still more preferably 1 to 2 times, to form a coating layer. The number of times of the coating step of an acidic polymer solution may be different from that of the coating step of a basic polymer solution.

[0102]

The present inventors have found that excellent wettability and lubricity can be imparted by very small number of times of the coating steps (total number of coating steps of acidic and basic polymer solutions is 2 or 3) in the method for producing a low water content soft lens for eye of the present invention. This fact is crucially important for industry from the viewpoint of shortening of the production process. In that sense, the total number of coating steps of acidic and basic polymer solutions is preferably 2 or 3, and not preferably 2.

[0103]

The present inventors have also confirmed that wettability and lubricity are scarcely developed only by performing either the coating step of an acidic polymer solution or the coating step of a basic polymer solution once in the low water content soft lens for eye of the present invention.

[0104]

From the viewpoint of wettability, lubricity and shortening of the production process, coating of the coating layer is

preferably performed with the constitution selected from the following constitutions 1 to 4. The following notation shows that the respective coating steps are sequentially applied to a surface of a molding from left to right.

[0105]

Constitution 1: Coating of basic polymer solution/coating of acidic polymer solution

Constitution 2: Coating of acidic polymer solution/coating of basic polymer solution

Constitution 3: Coating of basic polymer solution/coating of acidic polymer solution/coating of basic polymer solution

Constitution 4: Coating of acidic polymer solution/coating of basic polymer solution/coating of acidic polymer solution

Among these constitutions, constitution 1 and constitution 4 are more preferably since the obtained low water content soft lens for eye exhibits particularly excellent wettability, and constitution 1 is most preferably from the viewpoint of production-related simplicity.

[0106]

In the case of coating an acidic polymer solution and a basic polymer solution, a surface of a base material may be untreated or already treated. As used herein, the phrase "surface of a base material is already treated" means that a surface of a base material is subjected to a surface treatment or surface modification by a known method. Suitable examples of the surface

treatment or surface modification include a plasma treatment, a chemical modification, a chemical functionalization, a plasma coating and the like.

[0107]

One of preferred aspects of the method for producing a low water content soft lens for eye of the present invention includes the following steps 1 to 3 in this order:

<Step 1>

Step of polymerizing a mixture of a component A which is polysiloxane compound having a plurality of polymerizable functional groups per molecule, and also having a number average molecular weight of 6,000 or more, and a component B which is a polymerizable monomer having a fluoroalkyl group, to obtain a lens-shaped molding;

<Step 2>

Step of bringing the molding obtained in the step 1 into contact with a basic polymer solution, and then washing the molding, to remove the surplus basic polymer solution; and

<Step 3>

Step of bringing the molding obtained in the step 2 into contact with an acidic polymer solution, and then washing the molding, to remove the surplus acidic polymer solution.

[0108]

As mentioned above, a layer made of an acidic polymer and a basic polymer can be formed on a lens-shaped molding by

sequentially bringing the molding into contact with an acidic polymer solution and a basic polymer solution. Thereafter, surplus polymer is preferably removed by sufficiently washing.

[0109]

It is possible to apply, as the method of bringing the molding into contact with an acidic polymer solution or a basic polymer solution, various coating methods such as an immersion method (dipping method), a brush coating method, a spray coating method, a spin coating method, a die coating method and a squeegee method.

[0110]

When contact with a solution is performed by an immersion method, immersion time can vary depending on various factors. Immersion of a molding in an acidic polymer solution or a basic polymer solution is preferably performed for 1 to 30 minutes, more preferably 2 to 20 minutes, and most preferably 1 to 5 minutes.

[0111]

The concentration of acidic and basic polymer solutions can vary depending on properties of an acidic polymer or a basic polymer, thickness of a desired coating layer, and other various factors. The concentration of the acidic or basic polymer is preferably from 0.001 to 10% by weight, more preferably from 0.005 to 5% by weight, and most preferably from 0.01 to 3% by weight.

[0112]

The pH of acidic and basic polymer solutions is preferably

maintained within a range from 2 to 5, and more preferably from 2.5 to 4.5.

[0113]

Removal of surplus acidic and basic polymers by washing is commonly performed by rinsing a molding after coating using clean water or an organic solvent. Rinsing is preferably performed by immersing the molding in water or an organic solvent or exposing to a water flow or an organic solvent flow. Rinsing may be completed in one step. However, it was recognized that it is efficient that a rinsing step is performed plural times. Rinsing is preferably performed in 2 to 5 steps. Immersion of each molding in a rinsing solution is preferably performed for 1 to 3 minutes.

[0114]

Pure water is also preferably used as the rinsing solution. In order to increase adhesion of a coating layer, it is preferred to use an aqueous buffered solution having pH adjusted within a range from 2 to 7, more preferably from 2 to 5, and still more preferably from 2.5 to 4.5.

[0115]

The step of drying or removing an excess rinsing solution may also be included. A molding can be dried to some extent by merely being left to stand under air atmosphere. Drying is preferably accelerated by supplying a mild air flow to the surface. Flow rate of the air flow can be adjusted as a function of the

strength of a material to be dried, and mechanical fixturing of a material. It is not necessary to completely dry a molding. Herein, it is important to remove droplets of a solution adhered onto a surface of the molding as compared with drying of the molding. Therefore, the molding is only dried until a film of water or a solution on the surface of the mold is removed, resulting in shortening of the process time, favorably.

[0116]

It is preferred that an acidic polymer and a basic polymer are alternately coated. It is possible to obtain a low water content soft lens for eye, which has excellent wettability and lubricity that cannot be obtained by a single layer, and also has excellent comfort that cannot be obtained by a single layer, by alternately coating the polymers.

[0117]

The coating layer can be asymmetric. As used herein, "asymmetric" refers to the fact that a coating layer formed on a first side of a low water content soft lens for eye is different from that formed on a second side opposite the first side. As used herein, "different coating layer" refers to the fact that a coating layer formed on a first side and a coating layer formed on a second side each has different surface characteristics or functionalities.

[0118]

The thickness of the coating layer can be controlled by

adding one or more salts such as sodium chloride to an acidic or basic polymer solution. The concentration of the salt is preferably from 0.1 to 2.0% by weight. As the concentration of the salt increases, a polyelectrolyte exhibits a more spherical spatial structure. However, when the concentration becomes too high, even if the polyelectrolyte is deposited on a surface of a molding, it is not satisfactorily deposited. More preferably, the concentration of the salt is from 0.7 to 1.3% by weight.

[0119]

The low water content soft lens for eye of the present invention is useful as a lens for eye, such as a low water content soft contact lens, an intraocular lens, an artificial cornea, a corneal inlay, a corneal onlay or a spectacle lens. The soft lens is particularly suitable as a low water content soft contact lens.

[Examples]

[0120]

The present invention will be specifically described below by way of Examples, but the present invention is not limited thereto.

[0121]

Analytical Method and Evaluation Method

In the present description, dry state means a state where a specimen is vacuum-dried at 40°C for 16 hours, and then vacuum-dried at room temperature (25°C) for 5 hours vacuum. The

degree of vacuum in the vacuum drying is set to 2 hPa or less. The measurement of mechanical properties in a dry state is carried out as soon as possible after the vacuum drying.

[0122]

In the present description, wet state means a state where a specimen is immersed in pure water at room temperature (25°C) for 24 hours or more. The measurement of mechanical properties in a wet state is carried out as soon as possible after pulling out the specimen from pure water.

[0123]

(1) Molecular Weight

Weight average molecular weight and number average molecular weight were measured by a GPC method under the following conditions.

Pump: TOSOH DP-8020

Detector: TOSOH RI-8010

Column oven: Shimadzu CTO-6A

Auto-sampler: TOSOH AS-8010

Column: TOSOH tskgel GMHHR-M (7.8 mm in inner diameter × 30 cm, 5 μm in particle diameter) × two columns

Column temperature: 35°C

Mobile phase: chloroform

Flow rate: 1.0 ml/minute

Sample concentration: 0.4% by weight

Injection amount: 100 μL

Standard sample: polystyrene (having a molecular weight of 1,010 to 1,090,000)

(2) Elongation

Using a prescribed blanking die, specimens each measuring 5 mm in width (minimum portion), 14 mm in length and about 0.2 mm in thickness were cut out from contact lens-shaped samples, and then stretched up to the length, which is 1.5 times (elongation of 50%) longer than an initial length, by hands. Five specimens were tested and the number of specimens, which were not broken, was written.

[0124]

(3) Folding Resistance

A contact lens-shaped specimen was folded in two by fingers and then strongly rubbed by fingers. Five specimens were tested and judged by the following criteria.

- A: All specimens are not failed.
- B: Some specimens are not failed.
- C: All specimens are failed with slight degree.
- D: All specimens are failed with intermediate degree between C and E.
- E: All specimens are failed to fragments.

[0125]

(4) Transparency

A contact lens-shaped specimen was visually observed and transparency was evaluated by the following criteria.

- A: Transparent with no turbidity
- B: White turbidity to about intermediate degree between A and C
- C: Semi-transparent with white turbidity.
- D: White turbidity with about intermediate degree between C and E
- E: White turbidity with no transparency

[0126]

(5) Water Content

A contact lens-shaped specimen was used. The specimen was dried by a vacuum drying oven at 40°C for 16 hours and weight (Wd) was measured. After the specimen was hydrated by immersing in pure water in a constant temperature bath at 40°C at least overnight, water on a surface was wiped off by a wiping cloth ("Kimwipe®", manufactured by NIPPON PAPER CRECIA Co., LTD.) and weight (Ww) was measured. Water content was determined by the following equation. In the case the obtained value is less than 1%, it was judged as measurement limitation or less and was written as "less than 1%".

$$\text{Water content (\%)} = 100 \times (Ww - Wd) / Ww$$

(6) Water Wettability

A contact lens-shaped specimen was immersed in a borate buffer (pH 7.1 to 7.3) in a beaker at room temperature. The beaker containing the specimen and the borate buffer was exposed to ultrasonic using a ultrasonic cleaner (for 1 minute). The

specimen was pulled up from the borate buffer and the specimen was held in air so that a diameter direction becomes vertical. A state of a surface of the specimen was visually observed, and then judged by the following criteria.

- A: A liquid film on a surface is held for 20 seconds or more.
- B: A liquid film on a surface is broken within 10 to 20 seconds.
- C: A liquid film on a surface is broken within 5 to 10 seconds.
- D: A liquid film on a surface is broken within 1 to 5 seconds.
- E: A liquid film on a surface is broken instantly (within 1 second).

[0127]

(7) Measurement of Dynamic Contact Angle

Using, as dynamic contact angle samples, film-shaped specimens each measuring 5 mm × 10 mm × about 0.1 mm cut out from samples molded into a film, or strip-shaped specimens of 5 mm in width cut out from contact lens-shaped samples, advancing dynamic contact angle relative to a borate buffer (pH 7.1 to 7.3) was measured. An immersion rate was set to 0.1 mm/sec, and an immerse depth was set to 7 mm.

[0128]

(8) Tensile Elastic Modulus, Elongation at Break

Using a prescribed blanking die, specimens each measuring 5 mm in width (minimum portion), 14 mm in length and 0.2 mm in thickness were cut out from contact lens-shaped samples. Using the specimens, a tensile test was carried out by a TENSILON Model

RTM-100, manufactured by ORIENTEC Co., Ltd. A testing speed was 100 mm/minute, and a distance between grips (initial) was 5 mm.

[0129]

(9) Lubricity

Lubricity was subjected to sensory evaluation after rubbing samples (contact lens shape) in a wet state five times with a finger of a person.

A: Excellent lubricity

B: About intermediate lubricity between A and C

C: Moderate lubricity

D: Little lubricity (about intermediate lubricity between C and E)

E: No lubricity

[0130]

(10) Adhesion of Mucin

Mucin, Bovine Submaxillary Gland (Catalog No. 499643) manufactured by CALBIOCHEM Corporation was used as mucin. Contact lens-shaped samples were immersed in an aqueous mucin solution having a concentration of 0.1% under the conditions of 37°C for 20 hours, and then the amount of mucin adhered to samples was determined by a bicinchoninic acid (BCA) protein assay method.

[0131]

(11) Adhesion of Lipid

In a 500 ml beaker, a stirring bar (36 mm) was placed, and

1.5 g of methyl palmitate and 500 g of pure water were charged. A temperature of a water bath was set to 37°C and the above beaker was placed in the center of the water bath, followed by stirring for one hour using a magnetic stirrer. A rotation speed was set to 600 rpm. Contact lens-shaped samples were put in a lens basket one by one and then put in the above beaker, followed by stirring. After 1 hour, stirring was stopped and samples in the lens basket were subjected to rubbing cleaning using city water at 40°C and a liquid detergent for domestic use ("Mamalemon[®]", manufactured by Lion Corporation). After cleaning, samples were put in a screw tube containing a borate buffer (pH 7.1 to 7.3) and then immersed in an ice bath for 1 hour. After pulling out the screw tube from the ice bath, white turbidity of samples was visually observed and the amount of methyl palmitate adhered to samples was judged by the following criteria.

- A: Transparent with no white turbidity
- B: Slight white turbidity is observed
- C: Considerable white turbidity is observed
- D: White turbidity accounts for most part
- E: White turbidity accounts for entirety

[0132]

(12) Artificial Lacrimal Fluid Immersion Test

A tear-like fluid (TLF) buffer solution, which was prepared in accordance with the method disclosed in lines 5 to 36 on page 32 of WO 2008/127299 pamphlet, except that oleic acid is used

in place of the oleic acid propyl ester, was used as an artificial lacrimal fluid. In 1 well of a multiplate for culture (24-well model, material: polystyrene, radiosterilized), 2 mL of an artificial lacrimal fluid was charged and then one sample (with contact lens shape) was immersed. Shaking was carried out at 100 rpm and 37°C for 24 hours. After pulling out the sample, the sample was lightly washed with phosphate buffer solution (PBS) and then immersed in the well in which the artificial lacrimal fluid was replaced by 2 mL of an artificial lacrimal fluid. Furthermore, after shaking at 100 rpm and 37°C for 24 hours, the sample was lightly washed with PBS and the amount of deposits was observed by visually evaluating the degree of white turbidity of the sample. The evaluation was carried out according to the following criteria.

- A: No white turbidity is observed.
- B: Slight white turbidity (less than 10% of area) is observed
- C: Considerable white turbidity (10 to 50% of area) is observed
- D: White turbidity accounts for most part (50 to 100% of area), while back side can be seen through
- E: Thick white turbidity accounts for entirety, while back side cannot be easily seen through

[0133]

(13) Transparency (Projector)

In a glass petri dish, a borate buffer (pH 7.1 to 7.3) was charged, and then a contact lens-shaped sample was placed. Using

a universal projector (MODEL V-10A, manufactured by Nikon Corporation), transparency was visually observed when irradiating samples in a petri dish with light from above and below, and then evaluated according to the following criteria.

- A: Transparent with no white turbidity
- B: Slight white turbidity is observed
- C: Considerable white turbidity is observed
- D: White turbidity accounts for most part
- E: White turbidity accounts for entirety

[0134]

(14) Degree of Pigmentation

Degree of pigmentation (depth of blue color) of samples (contact lens shape) was visually observed and then evaluated according to the following criteria.

- A: Coloration is recognized at a glance
- B: About intermediate degree between A and C of pigmentation
- C: Slight coloration is recognized
- D: About intermediate degree between C and D of pigmentation
- E: No coloration is recognized

[0135]

(15) Lens Molding Ratio

Lens molding ratio was determined by dividing a diameters of a sample (with contact lens shape) by a diameter of a gap portion (having a shape corresponding to the sample shape) of a mold used for molding the sample.

[0136]

(16) Friction

Using the apparatus shown in Fig. 1, a dynamic friction between a film, as a sample, and an artificial leather was measured. An artificial leather 1 ("SUPPLALE[®]", model number: PBZ13001, manufactured by Idemitsu Technofine Co., Ltd.) was stuck onto one surface of a glass plate measuring 26 mm × 26 mm × 1.4 mm to which a fishing line for pulling in a horizontal direction is attached. The artificial leather was stuck so that the back side faces outside. A film 2 measuring 60 mm × 60 mm × 0.25 mm in a wet state was placed on a horizontal rubber plate 3 and then a surface of the film was sufficiently wetted with a borate buffer (pH 7.1 to 7.3). The above glass plate was placed therein so that the artificial leather faces the film, and then a plastic container 4 containing small iron balls (the total weight of iron balls and a container is 50 g) was placed thereon. Using a tensile testing machine (RTM-100, manufactured by ORIENTEC Co., Ltd.), the fishing line attached to the glass plate was pulled at a rate of 100 mm/minute in a horizontal direction through a pulley. At this time, a dynamic friction between the artificial leather (back side) and the film was measured by a force to be applied to the tensile testing machine.

(17) Boiling Resistance

Samples (with contact lens shape) immersed in clean pure water were put in a closed vial bottle. Autoclave sterilization

was carried out at 121°C for 30 minutes, and then samples were cooled to room temperature. Five cycles were repeated, one cycle including a series of the above operations. Thereafter, the above-mentioned water wettability (6) was evaluated.

(18) Scrubbing Resistance A

Samples (with contact lens shape) were placed in the recess formed in the center of the flat of the hand and a cleaning solution ("OPTI FREE[®]", ALCON JAPAN LTD.) was added. After scrubbing front and back sides (each 10 times) by ball of the forefinger of another hand, samples were put in a screw tube containing clean "OPTI FREE[®]" and then left to stand for 4 hours or more. Fifteen cycles were repeated, provided that one cycle includes a series of the above operations. Samples were then washed with pure water and immersed in a borate buffer (pH 7.1 to 7.3). Thereafter, the above-mentioned water wettability (6) was evaluated.

(19) Scrubbing Resistance B

In the same manner as in (18), except for using "ReNU[®]" (Bausch & Lomb Incorporated) in place of "OPTI FREE[®]", the evaluation was carried out.

[0137]

Reference Example 1

Polydimethylsiloxane having a methacryloyl group at both ends (DMS-R31, Gelest, Inc., below-mentioned compound of the formula (M2), weight average molecular weight of 30,000, number average molecular weight of 13,000) (20 parts by weight) as a

component A, trifluoroethyl acrylate (Biscoat 3F, Osaka Organic Chemical Industry Ltd.) (80 parts by weight) as a component B, IRGACURE® 1850 (Ciba Specialty Chemicals Inc., 2 parts by weight) and tetrahydrolinalool (20 parts by weight) were mixed and then stirred. As a result, a uniform and transparent monomer mixture was obtained. This monomer mixture was charged in a test tube and degassing was carried out under reduced pressure of 20 Torr (27 hPa) while stirring using a touch mixer, and then the pressure was returned to atmospheric pressure using an argon gas. This operation was repeated three times. In a glove box under a nitrogen atmosphere, the monomer mixture was injected into a mold for contact lens made of a transparent resin (poly-4-methylpentene-1) and then polymerized by irradiating with light (8,000 lux, 20 minutes) using a fluorescent lamp (Toshiba Corporation, FL-6D, quasi-daylight, 6W, 4 lamps). After polymerization, the whole mold was immersed in an aqueous 60% by weight isopropyl alcohol solution and a contact lens-shaped molding was removed from the mold. The obtained molding was immersed in a large excess amount of an aqueous 80% by weight isopropyl alcohol solution at 60°C for 2 hours. Furthermore, the molding was immersed in a large excess amount of an aqueous 50% by weight isopropyl alcohol solution at room temperature for 30 minutes, followed by immersion in a large excess amount of an aqueous 25% by weight isopropyl alcohol solution at room temperature for 30 minutes, and further immersion in a large

excess amount of pure water at room temperature for 30 minutes. Finally, the molding immersed in clean pure water was put in a closed vial bottle, and then autoclave sterilization was carried out at 121°C for 30 minutes. The obtained molding had a water content of less than 1%. The evaluation results of the obtained molding are shown in Table 1.

[0138]

Reference Examples 2 to 12

In the very same manner as in Reference Example 1, except that the use amounts of components A and B were changed to amounts shown in Table 1, moldings were obtained. Both the obtained moldings had a water content of less than 1%. The evaluation results of the obtained molding are shown in Table 1.

[0139]

[Table 1]

	Component A DMS-R31 (Parts by weight)	Component B Biscoat 3F (Parts by weight)	Si atom Content (% by weight)	Evaluation results				
				Transparency	Elongation (number of specimens which were not broken)	Folding resistance	Tensile elastic modulus (kPa)	Elongation at break (%)
Reference Example 1	20	80	7.4					
Reference Example 2	40	60	15	A	5	A	450	400
Reference Example 3	45	55	17	A	5	A	510	250
Reference Example 4	50	50	19	A	5	A	Unevaluated	Unevaluated
Reference Example 5	55	45	20	B	5	A	Unevaluated	Unevaluated
Reference Example 6	60	40	22	C	5	A	560	270
Reference Example 7	65	35	24	C	5	A	Unevaluated	Unevaluated
Reference Example 8	70	30	26	C	5	A	Unevaluated	Unevaluated
Reference Example 9	75	25	28	C	5	A	Unevaluated	Unevaluated
Reference Example 10	80	20	30	C	5	A	470	270
Reference Example 11	100	0	37	D	3	A	Unevaluated	Unevaluated
Reference Example 12	0	100	-	*1	*1	*1	*1	*1

49

*1: failed to mold into a lens shape due to poor polymerization

[0140]

Reference Examples 13 to 19

In the very same manner as in Reference Example 1, except that polydimethylsiloxane having a methacryloyl group at both ends (DMS-R22, Gelest, Inc., below-mentioned compound of the formula (M2), weight average molecular weight of 8,300, number average molecular weight of 7,400) was used in the amount shown in Table 2 as a component A, and that trifluoroethyl acrylate (Biscoat 3F, Osaka Organic Chemical Industry Ltd.) was used in the amount shown in Table 2 as a component B, moldings were obtained. The obtained molding had a water content of less than 1%. The evaluation results of the obtained molding are shown in Table 2.

[0141]

[Table 2]

	Component A DMS-R22 (Parts by weight)	Component B Biscoat 3F (Parts by weight)	Si atom content (% by weight)	Evaluation results				
				Transparency	Elongation (number of specimens which were not broken)	Folding resistance	Tensile elastic modulus (kPa)	Elongation at break (%)
Reference Example 13	10	90	3.7	C	5	B	Unevaluated	Unevaluated
Reference Example 14	20	80	7.3	A	5	B	630	190
Reference Example 15	40	60	15	A	5	B	960	170
Reference Example 16	50	50	18	A	5	C	Unevaluated	Unevaluated
Reference Example 17	60	40	22	A	4	E	1140	90
Reference Example 18	80	20	29	A	4	E	1110	80
Reference Example 19	100	0	37	A	4	E	920	160

[0142]

Reference Examples 20 to 24

In the very same manner as in Reference Example 1, except that polydimethylsiloxane having a methacryloyl group at both ends (X-22-164C, Shin-Etsu Chemical Co., Ltd., weight average molecular weight of 7,200, number average molecular weight of 4,800) (50 parts by weight) was used as a component A, and that the monomer having a fluoroalkyl group (50 parts by weight) shown in Table 3 was used as a component B, moldings were obtained. The evaluation results of the obtained molding are shown in Table 3.

[0143]

[Table 3]

	Component A X-22-164C (Parts by weight)	Component B		Si atom content (%byweight)	Evaluation results		
		Name	(Parts by weight)		Transparency	Elongation (number of specimens which were not broken)	Folding resistance
Reference Example 20	50	Biscoat 3FM	50	18	A	2	D
Reference Example 21	50	Biscoat 8F	50	18	B	0	E
Reference Example 22	50	Biscoat 3F	50	18	A	1	D
Reference Example 23	50	Biscoat 17F	50	—	*1	*1	*1
Reference Example 24	50	HFIP-M	50	18	A	0	D

*1: abandoned polymerization because of phase separation of polymerization raw solution

[0144]

Biscoat 3FM: Trifluoroethylmethacrylate (Osaka Organic Chemical Industry Ltd.)

Biscoat 8F: Octafluoropentyl acrylate (Osaka Organic Chemical Industry Ltd.)

Biscoat 3F: Trifluoroethyl acrylate (Osaka Organic Chemical Industry Ltd.)

Biscoat 17F: Heptadecafluorodecyl acrylate (Osaka Organic Chemical Industry Ltd.)

HFIP-M: Hexafluoroisopropyl methacrylate (Central Glass Co., Ltd.).

[0145]

Reference Examples 25 to 37

In the very same manner as in Reference Example 1, except that the polydimethylsiloxane having a methacryloyl group at both ends shown in Table 4 (below-mentioned compound of the formula (M2)) was used in the amount shown in Table 4 as a component A, the component B was not used, and the monomer shown in Table 4 (50 parts by weight) was used in the amount shown in Table 4 as a component C, moldings were obtained. The evaluation results of the obtained molding are shown in Table 4.

[0146]

[Table 4]

	Component A				Component C		Si atom content (% by weight)	Evaluation results		
	Name	Weight average molecular weight	Number average molecular weight	Parts by weight	Name	Parts by weight		Transparency	Elongation (number of specimens which were not broken)	Folding resistance
Reference Example 25	X-22-164A	3,100	2,300	50	Butyl acrylate	50	17	A	0	E
Reference Example 26	X-22-164B	5,200	3,700	50	Butyl acrylate	50	18	A	0	D
Reference Example 27	X-22-164C	7,200	4,800	50	Butyl acrylate	50	18	B	1	D
Reference Example 28	X-22-164C	7,200	4,800	50	N,N-dimethyl acrylamide	50	18	E	0	E
Reference Example 29	X-22-164A	3,100	2,300	50	2-ethylhexyl acrylate	50	17	D	0	D
Reference Example 30	X-22-164B	5,200	3,700	50	2-ethylhexyl acrylate	50	18	D	0	D
Reference Example 31	X-22-164C	7,200	4,800	50	2-ethylhexyl acrylate	50	18	B	1	D
Reference Example 32	DMS-R31	30,000	13,000	50	Butyl acrylate	50	19	B	5	A
Reference Example 33	DMS-R22	8,300	7,400	50	Butyl acrylate	50	18	B	5	A
Reference Example 34	DMS-R31	30,000	13,000	50	2-ethylhexyl acrylate	50	19	A	5	A
Reference Example 35	DMS-R22	8,300	7,400	50	2-ethylhexyl acrylate	50	18	A	5	A
Reference Example 36	Synthesized compound 1	113,000	75,000	50	2-ethylhexyl acrylate	50	19	B	5	A
Reference Example 37	Synthesized compound 2	157,000	103,000	50	2-ethylhexyl acrylate	50	19	D	4	B

Synthesized compound 1: synthesized in laboratory by inventors

Synthesized compound 2: synthesized in laboratory by inventors

[0147]

<Synthesis Examples>

Synthesis Examples of copolymers used for coating in Examples are shown. In Synthesis Examples, molecular weight of each copolymer was measured under the following conditions.

(GPC Measurement Conditions)

Apparatus: Prominence GPC system, manufactured by Shimadzu Corporation

Pump: LC-20AD

Auto-sampler: SIL-20AHT

Column oven: CTO-20A

Detector: RID-10A

Column: manufactured by TOSOH CORPORATION GMPWXL (7.8 mm in inner diameter × 30 cm, 13 μm in particle diameter)

Solvent: water/methanol = 1/1 (addition of 0.1N lithium nitrate)

Flow rate: 0.5 ml/minute

Measurement time: 30 minutes

Sample concentration: 0.1% by weight

Injection amount: 100 μL

Standard sample: Polyethylene oxide standard sample, manufactured by Agilent (0.1 kD to 1,258 kD).

[0148]

Synthesis Example 1

<CPVPA: N-vinylpyrrolidone/acrylic acid (molar ratio of 2/1)>

In a 500 mL three-necked flask, N-vinylpyrrolidone (66.68

g, 0.60 mol), acrylic acid (21.62 g, 0.30 mol), dimethyl sulfoxide (353.96 g), a polymerization initiator VA-061 (Wako Pure Chemical Industries, Ltd., 0.1408 g, 0.562 mmol) and 2-mercaptoethanol (43.8 μ L, 0.63 mmol) were charged, and then equipped with a three-way stop-cock, a reflux condenser tube, a thermometer and a mechanical stirrer. The concentration of the monomer was 20% by weight. After degassing inside the three-necked flask using a vacuum pump and repeating replacement by argon three times, stirring was carried out at 50°C for 0.5 hours, followed by temperature rise to 70°C and further stirring for 6.5 hours. After completion of the polymerization, the polymerization reaction solution was cooled to room temperature and 100 mL of water was added, and then the solution was poured into 400 mL of acetone and the mixed solution was left to stand overnight. On the next day, 200 mL of acetone was further added and the solution was left to stand, and then the supernatant was removed by decantation. The obtained solid component was washed seven times with acetone/water (= 400 mL/100 mL). The solid component was dried overnight by a vacuum drying oven at 60°C. Liquid nitrogen was charged and the solid component was crushed by a spatula, and then dried by a vacuum drying oven at 60°C for 3 hours. The thus obtained copolymer had a molecular weight of M_n : 46 kD, M_w : 180 kD ($M_w/M_n = 3.9$).

[0149]

Synthesis Example 2

<CPVPA: N-vinylpyrrolidone/acrylic acid (molar ratio of 1/2)>

In a 500 mL three-necked flask, N-vinylpyrrolidone (33.34 g, 0.30 mol), acrylic acid (43.24 g, 0.60 mol), dimethyl sulfoxide (307.08 g), a polymerization initiator VA-061 (Wako Pure Chemical Industries, Ltd., 0.1408 g, 0.562 mmol) and 2-mercaptoethanol (43.8 μ L, 0.63 mmol) were charged, and then equipped with a three-way stop-cock, a reflux condenser tube, a thermometer and a mechanical stirrer. The concentration of the monomer was 20% by weight. After degassing inside the three-necked flask using a vacuum pump and repeating replacement by argon three times, stirring was carried out at 50°C for 0.5 hours, followed by temperature rise to 70°C and further stirring for 6.5 hours. After completion of the polymerization, the polymerization reaction solution was cooled to room temperature and 100 mL of water was added, and then the solution was poured into 500 mL of acetone and the mixed solution was left to stand overnight. On the next day, 200 mL of acetone was further added and then the supernatant was removed by decantation. The obtained solid component was washed seven times with acetone/water (= 700 mL/100 mL). The solid component was dried overnight by a vacuum drying oven at 60°C. Liquid nitrogen was charged and the solid component was crushed by a spatula, and then dried by a vacuum drying oven at 60°C for 3 hours. The thus obtained copolymer had a molecular weight of Mn: 65 kD, Mw: 202 kD ($M_w/M_n = 3.1$).

[0150]

Synthesis Example 3

<CPVPA: N-vinylpyrrolidone/acrylic acid (molar ratio of 90/10)>

In a 500 mL three-necked flask, N-vinylpyrrolidone (NVP, 90.02 g, 0.81 mol), acrylic acid (6.49 g, 0.09 mol), dimethyl sulfoxide (386.8 g), a polymerization initiator VA-061 (Wako Pure Chemical Industries, Ltd., 0.1408 g, 0.562 mmol) and 2-mercaptoethanol (2-ME, 43.8 μ L, 0.63 mmol) were charged, and then equipped with a three-way stop-cock, a reflux condenser tube, a thermometer and a mechanical stirrer. The concentration of the monomer was 20% by weight. After degassing inside the three-necked flask using a vacuum pump and repeating replacement by argon three times, stirring was carried out at 50°C for 0.5 hours, followed by temperature rise to 70°C and further stirring for 6.5 hours. After completion of the polymerization, the polymerization reaction solution was cooled to room temperature and 100 mL of water was added, and then the solution was poured into 500 mL of acetone and the mixed solution was left to stand overnight. On the next day, 200 mL of acetone was further added and 100 mL of hexane was added, and then the supernatant was removed by decantation. The obtained solid component was washed seven times with acetone/water (= 500 mL/100 mL). The solid component was dried overnight by a vacuum drying oven at 60°C. Liquid nitrogen was charged and the solid component was crushed by a spatula, and then dried by a vacuum drying oven at 60°C for 3 hours. The thus obtained copolymer had a molecular weight

of Mn: 35 kD, Mw: 130 kD ($M_w/M_n = 3.8$).

[0151]

Synthesis Example 4

<CPVPA: N-vinylpyrrolidone/acrylic acid (molar ratio of 80/20)>

In the same manner as in Synthesis Example 3, except that 0.72 mol of N-vinylpyrrolidone and 0.18 mol of acrylic acid were respectively used, a copolymer was obtained. The thus obtained copolymer had a molecular weight of Mn: 45 kD, Mw: 193 kD ($M_w/M_n = 4.4$).

[0152]

Synthesis Example 5

<CPDA: N,N-dimethylacrylamide/acrylic acid (molar ratio of 2/1)>

In a 500 mL three-necked flask, N,N-dimethylacrylamide (59.50 g, 0.600 mol), acrylic acid (21.62 g, 0.300 mol), pure water (325.20 g), a polymerization initiator VA-061 (Wako Pure Chemical Industries, Ltd., 0.1408 g, 0.562 mmol) and 2-mercaptoethanol (43.8 μ L, 0.63 mmol) were charged, and then equipped with a three-way stop-cock, a reflux condenser tube, a thermometer and a mechanical stirrer. The concentration of the monomer was 20% by weight. After degassing inside the three-necked flask using a vacuum pump and repeating replacement by argon three times, stirring was carried out at 50°C for 0.5 hours, followed by temperature rise to 70°C and further stirring for 6.5 hours. After completion of the polymerization, the polymerization reaction solution was concentrated up to 400 g

by an evaporator, and then the solution was poured into 2-propanol/n-hexane (=500 mL/500 mL). After being left to stand, the supernatant was removed by decantation. The obtained solid component was washed three times with 2-propanol/n-hexane (= 250 mL/250 mL). The solid component was washed seven times with acetone/water (= 500 mL/100 mL). The solid component was dried overnight by a vacuum drying oven at 60°C. Liquid nitrogen was charged and the solid component was crushed by a spatula, and then dried by a vacuum drying oven at 60°C for 3 hours. The thus obtained copolymer had a molecular weight of Mn: 55 kD, Mw: 192 kD (Mw/Mn = 3.5).

[0153]

Synthesis Example 6

<CPDA: N,N-dimethylacrylamide/acrylic acid (molar ratio of 1/2)>

In a 500 mL three-necked flask, N,N-dimethylacrylamide (29.70 g, 0.300 mol), acrylic acid (43.20 g, 0.600 mol), pure water (292.40 g), a polymerization initiator VA-061 (Wako Pure Chemical Industries, Ltd., 0.1408 g, 0.562 mmol) and 2-mercaptoethanol (43.8 μ L, 0.63 mmol) were charged, and then equipped with a three-way stop-cock, a reflux condenser tube, a thermometer and a mechanical stirrer. The concentration of the monomer was 20% by weight. After degassing inside the three-necked flask using a vacuum pump and repeating replacement by argon three times, stirring was carried out at 50°C for 0.5 hours, followed by temperature rise to 70°C and further stirring

for 6.5 hours. After completion of the polymerization, the polymerization reaction solution was concentrated up to 350 g by an evaporator, and then the solution was poured into 2-propanol/n-hexane (=500mL/500mL). After being left to stand, the supernatant was removed by decantation. The obtained solid component was washed three times with 2-propanol/n-hexane (= 250 mL/250 mL). The solid component was dried overnight by a vacuum drying oven at 60°C. Liquid nitrogen was charged and the solid component was crushed by a spatula, and then dried by a vacuum drying oven at 60°C for 3 hours. The thus obtained copolymer had a molecular weight of Mn: 87 kD, Mw: 235 kD (Mw/Mn = 2.7).

[0154]

Synthesis Example 7

<CPDA: N,N-dimethylacrylamide/acrylic acid (molar ratio of 90/10)>

In a 500 mL three-necked flask, N,N-dimethylacrylamide (DMA, 80.30 g, 0.810 mol), acrylic acid (6.49 g, 0.090 mol), pure water (347.90 g), a polymerization initiator VA-061 (Wako Pure Chemical Industries, Ltd., 0.1408 g, 0.562 mmol) and 2-mercaptoethanol (2-ME, 43.8 μ L, 0.63 mmol) were charged, and then equipped with a three-way stop-cock, a reflux condenser tube, a thermometer and a mechanical stirrer. The concentration of the monomer was 20% by weight. After degassing inside the three-necked flask using a vacuum pump and repeating replacement by argon three

times, stirring was carried out at 50°C for 0.5 hours, followed by temperature rise to 70°C and further stirring for 6.5 hours. After completion of the polymerization, the polymerization reaction solution was concentrated up to 470 g by an evaporator, and then the solution was poured into 2-propanol/n-hexane (= 500 mL/500 mL). After being left to stand, the supernatant was removed by decantation. The obtained solid component was washed five times with 2-propanol/n-hexane (= 250 mL/250 mL). The solid component was dried overnight by a vacuum drying oven at 60°C. Liquid nitrogen was charged and the solid component was crushed by a spatula, and then dried by a vacuum drying oven at 60°C for 3 hours. The thus obtained copolymer had a molecular weight of Mn: 54 kD, Mw: 162 kD ($M_w/M_n = 3.0$).

[0155]

Synthesis Example 8

<CPDA: N,N-dimethylacrylamide/acrylic acid (molar ratio of 95/5)>

In a three-necked flask, N,N-dimethylacrylamide (DMA, 0.19 mol), acrylic acid (AA, 0.01 mol), pure water, a polymerization initiator VA-061 (Wako Pure Chemical Industries, Ltd., 0.093 mmol) and 2-mercaptoethanol (2-ME, 0.07 mmol) were charged, and then equipped with a three-way stop-cock, a reflux condenser tube, a thermometer and a mechanical stirrer. The concentration of the monomer was 20% by weight. After degassing inside the three-necked flask using a vacuum pump and repeating replacement

by argon three times, stirring was carried out at 50°C for 0.5 hours, followed by temperature rise to 70°C and further stirring for 6.5 hours. After completion of the polymerization, the polymerization reaction solution was concentrated up to 350 g by an evaporator, and then the solution was poured into 2-propanol/n-hexane (=200 mL/200 mL). After being left to stand, the supernatant was removed by decantation. The obtained solid component was washed three times with 2-propanol/n-hexane (= 100 mL/100 mL). The solid component was dried overnight by a vacuum drying oven at 60°C. Liquid nitrogen was charged and the solid component was crushed by a spatula, and then dried by a vacuum drying oven at 60°C for 3 hours. The thus obtained copolymer had a molecular weight of Mn: 77 kD, Mw: 229 kD.

[0156]

Synthesis Examples 9 to 16

<CPDA: N,N-dimethylacrylamide/acrylic acid>

Polymers were obtained by the same procedure as in Synthesis Example 8, except that amounts and concentrations of monomers of N,N-dimethylacrylamide (DMA), acrylic acid (AA), a polymerization initiator VA-061 and 2-mercaptoethanol (2-ME) were set to values shown in Table 5.

[0157]

[Table 5]

	DMA (mol)	AA (mol)	VA-061 (mmol)	2-ME (mmol)	Monomer concentration (% by weight)
Synthesis Example 8	0.19	0.01	0.093	0.070	20
Synthesis Example 9	0.16	0.04	0.124	0.140	20
Synthesis Example 10	0.10	0.10	0.124	0.140	20
Synthesis Example 11	0.19	0.01	0.031	0.035	15
Synthesis Example 12	0.16	0.04	0.031	0.035	15
Synthesis Example 13	0.10	0.10	0.031	0.035	15
Synthesis Example 14	0.19	0.01	0.015	0.017	15
Synthesis Example 15	0.16	0.04	0.025	0.023	15
Synthesis Example 16	0.10	0.10	0.025	0.035	15

[0158]

Synthesis Example 17

<CPDEAC: N,N-diethyl acrylamide/acryloylmorpholine>

In a 300 mL three-necked flask, N,N-diethyl acrylamide (12.71 g, 0.100 mol), N-acryloylmorpholine (14.12 g, 0.100 mol), t-amyl alcohol (63.20 g), a polymerization initiator VA-061 (Wako Pure Chemical Industries, Ltd., 0.0310 g, 0.124 mmol) were charged, and then equipped with a three-way stop-cock, a reflux condenser tube, a thermometer and a mechanical stirrer. The concentration of the monomer was 30% by weight. After degassing inside the three-necked flask using a vacuum pump and repeating replacement by argon three times, stirring was carried out at 70°C for 1 hour, followed by temperature rise to 75°C and further stirring for 4 hours. After completion of the polymerization, the polymerization reaction solution was cooled to room temperature

and the solvent was distilled off by an evaporator, and then washed once with each of n-hexane/methanol (= 300 mL/80 mL, 130 mL/35 mL, 100 mL/20 mL and 100 mL/10 mL). The solid component was dried overnight by a vacuum drying oven at 60°C. Liquid nitrogen was charged and the solid component was crushed by a spatula, and then dried by a vacuum drying oven at 60°C for 3 hours. The thus obtained copolymer had a molecular weight of Mn: 49kD, Mw: 162kD (Mw/Mn = 3.3).

[0159]

Synthesis Example 18

<CPACDM: Acryloylmorpholine/N,N-dimethylacrylamide>

In a 300 mL three-necked flask, N-acryloylmorpholine (14.20 g, 0.101 mol), N,N-dimethylacrylamide (DMA, 9.92 g, 0.100 mol), t-amyl alcohol (96.63 g), a polymerization initiator VA-061 (Wako Pure Chemical Industries, Ltd., 0.0310 g, 0.124 mmol), 2-mercaptoethanol (86 μ L, 1.23 mmol) were charged, and then equipped with a three-way stop-cock, a reflux condenser tube, a thermometer and a mechanical stirrer. The concentration of the monomer was 20% by weight. After degassing inside the three-necked flask using a vacuum pump and repeating replacement by argon three times, stirring was carried out at 70°C for 1 hour, followed by temperature rise to 75°C and further stirring for 4 hours. After completion of the polymerization, the polymerization reaction solution was cooled to room temperature and the solvent was distilled off by an evaporator, and then

washed once with each of n-hexane/methanol (= 400 mL/30 mL, 500 mL/40 mL, 130 mL/3 mL and 200 mL/7 mL). The solid component was dried overnight by a vacuum drying oven at 60°C. Liquid nitrogen was charged and the solid component was crushed by a spatula, and then dried by a vacuum drying oven at 60°C for 3 hours. The thus obtained copolymer had a molecular weight of Mn: 4.3 kD, Mw: 17 kD (Mw/Mn = 4.1)).

[0160]

Synthesis Example 19

<CPDEDM: N,N-diethyl acrylamide/N,N-dimethylacrylamide>

In a 300 mL three-necked flask, N,N-diethyl acrylamide (DEAA, 19.22 g, 0.151 mol), N,N-dimethylacrylamide (DMA, 14.88 g, 0.150 mol), TAA (104.65 g) and a polymerization initiator VA-061 (Wako Pure Chemical Industries, Ltd., 0.0465 g, 0.186 mmol) were charged, and then equipped with a three-way stop-cock, a reflux condenser tube, a thermometer and a mechanical stirrer. The concentration of the monomer was 25% by weight. After degassing inside the three-necked flask using a vacuum pump and repeating replacement by argon three times, stirring was carried out at 70°C for 1.5 hours, followed by temperature rise to 75°C and further stirring for 3.5 hours. After completion of the polymerization, the polymerization reaction solution was cooled to room temperature and the solvent was distilled off by an evaporator, and then washed once with each of n-hexane/methanol (= 500 mL/0 mL, 250 mL/25 mL, 200 mL/30 mL and 200 mL/3 mL). The solid component

was dried overnight by a vacuum drying oven at 60°C. Liquid nitrogen was charged and the solid component was crushed by a spatula, and then dried by a vacuum drying oven at 60°C for 3 hours. The thus obtained copolymer had a molecular weight of Mn: 90kD, Mw: 327kD (Mw/Mn = 3.7).

[0161]

Synthesis Example 20

<CPHEDM:

N-(2-hydroxyethyl)acrylamide/N,N-dimethylacrylamide>

In a 300 mL three-necked flask, N-(2-hydroxyethyl)acrylamide (15.04 g, 0.100 mol), N,N-dimethylacrylamide (9.96g, 0.100mol), t-amyl alcohol (99.80 g), polymerization initiator VA-061 (Wako Pure Chemical Industries, Ltd., 0.0310 g, 0.124 mmol) were charged, and then equipped with a three-way stop-cock, a reflux condenser tube, a thermometer and a mechanical stirrer. The concentration of the monomer was 20% by weight. After degassing inside the three-necked flask using a vacuum pump and repeating replacement by argon three times, stirring was carried out at 70°C for 1 hour, followed by temperature rise to 75°C and further stirring for 4 hours. After completion of the polymerization, the polymerization reaction solution was cooled to room temperature and the solvent was distilled off by an evaporator, and then washed once with each of n-hexane/methanol (= 200 mL/100 mL, 200 mL/100 mL, 100 mL/40 mL and 100 mL/60 mL). The solid component

was dried overnight by a vacuum drying oven at 60°C. Liquid nitrogen was charged and the solid component was crushed by a spatula, and then dried by a vacuum drying oven at 60°C for 3 hours. The thus obtained copolymer had a molecular weight of Mn: 109 kD, Mw: 660 kD ($M_w/M_n = 6.1$).

[0162]

Synthesis Example 21

<CPHA: 2-hydroxyethyl methacrylate/acrylic acid (molar ratio of 3/1)>

In a 300 mL three-necked flask, 2-hydroxyethyl methacrylate (HEMA, 17.1 g, 0.15 mol), acrylic acid (AA, 3.6 g, 0.05 mol), dimethyl sulfoxide (48.4 g) and a polymerization initiator VA-061 (Wako Pure Chemical Industries, Ltd., 0.0310 g, 0.124 mmol) were charged, and then equipped with a three-way stop-cock, a reflux condenser tube, a thermometer and a mechanical stirrer. The concentration of the monomer was 30% by weight. After degassing inside the three-necked flask using a vacuum pump and repeating replacement by argon three times, stirring was carried out at 60°C for 0.5 hours, followed by temperature rise to 70°C and further stirring for 4.5 hours. After completion of the polymerization, the polymerization reaction solution was cooled to room temperature and 100 mL of ethanol was added, and then the mixed solution was poured into 500 mL of water and left to stand overnight. On the next day, the supernatant was discarded and the obtained solid component was further washed twice with

500 mL of water. The solid component was dried overnight by a vacuum drying oven at 60°C. Liquid nitrogen was charged and the solid component was crushed by a spatula, and then dried by a vacuum drying oven at 60°C for 3 hours. The thus obtained copolymer had a molecular weight of Mn: 61 kD, Mw: 267 kD (Mw/Mn = 4.4).

[0163]

Synthesis Example 22

<CPHA: 2-hydroxyethyl methacrylate/acrylic acid (molar ratio of 3/1)>

In a 300 mL three-necked flask, 2-hydroxyethyl methacrylate (HEMA, 10.3 g, 0.09 mol), acrylic acid (AA, 2.2 g, 0.03 mol), dimethyl sulfoxide (49.7 g), polymerization initiator VA-061 (Wako Pure Chemical Industries, Ltd., 0.009 g, 0.038 mmol) and 2-mercaptoethanol (2-ME, 2.6 μ L, 0.038 mmol) were charged, and then equipped with a three-way stop-cock, a reflux condenser tube, a thermometer and a mechanical stirrer. The concentration of the monomer was 20% by weight. After degassing inside the three-necked flask using a vacuum pump and repeating replacement by argon three times, stirring was carried out at 60°C for 0.5 hours, followed by temperature rise to 70°C and further stirring for 4.5 hours. After completion of the polymerization, the polymerization reaction solution was cooled to room temperature and 20 mL of ethanol was added, and then the mixed solution was poured into 500 mL of water and left to stand overnight. On the

next day, the supernatant was discarded and the obtained solid component was further washed twice with 500 mL of water. The solid component was dried overnight by a vacuum drying oven at 60°C. Liquid nitrogen was charged and the solid component was crushed by a spatula, and then dried by a vacuum drying oven at 60°C for 3 hours. The thus obtained copolymer had a molecular weight of Mn: 83 kD, Mw: 188 kD ($M_w/M_n = 2.3$).

[0164]

Synthesis Example 23

<CPHA: 2-hydroxyethyl methacrylate/acrylic acid (molar ratio of 3/1)>

In a 300 mL three-necked flask, 2-hydroxyethyl methacrylate (HEMA, 10.3 g, 0.09 mol), acrylic acid (AA, 2.2 g, 0.03 mol), dimethyl sulfoxide (49.8 g), a polymerization initiator VA-061 (Wako Pure Chemical Industries, Ltd., 0.009 g, 0.038 mmol), 2-mercaptoethanol (2-ME, 7.8 μ L, 0.111 mmol) were charged, and then equipped with a three-way stop-cock, a reflux condenser tube, a thermometer and a mechanical stirrer. The concentration of the monomer was 20% by weight. After degassing inside the three-necked flask using a vacuum pump and repeating replacement by argon three times, stirring was carried out at 60°C for 0.5 hours, followed by temperature rise to 70°C and further stirring for 4.5 hours. After completion of the polymerization, the polymerization reaction solution was cooled to room temperature and 20 mL of ethanol was added, and then the mixed solution was

poured into 500 mL of water and left to stand overnight. On the next day, the supernatant was discarded and the obtained solid component was further washed twice with 500 mL of water. The solid component was dried overnight by a vacuum drying oven at 60°C. Liquid nitrogen was charged and the solid component was crushed by a spatula, and then dried by a vacuum drying oven at 60°C for 3 hours. The thus obtained copolymer had a molecular weight of Mn: 50 kD, Mw: 96 kD ($M_w/M_n = 1.9$).

[0165]

Synthesis Example 24

<CPHA: 2-hydroxyethyl methacrylate/acrylic acid (molar ratio of 1/1)>

In a 200 mL three-necked flask, 2-hydroxyethyl methacrylate (HEMA, 11.4 g, 0.10 mol), acrylic acid (AA, 7.21 g, 0.10 mol), dimethyl sulfoxide (74.5 g) and a polymerization initiator VA-061 (Wako Pure Chemical Industries, Ltd., 0.016 g, 0.062 mmol) were charged, and then equipped with a three-way stop-cock, a reflux condenser tube, a thermometer and a mechanical stirrer. The concentration of the monomer was 20% by weight. After degassing inside the three-necked flask using a vacuum pump and repeating replacement by argon three times, stirring was carried out at 60°C for 0.5 hours, followed by temperature rise to 70°C and further stirring for 6.5 hours. After completion of the polymerization, the polymerization reaction solution was cooled to room temperature, and then the mixed solution was poured into

water (1,000 mL)/ethanol (10 mL) and left to stand overnight. On the next day, the supernatant was discarded and the obtained solid component was further washed twice with 700 mL of water. The solid component was dried overnight by a vacuum drying oven at 60°C. Liquid nitrogen was charged and the solid component was crushed by a spatula, and then dried by a vacuum drying oven at 60°C for 3 hours. The thus obtained copolymer had a molecular weight of Mn: 79 kD, Mw: 226 kD ($M_w/M_n = 2.9$).

[0166]

Reference Example 38

Hereinafter, pure water means water purified by filtering through a reverse osmosis membrane.

Preparation of Coating Solution

<PEI solution A>

Polyethyleneimine (P3143, Sigma-Aldrich Corporation, molecular weight of 750,000) was dissolved in pure water to obtain an aqueous 1% by weight solution.

<PEI solution B>

Polyethyleneimine (P-70, 167-11951, Wako Pure Chemical Industries, Ltd., molecular weight of 70,000) was dissolved in pure water to obtain an aqueous 1% by weight solution.

<PAA solution>

Polyacrylic acid (169-18591, Wako Pure Chemical Industries, Ltd., molecular weight 250,000) was dissolved in pure water to obtain an aqueous 1.2% by weight solution.

<PAAM solution A>

Polyallylamine (PAA-15C, Nitto Boseki Co., Ltd., molecular weight 15,000) was dissolved in pure water to obtain an aqueous 1% by weight solution.

<PAAM solution B>

Polyallylamine (PAA-25, Nitto Boseki Co., Ltd., molecular weight 25,000) was dissolved in pure water to obtain an aqueous 1% by weight solution.

<PAS solution>

A diallyldimethylammonium chloride polymer (PAS-H-10L, Nitto Boseki Co., Ltd., molecular weight of 200,000) was dissolved in pure water to obtain an aqueous 1% by weight solution

<Solution of Copolymer>

The copolymers obtained in the Synthesis Examples shown in Table 6 were respectively dissolved in the solvents shown in Table 6 to obtain solutions having each concentration shown in Table 6.

[0167]

[Table 6]

	Copolymer	Copolymerization monomer A	Copolymerization monomer B	A (Molar ratio)	B (Molar ratio)	Mn (kD)	Mw (kD)	Solvent	Solution concentration (% by weight)
CPVPA solution A	Synthesis Example 1	NVP	AA	2	1	46	180	Pure water	1
CPVPA solution B	Synthesis Example 2	NVP	AA	1	2	65	202	Pure water	1
CPVPA solution C	Synthesis Example 3	NVP	AA	90	10	35	130	Pure water	1
CPVPA solution D	Synthesis Example 4	NVP	AA	80	20	45	193	Pure water	1
CPDA solution A	Synthesis Example 5	DMA	AA	2	1	55	192	Pure water	1
CPDA solution B	Synthesis Example 6	DMA	AA	1	2	87	235	Pure water	1
CPDA solution C	Synthesis Example 7	DMA	AA	90	10	54	162	Pure water	1
CPDA solution D	Synthesis Example 8	DMA	AA	95	5	77	229	Pure water	1
CPDA solution E	Synthesis Example 9	DMA	AA	80	20	80	227	Pure water	1
CPDA solution F	Synthesis Example 10	DMA	AA	50	50	84	195	Pure water	1
CPDA solution G	Synthesis Example 11	DMA	AA	95	5	139	423	Pure water	1
CPDA solution H	Synthesis Example 12	DMA	AA	80	20	114	442	Pure water	1
CPDA solution I	Synthesis Example 13	DMA	AA	50	50	148	472	Pure water	1
CPDA solution J	Synthesis Example 14	DMA	AA	95	5	190	609	Pure water	1

	Copolymer	Copolymerization monomer A	Copolymerization monomer B	A (Molar ratio)	B (Molar ratio)	Mn (kD)	Mw (kD)	Solvent	Solution concentration (% by weight)
CPDA solution K	Synthesis Example 15	DMA	AA	80	20	169	537	Pure water	1
CPDA solution L	Synthesis Example 16	DMA	AA	50	50	124	552	Pure water	1
CPDEAC solution	Synthesis Example 17	DEAA	ACMO	50	50	49	162	Pure water	1
CPACDM solution	Synthesis Example 18	ACMO	DMA	50	50	4.3	17	Pure water	1
CPDEDM solution	Synthesis Example 19	DEAA	DMA	50	50	90	327	Pure water	1
CPHEDM solution	Synthesis Example 20	HEAA	DMA	50	50	109	660	Pure water	1
CPHA solution A	Synthesis Example 21	HEMA	AA	3	1	61	267	Aqueous 0.5 wt% methanol solution	0.1
CPHA solution B	Synthesis Example 22	HEMA	AA	3	1	83	188	Aqueous 0.5 wt% methanol solution	0.1
CPHA solution C	Synthesis Example 23	HEMA	AA	3	1	50	96	Aqueous 0.5 wt% methanol solution	0.1
CPHA solution D	Synthesis Example 24	HEMA	AA	1	1	79	226	Aqueous 0.5 wt% methanol solution	0.1
CPHA solution E	Synthesis Example 23	HEMA	AA	3	1	50	96	Aqueous 0.5 wt% methanol solution	0.01
CPHA solution F	Synthesis Example 23	HEMA	AA	3	1	50	96	Aqueous 5 wt% methanol solution	1

NVP: N-vinylpyrrolidone

DMA: N,N-dimethylacrylamide

DEAA: N,N-diethylacrylamide

ACMO: Acryloylmorpholine

HEAA: N-(2-hydroxyethyl)acrylamide

HEMA: 2-hydroxyethyl methacrylate

AA: Acrylic acid

<Other Solutions>

The substances shown in Table 7 were respectively dissolved in pure water to obtain aqueous solutions having each concentration shown in Table 7.

[0169]

[Table 7]

	Name of substance	Mw (kD)	Solution concentration (% by weight)
PEI solution A	Polyethyleneimine	750	1
PEI solution B	Polyethyleneimine	70	1
PAA solution	Polyacrylic acid	250	1.2
PAAM solution A	Polyallylamine	15	1
PAAM solution B	Polyallylamine	25	1
PAS solution	Diallyldimethylammonium chloride polymer	200	1
PVP solution	Polyvinylpyrrolidone (K90)	300	1
PDMAA solution	Poly(N,N-dimethylacrylamide)	400	1
VA64 solution	Vinylpyrrolidone/vinyl acetate (60/40) copolymer	190	1
PACMO solution	Polyacryloylmorpholine	243	1
PDEAA solution	Poly(N,N-diethylacrylamide)	47	1
PMMAA solution	Poly(N-methoxymethylacrylamide)	17	1
PHMAA solution	Poly(N-hydroxymethylacrylamide)	148	1
PNVF solution	Poly(N-vinylformamide)	183	1
PHEAA solution	Poly[N-(2-hydroxyethyl)acrylamide]	88	1
AcOH solution	Acetic acid	—	1
DEA solution	Diethylamine	—	1
AP solution A	Hyaluronic acid Na	1,190	0.1
AP solution B	KIMICA ALGIN I-3	349	0.1
AP solution C	Alginic acid ester HV	328	0.1
AP solution D	NS-300 (Carmellose)	12,000	0.1
AP solution E	SUNROSE (APP-84)	543	0.1
AP solution F	Chondroitin sulfate Na	25	0.1
AP solution G	GLYLOID 6C	500	0.1
AP solution H	Rhaball gum CG-SFT	5,340	0.1
AP solution I	APP-84	543	1

[0170]

Hyaluronic acid Na: Sodium hyaluronate (CHA) (CHISSO CORPORATION)

KIMICA ALGIN I-3: Sodium alginate (KIMICA Corporation)

KIMILOID HV: Alginic acid propylene glycol ester (KIMICA

corporation)

NS-300 (Carmellose): Carboxymethyl cellulose (GOTOKU CHEMICAL COMPANY LTD.)

SUNROSE (APP-84): Carboxymethyl cellulose
(NIPPON PAPER Chemicals CO., LTD.)

Chondroitin sulfate Na: Chondroitin sulfate sodium (SEIKAGAKU CORPORATION)

GLYLOID 6C: Tamarind gum (Dainippon Sumitomo Pharma Co., Ltd.)

Rhaball gum CG-SFT: Xanthan gum (Dainippon Sumitomo Pharma Co., Ltd.).

[0171]

Examples 1 to 3

The moldings obtained in the respective Reference Examples shown in Table 8 were immersed in a PEI solution A for 30 minutes and then respectively immersed in three pure water baths for 5 minutes. The moldings were immersed in a PAA solution for 30 minutes and then respectively immersed in three pure water baths for 5 minutes. Wettability and dynamic contact angle of the obtained low water content soft contact lenses were evaluated. The results are shown in Table 8. The reference sign "-" in the table means that a coating operation using a solution is not carried out.

[0172]

Examples 4 to 6

The moldings obtained in the respective Reference Examples

shown in Table 8 were immersed in a PAA solution for 30 minutes and then respectively immersed in three pure water baths for 5 minutes. The moldings were immersed in a PEI solution A for 30 minutes and then respectively immersed in three pure water baths for 5 minutes. The moldings were immersed in a PAA solution for 30 minutes and then respectively immersed in three pure water baths for 5 minutes. Wettability and dynamic contact angle of the obtained low water content soft contact lenses were evaluated. The results are shown in Table 8.

[0173]

Examples 7 to 14

The moldings obtained in the respective Reference Examples shown in Table 8 were immersed in a first solution for 30 minutes and then respectively immersed in three pure water baths for 5 minutes. The moldings were immersed in a second solution for 30 minutes and then respectively immersed in three pure water baths for 5 minutes. The moldings were immersed in a PAA solution for 30 minutes and then respectively immersed in three pure water baths for 5 minutes. Wettability and dynamic contact angle of the obtained low water content soft contact lenses were evaluated. The results are shown in Table 8.

[0174]

Comparative Examples 1 to 3

Wettability and dynamic contact angle of the moldings obtained in the respective Reference Examples shown in Table

8 were evaluated. The results are shown in Table 8. The reference sign "-" in the table means that a coating operation using a solution is not carried out.

[0175]

Comparative Examples 4 to 6

The moldings obtained in the respective Reference Examples shown in Table 8 were immersed in a PEI solution A for 30 minutes and then respectively immersed in three pure water baths for 5 minutes. Wettability and dynamic contact angle of the obtained low water content soft contact lenses were evaluated. The results are shown in Table 8. The reference sign "-" in the table means that a coating operation using a solution is not carried out.

[0176]

Comparative Examples 7 to 9

The moldings obtained in the respective Reference Examples shown in Table 8 were immersed in a PAA solution for 30 minutes and then respectively immersed in three pure water baths for 5 minutes. Wettability and dynamic contact angle of the obtained low water content soft contact lenses were evaluated. The results are shown in Table 8. The reference sign "-" in the table means that a coating operation using a solution is not carried out.

[0177]

[Table 8]

	Molding subjected to coating	First solution	Second solution	Third solution	Wettability	Dynamic contact angle (Advance)
Example 1	Reference Example 4	PEI solution A	PAA solution	—	A	Unevaluated
Example 2	Reference Example 16	PEI solution A	PAA solution	—	A	Unevaluated
Example 3	Reference Example 22	PEI solution A	PAA solution	—	A	Unevaluated
Example 4	Reference Example 4	PAA solution	PEI solution A	PAA solution	A	65
Example 5	Reference Example 16	PAA solution	PEI solution A	PAA solution	A	59
Example 6	Reference Example 22	PAA solution	PEI solution A	PAA solution	A	54
Example 7	Reference Example 4	PAA solution	PAS solution	PAA solution	A	Unevaluated
Example 8	Reference Example 4	PAA solution	PAAM solution A	PAA solution	A	Unevaluated
Example 9	Reference Example 4	PAA solution	PAAM solution B	PAA solution	A	Unevaluated
Example 10	Reference Example 4	PAA solution	PEI solution B	PAA solution	A	Unevaluated
Example 11	Reference Example 22	PAA solution	PAS solution	PAA solution	A	Unevaluated
Example 12	Reference Example 22	PAA solution	PAAM solution A	PAA solution	A	Unevaluated
Example 13	Reference Example 22	PAA solution	PAAM solution B	PAA solution	A	Unevaluated
Example 14	Reference Example 22	PAA solution	PEI solution B	PAA solution	A	Unevaluated

	Molding subjected to coating	First solution	Second solution	Third solution	Wettability	Dynamic contact angle (Advance)
Comparative Example 1	Reference Example 4	—	—	—	E	115
Comparative Example 2	Reference Example 16	—	—	—	E	118
Comparative Example 3	Reference Example 22	—	—	—	E	113
Comparative Example 4	Reference Example 4	PEI solution A	—	—	E	Unevaluated
Comparative Example 5	Reference Example 16	PEI solution A	—	—	E	Unevaluated
Comparative Example 6	Reference Example 22	PEI solution A	—	—	E	Unevaluated
Comparative Example 7	Reference Example 4	PAA solution	—	—	E	Unevaluated
Comparative Example 8	Reference Example 16	PAA solution	—	—	E	Unevaluated
Comparative Example 9	Reference Example 22	PAA solution	—	—	E	Unevaluated

Reference Examples 39 to 42

In the very same manner as in Reference Example 1, except that polydimethylsiloxane having a methacryloyl group at both ends (DMS-R31, Gelest, Inc., below-mentioned compound of the formula (M2), number average molecular weight of 13,000) (50 parts by weight) was used as a component A, and that a monomer having a fluoroalkyl group shown in Table 9 (50 parts by weight) was used as a component B, a low water content soft contact lenses were obtained. The evaluation results of the obtained low water content soft contact lenses are shown in Table 9.

[0179]

[Table 9]

	Component A DMS-R31 (Parts by weight)	Component B		Si atom content (% by weight)	Evaluation results		
		Name	(Parts by weight)		Transparency	Elongation (number of specimens which were not broken)	Folding resistance
Reference Example 39	50	Biscoat 3FM	50	19	A	4	B
Reference Example 40	50	Biscoat 8F	50	19	B	3	B
Reference Example 41	50	Biscoat 17F	50	19	*1	*1	*1
Reference Example 42	50	HFIP-M	50	19	A	4	A

*1: abandoned polymerization because of phase separation of polymerization raw solution

[0180]

Biscoat 3FM: Trifluoroethylmethacrylate (Osaka Organic Chemical Industry Ltd.)

Biscoat 8F: Octafluoropentyl acrylate (Osaka Organic Chemical Industry Ltd.)

Biscoat 17F: Heptafluorodecyl acrylate (Osaka Organic Chemical Industry Ltd.)

HFIP-M: Hexafluoroisopropyl methacrylate (Central Glass Co., Ltd.).


[0181]

Reference Example 43

Polydimethylsiloxane having a methacryloyl group at both ends (DMS-R31, Gelest, Inc., below-mentioned compound of the formula (M2), number average molecular weight of 30,000) (50 parts by weight) as a component A, trifluoroethyl acrylate (Biscoat 3F, Osaka Organic Chemical Industry Ltd.) (46 parts by weight) as a component B, methyl methacrylate (3 parts by weight) as a component C, an ultraviolet absorber having a polymerizable group (RUVA-93, compound represented by the formula (M1), Otsuka Chemical Co., Ltd.) (1 part by weight) as a component C, a polymerization initiator "IRGACURE[®]" 1850 (Ciba Specialty Chemicals Inc., 2 parts by weight) and t-amyl alcohol (10 parts by weight) were mixed and then stirred. As a result, a uniform and transparent monomer mixture was obtained. This monomer mixture was charged in a test tube and degassing was carried out under reduced pressure of 20 Torr (27 hPa) while stirring

using a touch mixer, and then the pressure was returned to atmospheric pressure using an argon gas. This operation was repeated three times. In a glove box under a nitrogen atmosphere, the monomer mixture was injected into a mold for contact lens made of a transparent resin (poly-4-methylpentene-1) and then polymerized by irradiating with light (8,000 lux, 20 minutes) using a fluorescent lamp (Toshiba Corporation, FL-6D, quasi-daylight, 6W, 4 lamps). After polymerization, the whole mold was immersed in an aqueous 60% by weight isopropyl alcohol solution and a contact lens-shaped molding was removed from the mold. The obtained molding was immersed in a large excess amount of an aqueous 80% by weight isopropyl alcohol solution at 60°C for 2 hours. Furthermore, the molding was immersed in a large excess amount of an aqueous 50% by weight isopropyl alcohol solution at room temperature for 30 minutes, followed by immersion in a large excess amount of an aqueous 25% by weight isopropyl alcohol solution at room temperature for 30 minutes, and further immersion in a large excess amount of pure water at room temperature for 30 minutes. Finally, the molding immersed in clean pure water was put in a closed vial bottle, and then autoclave sterilization was carried out at 121°C for 30 minutes. The obtained molding had a water content of less than 1%. Using two glass plates and a gasket as a mold, a film-shaped sample measuring 60 mm × 60 mm × 0.25 mm was obtained.

[Chemical Formula 3]



[0183]

Reference Examples 44 to 47 and 70 to 75

In the same manner as in Reference Example 43, except that the components shown in Table 10 were used, contact lens-shaped moldings, and film-shaped samples each measuring 60 mm × 60 mm × 0.25 mm were obtained. The reference sign "-" in the table means that the component is not used.

[0184]

[Table 10]

	Component A		Component B		Component C		Component C		Component C	Component C	Polymerization initiator		Solvent		Si atom content (% by weight)
	Name	Parts by weight	Name	Parts by weight	Name	Parts by weight	Name	Parts by weight	Ultraviolet absorber RUVA-93 (Parts by weight)	Colorant Uniblue A (Parts by weight)	Name	Parts by weight	Name	Parts by weight	
Reference Example 43	DMS-R31	50	Biscoat 3F	46	MMA	3	—	—	1	—	IRGACURE 1850	1	TAA	10	19
Reference Example 44	FM-7726	50	Biscoat 3F	46	MMA	3	—	—	1	—	IRGACURE 1850	1	TAA	10	19
Reference Example 45	FM-7726L	50	Biscoat 3F	46	MMA	3	—	—	1	—	IRGACURE 1850	1	TAA	10	19
Reference Example 46	X-22-164C	50	Biscoat 3F	46	MMA	3	—	—	1	—	IRGACURE 1850	1	TAA	10	18
Reference Example 47	DMS-R22	50	Biscoat 3F	46	MMA	3	—	—	1	—	IRGACURE 1850	1	TAA	10	18
Reference Example 48	FM-7726	49	Biscoat 3F	45	EHMA	5	DMAA	1	1	0.1	IRGACURE 819	0.5	TAA	10	18
Reference Example 49	FM-7726	47	Biscoat 3F	45	EHMA	5	DMAA	3	1	0.1	IRGACURE 819	0.5	TAA	10	18
Reference Example 50	FM-7726	45	Biscoat 3F	45	EHMA	5	DMAA	5	1	0.1	IRGACURE 819	0.5	TAA	10	17
Reference Example 51	FM-7726	42	Biscoat 3F	45	EHMA	5	DMAA	8	1	0.1	IRGACURE 819	0.5	TAA	10	16
Reference Example 52	FM-7726	49	Biscoat 3F	45	EHMA	5	DMAEA	1	1	0.1	IRGACURE 819	0.5	TAA	10	18
Reference Example 53	FM-7726	47	Biscoat 3F	45	EHMA	5	DMAEA	3	1	0.1	IRGACURE 819	0.5	TAA	10	18
Reference Example 54	FM-7726	42	Biscoat 3F	45	EHMA	5	DMAEA	8	1	0.1	IRGACURE 819	0.5	TAA	10	16
Reference Example 55	FM-7726	49	Biscoat 3F	45	EHMA	5	DMAEAA	1	1	0.1	IRGACURE 819	0.5	TAA	10	18

	Component A		Component B		Component C		Component C		Component C	Component C	Polymerization initiator		Solvent		Si atom content (% by weight)
	Name	Parts by weight	Name	Parts by weight	Name	Parts by weight	Name	Parts by weight	Ultraviolet absorber RUVA-93 (Parts by weight)	Colorant Uniblue A (Parts by weight)	Name	Parts by weight	Name	Parts by weight	
Reference Example 56	FM-7726	47	Biscoat 3F	45	EHMA	5	DMAFPA	3	1	0.1	IRGACURE 819	0.5	TAA	10	18
Reference Example 57	FM-7726	42	Biscoat 3F	45	EHMA	5	DMAFPA	8	1	0.1	IRGACURE 819	0.5	TAA	10	16
Reference Example 58	FM-7726	49	Biscoat 3F	45	EHMA	5	DEAEMA	1	1	0.1	IRGACURE 819	0.5	TAA	10	18
Reference Example 59	FM-7726	47	Biscoat 3F	45	EHMA	5	DEAEMA	3	1	0.1	IRGACURE 819	0.5	TAA	10	18
Reference Example 60	FM-7726	42	Biscoat 3F	45	EHMA	5	DEAEMA	8	1	0.1	IRGACURE 819	0.5	TAA	10	16
Reference Example 61	FM-7726	49	Biscoat 3F	45	EHMA	5	AA	1	1	0.1	IRGACURE 819	0.5	TAA	10	18
Reference Example 62	FM-7726	47	Biscoat 3F	45	EHMA	5	AA	3	1	0.1	IRGACURE 819	0.5	TAA	10	18
Reference Example 63	FM-7726	42	Biscoat 3F	45	EHMA	5	AA	8	1	0.1	IRGACURE 819	0.5	TAA	10	16
Reference Example 64	FM-7726	49	Biscoat 3F	45	EHMA	5	MAA	1	1	0.1	IRGACURE 819	0.5	TAA	10	18
Reference Example 65	FM-7726	47	Biscoat 3F	45	EHMA	5	MAA	3	1	0.1	IRGACURE 819	0.5	TAA	10	18
Reference Example 66	FM-7726	42	Biscoat 3F	45	EHMA	5	MAA	8	1	0.1	IRGACURE 819	0.5	TAA	10	16
Reference Example 67	DMS-R31	50	Biscoat 3F	46	MMA	3	—	—	1	0.1	IRGACURE 819	0.5	TAA	10	19
Reference Example 68	FM-7726	50	Biscoat 3F	46	MMA	3	—	—	1	0.1	IRGACURE 819	0.5	TAA	10	19

	Component A		Component B		Component C		Component C		Component C	Component C	Polymerization initiator		Solvent		Si atom content (% by weight)
	Name	Parts by weight	Name	Parts by weight	Name	Parts by weight	Name	Parts by weight	Ultraviolet absorber RUVA-93 (Parts by weight)	Colorant Uniblue A (Parts by weight)	Name	Parts by weight	Name	Parts by weight	
Reference Example 69	FM-7726L	50	Biscoat 3F	46	MMA	3	—	—	1	0.1	IRGACURE 819	0.5	TAA	10	19
Reference Example 70	FM-7726	50	Biscoat 3F	46	MMA	3	—	—	1	—	IRGACURE 819	2	TAA	10	19
Reference Example 71	DMS-R31	50	Biscoat 3F	46	MMA	3	—	—	1	—	IRGACURE 819	2	TAA	10	19
Reference Example 72	DMS-R31	50	Biscoat 3F	46	MMA	3	—	—	1	—	IRGACURE 1850	1	TAA	20	19
Reference Example 73	DMS-R31	50	Biscoat 3F	46	MMA	3	—	—	1	—	IRGACURE 819	0.25	TAA	20	19
Reference Example 74	FM-7726	50	Biscoat 3F	46	MMA	3	—	—	1	—	IRGACURE 819	0.25	TAA	20	19
Reference Example 75	FM-7726L	50	Biscoat 3F	46	MMA	3	—	—	1	—	IRGACURE 819	0.25	TAA	20	19

DMS-R31: Compound of the formula (M2), Mw 30 kD, Mn 13 kD, Gelest, Inc.

FM-7726: Compound of the formula (M2), Mw: 29 kD, Mn: 26 kD, CHISSO CORPORATION

FM-7726L: Compound of the formula (M2), Mw: 31 kD, Mn: 20 kD, CHISSO CORPORATION


X-22-164C: Compound of the formula, (M2) Mw: 7.2 kD, Mn: 4.8 kD, Shin-Etsu Chemical Co. Ltd.

DMS-R22: Compound of the formula (M2), Mw: 8.3 kD, Mn: 7.4 kD, Gelest, Inc.

In the formula (M2), n represents the number of repeating units and is determined by the molecular weight of the compound.

[0186]

[Chemical Formula 4]



[0187]

Biscoat 3F: Trifluoroethyl acrylate

MMA: Methyl methacrylate

EHMA: 2-ethylhexyl acrylate

DMAA: N,N-dimethylacrylamide

DMAEA: N,N-dimethylaminoethyl acrylate

DMAPEA: N,N-diethylaminopropyl acrylamide

DEAEMA: N,N-diethylaminoethyl methacrylate

TAA: t-amyl alcohol

AA: Acrylic acid

MAA: Methacrylic acid


Reference Example 48

Polydimethylsiloxane having a methacryloyl group at both ends (FM7726, CHISSO CORPORATION, above-mentioned compound of the formula (M2), weight average molecular weight of 29 kD, number average molecular weight of 26 kD) (49 parts by weight) as a component A, trifluoroethyl acrylate (Biscoat 3F, Osaka Organic Chemical Industry Ltd.) (45 parts by weight) as a component B, 2-ethylhexyl acrylate (5 parts by weight) as a component C, N,N-dimethylacrylamide (1 part by weight) as a component C, an ultraviolet absorber having a polymerizable group (RUVA-93, Otsuka Chemical Co., Ltd.) (1 part by weight) as a component C, a colorant having a polymerizable group [(Uniblue A, Sigma-Aldrich Corporation, formula (M3)) (0.1 part by weight) as a component C, a polymerization initiator "IRGACURE®" 819 (Ciba Specialty Chemicals Inc., 0.75 part by weight) and t-amyl alcohol (10 parts by weight) were mixed and then stirred. The mixture was filtered through a membrane filter (0.45 μ m) to remove insoluble matters, and thus a monomer mixture was obtained. This monomer mixture was charged in a test tube and degassing was carried out under reduced pressure of 20 Torr (27 hPa) while stirring using a touch mixer, and then the pressure was returned to atmospheric pressure using an argon gas. This operation was repeated three times. In a glove box under a nitrogen atmosphere,

the monomer mixture was injected into a mold for contact lens made of a transparent resin (poly-4-methylpentene-1) and then polymerized by irradiating with light (8,000 lux, 20 minutes) using a fluorescent lamp (Toshiba Corporation, FL-6D, quasi-daylight, 6W, 4 lamps). After polymerization, the whole mold was immersed in an aqueous 60% by weight isopropyl alcohol solution and a contact lens-shaped molding was removed from the mold. The obtained molding was immersed in a large excess amount of an aqueous 80% by weight isopropyl alcohol solution at 60°C for 2 hours. Furthermore, the molding was immersed in a large excess amount of an aqueous 50% by weight isopropyl alcohol solution at room temperature for 30 minutes, followed by immersion in a large excess amount of an aqueous 25% by weight isopropyl alcohol solution at room temperature for 30 minutes, and further immersion in a large excess amount of pure water at room temperature for 30 minutes. Finally, the molding immersed in clean pure water was put in a closed vial bottle, and then autoclave sterilization was carried out at 121°C for 30 minutes. The obtained molding had a water content of less than 1%. Using two glass plates and a gasket as a mold, a film-shaped sample measuring 60 mm × 60 mm × 0.25 mm was obtained.

[0188]

[Chemical Formula 5]



[0189]

Reference Examples 49 to 69

In the same manner as in Reference Example 48, except that the components shown in Table 10 were used, contact lens-shaped moldings, and film-shaped samples each measuring 60 mm × 60 mm × 0.25 mm were obtained. The reference sign "-" in the table means that the component is not used.

[0190]

Examples 15 to 183, Comparative Examples 10 to 30 and Control Example 1 and 2

The moldings or commercially available contact lenses obtained in the respective Reference Examples shown in Tables 11 to 16 were immersed in a first solution shown in Tables 11 to 16 for 30 minutes and then respectively immersed in three pure water baths for 5 minutes. The moldings or commercially available contact lens were immersed in a second solution shown in Tables 11 to 16 for 30 minutes and then respectively immersed in three pure water baths for 5 minutes. The above-mentioned operations were similarly repeated with respect to third to fifth solutions. The evaluation of the obtained low water content soft

contact lens was carried out. The results are shown in Tables 11 to 16. The reference sign "-" in the table means that a coating operation using a solution is not carried out, or the evaluation is not carried out.

[0191]

Control Examples are commercially available silicone hydrogel soft contact lenses and have a problem that wearers often feel dry, while other physical properties are almost satisfactory. Therefore, it is preferred that the respective physical properties of the low water content soft contact lenses of the present invention are equal or superior to those of Control Examples.

[0192]

[Table 11-1]

	Molding subjected to coating	First solution	Second solution	Third solution	Evaluation results					
					Wettability	Dynamic contact angle (Advance)	Friction (gf)	Lubricity	Adhesion of mucin ($\mu\text{g}/\text{cm}^2$)	Adhesion of lipid
Example 15	Reference Example 46	PAA solution	PEI solution A	—	B	60	61	C	2.7	—
Example 16	Reference Example 46	PAA solution	PEI solution A	PAA solution	A	36	42	C	3.4	D
Example 17	Reference Example 46	PAA solution	PEI solution A	CPDA solution B	B	34	22	A	6.0	—
Example 18	Reference Example 46	PAA solution	PEI solution A	CPDA solution A	B	32	20	A	1.8	—
Example 19	Reference Example 46	PAA solution	PEI solution A	CPDA solution C	C	39	46	A	2.3	—
Example 20	Reference Example 46	PAA solution	PEI solution A	CPDA solution D	C	41	25	A	5.1	—
Example 21	Reference Example 46	PAA solution	PEI solution A	CPDA solution E	C	24	29	A	3.2	—
Example 22	Reference Example 46	PAA solution	PEI solution A	CPDA solution F	A	29	14	A	3.0	—
Example 23	Reference Example 46	PAA solution	PEI solution A	CPDA solution G	C	52	18	A	3.0	—
Example 24	Reference Example 46	PAA solution	PEI solution A	CPDA solution H	B	20	16	A	3.3	—

	Molding subjected to coating	First solution	Second solution	Third solution	Evaluation results					
					Wettability	Dynamic contact angle (Advance)	Friction (gf)	Lubricity	Adhesion of Mucin ($\mu\text{g}/\text{cm}^2$)	Adhesion of lipid
Example 25	Reference Example 46	PAA solution	PEI solution A	CPDA solution I	A	16	14	A	3.9	—
Example 26	Reference Example 46	PAA solution	PEI solution A	CPDA solution J	C	42	23	A	3.5	—
Example 27	Reference Example 46	PAA solution	PEI solution A	CPDA solution K	C	31	19	A	3.4	—
Example 28	Reference Example 46	PAA solution	PEI solution A	CPDA solution L	A	16	19	A	3.9	—
Example 29	Reference Example 46	PAA solution	PEI solution A	AP solution A	B	26	55	C	2.4	—
Example 30	Reference Example 46	PAA solution	PEI solution A	AP solution B	B	25	53	C	2.3	—
Example 31	Reference Example 46	PAA solution	PEI solution A	AP solution C	B	22	47	C	2.6	—
Example 32	Reference Example 46	PAA solution	PEI solution A	AP solution D	A	41	61	C	3.1	—
Example 33	Reference Example 46	PAA solution	PEI solution A	AP solution E	A	25	71	C	1.9	—
Example 34	Reference Example 46	PAA solution	PEI solution A	AP solution F	B	57	57	C	2.7	—

	Molding subjected to coating	First solution	Second solution	Third solution	Evaluation results					
					Wettability	Dynamic contact angle (Advance)	Friction (gf)	Lubricity	Adhesion of mucin ($\mu\text{g}/\text{cm}^2$)	Adhesion of lipid
Example 35	Reference Example 46	PAA solution	PEI solution A	AP solution G	B	53	63	C	2.8	—
Example 36	Reference Example 46	PAA solution	PEI solution A	AP solution H	B	50	49	C	2.9	—
Example 37	Reference Example 46	PAA solution	PEI solution A	AP solution I	A	47	55	C	2.5	—
Example 38	Reference Example 46	PAA solution	PEI solution A	PVP solution	B	53	57	D	2.7	—
Example 39	Reference Example 46	PAA solution	PEI solution A	VA64 solution	C	83	59	D	3.0	—
Example 40	Reference Example 46	PAA solution	PEI solution A	PDMAA solution	C	49	66	D	3.9	—
Example 41	Reference Example 46	PAA solution	PEI solution A	PACMO solution	A	45	59	D	3.8	—
Example 42	Reference Example 46	PAA solution	PEI solution A	PDEAA solution	C	66	60	D	4.4	—
Example 43	Reference Example 46	PAA solution	PEI solution A	PMMAA solution	C	85	74	D	3.6	—
Example 44	Reference Example 46	PAA solution	PEI solution A	PHMAA solution	B	59	69	D	3.2	—

	Molding subjected to coating	First solution	Second solution	Third solution	Evaluation results					
					Wettability	Dynamic contact angle (Advance)	Friction (gf)	Lubricity	Adhesion of Mucin ($\mu\text{g}/\text{cm}^2$)	Adhesion of lipid
Example 45	Reference Example 46	PAA solution	PEI solution A	PNVF solution	A	37	68	D	3.2	—
Example 46	Reference Example 46	PAA solution	PEI solution A	PHEAA solution	B	51	73	D	3.9	—
Example 47	Reference Example 46	PAA solution	PEI solution A	CPDEAC solution	B	60	63	D	3.4	—
Example 48	Reference Example 46	PAA solution	PEI solution A	CPACDM solution	A	26	64	D	3.7	—
Example 49	Reference Example 46	PAA solution	PEI solution A	CPDEDM solution	C	76	54	D	3.7	—
Example 50	Reference Example 46	PAA solution	PEI solution A	CPHEDM solution	A	52	72	D	4.3	—
Example 51	Reference Example 46	PAA solution	PEI solution A	—	B	—	61	D	3.0	E
Example 52	Reference Example 46	PEI solutionA	PAA solution	—	A	—	38	C	4.4	—
Example 53	Reference Example 46	PEI solutionA	CPDA solution A	—	C	—	—	B	—	—

[Table 11-2]

	Molding subjected to coating	First solution	Second solution	Third solution	Evaluation results					
					Wettability	Dynamic contact angle (Advance)	Friction (gf)	Lubricit y	Adhesion of mucin ($\mu\text{g}/\text{cm}^2$)	Adhesion of lipid
Comparative Example 10	Reference Example 46	—	—	—	E	113	60	E	2.6	D
Comparative Example 11	Reference Example 46	PEI solution A	—	—	D	—	—	E	2.2	—
Comparative Example 12	Reference Example 46	PAA solution	—	—	E	—	—	E	2.3	—
Comparative Example 13	Reference Example 46	CPDA solution A	—	—	E	—	—	E	—	—
Comparative Example 14	Reference Example 46	PVP solution	—	—	E	—	—	E	—	—
Comparative Example 15	Reference Example 46	VA64 solution	—	—	E	—	—	E	—	—
Comparative Example 16	Reference Example 46	PDMAA solution	—	—	E	—	—	E	—	—
Comparative Example 17	Reference Example 46	PEI solution A	PEI solution A	—	C	—	—	E	—	—
Comparative Example 18	Reference Example 46	PAA solution	PAA solution	—	E	—	—	E	—	—
Comparative Example 19	Reference Example 46	PAA solution	CPDA solution A	—	E	—	—	E	—	—
Comparative Example 20	Reference Example 46	AcOH solution	PEI solution A	—	C	—	—	E	—	—

	Molding subjected to coating	First solution	Second solution	Third solution	Evaluation results					
					Wettability	Dynamic contact angle (Advance)	Friction (gf)	Lubricit y	Adhesion of Mucin ($\mu\text{g}/\text{cm}^2$)	Adhesion of lipid
Comparative Example 21	Reference Example 46	DEA solution	PAA solution	—	E	—	—	E	—	—
Comparative Example 22	Reference Example 46	AcOH solution	DEA solution	PAA solution	E	—	—	E	—	—
Comparative Example 23	Reference Example 46	AcOH solution	DEA solution	DEA solution	E	—	—	E	—	—
Comparative Example 24	Reference Example 46	DEA solution	AcOH solution	AcOH solution	E	—	—	E	—	—
Control Example 1	SHG-A	—	—	—	A	38	38	B	2.5	D
Control Example 2	SHG-B	—	—	—	A	38	—	C	4.6	A
Example 54	Reference Example 43	PAA solution	PEI solution A	PAA solution	A	44	46	C	2.7	—
Example 55	Reference Example 43	PAA solution	PEI solution A	CPDA solution B	A	32	24	A	5.4	—
Example 56	Reference Example 43	PAA solution	PEI solution A	CPDA solution A	A	26	20	A	1.4	—
Example 57	Reference Example 43	PAA solution	PEI solution A	CPDA solution C	A	40	35	A	1.6	—
Example 58	Reference Example 43	PAA solution	PEI solution A	CPVPA solution C	B	59	46	B	3.8	—
Example 59	Reference Example 43	PAA solution	PEI solution A	CPVPA solution D	B	60	43	B	3.4	—

[0194]

SHG-A: Commercially available silicone hydrogel soft contact lens A

SHG-B: Commercially available silicone hydrogel soft contact lens B

[0195]

[Table 12]

	Molding subjected to coating	First solution	Second solution	Third solution	Evaluation results			
					Transparency	Coloration	Wettability	Lubricity
Example 60	Reference Example 44	PAA solution	PEI solution A	PAA solution	A	—	A	C
Example 61	Reference Example 44	PAA solution	PEI solution A	CPDAsolutionB	A	—	A	A
Example 62	Reference Example 44	PAA solution	PEI solution A	CPDAsolutionA	A	—	A	A
Example 63	Reference Example 44	PAA solution	PEI solution A	CPDAsolutionC	A	—	A	A
Example 64	Reference Example 44	PAA solution	PEI solution A	CPVPA solution C	A	—	B	B
Example 65	Reference Example 44	PAA solution	PEI solution A	CPVPA solution D	A	—	B	B
Example 66	Reference Example 45	PAA solution	PEI solution A	CPDAsolutionA	A	—	A	A
Example 67	Reference Example 47	PAA solution	PEI solution A	CPDAsolutionA	A	—	A	A
Example 68	Reference Example 48	PAA solution	PEI solution A	CPHASolutionA	A	A	B	B
Example 69	Reference Example 49	PAA solution	PEI solution A	CPHASolutionA	A	A	B	B
Example 70	Reference Example 50	PAA solution	PEI solution A	CPHASolutionA	B	A	B	B

	Molding subjected to coating	First solution	Second solution	Third solution	Evaluation results			
					Transparency	Coloration	Wettability	Lubricity
Example 71	Reference Example 51	PAA solution	PEI solution A	CPHAsolutionA	C	A	B	B
Example 72	Reference Example 52	PAA solution	PEI solution A	CPHAsolutionA	A	A	B	B
Example 73	Reference Example 53	PAA solution	PEI solution A	CPHAsolutionA	B	A	B	B
Example 74	Reference Example 54	PAA solution	PEI solution A	CPHAsolutionA	C	A	B	B
Example 75	Reference Example 55	PAA solution	PEI solution A	CPHAsolutionA	A	A	B	B
Example 76	Reference Example 56	PAA solution	PEI solution A	CPHAsolutionA	B	A	B	B
Example 77	Reference Example 57	PAA solution	PEI solution A	CPHAsolutionA	C	A	B	B
Example 78	Reference Example 58	PAA solution	PEI solution A	CPHAsolutionA	A	A	B	B
Example 79	Reference Example 59	PAA solution	PEI solution A	CPHAsolutionA	B	A	B	B
Example 80	Reference Example 60	PAA solution	PEI solution A	CPHAsolutionA	C	A	B	B
Example 81	Reference Example 61	PAA solution	PEI solution A	CPHAsolutionA	A	A	B	B

	Molding subjected to coating	First solution	Second solution	Third solution	Evaluation results			
					Transparency	Coloration	Wettability	Lubricity
Example 82	Reference Example 62	PAA solution	PEI solution A	CPHAsolutionA	B	A	B	B
Example 83	Reference Example 63	PAA solution	PEI solution A	CPHAsolutionA	C	A	B	B
Example 84	Reference Example 64	PAA solution	PEI solution A	CPHAsolutionA	A	A	B	B
Example 85	Reference Example 65	PAA solution	PEI solution A	CPHAsolutionA	B	A	B	B
Example 86	Reference Example 66	PAA solution	PEI solution A	CPHAsolutionA	C	A	B	B
Example 87	Reference Example 67	PAA solution	PEI solution A	CPHAsolutionA	A	E	B	B
Example 88	Reference Example 68	PAA solution	PEI solution A	CPHAsolutionA	A	E	B	B
Example 89	Reference Example 69	PAA solution	PEI solution A	CPHAsolutionA	A	E	B	B
Control Example 1	SHG-A	—	—	—	A	A	A	B
Control Example 2	SHG-B	—	—	—	A	A	A	C

[Table 13]

	Molding subjected to coating	First solution	Second solution	Third solution	Fourth solution	Fifth solution
Control Example 1	SHG-A	—	—	—	—	—
Control Example 2	SHG-B	—	—	—	—	—
Comparative Example 25	Reference Example 70	—	—	—	—	—
Comparative Example 26	Reference Example 70	PAA solution	—	—	—	—
Comparative Example 27	Reference Example 70	PEI solution A	—	—	—	—
Comparative Example 28	Reference Example 70	CPHA solution E	—	—	—	—
Comparative Example 29	Reference Example 70	CPDA solution A	—	—	—	—
Comparative Example 30	Reference Example 70	CPHA solution A	—	—	—	—
Example 90	Reference Example 70	PAA solution	PEI solution A	—	—	—
Example 91	Reference Example 70	PEI solution A	PAA solution	—	—	—
Example 92	Reference Example 70	PAA solution	PEI solution A	PAA solution	—	—
Example 93	Reference Example 70	PAA solution	PEI solution A	CPDA solution A	—	—
Example 94	Reference Example 70	PAA solution	PEI solution A	CPHA solution E	—	—
Example 95	Reference Example 70	CPHA solution E	PEI solution A	CPDA solution A	—	—
Example 96	Reference Example 70	CPDA solution A	PEI solution A	CPHA solution E	—	—
Example 97	Reference Example 70	PAA solution	PEI solution A	*1	—	—

	Molding subjected to coating	First solution	Second solution	Third solution	Fourth solution	Fifth solution
Example 98	Reference Example 70	PAA solution	PEI solution A	CPHA solution E	PEI solution A	CPDA solution A
Example 99	Reference Example 70	PAA solution	PEI solution A	CPDA solution A	PEI solution A	CPHA solution E
Example 100	Reference Example 70	PAA solution	PEI solution A	CPHA solution A	—	—
Example 101	Reference Example 70	PAA solution	PEI solution A	CPHA solution B	—	—
Example 102	Reference Example 70	PAA solution	PEI solution A	CPHA solution C	—	—
Example 103	Reference Example 70	PAA solution	PEI solution A	CPHA solution F	—	—
Example 104	Reference Example 70	PEI solution A	CPDA solution A	—	—	—
Example 105	Reference Example 70	PAA solution	PEI solution A	CPHA solution A	—	—
Example 106	Reference Example 70	CPDA solution A	PEI solution A	CPHA solution A	—	—
Example 107	Reference Example 70	PAA solution	PEI solution A	*2	—	—
Example 108	Reference Example 70	PAA solution	PEI solution A	CPHA solution A	PEI solution A	CPDA solution A
Example 109	Reference Example 70	PAA solution	PEI solution A	CPDA solution A	PEI solution A	CPHA solution A

	Evaluation results							
	Transparency	Wettability	Lubricity	Adhesion of mucin ($\mu\text{g}/\text{cm}^2$)	Artificial lacrimal fluid immersion test	Boiling resistance	Scrubbing resistance A	Scrubbing resistance B
Control Example 1	A	A	B	2.5	B	A	B	B
Control Example 2	A	A	C	4.6	E	A	B	B
Comparative Example 25	A	E	E	3.9	C	E	E	E
Comparative Example 26	A	D	E	3.6	D	E	D	D
Comparative Example 27	A	D	D	3.1	E	D	D	D
Comparative Example 28	A	E	E	3.5	E	—	—	—
Comparative Example 29	A	E	E	4.1	E	E	E	D
Comparative Example 30	A	E	E	3.9	D	E	E	E

	Evaluation results							
	Transparency	Wettability	Lubricity	Adhesion of mucin (μg/cm ²)	Artificial lacrimal fluid immersion test	Boiling resistance	Scrubbing resistance A	Scrubbing resistance B
Example 90	A	B	C	3.0	E	B	B	B
Example 91	A	A	C	8.2	E	A	A	A
Example 92	A	A	B	7.5	E	A	A	A
Example 93	A	A	A	2.5	D	A	A	A
Example 94	A	C	C	2.9	E	—	—	—
Example 95	A	B	A	2.4	E	—	—	—
Example 96	A	C	C	2.3	C	—	—	—
Example 97	A	B	A	3.1	C	—	—	—
Example 98	A	B	A	2.9	C	—	—	—
Example 99	A	C	C	3.0	D	—	—	—
Example 100	A	B	B	2.3	C	B	B	B

	Evaluation results							
	Transparency	Wettability	Lubricity	Adhesion of mucin ($\mu\text{g}/\text{cm}^2$)	Artificial lacrimal fluid immersion test	Boiling resistance	Scrubbing resistance A	Scrubbing resistance B
Example 101	A	B	B	2.8	C	—	—	—
Example 102	A	C	B	3.7	C	—	—	—
Example 103	A	C	B	2.3	C	—	—	—
Example 104	A	B	A	2.5	E	B	B	B
Example 105	A	B	B	2.9	C	B	B	B
Example 106	A	C	B	2.6	C	C	C	C
Example 107	A	C	A	3.3	C	C	C	C
Example 108	A	B	A	3.2	C	B	B	B
Example 109	A	C	B	2.4	C	C	C	C

[0197]

*1: 1:1 (weight) mixture OF CPHA solution E and CPDA solution A

*2: 1:1 (weight) mixture of CPHA solution A and CPDA solution A

[0198]

[Table 14]

	Molding subjected to coating	First solution	Second solution	Third solution
Control Example 1	SHG-A	—	—	—
Control Example 2	SHG-B	—	—	—
Example 110	Reference Example 72	PAA solution	PEI solution A	CPHA solution A
Example 111	Reference Example 73	PAA solution	PEI solution A	CPHA solution A
Example 112	Reference Example 74	PAA solution	PEI solution A	CPHA solution A
Example 113	Reference Example 75	PAA solution	PEI solution A	CPHA solution A

	Evaluation results					
	Transparency	Transparency (Projector)	Water content (%)	Lens molding ratio	Tensile elastic modulus (kPa)	Elongation at break (%)
Control Example 1	A	A	19	—	2000	240
Control Example 2	A	A	37	—	850	240
Example 110	A	B	Less than 1	0.917	660	410
Example 111	A	B	Less than 1	0.916	740	320
Example 112	A	A	Less than 1	0.939	880	390
Example 113	A	C	Less than 1	0.905	630	300

	Evaluation results				
	Wettability	Lubricity	Boiling resistance	Scrubbing resistance A	Scrubbing resistance B
Control Example 1	A	C	A	B	B
Control Example 2	A	B	A	B	B
Example 110	B	B	B	B	B
Example 111	B	B	B	B	B
Example 112	B	B	B	B	B
Example 113	B	B	B	B	B

[0199]

[Table 15]

	Molding subjected to coating	First solution	Second solution	Third solution	Evaluation results			
					Transparency	Folding resistance	Wettability	Lubricity
Control Example 1	SHG-A	—	—	—	A	A	A	C
Control Example 2	SHG-B	—	—	—	A	A	A	B
Example 114	Reference Example 1	PAA solution	PEI solution A	CPHA solution A	A	A	B	B
Example 115	Reference Example 2	PAA solution	PEI solution A	CPHA solution A	A	A	B	B
Example 116	Reference Example 3	PAA solution	PEI solution A	CPHA solution A	A	A	B	B
Example 117	Reference Example 4	PAA solution	PEI solution A	CPHA solution A	A	A	B	B
Example 118	Reference Example 5	PAA solution	PEI solution A	CPHA solution A	B	A	B	B
Example 119	Reference Example 6	PAA solution	PEI solution A	CPHA solution A	C	A	B	B
Example 120	Reference Example 7	PAA solution	PEI solution A	CPHA solution A	C	A	B	B
Example 121	Reference Example 8	PAA solution	PEI solution A	CPHA solution A	C	A	B	B
Example 122	Reference Example 9	PAA solution	PEI solution A	CPHA solution A	C	A	B	B
Example 123	Reference Example 10	PAA solution	PEI solution A	CPHA solution A	C	A	B	B

	Molding subjected to coating	First solution	Second solution	Third solution	Evaluation results			
					Transparency	Folding resistance	Wettability	Lubricit y
Example 124	Reference Example 11	PAA solution	PEI solution A	CPHA solution A	D	A	B	B
Example 125	Reference Example 13	PAA solution	PEI solution A	CPHA solution A	C	B	B	B
Example 126	Reference Example 14	PAA solution	PEI solution A	CPHA solution A	A	B	B	B
Example 127	Reference Example 15	PAA solution	PEI solution A	CPHA solution A	A	B	B	B
Example 128	Reference Example 16	PAA solution	PEI solution A	CPHA solution A	A	C	B	B
Example 129	Reference Example 17	PAA solution	PEI solution A	CPHA solution A	A	E	B	B
Example 130	Reference Example 18	PAA solution	PEI solution A	CPHA solution A	A	E	B	B
Example 131	Reference Example 19	PAA solution	PEI solution A	CPHA solution A	A	E	B	B
Example 132	Reference Example 20	PAA solution	PEI solution A	CPHA solution A	A	D	B	B
Example 133	Reference Example 21	PAA solution	PEI solution A	CPHA solution A	B	E	B	B
Example 134	Reference Example 22	PAA solution	PEI solution A	CPHA solution A	A	D	B	B

	Molding subjected to coating	First solution	Second solution	Third solution	Evaluation results			
					Transparency	Folding resistance	Wettability	Lubricit y
Example 135	Reference Example 24	PAA solution	PEI solution A	CPHA solution A	A	D	B	B
Example 136	Reference Example 25	PAA solution	PEI solution A	CPHA solution A	A	E	B	B
Example 137	Reference Example 26	PAA solution	PEI solution A	CPHA solution A	A	D	B	B
Example 138	Reference Example 27	PAA solution	PEI solution A	CPHA solution A	B	D	B	B
Example 139	Reference Example 28	PAA solution	PEI solution A	CPHA solution A	E	E	B	B
Example 140	Reference Example 29	PAA solution	PEI solution A	CPHA solution A	D	D	B	B
Example 141	Reference Example 30	PAA solution	PEI solution A	CPHA solution A	D	D	B	B
Example 142	Reference Example 31	PAA solution	PEI solution A	CPHA solution A	B	D	B	B
Example 143	Reference Example 32	PAA solution	PEI solution A	CPHA solution A	B	A	B	B
Example 144	Reference Example 33	PAA solution	PEI solution A	CPHA solution A	B	A	B	B
Example 145	Reference Example 34	PAA solution	PEI solution A	CPHA solution A	A	A	B	B

	Molding subjected to coating	First solution	Second solution	Third solution	Evaluation results			
					Transparency	Folding resistance	Wettability	Lubricit y
Example 146	Reference Example 35	PAA solution	PEI solution A	CPHA solution A	A	A	B	B
Example 147	Reference Example 36	PAA solution	PEI solution A	CPHA solution A	B	A	B	B
Example 148	Reference Example 37	PAA solution	PEI solution A	CPHA solution A	D	B	B	B

[0200]

[Table 16]

	Molding subjected to coating	First solution	Second solution	Third solution	Evaluation results			
					Transparency	Folding resistance	Wettability	Lubricity
Example 149	Reference Example 1	PAA solution	PEI solution A	CPDA solution A	A	A	A	A
Example 150	Reference Example 2	PAA solution	PEI solution A	CPDA solution A	A	A	A	A
Example 151	Reference Example 3	PAA solution	PEI solution A	CPDA solution A	A	A	A	A
Example 152	Reference Example 4	PAA solution	PEI solution A	CPDA solution A	A	A	A	A
Example 153	Reference Example 5	PAA solution	PEI solution A	CPDA solution A	B	A	A	A
Example 154	Reference Example 6	PAA solution	PEI solution A	CPDA solution A	C	A	A	A
Example 155	Reference Example 7	PAA solution	PEI solution A	CPDA solution A	C	A	A	A
Example 156	Reference Example 8	PAA solution	PEI solution A	CPDA solution A	C	A	A	A
Example 157	Reference Example 9	PAA solution	PEI solution A	CPDA solution A	C	A	A	A
Example 158	Reference Example 10	PAA solution	PEI solution A	CPDA solution A	C	A	A	A
Example 159	Reference Example 11	PAA solution	PEI solution A	CPDA solution A	D	A	A	A
Example 160	Reference Example 13	PAA solution	PEI solution A	CPDA solution A	C	B	A	A
Example 161	Reference Example 14	PAA solution	PEI solution A	CPDA solution A	A	B	A	A
Example 162	Reference Example 15	PAA solution	PEI solution A	CPDA solution A	A	B	A	A
Example 163	Reference Example 16	PAA solution	PEI solution A	CPDA solution A	A	C	A	A
Example 164	Reference Example 17	PAA solution	PEI solution A	CPDA solution A	A	E	A	A
Example 165	Reference Example 18	PAA solution	PEI solution A	CPDA solution A	A	E	A	A
Example 166	Reference Example 19	PAA solution	PEI solution A	CPDA solution A	A	E	A	A

	Molding subjected to coating	First solution	Second solution	Third solution	Evaluation results			
					Transparency	Folding resistance	Wettability	Lubricity
Example 167	Reference Example 20	PAA solution	PEI solution A	CPDA solution A	A	D	A	A
Example 168	Reference Example 21	PAA solution	PEI solution A	CPDA solution A	B	E	A	A
Example 169	Reference Example 22	PAA solution	PEI solution A	CPDA solution A	A	D	A	A
Example 170	Reference Example 24	PAA solution	PEI solution A	CPDA solution A	A	D	A	A
Example 171	Reference Example 25	PAA solution	PEI solution A	CPDA solution A	A	E	A	A
Example 172	Reference Example 26	PAA solution	PEI solution A	CPDA solution A	A	D	A	A
Example 173	Reference Example 27	PAA solution	PEI solution A	CPDA solution A	B	D	A	A
Example 174	Reference Example 28	PAA solution	PEI solution A	CPDA solution A	E	E	A	A
Example 175	Reference Example 29	PAA solution	PEI solution A	CPDA solution A	D	D	A	A
Example 176	Reference Example 30	PAA solution	PEI solution A	CPDA solution A	D	D	A	A
Example 177	Reference Example 31	PAA solution	PEI solution A	CPDA solution A	B	D	A	A
Example 178	Reference Example 32	PAA solution	PEI solution A	CPDA solution A	B	A	A	A
Example 179	Reference Example 33	PAA solution	PEI solution A	CPDA solution A	B	A	A	A
Example 180	Reference Example 34	PAA solution	PEI solution A	CPDA solution A	A	A	A	A
Example 181	Reference Example 35	PAA solution	PEI solution A	CPDA solution A	A	A	A	A
Example 182	Reference Example 36	PAA solution	PEI solution A	CPDA solution A	B	A	A	A
Example 183	Reference Example 37	PAA solution	PEI solution A	CPDA solution A	D	B	A	A

[0201]

Example 184 <Measurement of Oxygen Transmission Rate>

A film (having a thickness of 0.19 mm) produced in the same manner as in Example 62 was cut into size of 20 mm × 20 mm, to obtain samples. Using an oxygen transmission rate analyzer, Model OX-TRAN2/21 (Hitachi High-Technologies Corporation), oxygen transmission rate was measured. A mixed gas of nitrogen (98%)/hydrogen (2%) was used as a carrier gas, and a mixed gas of nitrogen (79.3%)/oxygen (20.7%) was used as a measuring gas. Humidification of the gas was not carried out. The oxygen transmission rate of the sample was 390×10^{-11} (cm²/sec) (mLO₂) / (mL·hPa). The oxygen transmission rate of a gas permeable hard contact lens "Menicon® Z" manufactured by Menicon Co., Ltd., measured by the same apparatus under the same conditions, was 150×10^{-11} (cm²/sec) (mLO₂) / (mL·hPa), and the oxygen transmission rate of a gas permeable hard contact lens "Breath-o Hard®" manufactured by Toray Industries, Inc. was 120×10^{-11} (cm²/sec) (mLO₂) / (mL·hPa).

[0202]

Example 185

Subjects A and B wore the low water content soft contact lens produced in Example 93 for 6 hours. Both subjects A and B did not feel dry during wear, and felt comfort without feeling sticky to the cornea.

[0203]

Example 186

Subjects A and B wore the low water content soft contact lens produced in Example 100 for 6 hours. Both subjects A and B did not feel dry during wear, and felt comfort without feeling sticky to the cornea.

[0204]

Comparative Example 31

Subjects A and B wore a commercially available silicone hydrogel soft contact lens C (water content: 46%) for 6 hours. Both subjects A and B felt dryness of eyes and did not feel comfort. They did not feel sticky to the cornea.

[0205]

Comparative Example 32

A contact lens produced in accordance with Example 6 of Japanese Unexamined Patent Publication (Kokai) No. 2002-080538 was subjected to the same coating operation as in Example 93. The obtained silicone hydrogel soft contact lens (having water content of 40%) exhibits transparency (A), wettability (A) and lubricity (A). Subjects A and B wore the silicone hydrogel soft contact lens for 6 hours. Both subjects A and B felt dryness of eyes and did not feel comfort. They did not feel sticky to the cornea.

[0206]

Comparative Example 33

Subjects A and B wore a low water content soft contact lens (having water content of less than 1%) in accordance with Example

1 of Japanese Unexamined Patent Publication (Kokai) No. 2002-311395. Both subjects A and B felt sticky to the cornea within 30 minutes and stopped wearing.

[Industrial Applicability]

[0207]

The present invention relates to a low water content soft lens for eye, and is useful as a lens for eye, such as a low water content soft contact lens, an intraocular lens, an artificial cornea, a corneal inlay, a corneal onlay or a spectacle lens. The low water content soft lens for eye is particularly suitable as a low water content soft contact lens.

[Reference Signs List]

[0208]

- 1: Artificial leather
- 2: Sample film
- 3: Rubber plate
- 4: Plastic container containing iron balls

[CLAIMS]

1. A low water content soft lens for eye, comprising a base material, a layer made of an acidic polymer and a basic polymer being formed on at least a part of a surface of the base material, wherein water content of the lens is 1% or less.

2. The low water content soft lens for eye according to claim 1, wherein the base material contain, as a main component, a polymer of the following component A, or a copolymer of the following components A and B:


component A: a polysiloxane compound which has a plurality of polymerizable functional groups per molecule, and also has a number average molecular weight of 6,000 or more, and

component B: a polymerizable monomer having a fluoroalkyl group.

3. The low water content soft lens for eye according to claim 2, wherein the component A is a polysiloxane compound having two polymerizable functional groups per molecule.

4. The low water content soft lens for eye according to claim 3, wherein the component A is a polysiloxane compound represented by the following formula (A1):

[Chemical Formula 1]



wherein X^1 and X^2 each independently represents a polymerizable functional group; R^1 to R^8 each independently represents a substituent selected from hydrogen, an alkyl group having 1 to

20 carbon atoms, a phenyl group and a fluoroalkyl group having 1 to 20 carbon atoms; L^1 and L^2 each independently represents a divalent group; and a and b each independently represents the number of the respective repeating units.

5. The low water content soft lens for eye according to claim 4, wherein X^1 and X^2 in the formula (A1) are (meth)acryloyl groups.

6. The low water content soft lens for eye according to any one of claims 2 to 5, wherein the base material contains 5% by weight or more of silicon atoms.

7. The low water content soft lens for eye according to claim 2, wherein the component B is a (meth)acrylic acid fluoroalkyl ester.

8. The low water content soft lens for eye according to any one of claims 1 to 7, wherein the layer made of an acidic polymer and a basic polymer includes one or more layers made of an acidic polymer, and one or more layers made of a basic polymer.

9. The low water content soft lens for eye according to any one of claims 1 to 8, wherein the layer made of an acidic polymer and a basic polymer is composed of one layer made of an acidic polymer and one layer made of a basic polymer, so two layers in total.

10. The low water content soft lens for eye according to any one of claims 1 to 8, wherein the layer made of an acidic polymer and a basic polymer is composed of one or two layers made of an acidic polymer, and one or two layers made of a basic polymer,

so three layers in total.

11. The low water content soft lens for eye according to any one of claims 1 to 8, wherein the layer made of an acidic polymer and a basic polymer contains two or more kinds of acidic polymers and one or more kinds of basic polymers.

12. The low water content soft lens for eye according to any one of claims 1 to 11, wherein at least one kind among the acidic and basic polymers is a polymer having a group selected from a hydroxyl group and an amide bond.

13. The low water content soft lens for eye according to claim 12, wherein at least one kind among the acidic and basic polymers is a polymer having a hydroxyl group.

14. The low water content soft lens for eye according to claim 12, wherein two or more kinds among the acidic and basic polymers are polymers having a group selected from a hydroxyl group and an amide bond.

15. A method for producing a low water content soft lens for eye, which comprises the following steps 1 to 3 in this order, wherein water content of the lens is 1% or less:

<Step 1>

Step of polymerizing a mixture of a component A which is polysiloxane compound having a plurality of polymerizable functional groups per molecule, and also having a number average molecular weight of 6,000 or more, and a component B which is a polymerizable monomer having a fluoroalkyl group, to obtain a lens-shaped molding;

<Step 2>

Step of bringing the molding obtained in the step 1 into contact with a basic polymer solution, and then washing the molding, to remove the surplus basic polymer solution; and

<Step 3>

Step of bringing the molding obtained in the step 2 into contact with an acidic polymer solution, and then washing the molding, to remove the surplus acidic polymer solution.