What is claimed is:

1. A method for selectively hydrogenating acetylene, the method comprising contacting a catalyst composition comprising a porous support, palladium, and at least one ionic liquid with a process gas comprising

ethylene, present in the process gas in an amount of at least 10 mol.%;

acetylene, present in the process gas in an amount of at least 1 ppm;

hydrogen, present in the process gas in an amount of at least 5 mol.%; and

~~0~~ 50 ppm to 190 ppm carbon monoxide;

wherein the catalyst composition comprises

a porous support, present in the composition in an amount within the range of 90 wt.% to 99.9 wt.%;

palladium, present in the composition in an amount within the range of at least 0.02 wt.%, calculated on an elemental mass basis; and

one or more ionic liquids, present in the composition in a combined amount up to 10 wt.%,

wherein the hydrogenation catalyst has a BET surface area of no more than 10 m^2/g and a pore volume of at least 0.05 mL/g; wherein at least 90% of the acetylene present in the process gas is hydrogenated, and no more than 1 mol.% of the total of acetylene and ethylene present in the process gas is converted to ethane.

2. A method according to claim 1, wherein carbon monoxide is present in the process gas in an amount up to 150 ppm.

3. A method according to claim 1, wherein carbon monoxide is present in the process gas in an amount up to 85 ppm.

~~4. A method for selectively hydrogenating acetylene, the method comprising contacting a catalyst composition comprising a porous support, palladium, and at least one ionic liquid with a process gas comprising~~

~~ethylene, present in the process gas in an amount of at least 10 mol.%;~~

~~acetylene, present in the process gas in an amount of at least 1 ppm;~~

~~hydrogen, present in the process gas in an amount of at least 5 mol.%; and~~

~~at least 600 ppm carbon monoxide;~~

~~wherein the catalyst composition comprises~~

~~a porous support, present in the composition in an amount within the range of 90 wt.% to 99.9 wt.%;~~

~~palladium, present in the composition in an amount within the range of at least 0.02 wt.%, calculated on an elemental mass basis; and~~

~~one or more ionic liquids, present in the composition in a combined amount up to 10 wt.%,~~

~~wherein the hydrogenation catalyst has a BET surface area of no more than 10 m^2/g and a pore volume of at least 0.05 mL/g;wherein at least 90% of the acetylene present in the process gas is hydrogenated, and no more than 1 mol.% of the total of acetylene and ethylene present in the process gas is converted to ethane.~~

~~5. A method according to claim 4, wherein carbon monoxide is present in the process gas in an amount within the range of 1000 ppm to 20,000 ppm.~~

~~6~~4. A method according to any of claims 1-~~3~~5, wherein the process gas is contacted with the catalyst at a gas hourly space velocity (GHSV) within the range of 2,000 h^{-1} to 40,000 h^{-1}.

~~7~~5. A method according to any of claims 1-~~3~~5, wherein the process gas is contacted with the catalyst at a GHSV within the range of 7,100 h^{-1} to 40,000 h^{-1}.

~~8~~6. A method according to any of claims 1-~~5~~3, wherein the selective hydrogenation is conducted at a temperature within the range of 20 °C to 140 °C.

~~9~~7. A method according to any of claims 1-~~5~~3, wherein at least 95% of the acetylene present in the process gas is hydrogenated.

~~10~~8. A method according to any of claims 1-~~5~~3, wherein the amount of ethane in the product of the selective hydrogenation is no more than 0.5 mol.% greater than the amount of ethane in the process gas.

~~11~~9. A method according to any of claims 1-~~3~~5, wherein ethylene is present in the process gas in an amount of at least 20 mol.%.

~~12~~10. A method according to any of claims 1-~~5~~3, wherein acetylene is present in the process gas in an amount of at least 500 ppm.

~~13~~11. A method according to any of claims 1-~~5~~3, wherein hydrogen is present in the process gas in an amount in the range of 5 mol.% to 35 mol.%.

~~14~~12. The method according to any of claims 1-~~5~~3, wherein the process gas contains no more than 5 mol.% of carbon-containing components other than C_1 components (e.g., methane, carbon monoxide, and carbon dioxide), C_2 components (e.g., ethylene, ethane, and acetylene) and C_3 components (e.g., propane, propylene, methyl acetylene, and propadiene).

~~15~~13. A method according to any of claims 1-~~5~~3, wherein the porous support is selected from alumina, silica, titania, and mixtures thereof.

~~16~~14. A method according to any of claims 1-~~5~~3, wherein the at least one ionic liquid is selected from 1-butyl-3-methylimidazolium triflate, 1-ethyl-3-methylpyridinium ethylsulfate, 1-butyl-1-methylpyrrolidinium triflate, 1-butyl-2,3-dimethylimidazolium triflate, 1-butyl-3-methylimidazolium tricyanomethane, 1-butyl-3-methylimidazolium methylsulfate, 1-butyl-3-methylimidazolium octylsulfate, 1-butyl-3-methylimidazolium tetrafluoroborate, 1-ethyl-3-methylimidazolium ethylsulfate, 1-ethyl-3-methylimidazolium methylphosphonate, 1-ethyl-3-methylimidazolium triflate, 1-butyl-1-methylpyrrolidinium bis(trifluoromethylsulfonyl)imide, 1-butyl-1-methylpyrrolidinium tetracyanoborate, 1-butyl-1-methylpyrrolidinium tris(pentafluoroethyl)trifluorophosphate, 1-butyl-3-methylimidazolium bis(trifluoromethylsulfonyl)imide, 1-butyl-3-methylimidazolium tricyanomethane, 1-ethyl-3-methylpyridinium bis(trifluoromethylsulfonyl)imide, 1-ethyl-3-methylimidazolium tetracyanoborate, 1-ethyl-3-methylimidazolium tris(pentafluoroethyl)trifluorophosphate, 1-methyl-3-octylimidazolium triflate, ethyldimethyl-(2-methoxyethyl)ammonium tris(pentafluoroethyl)trifluorophosphate, tributylmethylammonium dicyanamide, tricyclohexyltetradecylphosphonium tris(pentafluoroethyl)trifluorophosphate, and 1-ethyl-3-methylimidazolium bis(trifluoromethylsulfonyl)imide.