

SPECIFICATION

Diamond Sintered Body Having High Strength and High Wear Resistance, and Tool Including the Same

5

Technical Field

The present invention relates generally to a diamond sintered body having high strength and high wear resistance, and particularly, to a highly strong and highly abrasion-resisting diamond sintered body having high wear resistance, chipping resistance, shock resistance and thermal conductivity, and a tool including the sintered body.

10

Background Art

Diamond is the hardest material present on earth. Particularly, a diamond sintered body hardly suffers from chips caused by the cleavage, a shortcoming of monocrystalline diamond, and therefore is often used as a material for a cutting tool for a nonferrous material such as an aluminum-silicon alloy. Japanese Patent Publication Nos. 39-20483 and 52-12126 for example disclose sintered bodies formed by sintering diamond particles using a ferrous metallic binder such as cobalt.

15

20

Among these diamond sintered bodies, those having granules with a diamond particle size of less than 5 μ m or those having extra fine granules with a particle size of at most 1 μ m are known as highly chipping-resisting materials. Japanese Patent Publication No. 39-20483 for example discloses a diamond sintered body including fine diamond particles and ferrous metal powder which allows diamond to be dissolved and re-precipitated, and Japanese Patent Publication No. 58-32224 for example discloses a diamond sintered body including sintered diamond particles having a particle size of at most 1 μ m, a carbide, a nitride and a boride of a metal belonging to group 4a, 5a or 6a in the periodic table, a solid solution or mixture thereof and a ferrous alloy.

25

30

When these fine diamond particles and a ferrous metal such as cobalt or tungsten carbide-cobalt are used as starting materials for

sintering, diamond particles could often grow abnormally unless the temperature and pressure conditions are strictly controlled, because such diamond particles are extremely active. Therefore, the size of the diamond particles partly becomes extremely large, which makes it difficult to provide
5 a diamond sintered body having a particle size of at most $1\mu\text{m}$ and a homogeneous microstructure with high yields.

In order to solve this problem, there is known a method of controlling the growth of particles by providing hard particles such as tungsten carbide, cubic boron nitride and silicon carbide at diamond grain boundaries.

10 Japanese Patent Publication No. 61-58432 for example discloses a diamond sintered body formed by adding tungsten carbide as hard particles.

This method however controls abnormal growth of diamond particles by providing hard particles having low compatibility with diamond particles between the diamond particles, thereby physically and chemically
15 preventing direct bonding between the diamond particles, and therefore the formation of skeletons by sintering between the diamond particles is insufficient. As a result, the chipping resistance, shock resistance and thermal conductivity, i.e., essential characteristics of diamond are disadvantageously lowered.

20 Meanwhile, among various diamond sintered bodies, coarse grained ones having a particle size from at least $5\mu\text{m}$ to at most $100\mu\text{m}$ are generally known as having high wear resistance. Such coarse grained diamond particles are, however, not easily sintered, and therefore a known method forms a carbide on the surface of diamond particles in order to
25 make sintering easier. Japanese Patent Laying-Open No. 63-134565 for example discloses a method of producing a carbide on the surface of diamond particles, thereby enhancing the binding force of a sintering aid metal to individual diamond particles to ease sintering. Many products of diamond sintered body using sintering aid including a tungsten carbide in
30 order to ease sintering are manufactured.

When a carbide is thus generated on the surface of diamond particles, however, the wear resistance, chipping resistance, shock resistance and thermal conductivity are lower than diamond sintered bodies including

only diamond particles and a ferrous metal. If a tungsten carbide is added to a sintering aid, the content of the sintering aid increases, which is more likely to deteriorate the wear resistance of the diamond sintered body.

5 In recent years, harder materials difficult to cut increase in work materials machining with a diamond sintered body. As a result, it is required that the sintered body has wear resistance, chipping resistance, shock resistance and thermal conductivity higher than conventional sintered bodies.

10 The present invention is directed to a solution to the above-described problems, and it is an object of the present invention to provide a diamond sintered body having wear resistance, chipping resistance, shock resistance and thermal conductivity higher than conventional diamond sintered bodies.

15 Disclosure of the Invention

The inventors have found that the strength such as chipping and shock resistance, wear resistance and thermal conductivity of a diamond sintered body could be improved by strengthening direct bonds between diamond particles as a result of their earnest study to improve the chipping
20 resistance and wear resistance. Conventional sintered bodies using granular diamond powder have used hard particles having low compatibility with diamond particles in order to restrain the growth of the diamond particles, and methods of restraining grain growth without using such hard particles were considered by the inventors.

25 As a result, it was found that diamond dissolved in a ferrous metal as a sintering aid at the time of sintering, and as the diamond sintered body cooled down after the sintering, the diamond in the ferrous metal was re-precipitated, which caused abnormal growth of diamond particles. It was then found that in order to prevent this phenomenon, metallic
30 tungsten could be added to the ferrous metal as the sintering aid, which reduced the amount of diamond dissolved in the ferrous metal, which could reduce re-precipitation and prevent diamond particles from abnormally growing. By this method, the use of conventional hard particles is not

necessary, diamond particles are more easily bonded with one another, so that a strong skeleton is formed. Furthermore, since the hard particles are not necessary, the content of diamond in the resultant diamond sintered body increases.

5 In a sintered body using coarse-grained diamond powder, metal tungsten added in a sintering aid makes it easier to sinter the diamond particles. Therefore, the addition of tungsten carbide as conventionally practiced is not necessary, which improves the wear resistance of the diamond sintered body.

10 It was also found that the wear resistance of the sintered body increased as the content of diamond particles in the diamond sintered body increased.

 It was also found that the size of defects in the sintered body was closely related with strength characteristics such as the chipping resistance and shock resistance of the sintered body. The defects herein are diamond
15 particles having an extremely large size in the sintered body, a pool of a sintering aid such as a solvent metal, a fault in the diamond sintered body and the like. The strength of the sintered body increases as defects in the diamond sintered body are reduced.

20 A highly strong and abrasion resistant diamond sintered body according to the present invention based on the above knowledge includes sintered diamond particles, and a sintering aid and an inevitable impurity as the remainder. The content of the sintered diamond particles is at least 80 vol. % and less than 99 vol. %. The diamond particles have a particle
25 size in the range from at least 0.1 μ m to at most 70 μ m. Sintered diamond particles next to each other are directly bonded. The sintering aid includes at least one kind selected from the group consisting of iron, cobalt and nickel, and metallic tungsten. Herein, the substance represented by the word "tungsten" may be metallic tungsten or a tungsten compound such
30 as tungsten carbide. The content of tungsten in the sintered body is in the range from at least 0.01 wt % to at most 8 wt %.

 In such a diamond sintered body, metallic tungsten is added in the sintering aid. As a result, abnormal growth of diamond particles used as a

raw material may be restrained without adding hard particles even if the size of the diamond particles is small. Meanwhile, if the size of diamond particles used as a raw material is large, a highly strong diamond sintered body having high chipping resistance, wear resistance, shock resistance and thermal conductivity may be provided by adding metallic tungsten in the sintering aid. Since the amount of the sintering aid to be added is smaller than the conventional cases and the content of diamond is larger, the wear resistance will not be lowered.

The content of sintered diamond particles is set in the range from at least 80 % by volume to less than 99 % by volume for the following reason. If the content of sintered diamond particles is less than 80 volume %, the strength such as chipping resistance and shock resistance, and the wear resistance are reduced, while the content of diamond particles cannot be technically set to the level equal to or higher than 99 % by volume.

The size of sintered diamond particles is set in the range from at least 0.1 μ m to at most 70 μ m for the following reason. If the size of sintered diamond particles is less than 0.1 μ m, the surface area of diamond particles increases, and then a diamond sintered body is more likely to abnormally grow, which reduces the wear resistance of the diamond sintered body. If the particle size exceeds 70 μ m, the cleavage of diamond particles reduces the strength of the diamond sintered body.

The content of tungsten in the sintered body is set in the range from at least 0.01 % by weight to at most 8 % by weight for the following reason. If the content of tungsten is less than 0.01 % by weight, the effect of adding metal tungsten in the sintering aid cannot be obtained. If the content of tungsten exceeds 8 % by weight, the content of diamond in the sintered body is reduced, and the diamond dissolved in the sintering aid is too small, resulting in incomplete sintering.

The diamond sintered body includes tungsten carbide, the ratio (I_{WC}/I_D) of X-ray diffraction intensity I_{WC} by the plane index (100) or the plane index (101) of the tungsten carbide in the diamond sintered body relative to X-ray diffraction intensity I_D by the plane index (111) of the sintered diamond particles is less than 0.02, the diamond sintered body

contains cobalt, and the ratio (I_{Co}/I_D) of X-ray diffraction intensity I_{Co} by the plane index (200) of cobalt in the diamond sintered body relative to I_D is preferably less than 0.4.

5 The diamond sintered body contains nickel, and the ratio (I_{Ni}/I_D) of X-ray diffraction intensity I_{Ni} by the plane index (200) of the nickel in the diamond sintered body relative to X-ray diffraction intensity I_D by the plane index (111) of the sintered diamond particles is preferably less than 0.4.

10 The diamond sintered body contains iron, and the ratio (I_{Fe}/I_D) of X-ray diffraction intensity I_{Fe} by the plane index (200) of the iron in the diamond sintered body relative to X-ray diffraction intensity I_D by the plane index (111) of the sintered diamond particles is preferably less than 0.2. Herein, the "X-ray diffraction intensity" refers to the level of a peak in an X-ray diffraction profile using a $CuK\alpha$ radiation (a characteristic X-ray generated by the K-shell of Cu).

15 The above conditions are defined because if I_{WC}/I_D exceeds 0.02, the amount of tungsten carbide is excessive, which lowers the wear resistance. If the intensity ratio of the intensity by the above ferrous metals are without the above-described ranges, the amount of the ferrous metal in diamond sintered body becomes excessive, which also lowers the wear
20 resistance of the diamond sintered body.

The sintering aid further includes palladium, and the ratio of the palladium in the sintering aid is preferably in the range from at least 0.005 % by weight to at most 40 % by weight. In this case, since the palladium is added to the sintering aid, the melting point of the sintering aid is lowered,
25 so that the diamond sintered body may be sintered at low temperatures. The ratio of the palladium is set in the range from at least 0.005 % by weight to at most 40 % by weight for the following reason. If the ratio of palladium is less than 0.005 % by weight, the amount of palladium is not enough for lowering the melting point of the sintering aid, while if the ratio
30 exceeds 40 % by weight, the melting point of the sintering aid conversely increases, which makes sintering hard.

The sintering aid further includes at least one kind selected from the group consisting of tin, phosphorus and boron, and the total percentage of

tin, phosphorus and boron in the sintering aid is preferably at least 0.01 % by weight and at most 30 % by weight. In this case, since at least one kind from tin, phosphorus and boron is included in the sintering aid, any of these elements lowers the melting point of the sintering aid. As a result, the diamond powder may be sintered at relatively low temperatures.

Herein, the ratio of these elements is set in the range from at least 0.01 % by weight to at most 30 % by weight for the following reason. If the ratio of these elements is less than 0.01 % by weight, the effect of lowering the melting point of the sintering aid is not enough, while if the ratio exceeds 30 % by weight, diamond hardly dissolves in the ferrous group metal in the sintering aid at the time of sintering. Thus, the bonds between diamond particles will not be enough, and the strength or thermal conductivity are lowered.

The inventors also noticed oxygen or oxide adsorbing the surface of diamond powder, a raw material to manufacture a diamond sintered body, and found that removal of these substances could reduce defects in the sintered body, and the strength of diamond sintered body could be improved. As a result, the percentage of oxygen in the diamond sintered body is preferably in the range from at least 0.005 % by weight to 0.08 % by weight, because ratios less than 0.005 % by weight are not available by the present technical level, while the strength of the diamond sintered body could be the same as conventional cases for a ratio equal to higher than 0.08 % by weight.

Traverse resistance measured at a span of 4mm, using a measurement test piece having a length of 6mm, a width of 3mm and a thickness in the range from at least 0.35mm to at most 0.45mm manufactured from a diamond sintered body obtained as described above is preferably in the range from at least 50kgf/mm² to 300kgf/mm².

Traverse resistance measured at a span of 4mm, using a test piece manufactured from the diamond sintered body thus obtained and dissolved in fluoro-nitric acid is preferably at least 50kgf/mm².

The above-described highly strong and abrasion-resistant diamond sintered body is preferably used as a tool. In this case, the tool including

the highly strong and abrasion-resistant diamond sintered body includes sintered diamond particles, and a sintering aid and an inevitable impurity as the remainder. The content of the sintered diamond particles is in the range from at least 80 % volume by volume to less than 99 % by volume.

5 The sintered diamond particles have a particle size in the range from at least 0.1 μ m to at most 70 μ m. Sintered diamond particles next to each other are directly bonded. The sintering aid includes at least one kind selected from the group consisting of iron, cobalt and nickel, and metallic tungsten. The content of the tungsten in the sintered body is in the range
10 from at least 0.01 % by weight to at most 8 % by weight.

In order to provide a diamond sintered body according to the present invention, a sintering aid is homogeneously distributed and does not contain unnecessary components. As a method of coating particles included in diamond powder with a sintering aid in view of the above
15 points, CVD (Chemical Vapor Deposition) methods and PVD (Physical Vapor Deposition) methods or solution precipitation methods may be employed.

Furthermore, since the homogeneously of a sintering aid coating the surface of diamond particles is significantly important for improvements in the difficulty of sintering diamond powder and the strength of the diamond
20 sintered body according to the present invention, and the method should be highly economical, an electroless plating disclosed in Japanese Patent Laying-Open No. 8-225875 by the inventors may be most preferably employed.

25
Best Mode for Carrying Out the Invention

First Embodiment

Manufacture of Diamond Sintered Body

Different kinds of diamond powder having different particle sizes
30 and sintering aids having different components (1A to 1H) given in Table 1 were prepared. Sintering aids 1A, 1B, 1E and 1F were added to diamond powder by eletroless plating, sintering aids 1C and 1G by ultrafine particle powder mixing, and sintering aids 1D and 1H by cemented carbide

ballmilling. For the ultrafine powder mixing, ultrafine cobalt powder having a particle size of at most 0.5 μ m and diamond powder were placed in a container formed of Teflon to have a prescribed composition, and then Teflon balls were placed in the container, and then they were mixed for three hours to manufacture a powder sample. For the cemented carbide ballmilling, diamond powder, tungsten carbide powder and cobalt powder were placed in a container formed of tungsten carbide-cobalt together with tungsten carbide-cobalt balls for mixing for a prescribed time period. The time for mixing was controlled to manufacture sample powder having a prescribed sintering aid composition. The samples by these methods are given in Table 1.

Table 1

Sample No.	Diamond Powder Particle Size (μ m)	Method of Adding Sintering Aid	Content of Sintering Aid (% by vol)	Composition of Sintering Aid (% by wt)
1A	0.1 ~ 4	electroless plating	7.0	90.85 Co, 5.0 W, 4.0 Fe, 0.05Pd, 0.10 Sn
1B	0.1 ~ 4	electroless plating	25.0	90.85 Co, 5.0 W, 4.0 Fe, 0.05 Pd, 0.10 Sn
1C	0.1 ~ 4	ultrafine particle powder mixing	7.0	100 Co
1D	0.1 ~ 4	cemented carbide ballmill	7.0	25 Co, 75 WC,
1E	0.1 ~ 60	electroless plating	7.0	90.85 Co, 5.0 W, 4.0 Fe, 0.05 Pd, 0.10 Sn
1F	0.1 ~ 60	electroless plating	25.0	90.85 Co, 5.0 W, 4.0 Fe, 0.05 Pd, 0.10 Sn
1G	0.1 ~ 60	ultrafine particle powder mixing	7.0	100 Co
1H	0.1 ~ 60	cemented carbide ballmill	7.0	25 Co, 75 WC,

The "Composition of sintering aid" in Table 1 refers to the percentage

of each component in the sintering aid. For example, in the case labeled "90.85 Co", 90.85 % by weight of the sintering aid is cobalt.

Samples 1A to 1D were heat-treated at 1300°C for 60 minutes, and 1E to 1H were heat-treated at 1500°C for 60 minutes. Samples 1A to 1H were each placed in a tantalum container, and sintered under a pressure of 55kb, at a temperature of 1450°C using a belt type ultra high pressure apparatus to provide a diamond sintered body.

Evaluation of Diamond Sintered Body

Measurement of Diffraction Intensity Ratio

The diamond sintered body obtained by the above process was subjected to X-ray diffraction an electron beam at an acceleration voltage of 40kV directed to a copper target, at a current of 25mA, at a diffraction angle 2θ in the range from 20° to 80°, and at a scanning speed of 0.1°/sec, using a $\text{CuK}\alpha$ radiation (a characteristic X-ray generated by the K-shell of Cu). As a result, the levels (of intensity) I_{WC} , I_{D} , and I_{Co} of diffraction peaks of the plane index (101) of tungsten carbide, the plane index (111) of diamond, and the plane index (200) of cobalt were measured.

Measurement of Strength

A plurality of rectangular parallelepiped test pieces having a length of 6mm, a width of 3mm, and a thickness of 0.4mm were cut from each diamond sintered body. The strength (transverse rupture strength) of the sintered body was measured by a three-point bending test at a span distance of 4mm for these samples. The samples were placed in a fluoronitric acid solution produced by mixing 40ml nitric acid of a molarity of 30% and 10ml hydrogen fluoride of a molarity of 45%. These samples were each placed in a sealed container, maintained at 130°C for three hours for dissolution. The strength (transverse rupture strength) of the sintered bodies was measured by a three-point bending test at a span distance of 4mm for the samples subjected to and not subjected to the dissolution treatment.

Measurement of W Content

The total contents of metallic tungsten (W) and tungsten carbide relative to the weight of the diamond sintered body were measured by

plasma emission spectrochemical analysis.

Measurement of Diamond Content

5 The surface of the diamond sintered body was observed using a microscope, and the region of diamond particles was measured to determine the diamond content in the sintered body.

Evaluation of Cutting Performance

A tool for cutting is manufactured using the sintered body, and the cutting performance was evaluated under the following condition.

10 Workpiece: Al-16 % by weight Si alloy round bar
The rotating speed of the surface of the workpiece: 700m/min
Depth of cut: 0.5mm
Feed rate: 0.15mm/rev
Cutting time: 5min

Confirming the Presence of Metallic Tungsten

15 Samples to be observed by a transmission electron microscope were manufactured from the obtained sintered bodies, observed in a plurality of arbitrary fields of view, and the presence/absence of metallic tungsten was determined based on the electron diffraction pattern. The result is given in Table 2.




Table 2

Sample No.	X-ray Diffraction Intensity Ratio (%)		Strength (kgf/mm ²)		W Content (% by wt)	Diamond Content (% by vol)	Flank Wear Width (μm)	Metallic Tungsten
	I _{wc} /I _D	I _{co} /I _D	Before Treated	After Treated				
1A	0.1	31	256	142	4.1	86	81	○
1B	0.9	45	210	117	4.5	80	103	○
1C	Sintering not possible							
1D	Sintering not possible							
1E	0.1	17	121	82	1.7	96	66	○
1F	0.2	25	103	71	1.9	91	73	○
1G	1.8	28	87	59	2.1	83	Chipping	×
1H	12	31	95	68	6.2	88	79	×

○: metallic tungsten present ×: absent

The "W content" in Table 2 represents the percentage by weight of tungsten (metallic tungsten and tungsten carbide in total) in the sintered body. The presence and absence of metallic tungsten observed by the transmission electron microscope was represented by "○" and "×" in the Table.

As can be seen from Table 2, products 1A and 1E according to the present invention show good performances both in the strength and flank wear.

Meanwhile, for 1C and 1D, the sintering aid was insufficient in amount and heterogeneously distributed, and therefore the dissolution of the sintering aid did not occur homogeneously within the powder diamond, so that a complete sintered body was not obtained.

It was observed that the sintering aid was heterogeneously distributed in the microstructure of the sintered body 1G, which caused chipping in the tool while cutting, and the tool could no longer be used.

As a result, products 1A and 1E according to the present invention provided higher strength, a smaller flank wear width and higher chipping resistance than conventional products 1D and 1H, and would show better performance as a good cutting tool. As a result of the observation with the microscope, sintered diamond particles next to each other were directly bonded.

Second Embodiment

Experiments to compare the characteristic of sintered bodies depending upon the particle sizes of diamond particles were performed. Several diamond powder samples having various particle sizes was prepared. A sintering aid was added to the diamond powder by an electroless plating such that the ratio of the diamond powder is 93% by volume and the ratio of a sintering aid having a prescribed position is 7% by volume, then heat treated, and diamond sintered bodies were manufactured according to the same method as the first embodiment.

The strength and flank wear width of the diamond sintered bodies were measured according to the method the same as the first embodiment. The result is given in Table 3.

Table 3

Sample No.	Diamond Power Particle Size(μm)	Diamond Content (% by vol)	Composition of Sintering Aid (% by wt)	Strength (kgf/mm^2)	Flank Wear Width (μm)	I_{wc}/I_D	W Content (% by wt)	Metallic Tungsten
2A	0.1~4	83	94.85 Co, 5.0 W, 0.05 Pd, 0.10 Sn	238	91	0.5	4.3	○
2B	0.1~60	93	94.85 Co, 5.0 W, 0.05 Pd, 0.10 Sn	105	67	0.2	2.1	○
2C	20~100	96	94.85 Co, 5.0 W, 0.05 Pd, 0.10 Sn	45	chipping	0.1	1.2	○

○: metallic tungsten present ×: absent

In a product 2A, the content of diamond was reduced, because much diamond was dissolved in the sintering aid, while in 2C, the sintering aid flowed out, and therefore the content of diamond increased. As can be seen from Table 3, a sample with a smaller diamond particle size, in other words, a finer sample (2A) has higher strength, and therefore higher shock resistance. Meanwhile, a sample with a larger particle size, in other words, a sample with coarse particles (2B) has a smaller width of flank wear, and has higher wear resistance. In 2C, the diamond particle size was so large that chipping was caused during cutting and the cutting test could not be continued.

Third Embodiment

Experiments about characteristics of sintered bodies depending upon the amount of metallic tungsten added in the sintering aid were performed. Several diamond powder samples having various particle sizes were prepared. Sintering aids having various ratios of tungsten were added to diamond powder samples by electroless plating, and subjected to heat treatment, followed by sintering according to the method the same as the first embodiment to obtain diamond sintered bodies. For the obtained diamond sintered bodies, the strength and flank wear width were measured according to the method the same as the first embodiment. The result is given in Table 4.

Table 4

Sample No.	Diamond Particle Size (μm)	Composition of Sintering aid (% by wt)	Diamond Content (% by vol)	Strength (kgf/mm^2)	Flank Wear Width (μm)	W Content (% by wt)	I _{wc} / I _D	Metallic Tungsten
3A	0.1~4	90.85 Co, 5.0 W, 4.0 Fe, 0.05 Pd, 0.10 Sn	86	256	81	4.1	0.1	○
3B	0.1~4	80.85 Co, 15.0 W, 4.0 Fe, 0.05 Pd, 0.10 Sn	79	186	110	13.4	2.1	○
3C	0.1~4	95.85 Co, 4.0 Fe, 0.05 Pd, 0.10 Sn	Abnormal grain growth					
3D	0.1~60	90.85 Co, 5.0 W, 4.0 Fe, 0.05 Pd, 0.10 Sn	96	121	66	1.7	0.1	○
3E	0.1~60	80.85 Co, 15.0 W, 4.0 Fe, 0.05 Pd, 0.10 Sn	90	103	85	8.2	1.7	○
3F	0.1~60	95.85 Co, 4.0 Fe, 0.05 Pd, 0.10 Sn	Partly not sintered					

○: metallic tungsten present ×: absent

Samples 3A and 3D in Table 4 are diamond sintered bodies manufactured from the same powder as samples 1A and 1E manufactured according to the first embodiment. Samples 3B, 3C, 3E and 3F were produced by changing the amount of metallic tungsten added in the sintering aid.

It is appreciated that when the amount of tungsten in the sintering aid exceeds 8 % by weight like samples 3B and 3E, the "strength" is small while the "width of flank wear" is large, and therefore the strength or wear resistance is lowered. For samples 3C and 3F without adding metallic tungsten, sintering was often incomplete and sintered body was not stably obtained. It is appreciated that samples 3A and 3D in which the amount of tungsten added in the sintered bodies is at least 0.01 % by weight and at most 8 % by weight have high strength and wear resistance.

Fourth Embodiment

Experiments were performed about the effect of the amount of palladium added in the sintering aid on the stability of obtaining complete sintered body. Several diamond powder samples having various particle sizes were prepared. The powder samples were formed by adding a sintering aid containing tungsten and palladium in various ratios, iron in 4.0 % by weight, and tin in 0.1 % by weight with the remainder of cobalt. These samples were maintained at a temperature of 1450°C under a pressure of 50kb for 20 minutes, using a belt type ultra high pressure apparatus. The result is given in Table 5.

Table 5

W Content (% by wt)	Pd Content (% by wt)	Diamond Powder Particle Size (μm)		
		0.1~1	1~2	5~10
4.0	—	○ (3.8)	○ (3.5)	○ (2.9)
4.0	0.02	○ (3.7)	○ (3.2)	○ (2.5)
—	0.02	△ (particle growth)	○	○
—	—	×	×	○

Parenthesized numbers each represent the content of tungsten (% by wt).

The "○" in Table 5 indicates that the powder sample was sintered and the particles did not grow abnormally. The "△ (particles growth)" indicates that the powder sample was sintered but part of the diamond particles grew abnormally. The "×" indicates that the powder sample was not completely sintered. For the samples with addition of metallic tungsten, the result of analysis of the content of tungsten in the sintered body is indicated in parentheses in the table. As can be seen from Table 5, in a sample including only tungsten and a sample including tungsten and palladium, the sintering was surely performed. In a sample without tungsten and including palladium, the sintering was performed to a certain extent, but the sintering was not performed sufficiently if fine diamond powder was used. This shows that the sintering is easily performed if the content of palladium is at least 0.01 % by weight and at most 40 % by weight, which is the range according to the present invention.

Fifth Embodiment

Experiments were performed about characteristics of sintered bodies produced with an additional sintering aid. Several diamond powder samples having a particle size in the range from 0.1 to 30 μ m were prepared. The diamond powder samples were subjected to degreasing and acid cleaning in order to add a sintering aid by electroless plating. The diamond powder samples were immersed in a cold solution containing palladium chloride, stannous chloride and hydro-chloric acid for two minutes at room temperature as a pre-treatment. Subsequently, the diamond powder samples were immersed in a sulfuric acid aqueous solution for two minutes. Then, the samples were washed with water, and then immersed in a Ni-B aqueous solution for plating at a temperature of 90°C containing nickel chloride and sodium boron hydroxide for two minutes to provide diamond powder samples coated with the sintering aid.

After the diamond powder samples were compressed for shaping, a metal plate and as an additional sintering aid having a composition given in Table 6 and the compact were layered and enclosed in a tantalum container.

Table 6

Sample No.	Diamond Powder Particle Size (μm)	Amount of Sintering Aid for Coating (% by vol)	Composition of Sintering Aid (% by wt)	Composition of Additional Sintering Aid (% by wt)
4A	0.1~30	0.1	87.0Ni, 7.0Pd, 5.0W, 1.0Sn	100 Ni
4B	0.1~30	0.1	87.0Ni, 7.0Pd, 5.0W, 1.0Sn	98 Ni, 2.0 B
4C	0.1~30	0.1	87.0Ni, 7.0Pd, 5.0W, 1.0Sn	89 Ni, 11 B
4D	0.1~30	0.1	87.0Ni, 7.0Pd, 5.0W, 1.0Sn	79 Ni, 21 B
4E	0.1~30	0.1	87.0Ni, 7.0Pd, 5.0W, 1.0Sn	66 Ni, 34 B

The " composition of additional sintering aid " in Table 6 is the composition of the metal plate. The " amount of sintering aid for coating " represents the ratio of the sintering aid in the diamond sintered body in percentage by volume.

Subsequently, the tantalum container was maintained at a temperature of 1550°C and under a pressure of 60kb for 10 minutes using a girdle type ultra high pressure apparatus. As a result, each diamond sintered body was produced.

Each of the sintered bodies was processed into a test piece having a length of 6mm, a width of 3mm and a thickness of 0.3mm, followed by three-point bending test at a span distance of 4mm to evaluate the strength. The result is given in Table 7.

Table 7

Sample No.	Diamond Content (% by vol)	Total Content of Sn and B in Sintering Aid (% by wt)	Strength (kgf/mm ²)
4A	94	0.005	88
4B	94	1.99	118
4C	94	11.0	105
4D	94	20.9	94
4E	94	33.8	72

As can be seen from Table 7, the strengths of 4B, 4C and 4D are higher than those of 4A and 4E.

5 More specifically, the total content of tin, phosphorus and boron in a sintering aid is preferably at least 0.01 % by weight and at most 30 % by weight. When the same experiments were performed with a sintering aid containing tin, phosphorus and boron, it was found that the total content of these substances was preferably at least 0.01 % by weight and at most 30 %
10 by weight.

Sixth Embodiment

Experiments were performed about characteristics of diamond sintered bodies while the heat treatment temperature of the diamond powder samples were varied. Products 1A and 1E produced according to
15 the first embodiment were heat-treated under various conditions. Then, diamond sintered bodies were produced by sintering the powder subjected to the heat treatment under the conditions the same as those of the first embodiment. The strength of these diamond sintered body were measured according to the same method as that in the first embodiment, and the
20 content of oxygen in the sintered bodies were measured by plasma emission spectrochemical analysis. The result is given in Table 8.

Table 8

Sample No.	Heat Treatment Condition	Strength (kgf/mm ²)	Oxygen Content (% by wt)
5A-1	1300°C, 60min	256	0.025
5A-2	1200°C, 60min	207	0.110
5A-3	1100°C, 60min	184	0.143
5E-1	1500°C, 60min	121	0.009
5E-2	1400°C, 60min	105	0.015
5E-3	1300°C, 60min	88	0.022

In Table 8, samples 5A-1 to 5A-3 were obtained using powder used for 1A according to the first embodiment. Samples 5E-1 to 5E-3 were obtained using powder for 1E. As a result, it is appreciated that the amount of oxygen remaining in the sintered body tends to decrease and therefore the strength of the sintered body increases as the heat treatment temperature is raised.

Note that it was appreciated from another experiment that powder sample 1A was not appropriately used, because the surface of the diamond powder was extremely graphitized when heat-treated at a high temperature equal to or higher than 1400°C, which causes graphite to remain in the resultant sintered body so that the sintering and cutting performance were lowered.

Seventh Embodiment

A diamond powder sample having a particle size in the range from 0.1 to 15 μ m was prepared, and a sintering aid identical to that added to powder samples 1A according to the first embodiment was added, followed by heat treatment at 1300°C in a vacuum. Subsequently, the powder after the heat treatment was filled within a container of an alloy containing tungsten carbide in 10% by weight and having an outer diameter of 20mm, an inner diameter of 12mm and a height of 18mm, followed by sintering at a high pressure and high temperature conditions. Wire drawn dies having a line size diameter of 3mm were manufactured from the resultant sintered body. The dies was used for a wire drawing test for a copper-plated steel

wire at a speed of 500m/min, with a water-soluble lubricant. As a result, an 80 ton-steel wire was produced by wire drawing, and the surface of the wire was fine.

Eighth Embodiment

5 Diamond sintered bodies 1A and 1E according to the first embodiment were used to manufacture a circular throw-away tip having a diameter of 13.2mm and a thickness of 3.2mm, and a round bar of granite having a compression strength of 1500kg/cm² was cut by a general purpose lathe under the following conditions:

10 The rotating speed of the surface of workpiece to be cut: 180m/min
Depth of cut: 0.5mm
Feed rate: 0.25mm/rev
Cutting time: 3 min

15 As a result, no chipping was observed in diamond sintered body 1A, and the flank abrasion width was above 0.5mm. Meanwhile, in diamond sintered body 1E, chipping as large as 0.03mm was observed at the cutting edge, while the flank wear width was as small as 0.1mm, which is small enough for the cutting test to be continued.

20 When a tool manufactured from a conventional diamond sintered body was used for cutting, the cutting resistance increases by abrasion at the time point after cutting for about 2 minutes, abnormal noises were heard during cutting, and therefore the cutting could not be continued. Extreme flank wear was observed in the used tool, and there was a cracking reaching to the cemented carbide which supports the diamond
25 sintered body.

When the diamond sintered body according to the present invention was applied to a drill bit tool which required shock resistance, good results were brought about.

Ninth Embodiment

30 Several diamond powder samples having a particle size in the range from 0.1 to 60μm were provided with a sintering aid containing cobalt, tungsten, iron and palladium in various percentages by electroless plating, followed by a heat treatment and then sintering. The obtained various

sintering bodies were subjected to X-ray diffraction as is the case with the first embodiment, the diffraction intensity I_{Ni} by the plane index (200) of nickel, the diffraction intensity I_{Fe} by the plane index (200) of iron and the diffraction intensity I_D by the plane index (111) of diamond particles were measured and the ratios I_{Ni}/I_D and I_{Fe}/I_D were obtained. The strength and flank abrasion width of each of the sintered bodies was checked similarly to the first embodiment.

As a result, the samples with I_{Ni}/I_D of less than 0.4 or I_{Fe}/I_D less than 0.4 had high strength and a small width of flank wear.

Industrial Applicability

A highly strong and highly abrasion-resistant diamond sintered body according to the present invention may applied to cutting tools such as a milling cutter, and an end mill, abrasion-resistant tools such as wire drawn dies, and shock-resisting parts such as a golf club head and a shock type power grinding jig.

CLAIMS

1. A high strength and high wear resistance diamond sintered body comprising sintered diamond particles and a sintering aid and an inevitable impurity as the remainder,
the content of said sintered diamond particles being at least 80 % by volume and less than 99 % by volume,
said sintered diamond particles having a particle size in the range from at least 0.1 μ m to at most 70 μ m,
said sintered diamond particles next to each other being directly bonded,
said sintering aid comprising at least one kind selected from the group consisting of iron, cobalt and nickel, and metallic tungsten,
the content of said tungsten in the sintered body being in the range from at least 0.01 % by weight to at most 8 % by weight
2. The high strength and high wear resistance diamond sintered body as recited in claim 1, further comprising tungsten carbide, wherein the ratio (I_{WC}/I_D) of X-ray diffraction intensity I_{WC} by the plane index (100) or the plane index (101) of said tungsten carbide in said diamond sintered body and X-ray diffraction intensity I_D by the plane index (111) of said sintered diamond particles is less than 0.02, said diamond sintered body further comprising cobalt, the ratio (I_{CO}/I_D) of X-ray diffraction intensity I_{CO} by the plane index (200) of said cobalt in said diamond sintered body and said I_D being less than 0.4.
3. The high strength and high wear resistance diamond sintered body as recited in claim 1, further comprising nickel, wherein the ratio (I_{Ni}/I_D) of X-ray diffraction intensity I_{Ni} by the plane index (200) of said nickel in said diamond sintered body and X-ray diffraction intensity I_D by the plane index (111) of said sintered diamond particles is less than 0.4.
4. The high strength and high wear resistance diamond sintered



body as recited in claim 1, further comprising iron, wherein the ratio (I_{Fe}/I_D) of X-ray diffraction intensity I_{Fe} by the plane index (200) of said iron in said diamond sintered body and X-ray diffraction intensity I_D by the plane index (111) of said sintered diamond particles is less than 0.2

5

5. The high strength and high wear resistance diamond sintered body as recited in claim 1, wherein

10 said sintering aid further includes palladium, and the percentage of said palladium in said sintering aid is in the range from at least 0.005 % by weight to at most 40 % by weight.

6. The high strength and high wear resistance diamond sintered body as recited in claim 1, wherein

15 said sintering aid further includes at least one kind selected from the group consisting of tin, phosphorus and boron, and the total percentage of said tin, phosphorus and boron in said sintering aid is in the range from at least 0.01 % by weight to at most 30 % by weight.

20 7. The high strength and high wear resistance diamond sintered body as recited in claim 1, wherein

the percentage of oxygen in said diamond sintered body is in the range from at least 0.005 % by weight to less than 0.08 % by weight

25 8. The high strength and high wear resistance diamond sintered body as recited in claim 1, wherein

30 the strength (transverse rupture strength) of said diamond sintered body measured at a span of 4mm, using a measurement test piece having a length of 6mm, a width of 3mm and a thickness from at least 0.35mm to at most 0.45mm is in the range from at least 50kgf/mm² to at most 300kgf/mm².

9. The high strength and high wear resistance diamond sintered body as recited in claim 8, wherein

This Sheet Has Been Replaced



the strength (transverse rupture strength) of said diamond sintered body measured at a span of 4mm, using said test piece dissolved by a fluoro-nitric acid is at least 50kgf/mm².

- 5 10. A tool including a high strength and high wear resistance diamond sintered body comprising sintered diamond particles, and a sintering aid and an inevitable impurity as the remainder, the content of said sintered diamond particles being in the range from at least 80 % by volume to less than 99 % by volume,
- 10 said sintered diamond particles having a particle size in the range from at least 0.1 μ m to at most 70 μ m,
- said sintered diamond particles next to each other being directly bonded,
- said sintering aid including at least one kind selected from the group
- 15 consisting of iron, cobalt and nickel, and metallic tungsten,
- the content of said tungsten in the sintered body being in the range from at least 0.01 % by weight to at most 8 % by weight.



This Sheet Has Been Replaced

