

Description

This invention relates to a hydrofining process for hydrocarbon-containing feed streams. In one aspect, this invention relates to a process for removing metals from a hydrocarbon-containing feed stream. In another aspect, this invention relates to a process for removing sulfur or nitrogen from a hydrocarbon-containing feed stream. In still another aspect, this invention relates to a process for removing potentially cokeable components from a hydrocarbon-containing feed stream. In still another aspect, this invention relates to a process for reducing the amount of heavies in a hydrocarbon-containing feed stream.

It is well known that crude oil as well as products from extraction and/or liquefaction of coal and lignite, products from tar sands, products from shale oil and similar products may contain components which make processing difficult. As an example, when these hydrocarbon-containing feed streams contain metals such as vanadium, nickel and iron, such metals tend to concentrate in the heavier fractions such as the topped crude and residuum when these hydrocarbon-containing feed streams are fractionated. The presence of the metals make further processing of these heavier fractions difficult since the metals generally act as poisons for catalysts employed in processes such as catalytic cracking, hydrogenation or hydrodesulfurization.

The presence of other components such as sulfur and nitrogen is also considered detrimental to the processability of a hydrocarbon-containing feed stream. Also, hydrocarbon-containing feed streams may contain components (referred to as Ramsbottom carbon residue) which are easily converted to coke in processes such as catalytic cracking, hydrogenation or hydrodesulfurization. It is thus desirable to remove components such as sulfur and nitrogen and components which have a tendency to produce coke.

It is also desirable to reduce the amount of heavies in the heavier fractions such as the topped crude and residuum. As used herein the term heavies refers to the fraction having a boiling range higher than about 538°C (1000°F). This reduction results in the production of lighter components which are of higher value and which are more easily processed.

It is thus an object of this invention to provide a process to remove components such as metals, sulfur, nitrogen and Ramsbottom carbon residue from a hydrocarbon-containing feed stream and to reduce the amount of heavies in the hydrocarbon-containing feed stream (one or all of the described removals and reduction may be accomplished in such process, which is generally referred to as a hydrofining process, depending on the components contained in the hydrocarbon-containing feed stream). Such removal of reduction provides substantial benefits in the subsequent processing of the hydrocarbon-containing feed streams.

EP—A—111,912 and EP—A—127,059 disclose processes for demetallizing hydrocarbon feedstreams whereby the life and activity of the catalyst composition used in the demetallization process may be increased by the addition of a decomposable metal compound selected from the metals of Group VB, Group VIB, Group VIIB and Group VIII of the Periodic Table into the hydrocarbon feed. The preferred metal is molybdenum and the preferred composition is molybdenum hexacarbonyl.

In accordance with the present invention, a hydrocarbon-containing feed stream, which also contains metals (such as vanadium, nickel, iron), sulfur, nitrogen and/or Ramsbottom carbon residue, is contacted with a solid catalyst composition comprising alumina, silica or silica-alumina. The catalyst composition also contains at least one metal selected from Group VIB, Group VIIB, and Group VIII of the Periodic Table, in the oxide or sulfide form. At least one decomposable compound selected from the group consisting of the compounds of metals of Group IVB of the Periodic table (i.e., titanium, zirconium and hafnium) is mixed with the hydrocarbon-containing feed stream prior to contacting the hydrocarbon-containing feed stream with the catalyst composition. The hydrocarbon-containing feed stream, which also contains the Group IVB metal, is contacted with the catalyst composition in the presence of hydrogen under suitable hydrofining conditions. After being contacted with the catalyst composition, the hydrocarbon-containing feed stream will contain a significantly reduced concentration of metals, sulfur, nitrogen and Ramsbottom carbon residue as well as a reduced amount of heavy hydrocarbon components. Removal of these components from the hydrocarbon-containing feed stream in this manner provides an improved processability of the hydrocarbon-containing feed stream in processes such as catalytic cracking, hydrogenation or further hydrodesulfurization. Use of the decomposable compound results in improved removal of metals, primarily vanadium and nickel.

The decomposable compound may be added when the catalyst composition is fresh or at any suitable time thereafter. As used herein, the term "fresh catalyst" refers to a catalyst which is new or which has been reactivated by known techniques. The activity of fresh catalyst will generally decline as a function of time if all conditions are maintained constant. It is believed that the introduction of the decomposable compound will slow the rate of decline from the time of introduction and in some cases will dramatically improve the activity of an at least partially spent or deactivated catalyst from the time of introduction.

For economic reasons it is sometimes desirable to practice the hydrofining process without the addition of the decomposable compound until the catalyst activity declines below an acceptable level. In some cases, the activity of the catalyst is maintained constant by increasing the process temperature. The decomposable compound is added after the activity of the catalyst has dropped to an unacceptable level and the temperature cannot be raised further without adverse consequences. It is believed that the addition

of the decomposable compound at this point will result in a dramatic increase in catalyst activity based on the results set forth in Example IV.

Other objects and advantages of the invention will be apparent from the foregoing brief description of the invention and the appended claims as well as the detailed description of the invention which follows.

5 The catalyst composition used in the hydrofining process to remove metals, sulfur, nitrogen and Ramsbottom carbon residue and to reduce the concentration of heavies comprises a support and a promoter. The support comprises alumina, silica or silica-alumina. Suitable supports are believed to be Al_2O_3 , SiO_2 , $\text{Al}_2\text{O}_3\text{-SiO}_2$, $\text{Al}_2\text{O}_3\text{-TiO}_2$, $\text{Al}_2\text{O}_3\text{-BPO}_4$, $\text{Al}_2\text{O}_3\text{-AlPO}_4$, $\text{Al}_2\text{O}_3\text{-Zr}_3(\text{PO}_4)_4$, $\text{Al}_2\text{O}_3\text{-SnO}_2$ and $\text{Al}_2\text{O}_3\text{-ZnO}$. Of these supports, Al_2O_3 is particularly preferred.

10 The promoter comprises at least one metal selected from the group consisting of the metals of Group VIB, Group VIIB, and Group VIII of the Periodic Table. The promoter will generally be present in the catalyst composition in the form of an oxide or sulfide. Particularly suitable promoters are iron, cobalt, nickel, tungsten, molybdenum, chromium, manganese, vanadium and platinum. Of these promoters, cobalt, nickel, molybdenum and tungsten are the most preferred. A particularly preferred catalyst composition is 15 Al_2O_3 promoted by CoO and MoO_3 or promoted by CoO , NiO and MoO_3 .

Generally, such catalysts are commercially available. The concentration of cobalt oxide in such catalysts is typically in the range of .5 weight percent to 10 weight percent based on the weight of the total catalyst composition. The concentration of molybdenum oxide is generally in the range of 2 weight percent to 25 weight percent based on the weight of the total catalyst composition. The concentration of nickel 20 oxide in such catalysts is typically in the range of .3 weight percent to 10 weight percent based on the weight of the total catalyst composition. Pertinent properties of four commercial catalysts which are believed to be suitable are set forth in Table I.

Catalyst	CoO (wt %)	MoO (wt %)	NiO (wt %)	Bulk density* (g/cc)	Surface area (M^2/g)
Shell 344	2.99	14.42	—	0.79	186
30 Katalco 477	3.3	14.0	—	.64	236
KF-165	4.6	13.9	—	.76	274
35 Commercial catalyst D Harshaw chemical company	0.92	7.3	0.53	—	178

* Measured on 0.84/0.42 mm (20/40 mesh) particles, compacted.

40 The catalyst composition can have any suitable surface area and pore volume. In general, the surface area will be in the range of 2 to 400 m^2/g , preferably 100 to 300 m^2/g , while the pore volume will be in the range of 0.1 to 4.0 cc/g, preferably 0.3 to 1.5 cc/g.

Presulfiding of the catalyst is preferred before the catalyst is initially used. Many presulfiding procedures are known and any conventional presulfiding procedure can be used. A preferred presulfiding 45 procedure is the following two step procedure.

The catalyst is first treated with a mixture of hydrogen sulfide in hydrogen at a temperature in the range of 175°C to 225°C, preferably about 205°C. The temperature in the catalyst composition will rise during this first presulfiding step and the first presulfiding step is continued until the temperature rise in the catalyst has substantially stopped or until hydrogen sulfide is detected in the effluent flowing from the reactor. The mixture of hydrogen sulfide and hydrogen preferably contains in the range of 5 to 20 percent 50 hydrogen sulfide, preferably about 10 percent hydrogen sulfide.

The second step in the preferred presulfiding process consists of repeating the first step at a temperature in the range of 350°C to 400°C, preferably 370°C, for about 2—3 hours. It is noted that other mixtures containing hydrogen sulfide may be utilized to presulfide the catalyst. Also the use of hydrogen 55 sulfide is not required. In a commercial operation, it is common to utilize a light naphtha containing sulfur to presulfide the catalyst.

As has been previously stated, the present invention may be practiced when the catalyst is fresh or the addition of the decomposable compound of a Group IVB metal may be commenced when the catalyst has been partially deactivated. The addition of the decomposable compound of a Group IVB metal may be 60 delayed until the catalyst is considered spent.

In general, a "spent catalyst" refers to a catalyst which does not have sufficient activity to produce a product which will meet specifications, such as maximum permissible metals content, under available refinery conditions. For metals removal, a catalyst which removes less than about 50% of the metals contained in the feed is generally considered spent.

65 A spent catalyst is also sometimes defined in terms of metals loading (nickel+vanadium). The metals

loading which can be tolerated by different catalyst varies but a catalyst whose weight has increased at least about 15% due to metals (nickel+vanadium) is generally considered a spent catalyst.

Any suitable hydrocarbon-containing feed stream may be hydrofined using the above described catalyst composition in accordance with the present invention. Suitable hydrocarbon-containing feed streams include petroleum products, coal, pyrolyzates, products from extraction and/or liquefaction of coal and lignite, products from tar sands, products from shale oil and similar products. Suitable hydrocarbon feed streams include gas oil having a boiling range from 205°C to 538°C, topped crude having a boiling range in excess of about 343°C and residuum. However, the present invention is particularly directed to heavy feed streams such as heavy topped crudes and residuum and other materials which are generally regarded as too heavy to be distilled. These materials will generally contain the highest concentrations of metals, sulfur, nitrogen and Ramsbottom carbon residues.

It is believed that the concentration of any metal in the hydrocarbon-containing feed stream can be reduced using the above described catalyst composition in accordance with the present invention. However, the present invention is particularly applicable to the removal of vanadium, nickel and iron.

The sulfur which can be removed using the above described catalyst composition in accordance with the present invention will generally be contained in organic sulfur compounds. Examples of such organic sulfur compounds include sulfides, disulfides, mercaptans, thiophenes, benzylthiophenes, dibenzylthiophenes, and the like.

The nitrogen which can be removed using the above described catalyst composition in accordance with the present invention will also generally be contained in organic nitrogen compounds. Examples of such organic nitrogen compounds include amines, diamines, pyridines, quinolines, porphyrins, benzoquinolines and the like.

While the above described catalyst composition is effective for removing some metals, sulfur, nitrogen and Ramsbottom carbon residue, the removal of metals can be significantly improved in accordance with the present invention by introducing a suitable decomposable compound selected from the group consisting of compounds of the metals of Group IVB of the Periodic Table into the hydrocarbon-containing feed stream prior to contacting the hydrocarbon containing feed stream with the catalyst composition. As has been previously stated, the introduction of the decomposable compound may be commenced when the catalyst is new, partially deactivated or spent with a beneficial result occurring in each case.

Any suitable decomposable compound of a Group IVB metal can be introduced into the hydrocarbon-containing feed stream. Examples of suitable compounds of titanium, zirconium or hafnium are aliphatic, cycloaliphatic and aromatic carboxylates having 1—20 carbon atoms, (e.g., octoates, neodecanoates, tallates, naphthenates), diketones (e.g., acetylacetonates), carbonyls, cyclopentadienyl complexes, mercaptides, xanthates, carbamates, dithiocarbamates, thiophosphates, dithiophosphates and mixtures thereof. Zirconium is a particularly preferred Group IVB metal. Zirconium octoate is a preferred decomposable compound.

Any suitable concentration of the decomposable compound may be added to the hydrocarbon-containing feed stream. In general, a sufficient quantity of the decomposable compound will be added to the hydrocarbon-containing feed stream to result in a concentration of Group IVB metal in the range of 1 to 500 ppm and more preferably in the range of 5 to 50 ppm.

High concentrations such as about 500 ppm and above should be avoided to prevent plugging of the reactor. It is noted that one of the particular advantages of the present invention is the very small concentrations of Group IVB metal which result in a significant improvement. This substantially improves the economic viability of the process.

After the decomposable compound has been added to the hydrocarbon-containing feed stream for a period of time, it is believed that only periodic introduction of the additive is required to maintain the efficiency of the process.

The decomposable compound may be combined with the hydrocarbon-containing feed stream in any suitable manner. The decomposable compound may be mixed with the hydrocarbon-containing feed stream as a solid or liquid or may be dissolved in a suitable solvent (preferably an oil) prior to introduction into the hydrocarbon-containing feed stream. Any suitable mixing time may be used. However, it is believed that simply injecting the decomposable compound into the hydrocarbon-containing feed stream is sufficient. No special mixing equipment or mixing period are required.

The pressure and temperature at which the decomposable compound is introduced into the hydrocarbon-containing feed stream is not thought to be critical. However, a temperature below 450°C is recommended.

The hydrofining process can be carried out by means of any apparatus whereby there is achieved a contact of the catalyst composition with the hydrocarbon containing feed stream and hydrogen under suitable hydrofining conditions. The hydrofining process is in no way limited to the use of a particular apparatus. The hydrofining process can be carried out using a fixed catalyst bed, fluidized catalyst bed or a moving catalyst bed. Presently preferred is a fixed catalyst bed.

Any suitable reaction time between the catalyst composition and the hydrocarbon-containing feed stream may be utilized. In general, the reaction time will range from about 0.1 hours to about 10 hours. Preferably, the reaction time will range from about 0.3 to about 5 hours. Thus, the flow rate of the hydrocarbon containing feed stream should be such that the time required for the passage of the mixture

through the reactor (residence time) will preferably be in the range of about 0.3 to about 5 hours. This generally requires a liquid hourly space velocity (LHSV) in the range of about 0.10 to about 10 cc of oil per cc of catalyst per hour, preferably from about 0.2 to about 3.0 cc/cc/hr.

The hydrofining process can be carried out at any suitable temperature. The temperature will generally be in the range of about 150°C to about 550°C and will preferably be in the range of about 340° to about 440°C. Higher temperatures do improve the removal of metals but temperatures should not be utilized which will have adverse effects on the hydrocarbon-containing feed stream, such as coking, and also economic considerations must be taken into account. Lower temperatures can generally be used for lighter feeds.

Any suitable hydrogen pressure may be utilized in the hydrofining process. The reaction pressure will generally be in the range of atmospheric to 69 mPa (10,00 psig). Preferably, the pressure will be in the range of 3.45 to 20.7 MPa (500 to 3,000 psig). Higher pressures tend to reduce coke formation but operation at high pressure may have adverse economic consequences.

Any suitable quantity of hydrogen can be added to the hydrofining process. The quantity of hydrogen used to contact the hydrocarbon-containing feedstock will generally be in the range of 17.8 to 3562 m³ per m³ (100 to 20,000 standard cubic feet per barrel) of the hydrocarbon-containing feed stream and will more preferably be in the range of 175 to 1069 m³ per m³ (1,000 to 6,000 standard cubic feet per barrel) of the hydrocarbon-containing feed stream.

In general, the catalyst composition is utilized until a satisfactory level of metals removal fails to be achieved which is believed to result from the coating of the catalyst composition with the metals being removed. It is possible to remove the metals from the catalyst composition by certain leaching procedures but these procedures are expensive and it is generally contemplated that once the removal of metals falls below a desired level, the used catalyst will simply be replaced by a fresh catalyst.

The time in which the catalyst composition will maintain its activity for removal of metals will depend upon the metals concentration in the hydrocarbon-containing feed streams being treated. It is believed that the catalyst composition may be used for a period of time long enough to accumulate 10—200 weight percent of metals, mostly Ni, V, and Fe, based on the weight of the catalyst composition, from oils.

The following examples are presented in further illustration of the invention.

Example 1

In this example, the automated experimental setup for investigating the hydrofining of heavy oils in accordance with the present invention is described. Oil, with or without a dissolved decomposable molybdenum or zirconium compound, was pumped downward through an induction tube into a trickle bed reactor, 0.72 m (28.5 inches) long and 1.9 cm (0.75 inches) in diameter. The oil pump used was a Whitey Model LP 10 (a reciprocating pump with a diaphragm-sealed head; marketed by Whitey Corp., Highland Heights, Ohio). The oil induction tube extended into a catalyst bed (located about 8.9 cm (3.5 inches) below the reactor top) comprising a top layer of about 40 cc of low surface area α -alumina (14 grit Alundum; surface area less than 1 m²/gram; marketed by Norton Chemical Process Products, Akron, Ohio), a middle layer of 33.3 cc of a hydrofining catalyst, mixed with 85 cc of 36 grit Alundum, and a bottom layer of about 30 cc of α -alumina.

The hydrofining catalyst used was a commercial, promoted desulfurization catalyst (referred to as catalyst D in Table I) marketed by Harshaw Chemical Company, Beachwood, Ohio. The catalyst had an Al₂O₃ support having a surface area of 178 m²/g (determined by BET method using N₂ gas), a medium pore diameter of 1.4×10^{-8} m (140 Å) and at total pore volume of .682 cc/g (both determined by mercury porosimetry in accordance with the procedure described by American Instrument Company, Silver Springs, Maryland, catalog number 5-7125-13. The catalyst contained 0.92 weight-% Co (as cobalt oxide), 0.53 weight-% Ni (as nickel oxide); 7.3 weight-% Mo (as molybdenum oxide).

The catalyst was presulfided as follows. A heated tube reactor was filled with a 10.2 cm (4 inch) high bottom layer of Alundum, an 0.45 m (18 inch) high middle layer of 33 cc of catalyst D mixed with 85 cc of 36 grit Alundum, and a 15.2 cm (6 inch) top layer of Alundum. The reactor was purged with nitrogen (10 l/hr) and the catalyst was heated for one hour in a hydrogen stream (10 l/hr) to about 204°C (400°F). While the reactor temperature was maintained at about 204°C (400°F), the catalyst was exposed to a mixture of hydrogen (10 l/hr) and hydrogen sulfide (1.4 l/hr) for about 14 hours. The catalyst was then heated for about one hour in this mixture of hydrogen and hydrogen sulfide to a temperature of about 371°C (700°F). The reactor temperature was maintained at 371°C (700°F) for about 14 hours while the catalyst continued to be exposed to the mixture of hydrogen and hydrogen sulfide. The catalyst was then allowed to cool to ambient temperature conditions in the mixture of hydrogen and hydrogen sulfide and was finally purged with nitrogen.

Hydrogen gas was introduced into the reactor through a tube that concentrically surrounded the oil induction tube but extended only as far as the reactor top. The reactor was heated with a Thermcraft (Winston-Salem, N.C.) Model 211 3-zone furnace. The reactor temperature was measured in the catalyst bed at three different locations by three separate thermocouples embedded in an axial thermocouple well ((0.25 inch) 0.64 cm outer diameter). The liquid product oil was generally collected every day for analysis. The hydrogen gas was vented. Vanadium and nickel contents were determined by plasma emission analysis; sulfur content was measured by X-ray fluorescence spectrometry; Ramsbottom carbon residue

14

was determined in accordance with ASTM D524; pentane insolubles were measured in accordance with ASTM D893; and N content was measured in accordance with ASTM D3228.

The decomposable zirconium compound used was mixed in the feed by first placing 9.3 grams of Zr octoate (containing 6 weight-% Zr; Mooney Chemicals, Cleveland, Ohio) in 2.23 kg (5 lb) of oil with shaking or stirring, and then further diluting this mixture with 5.44 (12 lb) of oil with agitation. A decomposable molybdenum compound, $\text{Mo}(\text{CO})_6$ (Aldrich Chemical Company, Milwaukee, Wisconsin), was mixed with the feed in a similar manner. The resulting mixtures were supplied through the oil induction tube to the reactor when desired.

10 Example II

A desalted, topped (400°F+) Hondo Californian heavy crude (density at 38.5°C: about 0.96 g/cc) was hydrotreated in accordance with the procedure described in Example I. The liquid hourly space velocity (LHSV) of the oil was about 1.5 cc/cc catalyst/hr; the hydrogen feed rate was about 850 m³ of hydrogen per m³ (4,800 standard cubic feet (SCF) of hydrogen per barrel) of oil; the temperature was about 399°C (750°F) and the pressure was about 15.6 MPa (2250 psig). The zirconium compound added to the feed in run 3 was $\text{Zr}(\text{C}_8\text{H}_{17}\text{CO}_2)_4$ (see Example I); the molybdenum compound added to the feed in control run 2 was $\text{Mo}(\text{CO})_6$. Pertinent process conditions and demetallization results of two control runs and one invention run are summarized in Table II.

20

25

30

35

40

45

50

55

60

65

15

TABLE II

Run	Days on stream	LHSV	Temp °C (°F)	PPM in feed			PPM in product				% Removal of (Ni+V)
				Added metal	Ni	V	Ni+V	Ni	V	Ni+V	
1 (Control) No additive	1	1.58	399 (750)	0	103	248	351	30	54	84	76
	2	1.51	399 (750)	0	103	248	351	34	59	93	74
	3	1.51	399 (750)	0	103	248	351	35	62	97	72
	4	1.51	399 (750)	0	103	248	351	36	63	99	72
	5	1.49	399 (750)	0	103	248	351	35	64	99	72
	6	1.55	399 (750)	0	103	248	351	28	60	88	75
	7	1.53	399 (750)	0	103	248	351	38	71	109	69
	9	1.68	399 (750)	0	103	248	351	40	64	104	70
	10	1.53	399 (750)	0	103	248	351	20	26	46 ¹⁾	87 ¹⁾
	17	1.61	399 (750)	0	103	248	351	49	98	147 ¹⁾	58 ¹⁾
	18	1.53	399 (750)	0	103	248	351	40	75	115	67
	19	1.53	399 (750)	0	103	248	351	44	73	113	68
	20	1.57	399 (750)	0	103	248	351	44	75	119	66
	21	1.45	399 (750)	0	103	248	351	41	68	109	69
	22	1.49	399 (750)	0	103	248	351	41	60	101	71
	24	1.47	399 (750)	0	103	248	351	42	69	111	68
2 (Control) Mo(CO) ₆ Added	1	1.56	399 (750)	20 ²⁾	103	248	351	22	38	60	83
	1.5	1.56	399 (750)	20	103	248	351	25	42	67	81
	2.5	1.46	399 (750)	20	103	248	351	28	42	70	80
	3.5	1.47	399 (750)	20	103	248	351	19	35	54	85
	6	1.56	399 (750)	20	103	248	351	29	38	67	81
	7	1.55	399 (750)	20	103	248	351	25	25	50	86
	8	1.50	399 (750)	20	103	248	351	27	35	62	82
	9	1.53	399 (750)	20	103	248	351	27	35	62	82
	10	1.47	399 (750)	20	103	248	351	32	35	67	81
	11	1.47	399 (751)	20	103	248	351	25	35	60	83
	12	1.42	399 (750)	20	103	248	351	27	34	61	83
	13	1.47	399 (750)	20	103	248	351	31	35	66	81
	14	1.56	399 (750)	20	103	248	351	36	52	88	75
	15	1.56	399 (750)	20	103	248	351	47	68	115 ¹⁾	67 ¹⁾
3 (Invention) Zr-Octoate	2	1.61	399 (750)	25 ³⁾	113	242	355	27	41	68	81
	3	1.60	399 (750)	25	113	242	355	—	—	—	—
	4	—	399 (751)	25	113	242	355	29	41	70	80
	5	—	399 (750)	25	113	242	355	29	42	71	80
	6	1.65	398 (748)	25	113	242	355	29	45	74	79
	7	1.59	398 (748)	25	113	242	355	29	40	69	81
	11	—	399 (750)	25	113	242	355	29	52	81	77
	12	—	399 (750)	25	113	242	355	24	45	69	81

¹⁾ Results believed to be erroneous.²⁾ ppm Mo.³⁾ ppm Zr.

16

Data in Table II show that the dissolved zirconium octoate was an effective demetallizing agent (compare runs 3 and 1), almost as effective as $\text{Mo}(\text{CO})_6$ (run 2).

The removal of other undesirable impurities in the heavy oil in the three runs is summarized in Table III.

TABLE III				
	Run 1 (Control)	Run 2 (Control)	Run 3 (Invention)	
5				
	Wt-% in feed:			
10	Sulfur	5.6	5.6	5.3
	Carbon residue	9.9	9.9	9.6
	Pentane insolubles	13.4	13.4	13
	Nitrogen	0.70	0.70	0.71
15	Wt-% in product:			
	Sulfur	1.5—3.0	1.3—2.0	1.0—1.4
	Carbon residue	6.6—7.6	5.0—5.9	5.0—5.5
	Pentane insolubles	4.9—6.3	4.3—6.7	3.5—4.3
20	Nitrogen	0.60—0.68	0.55—0.63	0.49—0.55
	% Removal of:			
	Sulfur	46—73	64—77	74—81
	Carbon residue	23—33	40—49	43—48
	Pentane insolubles	53—63	50—68	67—73
25	Nitrogen	3—14	10—21	23—31

Data in Table III show that the removal of sulfur, Ramsbottom carbon residue, pentane insolubles and nitrogen was consistently higher in run 3 (with Zr octoate) than in run 1 (with no added metal). Zr octoate was also more effective than $\text{Mo}(\text{CO})_6$ in removing sulfur, pentane insolubles and nitrogen. The density of the product of invention run 3 ranged from 0.892 to 0.891 g/cc (at 38.5°C).

Example III

An Arabian heavy crude (containing about 30 ppm nickel, 102 ppm vanadium, 4.17 wt % sulfur, 12.04 wt %, carbon residue, and 10.2 wt % pentane insolubles) was hydrotreated in accordance with the procedure described in Example 1. The LHSV of the oil was 1.0, the pressure was 15.6 MPa (2250 psig), the hydrogen feed rate was 850 m³ hydrogen per m³ (4,800 standard cubic feet hydrogen per barrel) of oil, and the temperature was 765°F (407°C). The hydrofining catalyst was presulfided catalyst D.

In run 4, no molybdenum was added to the hydrocarbon feed. In run 5, molybdenum (IV) octoate was added for 19 days. Then molybdenum (IV) octoate, which had been heated at 335°C (635°F) for 4 hours in Monagas pipe line oil at a constant hydrogen pressure of 6.86 MPa (980 psig) in a stirred autoclave, was added for 8 days. The results of run 4 are presented in Table IV and the results of run 5 in Table V.

17

0 169 378

TABLE IV (Run 4)

	Days on stream	PPM Mo in feed	PPM in product oil			% - Removal of Ni+V
			Ni	V	Ni+V	
5	1	0	13	25	38	71
	2	0	14	30	44	67
10	3	0	14	30	44	67
	6	0	15	30	45	66
15	7	0	15	30	45	66
	9	0	14	28	42	68
	10	0	14	27	41	69
20	11	0	14	27	41	69
	13	0	14	28	42	68
25	14	0	13	26	39	70
	15	0	14	28	42	68
	16	0	15	28	43	67
30	19	0	13	28	41	69
	20	0	17	33	50	62
35	21	0	14	28	42	68
	22	0	14	29	43	67
	23	0	14	28	42	68
40	25	0	13	26	39	70
	26	0	9	19	28	79
45	27	0	14	27	41	69
	29	0	13	26	39	70
	30	0	15	28	43	67
50	31	0	15	28	43	67
	32	0	15	27	42	68
55						
60						
65						

18

O 169 378

TABLE V (Run 5)

5	Days on stream	PPM Mo in feed	PPM in product oil			% -Removal of Ni+V
			Ni	V	Ni+V	
			Mo (IV) octoate as Mo source			
10	3	23	16	29	45	66
	4	23	16	28	44	67
	7	23	13	25	38	71
15	8	23	14	27	41	69
	10	23	15	29	44	67
	12	23	15	26	41	69
20	14	23	15	27	42	68
	16	23	15	29	44	67
	17	23	16	28	44	67
25	20	Changed to hydro-treated Mo (IV) octoate				
	22	23	16	28	44	67
	24	23	17	30	47	64
30	26	23	16	26	42	68
	28	23	16	28	44	67
	35					

Referring now to Tables IV and V, it can be seen that the percent removal of nickel plus vanadium remained fairly constant. No improvements in metals, sulfur, carbon residue, and pentane insolubles removal was seen when untreated or hydro-treated molybdenum octoate was introduced in run 5. This demonstrates that not all decomposable transition metal carboxylates provide a beneficial effect.

Example IV

This example illustrates the rejuvenation of a substantially deactivated sulfided, promoted desulfurization catalyst (referred to as catalyst D in Table I) by the addition of a decomposable Mo compound to the feed, essentially in accordance with Example I except that the amount of Catalyst D was 10 cc. The feed was a supercritical Monagas oil extract containing about 29—35 ppm Ni, about 103—113 ppm V, about 3.0—3.2 weight-% S and about 5.0 weight-% Ramsbottom C. LHSV of the feed was about 5.0 cc/cc catalyst/hr; the pressure was about 15.6 MPa (2250 psig) the hydrogen feed rate was about 177 m³H₂ per m³ of oil (1000 SCF H₂ per barrel of oil); and the reactor temperature was about 775°F (413°C). During the first 600 hours on stream, no Mo was added to the feed; thereafter Mo(CO)₆ was added. Results are summarized in Table VI.

TABLE VI

5	Hours on stream	Feed				Product			% Removal of (Ni+V)
		Added Mo (ppm)	Ni (ppm)	V (ppm)	(Ni+V) (ppm)	Ni (ppm)	V (ppm)	(Ni+V) (ppm)	
	46	0	35	110	145	7	22	29	80
10	94	0	35	110	145	8	27	35	76
	118	0	35	110	145	10	32	42	71
	166	0	35	110	145	12	39	51	65
15	190	0	32	113	145	14	46	60	59
	238	0	32	113	145	17	60	77	47
20	299	0	32	113	145	22	79	101	30
	377	0	32	113	145	20	72	92	37
	430	0	32	113	145	21	74	95	34
25	556	0	29	108	137	23	82	105	23
	586	0	29	108	137	24	84	108	21
30	646	25	29	103	132	22	72	94	29
	676	25	29	103	132	20	70	90	32
	682	25	28	101	129	18	62	80	38
35	706	25	28	101	129	16	56	72	44
	712	25	28	101	129	16	50	66	49
40	736	25	28	101	129	9	27	36	72
	742	25	28	101	129	7	22	29	78
	766	25	28	101	129	5	12	17	87

Data in Table VI show that the demetallization activity of a substantially deactivated catalyst (removal of Ni+V after 586 hours: 21%) was dramatically increased (to about 87% removal of Ni+V) by the addition of Mo(CO)₆ for about 120 hours. At the time when the Mo addition commenced, the deactivated catalyst had a metal (Ni+V) loading of about 34 weight-% (i.e., the weight of the fresh catalyst had increased by 34% due to the accumulation of metals). At the conclusion of the test run, the metal (Ni+V) loading was about 44 weight-%. Sulfur removal was not significantly affected by the addition of Mo. Based on these results, it is believed that the addition of a decomposable zirconium compound to the feed would also be beneficial in enhancing the demetallization activity of substantially deactivated catalysts.

Claims

1. A process for hydrofining a hydrocarbon-containing feed stream characterized by the steps of: introducing a decomposable compound selected from compounds of the metals of Group IVB of the Periodic Table into said hydrocarbon-containing feed stream; and contacting said hydrocarbon-containing feed stream containing said decomposable metal compound under hydrofining conditions with hydrogen and a catalyst composition comprising a support selected from alumina, silica and silica-alumina and a promoter comprising at least one metal selected from Groups VIB, VIIB and VIII of the Periodic Table.

2. The process of claim 1 characterized in that said catalyst composition is a used catalyst composition which has been at least partially deactivated by use in said hydrofining process.



19

0 169 378

TABLE VI

	Hours on stream	Feed				Product			% -Removal of (Ni+V)
		Added Mo (ppm)	Ni (ppm)	V (ppm)	(Ni+V) (ppm)	Ni (ppm)	V (ppm)	(Ni+V) (ppm)	
5	46	0	35	110	145	7	22	29	80
10	94	0	35	110	145	8	27	35	76
	118	0	35	110	145	10	32	42	71
	166	0	35	110	145	12	39	51	65
15	190	0	32	113	145	14	46	60	59
	238	0	32	113	145	17	60	77	47
20	299	0	32	113	145	22	79	101	30
	377	0	32	113	145	20	72	92	37
	430	0	32	113	145	21	74	95	34
25	556	0	29	108	137	23	82	105	23
	586	0	29	108	137	24	84	108	21
30	646	25	29	103	132	22	72	94	29
	676	25	29	103	132	20	70	90	32
	682	25	28	101	129	18	62	80	38
35	706	25	28	101	129	16	56	72	44
	712	25	28	101	129	16	50	66	49
40	736	25	28	101	129	9	27	36	72
	742	25	28	101	129	7	22	29	78
	766	25	28	101	129	5	12	17	87

Data in Table VI show that the demetallization activity of a substantially deactivated catalyst (removal of Ni+V after 586 hours: 21%) was dramatically increased (to about 87% removal of Ni+V) by the addition of Mo(CO)₆ for about 120 hours. At the time when the Mo addition commenced, the deactivated catalyst had a metal (Ni+V) loading of about 34 weight-% (i.e., the weight of the fresh catalyst had increased by 34% due to the accumulation of metals). At the conclusion of the test run, the metal (Ni+V) loading was about 44 weight-%. Sulfur removal was not significantly affected by the addition of Mo. Based on these results, it is believed that the addition of a decomposable zirconium compound to the feed would also be beneficial in enhancing the demetallization activity of substantially deactivated catalysts.

Claims

1. A process for hydrofining a hydrocarbon-containing feed stream characterized by the steps of: introducing a decomposable compound selected from compounds of the metals of Group IVB of the Periodic Table into said hydrocarbon-containing feed stream; and contacting said hydrocarbon-containing feed stream containing said decomposable metal compound under hydrofining conditions with hydrogen and a catalyst composition comprising a support selected from alumina, silica and silica-alumina and a promoter comprising at least one metal selected from Groups VIB, VIIB and VIII of the Periodic Table.

2. The process of claim 1 characterized in that said catalyst composition is a used catalyst composition which has been at least partially deactivated by use in said hydrofining process.



0 169 378



3. The process of claim 2 characterized in that said used catalyst composition is a spent catalyst composition due to use in said hydrofining process.

4. The process of any of the preceding claims characterized in that said decomposable metal compound is a zirconium compound; in particular wherein said decomposable metal compound is zirconium octoate.

5. The process of any of the preceding claims characterized in that said catalyst composition comprises alumina, cobalt and molybdenum.

6. The process of any of the preceding claims characterized in that said catalyst composition additionally comprises nickel.

10 7. The process of any of the preceding claims characterized in that said decomposable metal compound is added in such an amount to result in a concentration of Group IVB metal in said hydrocarbon-containing feed stream in the range of 1 to 500 ppm; in particular wherein said amount is in the range of 5 to 50 ppm.

15 8. The process of any of the preceding claims characterized in that said hydrofining conditions comprise a reaction time between said catalyst composition and said hydrocarbon-containing feed stream in the range of 0.1 to 10 hours, a temperature in the range of 150 to 550°C, a pressure in the range of atmospheric to 69 MPa and a hydrogen flow rate in the range of 17.8 to 3562 m³ per m³ of said hydrocarbon-containing feed stream; in particular wherein said reaction time is in the range of 0.3 to 5 hours, said temperature is in the range of 340 to 440°C, said pressure is in the range of 3.45 to 20.7 MPa and
20 said hydrogen flow rate in the range of 178 to 1069 m³ per m³ of said feed stream.

9. The process of any of the preceding claims characterized in that the adding of said decomposable metal compound to said hydrocarbon-containing feed stream is interrupted periodically.

10. The process of any of the preceding claims characterized in that said hydrofining process is a demetallization process and said hydrocarbon-containing feed stream contains metals; in particular
25 wherein said metals are nickel and vanadium.

Patentansprüche

1. Hydrofining-Verfahren für kohlenwasserstoffhaltiges Einsatzmaterial, gekennzeichnet durch
30 folgende Stufen: Zuführen einer zersetzbaren Verbindung, ausgewählt unter Verbindungen der Metalle der Gruppe IVB des Periodensystems, in das kohlenwasserstoffhaltige Einsatzmaterial; und Kontaktieren des kohlenwasserstoffhaltigen Einsatzmaterials mit einem Gehalt an der zersetzbaren Metallverbindung unter Hydrofining-Bedingungen mit Wasserstoff und einer Katalysatorzusammensetzung, die einen unter Aluminiumoxid, Siliciumdioxid und Siliciumdioxid-Aluminiumoxid ausgewählten Träger und einen
35 Promotor mit einem Gehalt an mindestens einem aus den Gruppen VIB, VIIB und VIII des Periodensystems ausgewählten Metall enthält.

2. Verfahren nach Anspruch 1, dadurch gekennzeichnet, dass es sich bei der gebrauchten Katalysatorzusammensetzung um eine zumindest teilweise durch die Verwendung im Hydrofining-Verfahren desaktivierte Katalysatorzusammensetzung handelt.

40 3. Verfahren nach Anspruch 2, dadurch gekennzeichnet, dass es sich bei der gebrauchten Katalysatorzusammensetzung um eine aufgrund der Verwendung im Hydrofining-Verfahren erschöpfte Katalysatorzusammensetzung handelt.

4. Verfahren nach einem der vorstehenden Ansprüche, dadurch gekennzeichnet, dass es sich bei der zersetzbaren Metallverbindung um eine Zirkoniumverbindung, insbesondere Zirkoniumoctoat, handelt.

45 5. Verfahren nach einem der vorstehenden Ansprüche, dadurch gekennzeichnet, dass die Katalysatorzusammensetzung Aluminiumoxid, Kobalt und Molybdän enthält.

6. Verfahren nach einem der vorstehenden Ansprüche, dass die Katalysatorzusammensetzung zusätzlich Nickel enthält.

7. Verfahren nach einem der vorstehenden Ansprüche, dadurch gekennzeichnet, dass die zersetzbare Metallverbindung in einer solchen Menge zugesetzt wird, dass sich eine Konzentration des Metalls der Gruppe IVB im kohlenwasserstoffhaltigen Einsatzmaterial im Bereich von 1 bis 500 ppm, insbesondere im Bereich von 5 bis 50 ppm ergibt.

8. Verfahren nach einem der vorstehenden Ansprüche, dadurch gekennzeichnet, dass die Hydrofining-Bedingungen eine Zeit der Reaktion zwischen der Katalysatorzusammensetzung und dem kohlenwasserstoffhaltigen Einsatzmaterial im Bereich von 0,1 bis 10 Stunden, eine Temperatur im Bereich von 150 bis 550°C, einen Druck im Bereich von Atmosphärendruck bis 69 MPa und eine Wasserstoff-Strömungsgeschwindigkeit im Bereich von 17,8 bis 3562 m³ pro m³ des kohlenwasserstoffhaltigen Einsatzmaterials umfasst, wobei insbesondere die Reaktionszeit im Bereich von 0,3 bis 5 Stunden liegt, die Temperatur im Bereich von 340 bis 440°C liegt, der Druck im Bereich von 3,45 bis 20,7 MPa liegt und die
55 Wasserstoff-Strömungsgeschwindigkeit im Bereich von 178 bis 1069 m³ pro m³ des Einsatzmaterials liegt.

9. Verfahren nach einem der vorstehenden Ansprüche, dadurch gekennzeichnet, dass die Zugabe der zersetzbaren Metallverbindung zum kohlenwasserstoffhaltigen Einsatzmaterial periodisch unterbrochen wird.

10. Verfahren nach einem der vorstehenden Ansprüche, dadurch gekennzeichnet, dass es sich beim
65 Hydrofining-Verfahren um ein Demetallisierungsverfahren handelt und das kohlenwasserstoffhaltige



21

0 169 378

Einsatzmaterial Metalle enthält, wobei es sich bei den Metallen insbesondere um Nickel und Vanadin handelt.

Revendications

5

1. Procédé pour le reformage catalytique d'un courant d'alimentation contenant des hydrocarbures caractérisé en ce qu'il comprend les étapes: d'introduction d'un composé décomposable choisi parmi des composés des métaux du Groupe IVB de la Classification Périodique dans le courant d'alimentation contenant des hydrocarbures et de mise en contact du courant d'alimentation contenant des hydrocarbures contenant le composé de métal décomposable dans des conditions de reformage catalytique avec de l'hydrogène et une composition catalytique comprenant un support choisi parmi l'alumine, la silice et la silice-alumine et un activateur comprenant au moins un métal choisi parmi les Groupes VIB, VIIB et VIII de la Classification Périodique.

2. Procédé selon la revendication 1, caractérisé en ce que la composition catalytique est une composition catalytique usée qui a été au moins partiellement désactivée par son emploi dans le procédé de reformage catalytique.

3. Procédé selon la revendication 2, caractérisé en ce que la composition catalytique usée est une composition catalytique épuisée en raison de son emploi dans le procédé de reformage catalytique.

4. Procédé selon l'une quelconque des revendications précédentes, caractérisé en ce que le composé de métal décomposable est un composé de zirconium et plus particulièrement en ce que le composé de métal décomposable est de l'octoate de zirconium.

5. Procédé selon l'une quelconque des revendications précédentes, caractérisé en ce que la composition catalytique comprend de l'alumine, du cobalt et du molybdène.

6. Procédé selon l'une quelconque des revendications précédentes, caractérisé en ce que la composition catalytique comprend en plus du nickel.

7. Procédé selon l'une quelconque des revendications précédentes, caractérisé en ce que l'on ajoute le composé de métal décomposable en une quantité permettant d'obtenir une concentration en métal du groupe IVB dans le courant d'alimentation contenant des hydrocarbures comprise entre 1 et 500 ppm et plus particulièrement en ce que cette quantité est comprise entre 5 et 50 ppm.

8. Procédé selon l'une quelconque des revendications précédentes, caractérisé en ce que les conditions de reformage catalytique comprennent un temps de réaction entre la composition catalytique et le courant d'alimentation contenant des hydrocarbures compris entre 0,1 et 10 heures, une température comprise entre 150 et 550°C, une pression comprise entre la pression atmosphérique et 69 MPa et un débit d'hydrogène compris entre 17,8 et 3562 m³ par m³ de courant d'alimentation contenant des hydrocarbures et plus particulièrement en ce que le temps de réaction est compris entre 0,3 et 5 heures, la température est comprise entre 340 et 440°C, la pression est comprise entre 3,45 et 20,7 MPa et le débit d'hydrogène est compris entre 178 et 1069 m³ par m³ de courant d'alimentation.

9. Procédé selon l'une quelconque des revendications précédentes, caractérisé en ce que l'on interrompt périodiquement l'addition de composé de métal décomposable au courant d'alimentation contenant des hydrocarbures.

10. Procédé selon l'une quelconque des revendications précédentes, caractérisé en ce que le procédé de reformage catalytique est un procédé d'élimination des métaux et en ce que le courant d'alimentation contenant des hydrocarbures contient des métaux et plus particulièrement en ce que ces métaux sont du nickel et du vanadium.

45

50

55

60

65