

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau200002077-6
IP02 wpy

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08F 4/02, 4/12, 4/78	A1	(11) International Publication Number: WO 99/31146 (43) International Publication Date: 24 June 1999 (24.06.99)
(21) International Application Number: PCT/US98/20172 (22) International Filing Date: 25 September 1998 (25.09.98) (30) Priority Data: 08/991,318 16 December 1997 (16.12.97) US (63) Related by Continuation (CON) or Continuation-in-Part (CIP) to Earlier Application US 08/991,318 (CON) Filed on 16 February 1997 (16.02.97) (71) Applicant (for all designated States except US): PHILLIPS PETROLEUM COMPANY [US/US]; 4th and Keeler, Bartlesville, OK 74004 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): BENHAM, Elizabeth, Ann [US/US]; 431 Shannon, Bartlesville, OK 74006 (US). MCDANIEL, Max, Paul [US/US]; 1601 Melmart Drive, Bartlesville, OK 74006 (US). (74) Agents: RICHARDS, John; Ladas & Parry, 26 West 61st Street, New York, NY 10023 (US) et al.		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: PROCESSES FOR PRODUCING COPOLYMERS OF ETHYLENE AND AT LEAST ONE OTHER OLEFIN (57) Abstract A process comprising polymerizing ethylene with at least one olefin to produce a polymer, and said polymer are provided.		

- 1 -

PROCESSES FOR PRODUCING COPOLYMERS OF ETHYLENE
AND AT LEAST ONE OTHER OLEFIN

FIELD OF THE INVENTION

This invention is related to the field of processes that produce
5 polymers that comprise ethylene.

BACKGROUND OF THE INVENTION

There are many production processes that produce polymers that
comprise ethylene. There are also many manufacturing processes that use these
polymers to produce useful items. One of these manufacturing processes is called
10 blow molding. In general, blow molding is useful for producing hollow plastic
products. A principle advantage of blow molding is its ability to produce hollow
shapes without having to join two or more separately molded parts.¹ In order to
produce a good quality blow molded product, one needs to start with a good quality
polymer. However, producing such good quality polymers is difficult. Therefore,
15 the inventors provide this invention so that such good quality polymers are more
readily obtainable.

SUMMARY OF THE INVENTION

It is desirable to provide a process to polymerize ethylene with at
least one olefin to produce a polymer.

20 It is also desirable to provide a polymer.

In accordance with this invention a process is provided. This process
comprises polymerizing ethylene with at least one olefin to produce a polymer,
wherein said polymerizing is conducted in a polymerization zone, where said
polymerization zone is essentially free of cocatalyst, and wherein said polymerizing
25 is conducted using a catalyst, where said catalyst comprises chromium oxide on a
support, and where said support comprises silica, and where said support is
essentially free of titania, alumina, and phosphates, and where said catalyst has been
activated, and where said catalyst after being activated is then reduced, and wherein
said polymerizing is conducted in the presence of hydrogen, and wherein the

30 ¹ See **SPI Plastic Engineering Handbook**, Fifth Edition, pages 341-382, edited by M.L.
Berins, published by Van Nostrand Reinhold (1991).

- 2 -

majority of said olefin is produced by said catalyst, during said polymerizing.

When used in this specification, the term "essentially free" means that the substance or mixture of substances recited before this phrase does not include an amount of the substance or mixture of substances recited after this phrase that would materially
5 affect the properties of the substance or mixtures of substances recited before this phrase.

In accordance with this invention a polymer comprising the following properties a density from 0.94 to 0.96, a melt index from 0.01 to 0.1 g/10 min., a high load melt index from 5 to 100 g/10 min., and a heterogeneity index from 4 to
10 14, a shear ratio from 50 to 200, and a Bottle ESCR 33 percent higher than a comparison resin.

DETAIL DESCRIPTION OF THE INVENTION

This invention, in general, is a process comprising polymerizing ethylene with at least one olefin to produce a polymer.

15 This polymerizing is conducted in a polymerization zone. This polymerization zone can be any convenient reactor. However, currently, it is preferred when the polymerization zone is a loop reactor. It is even more preferred when said polymerizing is conducted in a loop reactor under slurry polymerization conditions. Currently, the preferred diluent for slurry polymerization is isobutane.
20 One of the important aspects of this polymerization zone is that it is essentially free of cocatalysts. This is because cocatalysts adversely affect the formation of the desired product. Examples of such cocatalysts are trihydrocarbylboron compositions and trihydrocarbylaluminum compositions. In general, the amount of these cocatalysts should be less than 1 part per million based on the weight of the diluent.
25 However, it is most preferred when no cocatalyst is added to the polymerization zone.

The catalyst used in this invention comprises chromium oxide on a support. The amount of chromium on said support is in the range of about 0.01 to about 5 weight percent, preferably about 0.1 to about 3 weight percent, and most
30 preferably from 0.5 to 2 weight percent, where such weight percents are based on the weight of the support. The catalyst should be essentially free of chromium halide compounds and organo-chromium compounds (hereafter "HO compounds") as

- 3 -

these HO compounds can adversely affect the formation of the desired polymer. In general, the amount of these HO compounds should be less than 0.2 weight percent based on the weight of the support. However, it is most preferred if no HO compounds were added to the catalyst or to the polymerization zone.

5 The support comprises silica. Additionally, such support has silica as its major component by weight. It is most preferred when said support consists of silica, with little, if any, impurities. The support should be essentially free of titania, alumina, and phosphates (hereafter "TAP compounds") since these TAP compounds can adversely affect the formation of the desired product. In general,
10 the amount of these TAP compounds should be less than 0.2 weight percent based on the weight of the support. However, it is most preferred when no TAP compounds are added to the catalyst or to the polymerization zone.

 The support should have a surface area from about 200 to about 550 square meters per gram. It is more preferred when the support has a surface area
15 from about 225 to 425 square meters per gram, and it is most preferred when said support has a surface area from 250 to 400 square meters per gram. Surface areas below about 200 m²/g have less activity, while surface areas above about 550 m²/g produces polymers that have a die swell that is too high, an amount of long chain branching that is too low, and possibly, a melt index that is too low.

20 The support should have a pore volume from about 0.7 to about 2.5 cubic centimeters per gram. It is more preferred when the support has a pore volume from about 0.8 to about 1.8 cm³/g, and it is most when said support has a pore volume from 1 to 1.7 cm³/ gram. Pore volumes below about 0.7 cm³/g have less activity, while pore volumes above about 2.5 cm³/g adversely affect the
25 formation of the desired polymer.

 Methods of producing these types of catalysts are known in the art. See for example, U.S. Patents 3,900,457; 4,081,407; 4,392,990; 4,405,501; 4,735,931; 4,981,831; the disclosures of which are hereby incorporated by reference.

30 The catalyst should be activated in an oxidizing ambient at a temperature from about 600 to about 900°C. It is even more preferred when the temperature is from about 625 to about 850°C, and it is most preferred when the

- 4 -

temperature is from 645 to 820°C. At temperatures below about 600°C the activity of the catalyst is reduced and the physical properties of the polymer are adversely affected. At temperatures above about 900°C the catalyst can begin to sinter, thus hurting the polymerizing properties of said catalyst. Currently, the preferred oxidizing ambient is air. This activation is carried out for a time period of about 1 minute to about 50 hours. This allows a portion of the chromium in a lower valance state to be converted to a hexavalent state.

After activation, the catalyst is then reduced in an reducing ambient at a temperature from about 200 to about 550°C. It is even more preferred when the temperature is from about 225 to about 525°C and it is most preferred when the temperature is from 250 to 500°C. At temperatures below about 200°C the catalyst may not be sufficiently reduced. At temperatures above about 550°C the activity of the catalyst can be adversely affected and the melt index of the polymer can be too low. Currently, preferred reducing ambients are a mixture of carbon monoxide and nitrogen, or just carbon monoxide. This reduction is carried out for a time period of about 1 minute to about 50 hours. This allows a portion of the hexavalent chromium to be converted to a lower valent state.

In general, the oxidizing ambient promotes the formation of hexavalent chromium while the reducing ambient promotes the formation of chromium atoms that have a valance less than 6.

Said polymerizing is conducted at a temperature from about 94 to about 112°C. However, it is preferred when said polymerizing is conducted at a temperature from about 96 to about 110°C and it even more preferred when said polymerizing is conducted at a temperature from 98 to 108°C. At temperatures below about 94°C the activity of the catalyst is adversely affected. At temperatures above about 112°C the reactor could foul due to the swelling of the polymer.

It is important to this invention that hydrogen be present in the polymerization zone. This is because hydrogen promotes the formation of the desired polymer by lowering the density of the polymer into the desired range. Currently, about 0.01 to 2 weight percent hydrogen can be used. However, it is preferred when about 0.05 to 1.5 weight percent is present in said polymerization zone, and it is more preferred when 0.1 to 1 weight percent of hydrogen is present

- 5 -

in said polymerization zone. These weight percents are based on the weight of the diluent in said polymerization zone. It should be noted that hydrogen is often used to modify the molecular weight of a polymer, however, it is believed that this is the first time hydrogen has been used to produce a specific polymer of a specific density range. In other words, this is the first time hydrogen has been used to fine tune the density of a polymer.

The ethylene used should be polymerization grade ethylene. However, 100% ethylene produces better results.

The olefins are alpha-olefins having from 4 to 12 carbon atoms. One of the important features of this invention is that the catalyst produces these olefins during said polymerizing. This eliminates the need for having a source of alpha-olefins for use as comonomers. However, small amounts of alpha-olefins can be added, if desired, as long as the majority of said olefins, by weight, are generated in situ. Currently, 1-butene, 1-hexene, and 1-octene are the most preferred olefins.

The polymer produced needs to have the following properties in order to be a polymer that is good for blow molding applications.

The density needs to be from about 0.94 to 0.96 grams per cubic centimeter. However, it is preferred when the density is from about 0.945 to 0.96 g/cm³ and it is more preferred when the density is from 0.95 to 0.955 g/cm.

Density is determined in accordance with ASTM D1505.

The melt index needs to be from about 0.01 to 1 grams per ten minutes. However, it is preferred when the melt index is from 0.1 to .8 g/10 min. and it is even more preferred when the melt index is from 0.2 to 0.6 g/10 min. Melt Index is determined in accordance with ASTM D 1238.

The high load melt index needs to be from about 5 to 100 grams per ten minutes. However, it is preferred when the high load melt index is from 10 to 80 g/10 min. and it is even more preferred when the melt index is from 20 to 70 g/10 min. High Load Melt Index is determined in accordance with ASTM D 1238.

The heterogeneity index (Mw/Mn) needs to be from about 4 to about 20. However, it is preferred when the heterogeneity index is from 6 to 20 and it is even more preferred when the heterogeneity index is from 8 to 18, and it is most preferred when the Heterogeneity index is from 10 to 16. The heterogeneity index

- 6 -

was determined by gel permeation chromatography.

The Shear Ratio (HLM/MI) needs to be from about 50 to about 200. However, it is preferred when the shear ratio is from about 65 to about 120 and it is even more preferred when the shear ratio is from 70 to 100.

5 The Bottle ESCR of an inventive resin should be about 33 percent higher than a comparison resin. However, it is more preferred when the Bottle ESCR of an inventive resin is 50 percent higher, and it is most preferred if the Bottle ESCR is 100 percent higher. For the purposes of this application the comparison resin is a resin made with the same catalyst as an inventive resin except
10 that the catalyst that makes the control resin has not been reduced. Additionally, these resins are produced under substantially, if not identical, polymerization conditions.

 Polymerization can be carried out in any manner known in the art such as gas phase, solution or slurry polymerization conditions. A stirred reactor
15 can be utilized for a batch process, or the reaction can be carried out continuously in a loop reactor.

 A preferred polymerization technique is that which is referred to as a particle form, or slurry process, wherein the temperature is kept below the temperature at which polymer swells badly. Such polymerization techniques are
20 well known in the art and are disclosed, for instance, in Norwood, U.S. Pat. No. 3,248,179, the disclosure of which is hereby incorporated by reference.

 Two preferred polymerization methods for the slurry process are those employing a loop reactor of the type disclosed in Norwood and those utilizing a plurality of stirred reactors either in series, parallel or combinations thereof
25 wherein the reaction conditions are different in the different reactors.

 The following examples are provided to further inform a person of ordinary skill in the art.

EXAMPLES

EXAMPLE ONE

30 The following bench scale reactor runs demonstrate the unexpected density suppression that occurs when hydrogen is used. No cocatalyst was used in any of these runs. In these runs the chromium was supported on a silica support.

- 7 -

The catalyst contained about one weight percent chromium, the support was mainly silica, and essentially free of titania, alumina, and phosphate, the support had a pore volume of 2.3 cm³/g, a surface area of 500 m²/g, and was activated for 3 hours in dry air at 871°C then reduced (if indicated) for one half hour at 350°C with carbon monoxide. About .05 grams of each catalyst was charged, under nitrogen, into a 2.4 liter autoclave reactor. Then exactly one liter of dry isobutane liquid was added as diluent, followed by 100 psi hydrogen pressure (if indicated). Finally ethylene was added to equal 550 psi. This pressure was maintained for about 1 to 1.5 hours (as indicated) as the reactor contents were stirred at 100°C. At the end of the run, the isobutane, ethylene, and hydrogen were flashed off and the dry polymer powder recovered. See Table One.

Table One							
Reduced	H ₂	Productivity	Run Time	Melt Index	HLMI	HLMI/MI	Density
No	No	1800	60	1.5	85	50	0.9654
No	Yes	1454	65	3.2	179	56	0.9678
Yes	No	882	78	0.39	33	85	0.9645
Yes	Yes	1658	79	0.88	56	63	0.9498

It should be noted that only the combination of a certain oxidized and reduced catalyst with hydrogen produced the desired polymer.

EXAMPLE TWO

The following runs were made in a 600 gallon continuous loop reactor. The catalyst was 969MS from Davison Chemical, having a surface area of 300 m²/g and pore volume of 1.6 cm³/g. It contained 1% chromium on silica, and was activated for 10 hours at 760°C, before a two hour reduction at 371°C with 10% carbon monoxide/90% nitrogen mixture. Residence time was set at about 75 minutes and reactor temperature was 101 to 104°C. Reactor conditions are shown in the Table Two.

Table Two				
Description	Invention	Alkyl Compounds		Control
reduction	yes	yes	yes	no
mol % H ₂	0.55	0.55	0.2	0
ppm TEB	0	0.5	0.3	0
Melt Index	0.62	0.63	0.39	0.35
Density	0.952	0.949	0.95	0.952
Die Swell	5.18	5.26	5.27	5.45
Bottle ESCR	210 hrs.	100 hrs.	170 hrs.	130 hrs.
Drop Impact	> 12 ft.	> 12 ft.	11.5 ft.	> 12 ft.

Notice that the first run used hydrogen to suppress the density. It took about 0.55 mole percent hydrogen to accomplish a density reduction down to 0.952. This represents an invention run. In the next run, an attempt was made to use a cocatalyst. Notice, however, that only 0.5 parts per million of triethyl boron could be added, rather than the usual 8 parts per million used earlier in film runs, and that even this minute amount caused an overshoot down to 0.949 (the target was 0.952). In the third run a similar attempt was made with cocatalyst, this time the amount was further diminished down to 0.3 parts per million triethyl boron, but even here the density suppression overshoot to 0.950 (target .952). The next run shows another control run, in which the catalyst was not reduced and no hydrogen was used either however, hexene was added to reduced the density. It is important to note the difficulty of using cocatalyst to lower the density of a polymer. It is difficult, if not impossible, in a commercial environment, to accurately measure and consistently apply the amounts of cocatalysts needed to achieve the desired results.

These resins were then blow molded into one gallon bottles weighing 105 grams. They were then tested for impact strength (water filled bottles were dropped from as high as 12 feet) and environmental stress crack resistance (ESCR). In the Bottle ESCR test, bottles were filled with a strong detergent (Orvus-K) and allowed to age in an oven at 60°C. Each day these Bottles were check for cracks.

- 9 -

The number of hours before cracking is noted. In the drop test, each day these bottles were checked for failure until all had broken. The time for 50% failure is noted. Also noted in the table below is the layflat, or die swell, measured during the molding operation. In general, a low number is preferred.

- 5 Notice in the table that the invention run also provides the best balance of properties for a blow molding resin. Bottle ESCR is noticeably higher, despite its higher density (in general Bottle ESCR is favored by lower density). The impact strength was also quite good for the invention resin. Bottles tolerated a 12 foot drop without breakage. Notice also that the invention runs had lower die
- 10 swell than all the other controls.

EXAMPLE THREE

The following runs were made in a 600 gallon continuous loop reactor. The conditions are shown in the Table Three.

A = Invention Runs: catalyst CO reduced and H₂ used in reactor

- 15 B = Control Runs: catalyst not CO reduced and no H₂ in reactor

C = Control Run: catalyst not CO reduced but H₂ used in reactor

Table Three		A-1	A-2	B-1	B-2	C-1
Catalyst Type:		EP-30	EP-30	EP-30	HA-30	969MS
Pore Volume (cc/g)		1.6	1.6	1.6	1.5	1.6
Surface area (sq m/g)		300	300	300	400	300
Activation Temperature °C		788	788	871	760	760
CO Reduction at 371 °C		Yes	Yes	No	No	No
Ethylene Conc. in reactor (mol%)		7.89	8.96	7.84	7.66	7.62
Reactor Temp. °C		103.8	103.1	95.1	106.3	102.0
H2 Cone in reactor (mol%)		.169	.18	0	0	.26
hexene feed (as wt% of ethylene feed)		0	0	0	.68	1.51
Melt Index (g/10 min)		.25	.20	.67	.54	.26
High Load Melt Index (g/10 min)		30.1	27.0	62.4	41.8	32.7
HLM/MI		120.4	135.0	93.1	77.4	125.8
Density (g/cc)		9520	9503	9673	.9578	.9530
Ash from catalyst residue (%).		.046	0.52	.091	.04	.047

EP-30 catalyst available commercially from Crosfield Co.
 HA-30 and 969MS available commercially from W.R. Grace Co.

- 11 -

Runs A-1 and A-2 are invention runs which show that the density of the resin is suppressed to the desired 0.950-0.952 level when the catalyst is CO-reduced and when H₂ is added to the reactor. This occurs even though no hexene or other comonomer or metal alkyl is fed to the reactor.

5 Run B-1 shows what happens when the catalyst is not CO reduced and when H₂ is not added to the reactor. The density is not suppressed, but instead is very high as expected from a homopolymer. Run B-2 shows that a significant amount of hexene must be fed to the reactor in order to suppress the density to only around 0.958 under these non-invention conditions.

10 Run C-1 shows an intermediate condition in which H₂ is added to the reactor but the catalyst is not CO-reduced. Notice that in order to suppress the density to only 0.953, a large amount of hexene must be fed to the reactor. Thus H₂ alone does not affect density, but only the combination of CO-reduced catalyst and H₂ in the reactor.

15

EXAMPLE FOUR

The following runs were made in a 23 gallon continuous loop reactor. The catalyst was either 969MS from Davison Chemical, having a surface area of 300m²/g and pore volume of 1.6 cm³/g, or 969ID from Davison Chemical, having a surface area of 300 m²/g and a pore volume of 1.2 cm³/g, or EP-30 from
20 Crosfield Chemical, having a surface area of 300 m²/g and pore volume of 1.6 cm³/g. Each contained 1% chromium on silica, and was activated for 10 hours at 760°C, before a two hour reduction at 371°C with 10% carbon monoxide/90% nitrogen mixture. Residence time was set at about 75 minutes. No cocatalyst or hexene was added to the reactor. Other conditions are as shown in Table IV.

- 12 -

Table Four	8	9	10	12	13
Catalyst	1450F EP30 CO 700F	1450F 969MS CO 700F	1450F 969MS CO 700F	1450F EP30 CO 700F	1450F EP30 CO 700F
Ethylene mol%	6.83	7.89	7.39	8.96	9.15
Temperature F	218.4	218.9	220.3	217.5	218.4
H ₂ mol%	1.05	.169	.132	.18	.024
MI	.53	.25	.34	.20	.22
HLMI	41.6	30.1	33.5	27.0	23.2
Density (g/cc)	9561	9520	9521	9508	9512
Ash %	.082	.046	.038	.052	.069

These resins were then also blown into 1 gallon bottles as described in the previous example. The properties of these bottles, and the resins themselves are shown in Table V.

From the properties below, notice that the bottle ESCR of these resins is quite good, particularly the 5202 types, even better than the controls. Notice also that processing, as measured by cycle time and head pressure, was equal or better than the controls. Invention runs also provide better impact. Other properties are generally comparable to the controls, or even superior in some cases. Die swell is generally low for these resins but it is typical for pilot plant resins to have slightly higher die swell than plant finished controls, as we see here. Finishing in the plant imparts a higher degree of LCB. The main point about die swell is that these numbers here are acceptable, and not high like the silica-titania catalysts. These numbers would typically be above 50%. Table 6 shows the breadth of the molecular weight distribution as described by Mw/Mn and by HLMI/Mi.

Table Five: 5502 type Resins:	Control HHM 5502 BN	Invention A	Control HHM 5202 BN	Invention B	Invention C	Invention D	Invention E
MI (g/10 min)	0.36	0.57	0.34	0.33	0.40	0.32	0.26
HLM (g/10 min)	33.5	38.9	30.7	26.3	31.0	23.9	21.4
HLM/MI	93	68.2	90.3	79.7	77.5	74.7	82.3
Density (gm/cc)	0.955	0.956	0.951	0.952	0.953	0.951	0.951
ESCR (A) (hours)	25	16	24	33	28	45	51
ESCR (B) (hours)	14	14	16	27	22	38	57
Cycle Time (sec)	16.15	15.63	15.56	14.88	16.12	14.97	15.18
Head pressure (psi)	5270	5240	5320	5290	5240	5540	5360
Diameter swell (%)	41.3	44.4	41.3	46.9	47.7	48.0	48.0
Bottle ESCR	92	97	172	235	230	>325	>370
Drop impact	8.9	11	11.3	11.5	11.2	11.5	11.5
Izod impact	2.5P	3.1P	2.1P	3.4P	3.0P	3.3P	3.7P

Table 6: Polymer properties	HHM 5502 BN 6261499	A	HHM 5202 BN 8161397	B	C	D	E
MI (g/10 min)	0.36	0.57	0.34	0.33	0.40	0.32	0.26
HLM/MI (g/10 min)	33.5	38.9	30.7	26.3	31.0	23.9	21.4
HLM/MI	93.1	68.2	90.3	79.7	77.5	74.7	82.3
Mw/1000	149	156	158	196	191	209	243
Mn/1000	13.7	13.8	20.2	130.0	12.7	13.8	11.8
Mw/Mn	10.9	11.3	7.8	15.1	15.0	15.2	20.6

CLAIMS

1. A process for producing copolymers of ethylene and at least one other olefin comprising polymerizing ethylene with at least one olefin to produce a polymer, wherein said polymerizing is conducted in a polymerization zone, where said polymerization zone is essentially free of cocatalyst, and
5 wherein said polymerizing is conducted using a catalyst, where said catalyst comprises chromium oxide on a support, and where the amount of said chromium on said support is from about 0.01 to 5 weight percent, and where said support comprises silica, and where said support is
10 essentially free of titania, alumina and, phosphates, and where said support has a surface area from about 200 to about 550 square meters per gram, and where said support has a pore volume from about 0.7 to about 2.5 cubic centimeters per gram, and
15 where said catalyst has been activated at a temperature in the range of about 600°C to about 900°C by using an oxidizing ambient, and where said catalyst after being activated is then reduced at a temperature in the range of about 200°C to about 550°C by using a reducing ambient, and wherein said polymerizing is conducted in the presence of
20 hydrogen, and wherein the majority of said olefin is produced by said catalyst, during said polymerizing.
2. A process according to claim 1, wherein said polymerization zone is a loop reactor.
- 25 3. A process according to claim 2, wherein said amount of chromium on said support is from about 0.1 to about 3 weight percent.
4. A process according to claim 3, wherein said surface area is from about 225 to about 425 m²/g.
5. A process according to claim 4, wherein said pore volume is
30 from about 0.8 to about 1.8 cm³/g.
6. A process according to claim 5, wherein said catalyst has been activated at a temperature in the range of about 625°C to about 850°C.

THIS SHEET HAS BEEN
REPLACED

This Sheet Has Been Replaced





7. A process according to claim 6, wherein said catalyst has been reduced at a temperature in the range of about 225°C to about 525°C.
8. A process according to claim 7, wherein the amount of hydrogen present in said polymerization zone is from about 0.01 to about 2 weight percent.
- 5 9. A process according to claim 8, wherein said amount of chromium on said support is from 0.5 to 2 weight percent.
10. A process according to claim 9, wherein said surface area is from 250 to 400 m²/g.
11. A process according to claim 10, wherein said pore volume is from 1 to 10 1.7 cm³/g.
12. A process according to claim 11, wherein said catalyst has been activated at a temperature in the range of 645°C to 820°C.
13. A process according to claim 12, wherein said catalyst has been reduced at a temperature in the range of 250°C to 500°C.
- 15 14. A process according to claim 13, wherein the amount of hydrogen present in said polymerization zone is from about 0.05 to about 1.5 weight percent.
15. A process according to claim 14, wherein the amount of hydrogen present in said polymerization zone is from 0.1 to 1 weight percent.
16. A process according to claim 15, wherein the polymerization 20 temperature is from about 96°C to about 110°C.
17. A process according to claim 16, wherein the polymerization temperature is from 98°C to 108°C.
18. A process according to claim 17, wherein said polymerization zone has a diluent that comprises, in major part, isobutane.
- 25 19. A process according to claim 18, wherein said polymer has a density from 0.95 to 0.955, a melt index from 0.2 to 0.6 g/10 min., a high load melt index from 20 to 70 g/10 min., and a heterogeneity index from 10 to 16.
20. A polymer produced by the process according to claim 19.
21. A polymer comprising the following properties a density from 0.95 to 30 0.955, a melt index from 0.2 to 0.6 g/10 min., a high load melt index from 20 to 70 g/10 min., and a heterogeneity index from 10 to 16, a shear ratio from 65 to 100, and a Bottle ESCR 100 percent higher than a comparison resin.

THIS SHEET HAS BEEN
REPLACED

This Sheet Has Been Replaced





CLAIMS

1. A process for producing copolymers of ethylene and at least one other olefin comprising polymerizing ethylene with at least one olefin to produce a polymer,

wherein said polymerizing is conducted in a polymerization zone, where said polymerization zone is essentially free of cocatalyst, and wherein said polymerizing is conducted using a catalyst,

where said catalyst comprises chromium oxide on a support, and

where the amount of said chromium on said support is from about 0.01 to 5 weight percent, and where said support comprises silica, and where said support is essentially free of titania, alumina and, phosphates, and

where said support has a surface area from about 200 to about 550 square meters per gram, and

where said support has a pore volume from about 0.7 to about 2.5 cubic centimeters per gram, and

where said catalyst has been activated at a temperature in the range of about 600°C to about 900°C by using a oxidizing ambient, and

where said catalyst after being activated is then reduced at a temperature in the range of about 200°C to about 550°C by using a reducing ambient, and

wherein said polymerizing is conducted in the presence of hydrogen, and


wherein the majority of said olefin is produced by said catalyst, during said polymerizing.

2. A process according to claim 1, wherein said polymerization zone is a loop reactor.

3. A process according to any preceding claim, wherein said amount of chromium on said support is from about 0.1 to about 3 weight percent.

4. A process according to any preceding claim, wherein said surface area is from about 225 to about 425 m²/g.

CASE: 33570





5. A process according to any preceding claim, wherein said pore volume is from about 0.8 to about 1.8 cm³/g.
6. A process according to any preceding claim, wherein said catalyst has been activated at a temperature in the range of about 625°C to about 850°C.
7. A process according to any preceding claim, wherein said catalyst has been reduced at a temperature in the range of about 225°C to about 525°C.
8. A process according to any preceding claim, wherein the amount of hydrogen present in said polymerization zone is from about 0.01 to about 2 weight percent.
9. A process according to claim 8, wherein said amount of chromium on said support is from 0.5 to 2 weight percent.
10. A process according to claim 9, wherein said surface area is from 250 to 400 m²/g.
11. A process according to claim 10, wherein said pore volume is from 1 to 1.7 cm³/g.
12. A process according to claim 11, wherein said catalyst has been activated at a temperature in the range of 645°C to 820°C.
13. A process according to claim 12, wherein said catalyst has been reduced at a temperature in the range of 250°C to 500°C.
14. A process according to claim 13, wherein the amount of hydrogen present in said polymerization zone is from about 0.05 to about 1.5 weight percent.
15. A process according to claim 14, wherein the amount of hydrogen present in said polymerization zone is from 0.1 to 1 weight percent.
16. A process according to any preceding claim, wherein the polymerization temperature is from about 96°C to about 110°C.
17. A process according to claim 16, wherein the polymerization temperature is from 98°C to 108°C.
18. A process according to any preceding claim, wherein said polymerization zone has a diluent that comprises, in major part, isobutane.
19. A process according to any preceding claim, wherein said polymer has a density from 0.95 to 0.955, a melt index from 0.2 to 0.6 g/10 min., a high load melt index from 20 to 70 g/10 min., and a heterogeneity index from 10 to 16.

REPLACEMENT SHEET

14 APR 2000



Substitute sheet - 10 April 2000

- 17 -

20. A polymer produced by the process according to claim 19.
21. A polymer comprising the following properties a density from 0.95 to 0.955, a melt index from 0.2 to 0.6 g/10 min., a high load melt index from 20 to 70 g/10 min., and a heterogeneity index from 10 to 16, a shear ratio from 65 to 100, and a Bottle ESCR 100 percent higher than a comparison resin.

