

Description

Title of Invention: ENTRY SHEET FOR DRILLING AND METHOD
FOR DRILLING PROCESSING USING SAME

Technical Field

[0001]

The present invention relates to an entry sheet for drilling and a method for drilling processing using the same.

Background Art

[0002]

As a method for drilling processing of a laminated board or a multi-layer board used in a printed wiring board material, a method has been generally adopted including piling one or more laminated boards or multi-layer boards, arranging, as an entry board, an aluminum foil alone or a sheet obtained by forming a resin composition layer on a surface of the aluminum foil (hereinafter, the "sheet" is referred to as "entry sheet for drilling") on the top of the laminated board or multi-layer board, and conducting hole boring processing. Although generally a "copper clad laminate" is often used as the laminated board, the laminated board may be a "laminated board that does not have copper foil on an outer layer". In the present invention, the laminated

board refers to the "copper clad laminate" and/or the "laminated board that does not have copper foil on an outer layer" unless otherwise stated.

[0003]

In recent years, as the improvements in reliability are demanded for printed wiring boards, and the high densification of the printed wiring boards progresses, high-quality drilling processing including the improvements in hole position accuracy and the reduction in roughness of hole walls has been demanded for the drilling processing of a laminated board or a multi-layer board.

[0004]

To meet above-described demands such as the improvements in hole position accuracy and the reduction in roughness of hole walls, a method for hole boring processing using a sheet containing a water-soluble resin such as a polyethylene glycol is proposed in Patent Literature 1. Moreover, a lubricant sheet for hole boring obtained by forming a water-soluble resin layer on a metallic foil is proposed in Patent Literature 2. Further, an entry sheet for hole boring obtained by forming a water-soluble resin layer on aluminum foil provided with a thin film of a thermosetting resin formed thereon is proposed in Patent Literature 3. Furthermore, a lubricant sheet for hole boring in which a non-halogen

colorant is blended in a lubricating resin composition is proposed in Patent Literature 4.

[0005]

As one example of the entry sheet for drilling, an entry sheet is proposed comprising a metallic foil and a layer of a resin composition, the layer formed on at least one surface of the metallic foil. However, the adhesion strength between the metallic foil and the layer of the resin composition is weak, and therefore the layer of the resin composition is peeled during drilling processing in the configuration of the entry sheet for drilling in which the metallic foil and the layer of the resin composition are in direct contact with each other, and the drill steps on the peeled layer of the resin composition, resulting in the deterioration of the hole position accuracy and the increase in the frequency of breakage of the drill in many cases. Moreover, the entry sheet for drilling is usually used in hole boring processing in such a way that the entry sheet is arranged on both surfaces of a plurality of laminated boards or multi-layer boards to make a set with a tape for fixation; however, the tape for fixation may be peeled together with the layer of the resin composition and the position of the entry sheet may be shifted. Therefore, the entry sheet for drilling practically used includes an adhesion layer (adhesion film) containing a urethane-based compound, a vinyl acetate-based compound, a vinyl

chloride-based compound, a polyester-based compound, a copolymerized product thereof, an epoxy-based compound, a cyanate-based compound, or the like formed between the metallic foil and the layer of the resin composition in order to improve the adhesion strength between the metallic foil and the layer of the resin composition (see, for example, Patent Literature 5).

Citation List

Patent Literature

[0006]

Patent Literature 1

Japanese Patent Laid-Open No. H04-92494

Patent Literature 2

Japanese Patent Laid-Open No. H05-169400

Patent Literature 3

Japanese Patent Laid-Open No. 2003-136485

Patent Literature 4

Japanese Patent Laid-Open No. 2004-230470

Patent Literature 5

Japanese Patent Laid-Open No. 2011-183548

Summary of Invention

Technical Problem

[0007]

On the other hand, however, when the adhesion layer is provided between the metallic foil and the layer of

the resin composition, the lubricating effect of the resin composition is prevented by the adhesion layer, and therefore the hole position accuracy, which is an important property required for an entry sheet for drilling, may be deteriorated. Thus, the development of an entry sheet for drilling having a strong adhesion strength between the metallic foil and the layer of the resin composition and having an excellent hole position accuracy without providing the adhesion layer between the metallic foil and the layer of the resin composition has been earnestly desired.

[0008]

In consideration of the present situation, an object of the present invention is to provide an entry sheet for drilling including a metallic foil and a layer of a resin composition, the layer formed on the metallic foil without interposing an adhesion layer, and which has a strong adhesion strength between the metallic foil and the layer of the resin composition and further has an excellent hole position accuracy during drilling processing; and to provide a method for drilling processing using the entry sheet for drilling.

Solution to Problem

[0009]

The present inventors have conducted various studies for the purpose of solving the problems, and have found

that an entry sheet for drilling in which a surface of the layer of the resin composition, the surface being in contact with the metallic foil, has a dispersion term γ_{SD} and a polar term γ_{SP} of the surface free energy in a particular range, has a strong adhesion strength between the metallic foil and the layer of the resin composition and further has an excellent hole position accuracy during drilling processing, thereby completed the present invention.

[0010]

That is, the present invention is as follows.

[1]

An entry sheet for drilling comprising:

a metallic foil; and

a layer of a resin composition, the layer formed on the metallic foil without interposing an adhesion layer, wherein

a surface of the layer of the resin composition, the surface being in contact with the metallic foil, has a dispersion term γ_{SD} of a surface free energy in a range from 27.0 to 37.0 mJ/m² and a polar term γ_{SP} of the surface free energy in a range from 0 to 5.0 mJ/m².

[2]

The entry sheet for drilling according to [1], wherein the resin composition comprises:

a water-insoluble resin (A); and

a water-soluble resin (B).

[3]

The entry sheet for drilling according to [2], wherein the water-insoluble resin (A) has the dispersion term γ_{SD} of the surface free energy in a range from 32.0 to 38.1 mJ/m² and the polar term γ_{SP} of the surface free energy in a range from 0 to 6.0 mJ/m².

[4]

The entry sheet for drilling according to [2] or [3], wherein the water-insoluble resin (A) is one or more selected from the group consisting of polyurethane resins, polyester resins, acrylic-based resins, and polyolefin-based resins.

[5]

The entry sheet for drilling according to any one of [2] to [4], wherein the water-soluble resin (B) is one or more selected from the group consisting of polyethylene oxide; polypropylene oxide; cellulose derivatives; polytetramethylene glycol; polyethylene glycol; polypropylene glycol; monoether compounds of polyoxyethylene; polyoxyethylene monostearate; polyoxyethylene sorbitan monostearate; polyglycerin monostearate compounds; and a polyoxyethylene-propylene copolymer.

[6]

The entry sheet for drilling according to [5], wherein the water-soluble resin (B) comprises:

a high-molecular-weight water-soluble resin (b1) having a weight average molecular weight of 50,000 or higher and 1,000,000 or lower; and

a low-molecular-weight water-soluble resin (b2) having a weight average molecular weight of 1,000 or higher and 30,000 or lower, and

the high-molecular-weight water-soluble resin (b1) contains at least one selected from the group consisting of polyethylene oxide, polypropylene oxide, and cellulose derivatives, and

the low-molecular-weight water-soluble resin (b2) contains at least one selected from the group consisting of polytetramethylene glycol; polyethylene glycol; polypropylene glycol; monoether compounds of polyoxyethylene; polyoxyethylene monostearate; polyoxyethylene sorbitan monostearate; polyglycerin monostearate compounds; and a polyoxyethylene-propylene copolymer.

[7]

The entry sheet for drilling according to any one of [2] to [6], wherein the resin composition comprises:

20 to 80 parts by mass of the water-insoluble resin (A); and

80 to 20 parts by mass of the water-soluble resin (B) each based on 100 parts by mass of a total amount of the water-insoluble resin (A) and the water-soluble resin (B) .

[8]

The entry sheet for drilling according to any one of [2] to [7], wherein the layer of the resin composition is formed using: an aqueous dispersion of the water-insoluble resin (A); and the water-soluble resin (B).

[9]

The entry sheet for drilling according to any one of [1] to [8], wherein the layer of the resin composition has a thickness of 0.02 to 0.3 mm.

[10]

The entry sheet for drilling according to any one of [1] to [9], wherein the metallic foil has a thickness of 0.05 to 0.5 mm.

[11]

A method for drilling processing comprising a hole formation step of forming a hole in a laminated board or a multi-layer board using the entry sheet for drilling according to any one of [1] to [10].

Advantageous Effects of Invention

[0011]

According to the present invention, an entry sheet for drilling having a strong adhesion strength between the metallic foil and the layer of the resin composition and having an excellent hole position accuracy during drilling processing even when an adhesion layer does not exist between the metallic foil and the layer of the

resin composition, and a method for drilling processing using the entry sheet for drilling can be provided. Moreover, the entry sheet for drilling not having an adhesion layer is economical in terms of both the raw material and the production process of the entry sheet.

Brief Description of Drawing

[0012]

[Figure 1] Figure 1 shows a graph showing the relation among a dispersion term γ_{SD} and a polar term γ_{SP} of surface free energy of a surface of a layer of a resin composition, the surface being in contact with a metallic foil, and adhesion force between the metallic foil and the layer of the resin composition.

Description of Embodiments

[0013]

Hereinafter, an embodiment for carrying out the present invention (hereinafter, referred to as "the present embodiment") will be described in detail; however, the present invention is not limited to the present embodiment, and various modifications can be made within a range not departing from the scope of the present invention.

[0014]

[I: Entry Sheet for Drilling]

An entry sheet for drilling according to the present embodiment comprises a metallic foil and a layer of a resin composition, the layer formed on the metallic foil without interposing an adhesion layer, wherein a surface of the layer of the resin composition, the surface being in contact with the metallic foil, has a dispersion term γ_{SD} of surface free energy in a range from 27.0 to 37.0 mJ/m² and a polar term γ_{SP} of the surface free energy in a range from 0 to 5.0 mJ/m².

[0015]

The entry sheet for drilling according to the present embodiment comprises the metallic foil and the layer of the resin composition, the layer formed on the metallic foil without interposing an adhesion layer. That is, the entry sheet for drilling includes the metallic foil and the layer of the resin composition in direct contact with each other without having an adhesion layer (resin film) for adhering the metallic foil and the layer of the resin composition to each other. This is because the above-described configuration has the adhesion strength that is practically sufficient without interposing an adhesion layer. Since there is no need to form an adhesion layer in the entry sheet for drilling according to the present embodiment, the material cost and a step of forming the adhesion layer are unnecessary, so that the entry sheet for drilling according to the present embodiment is also more excellent in terms of

economy than the conventional entry sheets for drilling. The layer of the resin composition may be formed on the one surface of the metallic foil or on both surfaces of the metallic foil. When the layer of the resin composition is formed on both surfaces of the metallic foil, the compositions of the resin composition for each layer may be the same or different.

[0016]

[II: Layer of Resin Composition]

The layer of the resin composition in the present embodiment is characterized in that the surface being in contact with the metallic foil has a dispersion term γ_{SD} of the surface free energy in a range from 27.0 to 37.0 mJ/m² and a polar term γ_{SP} of the surface free energy in a range from 0 to 5.0 mJ/m². Among others, the dispersion term γ_{SD} in a range from 30.0 to 37.0 mJ/m² and the polar term γ_{SP} in a range from 0 to 5.0 mJ/m² are particularly preferable. When the dispersion term γ_{SD} and the polar term γ_{SP} are in the range, the adhesion strength between the metallic foil and the layer of the resin composition is strong, and the machining property during drilling processing is satisfactory, so that the hole position accuracy during drilling processing is excellent.

[0017]

Hereinafter, the surface free energy will be described. Generally, molecules that exist inside a

resin exists in a stabilized state due to the interaction with surrounding molecules; however, molecules that exist at the surface of the resin form a surface and therefore have less stabilizing action by surrounding molecules. Therefore, the molecule that exists at the surface has larger free energy than the molecule that exists inside. The energy is called the surface free energy.

[0018]

Generally, the surface free energy which the surface of a substance has can be expressed by the dispersion term γ_{SD} and the polar term γ_{SP} . The dispersion term γ_{SD} and polar term γ_{SP} of the surface free energy are worked out in the following manner. It is known that the relation between the dispersion term γ_{SD} and polar term γ_{SP} of the surface free energy satisfies the following expression (1), wherein θ represents a contact angle obtained by dropping 1 to 2 μL of a solvent whose surface tension γ_L , dispersion term of the surface tension γ_{LD} , and polar term of the surface tension γ_{LP} are known, on the surface of the layer of the resin composition, the surface being in contact with the metallic foil, with the surface on the upper side.

$$\gamma_L (1 + \cos \theta) = 2 (\gamma_{SD} \times \gamma_{LD})^{0.5} + 2 (\gamma_{SP} \times \gamma_{LP})^{0.5} \quad (1)$$

[0019]

That is, the contact angle θ between a solvent and the surface of the layer of the resin composition being

in contact with the metallic foil is measured using two types of solvents whose surface tension γ_L , dispersion term of the surface tension γ_{LD} , and polar term of the surface tension γ_{LP} are known, and the measured contact angles are substituted into the expression (1) to solve simultaneous equations, so that the dispersion term γ_{SD} and polar term γ_{SP} of the surface free energy can be obtained for the surface of the layer of the resin composition, the surface being in contact with the metallic foil.

[0020]

Hereinafter, the specific measurement method will be described. The dispersion term γ_{SD} and polar term γ_{SP} of the surface free energy of the surface of the layer of the resin composition, the surface being in contact with the metallic foil, is worked out after making a film made of the layer of the resin composition. As the method for making the film of the resin composition, the film of the resin composition can be obtained by forming the film of the resin composition on the metallic foil and then peeling the layer of the resin composition; for simplicity, the film of the resin composition may be made by a method in which the film of the resin composition is formed on a commercially available peel film or release paper with a release agent, and then only the layer of the resin composition is peeled. This is because there is no difference in the values of the dispersion term γ_{SD}

and polar term γ_{SP} of the surface free energy irrespective of whether the film of the resin composition is made using the metallic foil or using the peel film or release paper with a release agent.

[0021]

On the surface, which was in contact with the metallic foil or the peel film of the film of the resin composition obtained by the method described above, 1 to 2 μL of two types of solvents whose surface tension γ_L , the dispersion term of the surface tension γ_{LD} , and the polar term γ_{LP} are known are dropped. Each droplet is photographed using a digital microscope (for example, VHX-100 manufactured by KEYENCE CORPORATION) from just beside. Subsequently, the contact angle θ formed between the film and the droplet is measured using measurement software attached to the digital microscope, or the like. By solving the simultaneous equations obtained by substituting the contact angle θ , the surface tension γ_L , the dispersion term of the surface tension γ_{LD} , the polar term of the surface tension γ_{LP} obtained for the two types of solvents into the expression (1) described above, the dispersion term γ_{SD} and polar term γ_{SP} for the layer of the resin composition can be obtained.

[0022]

The solvent that can be used for the measurement of the dispersion term γ_{SD} and polar term γ_{SP} of the surface free energy is not particularly limited as long as the

surface tension γ_L , the dispersion term of the surface tension γ_{LD} , and the polar term of the surface tension γ_{LP} are known; two types of solvents to be used preferably have greatly different dispersion term γ_{LD} and polar term γ_{LP} . Specifically, the solvents can be selected from: hydrocarbon solvents having only the dispersion term γ_{LD} and having a polar term γ_{LP} of 0, such as liquid paraffin, n-hexane, n-heptane, n-octane, n-nonane, n-decane, n-dodecane, n-tetradecane, and n-hexadecane; and solvents having both the dispersion term γ_{LD} and the polar term γ_{LP} , such as methylene iodide, tetrabromoethane, tetrachloroethane, hexachlorobutadiene, polydimethylsiloxane, water, glycerin, formamide, ethylene glycol, and diethylene glycol. Among others, the combination of liquid paraffin and glycerin is particularly preferable.

[0023]

The resin component that constitutes the layer of the resin composition is not particularly limited, and examples thereof include water-insoluble resins, water-soluble resins, or mixtures thereof. Among them, it is preferable to use a water-insoluble resin (A) and a water-soluble resin (B) together. When the water-insoluble resin (A) and the water-soluble resin (B) are used together, there is a tendency that the adhesion strength between the metallic foil and the layer of the resin composition is further improved and the hole

position accuracy during drilling processing is excellent. It is to be noted that the "water-solubility" in the present embodiment refers to a characteristic that a resin, when mixed with water, dissolves in the water, and that the "water-insolubility" refers to a characteristic that a resin, when mixed with water, does not dissolve in the water.

[0024]

The method for forming the layer of the resin composition will be described in detail below, but the layer of the resin composition is particularly preferably a layer formed using an aqueous dispersion of the water-insoluble resin (A) and the water-soluble resin (B). When the water-insoluble resin (A) is used as the aqueous dispersion, there is a tendency that the compatibility between the water-insoluble resin (A) and the water-soluble resin (B) is further improved and the adhesion strength between the metallic foil and the layer of the resin composition is further improved.

[0025]

[III-1: Water-Insoluble Resin (A)]

The water-insoluble resin (A) that can be used in the present embodiment is not particularly limited as long as the water-insoluble resin (A) is a resin having water-insolubility; the water-insoluble resin (A) has preferably a dispersion term γ_{SD} of the surface free energy in a range from 32.0 to 38.1 mJ/m² and a polar

term γ_{SP} of the surface free energy in a range from 0 to 6.0 mJ/m², particularly preferably a dispersion term γ_{SD} of the surface free energy in a range from 33.0 to 37.0 mJ/m² and a polar term γ_{SP} of the surface free energy in a range from 0 to 5.0 mJ/m². When the dispersion term γ_{SD} and the polar term γ_{SP} of the surface free energy of the water-insoluble resin (A) are in the range, the metallic foil and the layer of the resin composition are strongly adhered to each other and the layer of the resin composition does not peel during drilling processing, so that the hole position accuracy is excellent. It is to be noted that the surface free energy of the water-insoluble resin (A) can also be measured in the same manner as the surface free energy of the layer of the resin composition.

[0026]

It is preferable that the content of the water-insoluble resin (A) in the resin composition be 20 to 80 parts by mass, more preferably 30 to 70 parts by mass, and still more preferably 30 to 60 parts by mass based on 100 parts by mass of the total amount of the water-insoluble resin (A) and the water-soluble resin (B). When the content of the water-insoluble resin (A) is 20 parts by mass or more, there is a tendency that the adhesion strength between the metallic foil and the layer of the resin composition is further improved and the peeling of the layer of the resin composition is harder

to occur during drilling processing. On the other hand, when the content of the water-insoluble resin (A) is 80 parts by mass or less, there is a tendency that the hole position accuracy during drilling processing is further excellent.

[0027]

The water-insoluble resin (A) is not particularly limited, and examples thereof include polyurethane resins, polyester resins, acrylic-based resins, polyolefin-based resins, and polycarbonate resins. Among them, one or more selected from the group consisting of polyurethane resins, polyester resins, acrylic-based resins, and polyolefin-based resins are preferable. When the water-insoluble resin (A) is used, there is a tendency that the surface of the layer of the resin composition, the surface being in contact with the metallic foil described above, easily has a dispersion term γ_{SD} of the surface free energy in a range from 27.0 to 37.0 mJ/m² and a polar term γ_{SP} of the surface free energy in a range from 0 to 5.0 mJ/m² and the adhesion strength between the metallic foil and the layer of the resin composition is further improved. These resins may be used singly or in combinations of two or more.

[0028]

[III-2: Polyurethane Resin]

Examples of the polyurethane resin that can be used as the water-insoluble resin (A) in the present

embodiment include resins obtained by reacting a polyisocyanate compound, a polyol compound, and, if necessary, with another compound. Examples of the reaction for synthesizing the polyurethane resin include an acetone method, a prepolymer mixing method, a ketimine method, and a hot melt dispersion method.

[0029]

The polyisocyanate compound is not particularly limited, and examples thereof include organic polyisocyanate compounds that are used for producing a usual polyurethane resin and have two or more isocyanate groups in the molecule. Specific examples thereof include: aliphatic diisocyanates such as 1,4-tetramethylene diisocyanate, 1,6-hexamethylene diisocyanate (HDI), 3-isocyanatemethyl-3,5,5-trimethylcyclohexyl isocyanate, methylcyclohexyl-2,4-diisocyanate, methylcyclohexyl-2,6-diisocyanate, xylylene diisocyanate (XDI), tetramethylxylylene diisocyanate, and lysine diisocyanate; aromatic diisocyanates such as 1,5'-naphthene diisocyanate, tolidine diisocyanate, diphenylmethanemethane diisocyanate, tetraalkyldiphenylmethane diisocyanates, 4,4'-dibenzyl diisocyanate, and 1,3-phenylene diisocyanate; and triisocyanates such as lysine ester triisocyanate, triphenylmethane triisocyanate, 1,6,11-undecane triisocyanate, 1,8-isocyanate-4,4-isocyanate methyl octane, 1,3,6-hexamethylene triisocyanate, bicyclo

heptane triisocyanate, adducts of trimethylolpropane and toluylene diisocyanate, and adducts of trimethylolpropane and 1,6-hexamethylene diisocyanate. These compounds may be used singly or in combinations of two or more.

[0030]

The polyol compound is not particularly limited, and examples thereof include polyol compounds that are used for producing a usual polyurethane and have two or more hydroxy groups in the molecule. Specific examples of the polyol compound include: polyhydric alcohols such as ethylene glycol, diethylene glycol, propylene glycol, 1,4-butanediol, 1,6-hexanediol, neopentyl glycol, trimethylolpropane, and glycerin; polyether polyol compounds such as polyethylene glycol, polypropylene glycol, and polytetramethylene ether glycol; polyester polyol compounds obtained from a dicarboxylic acid such as adipic acid, sebacic acid, itaconic acid, maleic anhydride, terephthalic acid, isophthalic acid, fumaric acid, succinic acid, oxalic acid, malonic acid, glutaric acid, pimelic acid, suberic acid, and azelaic acid and a polyhydric alcohol such as ethylene glycol, diethylene glycol, propylene glycol, 1,4-butanediol, 1,6-hexanediol, neopentyl glycol, 1,2-propanediol, 1,3-propanediol, 1,9-nonanediol, 3-methyl-1,5-pentanediol, 1,3-propanediol, tripropylene glycol, trimethylolpropane, and glycerin; polylactone-based polyester polyol compounds such as polycaprolactone polyols and poly β -methyl- δ -

valerolactone; and polybutadiene polyols or hydrogenated products thereof, polycarbonate polyols, polythioether polyols, and polyacrylate polyols. These compounds may be used singly or in combinations of two or more.

[0031]

As described above, it is preferable that the polyurethane resin that is used as the water-insoluble resin (A) be used in a state of the aqueous dispersion to form the layer of the resin composition according to the present embodiment. The solid content of the resin contained in the aqueous dispersion of the polyurethane resin is not particularly limited but is preferably 20 to 50 % by mass from the viewpoint of the stability of the aqueous dispersion. The method for producing the aqueous dispersion of the polyurethane resin is not particularly limited, and the aqueous dispersion of the polyurethane resin can be produced by a publicly known method. Among others, it is preferable that the polyurethane resin synthesized from the above-described compounds and the like have a hydrophilic group in the molecule from the viewpoint of the improvement in dispersibility of the polyurethane resin component in water. As the hydrophilic group, anionic groups such as a sulfonyl group and a carboxyl group are preferable, and the carboxyl group is particularly preferable.

[0032]

When the hydrophilic group is the anionic group, it is preferable that the anionic group be neutralized with a neutralizing agent. The neutralizing agent is not particularly limited, and examples thereof include: tertiary amine compounds such as triethylamine and triethanolamine; inorganic alkaline compounds such as sodium hydroxide; and ammonia.

[0033]

If necessary, a compound to be a chain extender may be used in producing the aqueous dispersion of the polyurethane resin. The chain extender is not particularly limited, and examples thereof include: diamines such as ethylenediamine, 1,4-butanediamine, and 1,6-hexanediamine; tertiary amino alcohols such as triethanolamine; and monoalcohols such as methanol, ethanol, and butanol.

[0034]

The solvent in producing the aqueous dispersion of the polyurethane resin is usually an aqueous solvent, and, further, an organic solvent that does not have an isocyanate group can be used together. For example, ethyl acetate, acetone, methyl ethyl ketone, isopropyl alcohol, methanol, ethanol, and the like can be used. The amount of the organic solvents to be added is generally 1 to 100 parts by mass based on 100 parts by mass of the water content in the aqueous dispersion of the polyurethane resin.

[0035]

As the aqueous dispersion of the polyurethane resin, a commercially available product may be used as it is. Examples of the commercially available aqueous dispersion of the polyurethane resin include SUPERFLEX 820 (manufactured by DKS Co. Ltd.), SUPERFLEX 860 (manufactured by DKS Co. Ltd.), SUPERFLEX 740 (manufactured by DKS Co. Ltd.), UPRENE UXA 307 (manufactured by Sanyo Chemical Industries, Ltd.), HYDRAN AP 201 (manufactured by DIC Corporation), HYDRAN HW 140SF (manufactured by DIC Corporation), and HYDRAN WLS 201 (manufactured by DIC Corporation). When the aqueous dispersions of the water-insoluble resin (A) are used, there is a tendency that the adhesion strength between the metallic foil and the layer of the resin composition is further improved.

[0036]

[III-3: Polyester Resin]

Examples of the polyester resin that can be used as the water-insoluble resin (A) in the present embodiment include polyester resins obtained by subjecting a raw material containing a polyol compound having two or more hydroxyl groups and a polybasic carboxylic acid having two or more carboxyl groups to condensation polymerization.

[0037]

The polyol compound is not particularly limited as long as the polyol compound has two or more hydroxyl groups, and examples thereof include ethylene glycol, diethylene glycol, 1,3-propane diol, 1,2-propanediol, triethylene glycol, 2-methyl-1,3-propanediol, 2,2-dimethyl-1,3-propanediol, 2-butyl-2-ethyl-1,3-propanediol, 1,4-butanediol, 2-methyl-1,4-butanediol, 2-methyl-3-methyl-1,4-butanediol, 3-methyl-1,5-pentanediol, 1,5-pentanediol, 3-methyl-1,5-pentanediol, and 1,6-hexanediol. Moreover, examples of the polyol compound include ethylene oxide adducts of bisphenol A and propylene oxide adducts of bisphenol A as a glycol having a divalent aromatic structure, sorbitol, hexane-1,2,3,6-tetrol, 1,4-sorbitan, pentaerythritol, dipentaerythritol, tripentaerythritol, 1,2,4-butanetriol, 1,2,5-pentanetriol, glycerol, 2-methylpropanetriol, 2-methyl-1,2,4-butanetriol, trimethylolethane, trimethylolpropane, and 1,3,5-trihydroxymethylbenzene. These compounds may be used singly or in combinations of two or more.

[0038]

The polybasic carboxylic acid is not particularly limited as long as the polybasic carboxylic acid has two or more carboxyl groups, and examples thereof include terephthalic acid, isophthalic acid, orthophthalic acid, 2,6-naphthalenedicarboxylic acid, 1,2-cyclohexanedicarboxylic acid, 1,3-cyclohexanedicarboxylic acid, 1,4-cyclohexanedicarboxylic acid, 1,2,4-

benzenetricarboxylic acid, 2,5,7-naphthalenetetracarboxylic acid, 1,2,4-naphthalenetetracarboxylic acid, 1,2,4-butanetricarboxylic acid, 1,2,5-hexanetricarboxylic acid, 1,3-dicarboxyl-2-methyl-2-methylenecarboxyl propane, 1,2,4-cyclohexanetricarboxylic acid, tetra(methylenecarboxyl)methane, 1,2,7,8-octanetetracarboxylic acid, and pyromellitic acid. These compounds may be used singly or in combinations of two or more.

[0039]

As described above, it is preferable that the polyester resin that is used as the water-insoluble resin (A) be used in a state of the aqueous dispersion to form the layer of the resin composition according to the present embodiment. The solid content of the resin contained in the aqueous dispersion of the polyester resin is not particularly limited but is preferably 20 to 50% by mass from the viewpoint of the stability of the aqueous dispersion. The method for producing the aqueous dispersion of the polyester resin is not particularly limited, and the aqueous dispersion of the polyester resin can be produced by a publicly known method. It is to be noted that the aqueous dispersion of the polyester resin herein means a dispersion in which the polyester resin having hydrophobic moieties and hydrophilic moieties in the molecule thereof is dispersed stably in

water in such a form that the hydrophilic moieties surround the hydrophobic moieties.

[0040]

The polyester resin may be a resin in which a component having a hydrophilic group such as a carboxyl group or a sulfonic acid group is further copolymerized for the purpose of improving the dispersibility of the polyester resin to water. As the component having a hydrophilic group, for example, trimellitic acid, pyromellitic acid, and trimesic acid can be used, and the polyester resin obtained by neutralizing the obtained copolymer with an amine compound or an inorganic alkaline compounds such as ammonia or sodium hydroxide can be used.

[0041]

As the aqueous dispersion of the polyester resin, a commercially available product may be used as it is. Examples of the commercially available aqueous dispersion of the polyester resin include Vylonal MD 1480 (manufactured by Toyobo Co., Ltd.) and Vylonal MD 1985 (manufactured by Toyobo Co., Ltd.). These aqueous dispersions are particularly preferable as the aqueous dispersion of the water-insoluble resin (A) that can be used in forming the layer of the resin composition according to the present embodiment. This is because the adhesion strength between the metallic foil and the layer of the resin composition can be made particularly strong.

[0042]

[III-4: Acrylic-Based Resin]

The acrylic-based resin that can be used as the water-insoluble resin (A) in the present embodiment is not particularly limited as long as the acrylic-based resin is a copolymer using an unsaturated carboxylic acid compound as a main constituent. The unsaturated carboxylic acid is not particularly limited, and examples thereof include: α,β -unsaturated carboxylates (also referred to as ethylenically unsaturated carboxylates) such as methyl (meth)acrylate, ethyl (meth)acrylate, n-propyl (meth)acrylate, isopropyl (meth)acrylate, n-butyl (meth)acrylate, isobutyl (meth)acrylate, t-butyl (meth)acrylate, n-octyl (meth)acrylate, isononyl (meth)acrylate, cyclohexyl (meth)acrylate, methylcyclohexyl (meth)acrylate, t-butylcyclohexyl (meth)acrylate, cyclododecyl (meth)acrylate, isobornyl (meth)acrylate, 2-hydroxyethyl (meth)acrylate, 3-hydroxypropyl (meth)acrylate, 4-hydroxybutyl (meth)acrylate, glycidyl (meth)acrylate, polyethylene glycol (meth)acrylate, polypropylene glycol (meth)acrylate, and polyethylene-polypropylene glycol mono(meth)acrylate; monoalkyl esters of an unsaturated dicarboxylic acid, such as monoethyl itaconate and monobutyl fumarate; α,β -unsaturated carboxylic acids (also referred to as ethylenically unsaturated carboxylic acids) and unsaturated dicarboxylic acids such as (meth)acrylic acid, itaconic acid, maleic acid, and

fumaric acid; α,β -unsaturated carboxylic acid amides (also referred to as ethylenically unsaturated carboxylic acid amides) and N-substituted compounds thereof such as acrylamide, N-methylolacrylamide, N-methoxy methyl acrylamide, N-methoxy butyl acrylamide, and diacetone acrylamide; unsaturated alcohols such as allyl alcohol; α,β -unsaturated nitriles (also referred to as ethylenically unsaturated nitriles) such as (meth)acrylonitrile; and vinyl acetate. These compounds may be used singly or in combinations of two or more.

[0043]

As described above, it is preferable that the acrylic-based resin that is used as the water-insoluble resin (A) be used in a state of the aqueous dispersion to form the layer of the resin composition according to the present embodiment. The solid content of the resin contained in the aqueous dispersion of the acrylic-based resin is not particularly limited but is preferably 20 to 50% by mass from the viewpoint of the stability of the aqueous dispersion. The method for producing the aqueous dispersion of the acrylic-based resin is not particularly limited, and the aqueous dispersion of the acrylic-based resin can be produced by a publicly known method. Specific examples include: a method in which acrylic compounds are co-polymerized in an organic solvent such as methyl ethyl ketone, acetone, or ethyl acetate, the organic solvent is then evaporated, and thereafter

carboxyl groups are neutralized with an amine compound or an inorganic alkaline compound such as ammonia or sodium hydroxide in an aqueous solvent to disperse the copolymerized product; a method in which an acrylic compound and an emulsifying agent having an anionic hydrophilic group such as a carboxyl group or a sulfonic acid group, or an acrylic compound and a compound having a nonionic hydrophilic group, such as a monoether compound or a monoester compound including a polyethylene glycol or a polypropylene glycol, are mixed in an aqueous solvent, and the resultant mixture is subjected to emulsion polymerization; and, further, a method in which a component having hydrophilicity such as a carboxyl group or a sulfonic acid group and an acrylic compound are co-polymerized for self-emulsification.

[0044]

As the aqueous dispersion of the acrylic-based resin, a commercially available product may be used as it is. Examples of the commercially available aqueous dispersion of the acrylic-based resin include VONCOAT AK 3090 (manufactured by DIC Corporation), VONCOAT AN 678E (manufactured by DIC Corporation), and VONCOAT MAT 200E (manufactured by DIC Corporation). These aqueous dispersions are particularly preferable as the aqueous dispersion of the water-insoluble resin (A) that can be used in forming the layer of the resin composition according to the present embodiment. This is because the

adhesion strength between the metallic foil and the layer of the resin composition can be made particularly strong.
[0045]

[III-5: Polyolefin-Based Resin]

Examples of the polyolefin-based resin that can be used as the water-insoluble resin (A) in the present embodiment include resins using an olefin such as ethylene or propylene as a main constituent. Examples of the resins include copolymers of an olefin and an unsaturated carboxylic acid (hereinafter, also referred to as "olefin-unsaturated carboxylic acid copolymers"). The olefin is not particularly limited, but ethylene, propylene, and butylene are preferable, and ethylene is particularly preferable among them. The unsaturated carboxylic acid is not particularly limited, but (meth)acrylic acid (namely, acrylic acid or methacrylic acid), maleic acid, itaconic acid, and fumaric acid are preferable, and (meth)acrylic acid is more preferable among others. As the olefin-unsaturated carboxylic acid copolymer, copolymers of ethylene and (meth)acrylic acid and copolymers of propylene and (meth)acrylic acid are particularly preferable.

[0046]

As describe above, it is preferable that the polyolefin-based resin that is used as the water-insoluble resin (A) be used in a state of the aqueous dispersion to form the layer of the resin composition

according to the present embodiment. The solid content of the resin contained in the aqueous dispersion of the polyolefin-based resin is not particularly limited but is preferably 20 to 50% by mass from the viewpoint of the stability of the aqueous dispersion. The method for producing the aqueous dispersion of the polyolefin-based resin is not particularly limited, and the aqueous dispersion of the polyolefin-based resin can be produced by a publicly known method. Examples of the method include a method in which the above-described olefin-unsaturated carboxylic acid copolymer, an aqueous solvent, and, if necessary, an additional component such as a base or an emulsifying agent are stirred using a solid-liquid stirring apparatus or the like.

[0047]

Examples of the base that is used for producing the aqueous dispersion of the polyolefin-based resin include: ammonia; amine compounds such as diethylamine, triethylamine, monoethanolamine, dimethylethanolamine, and diethylethanolamine; and sodium hydroxide.

[0048]

As the aqueous dispersion of the polyolefin-based resin, a commercially available product may be used as it is. Examples of the commercially available aqueous dispersion of the polyolefin-based resin include ZAIKTHENE AC (manufactured by Sumitomo Seika Chemicals Company Limited), ZAIKTHENE NC (manufactured by Sumitomo

Seika Chemicals Company Limited), Hightech S 3148K (manufactured by TOHO Chemical Industry Co., Ltd.), and Hightech S 9242 (manufactured by TOHO Chemical Industry Co., Ltd.). These aqueous dispersions are particularly preferable as the aqueous dispersion of the water-insoluble resin (A) that can be used in forming the layer of the resin composition according to the present embodiment. This is because the adhesion strength between the metallic foil and the layer of the resin composition can be made particularly strong.

[0049]

[IV: Water-Soluble Resin (B)]

The water-soluble resin (B) is not particularly limited as long as the water-soluble resin (B) is a resin having water-solubility; it is preferable to use a high-molecular-weight water-soluble resin (b1) and a low-molecular-weight water-soluble resin (b2) together.

[0050]

It is preferable that the content of the water-soluble resin (B) in the resin composition be 20 to 80 parts by mass, more preferably 30 to 70 parts by mass, and still more preferably 40 to 70 parts by mass based on 100 parts by mass of the total amount of the water-insoluble resin (A) and the water-soluble resin (B). When the content of the water-soluble resin (B) is 20 parts by mass or more, there is a tendency that a further uniform layer of the resin composition can be formed. On

the other hand, when the content of the water-soluble resin (B) is 80 parts by mass or less, there is a tendency that the hole position accuracy is further excellent during drilling processing.

[0051]

The high-molecular-weight water-soluble resin (b1) is not particularly limited and preferably contains one or more selected from the group consisting of polyethylene oxide, polypropylene oxide, and cellulose derivatives. These compounds may be used singly or in combinations of two or more. It is preferable that the high-molecular-weight water-soluble resin (b1) have a weight average molecular weight of 50,000 or higher and 1,000,000 or lower from the viewpoint of improving the film forming property of the layer of the resin composition.

[0052]

The low-molecular-weight water-soluble resin (b2) is not particularly limited and examples thereof include: glycol compounds such as polyethylene glycol, polypropylene glycol, and polytetramethylene glycol; monoether compounds of polyoxyethylene such as polyoxyethylene oleyl ether, polyoxyethylene cetyl ether, polyoxyethylene stearyl ether, polyoxyethylene lauryl ether, polyoxyethylene nonylphenyl ether, and polyoxyethylene octylphenyl ether; and polyoxyethylene monostearate, polyoxyethylene sorbitan monostearate,

polyglycerin monostearate compounds, and a polyoxyethylene-propylene copolymer. Among these, it is preferable that the low-molecular-weight water-soluble resin (b2) contain at least one selected from the group consisting of polytetramethylene glycol, polyethylene glycol, polypropylene glycol, monoether compounds of polyoxyethylene, polyoxyethylene monostearate, polyoxyethylene sorbitan monostearate, polyglycerin monostearate compounds, and a polyoxyethylene-propylene copolymer. These compounds and copolymers may be used singly or in combinations of two or more. It is preferable that the low-molecular-weight water-soluble resin (b2) have a weight average molecular weight of 1,000 or higher and 30,000 or lower from the viewpoint of improving the lubricating property during drilling processing.

[0053]

Among the above-described water-soluble resins, it is preferable to use as the water-soluble resin (B), one or more selected from the group consisting of polyethylene oxide, polypropylene oxide, cellulose derivatives, polytetramethylene glycol, polyethylene glycol, polypropylene glycol, monoether compounds of polyoxyethylene, polyoxyethylene monostearate, polyoxyethylene sorbitan monostearate, polyglycerin monostearate compounds, and a polyoxyethylene-propylene copolymer. When such a water-soluble resin (B) is used,

there is a tendency that the film forming property of the layer of the resin composition and the hole position accuracy are further improved.

[0054]

Moreover, particularly in the case where the water-soluble resin (B) contains the high-molecular-weight water-soluble resin (b1) having a weight average molecular weight of 50,000 or higher and 1,000,000 or lower and the low-molecular-weight water-soluble resin (b2) having a weight average molecular weight of 1,000 or higher and 30,000 or lower, it is preferable that the high-molecular-weight water-soluble resin (b1) contain at least one selected from the group consisting of polyethylene oxide, polypropylene oxide, and cellulose derivatives, and the low-molecular-weight water-soluble resin (b2) contain at least one selected from the group consisting of polytetramethylene glycol, polyethylene glycol, polypropylene glycol, monoether compounds of polyoxyethylene, polyoxyethylene monostearate, polyoxyethylene sorbitan monostearate, polyglycerin monostearate compounds, and a polyoxyethylene-propylene copolymer. When such a water-soluble resin (B) is used, there is a tendency that the film forming property of the layer of the resin composition and the hole position accuracy are further improved.

[0055]

The content of the high-molecular-weight water-soluble resin (b1) is preferably 1 to 15 parts by mass, more preferably 2.5 to 10 parts by mass, and still more preferably 5 to 8 parts by mass based on 100 parts by mass of the total amount of the water-insoluble resin (A) and the water-soluble resin (B). When the content of the high-molecular-weight water-soluble resin (b1) is in the range, there is a tendency that the film forming property of the layer of the resin composition and the hole position accuracy are further improved.

[0056]

The content of the low-molecular-weight water-soluble resin (b2) is preferably 30 to 75 parts by mass, more preferably 40 to 75 parts by mass, and still more preferably 45 to 72 parts by mass based on 100 parts by mass of the total amount of the water-insoluble resin (A) and the water-soluble resin (B). When the content of the low-molecular-weight water-soluble resin (b2) is in the range, there is a tendency that the film forming property of the layer of the resin composition and the hole position accuracy are further improved.

[0057]

[V: Other Components]

If necessary, the layer of the resin composition may contain an additive. The type of additive is not particularly limited, and examples thereof include a surface conditioner, a leveling agent, an antistatic

agent, an emulsifying agent, an antifoaming agent, a wax additive, a coupling agent, a rheology control agent, an antiseptic agent, an antifungal agent, an antioxidant, a light stabilizer, a nucleating agent such as Na formate, a solid lubricant such as graphite, an organic filler, an inorganic filler, a heat stabilizer, and a coloring agent.

[0058]

The thickness of the layer of the resin composition in the present embodiment is appropriately selected according to the diameter of the drill bit that is used in conducting drilling processing, the constitution of the object of hole boring to which processing is conducted (for example, printed wiring board material such as laminated board or multi-layer board), and the like. Among others, it is preferable that the layer of the resin composition have a thickness in a range from 0.02 to 0.3 mm, more preferably in a range from 0.02 to 0.2 mm, and still more preferably in a range from 0.02 to 0.1 mm. When the layer of the resin composition has a thickness of 0.02 mm or more, a further sufficient lubricating effect can be obtained to reduce the load to the drill bit, so that there is a tendency that the breakage of the drill bit can be further suppressed. Moreover, when the resin composition layer has a thickness of 0.3 mm or less, there is a tendency that winding of the resin composition to the drill bit can be suppressed.

[0059]

[VI: Metallic Foil]

The metallic foil that is used for the entry sheet for drilling in the present embodiment is not particularly limited but is preferably a metallic material that has high adhesion with the resin composition layer and can endure the shock by the drill bit. Examples of the kind of metal of the metallic foil include aluminum from the viewpoint of availability, cost, and processability. It is preferable that the material quality of aluminum foil be aluminum having a purity of 95% or more. Examples of such aluminum foil include 5052, 3004, 3003, 1N30, 1N99, 1050, 1070, 1085, and 8021 specified in JIS-H4160. By using aluminum foil having an aluminum purity of 95% or more as the metallic foil, the shock by the drill bit is lessened, the biting property with the tip of the drill bit is improved, and these are coupled with the lubricating effect to the drill bit by the resin composition to enable the hole position accuracy of processed holes to be enhanced further.

[0060]

The metallic foil preferably has a thickness of 0.05 to 0.5 mm, more preferably 0.05 to 0.3 mm, and still more preferably 0.05 to 0.2 mm. When the metallic foil has a thickness of 0.05 mm or more, there is a tendency that the generation of burrs from the object of hole boring (for example, laminated board) during drilling processing

can be suppressed further. Moreover, when the metallic foil has a thickness of 0.5 mm or less, there is a tendency that the discharge of chips generated during drilling processing becomes easier.

[0061]

The thickness of each layer that constitutes the entry sheet for drilling according to the present embodiment is measured in the following manner. Firstly, the entry sheet is cut in the lamination direction of each layer using a cross-section polisher (manufactured by JEOL Ltd., trade name "CROSS-SECTION POLISHER SM-09010") or an ultramicrotome (manufactured by Leica, item number "EM UC7"). Thereafter, the cross section appeared by cutting is observed from a vertical direction relative to the cross section to measure the thicknesses of each constituent layer, such as, for example, the metallic foil and the layer of the resin composition, using a SEM (Scanning Electron Microscope, manufactured by KEYENCE CORPORATION, item number "VE-7800"). The thicknesses at 5 points to 1 view are measured, and the mean is determined to be the thickness of each layer.

[0062]

[VII: Method for Producing Entry Sheet for Drilling]

The method for producing the entry sheet for drilling according to the present embodiment is not particularly limited, and the entry sheet for drilling according to the present embodiment can be produced, for

example, in the following manner. The entry sheet for drilling according to the present embodiment is produced in such a way that the layer of the resin composition is formed on at least one surface of the metallic foil. The method for forming the layer of the resin composition is not particularly limited, and publicly known methods can be used. Examples of the methods include a method in which a solution of the resin composition, which is obtained by dissolving or dispersing the aqueous dispersion of the water-insoluble resin (A); and the water-soluble resin (B) in a solvent, is applied on the metallic foil by a coating method or the like, and then the applied solution is further dried and/or cooled to be solidified.

[0063]

In the case where the layer of the resin composition is formed by applying the solution of the resin composition on the metallic foil by a coating method or the like and then drying the applied solution, it is preferable that the solvent that is used in the solution of the resin composition be a mixed solution containing water and a solvent having a boiling point that is lower than the boiling point of water. The use of the mixed solution containing water and the solvent having a boiling point that is lower than the boiling point of water contributes to the reduction of residual bubbles in the layer of the resin composition. The type of solvent

having a boiling point that is lower than the boiling point of water is not particularly limited, but examples thereof include alcoholic compounds such as ethanol, methanol, and isopropyl alcohol, and a low boiling point solvent such as methyl ethyl ketone and acetone can also be used. As another solvent, a solvent obtained by mixing tetrahydrofuran or acetonitrile, which has a high compatibility with the resin composition, in water or the alcoholic compound can be used.

[0064]

[VIII: Method for Drilling Processing]

The method for drilling processing according to the present embodiment includes a hole formation step of forming a hole in a laminated board or a multi-layer board using the entry sheet for drilling. Moreover, when the drilling processing is conducted with a drill bit having a diameter (drill bit diameter) of 0.30 mmφ or less, the object of the present embodiment can be achieved further efficiently and surely. Particularly, the drilling processing, when used for the drill bits having a small diameter, as small as a diameter of 0.05 mmφ or more and 0.30 mmφ or less, further, as small as a diameter of 0.05 mmφ or more and 0.20 mmφ or less where the hole position accuracy matters, is suitable in that the hole position accuracy and the life of the drills are greatly improved. It is to be noted that the drill bit diameter of 0.05 mmφ is the lower limit of the diameter

for available drill bits, and if a drill bit having a diameter smaller than that becomes available, the above-described range becomes different. Moreover, there is no problem even when the entry sheet for drilling according to the present embodiment is adopted for drilling processing in which a drill bit having a diameter exceeding 0.30 mmφ is used.

[0065]

The entry sheet for drilling according to the present embodiment can be used suitably in conducting drilling processing for, for example, a printed wiring board material, more specifically, a laminated board or a multi-layer board. Specifically, the drilling processing can be conducted from the upper surface (layer side of resin composition) of the entry sheet for drilling by arranging the entry sheet on at least the top surface of a laminated board or a multi-layer board or a plurality of piled laminated boards or piled multi-layer boards (a printed wiring board material) so that the metallic foil side can be in contact with the printed wiring board material.

Examples

[0066]

Hereinafter, the effects of Examples according to the present invention will be described comparing with Comparative Examples that are out of the range of the

present invention. It is to be noted that "polyethylene glycol" is sometimes abbreviated as "PEG", "polyethylene oxide" as "PEO", "aqueous dispersion of polyurethane resin" as "polyurethane resin", "aqueous dispersion of polyester resin" as "polyester resin", "aqueous dispersion of acrylic-based resin" as "acrylic-based resin", and "aqueous dispersion of polyolefin-based resin" as "polyolefin-based resin".

[0067]

Hereinafter, the method for measuring the surface free energy, the method for measuring the adhesion force, and the method for measuring the hole position accuracy will be described.

[0068]

<Measurement of Dispersion Term γ_{SD} and Polar Term γ_{SP} of Surface Free Energy>

The method for measuring the dispersion term γ_{SD} and polar term γ_{SP} of the surface free energy will be described.

[0069]

(Pretreatment)

The resin composition solutions used in Examples and Comparative Examples or the aqueous dispersions of the water-insoluble resins (A) used in Examples and Comparative Examples were each applied on a peel film (PET 38 AL-5 manufactured by Lintec Corporation), and the applied aqueous dispersions were dried under drying

conditions of 120°C for 3 minutes, and then cooled and solidified to obtain the films of the resin compositions (layers of resin compositions). The obtained films were each peeled from the peel film and were stuck to a plate with the surfaces which had been in contact with the peel film on the upper side using a double-sided tape (No. 5000E manufactured by Nitto Denko Corporation) to prepare samples for measurement.

[0070]

(Measurement)

As the two types of solvents whose surface tension γ_L , dispersion term of the surface tension γ_{LD} , and polar term of the surface tension γ_{LP} are known, 2 μL of liquid paraffin and glycerin were each dropped on the samples for measurement. For liquid paraffin, $\gamma_L/\gamma_{LD}/\gamma_{LP} = 38.1/38.1/0$ (all the units are mJ/m^2). On the other hand, for glycerin, $\gamma_L/\gamma_{LD}/\gamma_{LP} = 63.4/37.0/26.4$ (all the units are mJ/m^2).

[0071]

The droplets of the two types of solvents dropped on the samples for measurement were observed and photographed from just beside with the digital microscope (VHX-100 manufactured by KEYENCE Corporation), and the contact angles each formed between the sample for measurement and the droplet was directly measured with the measurement software attached to the digital

microscope to obtain respective contact angles when the two types of solvents were used.

[0072]

The simultaneous equations obtained by substituting the obtained contact angle θ , and the surface tension γ_L , dispersion term of the surface tension γ_{LD} , and polar term of the surface tension γ_{LP} for liquid paraffin and glycerin into the following expression (1) were solved to determine the dispersion term γ_{SD} and γ_{SP} of the surface free energy of each sample for measurement.

$$\gamma_L (1 + \cos \theta) = 2 (\gamma_{SD} \times \gamma_{LD})^{0.5} + 2 (\gamma_{SP} \times \gamma_{LP})^{0.5} \quad (1)$$

It is to be noted that the values of the dispersion term γ_{SD} and polar term γ_{SP} of the surface free energy obtained by measurement according to the present method are the same as the values of the dispersion term γ_{SD} and polar term γ_{SP} of the surface free energy obtained by applying the resin composition solution on the metallic foil.

[0073]

<Method for Measuring Adhesion Force>

The adhesion force was measured in the following manner. Firstly, three samples were each prepared by cutting each entry sheet for drilling made in Examples and Comparative Examples in a width of 3 mm and a length of 100 mm. Subsequently, a double-sided tape was stuck to the whole surface of the layer of the resin

composition on each sample. Thereafter, one edge of the samples, to which the double-sided tape was stuck, was peeled in a length of 10 mm, and a jig for attaching a spring scale was attached to the metallic foil portion in the peeled samples. The spring scale (manufactured by Sanko Seikohjyo Co. Ltd., maximum measurable value of 1000 gf) was attached to the jig, and was pulled at a speed of 1 cm/sec to read the numerical value shown by the spring scale. The measurement was conducted for the three samples, and the mean of the three numerical values was determined as the numerical value of the adhesion force. When the metallic foil and the layer of the resin composition were not peeled, the result was denoted as ">1000".

[0074]

<Measurement of Hole Position Accuracy>

The hole position accuracy was measured in the following manner. Each entry sheet for drilling made in Examples and Comparative Examples was arranged, with the side of the layer of the resin composition on the upper side, on the upper surface of a copper clad laminate obtained by piling 5 copper clad laminates (trade name: HL 832, thickness of copper foil of 12 μm , double-sided board, manufactured by Mitsubishi Gas Chemical Company, Inc.) each having a thickness of 0.2 mm, and an entry board (paper phenolic laminated board, manufactured by RISHO KOGYO CO., LTD.) having a thickness of 1.5 mm was

arranged at the back surface (lower surface) of the lowest board of the piled copper clad laminates. Drilling processing of 6,000 holes in total was conducted under the conditions of the number of rotations: 200,000 rpm, the feeding speed: 2.6m/min, and the number of holes bored: 3,000 holes per one drill bit with 0.2 mm ϕ drill bits (trade name: C-CFU020S manufactured by TungALOY Corporation).

[0075]

The shift of the hole position at the back surface (lower surface) of the lowest board of the piled copper clad laminates from the designated coordinate was measured for the 3,000th hole (first drill bit) and the 6,000th hole (second drill bit) using a hole analyzer (type number: HA-1AM, manufactured by Hitachi Via Mechanics, Ltd.). The mean and the standard deviation (σ) of the obtained shifts were calculated to work out the "mean + 3 σ " for each drill bit. Thereafter, as the hole position accuracy of the whole drilling processing, the mean of the "mean + 3 σ " for each drill bit was worked out for two drill bits used. The expression used for working out the hole position accuracy is as represented by the following expression (2).

$$\text{Hole position accuracy of whole drilling processing } (\mu\text{m}) = \left(\sum_{i=1}^n \text{"mean} + 3\sigma"_{\text{i of drill bit}} \right) \div n \quad (2)$$

In the expression, n represents the number of drills used.

[0076]

The water-insoluble resins (A), the water-soluble resins (B), the additives, the solvents, and the specification of the metallic foil, which were used for producing the entry sheets for drilling of Examples and Comparative Examples, are shown in Table 1. The solid content of the resin in the water-insoluble resin (A) in Table 1 represents the amount (% by mass) of the solid content of the resin in the aqueous dispersion of the water-insoluble resin (A).

[0077]

[Table 1]

	Raw material	Trade name	Sign	Manufacturer	Surface free energy of water-insoluble resin (A)			Solid content of resin in water-insoluble resin (A)
					γSD mJ/m2	γSP mJ/m2		
Water-insoluble resin (A)	Polyurethane resin	SUPERFLEX 740	a	DKS Co. Ltd.	36.6	2.5	% by mass	
	Polyurethane resin	SUPERFLEX 820	b	DKS Co. Ltd.	35.4	1.8		40
	Polyurethane resin	SUPERFLEX 860	c	DKS Co. Ltd.	37.7	3.4		40
	Polyurethane resin	SUPERFLEX 210	d	DKS Co. Ltd.	36.1	4.2		35
	Polyurethane resin	SUPERFLEX 470	e	DKS Co. Ltd.	34.7	5.6		45
	Polyurethane resin	SUPERFLEX 500M	f	DKS Co. Ltd.	31.0	0.1		38
	Polyurethane resin	UPRENE UXA307	g	Sanyo Chemical Industries, Ltd.	36.6	2.8		40
	Polyurethane resin	HYDRAN AP201	h	DIC Corporation	36.7	0.9		23
	Polyurethane resin	HYDRAN HW140SF	j	DIC Corporation	36.5	2.2		25
	Polyurethane resin	HYDRAN WLS201	k	DIC Corporation	37.7	2.0		35
	Polyurethane resin	HYDRAN ADS110	l	DIC Corporation	34.0	6.6		50
	Polyester resin	Vylonal MD1480	m	Toyobo Co., Ltd.	36.6	3.9		25
	Polyester resin	Vylonal MD1985	n	Toyobo Co., Ltd.	36.3	0.8		27
	Polyester resin	Vylonal MD1500	o	Toyobo Co., Ltd.	37.1	4.5		30
	Polyester resin	Vylonal MD2000	p	Toyobo Co., Ltd.	36.9	5.5		40
	Water-soluble resin (B)	Acrylic resin	VONCOAT AK3090	q	DIC Corporation	35.2	0.1	
Acrylic resin		VONCOAT AN678E	r	DIC Corporation	34.4	3.9		45
Acrylic resin		VONCOAT MAT200E	s	DIC Corporation	35.4	4.6		45
Acrylic resin		VONCOAT AB886	t	DIC Corporation	32.5	0.0		50
Acrylic resin		VONCOAT ED85E	u	DIC Corporation	34.1	26.1		45
Polyolefin resin		ZAIKTHENE AC	v	Sumitomo Seika Chemicals Company Limited	36.2	0.3		30
Polyolefin resin		ZAIKTHENE NC	w	Sumitomo Seika Chemicals Company Limited	37.7	0.1		28
Polyolefin resin		Hightech S3148K	x	TOHO Chemical Industry Co., Ltd.	37.7	1.2		26
Polyolefin resin		Hightech S9242	y	TOHO Chemical Industry Co., Ltd.	37.7	0.4		20
Polyethylene oxide		ALKOX E-45	-	Meisei Chemical Works, Ltd.	-	-		-
Additive	Polyethylene glycol	PEG4000S	-	Sanyo Chemical Industries, Ltd.	-	-		-
	Sodium formate	-	-	Mitsubishi Gas Chemical Company, Inc.	-	-		-
Solvent	Surface conditioner	BYK-349	-	BYK Japan KK	-	-		-
	Ion-exchanged water	-	-	-	-	-		-
Metallic foil	Methanol	-	-	-	-	-		-
	Aluminum foil	JIS-A1100 H18 thickness: 0.1 mm	-	Mitsubishi Gas Chemical Company, Inc. Mitsubishi Aluminum Company, Ltd.	-	-		-

[0078]

Hereinafter, the method for producing the entry sheets for drilling of Examples and Comparative Examples will be described.

<Example 1>

In a water/methanol mixed solvent, 4.3 parts by mass of a polyethylene oxide (manufactured by Meisei Chemical Works, Ltd., ALKOX E-45) having a weight average molecular weight of 560,000 as the high-molecular-weight water-soluble resin (b1), 38.6 parts by mass of a polyethylene glycol (manufactured by Sanyo Chemical Industries, Ltd., PEG 4000S) having a weight average molecular weight of 3,300 as the low-molecular-weight water-soluble resin (b2), and 142.75 parts by mass (57.1 parts by mass in terms of solid content of resin) of an aqueous dispersion of a polyurethane resin (manufactured by DKS Co. Ltd., SUPERFLEX 740, solid concentration of 40%) were mixed so that the solid concentration of the resin composition would be 30%. The mixing ratio in the water/methanol mixed solvent was set to 50/50. The resin composition solution was applied on one surface of aluminum foil (aluminum foil used: JIS-A1100H, thickness of 0.1 mm, manufactured by Mitsubishi Aluminum Company, Ltd.) using a bar coater so that the layer of the resin composition would have a thickness after drying of 50 μm , and the applied resin composition solution was dried at 120°C for 3 minutes in a dryer and was then cooled to

normal temperature to make an entry sheet for drilling. The adhesive force, and the dispersion term γ_{SD} and polar term γ_{SP} of the surface free energy were measured by the above-described methods. The results are shown in Table 2.

[0079]

<Examples 2 to 50 and Comparative Examples 1 to 48>

In accordance with Example 1, the solutions of the resin compositions were prepared according to the types and content ratios of materials as shown in Tables 2 to 5 to make entry sheets for drilling each having a thickness of the layer of the resin composition after drying and solidification of 50 μm . The adhesion force between the metallic foil and the layer of the resin composition, and the dispersion term γ_{SD} and polar term γ_{SP} of the surface free energy of the layer of the resin composition were measured for the obtained entry sheets for drilling. These results are shown in Tables 2 to 5.

[0080]

The decision criteria for the adhesion force shown in Tables 2 to 5 are as follows. When the adhesion force between the metallic foil and the layer of the resin composition is weak, the layer of the resin composition is peeled because the load at the time of processing is applied to the entry sheet during drilling processing. As a result of diligent studies conducted by the present inventors, it has become clear that when the adhesion

force is 200 gf or more, the layer of the resin composition is not peeled during drilling processing, so that the decision criteria have been determined such that the adhesion force of 200 gf or more was rated as "○", and the adhesion force of less than 200 gf was rated as "×".

[0081]

[Table 2]

Classification	Water-insoluble resin (A)			Water-soluble resin (B) PEG400US		Surface free energy of water-insoluble resin (A)		Surface free energy of layer of resin composition		Adhesion force	Decision of adhesion force
	Type of resin	Trade name	Sign	Parts by mass	Parts by mass	γ SD mJ/m ²	γ SP mJ/m ²	γ SD mJ/m ²	γ SP mJ/m ²		
Example 1	Polyurethane resin	SUPERFLEX 740	a	57.1	38.6	36.6	2.5	29.8	5.0	gf	
Example 2	Polyurethane resin	SUPERFLEX 740	a	80.0	18.0	36.6	2.5	34.3	0.0	350	○
Example 3	Polyurethane resin	SUPERFLEX 820	b	30.0	63.0	35.4	1.8	35.9	2.8	>1000	○
Example 4	Polyurethane resin	SUPERFLEX 820	b	35.0	6.5	35.4	1.8	32.7	1.3	210	○
Example 5	Polyurethane resin	SUPERFLEX 820	b	40.0	58.5	35.4	1.8	33.1	1.5	1000	○
Example 6	Polyurethane resin	SUPERFLEX 820	b	45.0	5.5	35.4	1.8	31.8	1.2	>1000	○
Example 7	Polyurethane resin	SUPERFLEX 820	b	50.0	5.0	35.4	1.8	32.9	0.4	>1000	○
Example 8	Polyurethane resin	SUPERFLEX 860	c	52.2	4.8	37.7	3.4	34.3	0.2	265	○
Example 9	Polyurethane resin	SUPERFLEX 860	c	57.1	4.3	37.7	3.4	34.0	0.0	380	○
Example 10	Polyurethane resin	UPRENE LXA 307	g	57.1	4.3	36.6	2.8	27.5	2.6	>1000	○
Example 11	Polyurethane resin	HYDRAN AP 201	h	25.0	7.5	36.7	0.9	30.9	0.6	275	○
Example 12	Polyurethane resin	HYDRAN AP 201	h	35.0	6.5	36.7	0.9	31.7	1.1	>1000	○
Example 13	Polyurethane resin	HYDRAN AP 201	h	50.0	5.0	36.7	0.9	34.0	0.2	800	○
Example 14	Polyurethane resin	HYDRAN HW 140SF	j	40.0	6.0	36.5	2.2	35.1	1.4	213	○
Example 15	Polyurethane resin	HYDRAN HW 140SF	j	45.0	5.5	36.5	2.2	34.6	2.9	700	○
Example 16	Polyurethane resin	HYDRAN HW 140SF	j	50.0	5.0	36.5	2.2	33.5	1.0	>1000	○
Example 17	Polyurethane resin	HYDRAN WLS 201	k	25.0	7.5	37.7	2.0	30.8	1.7	230	○
Example 18	Polyurethane resin	HYDRAN WLS 201	k	30.0	7.0	37.7	2.0	29.2	0.9	260	○
Example 19	Polyurethane resin	HYDRAN WLS 201	k	35.0	6.5	37.7	2.0	29.0	1.8	355	○
Example 20	Polyester resin	Vyonal MD1480	m	71.4	2.9	36.6	3.9	36.5	0.1	>1000	○
Example 21	Polyester resin	Vyonal MD1985	n	73.0	2.7	36.3	0.8	35.8	1.7	>1000	○
Example 22	Acrylic resin	VONCOAT AK3090	q	50.0	5.0	35.2	0.1	33.5	2.4	275	○
Example 23	Acrylic resin	VONCOAT AK3090	q	70.0	3.0	35.2	0.1	34.7	0.0	>1000	○
Example 24	Acrylic resin	VONCOAT AN678E	r	41.0	5.9	34.4	3.9	28.2	1.4	537	○
Example 25	Acrylic resin	VONCOAT AN678E	r	50.0	5.0	34.4	3.9	30.7	0.8	>1000	○

Decision criteria for adhesion force
 200 gf or more: ○
 Less than 200 gf: ×

[0082]

[Table 3]

Classification	Water-insoluble resin (A)				Amount of water-soluble resin (B)		Surface free energy of water-insoluble resin (A)		Surface free energy of layer of resin composition		Adhesion force	Decision of adhesion force
	Type of resin	Trade name	Sign	Parts by mass	blended		γ SD mJ/m2	γ SP mJ/m2	γ SD mJ/m2	γ SP mJ/m2		
					ALKOX E-45	PEG4000S						
Example 26	Acrylic resin	VONCOAT MAT200E	s	45.0	Parts by mass 5.5	49.5	35.4	4.6	32.5	3.5	>1000	○
Example 27	Acrylic resin	VONCOAT MAT200E	s	50.0	5.0	45.0	35.4	4.6	35.7	0.7	>1000	○
Example 28	Polyolefin-based resin	ZAIKTHENE AC	v	25.0	7.5	67.5	36.2	0.3	34.1	0.6	325	○
Example 29	Polyolefin-based resin	ZAIKTHENE AC	v	30.0	7.0	63.0	36.2	0.3	35.6	0.4	325	○
Example 30	Polyolefin-based resin	ZAIKTHENE AC	v	35.0	6.5	58.5	36.2	0.3	35.8	0.5	475	○
Example 31	Polyolefin-based resin	ZAIKTHENE AC	v	45.0	5.5	49.5	36.2	0.3	35.9	0.1	>1000	○
Example 32	Polyolefin-based resin	ZAIKTHENE AC	v	50.0	5.0	45.0	36.2	0.3	35.8	0.0	>1000	○
Example 33	Polyolefin-based resin	ZAIKTHENE NC	w	22.0	7.8	70.2	37.7	0.1	35.0	2.6	253	○
Example 34	Polyolefin-based resin	ZAIKTHENE NC	w	24.0	7.6	68.4	37.7	0.1	33.4	4.6	237	○
Example 35	Polyolefin-based resin	ZAIKTHENE NC	w	25.0	7.5	67.5	37.7	0.1	33.6	4.7	300	○
Example 36	Polyolefin-based resin	ZAIKTHENE NC	w	27.0	7.3	65.7	37.7	0.1	35.3	3.0	>1000	○
Example 37	Polyolefin-based resin	ZAIKTHENE NC	w	35.0	6.5	58.5	37.7	0.1	36.2	2.6	250	○
Example 38	Polyolefin-based resin	ZAIKTHENE NC	w	40.0	6.0	54.0	37.7	0.1	34.4	2.1	>1000	○
Example 39	Polyolefin-based resin	ZAIKTHENE NC	w	45.0	5.5	49.5	37.7	0.1	36.7	0.1	>1000	○
Example 40	Polyolefin-based resin	ZAIKTHENE NC	w	50.0	5.0	45.0	37.7	0.1	35.4	1.7	>1000	○
Example 41	Polyolefin-based resin	Hightech S3148K	x	40.0	6.0	54.0	37.7	1.2	36.4	0.6	525	○
Example 42	Polyolefin-based resin	Hightech S3148K	x	45.0	5.5	49.5	37.7	1.2	36.1	0.3	825	○
Example 43	Polyolefin-based resin	Hightech S3148K	x	50.0	5.0	45.0	37.7	1.2	36.8	0.7	>1000	○
Example 44	Polyolefin-based resin	Hightech S9242	y	20.0	8.0	72.0	37.7	0.4	35.5	2.8	270	○
Example 45	Polyolefin-based resin	Hightech S9242	y	22.0	7.8	70.2	37.7	0.4	35.2	2.7	440	○
Example 46	Polyolefin-based resin	Hightech S9242	y	25.0	7.5	67.5	37.7	0.4	34.4	1.4	>1000	○
Example 47	Polyolefin-based resin	Hightech S9242	y	35.0	6.5	58.5	37.7	0.4	36.7	0.9	>1000	○
Example 48	Polyolefin-based resin	Hightech S9242	y	40.0	6.0	54.0	37.7	0.4	36.2	1.1	>1000	○
Example 49	Polyolefin-based resin	Hightech S9242	y	45.0	5.5	49.5	37.7	0.4	36.9	0.9	>1000	○
Example 50	Polyolefin-based resin	Hightech S9242	y	50.0	5.0	45.0	37.7	0.4	35.6	0.9	>1000	○

Decision criteria for adhesion force

200 gf or more: ○

Less than 200 gf: ×

[0083]

[Table 4]

Classifi-cation	Water-insoluble resin (A)			Water-soluble resin (B)		Surface free energy of water-insoluble resin (A)		Surface free energy of layer of resin composition		Adhesion force	Decision of adhesion force
	Type of resin	Trade name	Sign	ALKOX E-45		PEG4000S		γ SD mJ/m ²	γ SP mJ/m ²		
				Parts by mass	Parts by mass	Parts by mass	Parts by mass				
Comparative Example 1	PEO/PEG	Not blended	-	0.0	10.0	90.0	-	32.3	11.6	0	x
Comparative Example 2	Polyurethane resin	SUPERFLEX 740	a	30.8	6.9	62.3	36.6	2.5	23.7	0	x
Comparative Example 3	Polyurethane resin	SUPERFLEX 740	a	36.4	6.4	57.3	36.6	2.5	23.9	0	x
Comparative Example 4	Polyurethane resin	SUPERFLEX 740	a	41.8	5.8	52.4	36.6	2.5	26.4	0	x
Comparative Example 5	Polyurethane resin	SUPERFLEX 740	a	47.1	5.3	47.6	36.6	2.5	25.9	13	x
Comparative Example 6	Polyurethane resin	SUPERFLEX 740	a	52.2	4.8	43.0	36.6	2.5	27.9	6.0	135
Comparative Example 7	Polyurethane resin	SUPERFLEX 820	b	5.0	9.5	85.5	35.4	1.8	29.0	8.4	0
Comparative Example 8	Polyurethane resin	SUPERFLEX 860	b	10.0	9.0	81.0	35.4	1.8	31.4	12.1	0
Comparative Example 9	Polyurethane resin	SUPERFLEX 860	c	30.8	6.9	62.3	37.7	3.4	30.4	7.3	3
Comparative Example 10	Polyurethane resin	SUPERFLEX 210	d	28.0	7.2	64.8	36.1	4.2	37.3	0.9	0
Comparative Example 11	Polyurethane resin	SUPERFLEX 210	d	48.8	5.1	46.0	36.1	4.2	37.2	1.0	93
Comparative Example 12	Polyurethane resin	SUPERFLEX 470	e	33.3	6.7	60.0	34.7	5.6	36.5	6.3	33
Comparative Example 13	Polyurethane resin	SUPERFLEX 470	e	81.8	1.8	16.4	34.7	5.6	30.5	6.1	57
Comparative Example 14	Polyurethane resin	SUPERFLEX 500M	f	29.7	7.0	63.3	31.0	0.1	32.8	6.8	43
Comparative Example 15	Polyurethane resin	SUPERFLEX 500M	f	79.2	2.1	18.8	31.0	0.1	30.5	7.2	20
Comparative Example 16	Polyurethane resin	UPRENE UXA 307	g	30.8	6.9	62.3	36.6	2.8	29.1	8.2	5
Comparative Example 17	Polyurethane resin	UPRENE UXA 307	g	36.4	6.4	57.3	36.6	2.8	28.8	7.6	5
Comparative Example 18	Polyurethane resin	UPRENE UXA 307	g	41.8	5.8	52.4	36.6	2.8	31.6	5.4	35
Comparative Example 19	Polyurethane resin	UPRENE UXA 307	g	52.2	4.8	43.0	36.6	2.8	30.5	12.0	175
Comparative Example 20	Polyurethane resin	HYDRAN AP 201	h	15.0	8.5	76.5	36.7	0.9	28.7	5.4	43
Comparative Example 21	Polyurethane resin	HYDRAN WLS 201	k	20.0	8.0	72.0	37.7	2.0	30.7	5.7	145
Comparative Example 22	Polyurethane resin	HYDRAN HW 140SF	j	25.0	7.5	67.5	36.5	2.2	32.8	17.1	0
Comparative Example 23	Polyurethane resin	HYDRAN ADS110	i	25.0	7.5	67.5	34.0	6.6	26.0	20.0	0
Comparative Example 24	Polyurethane resin	HYDRAN ADS110	i	50.0	5.0	45.0	34.0	6.6	26.8	4.6	0
Comparative Example 25	Polyester resin	Vyonal MD1480	m	21.7	7.8	70.4	36.6	3.9	27.1	7.0	0

Decision criteria for adhesion force

200 gf or more: o

Less than 200 gf: x

[0084]

[Table 5]

Classifi-cation	Water-insoluble resin (A)				Water-soluble resin (B)		Surface free energy of water-insoluble resin (A)		Surface free energy of layer of resin composition		Adhesion force	Decision of adhesion force	
	Type of resin		Trade name	Sign	Parts by mass	PEG4000S	γSD mJ/m2	γSP mJ/m2	γSD mJ/m2	γSP mJ/m2			
Comparative Example 26	Polyester resin	Vynal MD1985	n	23.1	Parts by mass	69.2	69.2	36.3	0.8	30.2	9.1	0	×
Comparative Example 27	Polyester resin	Vynal MD1985	n	37.5	7.7	56.3	56.3	36.3	0.8	31.4	8.3	4	×
Comparative Example 28	Polyester resin	Vynal MD1985	n	42.4	6.3	51.8	51.8	36.3	0.8	31.5	7.4	155	×
Comparative Example 29	Polyester resin	Vynal MD1500	o	75.0	5.8	22.5	22.5	37.1	4.5	34.9	5.5	127	×
Comparative Example 30	Polyester resin	Vynal MD2000	p	80.0	2.5	18.0	18.0	36.9	5.5	36.6	5.5	0	×
Comparative Example 31	Acrylic resin	VONCOAT AK3090	q	10.0	2.0	81.0	81.0	35.2	0.1	30.8	5.7	0	×
Comparative Example 32	Acrylic resin	VONCOAT AK3090	q	25.0	9.0	67.5	67.5	35.2	0.1	31.3	7.2	0	×
Comparative Example 33	Acrylic resin	VONCOAT AK3090	q	30.0	7.5	63.0	63.0	35.2	0.1	35.7	6.1	38	×
Comparative Example 34	Acrylic resin	VONCOAT AN678E	r	25.0	7.0	67.5	67.5	34.4	3.9	31.0	10.3	0	×
Comparative Example 35	Acrylic resin	VONCOAT MAT200E	s	10.0	7.5	81.0	81.0	35.4	4.6	29.3	11.5	0	×
Comparative Example 36	Acrylic resin	VONCOAT MAT200E	s	25.0	9.0	67.5	67.5	35.4	4.6	29.7	7.3	60	×
Comparative Example 37	Acrylic resin	VONCOAT MAT200E	s	30.0	7.0	63.0	63.0	35.4	4.6	30.6	6.1	90	×
Comparative Example 38	Acrylic resin	VONCOAT AB886	t	10.0	9.0	81.0	81.0	32.5	0.0	28.8	5.8	0	×
Comparative Example 39	Acrylic resin	VONCOAT AB886	t	25.0	7.5	67.5	67.5	32.5	0.0	31.7	6.0	0	×
Comparative Example 40	Acrylic resin	VONCOAT ED85E	u	10.0	9.0	81.0	81.0	34.1	26.1	29.5	9.1	0	×
Comparative Example 41	Acrylic resin	VONCOAT ED85E	u	50.0	5.0	45.0	45.0	34.1	26.1	33.9	6.4	0	×
Comparative Example 42	Polyolefin-based resin	ZAITHENE AC	v	5.0	9.5	85.5	85.5	36.2	0.3	32.6	6.4	0	×
Comparative Example 43	Polyolefin-based resin	ZAITHENE AC	v	10.0	9.0	81.0	81.0	36.2	0.3	30.4	7.4	0	×
Comparative Example 44	Polyolefin-based resin	ZAITHENE NC	w	5.0	9.5	85.5	85.5	37.7	0.1	31.1	10.2	0	×
Comparative Example 45	Polyolefin-based resin	ZAITHENE NC	w	10.0	9.0	81.0	81.0	37.7	0.1	32.1	7.6	0	×
Comparative Example 46	Polyolefin-based resin	ZAITHENE NC	w	15.0	8.5	76.5	76.5	37.7	0.1	33.1	7.4	85	×
Comparative Example 47	Polyolefin-based resin	Hightech S9242	y	5.0	9.5	85.5	85.5	37.7	0.4	33.1	6.7	0	×
Comparative Example 48	Polyolefin-based resin	Hightech S9242	y	10.0	9.0	81.0	81.0	37.7	0.4	32.7	6.7	0	×

[0085]

Table 6 shows the relation among the surface free energy, the adhesion force, and the hole position accuracy. The decision criteria for the hole position accuracy are as follows. When the hole position accuracy worked out by method of the expression (2) is 20 μm or less, the hole position accuracy is denoted as "○" meaning that the property is excellent, and when the hole position accuracy is more than 20 μm , the hole position accuracy is denoted as "×". Moreover, when both the decision of the hole position accuracy and the decision of the adhesion force are "○", the comprehensive decision is denoted as "○" because the adhesion strength between the metallic foil and the layer of the resin composition is strong and the hole position accuracy is excellent, and when at least one of the decision of the hole position accuracy and the decision of the adhesion force is "×", the comprehensive decision is denoted as "×".

[0086]

[Table 6]

Classification	Water-insoluble resin (A)			Surface free energy of water-insoluble resin (A)		Surface free energy of layer of resin composition		Adhesion force	Hole position accuracy	Decision of adhesion force (*)	Decision of hole position accuracy (*)	Comprehensive decision
	Type of resin	Trade name	Sign	γ_{SD} mJ/m ²	γ_{SP} mJ/m ²	γ_{SD} mJ/m ²	γ_{SP} mJ/m ²					
Example 1	Polyurethane resin	SUPERFLEX 740	a	36.6	2.5	29.8	5.0	350	15.9	○	○	○
Example 7	Polyurethane resin	SUPERFLEX 820	b	35.4	1.8	32.9	0.4	>1000	17.9	○	○	○
Example 8	Polyurethane resin	SUPERFLEX 860	c	37.7	3.4	34.3	0.2	265	17.5	○	○	○
Example 12	Polyurethane resin	HYDRAN AP 201	h	36.7	0.9	31.7	1.1	>1000	17.7	○	○	○
Example 18	Polyurethane resin	HYDRAN WLS 201	k	37.7	2.0	29.2	0.9	260	17.4	○	○	○
Example 24	Acrylic resin	VONCOAT AN678E	r	34.4	3.9	28.2	1.4	537	15.9	○	○	○
Example 26	Acrylic resin	VONCOAT MAT200E	s	35.4	4.6	32.5	3.5	>1000	15.5	○	○	○
Example 32	Polyolefin-based resin	ZAITHENE AC	v	36.2	0.3	35.8	0.0	>1000	18.5	○	○	○
Example 38	Polyolefin-based resin	ZAITHENE NC	w	37.7	0.1	34.4	2.1	>1000	18.2	○	○	○
Example 43	Polyolefin-based resin	Hightech S3148K	x	37.7	1.2	36.8	0.7	>1000	16.5	○	○	○
Example 50	Polyolefin-based resin	Hightech S9242	y	37.7	0.4	36.9	0.9	>1000	17.8	○	○	○
Comparative Example 1	PEOPEG	Not blended	-	-	-	32.3	11.6	0	21.5	x	x	x
Comparative Example 2	Polyurethane resin	SUPERFLEX 740	a	36.6	2.5	23.7	6.2	0	20.5	x	x	x
Comparative Example 8	Polyurethane resin	SUPERFLEX 820	b	35.4	1.8	31.4	12.1	0	21.2	x	x	x
Comparative Example 9	Polyurethane resin	SUPERFLEX 860	c	37.7	3.4	30.4	7.3	3	21.5	x	x	x
Comparative Example 10	Polyurethane resin	SUPERFLEX 210	d	36.1	4.2	37.3	0.9	0	22.1	x	x	x
Comparative Example 13	Polyurethane resin	SUPERFLEX 470	e	34.7	5.6	30.5	6.1	57	27.4	x	x	x
Comparative Example 14	Polyurethane resin	SUPERFLEX 500M	f	31.0	0.1	32.8	6.8	43	32.2	x	x	x
Comparative Example 16	Polyurethane resin	UPRENE UXA 307	g	36.6	2.8	29.1	8.2	5	26.2	x	x	x
Comparative Example 20	Polyurethane resin	HYDRAN AP 201	h	36.7	0.9	28.7	5.4	43	26.5	x	x	x
Comparative Example 24	Polyurethane resin	HYDRAN ADS110	i	34.0	6.6	26.8	4.6	0	35.7	x	x	x
Comparative Example 25	Polyester resin	Vyonal MD1460	m	36.6	3.9	27.1	7.0	0	32.5	x	x	x
Comparative Example 30	Polyester resin	Vyonal MD2000	p	36.9	5.5	36.6	5.5	0	73.2	x	x	x
Comparative Example 34	Acrylic resin	VONCOAT AN678E	r	34.4	3.9	31.0	10.3	0	21.1	x	x	x
Comparative Example 42	Polyolefin-based resin	ZAITHENE AC	v	36.2	0.3	32.6	6.4	0	54.6	x	x	x
Comparative Example 44	Polyolefin-based resin	ZAITHENE NC	w	37.7	0.1	31.1	10.2	0	48.4	x	x	x
Comparative Example 48	Polyolefin-based resin	Hightech S9242	y	37.7	0.4	32.7	6.7	0	25.5	x	x	x

(*)1 Decision criteria for hole position accuracy

Hole position accuracy of 20 μ m or less: ○

Hole position accuracy of larger than 20 μ m: x

(*)2 Decision criteria for adhesion force

Adhesion force of 200 gf or more: ○

Adhesion force of less than 200 gf: x

[0087]

In Figure 1, the γ_{SD} and γ_{SP} of the surface free energy of the layers of the resin compositions of Examples and Comparative Examples are plotted. It is understood from Figure 1 that when the dispersion term γ_{SD} of the surface free energy is in a range from 27.0 to 37.0 mJ/m², and the polar term γ_{SP} of the surface free energy is in a range from 0 to 5.0 mJ/m², the adhesion force is satisfactory.

[0088]

It is understood from Table 6 that the adhesion force between the metallic foil and the layer of the resin composition is strong, and the hole position accuracy is satisfactory for the entry sheets for drilling of Examples 1, 7, 8, 12, 18, 24, 26, 32, 38, 43, and 50 in which the dispersion term γ_{SD} of the surface free energy is in a range from 27.0 to 37.0 mJ/m², and the polar term γ_{SP} of the surface free energy is in a range from 0 to 5.0 mJ/m². On the other hand, the adhesion force between the metallic foil and the layer of the resin composition was weak for the entry sheets for drilling of Comparative Examples 1, 2, 8, 9, 10, 13, 14, 16, 20, 24, 25, 30, 34, 42, 44, and 48 in which the dispersion term γ_{SD} of the surface free energy is less than 27.0 mJ/m² or exceeded 37.0 mJ/m², or the polar term γ_{SP} of the surface free energy exceeded 5.0 mJ/m², so that the peeling of the layer of the resin composition

occurred during drilling processing, and the hole position accuracy was poor.

[0089]

That is, it is understood from the results in Tables 2 to 6 that when the dispersion term γ_{SD} of the surface free energy of the surface of the layer of the resin composition, the surface being in contact with the metallic foil, is out of the range from 27.0 to 37.0 mJ/m² or the polar term γ_{SP} of the surface free energy is out of the range from 0 to 5.0 mJ/m², the adhesion strength between the metallic foil and the layer of the resin composition is weak and the layer of the resin composition is peeled during drilling processing, so that the hole position accuracy is deteriorated.

[0090]

The present application claims priority based on Japanese Patent Application (Japanese Patent Application No. 2015-056156) filed with Japan Patent Office on Mar. 19, 2015, the contents of which are hereby incorporated with reference.

Industrial Applicability

[0091]

The present invention has industrial applicability as an entry sheet for drilling that is used during drilling processing or the like of a laminated board or a multi-layer board. Particularly, the present invention

can provide an entry sheet for drilling that makes the hole position accuracy more excellent, that makes the breakage of a drill due to peeling of a layer of a resin composition from metallic foil less frequent, and that is more excellent in economy because an adhesion layer, which has been necessary so far, is unnecessary than conventional entry sheets for drilling.

Claims

[Claim 1]

An entry sheet for drilling comprising:
a metallic foil; and
a layer of a resin composition, the layer formed on the metallic foil without interposing an adhesion layer, wherein
a surface of the layer of the resin composition, the surface being in contact with the metallic foil, has a dispersion term γ_{SD} of a surface free energy in a range from 27.0 to 37.0 mJ/m² and a polar term γ_{SP} of the surface free energy in a range from 0 to 5.0 mJ/m².

[Claim 2]

The entry sheet for drilling according to claim 1, wherein the resin composition comprises:
a water-insoluble resin (A); and
a water-soluble resin (B).

[Claim 3]

The entry sheet for drilling according to claim 2, wherein the water-insoluble resin (A) has the dispersion term γ_{SD} of the surface free energy in a range from 32.0 to 38.1 mJ/m² and the polar term γ_{SP} of the surface free energy in a range from 0 to 6.0 mJ/m².

[Claim 4]

The entry sheet for drilling according to claim 2 or 3, wherein the water-insoluble resin (A) is one or more

selected from the group consisting of polyurethane resins, polyester resins, acrylic-based resins, and polyolefin-based resins.

[Claim 5]

The entry sheet for drilling according to any one of claims 2 to 4, wherein the water-soluble resin (B) is one or more selected from the group consisting of polyethylene oxide; polypropylene oxide; cellulose derivatives; polytetramethylene glycol; polyethylene glycol; polypropylene glycol; monoether compounds of polyoxyethylene; polyoxyethylene monostearate; polyoxyethylene sorbitan monostearate; polyglycerin monostearate compounds; and a polyoxyethylene-propylene copolymer.

[Claim 6]

The entry sheet for drilling according to claim 5, wherein

the water-soluble resin (B) comprises:

a high-molecular-weight water-soluble resin (b1) having a weight average molecular weight of 50,000 or higher and 1,000,000 or lower; and

a low-molecular-weight water-soluble resin (b2) having a weight average molecular weight of 1,000 or higher and 30,000 or lower, and

the high-molecular-weight water-soluble resin (b1) comprises at least one selected from the group consisting

of polyethylene oxide, polypropylene oxide, and cellulose derivatives, and

the low-molecular-weight water-soluble resin (b2) comprises at least one selected from the group consisting of polytetramethylene glycol; polyethylene glycol; polypropylene glycol; monoether compounds of polyoxyethylene; polyoxyethylene monostearate; polyoxyethylene sorbitan monostearate; polyglycerin monostearate compounds; and a polyoxyethylene-propylene copolymer.

[Claim 7]

The entry sheet for drilling according to any one of claims 2 to 6, wherein the resin composition comprises:

20 to 80 parts by mass of the water-insoluble resin (A); and

80 to 20 parts by mass of the water-soluble resin (B) each based on 100 parts by mass of a total amount of the water-insoluble resin (A) and the water-soluble resin (B).

[Claim 8]

The entry sheet for drilling according to any one of claims 2 to 7, wherein the layer of the resin composition is formed using: an aqueous dispersion of the water-insoluble resin (A); and the water-soluble resin (B).

[Claim 9]

The entry sheet for drilling according to any one of claims 1 to 8, wherein the layer of the resin composition has a thickness of 0.02 to 0.3 mm.

[Claim 10]

The entry sheet for drilling according to any one of claims 1 to 9, wherein the metallic foil has a thickness of 0.05 to 0.5 mm.

[Claim 11]

A method for drilling processing, the method comprising a hole formation step of forming a hole in a laminated board or a multi-layer board using the entry sheet for drilling according to any one of claims 1 to 10.