

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
4 November 2004 (04.11.2004)

PCT

(10) International Publication Number
WO 2004/094536 A1

(51) International Patent Classification⁷: **C09C 1/36**

(74) Agent: **MILLER, William, B.**; Kerr-McGee Chemical LLC, 123 Robert S. Kerr Avenue, Oklahoma City, OK 73102 (US).

(21) International Application Number:
PCT/US2003/037442

(22) International Filing Date:
21 November 2003 (21.11.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
10/400,376 27 March 2003 (27.03.2003) US

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for all designated States except US*): **KERR-MCGEE CHEMICAL LLC** [—/US]; 123 Robert S. Kerr Avenue, Oklahoma City, OK 73102 (US).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **BROWNBRIDGE, Thomas, Ian** [—/US]; 7140 Woodbridge Avenue, Oklahoma City, OK 73132 (US). **ENGLE, Jeffrey, Austin** [—/US]; 7804 N.W. 102nd Street, Oklahoma City, OK 73132 (US).

Declaration under Rule 4.17:


— *as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for all designations*

Published:

— *with international search report*

[Continued on next page]

(54) Title: PROCESS FOR PRODUCING TITANIUM DIOXIDE SLURRIES FROM MICRONIZER TAILS



(57) Abstract: Improved methods for producing titanium dioxide slurries. The output from a micronizer is passed through a condenser to condense the steam and form an aqueous slurry of titanium dioxide, which can in most cases then be further concentrated as desired or which can be sold or used without further concentration, instead of passing the micronizer output to apparatus for separating the TiO₂ from the steam, as is currently practiced in the art. The resultant slurry from the condenser is in a further refinement preferably sent to an agitated storage tank together with dispersant and anti-settling compounds to aid in preventing settling of the titanium dioxide solids out of the slurry. To help facilitate condensation of the steam/pigment mixture sent to the condenser, a portion of the condensed slurry is in yet a further refinement pumped from the slurry storage tank to a heat exchanger. The output from the heat exchanger is then fed to the condenser to facilitate the condensing of the steam in the condenser. The temperature and volume (flow) of cooled condensate to the condenser are set to match the amount of steam and its temperature so as to ensure that substantially all of the steam and contained pigment are collected from the condenser.

WO 2004/094536 A1



For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.