

Method for classifying unknown particles on a surface of a semiconductor wafer

The present invention pertains to a method for classifying small extraneous particles on semiconductor wafers.

- 5 Monocrystalline semiconductor wafers are the foundation of modern-day electronics. During the production of components on said semiconductor wafers, thermal operations and coating steps that are nowadays highly complex are performed.

Semiconductor wafers, especially silicon semiconductor wafers, are typically produced by first pulling a monocrystalline rod by means of the float zone method (FZ) or the Czochralski method (CZ). The rods produced accordingly are divided into
10 crystal pieces by means of saws suitable for this purpose, such as wire saws, internal diameter saws or band saws, and these pieces are then processed to semiconductor wafers typically in a wire saw or internal diameter saw.

- After further mechanical, chemo-mechanical and/or chemical steps, an epitaxial layer
15 may optionally be applied by CVD.

These semiconductor wafers thus produced are then made available to further component processing.

- Because of a narrowing of design rules in component processing, particles are a major negative quality feature in wafer production, with relevance for developments in
20 process and in cleaning. The shape, position, and chemical composition usually provide a pointer to the origin of the contaminating particles and hence indicate the potential for reducing their incidence in improved processes.

- Particles which constitute unwanted contamination of semiconductor wafers are typically imaged by means of an SEM (**S**canning **E**lectron **M**icroscope). The
25 combination of SEM and EDX (**E**nergy-**D**ispersive **X**-ray spectroscopy) provides a technique in this context which allows simultaneous determination of the location, size and shape, and also the chemical composition, of the particles.

This type of analysis is extremely suitable for particles having an extent of more than 200 nm.

Particles with a smaller extent are very difficult to classify, as the information about the structure of the particles is absent or affected by great error.

- 5 The closer the particle size to the limit of SEM resolution, the more demanding it becomes to classify the particles. For technical reasons, the resolution limit of EDX analysis is lower than that of SEM resolution.

- 10 As a result of the continual miniaturization in component processing, however, smaller particles are increasingly coming under the spotlight, since they give rise to problems in semiconductor component fabrication to an increased extent. Avoiding these particles in the production processes is therefore immensely important.

The size range of particle diameters that is of particular interest at the present time is the range between about 15 nm and 200 nm.

- 15 Particles of this size are no longer classifiable with the techniques prevailing in the prior art.

Prior art/description of problem

- 20 The patent specification **JP 2006 303 134 A2** describes an analytical technique in which extraneous substances on the surface of the semiconductor wafer are visualized by applying weak acid in its vapor phase to the surface of the semiconductor wafer and then using a particle counter to detect the extraneous substances thus adorned.

The drawback of the method disclosed in the patent specification is that while small particles can indeed be made “visible”, in other words detectable or countable, it is not possible to derive any information concerning the origin of the particles.

- 25 Patent application **US 2005 062 959 AA** describes a method in which the small particles to be analyzed serve as polymerization nuclei for a monomer, and the

particles enlarged by polymerization are subsequently analyzed with a particle counter.

This patent as well is concerned with the detection of particles; information regarding the structure of the particles remains hidden with this method. Moreover, the method
5 in question is an indirect method, allowing only the location of the particles to be measured.

The patent specification **US 5 715 052 A** describes a method in which a subregion of a small particle has been repeatedly analyzed using different optical conditions with the aid of additional light.

10 It is indeed possible in principle with the aid of this patent specification to classify particles by way of their internal structure. The method described fails, however, as soon as the particles under study are smaller than the resolution of the microscope used.

In the case of the very small particles for study, even the use of an SEM (**S**canning
15 **E**lectron **M**icroscope) fails to achieve the object, as it is no longer possible to resolve the internal structure of the particles.

Predominantly, therefore, the only possible classification is that using the spectrum of an energy-dispersive x-ray spectroscopy (EDX).

The problem here is that the analyzable EDX measurement signal becomes smaller
20 as the particles under study become smaller. The ambient conditions (for example, the increasing influence of the substrate surface/volume signal components) have an increasingly significant influence on the result of measurement, and therefore make a correct classification more difficult.

In the case of relatively small Si or SiO₂ particles, for example, direct classification via
25 EDX spectrum is not possible, since in this case the native oxide of the particles and the native oxide in the surroundings significantly influence the measurement signal.

Another significant influence is the high signal component arising from the substrate volume (volume of interaction), which suppresses the small fraction arising from the

particle volume, owing to the unfavorable ratio of effective particle volume to substrate volume.

It is an object of this invention, therefore, to provide techniques devoid of the drawbacks of the techniques available in the prior art.

- 5 The object is achieved by the methods described in the claims.

The features specified in relation to the above embodiments of the method of the invention can be transposed correspondingly to the products according to the invention. Conversely, the features specified in relation to the above embodiments of the products according to the invention can be transposed correspondingly to the method of the invention. These and other features of the embodiments according to
 10 the invention are elucidated in the description of the figures and in the claims. The individual features may be realized either separately or in combination as embodiments of the invention. Moreover, they may describe advantageous embodiments which are protectable in their own right.

15 **Brief description of the figures**

Figure 1 shows an oxygen measurement (EDX, number of photons in units standardized to 1) obtained from a spectrum of an energy-dispersive x-ray spectroscopy as a function of the measured diameter of spherical particles which are located on a substrate (in this specific case, a silicon semiconductor wafer).

20 The data points represented by empty circles are values which originate from deliberately applied SiO₂ particles. The shaded region indicates the confidence region in which SiO₂ particles ought to be situated with 95% probability, on the assumption that for these particles the oxygen content shows a linear dependence on the diameter.

25 The solid circles relate to particles which exhibit no significant dependence between the oxygen content and the particle diameter. The region in which these particles lie in the figure is significantly different from the aforementioned confidence region.

The data point represented by an empty triangle originates from a particle which apparently exhibits a certain dependence between the oxygen content and its diameter; nevertheless, the data point is outside the above-defined confidence region for SiO₂ particles.

5 Detailed description and working examples of the invention

In the invention, particles of known chemical composition and different size are applied to a surface of a substrate (test wafer). This substrate preferably comprises silicon.

10 Particles are applied to a test wafer preferably by means of a suspension containing the particles. The particles contained in the suspension preferably have a very limited size range between 15 nm and 3000 nm. It should also be ensured that the extraneous substance content (unwanted impurities) is minimal.

15 The particle suspension may be applied in analogy to the production of calibrating wafers for scattered laser light systems. The particle suspension in this case may be implemented over the whole area or, preferably, in spots (partial areas). The use of a particle counter may be helpful in this case.

20 An appropriate basis for correct classification of particles are standard particles of known size and chemical composition. Standardized particles are available on the market with a very wide variety of different chemical compositions, such as aluminum, copper or even yttrium.

The particles used preferably have the same chemical composition but different sizes, with the size distribution of the particles used being very preferably between 20 nm and 100 nm.

25 After the particles have been applied to a test wafer, the size of a number of particles is ascertained, and a spectrum of an energy-dispersive x-ray spectroscopy is recorded. Both items of information are stored.

The energy-dispersive x-ray spectroscopy may be measured using, for example, a Zeiss Auriga 60 SEM-EDX instrument, 70 mm² with EDAX Elite Super EDX Detector,

with the following settings: 5 keV, working distance: 6.1 mm, orifice 30 μm , EDX integration time: 10 s. However, any other equivalent instrument may also be used.

The size of the particle of known chemical composition is preferably determined using an electron microscope (Scanning Electron Microscope).

- 5 The “size” in this context refers to a diameter determined for the particle; equivalently, it may also refer to an area of the particle or to magnitudes derived directly therefrom.

The spectra obtained are preferably analyzed so that they produce the substantive content of the desired substance. This may be done by analyzing the corresponding peak in the spectrum that is characteristic of the chemical substance.

- 10 Particular preference is given to using SiO_2 particles, in which case the oxygen content and the size are determined. However, other particles with other, known chemical compositions may also be used for the same purpose.

- The substantive content is plotted preferably as a function of the size (diameter, for example), and this plot is used to determine a best-fit curve, which produces a
15 mathematical relationship between substantive content and size in the form of a best-fit curve.

Both the size and the chemical composition of particles of unknown chemical composition are ascertained on the surface of a semiconductor wafer which preferably comprises silicon.

- 20 In this case, an energy-dispersive x-ray spectroscopy is preferably used. The size of the unknown particles is ascertained preferably using an electron microscope (SEM).

- Figure 1** shows, for example, the oxygen content of SiO_2 particles, standardized by means of energy-dispersive x-ray spectroscopy, as a function of the diameter (hollow circles). A linear best-fit curve has been fitted so as to illustrate a proportionality
25 between oxygen content and diameter. It is also possible to ascertain a confidence region, so that 95% of the data points are situated within this region.

The position of the measurement points for particles of unknown chemical composition, shown in **Figure 1** (solid circles, hollow triangle) is able to provide information about the chemical composition, without data regarding the structure of the particles.

- 5 The data, indicated for example by solid circles, shows that the oxygen content of the particles is evidently largely independent of their size.

The inventors have recognized here that an SiO_2 particle can with high probability be ruled out as the origin of these particles. These particles would therefore be classified as “non- SiO_2 particles”.

- 10 For data points which fall within a confidence region for SiO_2 particles, it can be assumed with a high degree of probability that they are also SiO_2 particles. The classification therefore reads “ SiO_2 particles”.

- For data points which apparently neither fall within the confidence range for SiO_2 nor have an oxygen content independent of the size (e.g., hollow triangle in **Figure 1**), it
 15 can be assumed either that these are particles with a certain oxygen content that are not spherical, or that these are particles with a possibly intrinsic oxide layer. This information too may be useful if the aim is to determine the origin for the incidence of particles. Particles of this kind are also classified as “non- SiO_2 particles”.

- The inventors have recognized that the procedure described is especially
 20 advantageous when it can be assumed that the semiconductor wafer on which the unknown particles are located carries a certain oxide layer – for example, a native oxide layer. This oxide layer influences the energy-dispersive x-ray spectroscopy. Through the additional information on the size of the particle and through the comparison with a best-fit curve for known particles, this measurement error shows
 25 only a small negative effect.

A similar approach can be taken with particles of different chemical composition as well, in order, for example, to determine their probable origin.

The above description of illustrative embodiments should be understood as exemplary. The disclosure made therewith enables the skilled person on the one hand

to understand the present invention and its attendant advantages, and on the other hand the understanding of the skilled person extends to obvious modifications and alterations of the structures and methods described. The intention is therefore that the scope of protection of the claims is to cover all such modifications and alterations, and
5 also equivalents.

What is claimed is:-

1. A method for classifying unknown particles on a surface of a semiconductor wafer, comprising:
the application of particles of known chemical composition and different size to a
5 test wafer, ascertainment of a size of a plurality of particles of known chemical
composition, and recording of a spectrum of an energy-dispersive x-ray
spectroscopy of a plurality of particles of known chemical composition, followed by
the respective ascertainment of a substantive content therefrom, and fitting of a
best-fit curve to size and substantive content of the particles of known chemical
10 composition; additionally, the ascertainment of a particle size of an unknown
particle and recording of a spectrum of an energy-dispersive x-ray spectroscopy of
the unknown particle, and determination therefrom of the substantive content of
the unknown particle on a semiconductor wafer, and classification of the unknown
particle as the result of the comparison of the size and the substantive content of
15 the unknown particle with the best-fit curve.
2. The method as claimed in claim 1, wherein the best-fit curve is a straight line.
3. The method as claimed in either of the preceding claims, wherein the test wafer
comprises silicon.
4. The method as claimed in any of the preceding claims, wherein the semiconductor
20 wafer comprises silicon.
5. The method as claimed in any of the preceding claims, wherein the size of an
unknown particle is determined by means of an electron microscope.
6. The method as claimed in any of the preceding claims, wherein the size of a
known particle is determined by means of an electron microscope.
- 25 7. The method as claimed in any of the preceding claims, wherein the particles of
known chemical composition comprise SiO₂.