

Description

Technical Field

5 This invention relates to an electrocatalytic process for producing synthesis gas from light hydrocarbons such as methane or natural gas. The process of the invention is a continuous process for the production of synthesis gas in an electrochemical reactor while optionally generating electricity.

Background of the Invention

10 Synthesis gas is composed primarily of hydrogen and carbon monoxide. Generally the H₂/CO ratio is from about 0.6 to 6. The production of synthesis gas from light hydrocarbons such as methane and natural gas by partial oxidation is known. The present invention describes a process for the preparation of synthesis gas from methane and natural gas by oxidation in an electrochemical reactor. In addition to the synthesis gas, electricity
15 also may be generated as a by-product of the process of the invention.

Electrogenerative and voltametric processes are reviewed and compared with conventional electrochemical and heterogeneous processes in Ind. Eng. Chem. Process Dev., Vol. 18, No. 4, pp. 567-579. Oxidation reactions are discussed at p. 576.

20 Methane and natural gas have been subjected to chemical reactions conducted in electrocatalytic cells of various types, and various products have been isolated. Otsuka et al in Chemistry Letters, (Japan), pages 319-322, 1985, describe the conversion of methane to ethane/ethylene in an electrocatalytic cell using silver and silver/bismuth oxide as the anode materials and a temperature of 973°F (about 700°C). In an earlier publication, Bull. Chem. Soc. Jpn., 57, 3286-3289 (1984), the same authors described steam reforming of hydrocarbons through a wall of stabilized zirconia which acts as a hydrogen separator. The desired product is hydrogen
25 with a minimum of carbon dioxide, carbon monoxide or hydrocarbons.

In Patent Early Disclosure No. 1986-30,688 (Japan), Otsuka and Morikawa describe a method for manufacturing higher hydrocarbons from a lower hydrocarbon via oxidative dehydrogenation conducted in an electrolytic cell. The temperature of the oxygen supplied to the cell is from 300-1000°C.

30 More recently, Seimanides and Stoukides reported on the oxidation of methane in a solid electrolyte cell using catalysts such as silver and lithium/magnesium oxide-silver. Ethylene, ethane, carbon monoxide and carbon dioxide were the main products. Electrochemical techniques were applied to increase the selectivity to C₂ products (Preprint, AIChE Meeting, Miami, Florida, November, 1986).

Otsuka et al Chemistry Letters (Japan), 1985, 499-500 describe the selective oxidation of methane to ethane and/or ethylene in a conventional heterogeneous catalytic reactor. A low pressure mixture of oxygen
35 and methane in helium is passed over a metal oxide catalyst at 700°C. Among the metal oxides described as active for this reaction are included rare earth, main group metals and transition metals.

The electrocatalytic reactivity of hydrocarbons on a zirconia electrolyte surface is described by B.C. Nguyen, TA Lin and D.M. Mason in J. Electrochem Soc.: Electrochemical Science and Technology, September, 1986 pp1807-1815.

40 Numerous publications describe the complete oxidation of methane to carbon dioxide and water in fuel cells. These processes are not designed to be chemical processes, but rather to generate electricity from a fuel gas and air (or oxygen). The selectivity of these processes is designed for complete combustion rather than partial combustion.

FR-A-2374752 describes a process in which a gas comprising hydrogen and methane is passed into a fuel
45 cell with oxygen, to generate electricity, the cell containing electrolyte which may be zirconia/calcia or zirconia/yttria; temperatures of 400-700°C are described.

JP-A-62128901 describes a process for converting methane with oxygen into carbon monoxide and hydrogen in an electrochemical cell at a temperature of at least 700°C.

50 A process has now been found in which a light hydrocarbon is converted into synthesis gas with improved conversion of the hydrocarbon, improved selectivity to carbon monoxide and reduced selectivity to carbon dioxide. An electrocatalytic process is described for producing synthesis gas from light hydrocarbons such as methane or natural gas. The process generally comprises the steps of

(A) providing an electrochemical cell comprising a solid electrolyte having a first surface coated with conductive metal, metal oxide or mixtures thereof capable of catalyzing the reduction of oxygen to oxygen ions,
55 and a second surface coated with conductive metal, metal oxide or mixtures thereof, provided that both coatings are stable at the operating temperatures, the two conductive coatings optionally being connected by an external circuit,

(B) heating the electrolytic cell to a temperature of at least 1000°C,

(C) passing an oxygen-containing gas in contact with the first conductive coating to reduce the gas to form oxygen ions,

(D) passing methane, natural gas or other light hydrocarbons in contact with the second conductive coating, to react with the oxygen ions in partial combustion to form synthesis gas, and

(E) recovering synthesis gas.

Brief Description of the Drawings

Fig. 1 is a side view, and cross-section of an apparatus suitable for carrying out the process of this invention.

Fig. 2 is a top view, and cross-section of an electrochemical cell reactor useful for carrying out the process of the invention.

Fig. 3 is a side view, and cross-section of the reactor shown in Fig. 2.

Description of the Preferred Embodiments

This invention provides a continuous process for converting methane, natural gas or other mixtures of light hydrocarbons to synthesis gas in an electrochemical cell. The electrochemical cells utilized in the process of this invention are also referred to as electrolytic cells, electrogenerative cells or fuel cells.

The process of the present invention is conducted in an electrochemical cell such as schematically represented in Fig. 1 wherein a core of solid electrolyte 1 is coated on one surface 2 with a material 3 useful for reducing oxygen to oxygen ions. This coating provides the cathode side of the cell. On a second surface 4 of the core of solid electrolyte 1 is another coating of material 5. This coating is the anode. The two coatings may be connected by an external circuit through wire leads 6 and 7. An ammeter 8 may be included in the circuit. A battery may also be included in the circuit for applying an electric potential between the two conductive coatings (electrodes).

In practice, an oxygen-containing gas or gas mixture is passed in contact with the first conductive coating (the cathode), and the light hydrocarbon gas containing feed gas is passed in contact with the second conductive coating (anode). As the oxygen-containing gas contacts the first conductive coating, oxygen is reduced to oxide ions which are transported through the solid electrolyte to the anode side. At the anode side (second conductive coating or surface), the oxide ions react with the light hydrocarbon gas to produce synthesis gas, and electrons are released. The electrons return to the cathode side. In one embodiment (shown in Fig. 1) where the anode and cathode are connected through an external circuit, the electrons released from the anode return to the cathode via the external circuit. In this manner, the reaction can generate a current in addition to forming the synthesis gas.

The solid electrolytes used in the process of this invention can be any material which can transfer oxygen ions under the conditions of the process, and which are stable under the operating conditions, especially at temperatures above 1000°C. Typically, oxygen ion conducting solid electrolytes are solid solutions formed between oxides containing divalent and trivalent cations such as calcium oxide, scandium oxide, yttrium oxide, lanthanum oxide, etc. with oxides containing tetravalent cations such as zirconia, thoria and ceria. Their higher ionic conductivity is due to the existence of oxygen ion site vacancies. One oxygen ion vacancy occurs for each divalent or each two trivalent cations that are substituted for a tetravalent ion in the lattice. Some of the known solid oxide transfer materials include Y_2O_3 -stabilized ZrO_2 , CaO-stabilized ZrO_2 , Sc_2O_3 -stabilized ZrO_2 , Y_2O_3 -stabilized Bi_2O_3 , Y_2O_3 -stabilized CeO_2 , CaO-stabilized CeO_2 , ThO_2 , Y_2O_3 -stabilized ThO_2 , or ThO_2 , ZrO_2 , Bi_2O_3 , CeO_2 , or HfO_2 stabilized by addition of any one of the lanthanide oxides or CaO. The preferred solid electrolytes are the Y_2O_3 -(yttria) and CaO-(calcia) stabilized ZrO_2 (zirconia) materials. These two solid electrolytes are characterized by their high ionic conductivity, their oxygen ion conduction over wide ranges of temperature and oxygen pressure, and their relatively low cost.

The conductive coating on the solid electrolyte utilized as the cathode may be any material capable of reducing oxygen to oxygen ions and which is stable under the operating conditions. Examples of metals and metal oxides useful in the preparation of the cathode include nickel, gold, platinum, palladium, copper, lanthanum-manganese-strontium, indium oxide-stannous oxide mixtures, or any mixtures of said metals and metal oxides.

The conductive coating on the second surface of the solid electrolyte (the anode) can be any of a wide variety of conductive materials capable of facilitating the oxidative conversion of methane or natural gas to synthesis gas provided that the stable material is stable under the operating conditions. Examples of metals and metal oxides useful in forming the anode coating include nickel, gold, platinum, palladium, copper, or any mixtures of said metals and metal oxides, or other mixtures such as cerium and zirconium oxides, cerium and lanthanum oxides, etc.

The process of the present invention is conducted at a temperature of at least 1000°C and up to 1300°C. In one embodiment the process is conducted at temperatures within the range of 1050 to 1300°C, and more specifically within the range of 1050-1200°C. The electrolytic cell is heated to the desired temperature and the temperature is maintained during the reaction by external heating and/or the exothermicity of the reaction.

5 The oxygen-containing gas which is passed in contact with the first conductive coating or cathode can be air, pure oxygen, or any other gas containing at least 1% oxygen. In another embodiment, the oxygen-containing gas does not contain dioxygen, but rather contains oxygen in other forms such as N_2O , CO_2 , SO_2 , NO_2 , NO , etc. Preferably, the oxidizing gas is air.

10 The feed gases which are treated in accordance with the process of the present invention may comprise light hydrocarbons such as methane, natural gas, ethane, or other light hydrocarbon mixtures. The methane-containing feed gas can be methane or natural gas or any other gas which contains at least 1% methane. The natural gas can be either wellhead natural gas or processed natural gas. The composition of the processed natural gas varies with the needs of the ultimate user. A typical processed natural gas composition contains about 70% by weight of methane, about 10% by weight of ethane, 10% to 15% of CO_2 , and the balance is made up of smaller amounts of propane, butane and nitrogen.

15 The light hydrocarbon gas feed can be mixed with any inert diluent such as nitrogen, helium, neon, argon, krypton, xenon, or any other gas, including steam, which does not interfere with the desired reaction. Nitrogen and steam are diluents of choice.

20 The synthesis gas produced by the process of the invention at the anode is substantially nitrogen free and comprises a mixture of hydrogen, carbon monoxide and may contain some acetylene or ethylene or both. The synthesis gas also contains only small amounts of carbon dioxide. The synthesis gas can be converted to liquids using the Fischer-Tropsch process. The synthesis gas can be converted to methanol by commercial processes.

25 The present invention may be further exemplified by reference to Figs. 2 and 3. Fig. 2 is a top view of an electrochemical cell useful in conducting the process of the present invention, and Fig. 3 is a side view of the same cell. In both Figs. 2 and 3, the electrochemical cell comprises a shell 20 in which is placed a circular solid cylindrical electrolyte core 21. The inside surface of the solid electrolyte 21 is coated with an electrically conductive metal or metal oxide which serves as the cathode 22. The outer surface of the solid electrolyte 21 is coated with an electrically conductive material 23 which serves as the anode. A wire lead 26 is attached to the inside coating 22, and a second wire lead 27 is attached to the outside coating 23, and the two wire leads are connected to form an external circuit through ammeter 28. A battery may be connected in series with the ammeter. As can be seen from the construction illustrated in Figs. 2 and 3, the cell contains an inner open space 24 through the center of the cell and an outer open space 25 between the outer coating 23 or anode and the shell 20.

35 In practice, the process of the present invention is conducted with an apparatus such as illustrated in Figs. 2 and 3 by passing an oxygen-containing gas through the inner open space 24 and hydrocarbon-containing gas through the outer open space 25. The oxygen-containing gas which contacts the inside conductive coating 22 is converted to oxygen ions which migrate through the solid electrolyte 21 to contact the outside conductive coating 23. At the surface of the outside coating 23, the oxygen ion reacts with the light hydrocarbons contacting the outside conductive coating 23 to form the synthesis gas. During this reaction, the oxygen ion loses two electrons which travel from the outer conductive coating 23 through the circuit formed by leads 26 and 27 and the ammeter/battery 28 to the inner surface coating 22.

40 In another embodiment, the anodes and cathodes are reversed. That is, inside conductive coating 22 is the anode and the outer conductive coating 23 is the cathode. In this embodiment, the oxygen containing gas is passed through the outer open space 25, and the hydrocarbon passed through the inner or central open space 24. Otherwise, the process in this embodiment is the same as the embodiment discussed above.

The process of the present invention generally is conducted at a pressure of from 0.01-10 MPa (about 0.1 to about 100 atmospheres), more preferably between 0.05-1 MPa (about 0.5 to about 10 atmospheres).

50 The flow rate of the hydrocarbon through the reactor may be varied as desired so long as there is sufficient contact by the hydrocarbon with the anode to result in oxidative conversion to synthesis gas. Contact times of from 0.1 to about 100 seconds may be used, and contact times of from 1 to 20 seconds are generally sufficient.

In one embodiment of the invention, the conversion of the light hydrocarbons to synthesis gas is improved by applying an electric potential between the anode and cathode. Generally, a potential of up to about 4 volts can be applied between the electrodes. The desired electric potential can be applied by the use of a battery installed in the external circuit formed by 26, 27 and 28 in Fig. 2.

55 In the following Examples 1-3 and C-1, the light hydrocarbons are treated in accordance with the method of the present invention in a laboratory reactor similar to the reactor illustrated in Figs. 2 and 3. The reactor is made from a 60 cm. long (10 mm. OD, 8 mm. ID) tube of 8% yttria-stabilized zirconia obtained from Zircoa

Products (Corning). The inside and outside surfaces of the tube are coated with a thin layer of platinum ink (Engelhard #8926) to provide permeable electrodes. The tube is heated in air at 1060°C for 15 minutes. The platinum electrodes are connected to an external circuit via silver wires attached to platinum stripes painted on the side of the tube. The tube is heated in air at 850°C for about 15 minutes.

A 40 cm. section of 14 mm. OD quartz is fitted over the center section of the zirconia tube using SWAGE-LOK™ tube fitting and Teflon® ferrules. A SWAGELOK™ tube fitting also is attached to each end of the zirconia tube which extends out of the quartz sleeve. The assembly is placed in a split furnace capable of heating to the desired temperatures, and the silver wires are connected through an ammeter and voltage regulator.

The electrodes are conditioned as follows: air is passed through the inside of the zirconia tube at 50 cc./min. Nitrogen is passed through the space between the zirconia and quartz tubes at the rate of 50 cc./min., and the tube is heated to 800°C over the course of about 2 hours. As the reactor is heated, a current is observed in the circuit at about 380°C. After 10 minutes at 800°C, the reactor tube is heated to the reaction temperature, the nitrogen flow is replaced by the hydrocarbon, and the experiment commences.

In the following Examples 1-3 and Control-Examples C-1, the hydrocarbon is methane and the feed rate is adjusted to 8 cc./min. Samples of the gaseous products are obtained at about 20 minute intervals, and the gas samples are analyzed by gas chromatography on either a Carle Series S 111 H or a Carle Series S 400 gas chromatograph outfitted to analyze refinery gas mixtures. The results summarized below in Table I are based upon averages of at least two gas samples, and the electric current values are steady-state values. The methane conversion reported is the conversion at the termination of the reaction which is not necessarily at the completion of the reaction. The object was to analyze the product obtained. In Example 3, an external potential is applied by means of a Hewlett-Packard 6214B power supply connected in series with the ammeter. All of the experiments are conducted at atmospheric pressure.

TABLE I
Methane Conversion

Ex.	Temp. °C	Applied Voltage	Current mA	CH ₄ Conv* %	C-Molar Selec.** C ₂ 's	CO	CO ₂
C-1	800	0.0	227	23.5	--	95.9	4.1
1	1000	0.0	340	40.4	--	99.9	0.1
2	1100	0.0	330	39.2	--	99.9	0.1
3	1100	2.0	994	100.	--	96.8	3.2

* % CH₄ conversion = $\frac{\text{moles CH}_4 \text{ converted}}{\text{moles CH}_4 \text{ fed}}$

** % Selectivity = $\frac{\text{moles C in product}}{\text{moles CH}_4 \text{ converted}}$

The currents observed and recorded in the table show that electricity can be generated as a useful by-product, and the results also show that the methane conversion can be generally increased by the application of a voltage between the electrodes.

In the following Examples 4-6, the above-described reactor is utilized, the feed gas is a natural gas composition comprising, by volume, 78.5% methane, 12.0% carbon dioxide, 6.0% ethane and 3.5% propane. In Examples 4 and 5, the feed rate is 20 cc./min. whereas the feed rate in Example 6 is 3 cc./min. Also, in Examples 4-6, there is no externally applied voltage. Samples of the gaseous products are obtained and analyzed in the manner described above with respect to Examples 1-3. The results are summarized in the following Table II.

TABLE II

Natural Gas Conversion

Ex.	Temp. °C	Current mA	CH ₄ CO ₂	C ₂	C ₃	CO	H ₂
4	1000	373	50.9	7.0	2.1	11.8	28.2
5	1100	421	33.5	5.1	0.1	14.8	46.5
6	1100	430	0.3	0.1	---	37.0	62.6

The results in Table II show that (a) nearly quantitative conversion of a mixture of hydrocarbons to synthesis gas can be obtained (Example 6), (b) any carbon dioxide present in the feed is not harmful and can also be converted to synthesis gas, (c) the synthesis gas contains some C₂ product which is substantially ethylene and/or acetylene, and (d) electricity can be generated.

The cathode in the following example is platinum.
The cerium:lanthanum oxide anode is prepared as follows: the inside surface of a yttria-stabilized zirconia tube is coated with a thin layer of platinum ink to provide a permeable cathode. The tube is heated in air at 1060°C for 15 minutes. A mixture of cerium oxide and lanthanum oxide with a molar ratio of Ce:La of 1:1, slurred in a water/ethylene glycol mixture is applied to the external surface of the tube. The tube is fired in air at 1200°C for 3 hours. The electrodes are connected in the circuit via platinum stripes and silver wires as described in previous examples.

The cerium zirconium anode is prepared in the same manner except that cerium zirconate (CeZrO₄ from Ceracl) is substituted for the cerium oxide:lanthanum oxide mixture, and the tube is fired at only 120°C for 15 minutes. In Examples 7-9, the feed gas is methane, the flow rate is 8 cc/min, and an external voltage of 2.0 volts is applied in each of Examples 7-9. Other details of the process and the results of the analysis of the product obtained in Examples 7-9 are summarized in the following Table III.

TABLE III

Methane Conversion

Ex.	Anode Temp. °C	Current mA	CH ₄ Conv. %	C ₂	CO	C ₂	C ₂
7	1050	516	47.3	0.4	99.5	0.1	CO ₂
8	1050	623	36.5	1.9	77.6	20.5	
9	1100	621	49.2	0.9	90.9	8.2	

* See definition in Table I.

The results obtained in Examples 7-9 demonstrate that metal oxide anodes are effective in converting hydrocarbons to synthesis gas, and the synthesis gas can contain some C₂ material which is substantially ethylene and/or acetylene.

While the invention has been explained in relation to its preferred embodiments, it is to be understood that various modifications thereof will become apparent to those skilled in the art upon reading the specification. Therefore, it is to be understood that the invention disclosed herein is intended to cover such modifications as fall within the scope of the appended claims.

Claims

1. An electrocatalytic process for converting methane, natural gas or other light hydrocarbons to synthesis gas which comprises

(A) providing an electrochemical cell comprising a solid electrolyte having a first surface coated with conductive metal, metal oxide or mixtures thereof capable of facilitating the reduction of oxygen to oxygen ions, and a second surface coated with conductive metal, metal oxide or mixtures thereof, provided



TABLE II

Natural Gas Conversion

Ex.	Temp. °C	Current mA	Product Composition, Vol. %					
			CH ₄	CO ₂	C ₂	C ₃	CO	H ₂
4	1000	373	50.9	7.0	2.1	---	11.8	28.2
5	1100	421	33.5	5.1	0.1	---	14.8	46.5
6	1100	430	0.3	0.1	---	---	37.0	62.6

The results in Table II show that (a) nearly quantitative conversion of a mixture of hydrocarbons to synthesis gas can be obtained (Example 6), (b) any carbon dioxide present in the feed is not harmful and can also be converted to synthesis gas, (c) the synthesis gas contains some C₂ product which is substantially ethylene and/or acetylene, and (d) electricity can be generated.

The following Examples 7-9 illustrate the process of the present invention which utilizes rare earth metal oxide anodes. The cathode in the following example is platinum.

The cerium:lanthanum oxide anode is prepared as follows: the inside surface of a yttria-stabilized zirconia tube is coated with a thin layer of platinum ink to provide a permeable cathode. The tube is heated in air at 1060°C for 15 minutes. A mixture of cerium oxide and lanthanum oxide with a molar ratio of Ce:La of 1:1, slurried in a water/ethylene glycol mixture is applied to the external surface of the tube. The tube is fired in air at 1200°C for 3 hours. The electrodes are connected in the circuit via platinum stripes and silver wires as described in previous examples.

The cerium zirconium anode is prepared in the same manner except that cerium zirconate (CeZrO₄ from Cerac) is substituted for the cerium oxide:lanthanum oxide mixture, and the tube is fired at only 120°C for 15 minutes. In Examples 7-9, the feed gas is methane, the flow rate is 8 cc/min. and an external voltage of 2.0 volts is applied in each of Examples 7-9. Other details of the process and the results of the analysis of the product obtained in Examples 7-9 are summarized in the following Table III.

TABLE III

Methane Conversion

Ex.	Anode	Temp. °C	Current mA	CH ₄ Conv.* %	C Molar Selectivity*		
					C ₂	CO	CO ₂
7	CeLa	1050	516	47.3	0.4	99.5	0.1
8	CeZr	1050	623	36.5	1.9	77.6	20.5
9	CeZr	1100	621	49.2	0.9	90.9	8.2

* See definition in Table I.

The results obtained in Examples 7-9 demonstrate that metal oxide anodes are effective in converting hydrocarbons to synthesis gas, and the synthesis gas can contain some C₂ material which is substantially ethylene and/or acetylene.

While the invention has been explained in relation to its preferred embodiments, it is to be understood that various modifications thereof will become apparent to those skilled in the art upon reading the specification. Therefore, it is to be understood that the invention disclosed herein is intended to cover such modifications as fall within the scope of the appended claims.

Claims

1. An electrocatalytic process for converting methane, natural gas or other light hydrocarbons to synthesis gas which comprises

(A) providing an electrochemical cell comprising a solid electrolyte having a first surface coated with conductive metal, metal oxide or mixtures thereof capable of facilitating the reduction of oxygen to oxygen ions, and a second surface coated with conductive metal, metal oxide or mixtures thereof, provided



that both coatings are stable at the operating temperature.

(B) heating the electrochemical cell to a temperature of at least 1000°C,

(C) passing an oxygen-containing gas in contact with the first conductive coating, to reduce the gas to form oxygen ions

5 (D) passing methane, natural gas or other light hydrocarbons in contact with the second conductive coating, to react with the oxygen ions in partial combustion to form synthesis gas, and
(E) recovering synthesis gas.

2. The process of claim 1 wherein the two conductive coatings are connected by an external circuit.
- 10 3. The process of claim 1 or 2 wherein said solid electrolyte comprises yttria stabilised zirconia or calcia stabilised zirconia.
- 15 4. The process of any one of claims 1-3 wherein the first conductive coating comprises nickel, gold, platinum, palladium, copper, lanthanum-manganese-strontium or indium oxide-stannous oxide mixtures, or any mixtures of said metals.
5. The process of claim 4 wherein the first conductive coating comprises platinum.
- 20 6. The process of any one of Claims 1-5 wherein the second conductive coating comprises nickel, gold, platinum, palladium, copper, mixtures of said metals, cerium-lanthanum oxide mixtures, or cerium-zirconium oxide mixtures.
- 25 7. The process of Claim 6 wherein the second conductive coating is platinum.
8. The process of Claim 6 wherein the second conductive coating comprises a cerium-lanthanum oxide mixture.
- 30 9. The process of Claim 6 wherein the second conductive coating comprises a cerium-zirconium oxide mixture.
10. The process of any one of Claims 1-3 wherein the first and second conductive coatings are platinum.
- 35 11. The process of any one of the preceding Claims wherein the synthesis gas recovered in step (E) comprises carbon monoxide, hydrogen, and at least some acetylene and/or ethylene.
12. The process of Claim 11 wherein the recovered synthesis gas comprises carbon monoxide, hydrogen and at least some acetylene.
- 40 13. The process of any one of the preceding Claims conducted at a temperature of from about 1050°C to about 1300°C.
14. The process claim 13 wherein the temperature is from about 1050°C to about 1200°C.
- 45 15. The process of any one of the preceding Claims conducted at a pressure of from 0.01-10 MPa about 0.1 to about 100 atmospheres.
16. The process according to Claim 15, wherein the solid electrolyte is as defined in Claim 3 and the first conductive coating and second conductive coating which are connected by an external circuit are as defined in Claims 4 and 6 respectively, and the temperature is from 1050°C to about 1300°C.
- 50 17. The process of Claim 15 or 16 conducted at a pressure of from 0.05 - 1 MPa (about 0.5 to about 10 atmospheres).
- 55 18. The process of any one of the preceding Claims wherein the oxygen-containing gas is air or oxygen.
19. The process of Claim 18 wherein the oxygen-containing gas is air.



20. The process of any one of the preceding Claims wherein an electric potential is applied between the two conductive coatings.
21. The process of any one of the preceding Claims wherein methane is passed in contact with the second conductive surface.

Patentansprüche

1. Elektrokatalytisches Verfahren zur Umwandlung von Methan, Erdgas oder anderen leichten Kohlenwasserstoffen in Synthesegas, umfassend:
 - (A) Bereitstellen einer elektrochemischen Zelle, umfassend einen festen Elektrolyten mit einer ersten Oberfläche, die mit leitendem Metall, Metalloxid oder Gemischen davon überzogen ist, die in der Lage sind, die Reduktion von Sauerstoff zu Sauerstoffionen zu erleichtern, und einer zweiten Oberfläche, die mit leitendem Metall, Metalloxid oder Gemischen davon überzogen ist, mit der Maßgabe, daß beide Überzüge bei der Arbeitstemperatur stabil sind;
 - (B) Erwärmen der elektrochemischen Zelle auf eine Temperatur von wenigstens 1000°C;
 - (C) Vorbeileiten eines sauerstoffhaltigen Gases in Kontakt mit dem ersten leitenden Überzug, so daß das Gas unter Bildung von Sauerstoffionen reduziert wird;
 - (D) Vorbeileiten von Methan, Erdgas oder anderen leichten Kohlenwasserstoffen in Kontakt mit dem zweiten leitenden Überzug, so daß sie mit den Sauerstoffionen in partieller Verbrennung unter Bildung von Synthesegas reagieren; und
 - (E) Gewinnen von Synthesegas.
2. Verfahren gemäß Anspruch 1, wobei die beiden leitenden Überzüge über einen äußeren Stromkreis miteinander verbunden sind.
3. Verfahren gemäß Anspruch 1 oder 2, wobei der feste Elektrolyt mit Yttriumoxid stabilisiertes Zirkoniumdioxid oder mit Calciumoxid stabilisiertes Zirkoniumdioxid umfaßt.
4. Verfahren gemäß einem der Ansprüche 1-3, wobei der erste leitende Überzug Nickel, Gold, Platin, Palladium, Kupfer, Lanthan/Mangan/Strontium- oder Indiumoxid/Zinn(II)oxid-Gemische oder irgendwelche Gemische dieser Metalle umfaßt.
5. Verfahren gemäß Anspruch 4, wobei der erste leitende Überzug Platin umfaßt.
6. Verfahren gemäß einem der Ansprüche 1-5, wobei der zweite leitende Überzug Nickel, Gold, Platin, Palladium, Kupfer, Gemische dieser Metalle, Cer-/Lanthanoxid-Gemische oder Cer-/Zirkoniumoxid-Gemische umfaßt.
7. Verfahren gemäß Anspruch 6, wobei der zweite leitende Überzug aus Platin besteht.
8. Verfahren gemäß Anspruch 6, wobei der zweite leitende Überzug ein Cer-/Lanthanoxid-Gemisch umfaßt.
9. Verfahren gemäß Anspruch 6, wobei der zweite leitende Überzug ein Cer-/Zirkoniumoxid-Gemisch umfaßt.
10. Verfahren gemäß einem der Ansprüche 1-3, wobei der erste und der zweite leitende Überzug aus Platin bestehen.
11. Verfahren gemäß einem der vorangehenden Ansprüche, wobei das in Schritt (E) gewonnene Synthesegas Kohlenmonoxid, Wasserstoff und wenigstens etwas Acetylen und/oder Ethylen umfaßt.
12. Verfahren gemäß Anspruch 11, wobei das gewonnene Synthesegas Kohlenmonoxid, Wasserstoff und wenigstens etwas Acetylen umfaßt.
13. Verfahren gemäß einem der vorangehenden Ansprüche, das bei einer Temperatur von etwa 1050°C bis etwa 1300°C durchgeführt wird.



14. Verfahren gemäß Anspruch 13, wobei die Temperatur von etwa 1050°C bis etwa 1200°C beträgt.
15. Verfahren gemäß einem der vorangehenden Ansprüche, das bei einem Druck von 0,01-10 MPa (etwa 0,1 bis etwa 100 Atmosphären) durchgeführt wird.
16. Verfahren gemäß Anspruch 15, wobei der feste Elektrolyt wie in Anspruch 3 definiert ist und der erste leitende Überzug und der zweite leitende Überzug, die über einen äußeren Stromkreis miteinander verbunden sind, wie in Anspruch 4 bzw. 6 definiert sind und die Temperatur von 1050°C bis etwa 1300°C beträgt.
17. Verfahren gemäß Anspruch 15 oder 16, das bei einem Druck von 0,05-1 MPa (etwa 0,5 bis etwa 10 Atmosphären) durchgeführt wird.
18. Verfahren gemäß einem der vorangehenden Ansprüche, wobei das sauerstoffhaltige Gas Luft oder Sauerstoff ist.
19. Verfahren gemäß Anspruch 18, wobei das sauerstoffhaltige Gas Luft ist.
20. Verfahren gemäß einem der vorangehenden Ansprüche, wobei eine elektrische Spannung zwischen den beiden leitenden Überzügen angelegt wird.
21. Verfahren gemäß einem der vorangehenden Ansprüche, wobei Methan in Kontakt mit dem zweiten leitenden Überzug vorbeigeleitet wird.

Revendications

1. Procédé électrocatalytique pour convertir du méthane, du gaz naturel et d'autres hydrocarbures légers en gaz de synthèse, qui comprend les étapes consistant:
 - (A) à fournir une cellule électrochimique comprenant un électrolyte solide ayant une première surface revêtue de métal et d'oxyde métallique conducteurs ou de leurs mélanges capables de faciliter la réduction de l'oxygène en ions oxygène, et une deuxième surface revêtue de métal et d'oxyde métallique conducteurs ou de leurs mélanges, étant entendu que les deux revêtements sont stables à la température de fonctionnement,
 - (B) à chauffer la cellule électrochimique à une température d'au moins 1 000°C,
 - (C) à faire passer un gaz contenant de l'oxygène en contact avec le premier revêtement conducteur pour réduire le gaz pour former des ions oxygène,
 - (D) à faire passer du méthane, du gaz naturel ou d'autres hydrocarbures légers en contact avec le deuxième revêtement conducteur, pour réagir avec les ions oxygène dans une combustion partielle pour former un gaz de synthèse, et
 - (E) à recueillir le gaz de synthèse.
2. Procédé selon la revendication 1, dans lequel les deux revêtements conducteurs sont reliés par un circuit externe.
3. Procédé selon la revendication 1 ou 2, dans lequel ledit électrolyte solide comprend de la zircone stabilisée par de l'oxyde d'yttrium ou de la zircone stabilisée par de l'oxyde de calcium.
4. Procédé selon l'une des revendications 1 à 3, dans lequel le premier revêtement conducteur comprend du nickel, de l'or, du platine, du palladium, du cuivre, des mélanges lanthane-manganèse-strontium ou oxyde stanneux-oxyde d'indium, ou tout mélange desdits métaux.
5. Procédé selon la revendication 4, dans lequel le premier revêtement conducteur comprend du platine.
6. Procédé selon l'une des revendications 1 à 5, dans lequel le deuxième revêtement conducteur comprend du nickel, de l'or, du platine, du palladium, du cuivre, des mélanges desdits métaux, des mélanges d'oxydes de cérium-lanthane, ou des mélanges d'oxydes de cérium-zirconium.



7. Procédé selon la revendication 6, dans lequel le deuxième revêtement conducteur est du platine.
8. Procédé selon la revendication 6, dans lequel le deuxième revêtement conducteur comprend un mélange d'oxydes de cérium-lanthane.
- 5 9. Procédé selon la revendication 6, dans lequel le deuxième revêtement conducteur comprend un mélange d'oxydes de cérium-zirconium.
- 10 10. Procédé selon l'une des revendications 1 à 3, dans lequel les premier et deuxième revêtements conducteurs sont en platine.
11. Procédé selon l'une des revendications précédentes, dans lequel le gaz de synthèse recueilli dans l'étape (E) comprend du monoxyde de carbone, de l'hydrogène, et au moins un peu d'acétylène et/ou d'éthylène.
- 15 12. Procédé selon la revendication 11, dans lequel le gaz de synthèse recueilli comprend du monoxyde de carbone, de l'hydrogène et au moins un peu d'acétylène.
13. Procédé selon l'une des revendications précédentes, réalisé à une température d'environ 1 050°C à environ 1 300°C.
- 20 14. Procédé selon la revendication 13, dans lequel la température est d'environ 1 050°C à environ 1 200°C.
15. Procédé selon l'une des revendications précédentes, réalisé sous une pression de 0,01 à 10 MPa (environ 0,1 à environ 100 atmosphères).
- 25 16. Procédé selon la revendication 15, dans lequel l'électrolyte solide est tel que défini dans la revendication 3 et le premier revêtement conducteur et le deuxième revêtement conducteur qui sont reliés par un circuit externe sont tels que définis dans les revendications 4 et 6, respectivement, et la température est comprise entre 1 050°C et environ 1 300°C.
- 30 17. Procédé selon l'une des revendications 15 ou 16, effectué sous une pression de 0,05 à 1 MPa (environ 0,5 à environ 10 atmosphères).
- 35 18. Procédé selon l'une des revendications précédentes, dans lequel le gaz contenant de l'oxygène est l'air ou l'oxygène.
19. Procédé selon la revendication 18, dans lequel le gaz contenant de l'oxygène est l'air.
- 40 20. Procédé selon l'une des revendications précédentes, dans lequel on applique un potentiel électrique entre les deux revêtements conducteurs.
21. Procédé selon l'une des revendications précédentes, dans lequel le méthane est mis en contact avec la deuxième surface conductrice.