

PATENT SPECIFICATION

(11) 1 432 560

1 432 560

- (21) Application No. 56964/72 (22) Filed 11 Dec. 1972
 (23) Complete Specification filed 10 Dec. 1973
 (44) Complete Specification published 22 April 1976
 (51) INT. CL.² H01B 9/02
 (52) Index at acceptance
 H1A 13 2E3D1 2E3D2 3E 3M 5
 B5A 1G1 1G2 2A4X 2M
 (72) Inventor STEFAN VERNE



(54) IMPROVEMENTS IN ELECTRIC CABLES

(71) We, BICC LIMITED (formerly British Insulated Callender's Cables Limited), a British Company, of 21 Bloomsbury Street, London WC1B 3QN, do hereby declare the invention, for which we pray that a patent may be granted to us, and the method by which it is to be performed, to be particularly described in and by the following statement:—

This invention relates to single and multi-core electric cables and is particularly concerned with cores for such electric cables having an extruded dielectric of insulating material to the outer surface of which is applied a conductive or semi-conductive layer constituting a dielectric screen. Examples of insulating materials of which the core dielectric may be made include natural rubber compositions, synthetic rubber-like compositions such as butyl rubber, ethylene/propylene rubber, silicone rubber and styrene butadiene rubber and synthetic plastics materials such as olefin polymers, for example ordinary or cross-linked polyethylene, and olefin copolymers, for example of ethylene and propylene, all such materials hereinafter for convenience being included in the generic expression "rubber or plastics material".

In order to prevent the formation of spaces between a core dielectric and the dielectric screen in which electrical discharges can take place it is desirable that the dielectric screen should fit tightly on the core dielectric and with this purpose in view it has been proposed to form the dielectric screen of a cable core having an extruded dielectric of rubber or plastics material rendered electrically conductive by the incorporation of suitable additives, the extrusion of the dielectric screen being effected in such a way and the materials being such that, throughout its length, the extruded dielectric screen bonds firmly to the core dielectric. Whilst such a firm bond is highly desirable from an electrical point of view it has the disadvantage that, when jointing or terminating a cable incorporating a screened core of this form, it is difficult to cut back and strip the extruded dielectric screen cleanly from the core dielectric.

It is an object of the present invention to

provide an improved cable core having a dielectric screen which can be easily removed for jointing or terminating purposes.

According to the invention the cable core comprises a conductor having an extruded dielectric of rubber or plastics material, a dielectric screen comprising a layer of conductive or semi-conductive rubber or plastics material and, interposed between and bonded to the extruded dielectric and the dielectric screen throughout substantially the whole length of the core, an intermediate layer of rubber or plastics insulating material, the intermediate layer having throughout the layer or at least in a circumferentially continuous zone of the layer a cohesive strength substantially less than the cohesive strengths of the extruded dielectric and the dielectric screen and substantially less than the strengths of the bonds between the intermediate layer and the extruded dielectric and between the intermediate layer and the dielectric screen such that when stripping the dielectric screen from the core over a part of its length for jointing or terminating purposes separation takes place within the intermediate layer to leave a portion of the intermediate layer on the extruded dielectric.

Preferably the cohesive strength of the intermediate layer is not greater than 70% (and preferably not greater than 50%) but preferably at least 5% of the cohesive strength of the dielectric or the screen, whichever is weaker. These relations should hold good throughout the range of temperatures from the lowest ambient temperature at which jointing of the cable may need to be carried out up to the maximum working temperature at the interface between the dielectric and the intermediate layer.

Preferably the intermediate layer is substantially thinner than the dielectric screen, and ideally as thin as possible, subject to maintaining a substantially continuous layer; in practice the ratio between the radial thicknesses of the intermediate layer and the dielectric screen is preferably in the range 1:2 to 1:20. The intermediate layer may be applied by causing a conductor having an extruded dielectric to pass through a bath of

rubber or plastics insulating material in a viscous or fluid state but the intermediate layer is preferably applied by extrusion.

5 The invention also includes a method of forming a cable core in accordance with the invention which comprises extruding a layer of rubber or plastics insulating material on to a travelling conductor, which may or may not have a conductor screen applied thereto, to form the core dielectric; applying an intermediate layer of rubber or plastics insulating material to the outer surface of the core dielectric in such a way that the intermediate layer bonds to or can be subsequently bonded to, the core dielectric; and applying a layer of conductive or semi-conductive rubber or plastics material to the outer surfaces of the intermediate layer in such a way that the dielectric screen so formed bonds to, or can be subsequently bonded to the intermediate layer, the strengths of the bonds between the intermediate layer and the core dielectric and between the intermediate layer and the dielectric screen being substantially greater than the cohesive strength of the intermediate layer throughout the layer or at least in a circumferentially continuous zone of the layer, and the intermediate layer having, in the final product, a cohesive strength less than the cohesive strengths of the core dielectric and of the dielectric screen.

Preferably both the intermediate layer and the layer of conductive or semi-conductive rubber or plastics material constituting the dielectric screen are applied by extrusion and to obtain a firm bond between the intermediate layer and the core dielectric and between the intermediate layer and the extruded dielectric screen, the intermediate layer and dielectric screen are preferably extruded while the core dielectric and intermediate layer respectively are still hot. With this view in mind and with a view to maintaining as low as possible the additional cost incurred due to the provision of the intermediate layer, the core dielectric, intermediate layer and dielectric screen are preferably extruded on to a travelling conductor successively in line. Where a conductor screen is to be provided, preferably the conductor screen is an extruded layer of conductive or semi-conductive rubber or plastics material, the conductor screen and core dielectric preferably being extruded simultaneously in the same extrusion head.

Examples of rubber or plastics materials for the intermediate layer that can be applied by extrusion include ethylene/propylene rubber based compounds, with or without fillers and with or without curing agent added. Preferred ethylene/propylene rubber based compounds comprise:

COMPOUND NO.	PARTS BY WEIGHT							
	1	2	3	4	5	6	7	8
Keltan* 320	50	60	50	60	50	60	50	60
Elvax* 250	50	40	—	—	50	40	—	—
Elvax* 460	—	—	50	40	—	—	50	40
M100 Clay	—	—	—	—	100	100	100	100
Silane A-172	—	—	—	—	2	2	2	2

Keltan* 320 is a low Mooney viscosity ethylene - propylene terpolymer rubber supplied by N.V. Nederlands & Staatsmijnen (DSM); Elvax* 250 and 460 are grades of ethylene/vinyl acetate copolymer, supplied by E. I. Du Pont de Nemours & Co. The '250' grade contains 28% vinyl acetate, while the '460' grade is of higher molecular weight and contains 18% of vinyl acetate. M100 is a calcined clay filler supplied by English China Clays Ltd. Silane A-172 is vinyl tris (beta methoxy ethoxy) silane, supplied by Union Carbide Corp.

* Trade Marks.

65 Examples of rubber or plastics materials for the intermediate layer that can be applied by passing an insulated conductor through a bath of the material in a viscous or fluid state include blends of ethylene/vinyl acetate copolymers with synthetic resins.

70 Mixtures of low-Mooney viscosity ethylene/propylene rubber (Keltan 320) and an ethylene/vinyl acetate copolymer, with conven-

tional fillers, both with and without curing agent added, have been tested for use as an intermediate layer between moulded sheets of dielectric material and semi-conductive material based both on an ethylene/propylene rubber and on crosslinked polyethylene. It was found that both with the cured and with the uncured mixture used for the intermediate layer a good bond was obtained with dielectric

Material and semi-conductive material of both ethylene/propylene rubber and crosslinked polyethylene. To test the cohesive strength of the intermediate layers strips 25 mm wide were cut from moulded composite sheets, having dielectric and semi-conductive laminar each about 1 mm thick and an interposed layer about 0.1 mm thick. The semi-conductive layer was peeled from the dielectric layer of each strip and the force required was in all cases found to be below about 150 Newtons, which force is within the range of strengths capable of separation by hand. After stripping each strip it was found that a portion of the intermediate layer remained bonded to the dielectric layer and a portion of the intermediate layer remained bonded to the semi-conductive layer, thereby indicating that separation occurred within the intermediate layer. In the experiments described, the ethylene/propylene rubber based insulation and screen compounds were as follows:

	Parts by weight	
	EPR Compound 'A' (Insulation)	EPR Compound 'B' (Screen)
Intolan* 255	85	—
Vistalon* 404	—	100
Alkathene* WVG 23	15	—
Vulcan* XC72 Black	—	65.14
Sunpar* Oil 2280	31	—
Esso* D Process Oil	—	13.48
M100 Clay	153	—
Zinc Oxide	5	5.40
Flectol* H	2	0.54
Antioxidant MB	2	—
Silane A-172	3.1	—
Paraffin Wax	—	5.40
Sulphur	0.3	0.32
Retilox* F.40	7.87	7.72

Intolan* 255 is a high green strength ethylene propylene terpolymer rubber, supplied by International Synthetic Rubber Co.,

Vistalon* 404 is an ethylene propylene copolymer rubber, supplied by Esso Chemicals Ltd.

Alkathene* WVG 23 is a polyethylene supplied by Imperial Chemical Industries Ltd.

Vulcan* XC72 is a conductive grade of furnace carbon black supplied by Cabot Corporation.

Sunpar* Oil 2280 is a low-aromatic (paraffinic) oil supplied by Sun Oil Co.

Esso* D Process Oil is a mineral oil supplied by Esso Chemicals Ltd.

Flectol* H is an antioxidant, polymerised trimethyldihydroxyquinoline, supplied by Monsanto Co.

Antioxidant MB is 2-mercaptobenzimidazole supplied by Farbenfabriken Bayer A.G.

Retilox* F.40 is the α - α' bis-ter-butyl peroxide of m-p di-iso propyl-benzene (40% active), supplied by Joseph Weil & Co., Ltd., (Montecatini).

* Trade Marks.

Cross-linkable polyethylene compounds sold by Bakelite-Xylonite Ltd., under the designations HFDG 4360 and DPN 227 were used for insulation and screen respectively.

In the moulding of the sheets, aluminium foils were inserted in place of part of the intermediate layer to provide un-bonded gripping areas, and the peel strength was measured by a method substantially in accordance with British Standard 903 Part 31:1950 using an

Instron (Trade Mark) Universal testing machine with a grip separation rate of 50 mm/minute. The load was continuously recorded and average (for each of several samples) was determined using a planimeter. Results were as shown in the following table:

Outer Layers	EPR Compounds A & B		Bakelite* HFDG 4360 and DPN 227	
Compound No. (Intermediate Layer)	Peel Strength (N)		Peel Strength (N)	
	23°C	80°C	23°C	80°C
1	22.0	1.8	69.2	6.0
2	20.6	1.7	66.4	6.5
3	71.4	4.4	112.8	9.3
4	56.9	10.5	79.0	7.3
5	114.8	14.7	138.8	21.6
6	111.0	38.3	134.9	19.4
7	114.4	21.7	147.6	23.8
8	107.5	25.0	138.3	16.9

* trade mark.

The tests with the samples at 80°C showed a permanent bond between the intermediate layer and the dielectric layer and between the intermediate layer and the semi-conductive layer with a reduction in the cohesive strength of the intermediate layers of the composite sheets to about 10—35% of the value at 23°C.

The invention is further illustrated by a description, by way of example, of a preferred method of forming a cable core of the present invention with reference to the accompanying drawing which illustrates diagrammatically the apparatus employed.

In using the apparatus shown in the drawing to form a cable core a conductor C is passed through a dual extrusion head 1 where a layer of semi-conducting ethylene/propylene rubber based compound of radial thickness 1 mm and a layer of insulating ethylene/propylene rubber based compound of radial thickness 5 mm are extruded simultaneously on to the conductor and are subsequently cured by passing through a treatment chamber 2. After passing through an in-line scanner 3 which locates any voids in the core dielectric the covered conductor passes through an extruder 4 which applies a thin intermediate layer of the insulating material specified above as Compound No. 7, the intermediate layer having a radial thickness of 0.1 mm. The covered conductor subsequently passes through an extruder

5 which applies a layer of semi-conductive ethylene/propylene rubber based compound to a radial thickness of 1 mm, the dielectric screen so formed being cured by passage through a treatment chamber 6; because of diffusion effects, the intermediate layer is also at least partially cured by this treatment.

In cases where in-line scanning is not required, the first curing step in treatment chamber 2 can usually be omitted, all layers being cured in the chamber 6, and this may significantly reduce expense.

The intermediate layer is bonded both to the dielectric and to the dielectric screen, the strengths of the bonds being substantially greater than the cohesive strength of at least a substantially central peripherally continuous zone of the intermediate layer.

WHAT WE CLAIM IS:—

1. A cable core comprising a conductor having an extruded dielectric of rubber or plastics material, a dielectric screen comprising a layer of conductive or semi-conductive rubber or plastics material and interposed between and bonded to the extruded dielectric and the dielectric screen throughout substantially the whole length of the core, an intermediate layer of rubber or plastics insulating material, the intermediate layer having throughout the layer or at least in a circumferentially continuous

In the moulding of the sheets, aluminium foils were inserted in place of part of the intermediate layer to provide un-bonded gripping areas, and the peel strength was measured by a method substantially in accordance with British Standard 903 Part 31:1950 using an

Instron (Trade Mark) Universal testing machine with a grip separation rate of 50 mm/minute. The load was continuously recorded and average (for each of several samples) was determined using a planimeter. Results were as shown in the following table:

Outer Layers	EPR Compounds A & B		Bakelite* HFDG 4360 and DPN 227	
Compound No. (Intermediate Layer)	Peel Strength (N)		Peel Strength (N)	
	23°C	80°C	23°C	80°C
1	22.0	1.8	69.2	6.0
2	20.6	1.7	66.4	6.5
3	71.4	4.4	112.8	9.3
4	56.9	10.5	79.0	7.3
5	114.8	14.7	138.8	21.6
6	111.0	38.3	134.9	19.4
7	114.4	21.7	147.6	23.8
8	107.5	25.0	138.3	16.9

* trade mark.

The tests with the samples at 80°C showed a permanent bond between the intermediate layer and the dielectric layer and between the intermediate layer and the semi-conductive layer with a reduction in the cohesive strength of the intermediate layers of the composite sheets to about 10—35% of the value at 23°C.

The invention is further illustrated by a description, by way of example, of a preferred method of forming a cable core of the present invention with reference to the accompanying drawing which illustrates diagrammatically the apparatus employed.

In using the apparatus shown in the drawing to form a cable core a conductor C is passed through a dual extrusion head 1 where a layer of semi-conducting ethylene/propylene rubber based compound of radial thickness 1 mm and a layer of insulating ethylene/propylene rubber based compound of radial thickness 5 mm are extruded simultaneously on to the conductor and are subsequently cured by passing through a treatment chamber 2. After passing through an in-line scanner 3 which locates any voids in the core dielectric the covered conductor passes through an extruder 4 which applies a thin intermediate layer of the insulating material specified above as Compound No. 7, the intermediate layer having a radial thickness of 0.1 mm. The covered conductor subsequently passes through an extruder

5 which applies a layer of semi-conductive ethylene/propylene rubber based compound to a radial thickness of 1 mm, the dielectric screen so formed being cured by passage through a treatment chamber 6; because of diffusion effects, the intermediate layer is also at least partially cured by this treatment.

In cases where in-line scanning is not required, the first curing step in treatment chamber 2 can usually be omitted, all layers being cured in the chamber 6, and this may significantly reduce expense.

The intermediate layer is bonded both to the dielectric and to the dielectric screen, the strengths of the bonds being substantially greater than the cohesive strength of at least a substantially central peripherally continuous zone of the intermediate layer.

WHAT WE CLAIM IS:—

1. A cable core comprising a conductor having an extruded dielectric of rubber or plastics material, a dielectric screen comprising a layer of conductive or semi-conductive rubber or plastics material and interposed between and bonded to the extruded dielectric and the dielectric screen throughout substantially the whole length of the core, an intermediate layer of rubber or plastics insulating material, the intermediate layer having throughout the layer or at least in a circumferentially continuous





zone of the layer a cohesive strength substantially less than the cohesive strengths of the extruded dielectric and the dielectric screen and substantially less than the strengths of the bonds between the intermediate layer and the extruded dielectric and between the intermediate layer and the dielectric screen such that when stripping the dielectric screen from the core over a part of its length for jointing or terminating purposes separation takes place within the intermediate layer to leave a portion of the intermediate layer on the extruded dielectric.

2. A cable core comprising a conductor having an extruded dielectric of rubber or plastics material, a dielectric screen comprising a layer of conductive or semi-conductive rubber or plastics material and, interposed between and bonded to the extruded dielectric and the dielectric screen throughout substantially the whole length of the core, an intermediate extruded layer of rubber or plastics insulating material, the intermediate extruded layer having throughout the layer or at least in a circumferentially continuous zone of the layer a cohesive strength substantially less than the cohesive strengths of the extruded dielectric and the dielectric screen and substantially less than the strengths of the bonds between the intermediate extruded layer and the extruded dielectric and between the intermediate extruded layer and the dielectric screen such that when stripping the dielectric screen from the core over a part of its length for jointing or terminating purposes separation takes place within the intermediate layer to leave a portion of the intermediate layer on the extruded dielectric.

3. A cable core comprising a conductor having an extruded dielectric of rubber or plastics material, a dielectric screen comprising a layer of conductive or semi-conductive rubber or plastics material and, interposed between and bonded to the extruded dielectric and the dielectric screen throughout substantially the whole length of the core, an intermediate extruded layer of rubber or plastics insulating material, the intermediate extruded layer having a thickness in the range from $1/2$ to $1/20$ of the thickness of the dielectric screen and having throughout the layer or at least in a circumferentially continuous zone of the layer a cohesive strength substantially less than the cohesive strengths of the extruded dielectric and the dielectric screen and substantially less than the strengths of the bonds between the intermediate extruded layer and the extruded dielectric and between the intermediate extruded layer and the dielectric screen such that when stripping the dielectric screen from the core over a part of its length for jointing or terminating purposes separation takes place within the intermediate layer to leave a portion of the intermediate layer on the extruded dielectric.

4. A cable core as claimed in any one of the preceding claims in which the extruded dielectric and the dielectric screen are based on ethylene/propylene rubber.

5. A cable core as claimed in any one of Claims 1 to 3 in which the extruded dielectric and the dielectric screen are based on cross-linked polyethylene.

6. A cable core as claimed in any of the preceding claims in which the said intermediate layer is of an ethylene/propylene rubber based compound.

7. A cable core as claimed in Claim 6 in which the said compound includes an ethylene/vinyl acetate copolymer.

8. A cable core as claimed in Claim 6 or Claim 7 in which the said compound includes a filler.

9. A cable core as claimed in any one of the preceding claims in which the intermediate layer has a cohesive strength in the range from about 5% to 70% of the cohesive strength of whichever of the dielectric and the dielectric screen is the weaker.

10. A cable core as claimed in any one of the preceding claims in which the intermediate layer has a cohesive strength in the range from about 5% to 50% of the cohesive strength of whichever of the dielectric and the dielectric screen is the weaker.

11. A cable core as claimed in Claim 8 in which the said compound has substantially the composition hereinbefore described by way of example as Compound No. 7.

12. A cable core as claimed in Claim 7 or Claim 8 in which the said compound has substantially the composition hereinbefore described by way of example as any one of Compounds Nos. 1 to 6 or 8.

13. A cable core as claimed in Claim 4 or in any one of Claims 6 to 8, 11 or 12 when appendent thereto in which the dielectric and the dielectric screens have compositions substantially as hereinbefore described as Compound A and Compound B respectively.

14. A cable core substantially as hereinbefore described with reference to and as illustrated by the examples considered collectively.

15. An electric power cable including at least one core as claimed in any one of claims 1 to 11 and at least a surrounding protective sheath.

16. An electric power cable including at least one core as claimed in any one of Claims 12 to 14 and at least a surrounding protective sheath.

17. A method of forming a cable core comprising extruding a layer of rubber or plastics insulating material onto a travelling conductor, which may or may not have a conductor screen applied thereto, to form the core dielectric; applying an intermediate layer of rubber or plastics insulating material to the outer surface of the core dielectric in such a way that the intermediate layer bonds to or can be

subsequently bonded to the core dielectric; and applying a layer of conductive or semi-conductive rubber or plastics material to the outer surface of the intermediate layer in such a way that the dielectric screen so formed bonds to, or can be subsequently bonded to, the intermediate layer, the strengths of the bonds between the intermediate layer and the core dielectric and between the intermediate layer and the dielectric screen being substantially greater than the cohesive strength of the intermediate layer throughout the layer or at least in a circumferentially continuous zone of the layer, and the intermediate layer having, in the final product, a cohesive strength less than the cohesive strengths of the core dielectric and of the dielectric screen.

18. A method of forming a cable core comprising extruding a layer of rubber or plastics insulating material onto a travelling conductor, which may or may not have a conductor screen applied thereto, to form the core dielectric; extruding an intermediate layer of rubber or plastics insulating material onto the outer surface of the core dielectric in such a way that the intermediate layer bonds to the core dielectric; and extruding a layer of conductive or semi-conductive rubber or plastics material onto the outer surface of the intermediate layer in such a way that the dielectric screen so formed bonds to the intermediate layer, the strengths of the bonds between the intermediate layer and the core dielectric and between the intermediate layer and the dielectric screen being substantially greater than the cohesive strength of the intermediate layer throughout the layer or at least in a circumferentially continuous zone of the layer and the intermediate layer having, in the final product, a cohesive strength less than the cohesive strengths of the core dielectric and of the dielectric screen.

19. A method of forming a cable core comprising extruding a conductor screen onto a travelling conductor; extruding a layer of rubber or plastics insulating material onto it to form the core dielectric; extruding an intermediate layer of rubber or plastics insulating material onto the outer surface of the core dielectric in such a way that the intermediate layer bonds to the core dielectric; and extruding a layer of conductive or semi-conductive

rubber or plastics material onto the outer surface of the intermediate layer in such a way that the dielectric screen so formed bonds to the intermediate layer, the strengths of the bonds between the intermediate layer and the core dielectric and between the intermediate layer and the dielectric screen being substantially greater than the cohesive strength of the intermediate layer throughout the layer or at least in a circumferentially continuous zone of the layer and the intermediate layer having, in the final product, a cohesive strength less than the cohesive strengths of the core dielectric and of the dielectric screen.

20. A method as claimed in Claim 18 in which the conductor screen and core dielectric are extruded simultaneously in the same extrusion head.

21. A method as claimed in any one of Claims 18—20 in which the intermediate layer and the dielectric screen are extruded while the core dielectric and the intermediate layer respectively are still hot by a simultaneous in-line extrusion process.

22. A method as claimed in any one of claims 17—21 in which the intermediate layer is compounded without curing agents but becomes at least partially cured as a result of diffusion effects.

23. A method as claimed in any one of Claims 17—22 in which the intermediate layer has, in the final product, a cohesive strength in the range from about 5% to about 70% of the cohesive strength of whichever of the dielectric and the dielectric screen is the weaker.

24. A method as claimed in any one of Claims 17—22 in which the intermediate layer has, in the final product, a cohesive strength in the range from about 5% to about 50% of the cohesive strength of whichever of the dielectric and the dielectric screen is the weaker.

25. A method of making an electric cable core substantially and hereinbefore described with reference to the accompanying drawings.

26. An electric cable core made by the method claimed in any one of Claims 17—25.

R. F. TARBOX,
Agent for the Applicants,
38 Wood Lane,
London, W12 7DX.

