CLAIMS

1. A decorative board comprising:

a core layer including:

a fibrous base material;

a thermoplastic resin, and

an endothermic metal hydroxide;

an intermediate layer including:

a mixed paper containing 55-85% by weight of an endothermic metal hydroxide; and

a thermosetting resin;

a decorative layer including:

a decorative paper; and

a thermosetting resin,

the decorative board comprising a stack of the core layer, the intermediate layer, and the decorative layer stacked in this order,

wherein an amount of the thermoplastic resin included in the core layer is 29.38-100g/m^2.

2. The decorative board according to claim 1, wherein the endothermic metal hydroxide in the core layer or in the intermediate layer is an aluminum hydroxide or a magnesium hydroxide.

3. The decorative board according to claim 1 or 2, wherein the thermoplastic resin in the core layer is an acrylic resin emulsion.

4. The decorative board according to any one of claims 1 to 3, wherein the core layer includes a silane coupling agent.

5. The decorative board according to any one of claims 1 to 4, wherein the core layer includes a flame retardant.

6. The decorative board according to claim 5, wherein the core layer includes the flame retardant of 1-100g/m^2.

7. The decorative board according to claim 5 or 6, wherein the flame retardant is a nitrogen flame retardant or a phosphorus-nitrogen flame retardant.

8. The decorative board according to claim 7, wherein a phosphorus content of the phosphorus-nitrogen flame retardant is 1-30% by weight and a nitrogen content of the phosphorus-nitrogen flame retardant is 5-35% by weight.