

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
10 March 2005 (10.03.2005)

PCT

(10) International Publication Number
WO 2005/021847 A1

(51) International Patent Classification⁷: **D01F 6/70**

(21) International Application Number:
PCT/KR2004/002031

(22) International Filing Date: 13 August 2004 (13.08.2004)

(25) Filing Language: Korean

(26) Publication Language: English

(30) Priority Data:
10-2003-0060810
1 September 2003 (01.09.2003) KR

(71) Applicant (for all designated States except US):
HYOSUNG CORPORATION [KR/KR]; 450, Kong-
duk-Dong, Mapo-Gu, Seoul 121-020 (KR).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **KANG, Yeon, Soo**
[KR/KR]; 105-108, Woosung Apt., 85, Bakdal-Dong,
Manan-Gu, Anyang-Si, Gyeonggi-Do 430-030 (KR). **JIN,**
Joong, Seong [KR/KR]; 220, Hyosung Dormitory, 913-2,
Hogye-Dong, Dongan-Gu, Anyang-Si, Gyeonggi-Do
431-080 (KR). **SEO, Seung, Won** [KR/KR]; 991-2102,
Baekdoo Hanyang Apt., Sanbon-Dong, Gunpo-Si,
Gyeonggi-Do 435-040 (KR). **KWON, Ik, Hyeon**
[KR/KR]; 202-1304, Eunhaeng 2-cha Chunggu Apt., 548,
Daeya-Dong, Siheung-Si, Gyeonggi-Do 429-717 (KR).

(74) Agents: **KIM, Hak, Je** et al.; Phoenix International, Patent
and Law Office, Kwangwhamoon P.O. Box 1828, Seoul
110-618 (KR).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG,
MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH,
PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN,
TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI,
SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: PROCESS FOR PREPARING ELASTIC FIBER HAVING HIGH MODULUS, ALKALI-RESISTANCE AND HEAT-
RESISTANCE

(57) Abstract: Disclosed herein is a process for preparing an elastic fiber having a high modulus and superior resistance to alkali and heat. The process comprises the steps of adding 1~20% by weight of a cellulose acetate to a polyurethane or polyurethaneurea solution, based on the total weight of the polyurethane or polyurethaneurea, homogeneously stirring the mixture to obtain a spinning solution, and ripening and spinning the solution. According to the process, a high modulus and highly heat resistant elastic fiber can be prepared without a sudden change in conditions for preparation of the polymer.



WO 2005/021847 A1