

DIFFUSION BOND MIXTURE FOR HEALING SINGLE CRYSTAL ALLOYS

FIELD OF INVENTION

5 **[0001]** This invention relates to a composition and method for the repair of gas turbine engine components and, more particularly, to a diffusion bond paint mixture and thermal cycle for diffusion bond healing single crystal nickel-base superalloy articles.

BACKGROUND

10 **[0002]** Nickel-base superalloys are used in gas turbine engine components because of their superior creep strength properties in high temperature operating conditions. While such single-crystal superalloys represent a substantial improvement over other prior known nickel-base superalloys that do not have a
15 directionally oriented microstructure, they represent a compromise with respect to environmental attack during use, particularly to hot corrosion caused by oxidation and sulfidation. Further, despite the increased strength, single-crystal alloys are susceptible to cracks or other types of damage or deterioration that can occur from such experiences from thermal cycling or airborne object impact, or their
20 combinations. Also, discontinuities such as shrinkage, inclusions and cracks can occur during the manufacture of such components. Because of the relatively high cost of such components, it is sometimes desirable to repair rather than to replace them. However, superalloy components, once damaged, can tend to fail repeatedly in the same region, making it critical that any repairs made have mechanical,
25 environmental, and processing properties equivalent to or better than the original superalloy base metal.

30 **[0003]** Methods are known in the art to repair certain nickel-base superalloys, such as wide-gap brazing or transient-liquid phase processes. These processes involve cleaning the turbine engine component, applying a compatible diffusion bond mixture having a melting temperature lower than that of the substrate, and

heating the article to melt the diffusion bond mixture without causing thermal damage to the substrate. Most of these processes are used on equiaxed alloys, but it has been found to be more difficult to repair single-crystal alloys because introduction of impurities to the unicrystal can create points of weakness.

- 5 **[0004]** Repair diffusion bond mixtures have been formulated to include substantial amounts of melting point depressants, primarily silicon and boron, so that the diffusion bond mixture can be applied at temperatures that are sufficiently high to melt the mixture, but not high enough to melt the substrate and cause thermal damage to the substrate. Because the amount of melting point depressants
- 10 is so high, however, the diffusion bond mixture may differ significantly in composition from the substrate and the repaired area may not have the same properties as the adjacent substrate, increasing the risk of failure at the repaired area. In particular, undesirable large blocky or script-like brittle phases composed of chromium, titanium, and the family of refractory elements (e.g., tungsten,
- 15 tantalum) combined with the melting point depressants grow in the eutectic that forms between the substrate and the diffusion bond mixture. These brittle phases may weaken the repair composite. It should be appreciated, however, that conventional repairs generally result in safe end products when properly used.
- 20 **[0005]** Therefore, there is a need for a composition and method that minimizes the amount of diffusion bond mixture alloy applied to the part, and therefore the amount of boron. There is also need for a composition and method that minimizes eutectic brittle borides common to wide gap brazing processes and a composition and method to repair superalloy substrates that results in a repaired area that has properties very similar to the substrate.

25

SUMMARY OF THE INVENTION

- 26 **[0006]** The present invention is diffusion bond mixture paint used to repair single-crystal superalloy articles which minimizes the amount of diffusion bond mixture alloy applied to the article. The paint has of a two-alloy powder mixture, a
- 30 binder, and a carrier which also serves to thin the paint. The powder mixture has a

higher-melting temperature powder and a lower-melting temperature powder that cooperate to let the diffusion bond mixture melt and flow into the cracks, then allows the melting point depressants to diffuse into the substrate, and the resulting higher-melting temperature components to harden. The diffusion bond mixture paint is applied to a clean superalloy article and the article is heated through a three-step thermal cycle. The thermal cycle allows the paint to melt and flow into the damaged areas, then cool to wait for thermocouple stabilization and diffuse into the substrate. Other independent features and advantages of the preferred mixture composition and method will become apparent from the following detailed description, taken in conjunction with the accompanying drawings which illustrate, by way of example, the principles of the invention.

DETAILED DESCRIPTION OF THE INVENTION

[0007] The present invention is embodied in a diffusion bond mixture paint having a two-alloy powder mixture, a binder, and a carrier. Table 1 summarizes the composition of the diffusion bond mixture paint, wherein the powder mixture is combined with about 10% binder and about 5-20% carrier, by weight percentage. Example 1 illustrates a paint wherein 100 grams of the powder mixture is mixed with 10 grams of binder and 5 grams of carrier. Example 2 illustrates a paint wherein 100 grams of the powder mixture is mixed with 10 grams of binder and 20 grams of carrier.

TABLE 1

Composition of the Diffusion bond mixture Paint

Component	Relative Quantity (wt%)	Example 1	Example 2
Powder mixture	100	100 grams	100 grams
Binder	5-15	10 grams	10 grams
Carrier	5-20	5 grams	20 grams

[0008] The powder mixture contains a higher-melting temperature alloy powder and a lower-melting temperature alloy powder. In combination the two powders

define a homogenous powder system. The high-melt alloy powder, which has superior hot corrosion resistance along with good oxidation resistance and mechanical properties, is further characterized by the substantial absence of melting point depressant elements such as Si or B. The low-melt alloy powder, in contrast, contains melting point depressant elements Si, B, or both. In practice, the powders may also contain incidental impurities. The preferred high-melt alloys are MAR-M 247 and MAR-M 509. The preferred low-melt alloys are M3877 and MAR-M 509B. Table 2 lists the preferred powders and the amounts of each constituent component of each powder, by weight percentage.

TABLE 2

Powder Alloy Compositions
by wt %

	Higher Melting Point Components			Lower Melting Point Components	
	MAR-M 247	MAR-M 509		M3877	MAR-M 509B
Ni	60	10		82.1	10
W	10	7		-	7
Co	10	55		-	51.5
Cr	8.3	23.5		15.0	23.4
Al	5.5	-		-	-
Ti	1	0.2		-	0.2
Ta	3	3.5		-	3.5
Zr	0.1	0.5		-	0.5
Mo	0.7	-		-	-
C	0.1	0.6		-	0.6
Fe	-	-		-	-
Hf	1.5	-		-	-
B	0	0		3.5	2.9
Si	0	0		0	0.4

[0009] The preferred powders are combined in preferred ratios as shown in Table 3. The first preferred powder mixture, known by the brand name JetFix E, is a combination of about 49-51% MAR-M 247 and 49-51% M3877. The second preferred powder mixture, known by the brand name JetFix G, is a combination of about 59-61% MAR-M 247 and 39-41% M3877. The third preferred powder mixture, known by the brand name JetFix 555, is a combination of about 49-51% MAR-M 509 and 49-51% MAR-M 509B. The paints made from these powder mixtures have been used to repair MAR-M509 shrouds and CMSX-3 airfoils, among other gas turbine engine components.

TABLE 3
Preferred Ratios of Alloy Powders

	Higher Melting Point		Lower Melting Point	
	Components		Components	
	MAR-M 247	MAR-M 509	M3877	MAR-M 509B
JetFix E	49-51%	-	49-51%	-
JetFix G	59-61%	-	39-41%	-
JetFix 555	-	49-51%	-	49-51%

[0010] The powder mixtures are mixed with a binder and a carrier. The binder is preferably AB215, a non-fibrous binder known in the art, which is commercially available from Metal Methods, Inc., Frankfurt, Kentucky. The carrier is typically an alcohol that evaporates at a temperature below the melting point of the powder mixture, such as ethyl alcohol or acetone, and is preferably isopropanol. A purpose of the carrier is to thin, or reduce the viscosity, of the paint. This enables a very thin layer of paint to be applied to the substrate so as to reduce the amount of borides applied to the crack, thereby minimizing the eutectic brittle borides that may form. Ideally just enough of the paint is applied to supply the appropriate

amount of the powder mixture to heal the crack, but no more, thus reducing the brittle borides to a minimum. The resultant composition is a diffusion bond mixture paint that is applied to the superalloy articles with a paintbrush or sprayer.

[0011] To repair the damaged substrate, the articles are first prepared for repair
5 by a process known in the art. The articles are stripped of all the aluminide coating by acid stripping. Cracks are identified with visual inspection using a magnifier. Cracks greater than about 0.02" are closed and physically restrained with a clamp. Cracks are then welded together using spot welds. After the initial preparation, the cracks are then cleaned with a fluoride-ion cleaning process, which is also known
10 in the art. Pursuant to the present invention, the selected diffusion bond mixture paint is applied to the crack with a paint brush or sprayer in a thin layer, thereby limiting the amount of borides applied to the article. The article is then placed in a vacuum and heated at $2200^{\circ}\text{F} \pm 15^{\circ}\text{F}$ for 10-20 minutes to let the diffusion bond mixture melt and flow into the cracks. The article is then cooled to a minimum of
15 $1500^{\circ}\text{F} \pm 15^{\circ}\text{F}$ until thermocouple stabilization occurs. The article is then reheated at $2200^{\circ}\text{F} \pm 15^{\circ}\text{F}$ for 4 hours and 15 minutes ± 15 minutes to allow the melting point depressants to diffuse into the substrate. This diffusion results in a stronger repair that is less susceptible to incipient melting when the part is returned to service. The three-step thermal cycle allows the paint to melt and flow
20 into the damaged areas, then provides for thermocouple stabilization and finally diffusion into the substrate.

[0012] While what has been described is considered to be the best mode contemplated for carrying out the present invention and its preferred
embodiments, it will be understood by those skilled in the art that various changes
25 and modifications may be made, and equivalents may be substituted for elements thereof without departing from the true scope of the invention. Therefore, it is intended that this invention not be limited to the particular embodiments disclosed but that the invention will include all embodiments falling within the scope of the appended claims.

CLAIMS

I claim:

1. A diffusion bond mixture comprising:
 - a) an alloy powder mixture comprising:
 - 5 i) a first alloy powder having a first melting temperature, wherein the first alloy powder consists essentially of, by weight, 10% W, 10% Co, 8.3% Cr, 5.5% Al, 1.0% Ti, 3.0% Ta, 1.5% Hf, 0.1% Zr, 0.70% Mo, 0.1% C with the balance consisting of Ni and incidental impurities; and
 - 10 ii) a second alloy powder having a second melting temperature lower than the melting temperature of the first alloy powder and wherein the second alloy powder consists essentially of, by weight, about 15% Cr, 2.9% B and with the balance consisting of Ni and incidental impurities; and
 - 15 b) a binder; and
 - c) a carrier.
2. The mixture of claim 1 wherein:
the alloy powder mixture is, by weight percent, 49-51% of the first alloy
20 powder and 49-51% of the second alloy powder.
3. The mixture of claim 1 wherein:
the alloy powder mixture is, by weight percent, 59-61% of the first alloy
powder and 39-41% of the second alloy powder.
25
4. The mixture of claim 1 wherein:
 - a) the first alloy powder consists essentially of, by weight, 7% W, 10% Ni, 23.5% Cr, 0.2% Ti, 3.5% Ta, 0.35% Zr, and 0.6% C, with the balance consisting of Co and incidental impurities;

- b) the second alloy powder consists essentially of, by weight, 7% W, 10% Ni, 23.5% Cr, 0.2% Ti, 3.5% Ta, 0.35% Zr, 0.6% C, and 2.9% B with the balance consisting of Co and incidental impurities; and
- c) the alloy powder mixture is, by weight percent, 59-61% of the first alloy powder and 39-41% of the second alloy powder.

5. A method for repairing damage on an article having a superalloy substrate comprising the steps of:

- a) cleaning a damaged area with fluoride ion cleaning process;
- b) applying a diffusion bond mixture containing one or more melting point depressant to the to damaged area;
- c) heating the at least the area to be repaired in a vacuum to a temperature and for a time sufficient for the mixture to flow into the damaged area but low enough that the substrate is not damaged;
- d) cooling at least the area to be repaired until it has reached thermocouple stabilization; and
- e) heating the area to be repaired to diffuse one or more melting point depressants into the substrate.

6. The method of claim 5 wherein the diffusion bond mixture comprises:
- a) an alloy powder mixture comprising:
- i) a first alloy powder having a first melting temperature, wherein the first alloy powder consists essentially of, by weight, 10% W, 10% Co, 8.3% Cr, 5.5% Al, 1.0% Ti, 3.0% Ta, 1.5% Hf, 0.1% Zr, 0.70% Mo, 0.1% C with the balance consisting of Ni and incidental impurities; and

- 5 ii) a second alloy powder having a second melting temperature lower than the melting temperature of the first alloy powder and wherein the second alloy powder consists essentially of, by weight, about 15% Cr, 2.9% B and with the balance consisting of Ni and incidental impurities; and
- b) a binder; and
- c) a carrier.

7. The method according to claim 6 wherein the alloy powder mixture is,
10 by weight percent, 49-51% of the first alloy powder and 49-51% of the second alloy powder.

8. The method according to claim 6 wherein the alloy powder mixture is,
by weight percent, 59-61% of the first alloy powder and 39-41% of the second
15 alloy powder.

9. The method of claim 5 wherein the diffusion bond mixture comprises:
- a) an alloy powder mixture comprising:
- 20 i) a first alloy powder consists essentially of, by weight, 7% W, 10% Ni, 23.5% Cr, 0.2% Ti, 3.5% Ta, 0.35% Zr, and 0.6% C, with the balance consisting of Co and incidental impurities;
- ii) a second alloy powder consists essentially of, by weight, 7% W, 10% Ni, 23.5% Cr, 0.2% Ti, 3.5% Ta, 0.35% Zr, 0.6% C, and 2.9% B with the balance consisting of Co and incidental
25 impurities; wherein the alloy powder mixture is, by weight percent, 59-61% of the first alloy powder and 39-41% of the second alloy powder;
- b) a binder; and
- c) a carrier.

10. The method of claim 5 wherein:

a) the temperature and time of step (c) are $2200^{\circ}\text{F} \pm 15^{\circ}\text{F}$ for 10-20 minutes;

b) the temperature of step (d) is $1500^{\circ}\text{F} \pm 15^{\circ}\text{F}$; and

5 c) the temperature and time of step (e) are $2200^{\circ}\text{F} \pm 15^{\circ}\text{F}$ for 4 hours and 15 minutes ± 15 minutes.