

**Device for the Double-Sided Processing of Flat Workpieces and
Method for the Simultaneous Double-Sided Material Removal
Processing of a Plurality of Semiconductor Wafers**

- 5 The invention relates to a device for the double-sided processing of flat workpieces, comprising an upper working disc and a lower working disc, wherein at least one of the working discs can be driven in rotary fashion by means of a drive, and wherein the working discs form between themselves a working
10 gap, in which is arranged at least one carrier disc with at least one cutout for at least one workpiece to be processed, wherein the at least one carrier disc has teeth on its circumference, by means of which teeth it rolls on an inner and an outer gear wheel or pin ring if at least one of the gear
15 wheels or pin rings is set in rotation, wherein the gear wheels or pin rings each have a multiplicity of gear or pin arrangements with which the teeth of the carrier discs enter into engagement during rolling.
- 20 With devices of this type, flat workpieces, for example semiconductor wafers, can be subjected to material removal processing, for example honing, lapping, polishing or grinding. For this purpose, the workpieces are held in floating fashion in cutouts in carrier discs guided in rotary fashion in the
25 working gap and are simultaneously processed on both sides. In this case, the workpieces describe a cycloid movement in the working gap. With such devices, flat workpieces can be processed on both sides in a highly precise manner.
- 30 The contact between the outer teeth of the carrier discs and the teeth of the gear wheels or the pins of the pin rings results in wear on the gears or pins. It is therefore known from DE 295 20 741 U1, for pin rings, to mount sleeves in rotatable fashion on the pins of the pin rings, wherein the
35 carrier discs come into engagement with the sleeves. In the case of an embodiment of this type, frictional stress no longer

occurs between the carrier disc teeth and the pins. Rather, such contact takes place between the sleeve and the pin. However, since the sleeve bears on the pin over a much greater length, the surface loading and hence the possible abrasion are correspondingly lower. Furthermore, the sleeves can be replaced in a simple manner in the event of wear. By contrast, replacing the pins is comparatively complicated. Further configurations of such sleeves have been disclosed by DE 101 59 848 B1 and DE 102 18 483 B4. EP 0 787 562 B1 discloses sleeves composed of a plastic material.

In the case of the known devices, one problem is that the loading of the carrier discs on account of contact with the gears or pins and sleeves can lead to the teeth of the carrier disc being bent away upward or downward, which regularly leads to damage to the workpieces and also the working discs or their working layers. On account of the low strength, this is particularly critical in the case of plastic carrier discs that are otherwise desired. Moreover, premature wear of the carrier discs can occur in the case of the known devices. This is because the carrier disc partially leaves the working gap, in particular in the region of the gear wheels or pin rings, which can perform undesirable vertical movements owing to the lack of guidance there by the working gap. When this part of the carrier disc reenters the working gap, said movements lead to undesirable contact between the carrier disc surface and the edge of the working discs or their working layer, as a result of which intensified wearing of the carrier disc surface occurs.

The present invention also relates to a method for the simultaneous double-sided material removal processing of a plurality of semiconductor wafers, in which each semiconductor wafer lies freely mobile in a recess of one of a plurality of carrier discs set in rotation by means of an annular outer wheel or pin ring and an annular inner gear wheel or pin ring

and thereby moved on a cycloid path curve, while the semiconductor wafers are processed so as to remove material between two rotating annular working discs, and the carrier discs and/or semiconductor wafers temporarily leave the working
5 gap, delimited by the working discs, with a part of their surface during the processing.

For electronics, microelectronics and micro-electromechanics, semiconductor wafers with extreme requirements for global and
10 local planarity, one-side referenced local planarity (nanotopology), roughness and cleanness are used as starting materials (substrates). Semiconductor wafers are wafers of semiconductor materials, in particular compound semiconductors such as gallium arsenide or elementary semiconductors such as
15 silicon and germanium.

According to the prior art, semiconductor wafers are produced in a multiplicity of successive process steps. In general, the following production sequence is used:

- 20
- production of a monocrystalline semiconductor rod (crystal growth),
 - cutting the rod into individual wafers (internal hole or wire
25 sawing),
 - mechanical wafer preparation (lapping, grinding),
 - chemical wafer preparation (alkaline or acid etching)
 - 30 - chemo-mechanical wafer preparation: double-sided polishing (DSP) = stock polishing, single-sided haze-free or mirror polishing with a soft polishing pad (CMP)
 - 35 - optionally further coating steps (for example epitaxy, annealing)

Mechanical processing of the semiconductor wafers serves primarily for global planarization of the semiconductor wafer, also thickness calibration of the semiconductor wafers as well
5 as removal of the crystalline-damaged surface layer and of processing traces (sawing cuts, incision marks) caused by the previous cutting process.

Methods known in the prior art for mechanical wafer preparation
10 are single-sided grinding (SSG) with a cup grinding disc which contains a bound grinding agent, simultaneous grinding of both sides of the semiconductor wafer together between two cup grinding discs ("double-disc grinding", DDG) and lapping both
15 sides of a plurality of semiconductor wafers simultaneously between two annular working discs while supplying a slurry of free grinding agent (double-sided plane-parallel lapping, "lapping").

DE 103 44 602 A1 and DE 10 2006 032 455 A1 disclose methods for
20 simultaneously grinding both sides of a plurality of semiconductor wafers together with a movement process similar to that of lapping, but characterized by the use of a grinding agent which is bound firmly in working layers ("films", "pads") which are applied onto the working discs. Such a method is
25 referred to as "fine grinding with lapping kinematics" or "planetary pad grinding" (PPG).

Working layers used in PPG, which are adhesively bonded onto the two working discs, are described for example in US
6,007,407 A and US 6,599,177 B2. During the processing, the
30 semiconductor wafers are placed into thin guide cages, so-called carrier discs, which have corresponding openings for receiving the semiconductor wafers. The carrier discs have outer teeth, which engage in a rolling device comprising an inner and outer gear wheel and are moved by means of it in the
35 working gap formed between the upper and lower working discs.

The ability to carry out the PPG method is crucially determined by the properties of the carrier discs and their guiding during the rolling movement.

5

The semiconductor wafers must temporarily leave the working gap with a part of their surface during the processing. This temporary projection of a part of the area of the workpieces from the working gap will be referred to as the "workpiece excursion". The latter ensures that all regions of the tool are used uniformly and experience uniform wear which preserves the shape, and the desired plane-parallel shape is imparted to their semiconductor wafers without "balling" (thickness reduction toward the margin of the semiconductor wafer). The same applies similarly for lapping with a free lapping abrasive.

The methods of PPG grinding known in the prior art, for example described in DE 103 44 602 A1 and in DE 10 2006 032 455 A1, are however disadvantageous in this regard. With the methods known from the prior art, it is not possible to provide semiconductor wafers with sufficient planarity as far as the outermost marginal region, which are suitable for particularly demanding applications and future technology generations.

25

Specifically, it has been found that the carrier discs are susceptible to vertical dislocation from their central position until they disengage from the rolling device owing to strong bending. This is to be expected in particular when high or strongly alternating process forces act on the carrier discs as in the case of high removal rates, unfavorably selected process kinematics or when using particularly fine abrasives in the grinding pad.

The dislocation of the carrier discs is promoted because they have only a small total thickness (at most slightly greater

than the final thickness of the semiconductor wafers to be processed) and thus have only a limited strength against bending. Furthermore, the carrier disc is conventionally made of a steel core which is provided with a protective layer.

5 Direct contact of the steel core and the abrasive preferably used in PPG, i.e. diamond, leads to wear of the microedges of the diamond grains owing to the high solubility of carbon in iron, and therefore rapid loss of the cutting acuity of the working layers being used.

10

Frequent sharpening associated with high wear of the working layers, with the concomitant unstable process management, would also compromise the properties of the semiconductor wafers thereby processed and therefore make the use of PPG methods not
15 only uneconomical, but possibly even unviable for future technology generations.

As is known, the protective layers applied onto the steel core of the carrier disc experience wear. They should therefore have
20 a usable thickness which is as large as possible, in order to allow economical lifetimes of the consumable constituted by the "carrier disc". The protective layers are furthermore required in order to achieve low sliding friction between the working layers and the carrier discs. Suitable layers consist, for
25 example, of polyurethane. The layer is conventionally soft and does not therefore contribute to the stiffness of the carrier disc. The remaining steel core is therefore much thinner than the target thickness of the semiconductor wafers after the processing by means of PPG.

30

If the target thickness of a semiconductor wafer with a diameter of 300 mm after processing by means of PPG is for example 825 μm and the total thickness of the carrier disc being used is 800 μm , then 500 - 600 μm of this 800 μm total
35 thickness of the carrier disc is given over to the steel core which imparts stiffness, and 100 - 150 μm each to the anti-wear

coating on the two sides.

If for comparison the target thickness of the semiconductor wafer after processing by means of lapping is likewise 825 μm ,
5 then the carrier disc used for the lapping consists entirely of stiffness-imparting steel and has a thickness of 800 μm .

Since the bending of a plate, for the same material and the same shape and design, is known to vary with the third power of
10 its thickness, a carrier disc with a 500 μm thick steel core bends during PPG about four times as much as an 800 μm thick carrier disc during lapping.

For a carrier disc with a 600 μm thick steel core, the bending
15 during PPG is still 2.4 times that of an 800 μm thick carrier disc during lapping.

In the working gap, the maximum deviation from the plane setting of the carrier disc is limited by the difference
20 between the carrier disc thickness and instantaneous thickness of the semiconductor wafers. This is typically at most 100 μm . Wherever the carrier disc projects inward and outward from the annular working gap and engages into the rolling device comprising the inner and outer pin ring, no measures are
25 implemented in the prior art of PPG methods to limit the possible bending of the carrier disc. Owing to the workpiece excursion required, this unguided region is particularly large.

Bending of the carrier discs leads to the following disadvantages for the semiconductor wafers and for the carrier
30 discs, and therefore to an unstable and critical overall process:

a) The semiconductor wafer always extends partially from the reception opening of the carrier disc and is forced back in
35 when it re-enters the working gap. This also bends the

semiconductor wafer and presses it onto the outer or inner edge of the grinding pad. This can lead to the formation of local scratches and geometrical defects in the marginal region owing to the increased grinding effect.

5

b) The continual insertion and extraction of the semiconductor wafer into and from the bent carrier disc roughens the reception opening of the carrier disc, which is generally lined with an insert made of a soft plastic. Sometimes, the lining of the reception opening may even be torn out of the carrier disc. In any event, the service life of the carrier discs being used suffers detrimentally.

10

c) The roughened lining of the reception opening of the carrier disc brakes or stops the desired free rotation of the semiconductor wafers inside the reception opening. This can lead to planarity defects of the semiconductor wafer in respect of global planarity (for example TTV = total thickness variance) and local planarity (nanotopography).

15
20

d) The carrier disc, bent in its excursion, exerts high forces on the grinding bodies when it re-enters the working gap, in particular on the outer and inner edges of the annular working layer. The working layer can thereby be damaged. Entire grinding bodies ("tiles") can be torn out, or at least parts thereof can be displaced. If these fragments enter between the semiconductor wafer and the working layer, fracture of the semiconductor wafer is possible owing to the high point loading.

25
30

e) The bending of the carrier disc, with increased point loading of its protective layer at the points which sweep over the edge of the working layer, leads to greatly increased local wear. This considerably limits the lifetime of the carrier disc and makes the method uneconomical. The increased wear of the protective layer furthermore makes the working layer blunt.

35

This necessitates frequent resharpening processes which consume time and material, and are therefore detrimental to the economic viability of the method. Furthermore, the frequent process interruptions have a negative effect on the properties
5 of the semiconductor wafers thus processed.

JP 11254303 A2 discloses a device for guiding the carrier discs, which consists of two upper and lower spacers which converge conically or in a wedge shape and which are arranged
10 on the inner margin of an outer gear wheel of the lapping machine. The deformation of thin carrier discs is intended to be able to be prevented by means of such a device. However, the modification described therein for the lapping machine, which moreover is directed at the processing of glass substrates, has
15 substantial disadvantages and is unsuitable for carrying out methods of lapping and PPG grinding with workpiece excursion.

Both when lapping with free cutting abrasive in a slurry and for PPG grinding with abrasive bound firmly in grinding pads,
20 the working layers (cast-metal lapping plates or grinding pad) experience constant wear. The height of the lapping plate or grinding pad decreases continuously and the position of the plane, in which the carrier discs move in the working gap formed between the lapping plates or grinding pads, is
25 displaced progressively.

With increasing wear of the working layer and displacement of the movement plane of the carrier discs, the forcible guiding device disclosed in JP 11254303 A2 constrains the toothed outer
30 region of the carrier discs to roll increasingly in a different plane. This means that the wedge-shaped guide blocks, screwed firmly to the outer toothed wheel, would additionally bend the carrier disc with increasing wear of the working disc, which is disadvantageous.

35

Another disadvantage is that the guide blocks need to be

unscrewed before it is possible to change the carrier disc, which is necessary from time to time. This represents additional outlay.

In PPG grinding methods, carrier discs are conventionally used with a coating, which is necessary in order to avoid direct contact between the stiffness-imparting core of the carrier disc and the abrasive of the grinding pad (for example diamond). Owing to the design, the spacers described in JP 11254303 A2 engage far into the carrier disc and in each case sweep over the coating of the carrier disc in its marginal region. Owing to the vertical constraining forces which occur during the guiding of the carrier disc, the coating of the carrier discs is therefore exposed to particularly high wear in the guided region, when a device according to JP 11254303 A2 is employed. Another disadvantage of using the solution proposed in JP 11254303 A2 for PPG methods is therefore that the guide ring is engaged far into the carrier disc and can thus damage the carrier disc coating (for example polyurethane).

No satisfactory solution to the problem of carrier disc bending in the region of the workpiece excursion is therefore known from the prior art.

Embodiments of the present invention seek to provide a suitable device with which the wear and the risk of damage of the carrier discs and of the workpieces (e.g. semiconductor wafers) can be minimized, and furthermore a method for the simultaneous double-sided material removal processing of a plurality of semiconductor wafers, which prevents the carrier disc from bending out of the movement plane in the region of the workpiece excursion.

According to a first aspect of the present invention, there is provided a device for the double-sided processing of flat workpieces, comprising an upper working disc and a lower working disc,

wherein at least one of the working discs can be driven in rotary fashion by means of a drive, and wherein the working discs, form between themselves a working gap, in which is arranged at least one carrier disc with at least one cutout for at least one workpiece to be processed, wherein the at least one carrier disc has teeth

on its circumference, by means of which teeth it rolls on an inner and an outer gear wheel or pin ring if at least one of the gear wheels or pin rings is set in rotation, wherein the gear wheels or pin rings each have a multiplicity of gear or pin arrangements with which the teeth of the carrier discs enter into engagement during rolling, wherein at least one of the pin arrangements has at least one guide which delimits a movement of the margin of the at least one carrier disc in at least one axial direction, wherein one guide is formed by at least one shoulder extending around the circumference of the pin arrangement between a first, larger diameter and a second, smaller diameter of the pin arrangement and a further guide is formed by the side surfaces of at least one groove extending around the circumference of the pin arrangement.

The shoulder can particularly be perpendicular to a longitudinal axis of the pin arrangement or the sleeve respectively. The shoulder can also be formed by a sloped surface. The groove can also be perpendicular to the longitudinal axes of the pin arrangement or the sleeve respectively. The groove can have a square-shaped cross-section. The edges of the carrier discs are thereby guided by the side surfaces of the groove and therefore delimited in their movement on both sides in axial direction. The combination of shoulder and groove increases the flexibility of the use of the device as carriers with very different thicknesses can be used, wherein one type of carriers is guided in the groove and another, possibly much thicker type of carriers is guided by

the shoulder.

The gear or pin arrangements according to embodiments of the invention can have different diameters over their outer circumference in a longitudinal (or axial) direction.

The pin arrangements can each have a substantially cylindrical form.

They have on their outer surface, for example extending around their circumference, a guide which delimits the axial movement of the carrier disc margins, with the result that the latter are held substantially in the carrier disc plane. The gear arrangements can have corresponding guides. The guide can delimit the movement of the margins of the carrier discs in one or both axial directions, that is to say for example vertically upward and/or downward.

Furthermore, the delimitation can completely prevent the movement in the at least one axial direction or still permit a slight movement.

According to embodiments of the invention, therefore, the undesirable vertical movement of the carrier discs, in particular outside the working gap, is largely avoided by means of the guide. The risk of damage to the carrier discs and the workpieces to be processed is minimized.

The workpieces that are simultaneously processed on both sides by means of the device can be semiconductor wafers, for example.

Material removal processing, for example grinding, lapping, polishing or honing, can be effected by means of the device according to embodiments of the invention.

For this purpose the working discs can have suitable working layers.

According to embodiments of the invention, in particular, a plurality of carrier discs can be provided. The latter can in turn have a plurality of cutouts for a plurality of workpieces.

The workpieces held in the carrier discs move along a cycloid path in the working gap.

Each pin arrangement can have a guide according to embodiments of the invention. However, it is also conceivable to provide at least some of the pin arrangements with a guide.

The gear or pin arrangements can be embodied in one part or in multiple parts.

In principle, it is conceivable for the pin arrangements to consist in each case only of one pin, on whose outer surface itself the guide is formed.

However, it is also conceivable for the pin arrangements to consist of a plurality of parts.

In this case, therefore, the expression gear or pin arrangement encompasses not only the pins or gears themselves, but also for example separate component parts which, however, are connected thereto.

Likewise, the feature that at least one gear or pin arrangement has a guide also encompasses for example the provision of the guide between adjacent pins or gears, whether or not said guide is connected to the pins or gears.

According to a further embodiment the at least one groove is formed at the larger diameter portion of the pin arrangement.

Furthermore the smaller diameter of the pin arrangement can end in a free end of the pin arrangement starting from the shoulder without any diameter enlargement.

It is furthermore preferred if the pin arrangements of at least one of the pin rings are formed in each case from a pin and a sleeve mounted in rotatable fashion on the pin, wherein at least one of the sleeves, in particular all of the sleeves, for example, has the guide on the outer circumference thereof.

The sleeves, which can be embodied in one part or in multiple parts, can be arranged on the pin directly in rotary fashion or can be arranged on the pin for example by means of an inner casing serving as a sliding bearing.

The guide can be incorporated into the sleeve itself.

However, it is also conceivable, of course, to arrange on the outer surface of the sleeve a further device, for example a ring or the like, which then forms the guide.

Through the use of sleeves, the wear of the carrier discs and of the pin rings can be reduced in a manner known per se.

At the same time, the wear and the risk of damage of the carrier discs are minimized further by the guide formed on at least one of the sleeves.

The sleeves can be provided in particular on the outer and the inner pin ring or just one of the pin rings.

They can furthermore consist for example of a steel material (e.g. a hardened steel material, in particular high-grade steel material). Such a material is particularly resistant to wear.

However, it is also conceivable to produce the sleeves from a

different material, for example a plastic material. Metal abrasion is avoided by choosing a plastic.

According to one configuration, at least one of the the guides can have at least one radially extending guide surface. The guide surface extends in a radial plane, that is to say in particular a horizontal plane. The carrier disc then bears on the radial guide surface during processing and the movement of its margin is thus delimited in at least one axial direction.

Furthermore, the at least one pin arrangement or sleeve can have a plurality of grooves which are spaced apart axially with respect to one another, extend around the circumference of the pin arrangement or sleeve and the side surfaces of which in each case delimit a movement of the margin of the at least one carrier disc in an axial direction.

The grooves can in turn extend perpendicular to the longitudinal axis of the pin arrangement or sleeve.

The grooves can furthermore have different widths. In this case, the groove width can be adapted to the thickness of the carrier discs that are to be guided in each case. In this way, by means of a suitable height adaptation of the pin arrangements, carrier discs of different thicknesses can be guided with the same pin arrangements or sleeves. This increases the flexibility of the device.

It goes without saying that the radial guide surfaces, shoulders and/or grooves according to embodiments of the invention can be combined with one another in any desired manner.

Thus, by way of example, the pin arrangements or sleeves can each have at least one such shoulder and/or at least one such guide surface and/or one or a plurality of such grooves. The scope of use of the device is thereby extended. In particular,

workpieces having considerably different thicknesses can then also be guided with the same pin arrangements.

According to a further configuration, at least one groove can have a width which is greater than the thickness of the at least one carrier disc to be guided by 0.1 mm to 0.5 mm. This provides a small amount of play for the carrier disc in the groove opening which reduces the wear.

According to a further configuration, the at least one guide surface or the at least one shoulder or the at least one groove can have at least one circumferential bevel. Such a bevel leads to a facilitated entry of the carrier discs into the guide, for example the groove, and thus to a reduced wear. The risk of damage to the carrier discs and the workpieces is thereby reduced.

The bevels can be formed at the edge of the shoulder or at one or both edges of the groove opening and in a manner extending around the circumference of the pin arrangement or sleeve.

It has proved to be particularly suitable in practice for the bevel to have an opening angle of 10° to 45° relative to the guide surface or relative to the shoulder or relative to the groove.

As an alternative to the provision of bevels, for the same purpose it may also be provided that the at least one guide surface or the at least one shoulder or the at least one groove has at least one rounded edge. In turn, it is correspondingly possible in the case of grooves, of course, for both edges of the groove opening to be rounded.

Owing to the fact that for the carrier discs the risk of damage is minimized according to embodiments of the invention, it is advantageously possible, in accordance with a further configuration, to

produce said carrier discs from a nonmetallic materials in particular a plastic. In the prior art, such nonmetallic carrier discs are virtually Impossible owing to the risk of damage to the carrier discs.

According to a further configuration, the gear wheels or pin rings can be mounted by means of a height-adjustable mount, wherein a lifting device is provided for the mount. The height of the gear wheels or pin rings and thus of their gear or pin arrangements can thus be varied. If the gears or pins or sleeves have for example a plurality of guides spaced apart in an axial direction, e.g. grooves and/or shoulders having different thicknesses, by means of the height setting it is possible to set the gear wheels or pin rings to the corresponding carrier discs having different thicknesses.

According to an embodiment of the present invention, there is provided a method for the simultaneous double-sided material removal processing of a plurality of semiconductor wafers, in which each semiconductor wafer lies freely mobile in a recess of one of a plurality of carrier discs set in rotation by means of an annular outer drive wheel and an annular inner drive wheel and thereby moved on a cycloid path curve, while the semiconductor wafers are processed so as to remove material between two rotating annular working discs, and the carrier discs and/or semiconductor wafers temporarily leave the working gap, delimited by the working discs, with a part of their surface during the processing, wherein the carrier discs are guided in a movement plane which essentially extends coplanar with a midplane of the working gap by the carrier discs being guided in that movement plane, during the excursion of a part of the area of the carrier discs and/or semiconductor wafers from the working gap, in grooves of a plurality of grooved sleeves mounted on a pin and fitted on at least one of the two gear wheels.

According to a second aspect of the present invention, there is provided a method for the simultaneous double-sided material removal processing of a plurality of semiconductor wafers, in which each semiconductor wafer lies freely mobile in a recess of one of a plurality of carrier discs set in rotation by means of an annular outer gear wheel and an annular inner drive wheel and thereby moved on a cycloid path curve, while the semiconductor wafers are processed so as to remove material between two rotating annular working discs which comprise working layers, and the carrier discs and/or semiconductor wafers temporarily leave the working gap, delimited by the working discs, with a part of their surface during the processing, wherein the carrier discs are guided in a movement plane which essentially extends coplanar with a midplane of the working gap by the two working discs respectively comprising an annular region, which contains no working layer and ensures guiding of the carrier disc during the excursion of the carrier discs and/or semiconductor wafers from the working gap.

The above methods preferably involve double-sided grinding of the semiconductor wafer, each working disc comprising a working layer of abrasive material (in particular PPG methods).

In the method according to an embodiment of the invention above, double-sided lapping of the semiconductor wafers, while supplying a suspension which contains an abrasive material, is likewise preferred.

Lastly, the above methods may also involve double-sided polishing, while supplying a dispersion which contains silica sol, in which case each

working disc comprises a polishing pad as a working layer. In fact, no workpiece excursion takes places in double-sided polishing. Nevertheless, the carrier discs emerge from the working gap even in DSP so that guiding the carrier discs according to the method according to an embodiment of the invention above is also advantageous for DSP.

Brief Description of the Figures

Fig. 1 shows the basic construction of a device according to the invention for the double-sided processing of flat workpieces in a perspective view.

Fig. 2 shows a sleeve for a pin of a pin ring in a side view in accordance with the prior art.

Fig. 3 shows a sleeve according to a first exemplary embodiment of the invention in a side view.

Fig. 4 shows a sleeve according to a further exemplary embodiment of the invention in a side view.

Fig. 5 shows a sleeve according to a further exemplary embodiment of the invention in a side view.

Fig. 6 shows a sleeve according to a further exemplary embodiment of the invention in a side view.

Fig. 7 shows a sleeve according to a further exemplary embodiment of the invention in a side view.

Fig. 8 shows the sleeves illustrated in **Fig. 1** in a partial side view in an operating position.

Fig. 9 shows by way of example the carrier disc guiding on the pin ring.

Fig. 10 shows embodiments of the carrier disc guiding according to the invention by means of grooved pin sleeves.

5 **Fig. 11** shows an embodiment of the guiding of the carrier discs according to the invention by an annularly removed working layer of the working disc.

Fig. 12 shows the bending of the carrier discs in the prior art
10 and guiding of the carrier disc by a support ring.

Fig. 13 shows an overall view of the lower working disc with a working layer, carrier discs, rolling device and semiconductor wafers

15 **Fig. 14** shows thickness profile and plan view of semiconductor wafers, which have been processed with guiding of the carrier discs according to the invention (6B) and not according to the invention (6A, 6C, 6D).

20

List of References

1: workpiece (in particular semiconductor wafer)

25 2a: lower working layer carrier

2b: upper working layer carrier

3a: lower working layer

30

3b: upper working layer

4a: lower working disc

35 4b: upper working disc

- 5: guide cage for workpieces ("carrier disc")
- 6: workpiece excursion
- 5 7a: outer drive wheel (gear wheel / pin ring)
- 7b: inner drive wheel (gear wheel / pin ring)
- 8: machine base
- 10 9: pin ring height adjustment
- 10: outer teeth of the workpiece guide cage
- 15 11: pin
- 12: pin sleeve
- 13a: lower carrier disc guide
- 20 13b: upper carrier disc guide
- 14a: thickness decrease due to wear of the lower working layer
- 25 14b: thickness decrease due to wear of the upper working layer
- 15: groove
- 16: limited bending of the workpiece guide cage
- 30 17: projection of the workpiece from the guide cage
- 18a: separated workpiece carrier in the workpiece excursion /
ring, bottom
- 35 18b: separated workpiece carrier in the workpiece excursion /

ring, top

19: height adjustment of guide cage support ring

5 20: plastic molding ("insert")

21: migration of the workpiece from the guide cage

22: eruption of the plastic molding from the guide cage

10

23: fracture of the semiconductor wafer

24: marginal region of the semiconductor wafer, which enters excursion

15

25: reception opening for semiconductor wafer

26: readjustment of the guide device

20 27: play of the semiconductor wafer in the reception opening

28: excerpt (detailed representation)

29: anti-wear coating of the carrier disc

25

30: (steel) core of the carrier disc

31: support ring

30 32: opening of the guide device for the carrier discs

33: funnel-shaped groove opening

34: opening in the carrier disc guide for the pin sleeve

35

35: reduced thickness of the semiconductor wafer due to

- elevated grinding effect at the margin of the working layer
- 36: slight decrease in the thickness of the semiconductor wafer
- 5 37: processing traces (sawing cuts; anisotropic roughness)
- 38: region of the semiconductor wafer which sweeps over the margin of the working layer in the workpiece excursion
- 10 39: increased roughness
- 40: local decrease in the thickness of the semiconductor wafer in the marginal region.
- 15 41: unlimited deflection of the workpiece guide cage
- 42: double-sided processing machine
- 43: upper pivoting arm
- 20 44: base
- 45: pivoting device
- 25 46: rotation axis
- 48: guide of the sleeve
- 50: shoulder on the circumference of the sleeve
- 30 52: guide surface
- 56, 58: side surfaces of the groove
- 35 60: bevel at groove edge

62: workpiece

64: working gap

5 Detailed Description of the Invention

The invention will be described in detail below with the aid of **Fig. 1-14**.

10 Unless indicated otherwise, identical reference symbols designate identical objects in the figures.

Fig. 1 shows the basic construction of a device according to the invention for the double-sided processing of flat
15 workpieces.

A double-sided processing machine 42 with planetary kinematics is illustrated in the example in **Fig. 1**. The device 42 has an upper pivoting arm 43, which can be pivoted about a vertical
20 axis by means of a pivoting device 45 mounted on a lower base 44. An upper working disc 4b is carried on the pivoting arm 43. The upper working disc 4b can be driven in rotary fashion by means of a drive motor (not illustrated in more specific detail in **Fig. 1**). On its underside (not illustrated in **Fig. 1**), the
25 working disc 4b has a working surface, which can be provided with a working layer depending on the processing to be effected. The base 44 has a carrier section 8, which carries a lower working disc 4a. It likewise has a working surface on its top side. The lower working disc 4a can likewise be driven in a
30 rotary fashion by means of a drive motor (not illustrated), in particular in the opposite direction to the upper working disc 4b. Arranged on the lower working disc 4a are a plurality of carrier discs 5 each having cutouts 25 for workpieces to process, in the present case semiconductor wafers to be
35 processed. In the exemplary embodiment illustrated, the carrier discs 5 consist of a plastic. The carrier discs 5 have outer

teeth 10, with which they come into engagement with an inner pin ring 7b and an outer pin ring 7a of the device. The inner pin ring 7b and the outer pin ring 7a each have a multiplicity of pin arrangements, which, in the example illustrated, are
5 formed in each case from a cylindrical pin and a sleeve mounted in rotatable fashion on the pin. A rolling device is formed in this way, wherein the carrier discs 5 are likewise set in rotation in the event of a rotation of the lower working disc 4a by means of the inner pin ring 7b. The workpieces arranged
10 in the cutouts in the carrier discs 5 then move along cycloid paths.

For processing purposes the workpieces to be processed are inserted into the cutouts 25 in the carrier discs 5 (not
15 illustrated). As a result of the pivoting of the pivoting arm 43, the two working discs 4a, 4b are aligned coaxially with respect to one another. They then form between themselves a working gap, in which are arranged the carrier discs 5 with the workpieces held by the latter. With at least one rotating upper
20 or lower working disc 4a, 4b, afterward the upper working disc 4b, for example, is pressed onto the workpieces by means of a highly precise loading system. From the upper and lower working discs 4a, 4b, in each case a press-on force thus then acts on the workpieces to be processed and the latter are
25 simultaneously processed on both sides. The construction and the function of such a double-sided processing machine are known per se to the person skilled in the art.

Fig 2 illustrates a sleeve 12' according to the prior art. The
30 known sleeve 12' has a hollow-cylindrical form and during operation is placed onto the pins of the inner and/or outer pin ring 7a, 7b of a device as shown in **Fig. 1**. In this case, it is mounted on the respective pin in a manner such that it can be rotated along the rotation axis 46 illustrated in a dash-dotted
35 manner in **Fig. 2**.

Fig. 3 shows a sleeve 12 according to a first exemplary embodiment of the invention.

The sleeve 12 illustrated in **Fig. 3** likewise has a substantially cylindrical cutout by means of which it can be placed onto a pin of the pin rings 7a, 7b. In this case, in particular all or some of the pins of one or both pin rings 7a, 7b can be provided with such a sleeve 12. The sleeves illustrated in **Fig. 3** have on their outer surface a guide 48, which, in the example illustrated, is formed by a shoulder 50 - extending around the circumference of the sleeve 12 - between a first, larger diameter and a second, smaller diameter of the sleeve 12. In this case, the guide 48 has a radially extending guide surface 52 as a result of this shoulder 50. During operation, the carrier discs 5 engage by their outer teeth into the region of the sleeve 12 having the smaller diameter, wherein the radial guide surface 52 delimits the movement of the margins of the carrier discs 5 in an axial direction in such a way that an axial movement in the figure downward is prevented.

Fig. 4 shows a sleeve 12 according to the invention according to a further exemplary embodiment. As the guide 48, this sleeve 12 has a cross-sectionally rectangular groove 15 extending around the circumference of the sleeve 12. In this case, the carrier discs 5 in turn engage into the region of the sleeve 12 having a smaller diameter, said region being formed by the base of the groove. Side surfaces 56, 58 of the groove 15 form a guide of the margins of the carrier discs 5 in such a way that these can move out of the groove neither in an axial direction upward nor in an axial direction downward. The groove can permit a small amount of play of the carrier discs 5 by virtue of the fact that it has a width w that is greater than the thickness of the carrier disc 5 guided in the groove 15 by 0.1 mm to 0.5 mm.

In the case of the exemplary embodiment of a sleeve 12 according to the invention as illustrated in **Fig. 5**, in contrast to the exemplary embodiment from **Fig. 4**, two circumferential grooves 15 having different widths w_1 and w_2 are provided. By means of the two grooves 15, carrier discs 5 having different thicknesses can be guided by the same sleeve 12. For this purpose, in the case of the device shown in **Fig. 1**, the inner pin ring 7a and the outer pin ring 7b can be mounted by means of a height-adjustable mount, wherein a lifting device is provided for the mount. By means of the lifting device, it is possible to adjust the height of the pin rings 7a, 7b and with them the sleeves 12 arranged on the pins. In this way, the pins with the sleeves 12 mounted thereon in rotatable fashion can be aligned with the correct height position for the carrier disc 5 to be guided in each case.

The exemplary embodiment shown in **Fig. 6** combines the circumferential shoulder 50 with the circumferential radial guide surface 52 from **Fig. 3** with the circumferential groove 15 from **Fig. 4**, on the other hand. It is once again possible, through a suitable height adjustment by means of the lifting device, with the sleeve 12 illustrated in **Fig. 6**, both to delimit the movement of a comparatively thin carrier disc 5 on both sides axially in the circumferential groove 15 and to delimit for example the movement of carrier discs or other tools of considerable thickness by means of the radial guide surface 52 of the shoulder 50 on one side axially. This increases the flexibility of the device according to the invention.

30

The sleeves 12 illustrated in **Fig. 7** largely correspond to the sleeves shown in **Fig. 6**. In the case of the sleeve 12 in **Fig. 7**, however, the groove 15 has a circumferential bevel 60 in each case at both edges of its groove opening. The bevels 60 can have an opening angle α of 10° to 45° in each case relative to the groove, and in particular relative to its side surfaces

35

56, 58. The bevelings of the groove 15 facilitate the receiving of the carrier discs 5 in the groove 15 and reduce the risk of damage to the carrier discs 5. Even though corresponding bevels 60 are provided only at the groove edges in **Fig. 7**, it is also possible, of course, for the radial guide surface 52 of the shoulder 50 to have a corresponding bevel. Likewise, one or a plurality of corresponding bevels can be provided in the case of the exemplary embodiments of the sleeve 12 as shown in **Figs. 3 to 6**. Instead of the bevels, it is also conceivable to round the edges of the grooves 15 and/or of the radial guide surfaces 52.

The sleeve 12 illustrated in **Fig. 7** is shown partially in an operating position by way of example and extremely schematically in **Fig. 8**. It goes without saying that the proportions of the individual component parts are not depicted realistically for the illustration. The figure reveals the carrier disc 5, which holds in its cutouts 25 in each case workpieces 62 that are simultaneously processed on both sides in the working gap 64 between the upper working disc 4b and the lower working disc 4a. The carrier disc 5 is in engagement by its outer teeth 10 with the sleeve 12 and in particular the section formed by the base of the groove within the groove 15 having a smaller diameter. The carrier disc 5 is delimited axially with regard to its movement with a small amount of play in the groove 15 in both directions. A considerable vertical movement of the carrier disc 5 in the region outside the working gap 64 is reliably avoided in this way.

It is pointed out that even though a machine having pin rings (7a, 7b) is described in the exemplary embodiment illustrated, the pin arrangements correspondingly having a guide for the carrier discs, according to the invention a machine having a gear wheel arrangement, that is to say an inner and outer gear wheel instead of the inner and outer pin ring, could likewise be provided, in which case the gear arrangements can then have

corresponding guides.

Fig. 13 shows the plan view of the lower working disc 4a of a double-sided processing machine suitable for carrying out the method according to the invention.

The lower working disc 4a is represented with the applied lower working layer, consisting of a working layer carrier 2a and a working layer 3a, and the rolling device formed by the inner pin ring (7b) and outer pin ring (7a) for the workpiece guide cage ("carrier discs", 5) with inserted workpieces 1 (semiconductor wafers). 11 and 12 denote the pin and pin sleeve of the pin ring.

Fig. 13B depicts a detailed representation of excerpt 28 from **Fig. 13A**. In order to avoid damage on the semiconductor wafer 1 due to hard contact (fracture, splintering) or contamination with the e.g. metallic material of the carrier disc 5, the reception opening 25 of the carrier disc 5 is lined with a plastic insert 20. On its path over the working layer 3a, a part 6 of the semiconductor wafer 1 temporarily projects beyond the inner or outer edge of the working layer owing to the rotation of the carrier disc 5. This is referred to as "workpiece excursion". Since the semiconductor wafer 1 is inserted with play 27 into the reception opening 25 of the carrier disc 5, it can rotate freely so that an annular region 24 of the semiconductor wafer 1 enters into excursion 6 in the course of the processing.

Owing to wear, the working layer experiences a thickness reduction during the processing. This takes place inside the annular surface over which the semiconductor wafers sweep in the course of the processing. When the annular surface lies inside the annular working layer, a "trough-shaped" thickness profile is set up radially over the working layer. This leads to enhanced material removal at the edge of the semiconductor

wafer ("edge roll-off"), which is undesired. Yet when the working layer lies fully inside the swept annular surface, the semiconductor wafers experience a workpiece excursion and an edge roll-off does not occur.

5

A workpiece excursion is known, for example, from DE 102 007 013 058 A1.

Owing to a workpiece excursion, the carrier disc also projects
10 over a sizeable length without guiding from the working gap formed by the upper and lower working discs.

The bending of the carrier disc in the prior art and also the guiding of the carrier discs outside the working gap by means
15 of a support ring are illustrated schematically below (Fig. 12).

Fig. 12A shows the cross section through the upper 4a and lower working disc 4b with an upper 3b and lower working layer 3a on
20 working layer carriers 2b and 2a, and a carrier disc 5 with a reception opening 25 for the semiconductor wafer 1, which engages into a pin 11 with a pin sleeve 12 of the outer gear wheel. In the prior art, the carrier disc is not guided in the excursion region 6 and beyond to its outer teeth 10. When the
25 semiconductor wafers are moved during the processing, the rolling device transmits high forces to the carrier discs. The carrier discs then sometimes bend considerably in the unguided excursion region. This is known from lapping, in which a large excursion is preferred.

30

In PPG methods, the bending is further promoted by the carrier discs consisting only of a thin stiffness-imparting core material 30, for example of steel, which is coated on both sides with an anti-wear coating 29 that does not contribute to
35 the stiffness (**Fig. 12C** and **Fig. 12D**).

For the PPG method, rolling devices without measures for guiding the carrier discs in the movement plane are therefore unsuitable.

5 In the prior art without carrier disc guiding in excursion (**Fig. 12A**), the carrier disc is then sometimes bent (41) so that its outer teeth 10 leave the guiding by the pin 11 and pin sleeve 12 of the pin ring 7a and "jump over". Furthermore, the semiconductor wafers 1 sometimes project (17) from the carrier
10 disc 5 so much that they are no longer guided by its reception opening. When the carrier disc 5 rotates further and the working discs 4a and 4b or the working layers 3a and 3b force the carrier disc back into the working gap, the edge of the semiconductor wafer may be damaged, or fracture may occur.

15 In the prior art, suitable carrier discs usually have "plastic insert" which lines the reception opening. An example is shown by **Fig. 12C**. When the semiconductor wafer is forced back into the reception opening upon re-entering the working gap, as
20 shown by **Fig. 12D**, the plastic insert 20 therefore often erupts (22) or the semiconductor wafer itself breaks (23). This leads to damage or destruction of the semiconductor wafers and the carrier discs, and usually therefore also damage of the working layers 3a and 3b owing to fragments of the two in the working
25 gap.

As a suitable countermeasure, **Fig. 12B** represents a device in the form of a height-adjustable (19) so-called "support ring" 31. Although the support ring can limit excessive bending of
30 the carrier disc in one direction (16), it does not however prevent undesired upward departure from the pin ring guide (41), so that the device according to Fig. 4B does not allow the object of securely guiding the carrier disc without eruption and with low constraining forces in the excursion
35 region to be achieved to a sufficient degree. On the other hand, it prevents unimpeded flow of the cooling lubricant

(water) and grinding slurry out from the working gap over the edge of the working disc. This may lead to "aquaplaning" with loss of grinding action, and in particular undesired heating in the working gap. Such heating may lead to deformation of the working discs, which may entail a deterioration of the plane-parallelity achievable for the semiconductor wafers processed in this way. The use of support rings according to **Fig. 12B** in PPG methods is therefore less preferred.

Fig. 9 shows examples of double-sided carrier disc guiding in excursion.

Fig. 9A shows a lower (13a) and an upper guide ring 13b, fitted on the height-adjustable outer pin ring 7a - and in an identical form on the inner pin ring 7b (not shown). They form an opening 32, which is somewhat wider than the thickness of the carrier disc 5 and preferably widens in a funnel shaped so that the carrier disc can easily be "inserted" and, in particular, its outer teeth 10 do not remain hanging from the guide opening 32. In machines suitable for carrying out the method according to the invention, the pin rings 7a and 7b are height-adjustable (9). The carrier disc guide 13a and 13b can therefore constantly be readjusted in height so that it is always possible to compensate for a position change of the carrier discs due to wear of the working layers, so that the carrier disc is guided with low forces without forced bending.

Fig. 9B shows the case in which the lower (3a) and upper working layer 3b have respectively experienced wear 14a und 14b, so that the plane in which the carrier disc and semiconductor wafer are moved in the working gap is displaced by the amount 26. Readjustment of the guide device 13a and 13b likewise by this amount 12 then always leads to guiding of the carrier discs without constraining forces in excursion.

35

The upper carrier disc guide 13b may be guided around the pin

sleeves 12, as shown in **Fig. 9A** and **Fig. 9B**, so that it likewise ensure positioning of the sleeves 12 on the pins 11, or they may be guided through between the sleeves as shown in **Fig. 9E**. In this case, the pin sleeves 12 project through
5 corresponding openings 34 into the upper carrier disc guide 13b.

Further variants consist in fitting the upper carrier disc guide 13b on the machine frame 8 (**Fig. 9C**) or on the upper
10 working disc 4b (**Fig. 9D**). In the former case the upper guide 13b cannot be readjusted so that, when tracking the lower guide 13a, the guide gap 32 widens in the course of wear of the working layers 3a and 3b by the amount of the working layer wear, and the carrier disc guiding becomes somewhat "looser".
15 This is not however detrimental since, when using working layers suitable for carrying out the method with typical usable heights of max 1 mm, the carrier disc can in no case bend so much that the semiconductor wafer leaves the reception opening or damages the plastic insert, or the carrier disc can actually
20 disengage from the rolling device.

In the latter case (**Fig. 9D**), the effect of the wear 14b of the upper working layer 3b is that the upper carrier disc guide 13b presses the carrier disc 5 down somewhat; here again, however, this is not to a detrimental extent. Another disadvantage is
25 the high relative speed of the upper carrier disc guide 13b in relation to the lower carrier disc guide 13a, and particularly in relation to the carrier discs 5 which rotate essentially with the rotational speed determined by the slowly rotating outer (7a) or inner pin ring (7b).

30

Fig. 10 shows exemplary embodiments for carrying out the first method according to the invention.

Fig. 10A shows a pin sleeve 12, which contains circumferential
35 grooves 15. The base circle diameter of the grooving is equal to that of the outer gearing 10 of the carrier disc 5. The

grooves or channels 15 are preferably widened outward (33), so that the carrier disc can easily be "inserted" during the rolling process. Also preferably, the pin sleeve 12 is provided with a plurality of channels 15 so that the channels can be
5 changed after wear due to use. According to the invention, preferably only the outer pin ring 7a is equipped with channeled sleeves 12, since the torques acting on the carrier disc 5 are higher here and the carrier discs can more easily be placed into the rolling device formed by the outer 7a and inner
10 pin ring 7b and removed again. It is however also preferred for both pin rings to be equipped with grooved sleeves 12.

Fig. 10B shows the inventive use of grooved sleeves 12 after the occurrence of wear 14a of the lower (3a) and 14b of the
15 upper working layer 3b: the displacement 26 of the movement plane of the carrier disc 5 and semiconductor wafer 1 resulting from the wear can be compensated for by height adjustment 9 of the pin ring 7a, so that the carrier disc 5 is guided in a planar fashion with low forces and without forced bending.
20 Height adjustment 9 of the pin ring 7a is, however, less preferred. When using multiply grooved sleeves 12, it is preferable when changing a carrier disc 5 to place it into another groove or channel 15, cf. **Fig. 10F**. Height adjustment 9 of the pin ring 7a is not absolutely necessary.

25

Figs 10C to 10E show other exemplary embodiments of grooved sleeves 12 according to the invention according to the number of channels 15 (**Fig. 10C, Fig. 10D**) or, in the case of a simple rolling device, only with fixed pins 11 and without freely
30 rotatable sleeves 12 (**Fig. 10E**).

The pins 11, or pin sleeves 12, of the inner and outer pin rings 7a and 7b of the PPG grinding device transmit all the forces required for rolling and movement of the carrier disc 5
35 in the working gap. High compressive forces therefore occur between the (rotatable) pin sleeve 12 and the flank of the

outer teeth of the carrier disc 5, and also friction forces in the case of pin rings 7a/7b with stiff forces (non-rolling running). The pins/pin sleeves 11/12 and tooth flanks must therefore have a high material strength. The material of the core of the carrier disc 5, which imparts the stiffness necessary for the carrier disc 5 and therefore usually consists of (hardened) steel, another (hardened) metal or a (fiber-reinforced) composite of high-strength plastic, satisfies this strength condition anyway. Similar materials with high strength and low wear are preferred for the pins 11 and pin sleeves 12. The pins 11 and pin sleeves 12 are therefore preferably made of steel or another (hardened) metal, particularly preferably of hard metal (cemented carbides, tungsten carbide etc.). For critical applications, in which contamination of the workpieces by metal abrasion must be avoided, it is also preferable to use sleeves 12 made of a high-strength composite plastic, in particular glass- or carbon fiber-reinforced PEEK (polyether ether ketone) or other thermo- or duromer composite plastics, as well as those made of materials with high abrasion strength and/or low sliding friction, for example fiber-reinforced polyamide ("nylon"), aramid (PAI, PEI), polyacetal (POM), polyphenyl (PPS), polysulfone (PSU).

The embodiment of pin rings in which the pins 11 carry rotatable sleeves 12 that can follow by corotation the relative movement between the gear wheel 7a/7b and the outer teeth of the carrier disc 5, which occurs during the rolling of the carrier disc 5, is particularly preferred. So that the sleeves 12 can rotate particularly easily and with low wear on the pins 11, the sleeve 12 may also be configured in multiple parts and consist externally of the particularly suitable high-strength material described, which enters into engagement with the carrier disc 5, and internally of a material with a low sliding friction coefficient (for example polypropylene PP, polyethylene PE, polyamide [nylon 6, nylon 12, nylon 66], polyethylene terephthalate PET, polytetrafluoroethylene PTFE

("Teflon"), polyvinylidene difluoride PVDF etc.). The inner sliding layer may be configured in the form of an inner coating, or inner sleeves or rings which are pressed or adhesively bonded in.

5

Vertically, the sleeves 12 are preferably guided loosely by screwed "caps" of the pins 11 or by a ring connected to the entire outer pin ring 7a/7b, so that they cannot slip off the pins and are guided on them with a more or less large play in
10 the vertical direction, more or less uniformly in a plane.

The carrier discs 5 preferably consist of hardened material (for example hardened steel), and the engagement surface of the outer teeth with the sleeves 12 of the pin ring 7a/7b is very
15 small. The pin sleeves 12 therefore experience increased wear. The wear is particularly high in the outer pin ring 7a, since high torques are transmitted there (greater lever).

Multiply grooved sleeves 12 are preferably used, since a
20 different channel 15 can be used after wear without having to replace the entire sleeve. Fig. 2F shows the use of the lower channel in a sleeve 12, for example after the upper channel has been worn. The channel 15 to be used is selected by placing the carrier disc into the corresponding channel, preferably after
25 height adjustment 9 of the pin rings 7a and 7b.

In the PPG grinding method, carrier discs are used which are provided with a coating that prevents contact of the (metallic) core of the carrier disc with the abrasive of the working
30 layer. During processing of the workpieces with the PPG grinding method, the carrier discs in the working gap slide over the working layer (grinding pad). Shear and friction forces then occur on the coating of the carrier discs. At contour edges of the coating, these forces are particularly
35 high and particularly detrimental peel forces occur. In order to avoid detachment of the coating or increased wear, in

particular on the contour edges of the carrier disc coating, the coating - particularly in the case of only partial surface coating likewise according to the invention - is configured so that the length of the contour edges is as short as possible and the profile of the contour edges has curvatures which are as small as possible. Preferably, therefore, in particular an e.g. annular region along the profile of the outer teeth of the carrier discs is left uncoated. For example, the coating is configured circularly and extended onto the outer teeth only as far as the base circle of the outer teeth. Particularly preferably, the diameter of such a circular coating is even somewhat smaller than the base circle diameter of the outer teeth. (On the other hand, the region left free by the coating must not be so large that parts of the exposed metallic carrier disc core come in contact with the diamond of the grinding pad owing to bending of the carrier disc. The preferred width of the annular region, exposed in addition to the teeth left uncoated inside the base circle of the outer teeth, is therefore 0 - 5 mm.)

20

In the preferred embodiment of the present invention for guiding the carrier discs in the region of the workpiece excursion in the form of grooved pin sleeves or pins, the guiding channels come into contact with the carrier disc only along the tooth flanks of the outer teeth. In particular, the grooved pins or pin sleeves therefore never come in contact with the coating of the carrier discs, so that this is spared and not exposed to any additional wear. It is particularly preferable to coat the carrier discs with a thermosetting polyurethane elastomer with a layer hardness of from 50 to 90 Shore A, and particularly preferably from 60 to 70 Shore A.

Fig. 11 shows exemplary embodiments of devices for carrying out the second method according to the invention, in which the guiding of the carrier disc is effected by an annularly removed working layer, i.e. by an annular region of the working disc or

the working layer carrier, which comprises no working layer. The working layers suitable for carrying out the second method according to the invention preferably consist of a thicker carrier layer 2a (bottom) and 2b (top) and thinner working
5 layers 3a and 3b, which contain abrasive and act so as to remove material. The guiding of the carrier discs in these exemplary embodiments is achieved in that the working layers 3a and 3b are set back so that the desired workpiece excursion 6 is obtained, but the working layer carrier 2a (lower working
10 layer) and 2b (other working layer) are formed up to the edge of the working disc or even beyond it, so that the carrier disc 5 can bend only by a small amount 16 before it bears on one of the working layer carriers 2a or 2b, and further bending is thus prevented. **Fig. 11B** shows that the deflection with
15 increasing wear 14a, 14b of the working layers is limited even more effectively. With the working layers suitable for carrying out the method according to the invention, having a low usable height of the working layers, the maximum bending of the carrier discs 5 is preferably so small that their outer teeth
20 always engage into the pin sleeves 12 of the gear wheel 7a (outer) and 7b (inner; not shown).

Partial coating of the working layer carrier with a working layer, however, is difficult in terms of manufacturing
25 technology.

The embodiment in **Fig. 11C** is therefore particularly preferred, which uses working layers 3a (bottom) and 3b (top) and working layer carriers 2a and 2b in one piece and surface-wide up to
30 the desired size for the necessary workpiece excursion 6, and additional rings 18a (lower working disc) and 18b (upper working disc) are fitted.

Outer rings 18a and 18b which are mounted outside the outer
35 edge of the working layer (**Fig. 11C**), and inner rings which are mounted inside the inner edge of the working layer (not shown),

are preferably used.

The outer and inner rings preferably have the same ring width, since the extent of the workpiece excursion "outward" and
5 "inward" is usually identical.

The inner diameter of the outer rings is equal to or greater than the outer diameter of the working layer carriers 2a/2b with a working layer 3a/3b, and the outer diameter of the inner
10 rings is equal to or less than the inner diameter of the working layer carriers 2a/2b with a working layer 3a/3b.

Particularly preferably, the outer margins of the outer rings and the inner margins of the inner rings project beyond the
15 outer and inner edges 4a (bottom) and 4b (top), respectively, and as close as possible to the sleeves 12 on the outer (7a) and inner pin ring 7b (not shown), so that the carrier discs are guided over a region which is as large as possible and only very small maximum bending of the carrier disc is achieved (16
20 in **Fig. 11C**).

The present invention also relates to a semiconductor wafer.

Semiconductor wafers, which are produced by PPG according to
25 the prior art, have a range of undesired properties which makes them unsuitable for demanding applications.

Thus, the migration 21 described in **Fig. 12D** of the semiconductor wafer 1 out of the reception opening 25 of the carrier disc 5 bent (17) in excursion 6 does not necessarily
30 lead to fracture 23 of the semiconductor wafer, damage of the carrier disc or loss 22 of the plastic insert 20 upon re-entry into the working gap. Often, the semiconductor wafer is simply only forced under temporarily very elevated pressure beyond the
35 outer and inner margins of the lower 3a and upper working layer 3b and "jumps" back into the reception opening 25 of the

carrier disc upon re-entry into the working gap. The grinding effect thereby briefly enhanced in the marginal region leads to characteristic reduced thicknesses in the region of the workpiece excursion.

5

Fig. 14A shows the radial thickness profile of a semiconductor wafer processed by methods not according to the invention. The local thickness D (in micrometers, μm) is plotted against the radius R (in millimeters, mm). Wherever the semiconductor wafer has experienced an increased grinding effect by the edge of the working layer upon re-entry into the working gap (38), its thickness is reduced (35). Owing to the semiconductor wafer's own rotation in the reception opening of the carrier disc, these "re-entry marks" are then distributed more or less circularly at the distance 38 around the semiconductor wafer. Owing to the forced jumping of the semiconductor wafer back into the reception opening, the plastic insert 20 is often also damaged only locally, usually roughened. The semiconductor wafer's own rotation in the reception opening 25 of the carrier disc is impeded by the increased friction and individual flattenings 40 are formed in the excursion region (**Fig. 14C**, left) which are shown as a unilateral (asymmetric) thickness reduction in the radial thickness profile of the semiconductor wafer (**Fig. 14C**, right). **Fig. 14C** shows this in plan view (left) and in the semiconductor wafer's thickness profile obtained along the section axis A-A' (right).

Furthermore, semiconductor wafers processed by PPG methods not according to the invention often have an anisotropic distribution of the processing marks (grinding cuts) due to the PPG processing. 37 denotes grinding marks which have been imparted with a preferential direction along the grinding tool movement in the excursion region of the semiconductor wafer (**Fig. 14D**, left). They are noticeable in that they extend with the curvature of the outer or inner margin of the annular working layer and predominantly tangentially to the margin of

the semiconductor wafer. This anisotropic finish is not necessarily associated with an asymmetric thickness or shape variation of the semiconductor wafer; rather, it is expressed by local increased roughness and subsurface damage (39 in the
5 thickness profile of **Fig. 14D**, right).

A semiconductor wafer processed by methods according to the invention, in which the carrier disc was guided in the movement plane without constraint, does not show these defects
10 (**Fig. 14B**). The thickness profile is symmetrical, and the surface of the semiconductor wafer has an isotropic finish without local roughenings, increased grinding marks or flattenings in the marginal region. In the worst case, only a slight reduction in the thickness of the semiconductor wafer is
15 observed toward the marginal region, although in terms of size and curvature it does not represent any substantial degradation of the high quality of a semiconductor wafer processed according to the invention (36 in **Fig. 14B**).

20 The method according to the invention therefore also provides a semiconductor wafer which has particularly good properties in respect of isotropy, rotational symmetry, planarity and constant thickness, and is therefore suitable for particularly demanding applications.

25

Examples

A Peter Wolters AC-1500P3 polishing machine was used for the examples. The technical features of such a device are described
30 in DE 10007389 A1.

Grinding pads with abrasives firmly bound therein were used. Such grinding pads are disclosed in US 6,007,407 A and US 5,958,794 A.

35

Monocrystalline silicon wafers with a diameter of 300 mm were

provided as workpieces to be processed, which had an initial thickness of 915 μm . In the PPG grinding, material removal of 90 μm took place so that the final thickness of the silicon wafers after processing was about 825 μm .

5

The carrier discs used had a steel core with a thickness of 600 μm and were coated on both sides with a PU anti-wear layer having a thickness of 100 μm on each side.

- 10 The process pressure selected for the working discs was 100 - 300 daN to simulate different loading situations, and on average gave removal rates of 10 - 20 $\mu\text{m}/\text{min}$.

- 15 Deionized water (DI water) was used as a cooling lubricant with flow rates of between 3 and 20 l/min, adapted to the respectively resulting removal rates and the different heat inputs resulting from this during the processing.

- 20 In the first example, a corresponding process was carried out without any carrier disc guiding.

- 25 Even during the first run, damage of the silicon wafer at the margin occurred owing to the insert being torn out of the carrier disc and a grinding block or parts thereof being torn off.

In a second example, a process was carried out with a removed grinding pad section taken off.

- 30 No damage of the silicon wafer occurred here, although there was slight roughening of the semiconductor wafers in the outer marginal region. The geometry of the silicon wafers was acceptable.

- 35 In a second example, a process was carried out with carrier disc guiding by grooved in sleeves on the outer pin ring.

The silicon wafers showed good geometry, a homogeneous micrograph up to the wafer margin, and no damage of the semiconductor wafer edge. Four runs were possible without
5 damage/roughening of the running discs, the insert, the coating and without attack or tearing of the outermost grinding blocks.

Patent Claims

1. A device for the double-sided processing of flat workpieces ,
comprising an upper working disc and a lower working disc,
5 wherein at least one of the working discs can be driven in
rotary fashion by means of a drive, and wherein the working
discs, form between themselves a working gap, in which is
arranged at least one carrier disc with at least one cutout
for at least one workpiece to be processed, wherein the at
10 least one carrier disc has teeth on its circumference, by
means of which teeth it rolls on an inner and an outer gear
wheel or pin ring if at least one of the gear wheels or pin
rings is set in rotation, wherein the gear wheels or pin rings
each have a multiplicity of gear or pin arrangements with
15 which the teeth of the carrier discs enter into engagement
during rolling, wherein at least one of the pin arrangements
has at least one guide which delimits a movement of the margin
of the at least one carrier disc in at least one axial
direction, wherein one guide is formed by at least one
20 shoulder extending around the circumference of the pin
arrangement between a first, larger diameter and a second,
smaller diameter of the pin arrangement and a further guide is
formed by the side surfaces of at least one groove extending
around the circumference of the pin arrangement.
25
- 2 The device as claimed in claim 1, wherein the at least one
groove is formed at the larger diameter portion of the
pin arrangement.
- 30 3. The device as claimed in claims 1 or 2, wherein the smaller
diameter of the pin arrangement starting from the
shoulder ends without any diameter enlargement in a
free end of the pin arrangement.
- 35 4. The device as claimed in claims 1 or 2, wherein the pin
arrangements of at least one of the pin rings are in each

case formed from a pin and a sleeve mounted in rotatable fashion on the pin, wherein at least one of the sleeves has the guides on its outer circumference.

- 5 5. The device as claimed in claims 1 or 2, wherein one of the at least one guides has at least one radially extending guide surface.
- 10 6. The device as claimed in claims 1 or 2, wherein the at least one pin arrangement has a plurality of grooves which are spaced apart axially with respect to one another, extend around the circumference of the pin arrangement and the side surfaces of which in each case delimit a movement of the margin of the at least one carrier disc in an axial direction.
- 15 7. The device as claimed in claim 6, wherein the grooves have different widths.
- 20 8. The device as claimed in claim 6, wherein at least one groove has a width which is greater than the thickness of the at least one carrier disc by 0.1 mm to 0.5 mm.
- 25 9. A device as claimed in claim 6, wherein the at least one shoulder or the at least one groove has at least one circumferential bevel.
- 30 10. The device as claimed in claim 9, wherein the bevel has an opening angle of 10° to 45° relative to the shoulder or relative to the groove.
- 35 11. The device as claimed in claim 5, wherein the at least one guide surface has at least one circumferential bevel.
12. The device as claimed in claim 11, wherein the bevel has an opening angle of 10° to 45° relative to the guide surface.

13. The device as claimed in claim 6, wherein the at least one shoulder or the at least one groove has at least one rounded edge.

5

14. The device as claimed in claim 5, wherein the at least one guide surface has at least one rounded edge.

10

15. The device as claimed in claims 1 or 2, wherein the at least one carrier disc consists of a nonmetallic material.

15

16. The device as claimed in claims 1 or 2, wherein the pin rings or the gear wheels are mounted by means of a height-adjustable mount and a lifting device is provided for the mount.

20

17. Apparatus comprising the device of claims 1 or 2 for the simultaneous double-sided material removal processing of a plurality of semiconductor wafers.

25

18. A method for the simultaneous double-sided material removal processing of a plurality of semiconductor wafers, in which each semiconductor wafer lies freely mobile in a recess of one of a plurality of carrier discs set in rotation by means of an annular outer gear wheel and an annular inner drive wheel and thereby moved on a cycloid path curve, while the semiconductor wafers are processed so as to remove material between two rotating annular working discs which comprise working layers, and the carrier discs or semiconductor wafer temporarily leave the working gap, delimited by the working discs, with a part of their surface during the processing, wherein the carrier discs are guided in a movement plane which essentially extends coplanar with a midplane of the working gap by the two working discs respectively comprising, an annular region, which contains no working layer and ensures guiding of the carrier disc during the excursion of the carrier discs or semiconductor wafers

30

35

from the working gap.

19. The method as claimed in claim 18, wherein the material removal processing involves double-sided grinding of the semiconductor wafers and each working disc comprises a working layer of abrasive material.
20. The method as claimed in claim 18, wherein the material removal processing involves double-sided polishing while supplying a dispersion, which contains silica sol, each working disc comprising a polishing pad as a working layer.
21. The method as claimed in claim 18, wherein the guiding of the carrier disc is effected out by an annular set-back working layer, so that the desired workpiece excursion is achieved but the working layer carrier is formed up to the margin of the working disc or beyond it.
22. The method as claimed in claim 18, wherein the full surface of the working layers and the working layer carriers is used for the required workpiece excursion and they carry additional rings on the lower working disc and rings on the upper working disc, which bear no working layers.
23. The method as claimed in claim 22, wherein the outer rings are mounted outside the outer edge of the working layer and the inner rings are mounted inside the inner edge of the working layer.
24. The method as claimed in claim 23, the outer and inner rings have the same ring width.
25. The method as claimed in claim 23, wherein the inner diameter of the outer rings is equal to or greater than the outer diameter of the working layer carriers with a working layer, and the outer diameter of the inner rings is equal to

or less than the inner diameter of the working layer carriers with a working layer.