

Description

[TECHNICAL FIELD]

6 The present invention relates to a fluorine-containing copolymer, a process for its production, and its use.

[BACKGROUND ART]

10 The present inventors previously found that copolymers of fluoroolefin, cyclohexyl vinyl ether, alkyl vinyl ether and hydroxyalkyl vinyl ether can be cured by room temperature curing and bake-curing by means of a curing agent such as melamine or a polyvalent isocyanate, and provide a weatherable coating film which is rich in gloss and excellent in solvent resistance as disclosed in US-A-4345057 and Japanese Unexamined Patent Publication Nos. 34107/1982 and 136662/1983. However, as a result of progress of
 15 application of the above-mentioned copolymers as a solvent-based coating, problems were found such that 1) when they were applied to a high solid coating which have been highly demanded in recent years, the viscosity was too high and it was difficult to conduct good coating and 2) the sufficient clarity of the coated surface could not be obtained.

20 [DISCLOSURE OF INVENTION]

The present invention has been made to solve the above-mentioned problems and provides the following fluorine-containing copolymer.

25 A fluorine-containing copolymer comprising polymer units represented by the formulas a), b) and c), respectively in amounts of from 40 to 60 mol%, from 25 to 55 mol% and from 5 to 25 mol%, respectively, and having an intrinsic viscosity of from 0.01 to 0.05 dl/g as measured in an uncured state at 30°C in tetrahydrofuran, the ratio of the weight-average molecular weight and the number-average molecular weight measured by a gel permeation chromatography being not more than 2.0:

30 a) $(CF_2 - CFX)$ X is fluorine, chlorine or a perfluoroalkyl or perfluoroalkoxy group having 1 to 3 carbon atoms,
 b)



40 R¹ is hydrogen or a methyl group,
 R² is an unsubstituted or fluorine-substituted straight-chain, branched-chain or alicyclic alkyl group having 1 to 12 carbon atoms, and t is 0 or 1, and
 c)



50 R³ is hydrogen or a methyl group, R⁴ is an unsubstituted or fluorine-substituted straight-chain, branched-chain or alicyclic alkyl group having a hydroxyl group.

EP-A-0 212 508 describes a fluorine-containing copolymer which is useful as a water-based paint material. Some of the products have a low viscosity.

55 US-A-4640966 and JP-A-62174213 disclose fluoroolefin copolymers having an inherent viscosity of from 0.05 to 2.0 dl/g.


The present invention is also to provide a process for producing the fluorine-containing copolymer, and a coating composition, preferably of a top coat for an automobile, which is composed of a combination of

the fluorine-containing copolymer and a curing agent.

The fluorine-containing copolymer of the present invention is composed of polymer units represented by the formulas a), b) and c):

a) $(CF_2 - CFX)$ X is fluorine, chlorine or a perfluoroalkyl or perfluoroalkoxy group having 1 to 3 carbon atoms,


b)



15 R^1 is hydrogen or a methyl group,

R^2 is an unsubstituted or fluorine-substituted straight-chain, branched-chain or alicyclic alkyl group having 1 to 12 carbon atoms, and t is 0 or 1, and

c)




25 R^3 is hydrogen or a methyl group, R^4 is an unsubstituted or fluorine-substituted straight-chain, branched-chain or alicyclic alkyl group having a hydroxyl group.


The polymer units can be formed by copolymerizing the monomers represented by the formulas a'), b') and c'), respectively:

30 a') $CF_2 = CFX$ X is the same as defined above,

b')



40 R^1 , R^2 and t are the same as defined above, and c')



45 R^3 and R^4 are the same as defined above.

50 As the monomer represented by the formula a'), there may be exemplified tetrafluoroethylene, chlorotrifluoroethylene, hexafluoropropylene, perfluoromethyl vinyl ether, perfluoroethyl vinyl ether and perfluoropropyl vinyl ether. Preferred monomers are tetrafluoroethylene and chlorotrifluoroethylene. As the monomer represented by the formula b'), there may be exemplified an alkyl vinyl ether such as ethyl vinyl ether, n-butyl vinyl ether, ethylisopropenyl ether or n-butyliisopropenyl ether, a cycloalkyl vinyl ether such as cyclohexyl vinyl ether, a fluoroalkyl vinyl ether such as 2,2,3,3 tetrafluoropropyl vinyl ether, and a vinyl carboxylate such as vinyl acetate, isopropenyl acetate, n-vinyl butyrate, n-isopropenyl butyrate, vinyl valerate, isovinyl valerate, vinyl pivalate or vinyl laurate. Preferred monomers are the alkyl vinyl ether and cycloalkyl vinyl ether as mentioned above, and it is more preferable to use the both of them in combination.

As the monomer represented by the formula c'), there may be exemplified a hydroxyalkyl vinyl ether such as ω -hydroxybutyl vinyl ether or ω -hydroxyethyl vinyl ether, a hydroxycycloalkyl vinyl ether such as a monovinyl ether of cyclohexanediol or a monovinyl ether of cyclohexanedimethanol, and ω -hydroxybutylisopropenyl ether. Preferred monomer is the hydroxyalkyl vinyl ether as mentioned above. The polymer units represented by the formulas a), b) and c) each may be a single sort or a mixture of two or more sorts.

The fluorine-containing copolymer of the present invention comprises the polymer units represented by the formulas a), b) and c) in amounts of from 40 to 60 mol%, from 25 to 55 mol% and from 5 to 25 mol%, respectively. When the amount of the polymer unit represented by the formula a) is too small, weatherability will be poor. In each cases where the amount of the polymer unit represented by the formula a) is too small and too large, there are problems from the viewpoint of production. When the amount of the polymer unit represented by the formula b) is too large, weatherability will be poor, and when the amount is too small, the solubility to a solvent will be lower and thus the copolymer becomes unfavorably inappropriate as a base for a solvent-based coating. It is particularly important that the polymer unit represented by the formula c) is contained in a proportion within the range mentioned above from the viewpoint of the improvement of curability without impairing various useful properties as a base for coating material. That is, when the content of the polymer unit represented by the formula c) is too high, since the solubility of the copolymer is changed and the copolymer becomes insoluble to solvents other than a specific solvent such as an alcohol, not only the adaptability as a base for the solvent-based coating is limited, but also the flexibility of the cured coating film is reduced and the gellation time (pot life) in the presence of a curing agent is reduced, whereby unfavorably impairing the applicability of a coating to a great extent. When the above content is too low, various drawbacks are caused wherein the effect for improvement of curability is lost, the curing time is increased, and the solvent resistance of the cured coating film and the stain resistance are reduced, and further the adhesive property to a base or a primer is impaired.

It is important that the copolymer of the present invention has an intrinsic viscosity of from 0.01 to 0.05 dl/g, preferably from 0.02 to 0.05 dl/g, as measured in an uncured state at 30°C in tetrahydrofuran. When the viscosity is too low, the mechanical strength tends to be low and thus the formation of the coating film becomes substantially difficult. On the other hand, when the viscosity is too high, in the case where the copolymer is used for a solvent-based coating, there is a tendency that the concentration of a solution is to be lowered from the viewpoint of the viscosity and thus the applicability is impaired. In both cases, clarity is also unfavorably lowered.

The fluorine-containing copolymer has a ratio (M_w/M_n) of a weight-average molecular weight (hereinafter referred to as M_w) and a number-average molecular weight (hereinafter referred to as M_n) in terms of a polystyrene measured by a gel permeation chromatography within a range of not more than 2.0. When M_w/M_n is larger than 2.0, the viscosity of the coating material is elevated and thus the formation of a high density coating becomes difficult. Further, it causes a drawback that the clarity of the coating film is lowered. When M_w/M_n is larger than 2.0, it causes a drawback that the coating film properties, particularly solvent resistance, will be poor.

Such a fluorine-containing copolymer can be produced by conducting copolymerization by reacting a mixture of monomers in predetermined proportions with use of a polymerization initiation source such as a polymerization initiator or an ionizing radiation in the presence or absence of a polymerization medium. Here, the most preferable method is to conduct the polymerization while supplying the monomers to the polymerization system. In a method wherein respective monomers are charged at once at an initial stage of the polymerization, the concentration of the monomers becomes low with the progress of the polymerization. By such a tendency, the polymer produced at the initial stage and the polymer produced at a later stage of the polymerization are different in molecular weight. Accordingly, the copolymer tends to have a large M_w/M_n ratio, i.e. a large molecular weight distribution. Further, when the monomers are charged at once, the concentration of the monomers becomes low at the later stage of the reaction, the reaction speed is considerably lowered, and thus this method is unfavorable from the industrial viewpoint. On the other hand, in a method wherein the polymerization is conducted while supplying the monomers to the polymerization system, since the fluctuation of the monomer concentration is small, it is possible to make the molecular weight distribution small. Further, in the method wherein the monomers are charged at once, it is necessary to make the monomer concentration low for producing a low molecular weight polymer. Namely, it causes a drawback that the yield of a polymer per one batch becomes small. However, in a method wherein the polymerization is conducted while supplying the monomers, although the monomer concentration charged at the initial stage is low, the yield of the polymer per one batch becomes large as compared with the method of charging at once. In addition, the conversion of the monomer to the polymer becomes high as compared with the method of charging at once. That is, the method wherein the

polymerization is conducted while supplying the monomers can be said to be a process for production extremely superior in the polymerization efficiency. Also, although the method for supplying the monomers may be both of a continuous method and an intermittent method, a polymer having a small molecular weight distribution can easily be obtained when the supplying is conducted as continuously as possible.

5 Particularly, when the monomers are supplied continuously so that the monomer concentration become constant, the molecular-weight distribution becomes further small. As a method for supplying the monomers so that the monomer concentration become constant, when the monomers contain a gaseous monomer, there are, for example, a method wherein the gaseous monomer is supplied in such a manner that the internal pressure of the polymerization system becomes constant and, at the same time, other monomers

10 are supplied in an amount corresponding to the supplied amount of the gaseous monomer; and a method wherein the monomers are supplied while confirming the monomer concentration in the polymerization system by e.g. a gas chromatography. Also, the monomers may be supplied in such a manner that the concentrations of the respective monomers become constant, and the monomers may be supplied in such a manner that the total concentration of the monomers become constant. If the monomers are supplied in

15 such a manner that the concentrations of respective monomers become constant, a homogeneous polymer can be obtained. If the monomers are supplied in such a manner that the total concentration of the monomers is made constant and the concentrations of respective monomers are changed, functional polymers can be sometimes obtained. Also, in a method wherein the polymerization is conducted while supplying the monomers, a polymerization initiator may be supplied with the supplying of the monomers. If

20 the polymerization is conducted while supplying the polymerization initiator, since the heat of polymerization can be easily controlled, it is possible to obtain the polymer at the same yield in an extremely short time. The polymerization may be terminated by either spontaneous termination or forced termination. It is preferable to select the method of termination appropriately taking into consideration desired properties and the like, although the molecular-weight distribution is smaller in the case of the forced termination. As the

25 method for controlling the molecular weight of the polymer, there are, for example, a method wherein the control is conducted by adjusting the amount of the polymerization initiator and/or the concentration of the monomers, and a method wherein a molecular weight modifier such as a chain transfer agent is used. The method can be freely selected depending on objects, conditions and the like.

In the above-mentioned method for producing the fluorine-containing copolymer, as the polymerization

30 initiator, water-soluble ones or oil-soluble ones can be appropriately used depending on the polymerization manner or the polymerization medium. More specifically, as the water-soluble initiator, there may be exemplified an inorganic initiator, for example, a persulfate such as potassium persulfate, a hydrogen peroxide, or a redox initiator composed of a combination of these and a reducing agent, for example, sodium hydrosulfite or sodium thiosulfate, and also a system wherein a small amount of iron, ferrous salt,

35 silver nitrate or the like is coexisted with them, etc.; an organic initiator such as a peroxide of a dibasic acid, for example, a peroxide of disuccinic acid, a peroxide of diglutaric acid or a peroxide of monosuccinic acid, and a dihydrochloride of azobisisobutylamidine. As the oil-soluble initiator, there may be exemplified a peroxyester type peroxide such as t-butylperoxy isobutyrate or t-butylperoxy acetate; a dialkylperoxy dicarbonate such as diisopropylperoxy dicarbonate; benzoylperoxide; and azobisisobutyronitrile. The

40 amount of the polymerization initiator used can be appropriately changed depending on the type, the reaction conditions of the polymerization and the like, but is usually from about 0.005 to 5% by weight, particularly from 0.05 to 0.5% by weight, based on the monomers to be copolymerized.

In conducting the copolymerization, the reaction system is not particularly limited, and a suspension polymerization, an emulsion polymerization, a solution polymerization and the like can be practiced.

45 However, from the viewpoint of the stability of the operation of the polymerization, the easiness in separation of the produced copolymer and the like, preferably practiced are the emulsion polymerization in an aqueous medium; the solution polymerization using as a solvent an alcohol such as t-butanol, ester, an aromatic compound such as xylene, or a saturated hydrocarbon halide containing one or more fluorine atoms, and the like. When the copolymerization is conducted in the aqueous medium, it is preferable to add

50 a basic buffering agent so that the pH value of the liquid during the polymerization becomes more than 4, preferably 6. In the case of the solution polymerization, the addition of a basic substance is also effective.

In such a copolymerization, the copolymerization temperature can be selected from the range of from -30°C to +150°C depending on the polymerization initiation source, types of the polymerization medium and the like to select appropriately the optimum value. However, when the copolymerization is conducted in

55 an aqueous medium, the temperature to be practiced is from about 0°C to +100°C, preferably from 10°C to 90°C. Also, although the reaction pressure can be appropriately selected, it is desirable to use the pressure usually within the range of about from 1 to 100 kg/cm², particularly from 2 to 50 kg/cm². It is possible to conduct the copolymerization appropriately in the coexistence of a chain transfer agent to

depress the intrinsic viscosity of the produced copolymer within the above-mentioned range.

The copolymer of the present invention contains as a hardening site the hydroxyl group based on the polymer unit represented by the formula c), and can be thermoset by using a curing agent such as a melamine type curing agent, a urea type curing agent, a polybasic acid type curing agent, or a block
 5 polyvalent isocyanate type curing agent which are used for conventional thermosetting acryl coating. As the melamine type curing agent, there may be exemplified a butylated melamine, a methylated melamine, an epoxy-modified melamine and the like. The melamine type curing agent can be selected from those having various modification degrees ranging from 0 to 6 depending on the use thereof, and the self condensation
 10 degree thereof can be appropriately selected. As the urea type curing agent, there may be exemplified a methylated urea, a butylated urea and the like. As the polybasic acid type curing agent, there may be exemplified a long-chain aliphatic dicarboxylic acid, an aromatic polyvalent carboxylic acid or its anhydride, and the like. As the block polyvalent isocyanate type curing agent, used is a polyvalent isocyanate mentioned below whose isocyanate group is masked with a blocking agent. With the use of the melamine or urea type curing agent, the curing can be accelerated by adding an acidic catalyst.

15 The copolymer of the present invention can be cured at an ordinary temperature by using a polyvalent isocyanate. As the polyvalent isocyanate, particularly useful are a non-yellowing diisocyanate such as hexamethylene diisocyanate or isophoronediiisocyanate, and its modified product such as a polyol modified product. When the curing is conducted at an ordinary temperature by using the polyvalent isocyanate, it is possible to accelerate the curing by an addition of a conventional catalyst such as dibutyltin dilaurate.

20 In the production of the composition for the solvent-based coating from the copolymer of the present invention, various solvents can be used, for example, an aromatic hydrocarbon such as xylene or toluene, an alcohol such as n-butanol, an ester such as butyl acetate, a ketone such as methyl isobutyl ketone, a glycol ether such as ethyl cellosolve, and also various commercially available thinners.

The mixing of such a copolymer and solvent can be conducted by using various apparatuses such as a
 25 ball mill, a paint shaker, a sand mill, a jet mill, a three-roll mill or a kneader which are usually used for producing a coating material. At this time, there may be added a pigment, a dispersion stabilizer, a viscosity modifier, a repelling agent, a gelation inhibitor, an ultraviolet absorber or the like.

When the copolymer of the present invention is used for producing a thermosetting composition for coating, namely, baking coating, a curing agent such as a melamine type curing agent, a urea type curing
 30 agent, a polybasic acid type curing agent, a block polyvalent isocyanate type curing agent or the like is simultaneously mixed in the mixing step mentioned above to produce a one-pack type coating.

On the other hand, when the composition is a normal temperature setting type coating which uses a non-block polyvalent isocyanate, the curing agent component is separately prepared to provide a two-pack type coating. In this case, the coating can provide a coating film which has a usable time of about 1 to 10
 35 hours, is cured at room temperature for from several hours to several days, and has good properties by controlling the type of isocyanate and catalyst and their amounts to be added, the concentration of the copolymer, the contents of the unit based on the hydroxyalkyl vinyl ether in the copolymer, and the like.

[BRIEF DESCRIPTION OF DRAWINGS]

40 Fig. 1 is a graph showing the relationships between the concentrations of solid contents of the coating materials, which use the fluorine-containing copolymers in Example 1 and Comparative Example 1, and the viscosity of their solutions.

45 [BEST MODE FOR CARRYING OUT THE INVENTION]

EXAMPLE 1

Into a stainless steel autoclave having an internal capacity of 2.5 l and equipped with a stirrer (pressure
 50 resistance: 30kg/cm²), 651 g of xylene, 184 g of ethanol, 19.1 g of cyclohexyl vinyl ether (hereinafter referred to as CHVE), 10.9 g of ethyl vinyl ether (hereinafter referred to as EVE), 23.5 g of ω -hydroxybutyl vinyl ether (hereinafter referred to as HBVE) and 11.6 g of potassium carbonate were charged, and cooling deaeration and pressurizing with a nitrogen gas were repeated to remove dissolved air. Then, 58.9 g of chlorotrifluoroethylene (hereinafter referred to as CTFE) was introduced into the autoclave, and the mixture
 55 was heated. When the temperature in the autoclave was elevated to 65°C, the pressure was 1.0 kg/cm²G. After that, 9 ml of a xylene solution of 50% t-butylperoxypivalate (hereinafter referred to as PBPV) was added to initiate the reaction. With the reduction of the pressure, 470 g of CTFE, 153 g of CHVE, 87 g of EVE and 188 g of HBVE were continuously added to continue the reaction while maintaining the pressure.

In the progress of the reaction, 23 ml of a xylene solution of 50% PBPV was continuously added. After 14 hours, the feeding of respective monomers was stopped and the reaction was continued until 0.5 kg/cm²G, and then the autoclave was cooled with water to terminate the reaction. After the temperature lowered to room temperature, an unreacted monomer was purged and the autoclave was opened. The polymer thus obtained was isolated by drying under reduced pressure.

The yield of polymer was 991 g, the concentration of polymer was 49.9% and the degree of reaction of the monomers was 96.8%. The obtained polymer had an intrinsic viscosity (in THF, at 30 °C) ($[\eta]$) of 0.040 dl/g. The weight-average molecular weight and number-average molecular weight in terms of polystyrene as measured by GPC, and their ratio were 3500, 6500 and 1.86, respectively. The polymer composition of the copolymer quantified by identification by use of ¹³Cnmr spectrum was 51.0/14.9/15.1/19.0 with respect to CTFE/CHVE/EVE/HBVE (mol%).

EXAMPLES 2 to 4

Copolymers were produced under the conditions as shown in Table 1. The values of $[\eta]$, Mw, Mn, Mw/Mn and the content of HBVE of the obtained copolymers are also indicated.

The conditions of polymerization not indicated in the Table were the same as in Example 1.

Table 1

		Example 2	Example 3	Example 4
Charging at initial stage	CTFE (g)	29.5	58.9	
	TFE			50.6
	CHVE	9.6	19.1	19.1
	EVE	5.5	7.3	10.9
	IBVE			
	HBVE	11.8	29.4	23.5
	PBPV (ml)	13.5	9.0	8.0
Charging at posterior stage	CTFE (g)	179.5	470	
	TFE			404
	CHVE	48.7	153	153
	EVE	27.8	87	87
	IBVE			
	HBVE	59.8	188	188
	PBPV (ml)	45.5	22.0	19.0
	Polymerization pressure (kg/cm ² G)	0.5	1.0	3.0
	Polymerization time (hr)	11	15	14
	Yield of polymer (%)	90.7	94.0	95.5
	[η]	0.019	0.041	0.045
	Mw	2500	6320	6460
	Mn	1810	3360	3400
	Mw/Mn	1.38	1.88	1.90
	HBVE content (mol%)	19.5	24.4	19.1

IBVE is isobutyl vinyl ether
TFE is tetrafluoroethylene

Table 1 (continued)

		Example 5	Comp. Ex. 1	Comp. Ex. 2
Charging at initial stage	CTFE (g)		198.7	332.4
	TFE	50.6		
	CHVE	15.3	64.6	108.1
	EVE		36.9	61.8
	IBVE	25.2		
	HBVE	11.8	79.3	132.7
	PBPV (ml)	10.0	7.0	4.3
Charging at posterior stage	CTFE (g)			
	TFE	404		
	CHVE	153		
	EVE			
	IBVE	202		
	HBVE	94		
	PBPV (ml)	21.0		
	Polymerization pressure (kg/cm ² G)	3.0	2.6 ± 0.4	3.8 ± 0.2
	Polymerization time (hr)	15	10	6
	Yield of polymer (%)	93.0	85.4	87.0
	[η]	0.038	0.040	0.093
	Mw	5640	7380	15400
	Mn	3050	3350	5960
	Mw/Mn	1.85	2.20	2.59
	HBVE content (mol%)	14.8	19.5	19.3

IBVE is isobutyl vinyl ether

TFE is tetrafluoroethylene

COMPARATIVE EXAMPLE 1

Into a stainless steel autoclave having an internal capacity of 2.5 l and equipped with a stirrer (pressure resistance: 30 kg/cm²), 1098 g of xylene, 310 g of ethanol, 64.6 g of cyclohexyl vinyl ether, 36.9 g of ethyl vinyl ether, 79.3 g of ω -hydroxybutyl vinyl ether and 4.3 g of potassium carbonate were charged, then

dissolved air was removed by repeating the cooling deaeration and pressurizing with a nitrogen gas. Then, 198.7 g of chlorotrifluoroethylene was introduced into the autoclave, and heated. When the temperature in the autoclave was elevated to 65°C, the pressure was 2.6 kg/cm²G. After that, 7 ml of xylene solution of 50% t-butylperoxypivalate was added thereto to initiate the reaction. Then, the reaction was continued under stirring for 10 hours, and when the pressure was lowered to 0.4 kg/cm²G, the autoclave was cooled with water to terminate the reaction. After the temperature was lowered to room temperature, unreacted monomers were purged, and the autoclave was opened. The obtained polymer was isolated by drying under reduced pressure. The composition of the obtained copolymer was 50.4/15.2/14.9/19.5 by molar ratio with respect to CTFE/CHVE/EVE/HBVE, respectively. Values $[\eta]$, Mw, Mn and Mw/Mn of the copolymer are shown in Table 1.

COMPARATIVE EXAMPLE 2

The reaction of Comparative Example 1 was repeated in the same manner as in Comparative Example 1 except for the polymerization conditions not indicated in Table 1. Values $[\eta]$, Mw and Mn of the copolymer are also indicated in Table 1.

TEST EXAMPLES

The copolymers of Examples 1 to 5 and Comparative Examples 1 to 2 were used for production of coating materials and applied by coating under the conditions as indicated in Table 2.

Fig. 1 shows the relationships between the concentrations of solid contents of the coating materials and the viscosity of their solutions at 25°C. Table 3 shows the properties of the coated film.

Table 2

Recipe for coating	Copolymer	100 parts by weight
	Xylene	54
	Melamine resin varnish *1	50
	n-Butanol	20
	Solvesso #100 *2	20
Coating condi- tions	Substrate	An aluminum plate *4 treated with Allodine *3
	Undercoat	Acrylmelamine black coating
	Overcoat	The above composition was added with Solvesso *5 and diluted so that Ford cup viscosity become 23 sec./20°C, and then applied by spray coating. Baking was conducted at 140°C for 30 minutes. The film thickness was about 30 μ .

*1 Mitsui Toatsu Chemicals, Inc. LIVAN-20SE-60

*2 Esso Petroleum Co.

*3 NIPPON PAINT CO., LTD.

*4 Mitsubishi Alumi Co. 5052H34

*5 Esso Petroleum Co.

Table 3

Copolymer		Example 1	Example 2	Example 3	Example 4
Clarity of coating film	ICM value *1	90.4	93.0	90.5	87.5
	PGD value *2	0.9	0.9	0.9	0.9
Solvent resistance *3		◎	◎	◎	◎
Crosscut test *4		100/100	100/100	100/100	100/100
Pencil hardness *5		H	H	H	F
Shock resistance *6		○	○	○	○

Table 3 (continued)

Copolymer		Example 5	Comp. Ex. 1	Comp. Ex. 2
Clarity of coating film	ICM value *1	88.5	81.8	85.0
	PGD value *2	0.9	0.6	0.7
Solvent resistance *3		◎	◎	○
Crosscut test *4		100/100	100/100	100/100
Pencil hardness *5		F	H	F
Shock resistance *6		○	×	○

*1 Clarity measuring apparatus ICM-ID model produced by Suga Shikenki K.K.

5 *2 Clarity and gloss measuring apparatus PGD IV model produced by Nihon Shikisai Kenkyusho

10 *1 and *2 are both methods for measuring the appearance of the coating film objectively. In both cases, the larger the value is, the superior the clarity of the
15 image is.

*3 After the xylol rubbing test (100 times) was
20 conducted, the appearance of the coating film was observed visually.

25 ◎: no change, ○: substantially no change,
△: a little swelled

*4 100 crosscuts were made in accordance with JIS-K-5400
30 6.15. A cellophane adhesive tape was adhered with pressure on the crosscuts. Then, the cellophane tape was detached therefrom and the number of the
35 remaining crosscuts was counted to determine the adhesiveness.

40 *5 Conducted in accordance with JIS-K-5400 6.14 (pencil scratch test)

*6 Conducted in accordance with Du Pont impact test
45 (1/2"φ, 500 g, 40 cm).

○: good, X: formation of crack or peeling off

50 [INDUSTRIAL APPLICABILITY]

The copolymer of the present invention is excellent in surface hardness and gloss when used as a base for coating, and can provide under mild conditions a coating film which has visibility and is excellent in
55 solvent resistance, stain resistance and weatherability. The copolymer is useful as not only a baking coating which is applied to a color steel plate, a color aluminum plate, an aluminum sash and the like, but also dry-type coating which can be practiced in working place. The material of the substrate is not limited to a metal, and the copolymer is extremely useful as a coating for an inorganic material such as glass, cement or


concrete, and an organic material such as a plastic, for example, FRP, polyethylene, polypropylene, ethylene-vinyl acetate copolymer, nylon, acryl, polyester, ethylene-polyvinyl alcohol copolymer, vinyl chloride or vinylidene chloride, or lumbars. The copolymer of the present invention is particularly useful as a raw material for a high solid coating which is attributable to prevent environmental pollution and as a raw material of a coating for vehicles which has a high clarity.

Claims

1. A fluorine-containing copolymer comprising polymer units represented by the formulas a), b) and c), respectively in amounts of from 40 to 60 mol%, from 25 to 55 mol% and from 5 to 25 mol%, respectively:

a) $(\text{CF}_2 - \text{CFX})$ X is fluorine, chlorine or a perfluoroalkyl or perfluoroalkoxy group having 1 to 3 carbon atoms,


b)



R¹ is hydrogen or a methyl Group,

R² is an unsubstituted or fluorine-substituted straight-chain, branched-chain or alicyclic alkyl group having 1 to 12 carbon atoms, and t is 0 or 1, and

c)



R³ is hydrogen or a methyl group, R⁴ is a hydroxyl group-containing unsubstituted or fluorine-substituted straight-chain, branched-chain or alicyclic alkyl group,

characterized by having an intrinsic viscosity of from 0.01 to 0.05 dl/g as measured in an uncured state at 30°C in tetrahydrofuran, the ratio of the weight-average molecular weight and number-average molecular weight measured by a gel permeation chromatography being not more than 2.0.

2. The fluorine-containing copolymer according to Claim 1, wherein the polymer unit represented by the formula a) is a unit derived from at least one monomer selected from tetrafluoroethylene and chlorotrifluoroethylene, the polymer unit represented by the formula b) is a unit derived from at least one monomer selected from alkyl vinyl ether, cycloalkyl vinyl ether and vinyl carboxylate, and the polymer unit represented by the formula c) is a unit derived from at least one monomer selected from hydroxyalkyl vinyl ether and hydroxycycloalkyl vinyl ether.

3. The fluorine-containing copolymer according to Claim 2, wherein the copolymer comprises, as the polymer unit represented by the formula b), at least one unit derived from alkyl vinyl ether and at least one unit derived from cycloalkyl vinyl ether.

4. A process for producing a fluorine-containing copolymer as defined in claim 1 which comprises polymerizing monomers represented by the formulas a'), b') and c') respectively in the presence of a polymerization initiator, wherein the polymerization is conducted while supplying the monomers to a polymerization system:

a') $\text{CF}_2 = \text{CFX}$ X is fluorine, chlorine or a perfluoroalkyl or perfluoroalkoxy group having 1 to 3 carbon atoms,




concrete, and an organic material such as a plastic, for example, FRP, polyethylene, polypropylene, ethylene-vinyl acetate copolymer, nylon, acryl, polyester, ethylene-polyvinyl alcohol copolymer, vinyl chloride or vinylidene chloride, or lumbars. The copolymer of the present invention is particularly useful as a raw material for a high solid coating which is attributable to prevent environmental pollution and as a raw material of a coating for vehicles which has a high clarity.

Claims

1. A fluorine-containing copolymer comprising polymer units represented by the formulas a), b) and c), respectively in amounts of from 40 to 60 mol%, from 25 to 55 mol% and from 5 to 25 mol%, respectively:

a) $(CF_2 - CFX)$ X is fluorine, chlorine or a perfluoroalkyl or perfluoroalkoxy group having 1 to 3 carbon atoms,


b)



R¹ is hydrogen or a methyl Group,

R² is an unsubstituted or fluorine-substituted straight-chain, branched-chain or alicyclic alkyl group having 1 to 12 carbon atoms, and l is 0 or 1, and

c)



R³ is hydrogen or a methyl group, R⁴ is a hydroxyl group-containing unsubstituted or fluorine-substituted straight-chain, branched-chain or alicyclic alkyl group,

characterized by having an intrinsic viscosity of from 0.01 to 0.05 dl/g as measured in an uncured state at 30 °C in tetrahydrofuran, the ratio of the weight-average molecular weight and number-average molecular weight measured by a gel permeation chromatography being not more than 2.0.

2. The fluorine-containing copolymer according to Claim 1, wherein the polymer unit represented by the formula a) is a unit derived from at least one monomer selected from tetrafluoroethylene and chlorotrifluoroethylene, the polymer unit represented by the formula b) is a unit derived from at least one monomer selected from alkyl vinyl ether, cycloalkyl vinyl ether and vinyl carboxylate, and the polymer unit represented by the formula c) is a unit derived from at least one monomer selected from hydroxyalkyl vinyl ether and hydroxycycloalkyl vinyl ether.


3. The fluorine-containing copolymer according to Claim 2, wherein the copolymer comprises, as the polymer unit represented by the formula b), at least one unit derived from alkyl vinyl ether and at least one unit derived from cycloalkyl vinyl ether.

4. A process for producing a fluorine-containing copolymer as defined in claim 1 which comprises polymerizing monomers represented by the formulas a'), b') and c') respectively in the presence of a polymerization initiator, wherein the polymerization is conducted while supplying the monomers to a polymerization system:


a') $CF_2 = CFX$ X is fluorine, chlorine or a perfluoroalkyl or perfluoroalkoxy group having 1 to 3 carbon atoms,



b')

R¹ is hydrogen or a methyl group,R² is an unsubstituted or fluorine-substituted straight-chain, branched-chain or alicyclic alkyl group having 1 to 12 carbon atoms, and l is 0 or 1, and

c')

R³ is hydrogen or a methyl group, R⁴ is a hydroxyl group-containing unsubstituted or fluorine-substituted straight-chain, branched-chain or alicyclic alkyl group.

5. The process according to Claim 4, wherein the polymerization is conducted while supplying a polymerization initiator to the polymerization system.

6. The process according to Claim 4, wherein the monomer represented by the formula a') is at least one monomer selected from tetrafluoroethylene and chlorotrifluoroethylene, the monomer represented by the formula b') is at least one monomer selected from alkyl vinyl ether, cycloalkyl vinyl ether and vinyl carboxylate, and the monomer represented by the formula c') is at least one monomer selected from hydroxyalkyl vinyl ether and hydroxycycloalkyl vinyl ether.

7. The process according to Claim 6, wherein at least one alkyl vinyl ether and at least one cycloalkyl vinyl ether are used as the monomer represented by the formula b').

8. A coating composition which comprises the fluorine-containing copolymer of Claim 1 and a curing agent.

9. The coating composition according to Claim 8, wherein the curing agent is at least one selected from a melamine type curing agent, a urea type curing agent, a polybasic acid type curing agent, the blocked polyvalent isocyanate type curing agent and a polyvalent isocyanate type curing agent.

10. A composition of a top coat for an automobile which comprises the fluorine-containing copolymer of Claim 1 and a curing agent.


Patentansprüche

1. Fluorenthaltendes Copolymer, umfassend Polymereinheiten, wiedergegeben durch die Formeln a), b) und c), in Mengen von 40 bis 60 Mol-%, 25 bis 55 Mol-% bzw. 5 bis 25 Mol-%:

a) (CF₂ - CFX)

X ist Fluor, Chlor oder eine Perfluoralkyl- oder Perfluoralkoxygruppe mit 1 bis 3 Kohlenstoffatomen,


b)





R¹ ist Wasserstoff oder eine Methylgruppe, R² ist eine nichtsubstituierte oder fluorsubstituierte, geradkettige, verzweigt-kettige oder alicyclische Alkylgruppe mit 1 bis 12 Kohlenstoffatomen und l ist 0 oder 1 und

c)



R³ ist Wasserstoff oder eine Methylgruppe, R⁴ ist eine hydroxylgruppenenthaltende, nichtsubstituierte oder fluorsubstituierte, geradkettige, verzweigt-kettige oder alicyclische Alkylgruppe,

gekennzeichnet durch eine intrinsische Viskosität von 0,01 bis 0,05 dl/g, gemessen in ungehärtetem Zustand bei 30 °C in Tetrahydrofuran, wobei das Verhältnis des gewichtsmittleren Molekulargewichts und des zahlenmittleren Molekulargewichts, gemessen durch Gelpermeationschromatographie, nicht mehr als 2,0 ist.

2. Fluorenthaltendes Copolymer nach Anspruch 1, wobei die Polymereinheit, wiedergegeben durch die Formel a), eine Einheit ist, abgeleitet von mindestens einem Monomer, ausgewählt aus Tetrafluorethylen und Chlortrifluorethylen, die Polymereinheit, wiedergegeben durch die Formel b), eine Einheit ist, abgeleitet von mindestens einem Monomer, ausgewählt aus Alkylvinylether, Cycloalkylvinylether und Vinylcarboxylat und die Polymereinheit, wiedergegeben durch die Formel c), eine Einheit ist, abgeleitet von mindestens einem Monomer, ausgewählt aus Hydroxyalkylvinylether und Hydroxycycloalkylvinylether.


3. Fluorenthaltendes Copolymer nach Anspruch 2, wobei das Copolymer als Polymereinheit, wiedergegeben durch die Formel b), mindestens eine Einheit, abgeleitet von Alkylvinylether und mindestens eine Einheit, abgeleitet von Cycloalkylvinylether, umfaßt.

4. Verfahren zur Herstellung eines fluorenthaltenden Copolymers nach Anspruch 1, umfassend Polymerisation von Monomeren, wiedergegeben durch die Formeln a'), b') bzw. c'), in Gegenwart eines Polymerisationsstarters, wobei die Polymerisation ausgeführt wird während die Monomere zu einem Polymerisationssystem gegeben werden:

a') $\text{CF}_2 = \text{CFX}$,


X ist Fluor, Chlor oder eine Perfluoralkyl- oder Perfluoralkoxygruppe mit 1 bis 3 Kohlenstoffatomen,

b')



R¹ ist Wasserstoff oder eine Methylgruppe, R² ist eine nichtsubstituierte oder fluorsubstituierte, geradkettige, verzweigt-kettige oder alicyclische Alkylgruppe mit 1 bis 12 Kohlenstoffatomen und l ist 0 oder 1 und

c')



R³ ist Wasserstoff oder eine Methylgruppe, R⁴ ist eine hydroxylgruppenenthaltende, unsubstituierte oder fluorsubstituierte, geradkettige, verzweigt-kettige oder alicyclische Alkylgruppe.




5. Verfahren nach Anspruch 4, wobei die Polymerisation ausgeführt wird während der Polymerisationsstarter dem Polymerisationssystem zugeführt wird.
6. Verfahren nach Anspruch 4, wobei das durch Formel a') wiedergegebene Monomer mindestens ein Monomer ist, ausgewählt aus Tetrafluorethylen und Chlortrifluorethylen, das durch Formel b') wiedergegebene Monomer mindestens ein Monomer ist, ausgewählt aus Alkylvinylether, Cycloalkylvinylether und Vinylcarboxylat und das durch Formel c') wiedergegebene Monomer mindestens ein Monomer ist, ausgewählt aus Hydroxyalkylvinylether und Hydroxycycloalkylvinylether.
7. Verfahren nach Anspruch 6, wobei mindestens ein Alkylvinylether und mindestens ein Cycloalkylvinylether als Monomer, wiedergegeben durch die Formel b'), verwendet werden.
8. Beschichtungsmasse, umfassend das fluorenthaltende Copolymer nach Anspruch 1 und einen Härter.
9. Beschichtungsmasse nach Anspruch 8, wobei der Härter mindestens ausgewählt ist aus einem Härter vom Melamintyp, einem Härter vom Harnstofftyp, einem Härter vom mehrbasigen Säuretyp, einem Härter vom blockierten, mehrwertigen Isocyanattyp und einem Härter vom mehrwertigen Isocyanattyp.
10. Masse als Decklack für Kraftfahrzeuge, umfassend das fluorenthaltende Copolymer nach Anspruch 1 und einen Härter.

Revendications

1. Copolymère contenant du fluor, comportant des unités de polymère représentées par les formules a), b) et c), en quantités respectives de 40 à 60 % en moles, de 25 à 55 % en moles et de 5 à 25 % en moles :


a) $(CF_2 - CFX)$ X représentant le fluor, le chlore ou un groupe perfluoroalkyle ou perfluoroalkoxy présentant de 1 à 3 atomes de carbone,

b)



R^1 représentant l'hydrogène ou un groupe méthyle, R^2 représentant un groupe alkyle alicyclique, à chaîne linéaire ou à chaîne ramifiée, non substitué ou substitué par le fluor, présentant de 1 à 12 atomes de carbone, et x vaut 0 ou 1, et

c)




R^3 représentant l'hydrogène ou un groupe méthyle, R^4 représentant un groupe alkyle alicyclique, à chaîne linéaire ou à chaîne ramifiée, non substitué ou substitué par de fluor, contenant un groupe hydroxyle,


caractérisé en ce qu'il présente une viscosité intrinsèque de 0,01 à 0,05 dl/g, mesurée dans un état non durci à 30°C dans de tétrahydrofurane, de rapport entre le poids moléculaire moyen en poids et de poids moléculaire moyen en nombre mesurés par chromatographie par perméation de gel n'étant pas supérieur à 2,0.



2. Copolymère contenant du fluor selon la revendication 1, dans lequel d'unité de polymère représentée par la formule a) est une unité dérivée d'au moins un monomère choisi parmi le tétrafluoroéthylène et de chlorotrifluoroéthylène, l'unité de polymère représentée par la formule b) est une unité dérivée d'au moins un monomère choisi parmi un éther d'alkyle et de vinyle, un éther de cycloalkyle et de vinyle et un carboxylate de vinyle, et l'unité de polymère représentée par la formule c) est une unité dérivée d'au moins un monomère choisi parmi l'éther d'hydroxyalkyle et de vinyle et l'éther d'hydroxycycloalkyle et de vinyle.
3. Copolymère contenant du fluor selon la revendication 2, dans lequel de copolymère comporte comme unité de polymère représentée par la formule b) au moins une unité dérivée d'un éther d'alkyle et de vinyle et au moins une unité dérivée d'un éther de cycloalkyle et de vinyle.
4. Procédé de fabrication d'un copolymère contenant du fluor selon la revendication 1, qui comprend la polymérisation de monomères représentés par les formules a'), b') et c'), respectivement, en présence d'un initiateur de polymérisation, dans lequel la polymérisation est conduite tout en apportant les monomères à un système de polymérisation:
- a') $\text{CF}_2 = \text{CFX}$ X représentant le fluor, le chlore ou un groupe perfluoroalkyle ou perfluoroalkoxy présentant de 1 à 3 atomes de carbone,
- b')



- R¹ représentant l'hydrogène ou un groupe méthyle, R² représentant un groupe alkyle alicyclique, à chaîne linéaire ou à chaîne ramifiée, non substitué ou substitué par le fluor, présentant de 1 à 12 atomes de carbone, et t vaut 0 ou 1, et
- c')



- R³ représentant l'hydrogène ou un groupe méthyle, R⁴ représentant un groupe alkyle alicyclique, à chaîne linéaire ou à chaîne ramifiée, non substitué ou substitué par le fluor, et contenant un groupe hydroxyle.
5. Procédé selon la revendication 4, dans lequel la polymérisation est conduite tout en apportant un initiateur de polymérisation au système de polymérisation.
6. Procédé selon la revendication 4, dans lequel le monomère représenté par la formule a') est au moins un monomère choisi parmi le tétrafluoroéthylène et le chlorotrifluoroéthylène, le monomère représenté par la formule b') étant au moins un monomère choisi parmi un éther d'alkyle et de vinyle, un éther de cycloalkyle et de vinyle et un carboxylate de vinyle, et le monomère représenté par la formule c') est au moins un monomère choisi parmi un éther d'hydroxyalkyle et de vinyle et un éther d'hydroxycycloalkyle et de vinyle.
7. Procédé selon la revendication 6, dans lequel au moins un éther d'alkyle et de vinyle et au moins un éther de cycloalkyle et de vinyle sont utilisés comme monomère représenté par la formule b').
8. Composition de revêtement qui comprend le copolymère contenant du fluor selon la revendication 1, et un agent de durcissement.



9. Composition de revêtement selon la revendication 8, dans laquelle l'agent de durcissement est au moins un agent de durcissement choisi parmi un agent de durcissement du type mélamine, un agent de durcissement du type urée, un agent de durcissement du type polyacide, l'agent de durcissement du type isocyanate polyvalent bloqué et un agent de durcissement du type isocyanate polyvalent.

5

10. Composition d'une couche supérieure de revêtement pour une voiture automobile, qui comprend le copolymère contenant du fluor selon la revendication 1 et un agent de durcissement.

10

15

20

25

30

35

40

45

50

55