

ABSTRACT OF DISCLOSURE**METHOD FOR MANUFACTURING POLYSTYRENE TYPE BEADS AND
EXPANDABLE POLYSTYRENE TYPE BEADS**

A method for manufacturing polystyrene type beads and expandable polystyrene type beads comprises the step of
5 suspension polymerization of a styrene type monomer in an aqueous medium under agitation at an agitation blade tip speed of 2.3 to 5.5m/sec under the presence of a slightly water-soluble phosphate and a water-soluble sulfite and/or water soluble persulfate.

2-8730032

JUL 1980