

## ABSTRACT

LIQUID CRYSTALLINE POLYMER COMPOSITION AND  
MOLDED ARTICLE MADE OF THE SAME

5      Provided is a liquid crystalline polymer composition comprising: 100 parts by weight of a LCP, and equal to or more than 0.01 and less than 1 part by weight of a low temperature softening inorganic glass filler whose softening temperature is equal to or less than 550°C. The composition can provide a molded article which cause no or less blister formation upon reflow soldering using a lead-free solder.

No Figure



\*162162\*



\*G00002\*