

THIS SHEET HAS BEEN
REPLACED

ABSTRACT

POLYESTER RESIN COMPOSITION AND PROCESS
FOR THE PREPARATION THEREOF

Polyester compositions exhibiting decreased distortion (warping), improved processability and productivity are produced by melt-blending a thermoplastic polyester resin with between 3 and 65% by weight of a fibrous reinforcing medium, and between 3 and 65% by weight of binder-agglomerated glass granules.

This Sheet Has Been Replaced

