

N/66071A

S P E C I F I C A T I O N

F O R

PATENT APPLICATION

I N

S I N G A P O R E

in the name of W.R. GRACE & CO.-CONN., incorporated in
Connecticut, of 1114 Avenue of the Americas, New York, New York
10036, USA

ENTITLED

"HYDRAULIC CEMENT SET-ACCELERATING ADMIXTURES
INCORPORATING GLYCOLS"

☒ Description : paged 1 to paged 9
☒ Claim(s) : paged 10 to paged 12
☐ Drawing(s) : paged 1 to paged 1
☒ Abstract : paged 13 to paged 1

**HYDRAULIC CEMENT SET-ACCELERATING ADMIXTURES
 INCORPORATING GLYCOLS**

5 This invention relates to improvements in
 set-accelerating admixtures for hydraulic cement
 compositions such as mortars, grouts and concretes.
 More particularly the invention relates to novel
 set-accelerating admixtures and methods for
 set-acceleration employing the addition of certain low
 10 molecular weight glycols, e.g., glycerol and ethylene
 glycol.

15 Set accelerators are used when it is necessary to
 work with hydraulic cement compositions at freezing or
 near-freezing temperatures. The rate of hydration of
 Portland cement, for example, is very dependent on
 temperature, such that, at lower temperatures, Portland
 cement compositions will often harden at a rate slower
 than desired unless the hardening process is
 20 accelerated. In addition to accelerating the set, it is
 desirable to also attain an increase in the rate of
 early strength development at normal or low
 temperatures. This reduces curing and protection
 periods necessary to achieve specified strengths in
 25 concrete. Some techniques for accelerating the set are:
 increasing the proportion of cement in the mix, heating
 the mix, and using chemical admixtures that act on the
 components of the mix to increase the rate at which the
 cement paste sets.

30 Several chemical set accelerators are well-known.
 They include alkali hydroxides, silicates,
 fluorosilicates, calcium formate, sodium chloride,



calcium chloride, and calcium nitrate and calcium nitrite.

5 Calcium chloride is widely used because it is easy and inexpensive to produce and its effects on hydraulic cement are predictable and well-documented. However, like sodium chloride, it has the disadvantage of corroding steel. Thus, it can cause the corrosion of steel reinforcing bars in concrete. Other drawbacks of calcium chloride use include reduced compressive
10 strength at later ages, reduced response to air entrainment, and blotching of hardened concrete surfaces (Concrete Admixtures, Dodson: Van Nostrand Reinhold, 1990).

15 It is thus an object of this invention to provide new set-accelerating admixtures which reduce the set time of hydraulic cement compositions at lower temperatures, without inducing or promoting corrosion of steel reinforcement. Further objects of the invention are to provide methods for preparing such cement compositions
20 and to provide methods for reducing the set time of hydraulic cement compositions.

25 This invention is directed toward new hydraulic cement set-accelerating admixture compositions, to cement compositions containing such admixtures, and to methods for preparing said cement compositions. The admixture compositions comprise a set accelerator component and a C₂ to C₆ glycol component present in an amount effective to increase the set acceleration
30 properties of the set-accelerator component. The invention further relates to a method of making a hydraulic cement composition comprising adding to a cement composition comprising a hydraulic cement binder, a set-accelerating component, and a C₂ to C₆ glycol
35 component in an amount effective to increase



the set-acceleration properties of the set-accelerator component, and to a cement composition comprising a hydraulic cement binder, a set-accelerating component, and a C₂ to C₆ glycol component present in an amount effective to increase the set acceleration properties of the set-accelerator component.

It has been found that admixtures comprising a set-accelerating compound and certain low molecular weight glycols are surprisingly effective in reducing the set time of hydraulic cement compositions. Such admixtures are also found to be quite effective at lower working temperatures, i.e., below about 50°F. It appears that these low molecular weight glycols increase the set-acceleration properties of a set-accelerating compound. Additionally, admixtures of this invention may be formulated in such a way as to produce a composition that will inhibit corrosion in steel reinforcing bars commonly imbedded in cement compositions.

The term "glycol" as used herein is intended to mean two to six carbon, i.e., "C₂ to C₆", aliphatic di- and trihydric alcohols. Glycols suitable for use in the invention are those such as ethylene glycol, propylene glycol, and glycerol. Other compounds meeting the above definition will be apparent to those skilled in the art. Until now these compounds have not been known to have any set-accelerating qualities, i.e., they have been used primarily as grinding aids and set retarders. For this reason these compounds were not seen as having any value as part of a set-accelerating admixture. As such it was surprising to the inventors that a glycol as described herein could be used with a set-accelerating compound to significantly increase the set acceleration of a cement composition over that obtained by the addition of the set accelerator alone to



the cement composition. Thus this invention utilizes the glycol component to give the set acceleration of the cement composition containing the set accelerator a desired "boost."

5 The term "cement composition" as used herein refers to pastes, mortars and concrete compositions comprising a hydraulic cement binder. The above terms are terms of art. Pastes are mixtures composed of a hydraulic cement binder, for example, Portland cement, either alone or in
10 combination with fly ash, silica fume or blast furnace slag, and water; mortars are pastes additionally including fine aggregate, and concretes are mortars additionally including coarse aggregate. Such compositions may additionally include other admixtures
15 such as defoaming agents, air-entraining or detraining agents, set retarders, water reducing agents, superplasticizers, and other components known to those in the art for altering properties of the composition. The cement compositions of this invention are formed by
20 mixing required amounts of certain materials, e.g., a hydraulic cement, water, and fine or coarse aggregate, as may be applicable for the particular cement composition being formed.

 The set-accelerating component may be any compound
25 which, when added to a cement composition (as described above), reduces the amount of time required for the cement composition to harden. For example, an alkali or alkaline earth metal salt which is a salt of an organic or inorganic acid may be employed. Although the
30 following list is not meant to be limiting, examples of these compounds are alkali or alkaline earth metal nitrate, nitrite, and formate; alkali or alkaline earth metal salts of Group VI halogen and pseudohalogen acids, such as alkali or alkaline earth metal chloride,
35 bromide, iodide, thiocyanate, thiosulfate and



perchlorate; and alkali or alkaline earth metal
aluminates, silicates, and hydroxides, e.g., sodium
hydroxide. Calcium salts are particularly advantageous,
especially calcium nitrate, calcium chloride, and
5 calcium formate, and calcium nitrite.

It is also feasible to use a mixture of alkali or
alkaline earth metal salts, for example, a mixture of
calcium nitrate and calcium nitrite. Any ratio of the
salts used may be employed; in a preferred calcium
10 nitrate/calcium nitrite mixture, a range of weight
ratios of from about 1:3 to 3:1 may be used. The
inventors have found that such an admixture, using a
calcium nitrate/calcium nitrite mixture as the
set-accelerator component, is beneficial in inhibiting
15 corrosion in steel reinforcing bars commonly imbedded in
cement compositions.

If the set-accelerating component and glycol
component are added to the cement composition
separately, the glycol may be added, generally, in
20 percent solids on solids ("% s/s"), in the range of
about 0.05% s/s to 1.0% s/s (based on the weight of
hydraulic cement binder in the cement composition), with
a preferred range of about 0.1% s/s to 0.75% s/s, such
concentrations being generally those which provide the
25 desired boost in acceleration. The set-accelerating
component may be added in the usual amounts necessary
for set-acceleration, but generally in a range of from
about 0.05% s/s to about 4.0% s/s. (Note that through
the use of a glycol component of the invention, it is
30 also possible to reduce the amount of set-accelerator
component normally required for a certain level of set
acceleration, because of the better set-acceleration
provided by the combination of the glycol and the
35 set-accelerator.)



However, the inventors find it is preferable to combine the glycol component and the set-accelerating component in desired amounts before addition to a cement composition, so only one composition need be metered out and added to the cement composition. This is a simpler and more precise method than adding each component separately and reduces the opportunity for error in dispensing the correct formulation. If the set-accelerating component and glycol component are to be mixed before addition to a cement composition, the glycol component and the set-accelerating component may be combined in any proportion effective to give the desired results. Generally, the amount of the glycol in the mixture may range from about 0.5 to 40 weight % (based on the combined weight of glycol component and accelerator component), and preferably from about 2 to 30 weight %.

An admixture of the invention should be mixed into a hydraulic cement composition in an amount effective to allow the acceleration desired. The specific amount of the admixture can be readily determined and will depend on the cement composition, the ratio of components of the composition, and the degree of acceleration desired. The admixture is generally added to a cement composition in an amount which, as noted above, provides a glycol concentration of from about 0.05% s/s to 1.0% s/s, preferably from about 0.1% s/s to 0.75% s/s, such concentrations being generally those which provide the desired boost in acceleration.

The admixtures of this invention can be added to cement compositions in any conventional manner familiar to those in the art. The admixture should be substantially uniformly mixed with the cement composition.

The following examples are given for illustrative purposes only. Unless otherwise indicated, all parts and proportions are by weight.

Example 1

5 An admixture was prepared consisting of calcium nitrate and calcium nitrite, in a 2:1 ratio, in water. The total % solids of the admixture was 42.6%.

Example 2

10 An admixture of the invention was prepared consisting of calcium nitrate, calcium nitrite, and glycerol, in a 2:1:1 ratio (by weight), in water. The total % solids of the admixture was 45%.

Example 3

15 The admixtures prepared in Examples 1 and 2 were each added individually to mortars prepared using a Type I-II Portland cement, sand, and a water to cement ratio of 0.45. A blank mortar, containing no admixture, was also prepared. Each mortar was prepared by combining 4500g of sand, 900g of H₂O, and 2000g of cement in a Hobart mixer until homogeneous. A sufficient amount of the admixture solutions of Examples 1 and 2 was added to provide an admixture solids concentration of 0.5% s/s, and 2.0% s/s, based on the weight of hydraulic cement in the admixture. Set times were measured in accordance with ASTM C403. The test was performed at 55°F.

25 Table 1 presents the data, which demonstrate, at different addition rates, the utility of adding a glycol component of the invention (glycerol), to improve the performance of a set-accelerating compound, in this case
30 a mixture of calcium nitrate and calcium nitrite.



Example 4

An admixture of the invention was prepared consisting of calcium nitrate, calcium nitrite and glycerol, in a proportion of 60:16:24 (by weight), in water. The total
5 % solids of the admixture was 45%.

Example 5

The admixture prepared in Example 4 was added to mortars prepared using three different Type I-II Portland cements ("Cements 1, 2, and 3"), sand, and a
10 water to cement ratio of 0.45. Blank mortars, containing no admixture, were also prepared with each cement. Each mortar was prepared by combining 4500g of sand, 900g of H₂O, and 2000g of cement in a Hobart mixer until homogeneous. A sufficient amount of the admixture
15 solution of Example 4 was added to provide an admixture solids concentration of 2.5% s/s, based on the weight of hydraulic cement in the admixture. Set times were measured in accordance with ASTM C403. The test was performed at 40°F.

20 Table 2 presents the results, which show the set time performance with the three cement types. The data demonstrate the cold-temperature performance of a set accelerating cement admixture of the invention.

The preceding description of the invention has been
25 intended to illustrate rather than limit the invention. The inventors intend that various modifications or changes be made within the scope of the appended claims without departing from the spirit of the invention.



Table 1

<u>Admixture of Example #</u>	<u>Initial Set Time (hr)</u>	<u>Change In Initial Set Time (hr)</u>
blank	11.08	-
1 (at 0.5% s/s)	8.94	2.14
2 (at 0.5% s/s)	7.97	3.11
1 (at 2.0% s/s)	5.05	6.03
2 (at 2.0% s/s)	3.74	7.34

Table 2

<u>Admix. of Example #</u>	<u>Initial Set Time (hr)</u>			
	<u>Cement 1</u>	<u>Cement 2</u>	<u>Cement 3</u>	<u>Avg.</u>
blank	9.50	11.40	10.18	10.36
4	7.57	8.57	8.33	8.16

This Sheet Has Been Replaced






- 10 -

CLAIMS

1. An admixture for reducing the set time of a cement composition which contains a hydraulic cement binder, the admixture comprising
 - 5 (a) a set-accelerator component; and
 - (b) a C₂ to C₆ glycol component, present in an amount effective to increase the set acceleration properties of the set-accelerator component.
- 10 2. An admixture according to claim 1 wherein the amount of glycol component in the admixture is from 0.05 to 40 weight %, based on the combined weight of glycol component and accelerator component in the admixture.
- 15 3. An admixture according to claim 1 wherein the amount of glycol component in the admixture is from 2.0 to 30 weight %, based on the combined weight of glycol component and accelerator component in the admixture.
- 20 4. An admixture according to any one of claims 1 to 3 wherein the set-accelerating component is an alkali or alkaline earth metal salt of an organic or inorganic acid, or a mixture thereof.
5. An admixture according to claim 4 wherein the set-accelerating component is calcium nitrate, calcium nitrite, or a mixture thereof.
- 25 6. A cement composition comprising a hydraulic cement binder and
 - (a) a set-accelerator component; and



* C L N S *



- 11 -

- (b) a C_2 to C_6 glycol component in an amount effective to increase the set acceleration properties of the set-accelerator component.

7. A composition according to claim 6 wherein the amount of glycol component is from 0.05% s/s to 1.0% s/s, based on the amount of hydraulic cement binder in the composition.

8. A composition according to claim 6 wherein the amount of glycol component is from 0.1% s/s to 0.75% s/s, based on the weight of hydraulic cement binder in the composition.

9. A composition according to claim 6, 7 or 8 wherein the set-accelerator and/or the glycol are as defined in any one of claims 2 to 5.

10. A method for making a cement composition according to any one of claims 6 to 9 which contains a hydraulic cement binder, said method comprising adding to said cement composition

(a) a set-accelerator component; and

(b) a C_2 to C_6 glycol component, in an amount effective to increase the set acceleration properties of the set-accelerator component.

11. A method according to claim 10 wherein the set-accelerating component and glycol are as defined in any one of claims 2 to 5.

12. A corrosion-inhibiting, set-accelerating admixture for reducing the set time of a cement composition





- 12 -

which contains a hydraulic cement binder, said admixture comprising

- 5 (a) a set-accelerator component comprising a mixture of alkaline earth metal nitrate and alkaline earth metal nitrite; and
- (b) a C₂ to C₆ glycol component, present in an amount effective to increase the set acceleration properties of the set-accelerator component.

10 13. An admixture according to claim 12 wherein the glycol component is glycerol and the set-accelerating component is a mixture of calcium nitrate and calcium nitrite.

14. A product comprising
- 15 (a) a set-accelerator component comprising a mixture of alkaline earth metal nitrate and alkaline earth metal nitrite; and
- (b) a C₂ to C₆ glycol component, present in an amount effective to increase the set
- 20 acceleration properties of the set-accelerator component;

for simultaneous, separate or sequential use in reducing the set time of a cement composition which contains a hydraulic cement binder.

