

HOT-DIP Al-Zn-Mg-Si COATED STEEL SHEET AND METHOD OF PRODUCING SAME

TECHNICAL FIELD

5 **[0001]** This disclosure relates to a hot-dip Al-Zn-Mg-Si coated steel sheet having good corrosion resistance in flat parts and edge parts, and also having excellent corrosion resistance in worked parts, and to a method of producing the same.

BACKGROUND

10 **[0002]** Hot-dip Al-Zn alloy-coated steel sheets have both the sacrificial protection of Zn and the high corrosion resistance of Al, and thus rank highly in terms of corrosion resistance among hot-dip galvanized steel sheets. For example, PTL 1 (JP S46-7161 B) discloses a hot-dip Al-Zn alloy-coated steel
15 sheet in which the hot-dip coating contains from 25 mass% to 75 mass% of Al. Due to their excellent corrosion resistance, hot-dip Al-Zn alloy-coated steel sheets have been the subject of increased demand in recent years, particularly in the field of building materials for roofs, walls, and the like that undergo long-term exposure to outdoor environments, and the field of civil
20 engineering and construction for guardrails, wiring, piping, sound proof walls, and the like.

25 **[0003]** The hot-dip coating of a hot-dip Al-Zn alloy-coated steel sheet includes a main layer and an alloy layer present at an interface of the main layer with a base steel sheet. The main layer is mainly composed of regions where Zn is contained in a supersaturated state and Al is solidified by dendrite solidification (α -Al phase dendritic regions), and remaining interdendritic regions between the dendrites, and has a structure with the α -Al phase stacked in multiple layers in the thickness direction of the hot-dip coating. Due to such characteristic hot-dip coating structure, the corrosion path from the
30 surface becomes complex, making it difficult for corrosion to reach the base steel sheet. Therefore, better corrosion resistance can be achieved with a hot-dip Al-Zn alloy-coated steel sheet than with a hot-dip galvanized steel sheet having the same hot-dip coating thickness.

[0004] The inclusion of Mg in a hot-dip Al-Zn alloy coating is a known

technique for further improving corrosion resistance.

In one example of a technique relating to a hot-dip Al-Zn alloy-coated steel sheet containing Mg (hot-dip Al-Zn-Mg-Si coated steel sheet), PTL 2 (JP 5020228 B) discloses an Al-Zn-Mg-Si coated steel sheet in which the hot-dip
5 coating contains a Mg-containing Al-Zn-Si alloy. The Al-Zn-Si alloy contains from 45 wt% to 60 wt% of aluminum, from 37 wt% to 46 wt% of zinc, and from 1.2 wt% to 2.3 wt% of silicon, and has a Mg concentration of from 1 wt% to 5 wt%.

Moreover, PTL 3 (JP 5000039 B) discloses a surface treated steel
10 material having an Al alloy coating containing, by mass%, from 2% to 10% of Mg, from 0.01% to 10% of Ca, and from 3% to 15% of Si, the balance being Al and incidental impurities, and having a Mg/Si mass ratio in a specific range.

[0005] Hot-dip Al-Zn alloy-coated steel sheets that are to be used in the
15 automotive field, and particularly those that are to be used for outer panels, are typically supplied to automobile manufacturers and the like in a state in which production up to hot-dip coating in a continuous galvanizing line (CGL) has been completed. After being worked into the shape of a panel component, the hot-dip Al-Zn alloy-coated steel sheet is typically subjected to
20 chemical conversion treatment, and also general coating for automobile use by electrodeposition coating, intermediate coating and top coating. However, when a coating film of an outer panel obtained using a hot-dip Al-Zn alloy-coated steel sheet is scarred, the resulting scar acts as a start point for selective corrosion of interdendritic regions present at the interface of the
25 coating film and the hot-dip coating that contain a large amount of Zn. As a result, there have been cases in which significantly greater coating film blistering has occurred than with a hot-dip Zn coating and in which it has not been possible to ensure adequate corrosion resistance (post-coating corrosion resistance). In response, PTL 4 (JP 2002-12959 A), for example, discloses a
30 hot-dip Al-Zn alloy-coated steel sheet in which the formation of red rust from edge surfaces of the steel sheet is improved by adding Mg, Sn, or the like to the hot-dip coating composition in order that a Mg compound such as Mg_2Si , $MgZn_2$, Mg_2Sn , or the like is formed in the hot-dip coating layer.

CITATION LIST

Patent Literature

[0006] PTL 1: JP S46-7161 B

PTL 2: JP 5020228 B

5 PTL 3: JP 5000039 B

PTL 4: JP 2002-12959 A

SUMMARY

(Technical Problem)

10 **[0007]** As mentioned above, due to their excellent corrosion resistance, hot-dip Al-Zn alloy-coated steel sheets are often used in the field of building materials for roofs, walls, and the like that undergo long-term exposure to outdoor environments. Therefore, there is demand for the development of hot-dip Al-Zn-Mg-Si coated steel sheets with even better corrosion resistance
15 in order to extend product life in response to recent requirements for resource conservation and energy efficiency.

Moreover, in the hot-dip Al-Zn-Mg-Si coated steel sheets disclosed in PTL 2 and 3, the hot-dip coating has a hard main layer and thus tends to crack when worked by bending. This is problematic as the cracking results in poorer
20 corrosion resistance in worked parts (worked part corrosion resistance). Therefore, there is also demand for the improvement of worked part corrosion resistance. Also note that although reduced ductility due to Mg addition is remedied in PTL 2 through a “small” spangle size, in reality, it is essential that TiB is present in the hot-dip coating in PTL 2 in order to achieve this
25 objective, and thus PTL 2 is not considered to disclose a fundamental solution.

Furthermore, even when the hot-dip Al-Zn alloy-coated steel sheet disclosed in PTL 4 is subjected to subsequent coating, the problem in relation to post-coating corrosion resistance is not resolved, and there are some
30 applications for hot-dip Al-Zn alloy-coated steel sheets in which there is still demand for further improvement of post-coating corrosion resistance.

[0008] In view of the circumstances set forth above, it would be helpful to provide a hot-dip Al-Zn-Mg-Si coated steel sheet having good corrosion resistance in flat parts and edge parts, and also having excellent worked part

corrosion resistance, and to provide a method of producing this hot-dip Al-Zn-Mg-Si coated steel sheet.

(Solution to Problem)

5 **[0009]** As a result of extensive studies conducted with the aim of solving the problems set forth above, we decided to focus on a finding that in corrosion of a hot-dip Al-Zn-Mg-Si coated steel sheet, Mg_2Si present in interdendritic regions of a main layer of the hot-dip coating dissolves during initial corrosion, and Mg concentrates at the surface of corrosion products, which
10 contributes to improvement of corrosion resistance, and also a finding that it is necessary to eliminate single phase Si since single phase Si present in the main layer acts as a cathode site, leading to dissolution of the surrounding hot-dip coating. We conducted further intensive research and discovered that worked part corrosion resistance can be significantly improved by prescribing
15 the contents of Al, Mg, and Si components present in the main layer of the hot-dip coating and controlling the contents of Mg and Si in the hot-dip coating to within specific ranges such as to enable fine and uniform dispersion of Mg_2Si in the interdendritic regions of the main layer. We also discovered that fine and uniform formation of Mg_2Si can eliminate single phase Si from
20 the main layer of the hot-dip coating, and thereby also improve corrosion resistance of flat parts and edge parts.

In addition to the above, we discovered that by controlling the Mg content in the hot-dip coating to within a specific range, excellent post-coating corrosion resistance can be obtained.

25 **[0010]** This disclosure is made based on these discoveries and primary features thereof are as described below.

(1) A hot-dip Al-Zn-Mg-Si coated steel sheet comprising
a base steel sheet and a hot-dip coating on a surface of the base steel sheet, wherein
30 the hot-dip coating includes an interfacial alloy layer present at an interface with the base steel sheet and a main layer present on the interfacial alloy layer, and contains from 25 mass% to 80 mass% of Al, from greater than 0.6 mass% to 15 mass% of Si, and from greater than 0.1 mass% to 25 mass% of Mg, and

Mg content and Si content in the hot-dip coating satisfy formula (1):

$$M_{\text{Mg}}/(M_{\text{Si}} - 0.6) > 1.7 \quad (1)$$

where M_{Mg} represents the Mg content in mass% and M_{Si} represents the Si content in mass%.

5 **[0011]** (2) The hot-dip Al-Zn-Mg-Si coated steel sheet according to the foregoing (1), wherein

the main layer contains Mg_2Si , and Mg_2Si content in the main layer is 1.0 mass% or more.

10 **[0012]** (3) The hot-dip Al-Zn-Mg-Si coated steel sheet according to the foregoing (1), wherein

the main layer contains Mg_2Si , and an area ratio of Mg_2Si in a cross-section of the main layer is 1 % or more.

[0013] (4) The hot-dip Al-Zn-Mg-Si coated steel sheet according to the foregoing (1), wherein

15 the main layer contains Mg_2Si , and according to X-ray diffraction analysis, an intensity ratio of Mg_2Si (111) planes having an interplanar spacing d of 0.367 nm relative to Al (200) planes having an interplanar spacing d of 0.202 nm is 0.01 or more.

20 **[0014]** (5) The hot-dip Al-Zn-Mg-Si coated steel sheet according to any one of the foregoing (1) to (4), wherein

the interfacial alloy layer has a thickness of 1 μm or less.

[0015] (6) The hot-dip Al-Zn-Mg-Si coated steel sheet according to any one of the foregoing (1) to (4), wherein

25 the main layer includes an α -Al phase dendritic region, and a mean dendrite diameter of the α -Al phase dendritic region and a thickness of the hot-dip coating satisfy formula (2):

$$t/d \geq 1.5 \quad (2)$$

where t represents the thickness of the hot-dip coating in μm and d represents the mean dendrite diameter in μm .

30 **[0016]** (7) The hot-dip Al-Zn-Mg-Si coated steel sheet according to any one of the foregoing (1) to (6), wherein

the hot-dip coating contains from 25 mass% to 80 mass% of Al, from greater than 2.3 mass% to 5 mass% of Si, and from 3 mass% to 10 mass% of Mg.

(8) The hot-dip Al-Zn-Mg-Si coated steel sheet according to any one of the foregoing (1) to (6), wherein

the hot-dip coating contains from 25 mass% to 80 mass% of Al, from greater than 0.6 mass% to 15 mass% of Si, and from greater than 5 mass% to 10 mass% of Mg.

[0017] (9) A method of producing a hot-dip Al-Zn-Mg-Si coated steel sheet, comprising

hot-dip coating a base steel sheet by immersing the base steel sheet in a molten bath containing (consisting of) from 25 mass% to 80 mass% of Al, from greater than 0.6 mass% to 15 mass% of Si, and from greater than 0.1 mass% to 25 mass% of Mg, the balance being Zn and incidental impurities,

subsequently cooling a resultant hot-dip coated steel sheet to a first cooling temperature at an average cooling rate of less than 10 °C/sec, the first cooling temperature being no higher than a bath temperature of the molten bath and no lower than 50 °C below the bath temperature, and

then cooling the hot-dip coated steel sheet from the first cooling temperature to 380 °C at an average cooling rate of 10 °C/sec or more.

(Advantageous Effect)

[0018] According to this disclosure, it is possible to provide a hot-dip Al-Zn-Mg-Si coated steel sheet having good corrosion resistance in flat parts and edge parts, and also having excellent worked part corrosion resistance, and to provide a method of producing this hot-dip Al-Zn-Mg-Si coated steel sheet.

BRIEF DESCRIPTION OF THE DRAWINGS

[0019] In the accompanying drawings:

FIG. 1A illustrates pre- and post-corrosion states of a worked part of a disclosed hot-dip Al-Zn-Mg-Si coated steel sheet and FIG. 1B illustrates pre- and post-corrosion states of a worked part of a conventional hot-dip Al-Zn-Mg-Si coated steel sheet;

FIG. 2 illustrates, by scanning electron microscope energy dispersive X-ray spectroscopy (SEM-EDX), the states of various elements in a situation in which a worked part of a disclosed hot-dip Al-Zn-Mg-Si coated steel sheet

FIG. 3 illustrates, by SEM-EDX, the states of various elements in the case of a conventional hot-dip Al-Zn-Mg-Si coated steel sheet;

FIG. 4 illustrates a method of measuring dendrite diameter;

FIG. 5 illustrates a relationship between Si content and Mg content in a hot-dip coating and the state of phases formed in a main layer of the hot-dip coating;

FIG. 6 illustrates the procedure of a Japan Automotive Standards Organization Cyclic Corrosion Test (JASO-CCT);

FIG. 7 illustrates a sample for evaluation of post-coating corrosion resistance; and

FIG. 8 illustrates a cycle of an accelerated corrosion test (SAE J 2334).

15 DETAILED DESCRIPTION

[0020] (Hot-dip Al-Zn-Mg-Si coated steel sheet)

The hot-dip Al-Zn-Mg-Si coated steel sheet to which this disclosure relates includes a base steel sheet and a hot-dip coating on a surface of the base steel sheet. The hot-dip coating includes an interfacial alloy layer present at an interface with the base steel sheet, and a main layer present on the interfacial alloy layer. The hot-dip coating has a composition containing from 25 mass% to 80 mass% of Al, from greater than 0.6 mass% to 15 mass% of Si, and from greater than 0.1 mass% to 25 mass% of Mg, the balance being Zn and incidental impurities.

[0021] The Al content in the hot-dip coating is set as from 25 mass% to 80 mass%, and preferably from 35 mass% to 65 mass% from a viewpoint of balancing corrosion resistance with actual operation requirements. When the Al content of the main layer of the hot-dip coating is 25 mass% or more, dendrite solidification of Al occurs. This ensures a structure having excellent corrosion resistance in which the main layer is composed mainly of regions in which Zn is in a supersaturated state and Al is solidified by dendrite solidification (α -Al phase dendritic regions) and remaining interdendritic regions between the dendrites, and in which the dendritic regions are stacked in the thickness direction of the hot-dip coating. Corrosion resistance is

improved as the number of stacked α -Al phase dendritic regions increases because the corrosion path becomes more complex, which makes it more difficult for corrosion to reach the base steel sheet. To obtain significantly high corrosion resistance, the Al content of the main layer is more preferably

5 35 mass% or more. On the other hand, if the Al content of the main layer is greater than 80 mass%, the content of Zn having sacrificial corrosion protection ability with respect to Fe decreases, and corrosion resistance deteriorates. Accordingly, the Al content of the main layer is set as 80 mass% or less. Furthermore, when the Al content of the main layer is 65 mass% or

10 less, sacrificial corrosion protection ability with respect to Fe is ensured and adequate corrosion resistance is obtained even if the coating weight of the hot-dip coating is reduced and the steel base becomes more easily exposed. Accordingly, the Al content of the main layer of the hot-dip coating is preferably 65 mass% or less.

15 **[0022]** Si inhibits the growth of the interfacial alloy layer formed at the interface with the base steel sheet and is added to a molten bath for improving corrosion resistance and workability. Therefore, Si is inevitably contained in the main layer of the hot-dip coating. Specifically, when hot-dip coating treatment is performed in a molten bath containing Si in the case of an

20 Al-Zn-Mg-Si coated steel sheet, an alloying reaction takes place between Fe in the surface of the base steel sheet and Al or Si in the bath upon immersion of the steel sheet in the molten bath, whereby an Fe-Al compound and/or an Fe-Al-Si compound is formed. The formation of this Fe-Al-Si interfacial alloy layer inhibits growth of the interfacial alloy layer. A Si content of greater than

25 0.6 mass% in the hot-dip coating enables adequate inhibition of interfacial alloy layer growth. On the other hand, if the Si content in the hot-dip coating is greater than 15 mass%, this may provide a propagation path for cracks in the hot-dip coating, which reduces workability and facilitates precipitation of a Si phase that then acts as a cathode site. Although precipitation of the Si

30 phase can be inhibited by increasing the Mg content, this method leads to increased production cost and complicates management of the molten bath composition. Accordingly, the Si content in the hot-dip coating is set as 15 mass% or less. From a viewpoint of achieving a higher level of inhibition of both interfacial alloy layer growth and Si phase precipitation, the Si content in

the hot-dip coating is preferably from greater than 2.3 mass% to 5 mass%, and particularly preferably from greater than 2.3 mass% to 3.5 mass%.

[0023] The hot-dip coating contains from greater than 0.1 mass% to 25 mass% of Mg. When the main layer of the hot-dip coating is corroded, Mg becomes included in the corrosion products, which improves the stability of the corrosion products and delays corrosion progression, resulting in an effect of improved corrosion resistance. More specifically, Mg in the main layer of the hot-dip coating bonds to the Si described above to form Mg_2Si . When the hot-dip coated steel sheet is corroded, this Mg_2Si dissolves during initial corrosion, and thus Mg is included in the corrosion products. Mg concentrates at the surface of the corrosion products and has an effect of densifying the corrosion products such as to improve stability of the corrosion products and barrier properties against external causes of corrosion.

The reason for setting the Mg content of the hot-dip coating as greater than 0.1 mass% is that Mg_2Si can be formed and a corrosion delaying effect can be obtained when the Mg content is greater than 0.1 mass%. On the other hand, the reason for setting the Mg content as 25 mass% or less is that, when the Mg content is greater than 25 mass%, in addition to the effect of corrosion resistance improvement reaching saturation, production cost increases and management of the molten bath composition becomes complicated. From a viewpoint of achieving a greater corrosion delaying effect while also reducing production cost, the Mg content in the hot-dip coating is preferably from 3 mass% to 10 mass%, and more preferably from 4 mass% to 6 mass%.

[0024] Moreover, a Mg content in the hot-dip coating of 5 mass% or more can improve post-coating corrosion resistance, which is one objective in the present disclosure. In the case of a conventional hot-dip Al-Zn alloy-coated steel sheet that does not contain Mg, a dense and stable oxide film of Al_2O_3 forms at the periphery of the α -Al phase straight after the hot-dip coating is exposed to the atmosphere. Through the protective action of this oxide film, solubility of the α -Al phase becomes significantly lower than that of a Zn-rich phase in the interdendritic regions. Consequently, upon scarring of the coating film of a coated steel sheet obtained using the conventional hot-dip Al-Zn alloy-coated steel sheet as a base, the scar acts as a start point for selective corrosion of the Zn-rich phase at an interface of the coating film and the

hot-dip coating, and this corrosion progresses deep into a part where the coating film is not scarred, causing large coating film blisters. Therefore, post-coating corrosion resistance is poor. On the other hand, in the case of a coated steel sheet obtained using a hot-dip Al-Zn alloy-coated steel sheet that contains Mg as a base, a Mg_2Si phase that precipitates in interdendritic regions or Mg-Zn compound ($MgZn_2$, $Mg_{32}(Al,Zn)_{49}$, etc.) dissolves from an initial stage of corrosion and Mg is taken into the corrosion products. Corrosion products including Mg are highly stable, which inhibits corrosion from the initial stage thereof. Moreover, this can inhibit large coating film blisters caused by selective corrosion of the Zn-rich phase, which is a problem in the case of a coated steel sheet obtained using the conventional hot-dip Al-Zn alloy-coated steel sheet as a base. Consequently, a hot-dip Al-Zn alloy-coated steel sheet having a Mg-containing hot-dip coating displays excellent post-coating corrosion resistance. When the Mg content is 5 mass% or less, post-coating corrosion resistance may not be improved because the amount of Mg that dissolves during corrosion is small and thus stable corrosion products such as described above are not sufficiently formed. Conversely, when the Mg content is greater than 10 mass%, not only does the effect thereof reach saturation, but strong Mg compound corrosion occurs and solubility of the hot-dip coating layer as a whole is excessively increased. As a result, a large blister width may arise and deterioration of post-coating corrosion resistance may occur even if the corrosion products are stabilized because the dissolution rate of the hot-dip coating layer is increased. Accordingly, the Mg content is preferably in a range of from greater than 5 mass% to 10 mass% so as to ensure excellent post-coating corrosion resistance.

[0025] In the disclosed hot-dip Al-Zn-Mg-Si coated steel sheet, from a viewpoint of effectively dispersing Mg_2Si in the interdendritic regions, reducing the likelihood of formation of single phase Si, and achieving even better worked part corrosion resistance, it is preferable that the Mg content and the Si content in the hot-dip coating satisfy the following formula (1):

$$M_{Mg}/(M_{Si} - 0.6) > 1.7 \quad (1)$$

where M_{Mg} represents the Mg content (mass%) and M_{Si} represents the Si content (mass%).

[0026] Fine and uniform dispersion of Mg_2Si can dramatically improve worked part corrosion resistance because Mg_2Si gradually dissolves with Zn over the surface of the hot-dip coating and the entirety of the fracture surface of cracks in a worked part, a large amount of Mg is taken into the corrosion products, and a thick Mg-rich section is formed over the whole surface of the corrosion products, thereby inhibiting progression of corrosion. Moreover, fine and uniform dispersion of Mg_2Si throughout the main layer of the hot-dip coating without uneven distribution can also improve corrosion resistance of flat parts and edge parts by eliminating single phase Si that acts as a cathode site from the main layer.

In contrast, according to conventional techniques, as described for example in PTL 3, Mg_2Si is present as lumps of at least a certain size (specifically, lumps having a major diameter of 10 μm or more and a ratio of minor diameter to major diameter of 0.4 or more). Therefore, the Mg_2Si is coarse and unevenly distributed, and thus has a much higher dissolution rate than Zn during initial corrosion, leading to preferential dissolution and elution of Mg_2Si . Consequently, Mg is not effectively taken into the corrosion products, small and localized Mg-rich sections form at the surface of the corrosion products, and the desired effect of corrosion resistance improvement is not obtained.

[0027] FIG. 5 illustrates a relationship between Si content and Mg content in the hot-dip coating and the state of phases formed in the main layer of the hot-dip coating. It can be seen from FIG. 5 that within the scope of the disclosed composition (area surrounded by a dashed line in FIG. 5), single phase Si can be reliably eliminated from the main layer when formula (1) is satisfied.

[0028] The main layer of the hot-dip coating includes α -Al phase dendritic regions. The mean dendrite diameter of these dendritic regions and the thickness of the hot-dip coating satisfy the following formula (2):

$$t/d \geq 1.5 \quad (2)$$

where t represents the thickness of the hot-dip coating (μm) and d represents the mean dendrite diameter (μm).

When formula (2) is satisfied, the arms of the dendritic regions composed by the α -Al phase can be kept relatively small (i.e., the mean

dendrite diameter can be kept relatively small), Mg_2Si can be effectively dispersed in the interdendritic regions, and a state can be obtained in which Mg_2Si is finely and uniformly dispersed throughout the main layer of the hot-dip coating without uneven distribution.

5 **[0029]** FIGS. 1A and 1B schematically illustrate the change in state of a main layer of a hot-dip coating during corrosion of a worked part in the case of the disclosed hot-dip Al-Zn-Mg-Si coated steel sheet and in the case of a hot-dip Al-Zn-Mg-Si coated steel sheet according to a conventional technique.

As illustrated in FIG. 1A, in the case of the disclosed hot-dip
10 Al-Zn-Mg-Si coated steel sheet, the dendrites are small relative to the thickness t of the hot-dip coating, which facilitates fine and uniform dispersion of Mg_2Si . When a worked part of the disclosed hot-dip Al-Zn-Mg-Si coated steel sheet is corroded (note that cracks are present in the worked part), Mg_2Si that is present at fracture surfaces of the cracks into the
15 worked part of the hot-dip coating dissolves, and Mg concentrates at the surface of the corrosion products.

On the other hand, in the case of the conventional hot-dip Al-Zn-Mg-Si coated steel sheet, as illustrated in FIG. 1B, the dendrites are large relative to the thickness t of the hot-dip coating, which makes fine and
20 uniform dispersion of Mg_2Si difficult. When a worked part of the conventional hot-dip Al-Zn-Mg-Si coated steel sheet is corroded, Mg_2Si that is present at fracture surfaces of the cracks into the worked part dissolves, and Mg concentrates along some of the surface of the corrosion product. However, since the degree of dispersion of Mg_2Si throughout the main layer of the
25 hot-dip coating is poor compared to the disclosed hot-dip Al-Zn-Mg-Si coated steel sheet, the Mg-rich section covering the surface of the corrosion products is reduced. This is thought to facilitate the progression of corrosion in the worked part, resulting in inadequate corrosion resistance.

[0030] FIG. 2 illustrates, by energy dispersive X-ray spectroscopy using a
30 scanning electron microscope (SEM-EDS), the states of various elements when a worked part is corroded in the case of the disclosed hot-dip Al-Zn-Mg-Si coated steel sheet. It can be seen from FIG. 2 that when a worked part is corroded in the disclosed hot-dip Al-Zn-Mg-Si coated steel sheet, Mg concentrates at the surface of the main layer of the hot-dip coating (refer to

the photograph for Mg in FIG. 2).

FIG. 3 illustrates, by SEM-EDS, the states of various elements in the case of a hot-dip Al-Zn-Mg-Si coated steel sheet in which the hot-dip coating has a composition within the scope of this disclosure (Al: 55 mass%, Si: 1.6 mass%, Mg: 2.5 mass%), but in which the mean dendrite diameter of dendritic regions in the main layer and the thickness of the hot-dip coating do not satisfy the above formula (2). Upon observation, a small amount of precipitation of a Si single phase can be confirmed, and thus reduced corrosion resistance is inferred (refer to the photograph for Si in FIG. 3).

[0031] The term “dendrite diameter” refers to the center distance between adjacent dendrite arms (dendrite arm spacing). Herein, the dendrite diameter is measured in accordance with the secondary dendrite arm spacing method (refer to “Japan Institute of Light Metals, Committee of Casting and Solidification; Journal of Japan Institute of Light Metals; Vol. 38; p 54; 1988”). In the hot-dip coating of the disclosed hot-dip Al-Zn-Mg-Si coated steel sheet, the dendritic regions of the main layer of the hot-dip coating have a high level of orientation and there are large number of regions in which the arms are aligned.

Specifically, as illustrated in FIG. 4, the surface of the main layer of the hot-dip coating is polished and/or etched and is observed under magnification (for example, observed under $\times 200$ magnification) using a scanning electron microscope (SEM), and in a randomly selected field of view, a region where at least three dendrite arms are aligned is selected (three dendrites between A and B are selected in FIG. 4), and the distance along a direction of alignment of the arms (distance L in FIG. 4) is measured. Thereafter, the measured distance is divided by the number of dendrite arms ($L/3$ in FIG. 4) to calculate the dendrite diameter. The dendrite diameter is measured at three or more locations in one field of view, and the mean of the dendrite diameters obtained at these locations is calculated to determine the mean dendrite diameter.

[0032] In the disclosed hot-dip Al-Zn-Mg-Si coated steel sheet, the main layer contains Mg_2Si as described above, and the Mg_2Si content in the main layer is preferably 1.0 mass% or more. This enables fine and uniform dispersion of Mg_2Si throughout the main layer of the hot-dip coating in a more

reliable manner such that the desired corrosion resistance can be achieved.

Herein, the Mg_2Si content is measured by, for example, dissolving the hot-dip coating of the Al-Zn-Mg-Si coated steel sheet in acid and then measuring the amounts (g/m^2) of Si and Mg by ICP analysis (high-frequency
5 inductively coupled plasma emission spectroscopy). The content in the interfacial alloy layer (0.45 g/m^2 per $1 \text{ }\mu\text{m}$ of interfacial alloy layer) is subtracted from the amount of Si, and the difference is multiplied by 2.7 to convert to the amount (g/m^2) of Mg_2Si , which is then divided by the hot-dip coating weight (g/m^2) to calculate the mass percentage of Mg_2Si . However,
10 any analytical method by which the Mg_2Si content can be determined may be used.

[0033] The area ratio of Mg_2Si in the main layer upon observation of a cross-section of the main layer is preferably 1 % or more. This enables fine and uniform dispersion of Mg_2Si throughout the main layer of the hot-dip
15 coating in a more reliable manner such that the desired corrosion resistance can be achieved.

Herein, the area ratio of Mg_2Si is determined by, for example, performing SEM-EDX mapping of a cross-section of the hot-dip coating of the Al-Zn-Mg-Si coated steel sheet and then using image processing to calculate
20 the area ratio (%) of regions where Mg and Si are detected overlapping with one another (i.e., regions where Mg_2Si is present) in one field of view. However, any method that can determine the area ratio of regions where Mg_2Si is present may be used.

[0034] Moreover, with regards to Mg_2Si contained in the main layer, it is
25 preferable that according to X-ray diffraction analysis, an intensity ratio of Mg_2Si (111) planes (interplanar spacing $d = 0.367 \text{ nm}$) relative to Al (200) planes (interplanar spacing $d = 0.202 \text{ nm}$) is 0.01 or more. This enables fine and uniform dispersion of Mg_2Si throughout the main layer of the hot-dip coating in a more reliable manner such that the desired corrosion resistance
30 can be achieved.

Herein, this intensity ratio is calculated by obtaining an X-ray diffraction pattern under conditions of, for example, a tube voltage of 30 kV, a tube current of 10 mA, a Cu $\text{K}\alpha$ tube (wavelength $\lambda = 0.154 \text{ nm}$), and a measurement angle 2θ of from 10° to 90° , measuring the intensity of (200)

planes (interplanar spacing $d = 0.2024$ nm) indicating Al and the intensity of (111) planes (interplanar spacing $d = 0.367$ nm) indicating Mg_2Si , and then dividing the latter by the former. However, no specific limitations are placed on the X-ray diffraction analysis conditions.

- 5 **[0035]** With regards to Mg_2Si particles that are finely and uniformly dispersed in the interdendritic regions, the ratio of the minor diameter thereof relative to the major diameter thereof is preferably 0.4 or less, and more preferably 0.3 or less.

10 In conventional techniques, the ratio of the minor diameter relative to the major diameter of Mg_2Si particles is 0.4 or more as described, for example, in PTL 3. Since Mg_2Si is coarse and has an uneven distribution in this situation, the dissolution rate of Mg_2Si during initial corrosion is much higher than that of Zn, and Mg_2Si preferentially dissolves and elutes, as a result of which, Mg is not effectively taken into the corrosion products, a smaller
15 number of localized Mg-rich sections form at the surface of the corrosion products, and an effect of corrosion resistance improvement is not obtained.

On the other hand, setting a large difference between the major and minor diameters (aspect ratio) in the disclosed techniques contributes to fine and uniform dispersion of Mg_2Si particles present at the surface of the hot-dip
20 coating and at fracture surfaces of cracks into a worked part. This can dramatically improve worked part corrosion resistance because Mg_2Si gradually dissolves with Zn during corrosion, a large amount of Mg is taken into the corrosion products, and a thick Mg-rich section is formed over the whole surface of the corrosion products, thereby inhibiting progression of
25 corrosion.

Herein, the “major diameter” of Mg_2Si refers to the longest diameter in a Mg_2Si particle and the “minor diameter” of Mg_2Si refers to a shortest diameter in a Mg_2Si particle.

- 30 **[0036]** From a viewpoint of obtaining better corrosion resistance, the hot-dip coating preferably further contains Ca. In a situation in which the hot-dip coating further contains Ca, the total Ca content is preferably from 0.2 mass% to 25 mass%. When the total content is within the range set forth above, an adequate corrosion delaying effect can be obtained without this effect reaching saturation.

[0037] Furthermore, the main layer preferably further contains one or more selected from Mn, V, Cr, Mo, Ti, Sr, Ni, Co, Sb, and B in a total amount of from 0.01 mass% to 10 mass% because, in the same way as Mg and Ca, they improve the stability of corrosion products and have an effect of delaying progression of corrosion.

[0038] The interfacial alloy layer is present at the interface with the base steel sheet and, as previously mentioned, is an Fe-Al compound and/or an Fe-Al-Si compound that is inevitably formed by alloying reaction between Fe in the surface of the base steel sheet and Al and/or Si in the molten bath. Since the interfacial alloy layer is hard and brittle, it may act as a start point for cracks during working if it grows thick. Therefore, the thickness of the interfacial alloy layer is preferably minimized.

[0039] The interfacial alloy layer and the main layer can be examined by using a scanning electron microscope or the like to observe a polished and/or etched cross-section of the hot-dip coating. Although there are various methods for polishing and etching the cross-section, there is no specific limitation on which method is used as long as the method is normally used for observing hot-dip coating cross-sections. Furthermore, regarding observation conditions using a scanning electron microscope, it is possible to clearly observe the alloy layer and the main layer, for example, in a backscattered electron image at a magnification of $\times 1,000$ or more, with an acceleration voltage of 15 kV.

The presence or absence of Mg and one or more selected from Ca, Mn, V, Cr, Mo, Ti, Sr, Ni, Co, Sb, and B in the main layer can be confirmed by, for example, performing penetration analysis of the hot-dip coating using a glow discharge emission analyzer. However, use of a glow discharge emission analyzer is only intended as an example, and any other methods enabling examination of the presence and distribution of Mg, Ca, Mn, V, Cr, Mo, Ti, Sr, Ni, Co, Sb, and B in the main layer of the hot-dip coating can be adopted.

[0040] Furthermore, it is preferable that the aforementioned one or more selected from Ca, Mn, V, Cr, Mo, Ti, Sr, Ni, Co, Sb, and B form an intermetallic compound with one or more selected from Zn, Al, and Si in the main layer of the hot-dip coating. During the process of forming the hot-dip coating, the α -Al phase solidifies before the Zn-rich phase, and therefore the

intermetallic compound is discharged from the α -Al phase during the solidification process and gathers in the Zn-rich phase in the main layer of the hot-dip coating. Since the Zn-rich phase corrodes before the α -Al phase, the one or more selected from Ca, Mn, V, Cr, Mo, Ti, Sr, Ni, Co, Sb, and B are
5 taken into the corrosion products. As a result, it is possible to more effectively stabilize the corrosion products in the initial stage of corrosion. Furthermore, it is more preferable for Si to be included in the intermetallic compound because this means that the intermetallic compound absorbs Si within the hot-dip coating to reduce excessive Si in the main layer of the hot-dip coating
10 and, as a result, a decrease in bending workability caused by formation of non-solute Si (Si phase) in the main layer of the hot-dip coating can be prevented.

[0041] The following methods may be used to confirm whether Mg or one or more selected from Ca, Mn, V, Cr, Mo, Ti, Sr, Ni, Co, Sb, and B form an
15 intermetallic compound with one or more selected from Zn, Al, and Si. Examples of methods that can be used include a method of detecting such intermetallic compounds by wide angle X-ray diffraction from the surface of the hot-dip coated steel sheet and a method of detecting such intermetallic compounds by performing electron beam diffraction with a transmission
20 electron microscope on a cross-section of the hot-dip coating. Moreover, as long as such intermetallic compounds can be detected, any other method can be used.

[0042] The thickness of the hot-dip coating of the disclosed hot-dip Al-Zn-Mg-Si coated steel sheet is preferably 15 μm or more and 27 μm or less.
25 In general, corrosion resistance tends to become poorer as the thickness of the hot-dip coating is reduced, whereas workability tends to become poorer as the thickness of the hot-dip coating is increased.

The thickness of the interfacial alloy layer is preferably 1 μm or less. This is because high workability and better worked part corrosion resistance
30 can be achieved when the thickness of the interfacial alloy layer is 1 μm or less. For example, by setting the Si content in the hot-dip coating as greater than 0.6 mass% as previously described, growth of the interfacial alloy layer can be inhibited, and thus the thickness of the interfacial alloy layer can be restricted to 1 μm or less.

The thicknesses of the hot-dip coating and the interfacial alloy layer can be obtained by any method that enables accurate determination of these thicknesses. For example, each of these thicknesses may be determined by observing a cross-section of the hot-dip Al-Zn-Mg-Si coated steel sheet under an SEM, measuring the thickness at 3 locations in each of 3 fields of view, and then calculating the average of the thicknesses at these 9 measurement locations.

[0043] The disclosed hot-dip Al-Zn-Mg-Si coated steel sheet may be a surface-treated steel sheet that further includes a chemical conversion treatment coating and/or a coating film at the surface thereof.

[0044] It should be noted that no specific limitations are placed on the base steel sheet used in the disclosed hot-dip Al-Zn-Mg-Si coated steel sheet. For example, the base steel sheet is not limited to being a steel sheet that is the same as used in a typical hot-dip Al-Zn alloy coated steel sheet, and may alternatively be a high tensile strength steel sheet or the like.

[0045] (Method of producing hot-dip Al-Zn-Mg-Si coated steel sheet)

The following describes the disclosed method of producing a hot-dip Al-Zn-Mg-Si coated steel sheet.

The disclosed method of producing a hot-dip Al-Zn-Mg-Si coated steel sheet includes hot-dip coating a base steel sheet by immersing the base steel sheet in a molten bath containing from 25 mass% to 80 mass% of Al, from greater than 0.6 mass% to 15 mass% of Si, and from greater than 0.1 mass% to 25 mass% of Mg, the balance being Zn and incidental impurities, subsequently cooling a resultant hot-dip coated steel sheet to a first cooling temperature at an average cooling rate of less than 10 °C/sec, the first cooling temperature being no higher than a bath temperature of the molten bath and no lower than 50 °C below the bath temperature, and then cooling the hot-dip coated steel sheet from the first cooling temperature to 380 °C at an average cooling rate of 10 °C/sec or more.

The disclosed production method enables production of a hot-dip Al-Zn-Mg-Si coated steel sheet having good corrosion resistance in flat parts and edge parts, and also having excellent worked part corrosion resistance.

[0046] In the disclosed method of producing a hot-dip Al-Zn-Mg-Si coated steel sheet, normally a method is adopted in which production is carried out in

a continuous galvanizing line (CGL), but the disclosed production method is not specifically limited thereto.

5 **[0047]** No specific limitations are placed on the type of base steel sheet used for the disclosed hot-dip Al-Zn-Mg-Si coated steel sheet. For example, a hot rolled steel sheet or steel strip subjected to acid pickling descaling, or a cold rolled steel sheet or steel strip obtained by cold rolling the hot rolled steel sheet or steel strip may be used.

Moreover, no specific limitations are placed on conditions of pretreatment and annealing processes, and any method may be adopted.

10 **[0048]** The hot dip coating conditions may be in accordance with a conventional method without any specific limitations as long as an hot-dip Al-Zn alloy coating can be formed on the base steel sheet. For example, the base steel sheet may be subjected to reduction annealing, then cooled to a temperature close to the temperature of the molten bath, immersed in the
15 molten bath, and then subjected to wiping to form a hot-dip coating of a desired thickness.

[0049] The molten bath for hot-dip coating has a composition containing from 25 mass% to 80 mass% of Al, from greater than 0.6 mass% to 15 mass% of Si, and from greater than 0.1 mass% to 25 mass% of Mg, the balance being
20 Zn and incidental impurities.

The molten bath may further contain Ca for the purpose of further improving corrosion resistance.

[0050] In addition, the molten bath may contain one or more selected from Mn, V, Cr, Mo, Ti, Sr, Ni, Co, Sb, and B in a total amount of from 0.01 mass%
25 to 10 mass%. Setting the composition of the molten bath as described above enables formation of the hot-dip coating.

[0051] No specific limitations are placed on the temperature of the molten bath other than being a temperature that enables hot-dip Al-Zn-Mg-Si coating without solidification of the molten bath, and a commonly known molten bath
30 temperature may be adopted. For example, the temperature of a molten bath in which the Al concentration is 55 mass% is preferably from 575 °C to 620 °C, and more preferably from 580 °C to 605 °C.

[0052] As mentioned above, the hot-dip Al-Zn alloy coating includes an interfacial alloy layer present at an interface with the base steel sheet, and a

main layer present on the interfacial alloy layer. Although the composition of the main layer has slightly lower Al and Si contents at the interfacial alloy layer side thereof, as a whole, the composition is substantially the same as the composition of the molten bath. Therefore, the composition of the main layer of the hot-dip coating can be precisely controlled by controlling the composition of the molten bath.

[0053] In the disclosed production method, the steel sheet resulting from the hot dip coating is cooled to the first cooling temperature at an average cooling rate of less than 10 °C/sec, and is then cooled from the first cooling temperature to 380 °C at an average cooling rate of 10 °C/sec or more. Through our research, we realized that Mg₂Si is readily formed up until a temperature region roughly from the bath temperature of the molten bath to 50 °C below the bath temperature (first cooling temperature). Therefore, by restricting the cooling rate to an average value of less than 10 °C/sec until the first cooling temperature, the period of time during which Mg₂Si is formed in the main layer of the hot-dip coating is extended, thereby maximizing the amount of Mg₂Si that is formed, and Mg₂Si is finely and uniformly dispersed throughout the main layer of the hot-dip coating without uneven distribution, which enables excellent worked part corrosion resistance to be achieved. On the other hand, we realized that single phase Si readily precipitates in a temperature region from the first cooling temperature to 380 °C. Accordingly, precipitation of single phase Si can be inhibited by maintaining a cooling rate with an average value of 10 °C/sec or more from the first cooling temperature to 380 °C.

From a viewpoint of more reliably preventing precipitation of single phase Si, the average cooling rate from the first cooling temperature to 380 °C is preferably 20 °C/sec or more, and more preferably 40 °C/sec or more.

[0054] It should be noted that in the disclosed production method, with the exception of cooling conditions during and after the hot dip coating, a hot-dip Al-Zn-Mg-Si coated steel sheet may be produced in accordance with a conventional method without any specific limitations.

For example, a chemical conversion treatment coating may be formed on the surface of the hot-dip Al-Zn-Mg-Si coated steel sheet (chemical conversion treatment process) or a coating film may be formed on the surface

of the hot-dip Al-Zn-Mg-Si coated steel sheet in a separate coating line (coating film formation process).

[0055] The chemical conversion treatment coating can be formed by a chromating treatment or a chromium-free chemical conversion treatment
5 where, for example, a chromating treatment liquid or a chromium-free chemical conversion treatment liquid is applied, and without water washing, drying treatment is performed with a steel sheet temperature of 80 °C to 300 °C. These chemical conversion treatment coatings may have a single-layer structure or a multilayer structure, and in the case of a multilayer structure,
10 chemical conversion treatment can be performed multiple times sequentially.

Methods of forming the coating film include roll coater coating, curtain flow coating, and spray coating. The coating film can be formed by applying a coating material containing organic resin, and then heating and drying the coating material by hot air drying, infrared heating, induction
15 heating, or other means.

EXAMPLES

[0056] The following describes examples of the disclosed techniques.
(Example 1)

20 Hot-dip Al-Zn-Mg-Si coated steel sheet samples 1 to 57 were each produced in a continuous galvanizing line (CGL) using, as a base steel sheet, a cold rolled steel sheet of 0.5 mm in thickness that was produced by a conventional method.

Production conditions (molten bath temperature, first cooling
25 temperature, and cooling rate) and hot-dip coating conditions (composition, major diameter of Mg_2Si , minor diameter/major diameter of Mg_2Si , thickness of hot-dip coating, left side of formula (1), left side of formula (2), Mg_2Si content in main layer, Mg_2Si area ratio in main layer cross-section, intensity ratio of Mg_2Si relative to Al, and thickness of interfacial alloy layer) are
30 shown in Table 1.

The bath temperature of the molten bath was 590 °C in production of all the above hot-dip Al-Zn-Mg-Si coated steel sheet samples.

Sample 10 was subjected to treatment of being held at 200 °C for 30 minutes after hot-dip coating. The compositions of hot-dip coatings in

samples 11 to 13, 20, and 21 were within the same ranges as disclosed in PTL 2, whereas the compositions of hot-dip coatings in samples 28, 29, and 32 were within the same ranges as disclosed in PTL 3.

[0057] • Minor diameter and major diameter of Mg_2Si

5 The major and minor diameters of Mg_2Si were determined for each hot-dip Al-Zn-Mg-Si coated steel sheet sample by imaging the surface of the hot-dip coating using an optical microscope ($\times 100$ magnification), randomly selecting five Mg_2Si particles, measuring the major diameter and minor diameter of each of the selected Mg_2Si particles, and calculating the averages
10 of these measured major diameters and minor diameters. The major diameter (μm) and ratio of minor diameter relative to major diameter that were determined for Mg_2Si are shown in Table 1.

• Dendrite diameter

 The dendrite diameter was determined for each hot-dip Al-Zn-Mg-Si
15 coated steel sheet sample by observing a polished surface of a main layer of the hot-dip coating at $\times 200$ magnification using an SEM, selecting a region in which at least three dendrite arms were aligned in a randomly selected field of view, measuring the distance along the direction of alignment of the arms, and then dividing the measured distance by the number of dendrite arms. The
20 dendrite diameter was measured at three locations in one field of view and the mean of the measured dendrite diameters was calculated to determine the mean dendrite diameter. The determined dendrite diameter is shown in Table 1.

[0058] (Evaluation of hot-dip coating corrosion resistance)

25 (1) Evaluation of flat part and edge part corrosion resistance

 Each hot-dip Al-Zn-Mg-Si coated steel sheet sample was subjected to a Japan Automotive Standards Organization Cyclic Corrosion Test (JASO-CCT). Each cycle of the JASO-CCT included salt spraying, drying, and wetting under specific conditions as illustrated in FIG. 6.

30 The number of cycles until red rust formed was counted with respect to a flat part and an edge part of each of the samples, and was then evaluated in accordance with the following standard.

Excellent: Red rust formation cycle count ≥ 600 cycles

Satisfactory: $400 \text{ Cycles} \leq \text{Red rust formation cycle count} < 600$

Cycles

Unsatisfactory: $300 \text{ Cycles} \leq \text{Red rust formation cycle count} < 400$

Cycles

Poor: Red rust formation cycle count $< 300 \text{ Cycles}$

5 (2) Evaluation of bent worked part corrosion resistance

Each hot-dip Al-Zn-Mg-Si coated steel sheet sample was worked by 180° bending to sandwich three sheets of the same sheet thickness at the inside (3T bending), and was then subjected to a Japan Automotive Standards Organization Cyclic Corrosion Test (JASO-CCT) at the outside of the bend.

10 Each cycle of the JASO-CCT included salt spraying, drying, and wetting under specific conditions as illustrated in FIG. 6.

The number of cycles until red rust formed was counted with respect to the worked part of each of the samples, and was then evaluated in accordance with the following standard.

15 Excellent: Red rust formation cycle count $\geq 600 \text{ Cycles}$

Satisfactory: $400 \text{ Cycles} \leq \text{Red rust formation cycle count} < 600$

Cycles

Unsatisfactory: $300 \text{ Cycles} \leq \text{Red rust formation cycle count} < 400$

Cycles

20 Poor: Red rust formation cycle count $< 300 \text{ Cycles}$

[0059] Table 1

No.		Hot-dip coating											Production conditions				Evaluation			Remarks
		Composition (mass%)		MgSi major diameter (μm)	MgSi:minor diameter/ major diameter	Coating thickness (μm)	Dendrite diameter (μm)	Left side of formula (2)	MgSi content (mass%)	Mg ₂ Si area ratio (%)	Mg ₂ Si/Al intensity ratio	Interfacial alloy layer thickness (μm)	Left side of formula (1)	Molten bath temperature (°C)	First cooling temperature (°C)	Average cooling rate (°C/sec)		Hot-dip coating corrosion resistance		
																To first cooling temperature	From first cooling temperature to 380 °C			
Al	Mg	Si																Flat part	Edge part	Worked part
1	55	1.1	0.5	No Mg ₂ Si	No Mg ₂ Si	24	12.2	2.0	0.0	0.0	1.2	-11.0	590	540	5	23		Poor	Poor	Comparative example
2	55	3.2	0.5	No Mg ₂ Si	No Mg ₂ Si	23	11.0	2.1	0.0	0.0	1.2	-32.0	590	540	5	23		Poor	Poor	Comparative example
3	55	5.6	0.5	No Mg ₂ Si	No Mg ₂ Si	21	10.5	2.0	0.0	0.0	1.2	-56.0	590	540	5	23		Unsatisfactory	Poor	Comparative example
4	55	7.3	0.5	No Mg ₂ Si	No Mg ₂ Si	22	12.2	1.8	0.0	0.0	1.2	-73.0	590	540	5	23		Unsatisfactory	Poor	Comparative example
5	55	1.1	1.1	7	0.2	22	11.2	2.0	1.4	1.2	0.01	2.2	590	540	5	23		Satisfactory	Satisfactory	Example
6	55	3.2	1.1	8	0.2	23	11.6	2.0	1.4	1.2	0.01	6.4	590	540	5	23		Satisfactory	Satisfactory	Example
7	55	5.6	1.1	6	0.1	26	10.9	2.4	1.4	1.2	0.01	11.2	590	540	5	23		Satisfactory	Satisfactory	Example
8	55	10.5	1.1	5	0.1	22	10.3	2.1	1.4	1.2	0.01	1.0	590	540	5	23		Satisfactory	Satisfactory	Example
9	55	0.0	1.5	No Mg ₂ Si	No Mg ₂ Si	24	11.4	2.1	0.0	0.0	0.9	0.0	590	540	5	23		Unsatisfactory	Poor	Comparative example
10	55	0.0	1.5	No Mg ₂ Si	No Mg ₂ Si	23	10.8	2.1	0.0	0.0	0.9	0.0	590	540	5	23		Poor	Poor	Unsatisfactory
11	55	1.1	1.5	9	0.2	21	15.7	1.3	1.7	4.2	0.01	1.2	590	540	5	23		Unsatisfactory	Poor	Comparative example
12	55	1.8	1.5	6	0.2	22	12.3	1.8	2.8	5.8	0.01	2.0	590	540	5	23		Satisfactory	Satisfactory	Example
13	55	3.2	1.5	7	0.1	21	11.1	1.9	2.5	5.3	0.01	3.6	590	540	5	23		Satisfactory	Satisfactory	Example
14	55	5.6	1.5	8	0.2	24	9.6	2.5	2.5	5.3	0.01	6.2	590	540	5	23		Satisfactory	Satisfactory	Example
15	55	7.3	1.5	6	0.2	22	10.4	2.1	2.5	5.3	0.01	8.1	590	540	5	23		Satisfactory	Satisfactory	Example
16	55	10.5	1.5	7	0.2	23	11.6	2.0	2.5	5.3	0.01	11.7	590	540	5	23		Satisfactory	Satisfactory	Example
17	55	14.2	1.5	7	0.2	22	10.8	2.0	2.5	5.3	0.01	15.8	590	540	5	23		Satisfactory	Satisfactory	Example
18	55	0.0	2.3	No Mg ₂ Si	No Mg ₂ Si	20	12.5	1.6	0.0	0.0	0.7	0.0	590	540	5	23		Poor	Poor	Comparative example
19	55	0.2	2.3	No Mg ₂ Si	No Mg ₂ Si	22	15.5	1.4	0.3	1.3	0.0	0.1	590	540	5	23		Poor	Poor	Comparative example
20	55	2.3	2.3	8	0.2	23	16.9	1.4	3.6	6.9	0.02	1.4	590	540	5	23		Unsatisfactory	Poor	Comparative example
21	55	3.2	2.3	6	0.2	25	10.4	2.4	4.6	8.1	0.02	1.9	590	540	5	23		Satisfactory	Satisfactory	Example
22	55	5.6	2.3	7	0.2	21	11.0	1.9	4.6	8.1	0.02	3.3	590	540	5	23		Satisfactory	Satisfactory	Example
23	55	5.6	2.4	7	0.2	21	11.0	1.9	3.6	6.9	0.02	3.1	590	560	5	23		Satisfactory	Excellent	Example
24	55	5.6	2.4	7	0.2	21	11.0	1.9	2.8	5.8	0.01	3.1	590	590	5	23		Satisfactory	Excellent	Example
25	55	7.3	2.3	8	0.2	23	10.6	2.2	4.6	8.1	0.02	4.3	590	540	5	23		Satisfactory	Satisfactory	Example

Table 1 (cont'd)

No.		Hot-dip coating										Production conditions				Evaluation			Remarks		
		Composition (mass%)		Mg ₂ Si major diameter (μm)	Mg ₂ Si minor diameter/ major diameter	Coating thickness (μm)	Dendrite diameter (μm)	Left side of formula (2)	Mg ₂ Si content (mass%)	Mg ₂ Si area ratio (%)	Mg ₂ Si/Al intensity ratio	Interfacial alloy layer thickness (μm)	Left side of formula (1)	Molten bath temperature (°C)	First cooling temperature (°C)	Average cooling rate (°C/sec)		Hot-dip coating corrosion resistance			
																To first cooling temperature	From first cooling temperature to 380 °C				
																					Al
26	55	14.2	2.3	6	0.2	24	12.4	1.9	4.6	8.1	0.02	0.7	8.4	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
27	55	19.4	2.3	7	0.2	24	10.2	2.4	4.6	8.1	0.02	0.7	11.4	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
28	55	24.3	2.3	7	0.1	22	10.4	2.1	4.6	8.1	0.02	0.7	14.3	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
29	55	28.5	2.3	8	0.1	26	10.7	2.4	4.6	8.1	0.02	0.7	16.8	590	540	5	23	Unsatisfactory	Unsatisfactory	Unsatisfactory	Comparative example
30	55	3.2	3.1	13	0.5	19	15.2	1.3	5.1	8.7	0.03	0.7	1.3	590	540	15	15	Unsatisfactory	Poor	Poor	Comparative example
31	55	4.5	3.1	9	0.2	24	9.9	2.4	6.8	10.5	0.02	0.7	1.8	590	540	5	23	Excellent	Satisfactory	Excellent	Example
32	55	4.5	3.1	9	0.2	24	9.9	2.4	5.1	8.5	0.02	0.6	1.8	590	560	5	25	Excellent	Satisfactory	Excellent	Example
33	55	4.5	3.1	9	0.2	24	9.9	2.4	3.9	6.4	0.02	0.5	1.8	590	590	5	27	Excellent	Satisfactory	Excellent	Example
34	45	4.8	2.9	8	0.3	23	10.3	2.2	6.3	10.0	0.03	0.7	2.1	590	540	5	23	Excellent	Satisfactory	Excellent	Example
35	65	4.6	3.0	9	0.2	22	11.7	1.9	6.6	10.2	0.03	0.7	1.9	590	540	5	23	Excellent	Satisfactory	Excellent	Example
36	55	5.6	3.1	8	0.3	24	19.4	1.2	6.8	10.5	0.03	0.7	2.2	590	540	16	16	Unsatisfactory	Unsatisfactory	Unsatisfactory	Comparative example
37	55	5.6	3.1	8	0.3	22	17.1	1.3	6.8	10.5	0.03	0.7	2.2	590	540	18	18	Unsatisfactory	Unsatisfactory	Unsatisfactory	Comparative example
38	55	5.6	3.1	7	0.2	21	13.2	1.6	6.8	10.5	0.03	0.7	2.2	590	540	5	23	Excellent	Satisfactory	Excellent	Example
39	55	5.6	3.1	8	0.2	22	10.8	2.0	6.8	10.5	0.03	0.7	2.2	590	540	5	38	Excellent	Satisfactory	Excellent	Example
40	55	5.6	3.1	8	0.2	22	10.8	2.0	5.9	9.5	0.03	0.6	2.2	590	560	5	38	Excellent	Satisfactory	Excellent	Example
41	55	5.6	3.1	8	0.2	22	10.8	2.0	4.8	8.3	0.02	0.5	2.2	590	590	5	38	Excellent	Satisfactory	Excellent	Example
42	55	7.3	3.1	8	0.2	25	9.1	2.7	6.8	10.5	0.03	0.7	2.9	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
43	55	10.5	3.1	8	0.2	22	10.5	2.1	6.8	10.5	0.03	0.7	4.2	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
44	55	14.2	3.1	8	0.2	25	9.9	2.5	6.8	10.5	0.03	0.7	5.7	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
45	55	19.4	3.1	9	0.2	23	9.6	2.4	6.8	10.5	0.03	0.7	7.8	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
46	55	24.3	3.1	7	0.2	22	9.1	2.4	6.8	10.5	0.03	0.7	9.7	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
47	55	28.5	3.1	8	0.1	21	9.2	2.3	6.8	10.5	0.03	0.7	11.4	590	540	5	23	Unsatisfactory	Unsatisfactory	Unsatisfactory	Example
48	55	7.3	5.9	14	0.5	20	16.4	1.2	11.5	14.9	0.06	0.7	1.4	590	540	15	15	Unsatisfactory	Poor	Poor	Comparative example
49	55	10.5	5.9	7	0.2	22	9.5	2.3	14.5	17.4	0.07	0.7	2.0	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
50	55	14.2	5.9	8	0.2	23	10.6	2.2	14.5	17.4	0.07	0.7	2.7	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example

Table 1 (cont'd)

No.		Hot-dip coating										Production conditions				Evaluation			Remarks					
		Composition (mass%)		Mg:Si major diameter (μm)	Mg:Si minor diameter/ major diameter	Coating thickness (μm)	Dendrite diameter (μm)	Left side of formula (2)	Mg:Si content (mass%)	Mg:Si area ratio (%)	Mg:Si/Al interdiffusion ratio	Interfacial alloy layer thickness (μm)	Left side of formula (1)	Molten bath temperature (°C)	First cooling temperature (°C)	Average cooling rate (°C/sec)		Hot-dip coating corrosion resistance						
																To first cooling temperature	From first cooling temperature to 380 °C							
																					Fit part	Edge part	Worked part	
Al	Mg	Si	55	19.4	5.9	6	0.2	21	10.3	2.0	14.5	17.4	0.07	0.7	3.7	590	540	5	23	Satisfactory				Satisfactory
52	55	24.3	5.9	8	0.2	21	9.4	2.2	14.5	0.07	0.7	4.6	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Example
53	55	28.5	5.9	7	0.1	24	11.1	2.2	14.5	0.07	0.7	5.4	590	540	5	23	Unsatisfactory	Unsatisfactory	Unsatisfactory	Unsatisfactory	Unsatisfactory	Unsatisfactory	Unsatisfactory	Comparative example
54	55	14.2	8.5	7	0.2	22	9.7	2.3	21.6	0.11	0.7	1.8	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Example
55	55	19.4	8.5	7	0.2	25	10.5	2.4	21.6	0.11	0.7	2.5	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Example
56	55	24.3	8.5	7	0.2	23	9.3	2.5	21.6	0.11	0.7	3.1	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Example
57	55	28.5	8.5	6	0.2	21	8.9	2.4	21.6	0.11	0.7	3.6	590	540	5	0	Unsatisfactory	Unsatisfactory	Unsatisfactory	Unsatisfactory	Unsatisfactory	Unsatisfactory	Unsatisfactory	Comparative example
58	55	24.3	13.5	7	0.2	24	9.8	2.4	35.2	0.18	0.7	1.9	590	540	5	0	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Example
59	55	28.5	13.5	8	0.1	22	9.0	2.4	35.2	0.18	0.7	2.2	590	540	5	23	Unsatisfactory	Unsatisfactory	Unsatisfactory	Unsatisfactory	Unsatisfactory	Unsatisfactory	Unsatisfactory	Comparative example
60	55	24.3	16.2	8	0.1	23	8.7	2.6	38.4	0.19	0.7	1.6	590	540	5	23	Unsatisfactory	Poor	Poor	Poor	Poor	Poor	Poor	Comparative example
61	55	28.5	16.2	7	0.1	20	9.6	2.1	42.6	0.21	0.7	1.8	590	540	5	23	Unsatisfactory	Unsatisfactory	Unsatisfactory	Unsatisfactory	Unsatisfactory	Unsatisfactory	Unsatisfactory	Comparative example
62	55	3.2	1.5	7	0.1	17	10.9	1.6	5.2	0.01	0.9	3.6	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Example
63	55	5.6	1.5	8	0.2	15	9.6	1.6	5.5	0.01	0.9	6.2	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Example
64	55	7.3	1.5	6	0.2	16	10.1	1.6	5.3	0.01	0.8	8.1	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Example
65	55	10.5	1.5	7	0.2	17	10.8	1.6	5.5	0.01	0.9	11.7	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Example
66	55	14.2	1.5	7	0.2	17	10.7	1.6	5.3	0.01	0.9	15.8	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Example
67	55	5.6	3.1	8	0.2	17	10.5	1.6	4.8	0.02	0.5	2.2	590	590	5	38	Excellent	Satisfactory	Excellent	Excellent	Excellent	Excellent	Excellent	Example
68	55	7.3	3.1	8	0.2	15	9.1	1.6	6.8	0.03	0.7	2.9	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Example
69	30	4.8	2.9	6	0.2	17	10.5	1.6	6.4	0.03	0.5	2.1	560	520	5	23	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Example
70	35	4.8	2.9	7	0.2	17	10.8	1.6	6.2	0.03	0.5	2.1	570	530	5	23	Excellent	Satisfactory	Excellent	Excellent	Excellent	Excellent	Excellent	Example
71	45	4.8	2.9	8	0.3	16	10.3	1.6	6.3	0.03	0.7	2.1	590	540	5	23	Excellent	Satisfactory	Excellent	Excellent	Excellent	Excellent	Excellent	Example
72	65	4.8	2.9	8	0.2	18	11.2	1.6	6.3	0.03	0.7	2.1	590	540	5	23	Excellent	Satisfactory	Excellent	Excellent	Excellent	Excellent	Excellent	Example
73	70	4.8	2.9	8	0.2	18	11.5	1.6	6.1	0.03	0.9	2.1	620	570	5	23	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Satisfactory	Example
74	55	0.0	1.5	No Mg:Si	No Mg:Si	15	15.0	1.0	0.0	0.00	1.2	0.0	590	540	5	23	Poor	Poor	Poor	Poor	Poor	Poor	Poor	Comparative example

[0060] It can be seen from Table 1 that samples of the “Examples” had excellent corrosion resistance in flat parts, edge parts, and worked parts compared to the samples of the “Comparative examples”.

[0061] (Example 2)

5 Some of the hot-dip Al-Zn-Mg-Si coated steel sheet samples produced in Example 1 (refer to Table 2 for the sample numbers) were subjected to formation of a urethane resin-based chemical conversion coating (CT-E-364 produced by Nihon Parkerizing Co., Ltd.). The coating weight of the chemical conversion coating was 1 g/m².

10 Production conditions (molten bath temperature, first cooling temperature, and cooling rate) and hot-dip coating conditions (composition, major diameter of Mg₂Si, minor diameter/major diameter of Mg₂Si, thickness of hot-dip coating, left side of formula (1), left side of formula (2), Mg₂Si content in main layer, Mg₂Si area ratio in main layer cross-section, intensity ratio of Mg₂Si relative to Al, and thickness of interfacial alloy layer) are shown in Table 2.

[0062] (Evaluation of chemical conversion corrosion resistance)

(1) Evaluation of flat part and edge part corrosion resistance

20 Each hot-dip Al-Zn-Mg-Si coated steel sheet sample on which a chemical conversion coating had been formed was subjected to a Japan Automotive Standards Organization Cyclic Corrosion Test (JASO-CCT). Each cycle of the JASO-CCT included salt spraying, drying, and wetting under specific conditions as illustrated in FIG. 6.

25 The number of cycles until red rust formed was counted with respect to a flat part and an edge part of each of the samples, and was then evaluated in accordance with the following standard.

Excellent: Red rust formation cycle count $\geq$ 700 Cycles

Satisfactory: 500 Cycles $\leq$ Red rust formation cycle count < 700 Cycles

30 Unsatisfactory: 400 Cycles $\leq$ Red rust formation cycle count < 500 Cycles

Poor: Red rust formation cycle count < 400 Cycles

(2) Evaluation of bent worked part corrosion resistance

Each hot-dip Al-Zn-Mg-Si coated steel sheet sample on which a

chemical conversion coating had been formed was worked by 180° bending to sandwich three sheets of the same sheet thickness at the inside (3T bending), and was then subjected to a Japan Automotive Standards Organization Cyclic Corrosion Test (JASO-CCT) at the outside of the bend. Each cycle of the
5 JASO-CCT included salt spraying, drying, and wetting under specific conditions as illustrated in FIG. 6.

The number of cycles until red rust formed was counted with respect to the worked part of each of the samples, and was then evaluated in accordance with the following standard.

- 10 Excellent: Red rust formation cycle count $\geq$ 700 Cycles
 Satisfactory: 500 Cycles $\leq$ Red rust formation cycle count < 700
Cycles
 Unsatisfactory: 400 Cycles $\leq$ Red rust formation cycle count < 500
Cycles
15 Poor: Red rust formation cycle count < 400 Cycles

[0063] Table 2

Table 2		Hot-dip coating											Production conditions				Evaluation			Remarks		
		Composition (mass%)		MgSi major diameter (μm)	MgSi minor diameter/ major diameter	Coating thickness (μm)	Dendrite diameter (μm)	Left side of formula (2)	MgSi content (mass%)	MgSi area ratio (%)	MgSi/Al intensity ratio	Interfacial alloy layer thickness (μm)	Left side of formula (1)	Molten bath temperature (°C)	First cooling temperature (°C)	Average cooling rate (°C/sec)		Chemical conversion corrosion resistance				
																To first cooling temperature	From first cooling temperature to 380 °C	Flat part	Edge part		Worked part	
No.		Al	Mg	Si																		
1		55	5.6	0.5	No MgSi	No MgSi	21	10.5	2.0	0.0	0.00	1.2	-56.0	590	540	5	23	Poor	Poor	Poor	Comparative example	
2		55	7.3	0.5	No MgSi	No MgSi	22	12.2	1.8	0.0	0.00	1.2	-73.0	590	540	5	23	Poor	Poor	Poor	Comparative example	
3		55	3.2	1.1	8	0.2	23	11.6	2.0	1.4	1.2	0.01	1.0	6.4	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
4		55	5.6	1.1	6	0.1	26	10.9	2.4	1.4	1.2	0.01	1.0	11.2	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
5		55	0.0	1.5	No MgSi	No MgSi	24	11.4	2.1	0.0	0.00	0.9	0.0	0.0	590	540	5	23	Unsatisfactory	Poor	Poor	Comparative example
6		55	0.0	1.5	No MgSi	No MgSi	23	10.8	2.1	0.0	0.00	0.9	0.0	0.0	590	540	5	23	Poor	Poor	Unsatisfactory	Comparative example
7		55	1.1	1.5	9	0.2	21	15.7	1.3	1.7	4.2	0.01	0.9	1.2	590	540	5	23	Poor	Poor	Poor	Comparative example
8		55	1.8	1.5	6	0.2	22	12.3	1.8	2.5	5.3	0.01	0.9	2.0	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
9		55	5.6	1.5	8	0.2	24	9.6	2.5	2.5	5.3	0.01	0.9	6.2	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
10		55	10.5	1.5	7	0.2	23	11.6	2.0	2.5	5.3	0.01	0.9	11.7	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
11		55	0.0	2.3	No MgSi	No MgSi	20	12.5	1.6	0.0	0.00	0.7	0.0	0.0	590	540	5	23	Poor	Poor	Poor	Comparative example
12		55	0.2	2.3	No MgSi	No MgSi	22	15.5	1.4	0.3	1.3	0.00	0.7	0.1	590	540	5	23	Poor	Poor	Poor	Comparative example
13		55	3.2	2.3	6	0.2	25	10.4	2.4	4.6	8.1	0.02	0.7	1.9	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
14		55	5.6	2.4	7	0.2	21	11.0	1.9	3.6	6.9	0.02	0.6	3.1	590	560	5	23	Excellent	Satisfactory	Excellent	Example
15		55	5.6	2.4	7	0.2	21	11.0	1.9	2.8	5.8	0.01	0.5	3.1	590	590	5	23	Excellent	Satisfactory	Excellent	Example
16		55	7.3	2.3	8	0.2	23	10.6	2.2	4.6	8.1	0.02	0.7	4.3	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
17		55	19.4	2.3	7	0.2	24	10.2	2.4	4.6	8.1	0.02	0.7	11.4	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
18		55	28.5	2.3	8	0.1	26	10.7	2.4	4.6	8.1	0.02	0.7	16.8	590	540	5	23	Unsatisfactory	Unsatisfactory	Unsatisfactory	Comparative example
19		55	4.5	3.1	9	0.2	24	9.9	2.4	5.1	8.5	0.02	0.6	1.8	590	560	5	25	Excellent	Satisfactory	Excellent	Example
20		55	4.5	3.1	9	0.2	24	9.9	2.4	3.9	6.4	0.02	0.5	1.8	590	590	5	27	Excellent	Satisfactory	Excellent	Example

Table 2 (cont'd)

No.		Hot-dip coating										Production conditions				Evaluation			Remarks		
		Composition (mass%)		Mg/Si major diameter (μm)	Mg/Si minor diameter/ major diameter	Coating thickness (μm)	Dendrite diameter (μm)	Left side of formula (2)	Mg/Si content (mass%)	Mg/Si area ratio (%)	Mg/Si/Al intensity ratio	Interfacial alloy layer thickness (μm)	Left side of formula (1)	Molten bath temperature (°C)	First cooling temperature (°C)	Average cooling rate (°C/sec)		Chemical conversion corrosion resistance			
																To first cooling temperature	From first cooling temperature to 380 °C	Flat part		Edge part	Worked part
21	55	5.6	3.1	8	0.3	24	19.4	1.2	6.8	10.5	0.03	0.7	2.2	590	540	16	16	Unsatisfactory	Unsatisfactory	Unsatisfactory	Comparative example
22	55	5.6	3.1	8	0.3	22	17.1	1.3	6.8	10.5	0.03	0.7	2.2	590	540	18	18	Unsatisfactory	Unsatisfactory	Unsatisfactory	Comparative example
23	55	5.6	3.1	7	0.2	21	13.2	1.6	6.8	10.5	0.03	0.7	2.2	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
24	55	5.6	3.1	8	0.2	22	10.8	2.0	6.8	10.5	0.03	0.7	2.2	590	540	5	38	Excellent	Satisfactory	Excellent	Example
25	55	5.6	3.1	8	0.2	22	10.8	2.0	5.9	9.5	0.03	0.6	2.2	590	560	5	38	Excellent	Satisfactory	Excellent	Example
26	55	5.6	3.1	8	0.2	22	10.8	2.0	4.8	8.3	0.02	0.5	2.2	590	590	5	38	Excellent	Satisfactory	Excellent	Example
27	55	10.5	3.1	8	0.2	22	10.5	2.1	6.8	10.5	0.03	0.7	4.2	590	540	5	23	Excellent	Satisfactory	Excellent	Example
28	55	19.4	3.1	9	0.2	23	9.6	2.4	6.8	10.5	0.03	0.7	7.8	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
29	55	28.5	3.1	8	0.1	21	9.2	2.3	6.8	10.5	0.03	0.7	11.4	590	540	5	23	Unsatisfactory	Unsatisfactory	Unsatisfactory	Comparative example
30	55	7.3	5.9	14	0.5	20	16.4	1.2	11.5	14.9	0.06	0.7	1.4	590	540	15	15	Unsatisfactory	Poor	Poor	Comparative example
31	55	10.5	5.9	7	0.2	22	9.5	2.3	14.5	17.4	0.07	0.7	2.0	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
32	55	19.4	5.9	6	0.2	21	10.3	2.0	14.5	17.4	0.07	0.7	3.7	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
33	55	24.3	5.9	8	0.2	21	9.4	2.2	14.5	17.4	0.07	0.7	4.6	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
34	55	28.5	5.9	7	0.1	24	11.1	2.2	14.5	17.4	0.07	0.7	5.4	590	540	5	23	Unsatisfactory	Unsatisfactory	Unsatisfactory	Comparative example
35	55	14.2	8.5	7	0.2	22	9.7	2.3	21.6	22.7	0.11	0.7	1.8	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
36	55	24.3	8.5	7	0.2	23	9.3	2.5	21.6	22.7	0.11	0.7	3.1	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
37	55	28.5	8.5	6	0.2	21	8.9	2.4	21.6	22.7	0.11	0.7	3.6	590	540	5	23	Unsatisfactory	Unsatisfactory	Unsatisfactory	Comparative example
38	55	24.3	13.5	7	0.2	24	9.8	2.4	35.2	31.4	0.18	0.7	1.9	590	540	5	23	Satisfactory	Satisfactory	Satisfactory	Example
39	55	28.5	13.5	8	0.1	22	9.0	2.4	35.2	31.4	0.18	0.7	2.2	590	540	5	23	Unsatisfactory	Unsatisfactory	Unsatisfactory	Comparative example
40	55	24.3	16.2	8	0.1	23	8.7	2.6	38.4	33.3	0.19	0.7	1.6	590	540	5	23	Unsatisfactory	Poor	Poor	Comparative example
41	55	28.5	16.2	7	0.1	20	9.6	2.1	42.6	35.7	0.21	0.7	1.8	590	540	5	23	Unsatisfactory	Unsatisfactory	Unsatisfactory	Comparative example

[0064] It can be seen from Table 2 that the samples of the “Examples” had excellent corrosion resistance in flat parts, edge parts, and worked parts compared to the samples of the “Comparative examples”.

[0065] (Example 3)

5 With respect to each of the hot-dip Al-Zn-Mg-Si coated steel sheet samples subjected to formation of a chemical conversion coating in Example 2, 5 μm of an epoxy resin-based primer (JT-25 produced by Nippon Fine Coatings) and 15 μm of a melamine cured polyester-based top coating (NT-GLT produced by Nippon Fine Coatings) were applied in this order and
10 dried to produce a coated steel sheet sample.

 Production conditions (molten bath temperature, first cooling temperature, and cooling rate) and hot-dip coating conditions (composition, major diameter of Mg_2Si , minor diameter/major diameter of Mg_2Si , thickness of hot-dip coating, left side of formula (1), left side of formula (2), Mg_2Si
15 content in main layer, Mg_2Si area ratio in main layer cross-section, intensity ratio of Mg_2Si relative to Al, and thickness of interfacial alloy layer) are shown in Table 3.

[0066] (Evaluation of post-coating corrosion resistance)

(1) Evaluation of bent worked part corrosion resistance

20 Each coated steel sheet sample was worked by 180° bending to sandwich three sheets of the same sheet thickness at the inside (3T bending), and was then subjected to a Japan Automotive Standards Organization Cyclic Corrosion Test (JASO-CCT) at the outside of the bend. Each cycle of the JASO-CCT included salt spraying, drying, and wetting under specific
25 conditions as illustrated in FIG. 6.

 The number of cycles until red rust formed was counted with respect to the worked part of each of the samples, and was then evaluated in accordance with the following standard.

 Excellent: Red rust formation cycle count ≥ 600 Cycles

30 Satisfactory: $400 \text{ Cycles} \leq \text{Red rust formation cycle count} < 600$
Cycles

 Unsatisfactory: $300 \text{ Cycles} \leq \text{Red rust formation cycle count} < 400$
Cycles

 Poor: Red rust formation cycle count < 300 Cycles

[0067] Table 3

No.		Hot-dip coating										Production conditions				Evaluation		Remarks					
		Composition (mass%)		Mg ₂ Si major diameter (μm)	Mg ₂ Si minor diameter/ major diameter	Coating thickness (μm)	Dendrite diameter (μm)	Left side of formula (2)	Mg ₂ Si content (mass%)	Mg ₂ Si area ratio (%)	Mg ₂ Si/Al intensity ratio	Interfacial alloy layer thickness (μm)	Left side of formula (1)	Molten bath temperature (°C)	First cooling temperature (°C)	Average cooling rate (°C/sec)			Post-coating corrosion resistance				
																To first cooling temperature	From first cooling temperature to 380 °C						
																				To first cooling temperature	From first cooling temperature to 380 °C		
Al	Mg	Si	1	55	5.6	0.5	No Mg ₂ Si	21	10.5	2.0	0.0	0.0	1.2	-56.0	590	540	5	23	Poor			Comparative example	
					2	55	7.3	0.5	No Mg ₂ Si	22	12.2	1.8	0.0	0.0	1.2	-73.0	590	540	5	23	Poor	Comparative example	
					3	55	3.2	1.1	8	23	11.6	2.0	1.4	1.2	0.01	1.0	6.4	590	540	5	23	Satisfactory	Example
					4	55	5.6	1.1	6	26	10.9	2.4	1.4	1.2	0.01	1.0	11.2	590	540	5	23	Satisfactory	Example
					5	55	0.0	1.5	No Mg ₂ Si	24	11.4	2.1	0.0	0.0	0.00	0.9	0.0	590	540	5	23	Poor	Comparative example
					6	55	0.0	1.5	No Mg ₂ Si	23	10.8	2.1	0.0	0.0	0.00	0.9	0.0	590	540	5	23	Unsatisfactory	Comparative example
					7	55	1.1	1.5	9	21	15.7	1.3	1.7	4.2	0.01	0.9	1.2	590	540	5	23	Poor	Comparative example
					8	55	1.8	1.5	6	22	12.3	1.8	2.5	5.3	0.01	0.9	2.0	590	540	5	23	Satisfactory	Example
					9	55	5.6	1.5	8	24	9.6	2.5	2.5	5.3	0.01	0.9	6.2	590	540	5	23	Satisfactory	Example
					10	55	10.5	1.5	7	23	11.6	2.0	2.5	5.3	0.01	0.9	11.7	590	540	5	23	Satisfactory	Example
					11	55	0.0	2.3	No Mg ₂ Si	20	12.5	1.6	0.0	0.0	0.00	0.7	0.0	590	540	5	23	Poor	Comparative example
					12	55	0.2	2.3	No Mg ₂ Si	22	15.5	1.4	0.3	1.3	0.00	0.7	0.1	590	540	5	23	Poor	Comparative example
					13	55	3.2	2.3	6	25	10.4	2.4	4.6	8.1	0.02	0.7	1.9	590	540	5	23	Satisfactory	Example
					14	55	5.6	2.4	7	21	11.0	1.9	3.6	6.9	0.02	0.6	3.1	590	560	5	23	Excellent	Example
					15	55	5.6	2.4	7	21	11.0	1.9	2.8	5.8	0.01	0.5	3.1	590	590	5	23	Excellent	Example
					16	55	7.3	2.3	8	23	10.6	2.2	4.6	8.1	0.02	0.7	4.3	590	540	5	23	Satisfactory	Example
					17	55	19.4	2.3	7	24	10.2	2.4	4.6	8.1	0.02	0.7	11.4	590	540	5	23	Satisfactory	Example
					18	55	28.5	2.3	8	26	10.7	2.4	4.6	8.1	0.02	0.7	16.8	590	540	5	23	Unsatisfactory	Comparative example
					19	55	4.5	3.1	9	24	9.9	2.4	5.1	8.5	0.02	0.6	1.8	590	560	5	25	Excellent	Example
					20	55	4.5	3.1	9	24	9.9	2.4	3.9	6.4	0.02	0.5	1.8	590	590	5	27	Excellent	Example

Table 3 (cont'd)

No.		Hot-dip coating																Production conditions			Evaluation		Remarks
		Composition (mass%)		Mg ₂ Si major diameter (μm)	Mg ₂ Si minor diameter/ major diameter	Coating thickness (μm)	Dendrite diameter (μm)	Left side of formula (2)	Mg ₂ Si content (mass%)	Mg ₂ Si area ratio (%)	Mg ₂ Si/Al intensity ratio	Interfacial alloy layer thickness (μm)	Left side of formula (1)	Molten bath temperature (°C)	First cooling temperature (°C)	Average cooling rate (°C/sec)		Post-coating corrosion resistance					
																Al	Mg		Si	To first cooling temperature	From first cooling temperature to 380 °C		
		55	5.6	3.1	8	0.3	24	19.4	<u>1.2</u>	6.8	10.5	0.03	0.7	2.2	590	540	<u>16</u>	16	Unsatisfactory	Comparative example			
		55	5.6	3.1	8	0.3	22	17.1	<u>1.3</u>	6.8	10.5	0.03	0.7	2.2	590	540	<u>18</u>	18	Unsatisfactory	Comparative example			
		55	5.6	3.1	7	0.2	21	13.2	1.6	6.8	10.5	0.03	0.7	2.2	590	540	5	23	Satisfactory	Example			
		55	5.6	3.1	8	0.2	22	10.8	2.0	6.8	10.5	0.03	0.7	2.2	590	540	5	38	Satisfactory	Example			
		55	5.6	3.1	8	0.2	22	10.8	2.0	5.9	9.5	0.03	0.6	2.2	590	560	5	38	Excellent	Example			
		55	5.6	3.1	8	0.2	22	10.8	2.0	4.8	8.3	0.02	0.5	2.2	590	590	5	38	Excellent	Example			
		55	10.5	3.1	8	0.2	22	10.5	2.1	6.8	10.5	0.03	0.7	4.2	590	540	5	23	Satisfactory	Example			
		55	19.4	3.1	9	0.2	23	9.6	2.4	6.8	10.5	0.03	0.7	7.8	590	540	5	23	Satisfactory	Example			
		55	28.5	3.1	8	0.1	21	9.2	2.3	6.8	10.5	0.03	0.7	11.4	590	540	5	23	Unsatisfactory	Comparative example			
		55	7.3	5.9	<u>14</u>	<u>0.5</u>	<u>20</u>	<u>16.4</u>	<u>1.2</u>	11.5	14.9	0.06	0.7	<u>1.4</u>	590	540	<u>15</u>	15	Poor	Comparative example			
		55	10.5	5.9	7	0.2	22	9.5	2.3	14.5	17.4	0.07	0.7	2.0	590	540	5	23	Satisfactory	Example			
		55	19.4	5.9	6	0.2	21	10.3	2.0	14.5	17.4	0.07	0.7	3.7	590	540	5	23	Satisfactory	Example			
		55	24.3	5.9	8	0.2	21	9.4	2.2	14.5	17.4	0.07	0.7	4.6	590	540	5	23	Satisfactory	Example			
		55	28.5	5.9	7	0.1	24	11.1	2.2	14.5	17.4	0.07	0.7	5.4	590	540	5	23	Unsatisfactory	Comparative example			
		55	14.2	8.5	7	0.2	22	9.7	2.3	21.6	22.7	0.11	0.7	1.8	590	540	5	23	Satisfactory	Example			
		55	24.3	8.5	7	0.2	23	9.3	2.5	21.6	22.7	0.11	0.7	3.1	590	540	5	23	Satisfactory	Example			
		55	28.5	8.5	6	0.2	21	8.9	2.4	21.6	22.7	0.11	0.7	3.6	590	540	5	23	Unsatisfactory	Comparative example			
		55	24.3	13.5	7	0.2	24	9.8	2.4	35.2	31.4	0.18	0.7	1.9	590	540	5	23	Satisfactory	Example			
		55	28.5	13.5	8	0.1	22	9.0	2.4	35.2	31.4	0.18	0.7	2.2	590	540	5	23	Unsatisfactory	Comparative example			
		55	24.3	<u>16.2</u>	8	0.1	23	8.7	2.6	38.4	33.3	0.19	0.7	<u>1.6</u>	590	540	5	23	Poor	Comparative example			
		55	28.5	<u>16.2</u>	7	0.1	20	9.6	2.1	42.6	35.7	0.21	0.7	1.8	590	540	5	23	Unsatisfactory	Comparative example			

[0068] It can be seen from Table 3 that the samples of the “Examples” had excellent corrosion resistance in worked parts compared to the samples of the “Comparative examples”.

[0069] (Example 4)

5 Some of the hot-dip Al-Zn-Mg-Si coated steel sheet samples produced in Example 1 (refer to Table 4 for the sample numbers) were each sheared to a size of 90 mm × 70 mm and then subjected to zinc phosphate treatment as chemical conversion treatment, followed by electrodeposition coating, intermediate coating, and top coating in the same way as in coating treatment
10 for an automobile outer panel.

 Zinc phosphate treatment: A degreasing agent “FC-E2001” produced by Nihon Parkerizing Co., Ltd., a surface-modifying agent “PL-X” produced by Nihon Parkerizing Co., Ltd., and a zinc phosphate treatment agent “PB-AX35M” (temperature: 35°C) produced by Nihon Parkerizing Co., Ltd.
15 were used under conditions of a free-fluorine concentration in the zinc phosphate treatment liquid of 200 ppm and an immersion time in the zinc phosphate treatment liquid of 120 seconds.

 Electrodeposition coating: An electrodeposition coating material “GT-100” produced by Kansai Paint Co., Ltd. was used to perform
20 electrodeposition coating with a thickness of 15 μm.

 Intermediate coating: An intermediate coating material “TP-65-P” produced by Kansai Paint Co., Ltd. was used to perform spray coating with a thickness of 30 μm.

 Top coating: A top coating material “Neo6000” produced by Kansai
25 Paint Co., Ltd. was used to perform spray coating with a thickness of 30 μm.

 Production conditions (molten bath temperature, first cooling temperature, and cooling rate) and hot-dip coating conditions (composition, major diameter of Mg₂Si, minor diameter/major diameter of Mg₂Si, thickness of hot-dip coating, left side of formula (1), left side of formula (2), Mg₂Si
30 content in main layer, Mg₂Si area ratio in main layer cross-section, intensity ratio of Mg₂Si relative to Al, and thickness of interfacial alloy layer) are shown in Table 4.

[0070] (Evaluation of post-coating corrosion resistance)

 For each of the hot-dip Al-Zn-Mg-Si coated steel sheet samples

subjected to the coating treatment, a sample for evaluating post-coating corrosion resistance was obtained as illustrated in FIG. 7 by using tape to seal a non-evaluation surface (rear surface) and a 5 mm edge part of an evaluation surface, and then using a cutter knife to form a cross-cut scar in the center of the evaluation surface with a length of 60 mm and a center angle of 90°, and to a depth reaching the steel substrate of the hot-dip coated steel sheet.

The evaluation sample was subjected to an accelerated corrosion test (SAE J 2334) through cycles illustrated in FIG. 8. The accelerated corrosion test was started from wetting and was continued until 30 cycles had been completed. The coating film blister width of a part at which greatest coating film blistering from the scar part occurred (maximum coating film blister width) was measured, and then post-coating corrosion resistance was evaluated in accordance with the following standard. The evaluation results are shown in Table 4.

- 15 Excellent: Maximum coating film blister width ≤ 2.5 mm
- Good: $2.5 \text{ mm} < \text{Maximum coating film blister width} \leq 3.0 \text{ mm}$
- Poor: $3.0 \text{ mm} < \text{Maximum coating film blister width}$

[0071] Table 4

	Hot-dip coating												Production conditions				Evaluation		Remarks
	Composition (mass%)			Mg ₂ Si major diameter (μm)	Mg ₂ Si minor diameter/ major diameter	Coating thickness (μm)	Dendrite diameter (μm)	Left side of formula (2)	Mg ₂ Si content (mass%)	Mg ₂ Si area ratio (%)	Mg ₂ Si/Al intensity ratio	Interfacial alloy layer thickness (μm)	Left side of formula (1)	Molten bath temperature (°C)	First cooling temperature (°C)	Average cooling rate (°C/sec)		Post-coating corrosion resistance	
	Al	Mg	Si													To first cooling temperature	From first cooling temperature to 380 °C		
No.																			
62	55	3.2	1.5	7	0.1	17	10.9	1.6	2.4	5.2	0.01	0.9	3.6	590	540	5	23	Good	Example
63	55	5.6	1.5	8	0.2	15	9.6	1.6	2.6	5.5	0.01	0.9	6.2	590	540	5	23	Excellent	Example
64	55	7.3	1.5	6	0.2	16	10.1	1.6	2.5	5.3	0.01	0.8	8.1	590	540	5	23	Excellent	Example
65	55	10.5	1.5	7	0.2	17	10.8	1.6	2.6	5.5	0.01	0.9	11.7	590	540	5	23	Excellent	Example
66	55	14.2	1.5	7	0.2	17	10.7	1.6	2.5	5.3	0.01	0.9	15.8	590	540	5	23	Good	Example
67	55	5.6	3.1	8	0.2	17	10.5	1.6	4.8	8.3	0.02	0.5	2.2	590	590	5	38	Excellent	Example
68	55	7.3	3.1	8	0.2	15	9.1	1.6	6.8	10.5	0.03	0.7	2.9	590	540	5	23	Excellent	Example
69	30	4.8	2.9	6	0.2	17	10.5	1.6	6.4	10.1	0.03	0.5	2.1	560	520	5	23	Good	Example
70	35	4.8	2.9	7	0.2	17	10.8	1.6	6.2	9.9	0.03	0.5	2.1	570	530	5	23	Good	Example
71	45	4.8	2.9	8	0.3	16	10.3	1.6	6.3	10.0	0.03	0.7	2.1	590	540	5	23	Good	Example
72	65	4.8	2.9	8	0.2	18	11.2	1.6	6.3	10.0	0.03	0.7	2.1	590	540	5	23	Good	Example
73	70	4.8	2.9	8	0.2	18	11.5	1.6	6.1	9.8	0.03	0.9	2.1	620	570	5	23	Good	Example
74	55	0.0	1.5	No Mg ₂ Si	No Mg ₂ Si	15	15.0	1.0	0.0	0.0	0.00	1.2	0.0	590	540	5	23	Poor	Comparative example

Table 4

[0072] It can be seen from Table 4 that in the case of samples for which the Mg content was greater than 5 mass%, in contrast to samples for which the Mg content was 5 mass% or less, the maximum coating film blister width was restricted to 2.5 mm or less, and hot-dip Al-Zn alloy coated steel sheets
5 having excellent post-coating corrosion resistance were obtained.

Accordingly, it can be seen that among the samples of the “Examples”, a hot-dip Al-Zn-Mg-Si coated steel sheet having excellent post-coating corrosion resistance can be obtained by controlling the Mg content in the hot-dip coating layer to within an appropriate range.

10

INDUSTRIAL APPLICABILITY

[0073] According to this disclosure, it is possible to provide a hot-dip Al-Zn-Mg-Si coated steel sheet having good corrosion resistance in flat parts and edge parts, and also having excellent worked part corrosion resistance,
15 and also to provide a method of producing this hot-dip Al-Zn-Mg-Si coated steel sheet.

CLAIMS

1. A hot-dip Al-Zn-Mg-Si coated steel sheet comprising
a base steel sheet and a hot-dip coating on a surface of the base steel
5 sheet, wherein

the hot-dip coating includes an interfacial alloy layer present at an
interface with the base steel sheet and a main layer present on the interfacial
alloy layer, and contains from 25 mass% to 80 mass% of Al, from greater than
0.6 mass% to 15 mass% of Si, and from greater than 0.1 mass% to 25 mass%
10 of Mg, and

Mg content and Si content in the hot-dip coating satisfy formula (1):

$$M_{\text{Mg}}/(M_{\text{Si}} - 0.6) > 1.7 \quad (1)$$

where M_{Mg} represents the Mg content in mass% and M_{Si} represents the Si
content in mass%.

15

2. The hot-dip Al-Zn-Mg-Si coated steel sheet according to claim 1,
wherein

the main layer contains Mg_2Si , and Mg_2Si content in the main layer is
1.0 mass% or more.

20

3. The hot-dip Al-Zn-Mg-Si coated steel sheet according to claim 1,
wherein

the main layer contains Mg_2Si , and an area ratio of Mg_2Si in a
cross-section of the main layer is 1 % or more.

25

4. The hot-dip Al-Zn-Mg-Si coated steel sheet according to claim 1,
wherein

the main layer contains Mg_2Si , and according to X-ray diffraction
analysis, an intensity ratio of Mg_2Si (111) planes having an interplanar
30 spacing d of 0.367 nm relative to Al (200) planes having an interplanar
spacing d of 0.202 nm is 0.01 or more.

5. The hot-dip Al-Zn-Mg-Si coated steel sheet according to any one of
claims 1 to 4, wherein

the interfacial alloy layer has a thickness of 1 μm or less.

6. The hot-dip Al-Zn-Mg-Si coated steel sheet according to any one of claims 1 to 4, wherein

5 the main layer includes an α -Al phase dendritic region, and a mean dendrite diameter of the α -Al phase dendritic region and a thickness of the hot-dip coating satisfy formula (2):

$$t/d \geq 1.5 \quad (2)$$

where t represents the thickness of the hot-dip coating in μm and d represents
10 the mean dendrite diameter in μm .

7. The hot-dip Al-Zn-Mg-Si coated steel sheet according to any one of claims 1 to 6, wherein

 the hot-dip coating contains from 25 mass% to 80 mass% of Al, from
15 greater than 2.3 mass% to 5 mass% of Si, and from 3 mass% to 10 mass% of Mg.

8. The hot-dip Al-Zn-Mg-Si coated steel sheet according to any one of claims 1 to 6, wherein

20 the hot-dip coating contains from 25 mass% to 80 mass% of Al, from greater than 0.6 mass% to 15 mass% of Si, and from greater than 5 mass% to 10 mass% of Mg.

9. A method of producing a hot-dip Al-Zn-Mg-Si coated steel sheet,
25 comprising

 hot-dip coating a base steel sheet by immersing the base steel sheet in a molten bath containing from 25 mass% to 80 mass% of Al, from greater than 0.6 mass% to 15 mass% of Si, and from greater than 0.1 mass% to 25 mass% of Mg, the balance being Zn and incidental impurities,

30 subsequently cooling a resultant hot-dip coated steel sheet to a first cooling temperature at an average cooling rate of less than 10 $^{\circ}\text{C}/\text{sec}$, the first cooling temperature being no higher than a bath temperature of the molten bath and no lower than 50 $^{\circ}\text{C}$ below the bath temperature, and

 then cooling the hot-dip coated steel sheet from the first cooling

temperature to 380 °C at an average cooling rate of 10 °C/sec or more.