

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau

(43) International Publication Date
12 August 2021 (12.08.2021)



(10) International Publication Number
WO 2021/158204 A1

(51) International Patent Classification:

C03B 18/02 (2006.01) C03C 4/00 (2006.01)
C03C 3/087 (2006.01)

(21) International Application Number:

PCT/US2020/016363

(22) International Filing Date:

03 February 2020 (03.02.2020)

(25) Filing Language:

English

(26) Publication Language:

English

(71) Applicant: **VITRO FLAT GLASS LLC** [US/US]; 400
Guys Run Road, Cheswick, Pennsylvania 15024 (US).

(72) Inventors: **CID-AGUILAR, José, Guadalupe**; Rio Eu-
frates No. 324, Colonia Paseo de las Cumbres, Monterrey,
Nuevo León, 64346 (MX). **HASKINS, David, R.**; 10511
Old Babcock Blvd., Gibsonia, Pennsylvania 15044 (US).
BUCHANAN, Michael, J.; 90 Winterbrook Drive, Cran-
berry Township, Pennsylvania 16066 (US).

(74) Agent: **FORTNEY, Lester, N.** et al.; The Webb Law Firm,
One Gateway Center, 420 Ft. Duquesne Blvd., Suite 1200,
Pittsburgh, Pennsylvania Pittsburgh (US).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,


AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ,
CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO,
DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN,
HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP,
KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME,
MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ,
OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA,
SC, SD, SE, SG, SK, SL, ST, SV, SY, TH, TJ, TM, TN, TR,
TT, TZ, UA, UG, US, UZ, VC, VN, WS, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ,
UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ,
TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK,
EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV,
MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM,
TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,
KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: SODA LIME SILICA GLASS WITH HIGH VISIBLE LIGHT TRANSMITTANCE



(57) Abstract: The present invention provides a glass sheet having soda-lime-silica glass composition with a high visible light transmittance (L_{IC}) of at least 89%; with a dominant wavelength (DW) from about 490 to 505 nanometers and purity (Pe) of no more than 1% for control thickness of 5.66 mm, and methods of making the same. The glass composition comprising a low iron raw material, a total iron oxide (Fe_2O_3) of 0.02 to 0.06 wt. %, ferrous (FeO) from 0.006 to 0.02 wt. %, redox (FeO/Fe_2O_3) from about 0.30 to 0.55; Cr_2O_3 from about 0.3 to 10 ppm, TiO_2 from about 50 to 500 ppm; SnO_2 from about 10 to 500 ppm and a critical amount from about 0.10 to 0.25 wt. % of SO_3 . The low content of iron oxide is achieved by the partial substitution of regular raw materials by low iron raw materials, with a complete substitution of regular dolomite by a low iron dolomite with a maximum content of 0.020 wt. % Fe_2O_3 .