

METHOD FOR MEASURING THICKNESS VARIATIONS IN A LAYER OF A MULTILAYER SEMICONDUCTOR STRUCTURE

FIELD OF THE INVENTION

5 The present invention relates to a method for measuring thickness variations in a layer of a multilayer semiconductor layer, as well as to a system allowing application of said method.

BACKGROUND OF THE INVENTION

10 In the field of electronics, multilayer semiconductor structures are frequently used.

A particular example of such structures is a structure of the semiconductor-on-insulator (SeOI) type.

A structure of the SeOI type typically comprises from its base to its surface a supporting substrate, an electrically insulating layer and a thin semiconducting layer,
15 called active layer, in or on which electronic components are generally intended to be formed.

When the thin layer is in silicon, the structure is designated by the term of SOI, an acronym of "Silicon On Insulator".

The electrically insulating layer is in a dielectric material, notably an oxide of the
20 material of the supporting substrate and/or of the thin layer. This layer is then usually designated by the term of BOX, acronym of "Buried Oxide".

Recently, SOI structures having an extra-thin layer of silicon have been developed.

These structures are designated by the term of "FDSOI", for "Fully Depleted SOI", i.e. a totally depleted SOI.

25 By "ultra-thin" is meant a thickness of less than or equal to 50 nm, preferably less than or equal to 12 nm, which may even be reduced down to about 5 nm.

FDSOI structures are particularly advantageous for producing planar electronic components, for example FDMOS (acronym of "Fully Depleted Metal Oxide Semiconductor") transistors, for which the channel is formed in the or on the thin layer of
30 silicon.

Because of the extreme thinness of the thickness of said thin layer, the threshold voltage of the transistor (usually noted as V_t), which depends on this thickness, is a very sensitive to thickness variations of the thin layer.

For such applications, optimum uniformity of the thin silicon layer is therefore sought
35 so as to have minimum V_t variability from one transistor to the other.

Considering the small dimensions of these devices and their great proximity, it is necessary to measure the thickness variation between points very close to each other, for example every 0.5 μm .

This implies, during the method for making the SOI, measuring the thickness of the thin silicon layer and of the electrically insulating layer, in different points of the surface of the SOI, in a wide range of spatial wavelengths, typically comprised between 0.5 μm and 300 μm .

5 Present measurement methods are based on optical measurements, notably ellipsometry or spectral reflectometry.

In both cases, these methods imply conducting a large number of measurements by illuminating the SOI with a light flux having several optical wavelengths, so as to not only measure the thickness of the silicon layer but also that of the buried oxide layer.

10 However, with these techniques, it is not possible to conduct measurements with spatial wavelengths as small as 0.5 μm .

Thus, an ellipsometer allows measurements to be conducted with spatial wavelengths greater than or equal to about 40 μm .

15 On the other hand, these measurements take a long time and are a penalty in the manufacturing cycle of the SOIs.

Moreover, measurements conducted by ellipsometry or reflectometry with a single optical wavelength would not give the possibility of determining with sufficient accuracy the thickness of the silicon layer, since, for a given optical wavelength, the measured thickness of the silicon layer depends on the thickness and on the nature of the underlying buried oxide layer.

20 Document WO 2014/072109 discloses a method for measuring thickness variations in a layer of a multilayer semiconductor structure (typically an SOI, in particular an FDSOI) intended to conduct measurements in particular in the range of spatial wavelengths comprised between 0.5 and 40 μm , which is not accessible with the above-described measurement methods.

This method comprises:

- acquiring, with at least an image acquisition system, at least one image of the surface of said structure, said image being obtained by reflecting a quasi-monochromatic light flux on the surface of said structure,
- 30 - processing said at least one acquired image so as to determine, from intensity variations of the light reflected by said surface, the variations of the thickness of said layer to be measured (typically, the thickness of the superficial silicon layer),

wherein the wavelength of said quasi-monochromatic light flux is selected so as to correspond to a minimum of the sensitivity of the reflectivity of the multilayer structure with respect to a layer of the structure other than the layer for which thickness variations have to be measured.

35

The sensitivity of the reflectivity with respect to a layer of the structure, which is homogeneous to the reciprocal of a length, is defined as being the ratio between:

- the difference between the reflectivities of two multilayer structures for which the considered layer has a given thickness difference from one structure to the other (for example 0.1 nm) and
- said given thickness difference, the thicknesses of the other layers as for them being identical in both structures.

FIG. 1 illustrates the curves of the sensitivity of the reflectivity (noted as SR, expressed in $\text{\AA}^{-1}$) of an FDSOI structure versus the wavelength λ with non-polarized light calculated relatively to the silicon layer (curves Si1 and Si2) and relatively to the buried oxide layer (curves BOX1 and BOX2), for a thickness variation of the considered layer of 0.1 nm.

In this structure, the silicon layer has a thickness of about 12 nm and the buried oxide layer has a thickness of about 25 nm.

The rectangle in dotted lines appearing on this graph indicates an optimum range of wavelengths for illuminating the structure and for acquiring an image of the reflected light in order to determine the thickness variations in the silicon layer.

Indeed, in this interval, the sensitivity of the reflectivity with respect to the buried oxide layer is, in absolute value, a minimum (curves BOX1 and BOX2 passing through 0).

This means that the reflectivity variation measured with a quasi-monochromatic light flux in this range of wavelengths (being expressed, on an image of the surface, by intensity variations of the pixels) essentially depends on the thickness variations of the silicon curve to be measured.

It is therefore possible to determine, from intensity variations of the light reflected by the surface of the structure, the thickness variations of the layer to be measured.

In the illustrated example, the optimum wavelength of the light flux is comprised between about 510 and 530 nm. A quasi-monochromatic interferential filter around 515 nm, may therefore be selected for forming the incident light flux.

In order to build a map of the thickness variations of the layer, a calibration curve is first computed to establish a relationship between the grey levels of the acquired image and a local thickness of the layer to be measured.

An example of such a calibration curve is shown in FIG. 2.

The computation of such a curve requires:

- on the one hand, measuring (e.g. by ellipsometry) the thickness of the silicon layer of several FDSOI structures corresponding to given product specifications (such specifications typically comprise a target thickness of the silicon layer – e.g. 12 nm – and a target thickness of the buried oxide layer – e.g. 25 nm);

- on the other hand, acquiring images of zones of the surface of each of said structures with a quasi-monochromatic incident flux having a given wavelength, and measuring the intensity of the pixels of said images.

It is thus possible to associate a determined thickness of the silicon layer with a
5 corresponding grey level in the image.

The measurement points allow constructing a theoretical curve (c) that comprises, in abscissa, the grey levels GS (arbitrary unit), and in ordinate, the thickness t of the superficial silicon layer (angstroms).

This calibration curve is then used during inspection of each structure corresponding
10 to the product specifications for which said curve has been computed.

During inspection of a structure, a zone of the surface of the structure is illuminated with the above-mentioned quasi-monochromatic light flux and an image of the light flux reflected by said zone is acquired.

The intensity of the pixels of said image is measured and, thanks to the above-
15 mentioned calibration curve, the thickness of the silicon layer in this zone is deduced.

However, for an FDSOI structure corresponding to a product with given specifications, the thickness of the buried oxide layer is also likely to vary within the same structure and/or from one structure to another one.

As shown in FIG. 1, a thickness variation of the buried oxide layer corresponds to a
20 different wavelength to be applied, which in turn induces a variation of the reflectivity of the silicon layer and thus uncertainty on the real thickness of the thickness of said layer.

Such uncertainty is considered to range from 10 to 15% for an FDSOI structure corresponding to given product specifications.

The users of FDSOI structures now have increasingly stringent requirements
25 regarding the accuracy of the mapping of the thickness variations and it thus becomes necessary to reduce the measurement error so as to reach an error of 1% or less.

To improve the situation, one possibility would be to determine, for each measurement zone, a specific wavelength corresponding to the minimum of the sensitivity of the reflectivity for the respective thickness of the buried oxide layer, and to use a quasi-
30 monochromatic light flux having said specific wavelength to illuminate the structure in this zone.

However, such a solution is not practical on an industrial scale since it would require a high number of filters to obtain the quasi-monochromatic light flux with the desired wavelength.

BRIEF DESCRIPTION OF THE INVENTION

Embodiments of the invention seek to provide a method for measuring thickness variations in a layer of a multi-layer semiconductor structure, which allows reducing the measurement error while being compatible with an industrial implementation, in particular allowing using a quasi-monochromatic light flux having the same wavelength for all structures corresponding to same product specifications.

An aspect of the invention provides a method for measuring thickness variations in a first layer of a multilayer semiconductor structure, comprising:

- acquiring, with an image acquisition system, an image of at least one zone of the surface of said structure, said image being obtained by reflecting a quasi-monochromatic light flux on said zone of the surface of said structure,

- processing said acquired image so as to determine, from intensity variations of the light reflected by said zone of the surface, a map of the thickness variations of said first layer, said treatment comprising comparing the intensity of each pixel of the image with a predetermined calibration curve defining a relationship between the intensity of a pixel of the acquired image and a local thickness of the first layer, said calibration curve being determined for a given thickness of a second layer of the structure different from the first layer,

wherein the wavelength of said quasi-monochromatic light flux is selected so as to correspond to a minimum of the sensitivity of the reflectivity with respect to said second layer,

said method being characterized in that it further comprises:

- measuring, in particular by ellipsometry, the thickness of the second layer in said at least one zone of the surface of the structure,

- if said measured thickness is different from the thickness of the second layer considered in the calibration curve, applying a correction curve to the map of the thickness variations, wherein said correction curve defines, for said measured thickness of the second layer, a relationship between a thickness of the first layer and a correction factor to apply to the map of the thickness variations of the first layer, so as to determine a corrected map of thickness variations of the first layer.

The sensitivity of the reflectivity with respect to a layer of the structure, which is homogeneous to the reciprocal of a length, is defined as being the ratio between:

- the difference between the reflectivities of two multilayer structures for which the considered layer has a given thickness difference from one structure to the other (for example 0.1 nm) and

- said given thickness difference,

the thicknesses of the other layers as for them being identical in both structures.

In other words, both structures targeted above consist of the same layers, said layers having the same thickness in both structures except for the layer for which the sensitivity of the reflectivity is to be measured and to which is assigned a thickness which differs from one structure to the other.

5 This sensitivity of the reflectivity depends on the wavelength of the light flux used for the measurement.

For the application of the invention, the absolute value of said sensitivity is of interest, the minimum sought sensitivity relatively to a layer other than the layer to be measured being zero or close to 0.

10 By a "multilayer structure", is meant a structure comprising at least two layers which are transparent at the wavelength of the quasi-monochromatic measurement flux.

By "quasi-monochromatic" is meant a light flux for which the spectrum extends in a range of wavelengths which may extend up to ± 20 nm relatively to a rated wavelength. When the wavelength of said quasi-monochromatic flux is referred to, reference is made
15 to the rated wavelength. Naturally, a monochromatic light flux, i.e. having a single wavelength, may also be used for applying the invention.

According to an embodiment, the image acquisition system is an optical microscope.

According to another embodiment, the image acquisition system is a digital camera configured to acquire an image wherein the size of a pixel is less than or equal to
20 0.25 μm .

Advantageously, the numerical aperture of the image acquisition system is greater than or equal to 0.8.

The incidence of the light flux on the surface of the structure is preferably normal to said surface.

25 According to an embodiment, the multilayer structure is a structure consisting of two layers transparent to the wavelength of the quasi-monochromatic light flux on a supporting substrate.

In particular, the multilayer structure may be a semiconductor-on-insulator structure comprising a supporting substrate, an electrically insulating layer and a semiconducting
30 layer, and the layer for which the thickness variations are measured is said semiconducting layer.

According to an advantageous embodiment, said structure is an FDSOI structure, the layer for which the thickness variations are measured being a silicon layer having a thickness of less than or equal to 50 nm, preferably less than or equal to 12 nm.

35 According to an embodiment, images of a plurality of zones of the surface of the structure are acquired and the quasi-monochromatic light flux has the same wavelength for each zone.

The method may also be implemented on a plurality of semiconductor structures, wherein the quasi-monochromatic light flux has the same wavelength for each structure.

Another aspect of the invention provides a measurement system allowing the implementation of the method described above.

5 Said system comprises:

- a device for illuminating the structure, adapted for emitting a quasi-monochromatic light flux towards the surface of said structure, wherein the wavelength of said light flux corresponds to a minimum of the sensitivity of the reflectivity with respect to a second layer of the structure different from the first layer, said sensitivity of the reflectivity with respect to a layer being equal to the ratio between:
 - (i) the difference between the reflectivities of two multilayer structures for which the considered layer has a given thickness difference, and
 - (ii) said given thickness difference,
 the thicknesses of the other layers being identical in both multilayer structures,
- 15 - an image acquisition system laid out so as to acquire at least one image of a zone of the surface of the structure by reflection of said quasi-monochromatic light flux,
- a device for measuring, in particular by ellipsometry, the thickness of the second layer to be measured in said at least one zone of the surface of the structure,
- a memory wherein a calibration curve defining a relationship between intensity of a pixel in the acquired image and a local thickness of the first layer is stored, said calibration curve being determined for a given thickness of the second layer,
- 20 - a processing system configured for, from said at least one acquired image, determining from the intensity variations of the light reflected by said surface, a map of the variations of the thickness of the first layer by comparing the intensity of each pixel of the acquired image with the calibration curve,
- 25 - a computation system configured to receive thickness measurement data from the measuring device and for, if the measured thickness is different from the thickness of the second layer considered in the calibration curve, applying a correction curve to the map of the thickness variations, wherein said correction curve defines, for said measured thickness of the second layer, a relationship between a thickness of the first layer and a correction factor to apply to the map of the thickness variations of the first layer, so as to determine a corrected map of thickness variations of the first layer.
- 30

BRIEF DESCRIPTION OF THE DRAWINGS

Other features and advantages of the invention will become apparent from the detailed description which follows, with reference to the appended drawings wherein:

- FIG. 1 shows the curves of the sensitivity of the reflectivity of an FDSOI structure, versus the wavelength, relatively to the thin silicon layer (curves Si1 and Si2) and relatively to the buried oxide layer (curves BOX1 and BOX2),
- FIG. 2 shows a calibration curve of an optical microscope used in the method described in document WO 2014/072109,
- FIG. 3 is a sectional view of a multilayer structure, for which an attempt is made for measuring the thickness variations of one of the layers,
- FIG. 4 shows a correction curve to be applied to the thickness map in accordance with the invention.

DETAILED DESCRIPTION OF THE INVENTION

FIG. 3 illustrates a multilayer structure for which the thickness variations of one of the layers are to be measured.

The structure successively comprises from its surface S to its base a first layer 1, a second layer 2 and a supporting substrate 3.

The first and second layer are in selected materials so as to be transparent at the measurement wavelength, i.e. the incident light flux is able to cross each of said layers and be partly reflected on the surface of the underlying layer.

Generally, the semiconducting materials and the dielectric materials have this property, provided that they have a sufficiently thin thickness, i.e. typically less than 500 nm.

A very fine metal layer (i.e. having a thickness of less than 200 nm) may also be applied in such a multilayer structure.

The person skilled in the art is able to determine, for materials customarily used in the field of electronics, the maximum thicknesses for which they are transparent to a given wavelength.

The supporting substrate on the other hand plays a role of a mechanical support and is generally too thick (typically a few hundred μm) so as to be transparent to the measurement wavelength.

Said supporting substrate may be bulk or else consists of a plurality of layers of different materials.

In the example illustrated in FIG. 3, the structure is therefore a bilayer structure, the supporting structure not being considered as a layer, the thickness variations of which may be measured.

Nevertheless, the invention is not limited to such a structure but may also apply to a structure comprising three layers transparent to the measurement wavelength, or even more.

According to an advantageous application of the invention, the structure is a
5 structure of the semiconductor-on-insulator type, in which the supporting substrate is the substrate 3, the electrically insulating layer is the buried layer 2, and the semiconductor layer is the surface layer 1.

According to an embodiment, the layer for which thickness variations are measured is the surface semiconductor layer 1.

10 In the particular case of an FDSOI structure, the layer for which the thickness variations are measured is the surface layer 1, which is a silicon layer having a thickness of less than or equal to 50 nm, preferably less than or equal to 12 nm.

The principle of the measurement, based on the reflections occurring in both layers of the multilayer structure is described in document WO 2014/072109 (see in particular
15 Fig. 2 and the corresponding description) and will thus not be repeated here.

The sensitivity of the reflectivity relatively to a layer corresponds to the partial derivative of the reflectivity curve relatively to the thickness of the considered layer, the outer layers of the structure having a fixed thickness.

For example, for a structure of the SOI type as illustrated in FIG. 3, the sensitivity of
20 the reflectivity is calculated with respect to the semiconductor layer 1 by setting the thickness of the buried oxide layer 2 and by determining the reflectivity of the structure for two different thicknesses of the semiconductor layer 1, the difference between both of these thicknesses for example being 0.1 nm.

For the same structure, the sensitivity of the reflectivity is defined relatively to the
25 buried oxide layer 2 by setting the thickness of the semiconductor layer 1 and by determining the reflectivity of the structure for two different thicknesses of the buried oxide layer 2, the difference between both of these thicknesses for example being 0.1 nm.

In the case of a stack of three layers transparent to the measurement wavelength, the person skilled in the art is able to determine on this same principle the Fresnel
30 coefficients.

Notably, in the case when the structure comprises a surface layer, the thickness variations of which are to be determined, and two underlying transparent layers, it is possible to assimilate both of these layers to a single layer having a reflectivity and sensitivity which may be calculated from those of said two layers.

35 Advantageously, the incident flux on the surface S of the structure is normal to the latter, this configuration simplifying subsequent processing of the image.

However it is possible, by way of additional processing within the competence of one skilled in the art, to make use of an image acquired by reflection of a light flux not normal to the surface of the structure.

For acquiring at least one image of a zone of the surface, various image acquisition
5 systems may be used.

Preferably, the numerical aperture of the acquisition system is of at least 0.8.

According to an embodiment of the invention, said acquisition system comprises an optical microscope having a reflection mode, i.e. allowing illumination of the multilayer structure through its surface S to be observed. The system further comprises a sensor
10 able to acquire an image of a zone of the surface as seen by the microscope.

According to another embodiment of the invention, said acquisition system comprises a digital camera and allows direct acquisition of an image of a zone of the surface of the structure on which is reflected the incident light flux.

In order that the resolution of such a device is sufficient, it is considered that the size
15 of the pixels should be less than or equal to $0.25\text{ }\mu\text{m}$. In other words, a pixel of the device should correspond to an area with a side of $0.25\text{ }\mu\text{m}$ or less on the surface of the structure.

The microscope and the camera give the possibility of obtaining spatial wavelengths up to $0.5\text{ }\mu\text{m}$, which allows sufficiently fine determination of the thickness variations on the
20 surface of the structure.

The images acquired by the acquisition system are typically black and white images having different grey levels.

The acquisition system is calibrated so as to have each grey level (intensity of each pixel) correspond with a corresponding thickness of the layer to be measured.

As explained above, from several structures corresponding to same product
25 specifications, images of the surface are acquired by reflection of the quasi-monochromatic light flux and, on these same structures, a measurement by ellipsometry of the layer is conducted, for which the thickness variations are to be measured. The zones of the structure subjected to imaging and ellipsometry are the same; in other words,
30 the size and position of the zone for which an image is acquired are the same as the zone onto which ellipsometry is carried out.

A calibration curve of the type of the one illustrated in FIG. 2 is thereby obtained, which shows the thicknesses measured by ellipsometry versus the grey levels of the acquired image. In this figure, the grey levels correspond to an arbitrary scale.

In order to build the curve (c) of FIG. 2, the thickness of the silicon layer of five
35 FDSOI structures, for which the silicon layer had a thickness comprised between 11 and 13 nm, was measured by ellipsometry. Moreover images of the surface of these structures were acquired with an incident quasi-monochromatic light flux of 540 nm and the intensity

of the pixels of these images was measured. It was thus possible to associate a determined thickness with the corresponding grey level on the image. The measurement points were then used as a basis for defining the theoretical curve (c).

Based on the calibration curve, it is possible to produce from the intensity of the different pixels of an image, a mapping of the thickness of the layer for which the thickness variations are to be measured. This is done by comparing the intensity of each pixel of the image with a predetermined calibration curve defining a relationship between the intensity of a pixel of the acquired image and a local thickness of the first layer. Thus, for each pixel of the image, a corresponding local thickness is associated.

The calibration curve is computed for a given thickness of the other layer than the layer to be measured. For example, the calibration curve shown in FIG. 2 has been computed considering that the thickness of the buried oxide layer is 25 nm.

In order to take into account possible variations in the thickness of the buried oxide layer, a correction curve corresponding to a thickness different from the thickness considered in the product specifications is computed.

An example of such a correction curve is shown in FIG. 4. This curve establishes, for a given thickness of the buried oxide layer 2 (e.g. 24 nm), a relationship between the thickness of the silicon layer 1 (abscissa, nm) and a correction factor (ordinate, no unit) to be applied to the thickness map of the silicon layer 1 to obtain the real thickness.

The correction curve is obtained as follows.

For each structure, measurement of the thickness of the silicon layer and of the buried oxide layer is carried out by ellipsometry or reflectometry. Said measurement is done in a zone that is the same (in terms of size and position) as the zone for which an image is acquired. For example, if the image of the surface acquired through a microscope is $80\ \mu\text{m} \times 80\ \mu\text{m}$, the beam of the ellipsomètre has the same size as this image and is directed to the same zone of the surface of the structure. Theoretical calculations based on transfer matrix method for optical multilayer structures (see for example C.C.Katsidis and D.I.Siapkas, "General transfer-matrix method for optical multilayer systems with coherent, partially coherent and incoherent interference", Appl. Opt. vol. 41, p.3978-3987, 2002) allow determining, for the measured thickness of the BOX layer, a relationship between the real thickness of the silicon layer and the thickness measured from the grey levels of the image. This relationship is represented in the form of the correction curve of FIG. 4.

The correction curve is applied to the map of thickness variations of the silicon layer that has been obtained using the calibration curve. The correction is done, for each point of said map, by multiplying the respective thickness by the suitable correction factor given by the correction curve. The result of this multiplication is a corrected map of thickness variations that is more accurate than the previously determined map.

When images of several zones of the surface of the structure are acquired, a correction curve is computed for each zone using the method described above.

Since ellipsometry and/or reflectometry are usually available in test rooms for SOI structures in order to carry out various measurements on the structures, the specific measurement described above is easy to implement and does not alter the efficiency of the testing process, even if carried out onto each structure for which thickness variations are sought and possibly on several zones of said structure.

The use of a specific correction curve allows using the same wavelength for generating the thickness mapping for all the structures corresponding to same product specifications, since it allows taking into account the thickness variations of the other layer.

The measurement system for this purpose comprises a processing system configured so as to determine on an acquired image, from intensity variations of the light reflected by the surface, the variations of the thickness of said layer to be measured.

The processing system may thus comprise a computer provided with a microprocessor and a memory in which is recorded a program which may be executed by the microprocessor and containing instructions for applying the aforementioned computation steps.

The processing system may further comprise a screen for displaying a map of the thickness variations of the layer to be measured.

Moreover, the measurement system further comprises an illumination device capable of generating a quasi-monochromatic light flux with the wavelength considered to be optimal for the corresponding product specifications, i.e. a wavelength corresponding to a minimum of the sensitivity of the reflectivity with respect to a layer of the structure other than the layer for which the thickness variations have to be measured.

Advantageously, the processing system described above is itself configured in order to simulate the optical response of a multilayer structure and to automatically select the wavelength of the adequate quasi-monochromatic light flux. For this purpose, the measurement system further comprises an ellipsometer or reflectometer, which is used for conventionally measuring the thickness of each of the layers of the structure from the reflectivity of said layers.

Alternatively or additionally, the measurement system comprises a graphic interface on which a user inputs the characteristics of the relevant structure (material and thickness of the different layers). By knowing these thicknesses, the processing system applies a simulation of the sensitivity of the reflectivity relatively to each of the layers of the structure depending on the wavelength of an illumination light flux and infers therefrom a range of wavelengths in which the sensitivity of the reflectivity with respect to the layer(s) of the

structure other than the layer for which measurements of the thickness variations are to be obtained, is in absolute value, a minimum.

Finally, it is obvious that the examples which have just been given are only particular and by no means limiting illustrations as to the fields of application of the invention.

- 5 Notably, if the invention advantageously applies to the measurement of thickness variations of a structure of the FDSOI type, it is not limited to such a structure but to any multilayer structure comprising at least two layers transparent to the quasi-monochromatic light flux used for the measurement.

REFERENCES

- 10 WO 2014/07210

C.C.Katsidis and D.I.Siapkas, "General transfer-matrix method for optical multilayer systems with coherent, partially coherent and incoherent interference", Appl. Opt. vol. 41, p.3978-3987, 2002

CLAIMS

1. A method for measuring thickness variations in a first layer of a multilayer semiconductor structure, comprising:

- 5 - acquiring, with an image acquisition system, an image of at least one zone of the surface of said structure, said image being obtained by reflecting a quasi-monochromatic light flux on said zone of the surface of said structure,
- processing said acquired image so as to determine, from intensity variations of the light reflected by said zone of the surface, a map of the thickness variations of said first layer, said treatment comprising comparing the intensity of each pixel of the image with a predetermined calibration curve defining a relationship between the intensity of a pixel of the acquired image and a local thickness of the first layer, said calibration curve being determined for a given thickness of a second layer of the structure different from the first layer,

15 wherein the wavelength of said quasi-monochromatic light flux is selected so as to correspond to a minimum of the sensitivity of the reflectivity with respect to said second layer, said sensitivity of the reflectivity with respect to a layer being equal to the ratio between:

- 20 (i) the difference between the reflectivities of two multilayer structures for which the considered layer has a given thickness difference and
- (ii) said given thickness difference,

 the thicknesses of the other layers being identical in both multilayer structures, said method being characterized in that it further comprises:

- 25 - measuring, in particular by ellipsometry, the thickness of the second layer in said at least one zone of the surface of the structure,

- if said measured thickness is different from the thickness of the second layer considered in the calibration curve, applying a correction curve to the map of the thickness variations, wherein said correction curve defines, for said measured thickness of the second layer, a relationship between a thickness of the first layer and a correction factor to apply to the map of the thickness variations of the first layer, so as to determine a corrected map of thickness variations of the first layer.
- 30

2. The method according to claim 1, characterized in that said image acquisition system is an optical microscope.

35

3. The method according to claim 1, characterized in that said image acquisition system is a digital camera configured to acquire an image wherein the size of a pixel is less than or equal to 0.25 μm .

4. The method according to one of claims 1 to 3, characterized in that the numerical aperture of the image acquisition system is greater than or equal to 0.8.

5 5. The method according to one of claims 1 to 4, characterized in that the incidence of the light flux on the surface of the structure is normal to said surface.

6. The method according to one of claims 1 to 5, characterized in that the multilayer structure is a structure consisting of two layers transparent to the wavelength of
10 the quasi-monochromatic light flux on a supporting substrate.

7. The method according to one of claims 1 to 6, characterized in that said multilayer structure is a semiconductor-on-insulator structure comprising a supporting substrate, an electrically insulating layer and a semiconducting layer and in that the layer
15 for which the thickness variations are measured is said semiconducting layer.

8. The method according to claim 7, characterized in that said structure is an FDSOI structure, the layer for which the thickness variations are measured being a silicon layer having a thickness of less than or equal to 50 nm, preferably less than or equal to
20 12 nm.

9. The method according to one of claims 1 to 8, characterized in that images of a plurality of zones of the surface of the structure are acquired and in that the quasi-monochromatic light flux has the same wavelength for each zone.
25

10. The method according to one of claims 1 to 9, implemented on a plurality of semiconductor structures, characterized in that the quasi-monochromatic light flux has the same wavelength for each structure.

30 11. A system for measuring thickness variations in a first layer of a multilayer semiconductor structure, comprising:

- a device for illuminating the structure, adapted for emitting a quasi-monochromatic light flux towards the surface of said structure, wherein the wavelength of said light flux corresponds to a minimum of the sensitivity of the reflectivity with respect to a second
35 layer of the structure different from the first layer, said sensitivity of the reflectivity with respect to a layer being equal to the ratio between:

(i) the difference between the reflectivities of two multilayer structures for which the considered layer has a given thickness difference, and

(ii) said given thickness difference,

the thicknesses of the other layers being identical in both multilayer structures,

- an image acquisition system laid out so as to acquire at least one image of a zone of the surface of the structure by reflection of said quasi-monochromatic light flux,
- 5 - a device for measuring, in particular by ellipsometry, the thickness of the second layer to be measured in said at least one zone of the surface of the structure,
- a memory wherein a calibration curve defining a relationship between intensity of a pixel in the acquired image and a local thickness of the first layer is stored, said calibration curve being determined for a given thickness of the second layer,
- 10 - a processing system configured for, from said at least one acquired image, determining from the intensity variations of the light reflected by said surface, a map of the variations of the thickness of the first layer by comparing the intensity of each pixel of the acquired image with the calibration curve,
- a computation system configured to receive thickness measurement data from the
- 15 measuring device and for, if the measured thickness is different from the thickness of the second layer considered in the calibration curve, applying a correction curve to the map of the thickness variations, wherein said correction curve defines, for said measured thickness of the second layer, a relationship between a thickness of the first layer and a correction factor to apply to the map of the thickness variations of the first layer, so as to
- 20 determine a corrected map of thickness variations of the first layer.