

Title: FUNCTIONALIZED HIGH VINYL TERMINATED PROPYLENE BASED OLIGOMERS

Inventor(s): Patrick Brant and Donna J. Crowther

5 **PRIORITY CLAIM**

[0001] This application is a continuation in part of USSN 12/143,663 filed June 20, 2008, which is incorporated by reference herein.

FIELD OF THE INVENTION

10 [0002] This invention relates to olefin oligomerization, particularly propylene-ethylene oligomerization, to produce vinyl terminated oligomers.

BACKGROUND OF THE INVENTION

[0003] Alpha-olefins, especially those containing about 6 to about 20 carbon atoms, have been used as intermediates in the manufacture of detergents or other types of commercial products. Such alpha-olefins have also been used as monomers, especially in linear low density polyethylene. 15 Commercially produced alpha-olefins are typically made by oligomerizing ethylene. Longer chain alpha-olefins, such as vinyl-terminated polyethylenes are also known and can be useful as building blocks following functionalization or as macromonomers.

[0004] Allyl terminated low molecular weight solids and liquids of ethylene or propylene have also been produced, typically for use as branches in polymerization reactions. See, for example, 20 Rulhoff, Sascha and Kaminsky, (*"Synthesis and Characterization of Defined Branched Poly(propylene)s with Different Microstructures by Copolymerization of Propylene and Linear Ethylene Oligomers (C_n=26-28) with Metallocenes/MAO Catalysts,"* Macromolecules 16 2006, 1450-1460), and Kaneyoshi, Hiromu et al. (*"Synthesis of Block and Graft Copolymers with Linear Polyethylene Segments by Combination of Degenerative Transfer Coordination Polymerization and Atom Transfer Radical Polymerization,"* Macromolecules 38 2005, 5425-5435). 25

[0005] Further, US 4,814,540 discloses bis(pentamethyl cyclopentadienyl) hafnium dichloride, bis(pentamethyl cyclopentadienyl) zirconium dichloride and bis(tetramethyl n-butyl cyclopentadienyl) hafnium dichloride with methylalumoxane in toluene or hexane with or without hydrogen to make allylic vinyl terminated propylene homo-oligomers having a low degree of 30 polymerization of 2-10. These oligomers do not have high Mn's and have at least 93% allylic vinyl unsaturation. Likewise, these oligomers lack comonomer and are produced at low productivities with a large excess of alumoxane (molar ratio ≥ 600 Al/M ; M= Zr, Hf). Additionally, no less than 60 wt% solvent (solvent + propylene basis) is present in all of the examples.

[0006] Teuben, et al. (J. Mol. Catal. 62 1990, 277-87) used [Cp*₂MMe(THT)]+[BPh₄], M= Zr and Hf) to make propylene oligomers. For M = Zr a broad product distribution with oligomers up to 35

C₂₄ (Mn 336) was obtained at room temperature. Whereas for M = Hf only the dimer 4-methyl-1-pentene and the trimer 4,6-dimethyl-1-heptene were formed. The dominant termination mechanism appeared to be beta-methyl transfer from the growing chain back to the metal center, as was demonstrated by deuterium labeling studies.

5 [0007] X. Yang, et al. (Angew. Chem. Intl Edn. Engl. 31 1992 1375) discloses amorphous, low molecular weight polypropylene made at low temperatures where the reactions showed low activity and product having 90% allylic vinyls, relative to all unsaturations, by ¹H NMR. Thereafter, Resconi, et al. (J. Am. Chem. Soc. 114 1992, 1025-1032), disclose the use of bis(pentamethylcyclopentadienyl) zirconium and bis(pentamethylcyclopentadienyl)hafnium centers to polymerize propylene and
10 obtained beta-methyl termination resulting in oligomers and low molecular weight polymers with "mainly allyl- and iso-butyl-terminated" chains. As is the case in US 4,814,540, the oligomers produced do not have at least 93% allyl chain ends, an Mn of about 500 to about 20,000 g/mol (as measured by ¹H NMR), and the catalyst has low productivity (1-12,620 g/mmol metallocene.hr;>3000 wppm Al in products).

15 [0008] Similarly, Small and Brookhart, (*Macromol.* 32 1999, 2322) discloses the use of a pyridylbis amido iron catalyst in a low temperature polymerization to produce low molecular weight amorphous propylene materials apparently having predominant or exclusive 2,1 chain growth, chain termination via beta-hydride elimination, and high amounts of vinyl end groups. Dekmejian et al. (*Macromol.* 33, 2000, 8541-8548) discloses materials with up to about 81 percent vinyl termination
20 made using dimethylsilyl bis(2-methyl, 4-phenyl-indenyl) hafnium dichloride and methylalumoxane in toluene at about 120°C. The materials have a number average molecular weight of about 12,300 (measured with ¹H NMR) and a melting point of about 143°C.

[0009] Moscardi, et al. (*Organomet.* 20, 2001, 1918) discloses the use of *rac*-dimethylsilylmethylene bis(3-*t*-butyl indenyl) zirconium dichloride with methylalumoxane in batch
25 polymerizations of propylene to produce materials where "...allyl end group always prevails over any other end groups, at any [propene]." In these reactions, morphology control was limited and approximately 60% of the chain ends are allylic.

[0010] Coates, et al. (*Macromol* 2005 38, 6259) discloses preparation of low molecular weight syndiotactic polypropylene ([rrrr] = 0.46-0.93) with about 100% allyl end groups using
30 bis(phenoxyimine)titanium dichloride ((PHI)₂TiCl₂) activated with modified methyl alumoxane (MMAO; Al/Ti molar ratio = 200) in batch polymerizations run between -20 and +20°C for four hours. For these polymerizations, propylene was dissolved in toluene to create a 1.65 M toluene solution. Catalyst productivity was very low (0.95 to 1.14 g/mmol Ti/hr).

[0011] JP-2005-336092-A2 discloses the manufacture of vinyl-terminated propylene polymers
35 using materials such as H₂SO₄ treated montmorillonite, triethylaluminum, triisopropyl aluminum,

where the liquid propylene is fed into a catalyst slurry in toluene. This process produces substantially isotactic macromonomers not having a significant amount of amorphous material.

[0012] Rose, et al (Macromolecules 2008, 41, 559-567) discloses poly(ethylene-co-propylene) macromonomers not having significant amounts of iso-butyl chain ends. Those were made with bis(phenoxyimine) titanium dichloride ((PHI)₂TiCl₂) activated with modified methylalumoxane (MMAO; Al/Ti molar ratio range 150 to 292) in semi-batch polymerizations (30 psi propylene added to toluene at 0°C for 30 min, followed by ethylene gas flow at 32 psi of over-pressure at about 0°C for polymerization times of 2.3 to 4 hours to produce E-P copolymer having an Mn of about 4800 to 23,300. In four reported copolymerizations, allylic chain ends decreased with increasing ethylene incorporation roughly according to the equation:

$$\% \text{ allylic chain ends (of total unsaturations)} = -0.95(\text{mol\% ethylene incorporated}) + 100.$$

For example, 65% allyl (compared to total unsaturation) was reported for E-P copolymer containing 29 mol% ethylene. This is the highest allyl population achieved. For 64 mol% incorporated ethylene, only 42% of the unsaturations are allylic. Productivity of these polymerizations ranged from 0.78 x 10² g/ mmol Ti/hr to 4.62 x 10² g/ mmol Ti/hr.

[0013] Prior to this work, Zhu et al. reported only low (~38%) vinyl terminated ethylene-propylene copolymer made with the constrained geometry metallocene catalyst [C₅Me₄(SiMe₂N-tert-butyl)TiMe₂ activated with B(C₆F₅)₃ and MMAO (*Macromol* **2002** 35, 10062-10070 and *Macromol Rap. Commun.* **2003** 24 311-315).

[0014] Janiak and Blank summarize a variety of work related to oligomerization of olefins (*Macromol. Symp.* 236 **2006**, 14-22).

[0015] Rodriguez, et al in US 2005/0159299 discloses polymerization and oligomerization with catalyst compounds on a specifically treated support and exemplifies polymerization with a catalyst compound of dimethylsilyl bis(2-methyl, 4-phenyl indenyl) zirconium dimethyl on a capped support. Such catalysts however typically produce about 50% vinyl and about 50% vinylidene terminal unsaturations (of the termini that are unsaturated).

[0016] Example 18 of WO 95/27717 discloses using a dimethylsilanediyl bis(octahydrofluorenyl) zirconium dichloride compound with methylalumoxane at 50°C to make homo-propylene oligomer reported to have 95% allyl-termination, an "oligomerization degree" of 45 (which likely equates to an Mn of about 1890), and an estimated Al content of 90,000 ppm. The activities also appear low.

[0017] In all the prior art no catalysts are shown to produce high allylic chain unsaturations in high yields, a wide range of molecular weight, and with high productivity for propylene-based polymerizations, especially propylene-ethylene copolymerizations. Thus, there is still a need for propylene based macromonomers that have allyl termination present in high amounts (90% or more),

with control over a wide range of molecular weights that can be made at commercial temperatures (e.g. 25°C and above) and commercial rates (5,000 g/mmol/hr productivity or more). Alternately, there is a need for propylene ethylene oligomers having structural robustness (where addition of ethylene raises viscosity and the solubility parameter – relative to propylene - and provides for potential crystallizable ethylene runs, while lowering glass transition temperature). Further, there is a need for propylene based reactive materials having vinyl termination which can be functionalized (and or derivatized) and used in additive applications.

SUMMARY OF THE INVENTION

[0018] This invention relates to a functionalized co-oligomer comprising the reaction product of 1) a heteroatom containing group, and 2) a co-oligomer having an Mn of 300 to 30,000 g/mol (measured by ¹H NMR) and comprising 10 to 90 mol% propylene and 10 to 90 mol% of ethylene, wherein the oligomer has at least X% allyl chain ends (relative to total unsaturations) prior to functionalization, where: 1) $X = (-0.94(\text{mol\% ethylene incorporated}) + 100)$, when 10 to 60 mol% ethylene is present in the co-oligomer, and 2) $X = 45$, when greater than 60 and less than 70 mol% ethylene is present in the co-oligomer, and 3) $X = (1.83 * (\text{mol\% ethylene incorporated}) - 83)$, when 70 to 90 mol% ethylene is present in the co-oligomer, where the heteroatom containing group comprises where the functional group comprises one or more heteroatoms selected from the group consisting of P, O, S, N, Br, Cl, F, I and or B, and the functionalized co-oligomer has 0.75 to 1.10 functional groups per chain.

[0019] This invention further relates to a functionalized propylene oligomer, comprising the reaction product of 1) a heteroatom containing group and 2) an oligomer comprising more than 90 mol% propylene and less than 10 mol% ethylene wherein the oligomer has: at least 93% allyl chain ends, a number average molecular weight (Mn) of about 500 to about 20,000 g/mol, an isobutyl chain end to allylic vinyl group ratio of 0.8:1 to 1.35:1.0, and less than 100 ppm aluminum, where the heteroatom containing group comprises one or more heteroatoms selected from the group consisting of P, O, S, N, Br, Cl, F, I and or B, and the functionalized oligomer has 0.75 to 1.10 functional groups per chain.

[0020] This invention further relates to a functionalized propylene oligomer, comprising: the reaction product of 1) a heteroatom containing group, and 2) an oligomer comprising at least 50 mol% propylene and from 10 to 50 mol% ethylene, wherein the oligomer has: at least 90% allyl chain ends, an Mn of about 150 to about 10,000 g/mol, and an isobutyl chain end to allylic vinyl group ratio of 0.8:1 to 1.2:1.0, wherein monomers having four or more carbon atoms are present at from 0 to 3 mol%, where the heteroatom containing group comprises one or more heteroatoms selected from the group consisting of P, O, S, N, Br, Cl, F, I and or B, and the functionalized co-oligomer has 0.75 to 1.10 functional groups per chain.

[0021] This invention further relates to a functionalized propylene oligomer, comprising: the reaction product of 1) a functional group, and 2) an oligomer comprising at least 50 mol% propylene, from 0.1 to 45 mol% ethylene, and from 0.1 to 5 mol% C₄ to C₁₂ olefin, wherein the oligomer has: at least 90% allyl chain ends, an Mn of about 150 to about 10,000 g/mol, and an isobutyl chain end to allylic vinyl group ratio of 0.8:1 to 1.35:1.0, where the heteroatom containing group comprises one or more heteroatoms selected from the group consisting of P, O, S, N, Br, Cl, F, I and or B, and the functionalized co-oligomer has 0.75 to 1.10 functional groups per chain.

[0022] This invention further relates to a functionalized propylene oligomer, comprising: the reaction product of 1) a heteroatom containing group, and 2) an oligomer comprising at least 50 mol% propylene, from 0.1 to 45 wt% ethylene, and from 0.1 to 5 mol% diene, wherein the oligomer has: at least 90% allyl chain ends, an Mn of about 150 to about 10,000 g/mol, and an isobutyl chain end to allylic vinyl group ratio of 0.7:1 to 1.35:1.0, where the heteroatom containing group comprises one or more heteroatoms selected from the group consisting of P, O, S, N, Br, Cl, F, I and or B, and the functionalized co-oligomer has 0.75 to 1.10 functional groups per chain

[0023] This invention further relates to a functionalized homo-oligomer, comprising the reaction product of 1) a heteroatom containing group and 2) a homo-oligomer of propylene, wherein the oligomer has: at least 93% allyl chain ends, an Mn of about 500 to about 20,000 g/mol, an isobutyl chain end to allylic vinyl group ratio of 0.8:1 to 1.2:1.0, and less than 1400 ppm aluminum, where the heteroatom containing group comprises one or more heteroatoms selected from the group consisting of P, O, S, N, Br, Cl, F, I and or B, and the functionalized co-oligomer has 0.75 to 1.10 functional groups per chain.

[0024] This invention further relates to homogeneous processes to make such oligomers which are thereafter reacted with a heteroatom containing group to form functionalized and or derivatized oligomers.

BRIEF DESCRIPTION OF THE DRAWINGS

[0025] Figure 1 is a plot of percent allylic chain ends versus mol% ethylene for Examples 35 and 52 to 61. (The triangles are data from Macromolecules 2008, 41, 559-567. The squares represent Examples 52 to 61 and the circle represents Example 35.)

[0026] Figure 2 is a chart of the range of chemical shift assignments for the isobutyl chain ends for the E-P copolymers.

[0027] Figure 3 is a graph of %vinyl (relative to total olefin population of 100%) versus polymerization temperature (Tp) for isotactic polypropylenes made with catalyst J.

DETAILED DESCRIPTION

[0028] This invention relates to a propylene homo oligomer, comprising propylene and less than 0.5 wt% comonomer, preferably 0 wt% comonomer, wherein the oligomer has:

- i) at least 93% allyl chain ends (preferably at least 95%, preferably at least 97%, preferably at least 98%);
- ii) a number average molecular weight (Mn) of about 500 to about 20,000 g/mol, as measured by ¹H NMR (preferably 500 to 15,000, preferably 700 to 10,000, preferably 800 to 8,000 g/mol, preferably 900 to 7,000, preferably 1000 to 6,000, preferably 1000 to 5,000);
- iii) an isobutyl chain end to allylic vinyl group ratio of 0.8:1 to 1.3:1.0;
- iv) less than 1400 ppm aluminum, (preferably less than 1200 ppm, preferably less than 1000 ppm, preferably less than 500 ppm, preferably less than 100 ppm).

[0029] This invention relates to a propylene co-oligomer having an Mn of 300 to 30,000 g/mol as measured by ¹H NMR (preferably 400 to 20,000, preferably 500 to 15,000, preferably 600 to 12,000, preferably 800 to 10,000, preferably 900 to 8,000, preferably 900 to 7,000 g/mol), comprising 10 to 90 mol% propylene (preferably 15 to 85 mol%, preferably 20 to 80 mol%, preferably 30 to 75 mol%, preferably 50 to 90 mol%) and 10 to 90 mol% (preferably 85 to 15 mol%, preferably 20 to 80 mol%, preferably 25 to 70 mol%, preferably 10 to 50 mol%) of one or more alpha-olefin comonomers (preferably ethylene, butene, hexene, or octene, preferably ethylene), wherein the oligomer has at least X% allyl chain ends (relative to total unsaturations), where: 1) $X = (-0.94 (\text{mol\% ethylene incorporated}) + 100 \{ \text{alternately } 1.20 (-0.94 (\text{mol\% ethylene incorporated}) + 100), \text{alternately } 1.50 (-0.94 (\text{mol\% ethylene incorporated}) + 100) \})$, when 10 to 60 mol% ethylene is present in the co-oligomer, and 2) $X = 45 (\text{alternately } 50, \text{alternately } 60)$, when greater than 60 and less than 70 mol% ethylene is present in the co-oligomer, and 3) $X = (1.83 * (\text{mol\% ethylene incorporated}) - 83, \{ \text{alternately } 1.20 [1.83 * (\text{mol\% ethylene incorporated}) - 83], \text{alternately } 1.50 [1.83 * (\text{mol\% ethylene incorporated}) - 83] \})$, when 70 to 90 mol% ethylene is present in the co-oligomer.

[0030] Alternately X is 80% or more, preferably 85% or more, preferably 90% or more, preferably 95% or more.

[0031] In an alternate embodiment the oligomer has at least 80% isobutyl chain ends (based upon the sum of isobutyl and n-propyl saturated chain ends), preferably at least 85% isobutyl chain ends, preferably at least 90% isobutyl chain ends. Alternately, the oligomer has an isobutyl chain end to allylic vinyl group ratio of 0.8:1 to 1.35:1.0, preferably 0.9:1 to 1.20:1.0, preferably 0.9:1.0 to 1.1:1.0.

[0032] This invention relates to a propylene oligomer, comprising more than 90 mol% propylene (preferably 95 to 99 mol%, preferably 98 to 99 mol%) and less than 10 mol% ethylene (preferably 1 to 4 mol%, preferably 1 to 2 mol%), wherein the oligomer has:

at least 93% allyl chain ends (preferably at least 95%, preferably at least 97%, preferably at least 98%);

a number average molecular weight (Mn) of about 400 to about 30,000 g/mol, as measured by ¹H NMR (preferably 500 to 20,000, preferably 600 to 15,000, preferably 700 to 10,000 g/mol,

preferably 800 to 9,000, preferably 900 to 8,000, preferably 1000 to 6,000);

an isobutyl chain end to allylic vinyl group ratio of 0.8:1 to 1.35:1.0, and

less than 1400 ppm aluminum, (preferably less than 1200 ppm, preferably less than 1000 ppm, preferably less than 500 ppm, preferably less than 100 ppm).

5 [0033] This invention also relates to a propylene oligomer, comprising:

at least 50 (preferably 60 to 90, preferably 70 to 90) mol% propylene and from 10 to 50 (preferably 10 to 40, preferably 10 to 30) mol% ethylene, wherein the oligomer has:

at least 90% allyl chain ends (preferably at least 91%, preferably at least 93%, preferably at least 95%, preferably at least 98%);

10 an Mn of about 150 to about 20,000 g/mol, as measured by ¹H NMR (preferably 200 to 15,000, preferably 250 to 15,000, preferably 300 to 10,000, preferably 400 to 9,500, preferably 500 to 9,000, preferably 750 to 9,000); and

an isobutyl chain end to allylic vinyl group ratio of 0.8:1 to 1.3:1.0, wherein monomers having four or more carbon atoms are present at from 0 to 3 mol% (preferably at less than 1 mol%, preferably less than 0.5 mol%, preferably at 0 mol%).

15 [0034] This invention further relates to a propylene oligomer, comprising:

at least 50 (preferably at least 60, preferably 70 to 99.5, preferably 80 to 99, preferably 90 to 98.5) mol% propylene, from 0.1 to 45 (preferably at least 35, preferably 0.5 to 30, preferably 1 to 20, preferably 1.5 to 10) mol% ethylene, and from 0.1 to 5 (preferably 0.5 to 3, preferably 0.5 to 1) mol%

20 C₄ to C₁₂ olefin (such as butene, hexene or octene, preferably butene), wherein the oligomer has:

at least 90% allyl chain ends (preferably at least 91%, preferably at least 93%, preferably at least 95%, preferably at least 98%);

a number average molecular weight (Mn) of about 150 to about 15,000 g/mol, as measured by ¹H NMR (preferably 200 to 12,000, preferably 250 to 10,000, preferably 300 to 10,000, preferably 400 to 9500, preferably 500 to 9,000, preferably 750 to 9,000); and

an isobutyl chain end to allylic vinyl group ratio of 0.8:1 to 1.35:1.0.

[0035] This invention further relates to a propylene oligomer, comprising:

30 at least 50 (preferably at least 60, preferably 70 to 99.5, preferably 80 to 99, preferably 90 to 98.5) mol% propylene, from 0.1 to 45 (preferably at least 35, preferably 0.5 to 30, preferably 1 to 20, preferably 1.5 to 10) mol% ethylene, and from 0.1 to 5 (preferably 0.5 to 3, preferably 0.5 to 1) mol% diene (such as C₄ to C₁₂ alpha-omega dienes (such as butadiene, hexadiene, octadiene), norbornene, ethylidene norbornene, vinylnorbornene, norbornadiene, and dicyclopentadiene), wherein the oligomer has:

35 at least 90% allyl chain ends (preferably at least 91%, preferably at least 93%, preferably at least 95%, preferably at least 98%);

a number average molecular weight (Mn) of about 150 to about 20,000 g/mol, as measured by ^1H NMR (preferably 200 to 15,000, preferably 250 to 12,000, preferably 300 to 10,000, preferably 400 to 9,500, preferably 500 to 9,000, preferably 750 to 9,000); and

an isobutyl chain end to allylic vinyl group ratio of 0.7:1 to 1.35:1.0.

5 **[0036]** Any of the oligomers prepared herein preferably have less than 1400 ppm aluminum, preferably less than 1000 ppm aluminum, preferably less than 500 ppm aluminum, preferably less than 100 ppm aluminum, preferably less than 50 ppm aluminum, preferably less than 20 ppm aluminum, preferably less than 5 ppm aluminum.

10 **[0037]** This invention also relates to a homogeneous process, preferably a bulk process, to make such oligomers.


[0038] As used herein, the term "oligomer" is defined to have an Mn of from 100 to 25,000 g/mol as measured by ^1H NMR. When an oligomer is referred to as comprising an olefin, the olefin present in the oligomer is the oligomerized form of the olefin. A propylene oligomer is an oligomer having at least 50 mol% of propylene. A co-oligomer is an oligomer comprising at least two different
15 monomer units (such as propylene and ethylene). A homo-oligomer is an oligomer comprising units of the same monomer (such as propylene). As used herein, Mn is number average molecular weight (measured by ^1H NMR unless stated otherwise, as for example in Table 3A), Mw is weight average molecular weight (measured by Gel Permeation Chromatography), and Mz is z average molecular weight (measured by Gel Permeation Chromatography), wt% is weight percent, and mol% is mole
20 percent. Molecular weight distribution (MWD) is defined to be Mw (measured by Gel Permeation Chromatography) divided by Mn (measured by ^1H NMR). Unless otherwise noted, all molecular weight units (e.g., Mw, Mn, Mz) are g/mol.

[0039] "Allyl chain ends" is defined to be an oligomer having at least one terminus represented by ($\text{CH}_2\text{CH}=\text{CH}_2$ -oligomer), formula I:



allylic vinyl end group

25 where the "...." represents the oligomer chain. In a preferred embodiment the allyl chain ends is represented by the formula II:




allylic vinyl end group


The amount of allyl chain ends is determined using ^1H NMR at 120°C using deuterated tetrachloroethane as the solvent on a 500 MHz machine and in selected cases confirmed by ^{13}C NMR.
30

Resconi has reported proton and carbon assignments (neat perdeuterated tetrachloroethane used for proton spectra while a 50:50 mixture of normal and perdeuterated tetrachloroethane was used for carbon spectra; all spectra were recorded at 100°C on a Bruker AM 300 spectrometer operating at 300 MHz for proton and 75.43 MHz for carbon) for vinyl terminated propylene oligomers in J American Chemical Soc 114 1992, 1025-1032 that are useful herein.

[0040] "Isobutyl chain end" is defined to be an oligomer having at least one terminus represented by the formula:



where M represents the oligomer chain. In a preferred embodiment, the isobutyl chain end is represented by one of the following formulae:



where M represents the oligomer chain.

[0041] The percentage of isobutyl end groups is determined using ^{13}C NMR (as described in the example section) and the chemical shift assignments in Resconi et al, J Am. Chem. Soc. 1992, 114, 1025-1032 for 100% propylene oligomers and set forth in Figure 2 for E-P oligomers.

[0042] The "isobutyl chain end to allylic vinyl group ratio" is defined to be the ratio of the percentage of isobutyl chain ends to the percentage of allylic vinyl groups.

[0043] In a preferred embodiment, the propylene oligomer prior to functionalization comprises less than 3 wt% of functional groups selected from hydroxide, aryls and substituted aryls, halogens, alkoxys, carboxylates, esters, acrylates, oxygen, nitrogen, and carboxyl, preferably less than 2 wt%, more preferably less than 1 wt%, more preferably less than 0.5 wt%, more preferably less than 0.1 wt%, more preferably 0 wt%, based upon the weight of the oligomer.

[0044] The oligomer preferably has an M_n as determined by ^1H NMR of 150 to 25,000 g/mole, 200 to 20,000 g/mol, preferably 250 to 15,000 g/mol, preferably 300 to 15,000 g/mol, preferably 400 to 12,000 g/mol, preferably 750 to 10,000 g/mol. Further a desirable molecular weight range can be any combination of any upper molecular weight limit with any lower molecular weight limit described above. M_n is determined according to the methods described below in the examples section.

[0045] The oligomer preferably has a glass transition temperature (T_g) of less than 0°C or less (as determined by differential scanning calorimetry as described below), preferably -10°C or less, more preferably -20°C or less, more preferably -30°C or less, more preferably -50°C or less.

[0046] The oligomer preferably contains less than 80 weight % of C_4 olefin(s), (such as isobutylene n-butene, 2-butene, isobutylene, and butadiene), based upon the weight of the oligomer, preferably less than 10 wt%, preferably 5 wt%, preferably less than 4 wt%, preferably less than 3 wt%, preferably less than 2 wt%, preferably less than 1 wt%, preferably less than 0.5 wt%, preferably less than 0.25 wt% of C_4 olefin(s) based upon the weight of the oligomer.

[0047] Alternately, the oligomer preferably contains less than 20 weight % of C_4 or more olefin(s), (such as C_4 to C_{30} olefins, typically such as C_4 to C_{12} olefins, typically such as C_4 , C_6 , C_8 , C_{12} , olefins, etc.), based upon the weight of the oligomer, preferably less than 10 wt%, preferably 5 wt%, preferably less than 4 wt%, preferably less than 3 wt%, preferably less than 2 wt%, preferably less than 1 wt%, preferably less than 0.5 wt%, preferably less than 0.25 wt% of C_4 olefin(s) based upon the weight of the oligomer, as determined by ^{13}C NMR.

[0048] In another embodiment, the oligomer composition produced comprises at least 50 wt% (preferably at least 75 wt%, preferably at least 90 wt%, based upon the weight of the oligomer composition) olefins having at least 36 carbon atoms (preferably at least 51 carbon atoms, preferably at least 102 carbon atoms) as measured by ^1H NMR assuming one unsaturation per chain.

[0049] In another embodiment, the oligomer composition produced comprises less than 20 wt% dimer and trimer (preferably less than 10 wt%, preferably less than 5 wt%, more preferably less than 2 wt%, based upon the weight of the oligomer composition), as measured by GC.

[0050] In another embodiment, the oligomer produced here contains less than 25 ppm hafnium, preferably less than 10 ppm hafnium, preferably less than 5 ppm hafnium based on the yield of polymer produced and the mass of catalyst employed.

[0051] In another embodiment, the oligomers described herein may have a melting point (DSC first melt) of from 60 to 130°C , alternately 50 to 100°C . In another embodiment, the oligomers described herein have no detectable melting point by DSC following storage at ambient temperature (23°C) for at least 48 hours.

[0052] Melting temperature (T_m) and glass transition temperature (T_g) are measured using

Differential Scanning Calorimetry (DSC) using commercially available equipment such as a TA Instruments 2920 DSC. Typically, 6 to 10 mg of the sample, that has been stored at room temperature for at least 48 hours, is sealed in an aluminum pan and loaded into the instrument at room temperature. The sample is equilibrated at 25°C, then it is cooled at a cooling rate of 10°C/min to -80°C. The sample is held at -80°C for 5 min and then heated at a heating rate of 10°C/min to 25°C. The glass transition temperature is measured from the heating cycle. Alternatively, the sample is equilibrated at 25°C, then heated at a heating rate of 10°C/min to 150°C. The endothermic melting transition, if present, is analyzed for onset of transition and peak temperature. The melting temperatures reported are the peak melting temperatures from the first heat unless otherwise specified. For samples displaying multiple peaks, the melting point (or melting temperature) is defined to be the peak melting temperature (i.e., associated with the largest endothermic calorimetric response in that range of temperatures) from the DSC melting trace.

[0053] In another embodiment, the oligomers described herein are a liquid at 25°C.

[0054] In another embodiment, the oligomers described herein have an Mw (measured as described below) of 1,000 to about 30,000 g/mol, alternately 2000 to 25,000 g/mol, alternately 3,000 to 20,000 g/mol and/or an Mz of about 1700 to about 150,000 g/mol, alternately 800 to 100,000 g/mol.

[0055] Mw and Mz are measured by using a High Temperature Size Exclusion Chromatograph (either from Waters Corporation or Polymer Laboratories), equipped with a differential refractive index detector (DRI). Experimental details, are described in: T. Sun, P. Brant, R. R. Chance, and W. W. Graessley, *Macromolecules*, Volume 34, Number 19, 6812-6820, (2001) and references therein. Three Polymer Laboratories PLgel 10mm Mixed-B columns are used. The nominal flow rate is 0.5 cm³/min, and the nominal injection volume is 300 µL. The various transfer lines, columns and differential refractometer (the DRI detector) are contained in an oven maintained at 135°C. Solvent for the SEC experiment is prepared by dissolving 6 grams of butylated hydroxy toluene as an antioxidant in 4 liters of Aldrich reagent grade 1, 2, 4 trichlorobenzene (TCB). The TCB mixture is then filtered through a 0.7 µm glass pre-filter and subsequently through a 0.1 µm Teflon filter. The TCB is then degassed with an online degasser before entering the SEC. Polymer solutions are prepared by placing dry polymer in a glass container, adding the desired amount of TCB, then heating the mixture at 160°C with continuous agitation for about 2 hours. All quantities are measured gravimetrically. The TCB densities used to express the polymer concentration in mass/volume units are 1.463 g/ml at room temperature and 1.324 g/ml at 135°C. The injection concentration is from 1.0 to 2.0 mg/ml, with lower concentrations being used for higher molecular weight samples. Prior to running each sample the DRI detector and the injector are purged. Flow rate in the apparatus is then increased to 0.5 ml/minute, and the DRI is allowed to stabilize for 8 to 9 hours before injecting the

first sample. The concentration, c , at each point in the chromatogram is calculated from the baseline-subtracted DRI signal, I_{DRI} , using the following equation:

$$c = K_{DRI} I_{DRI} / (dn/dc)$$

where K_{DRI} is a constant determined by calibrating the DRI, and (dn/dc) is the refractive index increment for the system. The refractive index, $n = 1.500$ for TCB at 135°C and $\lambda = 690 \text{ nm}$. For purposes of this invention and the claims thereto $(dn/dc) = 0.104$ for propylene polymers and 0.1 otherwise. Units on parameters throughout this description of the SEC method are such that concentration is expressed in g/cm^3 , molecular weight is expressed in g/mole , and intrinsic viscosity is expressed in dL/g .

10 [0056] Molecular weight distribution (M_w/M_n – by GPC-DRI) is determined by the method above. In some embodiments, the oligomers of this invention have an M_w/M_n (by GPC-DRI) of 1.5 to 20 , alternately 1.7 to 10 .

Oligomerization Process

[0057] This invention also relates to a homogeneous process, preferably a bulk process, to make
15 the oligomers described herein. In a preferred embodiment, propylene and optional comonomers (such as ethylene) can be oligomerized by reacting a catalyst system (comprising metallocene compound(s), and one or more activators) with the olefins. Other additives may also be used, as desired, such as scavengers and/or hydrogen. Any conventional suspension, homogeneous bulk, solution, slurry, or high-pressure oligomerization process can be used. Such processes can be run in a
20 batch, semi-batch, or continuous mode. Such processes and modes are well known in the art. Homogeneous polymerization processes are preferred. (A homogeneous polymerization process is defined to be a process where at least $90 \text{ wt}\%$ of the product is soluble in the reaction media.) A bulk homogeneous process is particularly preferred. (A bulk process is defined to be a process where monomer concentration in all feeds to the reactor is $70 \text{ volume } \%$ or more.) Alternately no solvent or
25 diluent is present or added in the reaction medium, (except for the small amounts used as the carrier for the catalyst system or other additives, or amounts typically found with the monomer; e.g. propane in propylene).

[0058] Suitable diluents/solvents for oligomerization include non-coordinating, inert liquids. Examples include straight and branched-chain hydrocarbons such as isobutane, butane, pentane,
30 isopentane, hexanes, isohexane, heptane, octane, dodecane, and mixtures thereof; cyclic and alicyclic hydrocarbons such as cyclohexane, cycloheptane, methylcyclohexane, methylcycloheptane, and mixtures thereof such as can be found commercially (Isopars); perhalogenated hydrocarbons such as perfluorinated C_{4-10} alkanes, chlorobenzene, and aromatic and alkylsubstituted aromatic compounds such as benzene, toluene, mesitylene, and xylene. Suitable solvents also include liquid olefins which
35 may act as monomers or comonomers including ethylene, propylene, 1-butene, 1-hexene, 1-pentene,

3-methyl-1-pentene, 4-methyl-1-pentene, 1-octene, and 1-decene. Mixtures of the foregoing are also suitable.

[0059] In a preferred embodiment, the feed concentration for the oligomerization is 60 volume % solvent or less, preferably 40 volume % or less, preferably 20 volume % or less. Preferably the oligomerization is run in a bulk process.

[0060] Suitable additives to the oligomerization process can include one or more scavengers, promoters, modifiers, reducing agents, oxidizing agents, hydrogen, aluminum alkyls, or silanes.

[0061] In a preferred embodiment hydrogen is present in the oligomerization reactor at a partial pressure of 0.001 to 50 psig, preferably from 0.01 to 25 psig, more preferably 0.1 to 10 psig. It has been found that in the present systems, hydrogen can be used to provide increased activity without significantly impairing the catalyst's ability to produce allylic chain ends. Preferably the catalyst activity (calculated as g/mmolcatalyst/hr) is at least 20% higher than the same reaction without hydrogen present, preferably at least 50% higher, preferably at least 100% higher.

[0062] In an alternate embodiment, the productivity at least 4500 g/mmol/hour, preferably 5000 or more g/mmol/hour, preferably 10,000 or more g/mmol/hr, preferably 50,000 or more g/mmol/hr.


[0063] In an alternate embodiment, the productivity is at least 80,000 g/mmol/hr, preferably at least 150,000 g/mmol/hr, preferably at least 200,000 g/mmol/hr, preferably at least 250,000 g/mmol/hr, preferably at least 300,000 g/mmol/hr.


[0064] Preferred oligomerizations can be run at typical temperatures and/or pressures, such as from 25 to 150°C, preferably 40 to 120°C, preferably 45 to 80°C, and preferably from 0.35 to 10 MPa, preferably from 0.45 to 6 MPa, preferably from 0.5 to 4 MPa.

[0065] In a typical oligomerization, the residence time of the reaction is up to 60 minutes, preferably between 5 to 50 minutes, preferably 10 to 40 minutes.

Catalyst Compound

[0066] Catalyst compounds useful herein include one or more metallocene compound(s) represented by the formulae:





where

Hf is hafnium;

- 5 each X is, independently, selected from the group consisting of hydrocarbyl radicals having from 1 to 20 carbon atoms, hydrides, amides, alkoxides, sulfides, phosphides, halogens, dienes, amines, phosphines, ethers, or a combination thereof, preferably methyl, ethyl, propyl, butyl, phenyl, benzyl, chloride, bromide, iodide, (alternately two X's may form a part of a fused ring or a ring system);
- each Q is, independently carbon or a heteroatom, preferably C, N, P, S (preferably at least one Q is a
- 10 heteroatom, alternately at least two Q's are the same or different heteroatoms, alternately at least three Q's are the same or different heteroatoms, alternately at least four Q's are the same or different heteroatoms);
- each R¹ is, independently, hydrogen or a C₁ to C₈ alkyl group, preferably a C₁ to C₈ linear alkyl group, preferably methyl ethyl, propyl, butyl, pentyl, hexyl, heptyl or octyl, R¹ may the same or different as
- 15 R²;
- each R² is, independently, hydrogen or a C₁ to C₈ alkyl group, preferably a C₁ to C₈ linear alkyl group, preferably methyl ethyl, propyl, butyl, pentyl, hexyl, heptyl or octyl, provided that at least one of R¹ or R² is not hydrogen, preferably both of R¹ and R² are not hydrogen, preferably R¹ and/or R² are not branched;
- 20 each R³ is, independently, hydrogen, or a substituted or unsubstituted hydrocarbyl group having from 1 to 8 carbon atoms, preferably 1 to 6 carbon atoms, preferably a substituted or unsubstituted C₁ to C₈ linear alkyl group, preferably methyl ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, provided however that at least three R³ groups are not hydrogen (alternately four R³ groups are not hydrogen, alternately five R³ groups are not hydrogen);
- 25 {Alternately, when the catalyst compound is to be used to make the homo-oligomer then each R³ is, independently, hydrogen, or a substituted or unsubstituted hydrocarbyl group having from 1 to 8 carbon atoms, preferably 1 to 6 carbon atoms, preferably a substituted or unsubstituted C₁ to C₈ linear alkyl group, preferably methyl ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, provided however that: 1) all five R³ groups are methyl, or 2) four R³ groups are not hydrogen and at least one R³ group

is a C₂ to C₈ substituted or unsubstituted hydrocarbyl (preferably at least two, three, four or five R³ groups are a C₂ to C₈ substituted or unsubstituted hydrocarbyl));

each R⁴ is, independently, hydrogen or a substituted or unsubstituted hydrocarbyl group, a heteroatom or heteroatom containing group, preferably a substituted or unsubstituted hydrocarbyl group having
 5 from 1 to 20 carbon atoms, preferably 1 to 8 carbon atoms, preferably a substituted or unsubstituted C₁ to C₈ linear alkyl group, preferably methyl ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, substituted phenyl (such as propyl phenyl), phenyl, silyl, substituted silyl, (such as CH₂SiR', where R' is a C₁ to C₁₂ hydrocarbyl, such as methyl, ethyl, propyl, butyl, phenyl);

R⁵ is hydrogen or a C₁ to C₈ alkyl group, preferably a C₁ to C₈ linear alkyl group, preferably methyl,
 10 ethyl, propyl, butyl, pentyl, hexyl, heptyl or octyl;

R⁶ is hydrogen or a C₁ to C₈ alkyl group, preferably a C₁ to C₈ linear alkyl group, preferably methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl or octyl;

each R⁷ is, independently, hydrogen, or a C₁ to C₈ alkyl group, preferably a C₁ to C₈ linear alkyl group, preferably methyl ethyl, propyl, butyl, pentyl, hexyl, heptyl or octyl, provided however that at
 15 least seven R⁷ groups are not hydrogen, alternately at least eight R⁷ groups are not hydrogen, alternately all R⁷ groups are not hydrogen, (preferably the R⁷ groups at the 3 and 4 positions on each Cp ring of Formula IV are not hydrogen);

N is nitrogen;

T is a bridge, preferably, Si or Ge, preferably Si;

20 each R^a, is independently, hydrogen, halogen or a C₁ to C₂₀ hydrocarbyl, such as methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, phenyl, benzyl, substituted phenyl, and two R^a can form a cyclic structure including aromatic, partially saturated, or saturated cyclic or fused ring system;

and further provided that any two adjacent R groups may form a fused ring or multicenter fused ring system where the rings may be aromatic, partially saturated or saturated.

25 **[0067]** The term "substituted" means that a hydrogen group has been replaced with a hydrocarbyl group, a heteroatom or a heteroatom containing group. For example methyl cyclopentadiene (Cp) is a Cp group substituted with a methyl group and ethyl alcohol is an ethyl group substituted with an -OH group.

[0068] In an alternate embodiment, at least one R⁴ group is not hydrogen, alternately at least two
 30 R⁴ groups are not hydrogen, alternately at least three R⁴ groups are not hydrogen, alternately at least four R⁴ groups are not hydrogen, alternately all R⁴ groups are not hydrogen.

[0069] Catalyst compounds that are particularly useful in this invention include one or more of:

(1,3-Dimethylindenyl)(pentamethylcyclopentadienyl)Hafniumdimethyl,

(1,3,4,7-Tetramethylindenyl)(pentamethylcyclopentadienyl)Hafniumdimethyl,

35 (1,3-Dimethylindenyl)(tetramethylcyclopentadienyl)Hafniumdimethyl,

(1,3-Diethylindenyl)(pentamethylcyclopentadienyl)Hafniumdimethyl,
 (1,3-Dipropylindenyl)(pentamethylcyclopentadienyl)Hafniumdimethyl,
 (1-Methyl,3-propyllindenyl)(pentamethylcyclopentadienyl)Hafniumdimethyl,
 (1,3-Dimethylindenyl)(tetramethylpropylcyclopentadienyl)Hafniumdimethyl,
 5 (1,2,3-Trimethylindenyl)(pentamethylcyclopentadienyl)Hafniumdimethyl,
 (1,3-Dimethylbenzindenyl)(pentamethylcyclopentadienyl)Hafniumdimethyl,
 (2,7-Bis t-butylfluorenyl)(pentamethylcyclopentadienyl)Hafniumdimethyl,
 (9-Methylfluorenyl)(pentamethylcyclopentadienyl)Hafniumdimethyl,
 (2,7,9-Trimethylfluorenyl)(pentamethylcyclopentadienyl)Hafniumdimethyl,
 10 μ -Dihydrosilyl-bis(tetramethylcyclopentadienyl)Hafniumdimethyl,
 μ -Dimethylsilyl(tetramethylcyclopentadienyl)(3-propyltrimethylcyclopentadienyl) Hafniumdimethyl,
 and
 μ -Dicyclopropylsilyl(bis tetramethylcyclopentadienyl)Hafniumdimethyl.

[0070] In an alternate embodiment, the "dimethyl" after the transition metal in the list of catalyst
 15 compounds above is replaced with a dihalide (such as dichloride or difluoride) or a bisphenoxide,
 particularly for use with an alumoxane activator.

Activators and Activation Methods for Catalyst Compounds

[0071] The terms "cocatalyst" and "activator" are used herein interchangeably and are defined to
 be any compound which can activate any one of the catalyst compounds described above by
 20 converting the neutral catalyst compound to a catalytically active catalyst compound cation. Non-
 limiting activators, for example, include alumoxanes, aluminum alkyls, ionizing activators, which
 may be neutral or ionic, and conventional-type cocatalysts. Preferred activators typically include
 alumoxane compounds, modified alumoxane compounds, and ionizing anion precursor compounds
 that abstract one reactive, σ -bound, metal ligand making the metal complex cationic and providing a
 25 charge-balancing noncoordinating or weakly coordinating anion.

[0072] In one embodiment, alumoxane activators are utilized as an activator in the catalyst
 composition. Alumoxanes are generally oligomeric compounds containing $-Al(R^1)-O-$ sub-units,
 where R^1 is an alkyl group. Examples of alumoxanes include methylalumoxane (MAO), modified
 methylalumoxane (MMAO), ethylalumoxane and isobutylalumoxane. Alkylalumoxanes and
 30 modified alkylalumoxanes are suitable as catalyst activators, particularly when the abstractable ligand
 is an alkyl, halide, alkoxide or amide. Mixtures of different alumoxanes and modified alumoxanes
 may also be used. It may be preferable to use a visually clear methylalumoxane. A cloudy or gelled
 alumoxane can be filtered to produce a clear solution or clear alumoxane can be decanted from the
 cloudy solution. Another alumoxane is a modified methyl alumoxane (MMAO) cocatalyst type 3A

(commercially available from Akzo Chemicals, Inc. under the trade name Modified Methylalumoxane type 3A, covered under patent number US 5,041,584).

5 [0073] When the activator is an alumoxane (modified or unmodified), some embodiments select the maximum amount of activator at a 5000-fold molar excess Al/M over the catalyst precursor (per metal catalytic site). The minimum activator-to-catalyst-precursor is a 1:1 molar ratio. Alternate preferred ranges include up to 500:1, alternately up to 200:1, alternately up to 100:1 alternately from 1:1 to 50:1.

10 [0074] Aluminum alkyl or organoaluminum compounds which may be utilized as co-activators (or scavengers) include trimethylaluminum, triethylaluminum, triisobutylaluminum, tri-n-hexylaluminum, tri-n-octylaluminum and the like.

Ionizing Activators

15 [0075] It is within the scope of this invention to use an ionizing or stoichiometric activator, neutral or ionic, such as tri (n-butyl) ammonium tetrakis (pentafluorophenyl) borate, a tris perfluorophenyl boron metalloid precursor or a tris perfluoronaphthyl boron metalloid precursor, polyhalogenated heteroborane anions (WO 98/43983), boric acid (U.S. Patent No. 5,942,459) or combination thereof. It is also within the scope of this invention to use neutral or ionic activators alone or in combination with alumoxane or modified alumoxane activators. Much preferred activators are the ionic ones, not the neutral boranes.

20 [0076] Examples of neutral stoichiometric activators include tri-substituted boron, tellurium, aluminum, gallium and indium or mixtures thereof. The three substituent groups are each independently selected from alkyls, alkenyls, halogens, substituted alkyls, aryls, arylhalides, alkoxy and halides. Preferably, the three groups are independently selected from halogen, mono or multicyclic (including halosubstituted) aryls, alkyls, and alkenyl compounds and mixtures thereof, preferred are alkenyl groups having 1 to 20 carbon atoms, alkyl groups having 1 to 20 carbon atoms, 25 alkoxy groups having 1 to 20 carbon atoms and aryl groups having 3 to 20 carbon atoms (including substituted aryls). More preferably, the three groups are alkyls having 1 to 4 carbon groups, phenyl, naphthyl or mixtures thereof. Even more preferably, the three groups are halogenated, preferably fluorinated, aryl groups. Most preferably, the neutral stoichiometric activator is tris perfluorophenyl boron or tris perfluoronaphthyl boron.


30 [0077] Ionic stoichiometric activator compounds may contain an active proton, or some other cation associated with, but not coordinated to, or only loosely coordinated to, the remaining ion of the ionizing compound. Such compounds and the like are described in European publications EP-A-0 570 982, EP-A-0 520 732, EP-A-0 495 375, EP-B1-0 500 944, EP-A-0 277 003 and EP-A-0 277 004, and U.S. Patent Nos. 5,153,157, 5,198,401, 5,066,741, 5,206,197, 5,241,025, 5,384,299 and 5,502,124 35 and U.S. Patent Application Serial No. 08/285,380, filed August 3, 1994, all of which are herein fully

incorporated by reference.

[0078] Ionic catalysts can be prepared by reacting a transition metal compound with some neutral Lewis acids, such as $B(C_6F_6)_3$, which upon reaction with the hydrolyzable ligand (X) of the transition metal compound forms an anion, such as $[B(C_6F_5)_3(X)]^-$, which stabilizes the cationic transition metal species generated by the reaction. The catalysts can be, and preferably are, prepared with activator components which are ionic compounds or compositions.

[0079] Compounds useful as an activator component in the preparation of the ionic catalyst systems used in the process of this invention comprise a cation, which is preferably a Bronsted acid capable of donating a proton, and a compatible non-coordinating anion which anion is relatively large (bulky), capable of stabilizing the active catalyst species (the Group 4 cation) which is formed when the two compounds are combined and said anion will be sufficiently labile to be displaced by olefinic, diolefinic and acetylenically unsaturated substrates or other neutral Lewis bases such as ethers, amines and the like. Two classes of compatible non-coordinating anions have been disclosed in EP-A0 277,003 and EP-A0 277,004 published 1988: 1) anionic coordination complexes comprising a plurality of lipophilic radicals covalently coordinated to and shielding a central charge-bearing metal or metalloid core, and 2) anions comprising a plurality of boron atoms such as carboranes, metallocarboranes and boranes.

[0080] In a preferred embodiment, the stoichiometric activators include a cation and an anion component, and may be represented by the following formula:



wherein L is a neutral Lewis base; H is hydrogen; $(L-H)^+$ is a Bronsted acid; A^{d-} is a non-coordinating anion having the charge d-; and d is an integer from 1 to 3.

[0081] The cation component, $(L-H)_d^+$ may include Bronsted acids such as protonated Lewis bases capable of protonating a moiety, such as an alkyl or aryl, from the bulky ligand metallocene containing transition metal catalyst precursor, resulting in a cationic transition metal species.

[0082] The activating cation $(L-H)_d^+$ may be a Bronsted acid, capable of donating a proton to the transition metal catalytic precursor resulting in a transition metal cation, including ammoniums, oxoniums, phosphoniums, silyliums, and mixtures thereof, preferably ammoniums of methylamine, aniline, dimethylamine, diethylamine, N-methylaniline, diphenylamine, trimethylamine, triethylamine, N,N-dimethylaniline, methyldiphenylamine, pyridine, p-bromo N,N-dimethylaniline, p-nitro-N,N-dimethylaniline, phosphoniums from triethylphosphine, triphenylphosphine, and diphenylphosphine, oxoniums from ethers such as dimethyl ether, diethyl ether, tetrahydrofuran and dioxane, sulfoniums from thioethers, such as diethyl thioethers and tetrahydrothiophene, and mixtures thereof.

[0083] The anion component A^{d-} includes those having the formula $[M^{k+}Q_n]^{d-}$ wherein k is an

integer from 1 to 3; n is an integer from 2 to 6; $n - k = d$; M is an element selected from Group 13 of the Periodic Table of the Elements, preferably boron or aluminum, and Q is independently a hydride, bridged or unbridged dialkylamido, halide, alkoxide, aryloxy, hydrocarbyl, substituted hydrocarbyl, halocarbyl, substituted halocarbyl, and halosubstituted-hydrocarbyl radicals, said Q having up to 20 carbon atoms with the proviso that in not more than 1 occurrence is Q a halide. Preferably, each Q is a fluorinated hydrocarbyl group having 1 to 20 carbon atoms, more preferably each Q is a fluorinated aryl group, and most preferably each Q is a pentafluorophenyl group. Examples of suitable A^d also include diboron compounds as disclosed in U.S. Pat. No. 5,447,895, which is fully incorporated herein by reference.

10 **[0084]** Illustrative, but not limiting examples of boron compounds which may be used as an activating cocatalyst in the preparation of the improved catalysts of this invention are tri-substituted ammonium salts such as:

trimethylammonium tetraphenylborate, triethylammonium tetraphenylborate, tripropylammonium tetraphenylborate, tri(n-butyl)ammonium tetraphenylborate, tri(t-butyl)ammonium tetraphenylborate, N,N-dimethylanilinium tetraphenylborate, N,N-diethylanilinium tetraphenylborate, N,N-dimethyl-(2,4,6-trimethylanilinium) tetraphenylborate, tropillium tetraphenylborate, triphenylcarbenium tetraphenylborate, triphenylphosphonium tetraphenylborate triethylsilylium tetraphenylborate, benzene(diazonium)tetraphenylborate, trimethylammonium tetrakis(pentafluorophenyl)borate, triethylammonium tetrakis(pentafluorophenyl)borate, tripropylammonium tetrakis(pentafluorophenyl)borate, tri(n-butyl)ammonium tetrakis(pentafluorophenyl)borate, tri(sec-butyl)ammonium tetrakis(pentafluorophenyl)borate, N,N-dimethylanilinium tetrakis(pentafluorophenyl)borate, N,N-diethylanilinium tetrakis(pentafluorophenyl)borate, N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis(pentafluorophenyl)borate, tropillium tetrakis(pentafluorophenyl)borate, triphenylcarbenium tetrakis(pentafluorophenyl)borate, triphenylphosphonium tetrakis(pentafluorophenyl)borate, triethylsilylium tetrakis(pentafluorophenyl)borate, benzene(diazonium) tetrakis(pentafluorophenyl)borate, trimethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate, triethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate, tripropylammonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate, tri(n-butyl)ammonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate, dimethyl(t-butyl)ammonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate, N,N-dimethylanilinium tetrakis-(2,3,4,6-tetrafluorophenyl)borate, N,N-diethylanilinium tetrakis-(2,3,4,6-tetrafluorophenyl)borate, N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis-(2,3,4,6-tetrafluorophenyl)borate, tropillium tetrakis-(2,3,4,6-tetrafluorophenyl)borate, triphenylcarbenium tetrakis-(2,3,4,6-tetrafluorophenyl)borate, triphenylphosphonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate, triethylsilylium tetrakis-(2,3,4,6-tetrafluorophenyl)borate, benzene(diazonium) tetrakis-(2,3,4,6-tetrafluorophenyl)borate,

trimethylammonium tetrakis(perfluoronaphthyl)borate, triethylammonium
 tetrakis(perfluoronaphthyl)borate, tripropylammonium tetrakis(perfluoronaphthyl)borate, tri(n-
 butyl)ammonium tetrakis(perfluoronaphthyl)borate, tri(t-butyl)ammonium
 tetrakis(perfluoronaphthyl)borate, N,N-dimethylanilinium tetrakis(perfluoronaphthyl)borate, N,N-
 5 diethylanilinium tetrakis(perfluoronaphthyl)borate, N,N-dimethyl-(2,4,6-trimethylanilinium)
 tetrakis(perfluoronaphthyl)borate, tropillium tetrakis(perfluoronaphthyl)borate, triphenylcarbenium
 tetrakis(perfluoronaphthyl)borate, triphenylphosphonium tetrakis(perfluoronaphthyl)borate,
 triethylsilylium tetrakis(perfluoronaphthyl)borate, benzene(diazonium)
 tetrakis(perfluoronaphthyl)borate, trimethylammonium tetrakis(perfluorobiphenyl)borate,
 10 triethylammonium tetrakis(perfluorobiphenyl)borate, tripropylammonium
 tetrakis(perfluorobiphenyl)borate, tri(n-butyl)ammonium tetrakis(perfluorobiphenyl)borate, tri(t-
 butyl)ammonium tetrakis(perfluorobiphenyl)borate, N,N-dimethylanilinium
 tetrakis(perfluorobiphenyl)borate, N,N-diethylanilinium tetrakis(perfluorobiphenyl)borate, N,N-
 dimethyl-(2,4,6-trimethylanilinium) tetrakis(perfluorobiphenyl)borate, tropillium
 15 tetrakis(perfluorobiphenyl)borate, triphenylcarbenium tetrakis(perfluorobiphenyl)borate,
 triphenylphosphonium tetrakis(perfluorobiphenyl)borate, triethylsilylium
 tetrakis(perfluorobiphenyl)borate, benzene(diazonium) tetrakis(perfluorobiphenyl)borate,
 trimethylammonium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate, triethylammonium tetrakis(3,5-
 bis(trifluoromethyl)phenyl)borate, tripropylammonium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
 20 tri(n-butyl)ammonium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate, tri(t-butyl)ammonium
 tetrakis(3,5-bis(trifluoromethyl)phenyl)borate, N,N-dimethylanilinium tetrakis(3,5-
 bis(trifluoromethyl)phenyl)borate, N,N-diethylanilinium tetrakis(3,5-
 bis(trifluoromethyl)phenyl)borate, N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis(3,5-
 bis(trifluoromethyl)phenyl)borate, tropillium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
 25 triphenylcarbenium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate, triphenylphosphonium
 tetrakis(3,5-bis(trifluoromethyl)phenyl)borate, triethylsilylium tetrakis(3,5-
 bis(trifluoromethyl)phenyl)borate, benzene(diazonium) tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
 and dialkyl ammonium salts such as: di-(i-propyl)ammonium tetrakis(pentafluorophenyl)borate, and
 dicyclohexylammonium tetrakis(pentafluorophenyl)borate; and additional tri-substituted
 30 phosphonium salts such as tri(o-tolyl)phosphonium tetrakis(pentafluorophenyl)borate, and tri(2,6-
 dimethylphenyl)phosphonium tetrakis(pentafluorophenyl)borate.

[0085] Most preferably, the ionic stoichiometric activator $(L-H)_d^+ (A^{d-})$ is, N,N-
 dimethylanilinium tetrakis(perfluoronaphthyl)borate, N,N-dimethylanilinium
 tetrakis(perfluorobiphenyl)borate, N,N-dimethylanilinium tetrakis(3,5-
 35 bis(trifluoromethyl)phenyl)borate, triphenylcarbenium tetrakis(perfluoronaphthyl)borate,


triphenylcarbenium tetrakis(perfluorobiphenyl)borate, triphenylcarbenium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate, or triphenylcarbenium tetrakis(perfluorophenyl)borate.

[0086] In one embodiment, an activation method using ionizing ionic compounds not containing an active proton but capable of producing a bulky ligand metallocene catalyst cation and their non-coordinating anion are also contemplated, and are described in EP-A 0 426 637, EP-A 0 573 403 and U.S. Patent No. 5,387,568, which are all herein incorporated by reference.

[0087] The term "non-coordinating anion" (NCA) means an anion which either does not coordinate to said cation or which is only weakly coordinated to said cation thereby remaining sufficiently labile to be displaced by a neutral Lewis base. "Compatible" non-coordinating anions are those which are not degraded to neutrality when the initially formed complex decomposes. Further, the anion will not transfer an anionic substituent or fragment to the cation so as to cause it to form a neutral four coordinate metallocene compound and a neutral by-product from the anion. Non-coordinating anions useful in accordance with this invention are those that are compatible, stabilize the metallocene cation in the sense of balancing its ionic charge at +1, yet retain sufficient lability to permit displacement by an ethylenically or acetylenically unsaturated monomer during polymerization. In addition to these activator compounds or co-catalysts, scavengers are used such as tri-isobutyl aluminum or tri-octyl aluminum.

[0088] Invention process also can employ cocatalyst compounds or activator compounds that are initially neutral Lewis acids but form a cationic metal complex and a noncoordinating anion, or a zwitterionic complex upon reaction with the invention compounds. For example, tris(pentafluorophenyl) boron or aluminum act to abstract a hydrocarbyl or hydride ligand to yield an invention cationic metal complex and stabilizing noncoordinating anion, see EP-A 0 427 697 and EP-A 0 520 732 for illustrations of analogous Group-4 metallocene compounds. Also, see the methods and compounds of EP-A 0 495 375. For formation of zwitterionic complexes using analogous Group 4 compounds, see U.S. Patents 5,624,878; 5,486,632; and 5,527,929.

[0089] Another suitable ion forming, activating cocatalyst comprises a salt of a cationic oxidizing agent and a noncoordinating, compatible anion represented by the formula:



wherein OX^{e+} is a cationic oxidizing agent having a charge of $e+$; e is an integer from 1 to 3; and A^- , and d are as previously defined. Examples of cationic oxidizing agents include: ferrocenium, hydrocarbyl-substituted ferrocenium, Ag^+ , or Pb^{+2} . Preferred embodiments of A^{d-} are those anions previously defined with respect to the Bronsted acid containing activators, especially tetrakis(pentafluorophenyl)borate.

[0090] The typical NCA activator-to-catalyst-precursor ratio is a 1:1 molar ratio. Alternate preferred ranges include from 0.1:1 to 100:1, alternately from 0.5:1 to 200:1, alternately from 1:1 to

500:1 alternately from 1:1 to 1000:1. A particularly useful range is from 0.5:1 to 10:1, preferably 1:1 to 5:1.

Activator Combinations

5 [0091] It is within the scope of this invention that catalyst compounds can be combined with one or more activators or activation methods described above. For example, a combination of activators have been described in U.S. Patent Nos. 5,153,157 and 5,453,410, European publication EP-B1 0 573 120, and PCT publications WO 94/07928 and WO 95/14044. These documents all discuss the use of an alumoxane in combination with an ionizing activator.

Oligomer Uses

10 [0092] The oligomers prepared herein may be functionalized by reacting a heteroatom containing group with the oligomer with or without a catalyst. Examples include catalytic hydrosilylation, ozonolysis, hydroformylation, or hydroamination, sulfonation, halogenation, hydrohalogenation, hydroboration, epoxidation, or Diels-Alder reactions with polar dienes, Friedel-Crafts reactions with polar aromatics, maleation with activators such as free radical generators (e.g. peroxides). The
15 functionalized oligomers can be used in oil additives, as anti-fogging or wetting additives, adhesion promoters and many other applications. Preferred uses include additives for lubricants and or fuels. Preferred heteroatom containing groups include, amines, aldehydes, alcohols, acids, anhydrides, sulphonates, particularly succinic acid, maleic acid and maleic anhydride.

[0093] Other uses of the functionalized oligomers include as plasticizers, surfactants for soaps,
20 detergents, fabric softeners, antistatics, etc. Preferred heteroatom containing groups include, amines, aldehydes, alcohols, acids, anhydrides, and sulphonates, particularly succinic acid, maleic acid and maleic anhydride.

[0094] In some embodiments the oligomers produced herein are functionalized as described in U.S. Patent No. 6,022,929; A. Toyota, T. Tsutsui, and N. Kashiwa, Polymer Bulletin 48, 213-219,
25 2002; and J. Am. Chem. Soc., 1990, 112, 7433-7434.

[0095] In preferred embodiments, the oligomers of the present invention can be functionalized (e.g. chemically modified with one or more functional groups (also referred to as a heteroatom containing group) typically containing heteroatoms such as P, O, S, N, Br, Cl, F, I and or Br (preferably N, O, Cl and or Br, preferably N and or O). Preferred functional groups are selected from
30 the group consisting of acids, esters, anhydrides, acid-esters, oxycarbonyls, carbonyls, formyls, formylcarbonyls, hydroxyls, and acetyl halides. Particularly preferred functional groups include those represented by the formula: $-C(O)-X$, where the O is double bonded to the C and the X is hydrogen, nitrogen, hydroxy, oxyhydrocarbyl (e.g. ester), oxygen, the salt moiety $-OM$ wherein M is a metal, e.g. alkali, alkaline earth, transition metal, copper, zinc and the like, oxyhetero, e.g. $-O-Z$ wherein Z

represents a heteroatom such as phosphorus boron, sulfur, which heteroatom may be substituted with hydrocarbyl or oxyhydrocarbyl groups, or two acyl groups may be joined through (X).

[0096] Preferred heteroatom containing groups include acyl groups derived from monounsaturated mono-or dicarboxylic acids and their derivatives, e.g. esters and salts.

5 [0097] More specifically, oligomer functionalized with mono-or dicarboxylic acid material, i.e., acid, anhydride, salt or acid ester are preferred, including the reaction product of the oligomer with a monounsaturated carboxylic reactant comprising at least one member selected from the group consisting of (i) monounsaturated C₄ to C₁₀ dicarboxylic acid (preferably wherein (a) the carboxyl groups are vicinyl, (i.e. located on adjacent carbon atoms) and (b) at least one, preferably both, of said adjacent carbon atoms are part of said monounsaturation); (ii) derivatives of (i) such as anhydrides or 10 C₁ to C₅ alcohol derived mono-or diesters of (i); (iii) monounsaturated C₃ to C₁₀ monocarboxylic acid wherein the carbon-carbon double bond is conjugated to the carboxyl group, i.e., of the structure - C=C-C(O)- (where O is double bonded to C), and (iv) derivatives of (iii) such as C₁ to C₅ alcohol derived monoesters of (iii). Upon reaction with the oligomer, the double bond of the monounsaturated 15 carboxylic reactant becomes saturated. Thus, for example, maleic anhydride reacted with the oligomer becomes succinic anhydride, and acrylic acid becomes a propionic acid.

[0098] Suitable unsaturated acid materials thereof which are useful functional compounds, include acrylic acid, crotonic acid, methacrylic acid, maleic acid, maleic anhydride, fumaric acid, itaconic acid, itaconic anhydride, citraconic acid, citraconic anhydride, mesaconic acid, glutaconic 20 acid, chloromaleic acid, aconitic acid, crotonic acid, methylcrotonic acid, sorbic acid, 3-hexenoic acid, 10-decenoic acid, 2-pentene-1,3,5-tricarboxylic acid, cinnamic acid, and lower alkyl (e.g. C₁ to C₄ alkyl) acid esters of the foregoing, e.g. methyl maleate, ethyl fumarate, methyl fumarate, etc. Particularly preferred are the unsaturated dicarboxylic acids and their derivatives, especially maleic acid, fumaric acid and maleic anhydride.

25 [0099] Typically, from about 0.7 to about 4.0 (e.g., 0.8 to 2.6), preferably from about 1.0 to about 2.0, and most preferably from about 1.1 to about 1.7 moles of said monounsaturated carboxylic reactant are charged to the reactor per mole of oligomer charged.

[00100] Functionalization can be achieved by any suitable method. Useful methods include the reaction of an olefinic bond of the oligomer with an unsaturated, preferably a monounsaturated, 30 carboxylic reactant. Alternatively, the oligomer can be halogenated using chlorine or bromine-containing compounds. The halogenated oligomer can then be reacted with the monounsaturated carboxylic acid. The oligomer and the monounsaturated carboxylic reactant can also be contacted at elevated temperatures to cause a thermal "ene" reaction to take place. Alternatively, the monounsaturated carboxylic acid can be reacted with the oligomer by free radical induced grafting. 35 The oligomer of the present invention can be functionalized by contact with a hydroxy aromatic

compound in the presence of a catalytically effective amount of at least one acidic alkylation catalyst. The alkylated hydroxy aromatic compound can then be further reacted to form a derivative by Mannich Base condensation with an aldehyde and an amine reagent to yield a Mannich Base condensate. In yet another means to functionalize the oligomer, the oligomer may be contacted with carbon monoxide in the presence of an acid catalyst under Koch reaction conditions to yield the oligomer substituted with carboxylic acid groups. In addition to the above methods of functionalization, the oligomer of the present invention can be functionalized by methods of air oxidation, ozonolysis, hydroformylation, epoxidation and chloroamination. (For more information please see US 6,022,929 Column 21, line 16 to column 33, line 27.)

[00101] The functionalized oligomer can in turn be derivatized with a derivatizing compound. (For purposes of this invention and the claims thereto the term functionalized oligomer encompasses derivatized oligomer) The derivatizing compound can react with the functional groups of the functionalized oligomer by means such as nucleophilic substitution, Mannich Base condensation, and the like. The derivatizing compound can be polar and/or contain reactive derivative groups. Preferred derivatizing compounds are selected from hydroxy containing compounds, amines, metal salts, anhydride containing compounds and acetyl halide containing compounds. The derivatizing compounds can comprise at least one nucleophilic group and preferably at least two nucleophilic groups. A typical derivatized oligomer is made by contacting a functionalized oligomer, i.e., substituted with a carboxylic acid/anhydride or ester, with a nucleophilic reagent, e.g., amine, alcohol, including polyols, amino alcohols, reactive metal compounds and the like. (For more information please see US 6,022,929 column 33, line 27 to column 74, line 63.) Alternately a derivatized oligomer may be made by contacting a functionalized oligomer, substituted with a carboxylic acid/anhydride or ester, with a nucleophilic reagent, e.g., amine, to make a quaternary ammonium compound or amine oxide.

[00102] The functionalized oligomers and/or derivatized oligomers have uses as lubricating additives which can act as dispersants, viscosity index improvers, or multifunctional viscosity index improvers. Additionally they may be used as disinfectants (functionalized amines) and or wetting agents.

[00103] Functionalized oligomers and/or derivatized oligomers having uses as dispersants typically have Mn's (g/mol) of less than 20,000, preferably less than 10,000 and most preferably less than 8,000 and typically can range from 500 to 10,000 (e.g. 500 to 5,000), preferably from 1,000 to 8,000 (e.g. 1,000 to 5,000) and most preferably from 1,500 to 6,000 (e.g. 1,500 to 3,000).

[00104] The functionalized oligomers and/or derivatized oligomers described herein having Mn's (g/mol) of greater than 10,000, preferably greater than 10,000 to 30,000 (preferably 20,000 to 30,000) are useful for viscosity index improvers for lubricating oil compositions, adhesive additives,

antifogging and wetting agents, ink and paint adhesion promoters, coatings, tackifiers and sealants, and the like. In addition, such oligomers may be functionalized and derivatized to make multifunctional viscosity index improvers which also possess dispersant properties. (For more information please see US 6,022,929.)

5 **[00105]** The functionalized oligomers and/or derivatized oligomers described herein may be combined with other additives (such as viscosity index improvers, corrosion inhibitor, oxidation inhibitor, dispersant, lube oil flow improver, detergents, demulsifiers, rust inhibitors, pour point depressant, anti-foaming agents, antiwear agents, seal swellant, friction modifiers, and the like (described for example in US 6,022,929 at columns 60, line 42-column 78, line 54 and the references
10 cited therein) to form compositions for many applications, including but not limited to lube oil additive packages, lube oils, and the like.

Compositions containing these additives are typically are blended into the base oil in amounts which are effective to provide their normal attendant function. Representative effective amounts of such additives are illustrated as follows:

15

Compositions	(Typical) wt %*	(Preferred) wt %*
V.I. Improver	1-12	1-4
Corrosion Inhibitor	0.01-3	0.01-1.5
20 Oxidation Inhibitor	0.01-5	0.01-1.5
Dispersant	0.1-10	0.1-5
Lube Oil Flow Improver	0.01-2	0.01-1.5
Detergents and Rust inhibitors	0.01-6	0.01-3
Pour Point Depressant	0.01-1.5	0.01-1.5
25 Anti-Foaming Agents	0.001-0.1	0.001-0.01
Antiwear Agents	0.001-5	0.001-1.5
Seal Swellant	0.1-8	0.1-4
Friction Modifiers	0.01-3	0.01-1.5
Lubricating Base Oil	Balance	Balance

30 * Wt%'s are based on active ingredient content of the additive, and/or upon the total weight of any additive-package, or formulation which will be the sum of the A.I. weight of each additive plus the weight of total oil or diluent.

[00106] When other additives are employed, it may be desirable, although not necessary, to prepare additive concentrates comprising concentrated solutions or dispersions of the subject additives
35 of this invention (in concentrate amounts hereinabove described), together with one or more of said other additives (said concentrate when constituting an additive mixture being referred to herein as an additive-package) whereby several additives can be added simultaneously to the base oil to form the lubricating oil composition. Dissolution of the additive concentrate into the lubricating oil may be facilitated by solvents and by mixing accompanied with mild heating, but this is not essential. The
40 subject functionalized or derivatized oligomers of the present invention can be added to small amounts of base oil or other compatible solvents along with other desirable additives to form additive-

packages containing active ingredients in collective amounts of typically from about 2.5 to about 90%, and preferably from about 15 to about 75%, and most preferably from about 25 to about 60% by weight additives in the appropriate proportions with the remainder being base oil.

5 [00107] The final formulations may employ typically about 10 wt% of the additive-package with the remainder being base oil.

[00108] In another embodiment the functionalized (and optionally derivatized) propylene oligomers and propylene-ethylene co-oligomers ("functionalized (co)oligomers") described herein have less than 10 wt% allyl chain ends, preferably less than 8%, preferably less than 6%, preferably less than 5%, preferably less than 4, %preferably less than 3 %, preferably less than 2%, preferably
10 less than 1% (relative to total unsaturations as measured by ^1H NMR).

[00109] In another embodiment the functionalized (co)oligomers described herein have less than 10 % allyl chain ends, preferably less than 5%, preferably less than 1 %, (relative to total unsaturations as measured by ^1H NMR); and less than 10 wt% vinylidene unsaturations, preferably less than 5%, preferably less than 1 %, (relative to total unsaturations as measured by ^1H NMR);
15 and/or less than 10 % vinylene unsaturations, preferably less than 5%, preferably less than 1 %, (relative to total unsaturations as measured by ^1H NMR). No hydrogen or chain transfer/termination agent should be used during functionalization, derivitization or stripping (of unreacted monomer) for measurement of unsaturations.

[00110] In another embodiment, the functionalized (co)oligomers consist essentially of propylene, functional group and optionally ethylene. Alternately C_4 olefins (such as isobutylene, butadiene, n-butene) are substantially absent from the functionalized (co)oligomers. Alternately C_{4-20} olefins are substantially absent from the functionalized (co)oligomers. Alternately isobutylene is substantially absent from the functionalized (co)oligomers. By substantially absent is meant that the monomer is present in the oligomer/co-oligomer at 1 wt% or less, preferably at 0.5 wt % or less, preferably at 0
25 wt%.

[00111] In another embodiment, the number of functional groups is present at 0.60 to 1.2, alternately 0.75 to 1.1 functional groups per chain (preferably assuming that Mn has not altered by more than 15% as compared to the Mn of the oligomer or co-oligomer prior to functionalization and optional derivatization. Number of functional groups per chain = F/Mn , as determined by ^1H NMR as
30 follows: The instrument used is a 400 MHz Varian pulsed fourier transform NMR spectrometer equipped with a variable temperature proton detection probe operating at 120°C. The polymer sample is dissolved in 1,1,2,2-tetrachloroethane- d_2 (TCE- d_2) and transferred into a 5 mm glass NMR tube. (The solvent has less than 10,000 ppm water and is free of other contaminants that could change the chemical shifts in the NMR spectrum). Acquisition parameters are pulse width = 45°, acquisition
35 delay= 8 s and number of scans= 120. Chemical shifts are determined relative to the TCE- d_2 signal


which is set to 5.98 ppm. VRA is the normalized integrated signal intensity for the vinyls with shifts between from about 4.9 to 5.1 ppm. VRDA is the normalized integrated signal intensity for the vinylidene resonances between from about 4.65 to 4.85 ppm and the vinylene resonances at from about 5.15 to 5.6 ppm. IA is the normalized integrated signal intensities for the aliphatic region of interest between from about 0 to 2.1 ppm (IA). The number of vinyl groups/1000 Carbons (VI) is determined from the formula: $(VRA * 1000) / (IA + VRA + VDRA)$. Likewise, the number of vinylidene & vinylene groups / 1000 carbons (VE) is determined from the formula: $(VDRA * 1000) / (IA + VRA + VDRA)$. VRA, VDRA and IA are the normalized integrated signal intensities in the chemical shift regions defined above. Mn is calculated assuming one unsaturated end-group per oligomer chain. $Mn = (14,000 \text{ g/mol}) / (VI + VE)$.

[00112] After the oligomer in question is functionalized it is necessary to determine the resonances/chemical shift regions of the functional group to determine % functionalization. To do so, repeat the above ^1H NMR procedure on a clean sample of the functionalized oligomer (e.g. washed to remove unreacted materials, contaminants, etc.). Refer to "The Sadtler Guide to NMR Spectra", ed. William Walter Simons, published by the Sadtler Research Laboratories, 1972 for assistance in determining the shift regions for specific functional groups. The number of functional groups /1000 C's (F) = $(FA * 1000) / (FA + IA + VRA + VDRA)$, where FA = normalized integrated signal intensities in the chemical shift region of the functional group, , and IA, VRA, VDRA are as defined above.

[00113] Percent functionalization of the oligomer = $(F * 100) / (F + VI + VE)$. The number of vinyl groups/1000 carbons (VI*) and number of vinylidene groups/1000 carbons (VE*) for the functionalized oligomer are determined from the ^1H NMR spectra of the functionalized oligomer in the same manner as VI and VE for the unfunctionalized oligomer. Preferably the percent functionalization of the oligomer is 75% or more, preferably 80% or more, preferably 90% or more, preferably 95% or more.

[00114] In a preferred embodiment, $F + VI^* + VE^* \geq (0.50(VI + VE))$, preferably $F + VI^* + VE^* \geq (0.60(VI + VE))$, preferably $F + VI^* + VE^* \geq (0.70(VI + VE))$, preferably $F + VI^* + VE^* \geq (0.75(VI + VE))$, preferably $F + VI^* + VE^* \geq (0.80(VI + VE))$, preferably $F + VI^* + VE^* \geq (0.85(VI + VE))$, preferably $F + VI^* + VE^* \geq (0.90(VI + VE))$, preferably $F + VI^* + VE^* \geq (0.95(VI + VE))$, preferably $F + VI^* + VE^* \geq (0.98(VI + VE))$, preferably $F + VI^* + VE^* \geq (0.99(VI + VE))$.

[00115] In another embodiment, the functionalized (co)oligomers are represented by the formula:



where represents oligomer or co-oligmer

X is H or a functional group, provided at least one X is a functional group. Useful functional groups include any of the functional groups described above. Preferred functional groups include heteroatom containing groups where the heteroatom comprises P, O, S, N, Br, Cl, F, I and or Br (preferably N, O, Cl and or Br, preferably N and or O). Particularly preferred functional groups are selected from the group consisting of acids, esters, anhydrides, acid-esters, oxycarbonyls, carbonyls, formyls, formylcarbonyls, hydroxyls, and acetyl halides. Particularly preferred functional groups include those represented by the formula: $-C(O)-X^*$, where the O is double bonded to the C and the X^* is hydrogen, nitrogen, hydroxy, oxyhydrocarbyl (e.g. ester), oxygen, the salt moiety $-OM$ wherein M is a metal, e.g. alkali, alkaline earth, transition metal, copper, zinc and the like, oxyhetero, e.g. $-O-Z$ wherein Z represents a heteroatom such as phosphorus boron, sulfur, which heteroatom may be substituted with hydrocarbyl or oxyhydrocarbyl groups, or two acyl groups may be joined through (X^*).

[00116] Preferred functional groups include acyl groups derived from monounsaturated mono-or dicarboxylic acids and their derivatives, e.g. esters and salts.

[00117] More specifically, oligomer functionalized with mono-or dicarboxylic acid material, i.e., acid, anhydride, salt or acid ester are preferred, including the reaction product of the oligomer with a monounsaturated carboxylic reactant comprising at least one member selected from the group consisting of (i) monounsaturated C_4 to C_{10} dicarboxylic acid (preferably wherein (a) the carboxyl groups are vicinyl, (i.e. located on adjacent carbon atoms) and (b) at least one, preferably both, of said adjacent carbon atoms are part of said monounsaturation); (ii) derivatives of (i) such as anhydrides or C_1 to C_5 alcohol derived mono-or diesters of (i); (iii) monounsaturated C_3 to C_{10} monocarboxylic acid wherein the carbon-carbon double bond is conjugated to the carboxyl group, i.e., of the structure $-C=C-C(O)-$ (where O is double bonded to C), and (iv) derivatives of (iii) such as C_1 to C_5 alcohol derived monoesters of (iii).

[00118] Suitable unsaturated acid materials thereof which are useful functional groups, include acrylic acid, crotonic acid, methacrylic acid, maleic acid, maleic anhydride, fumaric acid, itaconic acid, itaconic anhydride, citraconic acid, citraconic anhydride, mesaconic acid, glutaconic acid, chloromaleic acid, aconitic acid, crotonic acid, methylecrotonic acid, sorbic acid, 3-hexenoic acid, 10-

decenoic acid, 2-pentene-1,3,5-tricarboxylic acid, cinnamic acid, and lower alkyl (e.g. C₁ to C₄ alkyl) acid esters of the foregoing, e.g. methyl maleate, ethyl fumarate, methyl fumarate, etc. Particularly preferred are the unsaturated dicarboxylic acids and their derivatives, especially maleic acid, fumaric acid and maleic anhydride.

5 **[00119]** Preferably at least 90 wt% of the functionalized or derivatized propylene oligomers or propylene-ethylene co-oligomers are represented by one or both of the above formulae, alternately at least 95 wt%, alternately at least 98 wt%, based upon the weight of the functionalized or derivatized propylene oligomers or propylene-ethylene co-oligomers.

10 **[00120]** In another embodiment the functionalized (co)oligomers have a melting point of 20°C or less, alternately 0°C or less, alternately -10°C or less, as measured by DSC as described below.

[00121] In another embodiment the functionalized (co)oligomers have a heat of fusion of 15 J/g or less, alternately 10 J/g or less, alternately 5 J/g or less, as measured by DSC as described below.

15 **[00122]** In another embodiment, the "isobutyl chain end to functional group ratio" is defined to be the ratio of the percent functionalization of the oligomer to the percentage of allylic vinyl groups. In a preferred embodiment the isobutyl chain end to functional group ratio is the same as any of the isobutyl chain end to allylic vinyl group ratios described herein.

[00123] In another embodiment the functionalized (co)oligomers described herein have the same Mn, and or Mw and or Mz as, or up to 15% greater than (preferably up to 10% greater than), as the starting (co)oligomer, "same" is defined to mean within 5%.

20 **[00124]** In another embodiment this invention relates to:

1. A functionalized co-oligomer preferably comprising the reaction product of: 1) a heteroatom containing group, and 2) a co-oligomer having an Mn of 300 to 30,000 g/mol (measured by ¹H NMR) and comprising 10 to 90 mol% propylene and 10 to 90 mol% of ethylene, wherein the oligomer has at least X% allyl chain ends (relative to total unsaturations) prior to functionalization, where: 1) X = (-0.94(mol% ethylene incorporated) + 100), when 10 to 60 mol% ethylene is present in the co-oligomer, and 2) X = 45, when greater than 60 and less than 70 mol% ethylene is present in the co-oligomer, and 3) X = (1.83* (mol% ethylene incorporated) -83), when 70 to 90 mol% ethylene is present in the co-oligomer, where the heteroatom containing group comprises where the functional group comprises one or more heteroatoms selected from the group consisting of P, O, S, N, Br, Cl, F, I and or B, and the functionalized co-oligomer has 0.75 to 1.10 functional groups per chain.

2. The co-oligomer of paragraph 1 wherein the co-oligomer has more than 90% allyl chain ends (relative to total unsaturations) prior to functionalization.

3. The co-oligomer of paragraph 1 wherein the co-oligomer comprises at 15 to 95 wt% ethylene and has more than 80% allyl chain ends (relative to total unsaturations) prior to functionalization.

4. The co-oligomer of paragraph 1 wherein the co-oligomer comprises at 30 to 95 wt% ethylene and has more than 70% allyl chain ends (relative to total unsaturations) prior to functionalization, preferably more than 90% allyl chain ends.

5. A functionalized propylene oligomer, comprising more than 90 mol% propylene and less than 10 mol% ethylene wherein the oligomer has: at least 93% allyl chain ends, a number average molecular weight (Mn) of about 500 to about 20,000 g/mol, an isobutyl chain end to allylic vinyl group ratio of 0.8:1 to 1.35:1.0, and less than 1400 ppm aluminum.

6. A functionalized propylene oligomer, comprising the reaction product of 1) a heteroatom containing group and 2) an oligomer comprising more than 90 mol% propylene and less than 10 mol% ethylene wherein the oligomer has: at least 93% allyl chain ends, a number average molecular weight (Mn) of about 500 to about 20,000 g/mol, an isobutyl chain end to allylic vinyl group ratio of 0.8:1 to 1.35:1.0, and less than 100 ppm aluminum, where the heteroatom containing group comprises one or more heteroatoms selected from the group consisting of P, O, S, N, Br, Cl, F, I and or B, and the functionalized oligomer has 0.75 to 1.10 functional groups per chain.

7. A functionalized propylene oligomer, comprising: the reaction product of 1) a heteroatom containing group, and 2) an oligomer comprising at least 50 mol% propylene and from 10 to 50 mol% ethylene, wherein the oligomer has: at least 90% allyl chain ends, an Mn of about 150 to about 10,000 g/mol, and an isobutyl chain end to allylic vinyl group ratio of 0.8:1 to 1.2:1.0, wherein monomers having four or more carbon atoms are present at from 0 to 3 mol%, where the heteroatom containing group comprises one or more heteroatoms selected from the group consisting of P, O, S, N, Br, Cl, F, I and or B, and the functionalized co-oligomer has 0.75 to 1.10 functional groups per chain.

8. A functionalized propylene oligomer, comprising: the reaction product of 1) a functional group, and 2) an oligomer comprising at least 50 mol% propylene, from 0.1 to 45 mol% ethylene, and from 0.1 to 5 mol% C₄ to C₁₂ olefin, wherein the oligomer has: at least 90% allyl chain ends, an Mn of about 150 to about 10,000 g/mol, and an isobutyl chain end to allylic vinyl group ratio of 0.8:1 to 1.35:1.0, where the heteroatom containing group comprises one or more heteroatoms selected from the group consisting of P, O, S, N, Br, Cl, F, I and or B, and the functionalized co-oligomer has 0.75 to 1.10 functional groups per chain.

9. A functionalized propylene oligomer, comprising: the reaction product of 1) a heteroatom containing group, and 2) an oligomer comprising at least 50 mol% propylene, from 0.1 to 45 wt% ethylene, and from 0.1 to 5 mol% diene, wherein the oligomer has: at least 90% allyl chain ends, an Mn of about 150 to about 10,000 g/mol, and an isobutyl chain end to allylic vinyl group ratio of 0.7:1 to 1.35:1.0, where the heteroatom containing group comprises one or more heteroatoms selected from the group consisting of P, O, S, N, Br, Cl, F, I and or B, and the functionalized co-oligomer has 0.75 to 1.10 functional groups per chain.

10. The oligomer of any of paragraphs 1 to 9, wherein the oligomer is a liquid at 25°C.

11. The oligomer of any of paragraphs 1-10, wherein the Mn is about 500 to about 7,500 g/mol, the Mw is 1,000 to about 20,000 g/mol, and the Mz is about 1400 (alternately 1700) to about 150,000 g/mol.

12. The functionalized (co)oligomer of any of paragraphs 1 to 11, wherein $F + VI^* + VE^* \geq (0.60(VI + VE))$, wherein VI is the number of vinyl groups/1000 carbons and VE is number of vinylidene groups/1000 carbons for the unfunctionalized oligomer, VI* is the number of vinyl groups/1000 carbons and VE* is the number of vinylidene groups/1000 carbons for the functionalized oligomer, and F is the number of functional groups per 1000 carbons.

13. The oligomer of any of paragraphs 1-12, wherein the oligomer has no detectable melting point by DSC following storage at ambient temperature for at least 48 hours.


14. The oligomer of any of paragraphs 1-12, wherein the oligomer has a melting peak of from about 60°C to about 130°C.


15. The functionalized oligomer of any of paragraphs 1-14 wherein the heteroatom containing group comprises sulfonates, amines, aldehydes, alcohols, or acids, preferably the heteroatom containing group comprises an epoxide, succinic acid, maleic acid or maleic anhydride, alternately the heteroatom containing group comprises one or more of acids, esters, anhydrides, acid-esters, oxycarbonyls, carbonyls, formyls, formylcarbonyls, hydroxyls, and acetyl halides.

16. The functionalized oligomer of any of paragraphs 1-15 wherein the functionalized oligomer has an Mn that is up to 15% greater than the Mn of the starting (co)oligomer, preferably up to 5% greater.

17. A homogenous process for making the functionalized propylene co-oligomer of any of the above paragraphs 1 to 16, wherein the process comprises:

1) a first homogenous process for making a propylene co-oligomer, said first process having productivity of at least 4500 g/mmol/hr, wherein the first process comprises: contacting, at a temperature of from 35°C to 150°C, propylene, 0.1 to 70 mol% ethylene and from 0 to about 5 wt% hydrogen in the presence of a catalyst system comprising an activator and at least one metallocene compound represented by the formulae:





where

Hf is hafnium;

each X is, independently, selected from the group consisting of hydrocarbyl radicals having from 1 to 20 carbon atoms, hydrides, amides, alkoxides, sulfides, phosphides, halogens, dienes, amines, phosphines, ethers, or a combination thereof, preferably methyl, ethyl, propyl, butyl, phenyl, benzyl, chloride, bromide, iodide, (alternately two X's may form a part of a fused ring or a ring system);

each Q is, independently carbon or a heteroatom, preferably C, N, P, S (preferably at least one Q is a heteroatom, alternately at least two Q's are the same or different heteroatoms, alternately at least three

Q's are the same or different heteroatoms, alternately at least four Q's are the same or different heteroatoms);

each R¹ is, independently, a C₁ to C₈ alkyl group, preferably a C₁ to C₈ linear alkyl group, preferably methyl ethyl, propyl, butyl, pentyl, hexyl, heptyl or octyl, R¹ may the same or different as R²;

each R² is, independently, a C₁ to C₈ alkyl group, preferably a C₁ to C₈ linear alkyl group, preferably methyl ethyl, propyl, butyl, pentyl, hexyl, heptyl or octyl, preferably R¹ and/or R² are not branched;

each R³ is, independently, hydrogen, or a substituted or unsubstituted hydrocarbyl group having from 1 to 8 carbon atoms, preferably 1 to 6 carbon atoms, preferably a substituted or unsubstituted C₁ to C₈ linear alkyl group, preferably methyl ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, provided however that at least three R³ groups are not hydrogen (alternately four R³ groups are not hydrogen, alternately five R³ groups are not hydrogen);

each R⁴ is, independently, hydrogen or a substituted or unsubstituted hydrocarbyl group, a heteroatom or heteroatom containing group, preferably a substituted or unsubstituted hydrocarbyl group having from 1 to 20 carbon atoms, preferably 1 to 8 carbon atoms, preferably a substituted or unsubstituted C₁ to C₈ linear alkyl group, preferably methyl ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, substituted phenyl (such as propyl phenyl), phenyl, silyl, substituted silyl, (such as CH₂SiR', where R' is a C₁ to C₁₂ hydrocarbyl, such as methyl, ethyl, propyl, butyl, phenyl);

R⁵ is hydrogen or a C₁ to C₈ alkyl group, preferably a C₁ to C₈ linear alkyl group, preferably methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl or octyl;

R⁶ is hydrogen or a C₁ to C₈ alkyl group, preferably a C₁ to C₈ linear alkyl group, preferably methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl or octyl;

each R^7 is, independently, hydrogen, or a C_1 to C_8 alkyl group, preferably a C_1 to C_8 linear alkyl group, preferably methyl ethyl, propyl, butyl, pentyl, hexyl, heptyl or octyl, provided however that at least seven R^7 groups are not hydrogen, alternately at least eight R^7 groups are not hydrogen, alternately all R^7 groups are not hydrogen, (preferably the R^7 groups at the 3 and 4 positions on each Cp ring of Formula IV are not hydrogen);

N is nitrogen;

T is a bridge, preferably, Si or Ge, preferably Si;


each R^a , is independently, hydrogen, halogen or a C_1 to C_{20} hydrocarbyl, such as methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, phenyl, benzyl, substituted phenyl, and two R^a can form a cyclic structure including aromatic, partially saturated, or saturated cyclic or fused ring system;

and further provided that any two adjacent R groups may form a fused ring or multicenter fused ring system where the rings may be aromatic, partially saturated or saturated; and 2) a second functionalizing process comprising contacting the co-oligomer produced in the first process with a heteroatom containing group.

18. A homogenous process for making the functionalized propylene homo-oligomer of any of paragraphs 1 to 16, comprising:

1) a first homogenous process for making a propylene homo-oligomer, said first process having productivity of at least 4500 g/mmol/hour, wherein the first process comprises:

contacting, at a temperature of from 30°C to 120°C, propylene, 0 mol% comonomer and from 0 to about 5 wt% hydrogen in the presence of a catalyst system comprising an activator and at least one metallocene compound represented by the formulae:



where

Hf is hafnium;

each X is, independently, selected from the group consisting of hydrocarbyl radicals having from 1 to 20 carbon atoms, hydrides, amides, alkoxides, sulfides, phosphides, halogens, dienes, amines, phosphines, ethers, or a combination thereof, preferably methyl, ethyl, propyl, butyl, phenyl, benzyl, chloride, bromide, iodide, (alternately two X's may form a part of a fused ring or a ring system);

each Q is, independently carbon or a heteroatom, preferably C, N, P, S (preferably at least one Q is a heteroatom, alternately at least two Q's are the same or different heteroatoms, alternately at least three Q's are the same or different heteroatoms, alternately at least four Q's are the same or different heteroatoms);

each R¹ is, independently, a C₁ to C₈ alkyl group, preferably a C₁ to C₈ linear alkyl group, preferably methyl ethyl, propyl, butyl, pentyl, hexyl, heptyl or octyl, R¹ may the same or different as R²;

each R² is, independently, a C₁ to C₈ alkyl group, preferably a C₁ to C₈ linear alkyl group, preferably methyl ethyl, propyl, butyl, pentyl, hexyl, heptyl or octyl, preferably R¹ and/or R² are not branched;

each R³ is, independently, hydrogen, or a substituted or unsubstituted hydrocarbyl group having from 1 to 8 carbon atoms, preferably 1 to 6 carbon atoms, preferably a substituted or unsubstituted C₁ to C₈ linear alkyl group, preferably methyl ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, provided however that: 1) all five R³ groups are methyl, or 2) four R³ groups are not hydrogen and at least one R³ group is a C₂ to C₈ substituted or unsubstituted hydrocarbyl (preferably at least two, three, four or five R³ groups are a C₂ to C₈ substituted or unsubstituted hydrocarbyl);

each R⁴ is, independently, hydrogen or a substituted or unsubstituted hydrocarbyl group, a heteroatom or heteroatom containing group, preferably a substituted or unsubstituted hydrocarbyl group having from 1 to 20 carbon atoms, preferably 1 to 8 carbon atoms, preferably a substituted or unsubstituted C₁ to C₈ linear alkyl group, preferably methyl ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, substituted phenyl (such as propyl phenyl), phenyl, silyl, substituted silyl, (such as CH₂SiR', where R' is a C₁ to C₁₂ hydrocarbyl, such as methyl, ethyl, propyl, butyl, phenyl);

R⁵ is hydrogen or a C₁ to C₈ alkyl group, preferably a C₁ to C₈ linear alkyl group, preferably methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl or octyl;

R⁶ is hydrogen or a C₁ to C₈ alkyl group, preferably a C₁ to C₈ linear alkyl group, preferably methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl or octyl;

each R⁷ is, independently, hydrogen, or a C₁ to C₈ alkyl group, preferably a C₁ to C₈ linear alkyl group, preferably methyl ethyl, propyl, butyl, pentyl, hexyl, heptyl or octyl, provided however that at least seven R⁷ groups are not hydrogen, alternately at least eight R⁷ groups are not hydrogen, alternately all R⁷ groups are not hydrogen, (preferably the R⁷ groups at the 3 and 4 positions on each Cp ring of Formula IV are not hydrogen);

N is nitrogen;

T is a bridge, preferably, Si or Ge, preferably Si;

each R^a, is independently, hydrogen, halogen or a C1 to C20 hydrocarbyl, such as methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, phenyl, benzyl, substituted phenyl, and two R^a can form a

cyclic structure including aromatic, partially saturated, or saturated cyclic or fused ring system; and further provided that any two adjacent R groups may form a fused ring or multicenter fused ring system where the rings may be aromatic, partially saturated or saturated; and

2) a second functionalizing process comprising contacting the homo-oligomer produced in the first process with a heteroatom containing group.

19. The process of paragraph 17 or 18, wherein the activator comprises one or more non-coordinating anions.

20. The process of paragraph 17, 18 or 19 wherein the catalyst system comprises one or more of (pentamethylcyclopentadienyl)(1,3 dimethylindenyl) hafnium) dimethyl, and (pentamethylcyclopentadienyl)(1,3 dimethylindenyl) hafnium) dichloride.

21. The process of paragraph 17 or 19, wherein the catalyst system comprises one or more of (1,3-Dimethylindenyl)(pentamethylcyclopentadienyl) Hafniumdimethyl,

(1,3,4,7-Tetramethylindenyl)(pentamethylcyclopentadienyl) Hafniumdimethyl,

(1,3-Dimethylindenyl)(tetramethylcyclopentadienyl) Hafniumdimethyl,

(1,3-Diethylindenyl)(pentamethylcyclopentadienyl) Hafniumdimethyl,

(1,3-Dipropylindenyl)(pentamethylcyclopentadienyl) Hafniumdimethyl,

(1-Methyl,3-propylindenyl)(pentamethylcyclopentadienyl) Hafniumdimethyl,

(1,3-Dimethylindenyl)(tetramethylpropylcyclopentadienyl) Hafniumdimethyl,

(1,2,3-Trimethylindenyl)(pentamethylcyclopentadienyl) Hafniumdimethyl,

(1,3-Dimethylbenzindenyl)(pentamethylcyclopentadienyl) Hafniumdimethyl,

(2,7-Bis t-butylfluorenyl)(pentamethylcyclopentadienyl) Hafniumdimethyl,

(9-Methylfluorenyl)(pentamethylcyclopentadienyl) Hafniumdimethyl,

(2,7,9-Trimethylfluorenyl)(pentamethylcyclopentadienyl) Hafniumdimethyl,

μ -Dihydrosilyl-bis(tetramethylcyclopentadienyl)Hafniumdimethyl,

μ -Dimethylsilyl(tetramethylcyclopentadienyl)(3-propyltrimethylcyclopentadienyl) Hafniumdimethyl,

μ -Dicyclopropylsilyl(bis tetramethylcyclopentadienyl)Hafnium dimethyl.

(1,3-Dimethylindenyl)(pentamethylcyclopentadienyl) Hafniumdihalide,

(1,3,4,7-Tetramethylindenyl)(pentamethylcyclopentadienyl) Hafniumdihalide,

(1,3-Dimethylindenyl)(tetramethylcyclopentadienyl) Hafniumdihalide,

(1,3-Diethylindenyl)(pentamethylcyclopentadienyl) Hafniumdihalide,

(1,3-Dipropylindenyl)(pentamethylcyclopentadienyl) Hafniumdihalide,

(1-Methyl,3-propylindenyl)(pentamethylcyclopentadienyl) Hafniumdihalide,
 (1,3-Dimethylindenyl)(tetramethylpropylcyclopentadienyl) Hafniumdihalide,
 (1,2,3-Trimethylindenyl)(pentamethylcyclopentadienyl) Hafniumdihalide,
 (1,3-Dimethylbenzindenyl)(pentamethylcyclopentadienyl) Hafniumdihalide,
 5 (2,7-Bis t-butylfluorenyl)(pentamethylcyclopentadienyl) Hafniumdihalide,
 (9-Methylfluorenyl)(pentamethylcyclopentadienyl) Hafniumdihalide,
 (2,7,9-Trimethylfluorenyl)(pentamethylcyclopentadienyl) Hafniumdihalide,
 μ -Dihydrosilyl-bis(tetramethylcyclopentadienyl)Hafniumdimethyl,
 μ -Dihalidesilyl(tetramethylcyclopentadienyl)(3-propyltrimethylcyclopentadienyl) Hafniumdihalide,
 10 and
 μ -Dicyclopropylsilyl(bis tetramethylcyclopentadienyl)Hafnium dihalide.

22. The process of paragraph 18 or 19, wherein the catalyst system comprises one or more of

(1,3-Dimethylindenyl)(pentamethylcyclopentadienyl) Hafniumdimethyl,
 (1,3,4,7-Tetramethylindenyl)(pentamethylcyclopentadienyl) Hafniumdimethyl,
 15 (1,3-Diethylindenyl)(pentamethylcyclopentadienyl) Hafniumdimethyl,
 (1,3-Dipropylindenyl)(pentamethylcyclopentadienyl) Hafniumdimethyl,
 (1-Methyl,3-propylindenyl)(pentamethylcyclopentadienyl) Hafniumdimethyl,
 (1,2,3-Trimethylindenyl)(pentamethylcyclopentadienyl) Hafniumdimethyl,
 (1,3-Dimethylbenzindenyl)(pentamethylcyclopentadienyl) Hafniumdimethyl,
 20 (2,7-Bis t-butylfluorenyl)(pentamethylcyclopentadienyl) Hafniumdimethyl,
 (9-Methylfluorenyl)(pentamethylcyclopentadienyl) Hafniumdimethyl,
 (2,7,9-Trimethylfluorenyl)(pentamethylcyclopentadienyl) Hafniumdimethyl,
 (1,3-Dimethylindenyl)(pentamethylcyclopentadienyl) Hafniumdihalide,
 (1,3,4,7-Tetramethylindenyl)(pentamethylcyclopentadienyl) Hafniumdihalide,
 25 (1,3-Diethylindenyl)(pentamethylcyclopentadienyl) Hafniumdihalide,
 (1,3-Dipropylindenyl)(pentamethylcyclopentadienyl) Hafniumdihalide,
 (1-Methyl,3-propylindenyl)(pentamethylcyclopentadienyl) Hafniumdihalide,
 (1,2,3-Trimethylindenyl)(pentamethylcyclopentadienyl) Hafniumdihalide,
 (1,3-Dimethylbenzindenyl)(pentamethylcyclopentadienyl) Hafniumdihalide,
 30 (2,7-Bis t-butylfluorenyl)(pentamethylcyclopentadienyl) Hafniumdihalide,
 (9-Methylfluorenyl)(pentamethylcyclopentadienyl) Hafniumdihalide, and
 (2,7,9-Trimethylfluorenyl)(pentamethylcyclopentadienyl) Hafniumdihalide.

23. The process of any of paragraphs 17 to 22, where the process has at least 70% conversion of
 allyl chain end to functional group, preferably at least 80%, preferably at least 90%, preferably at least
 35 95%.

24. The process of any of paragraphs 17 to 23, where the process is a solution process.

25. The process of any of paragraphs 17 to 24, where in the heteroatom containing group comprises one or more heteroatoms selected from the group consisting of P, O, S, N, Br, Cl, F, I and or B.

5 26. The process of any of paragraphs 17 to 25 wherein $F + VI^* + VE^* \geq (0.80(VI + VE))$, wherein VI is the number of vinyl groups/1000 carbons and VE is number of vinylidene groups/1000 Carbons for the unfunctionalized oligomer, VI* is the number of vinyl groups/1000 carbons and VE* is the number of vinylidene groups/1000 carbons for the functionalized oligomer, and F is the number of functional groups per 1000 carbons.

10 **[00125]** In a preferred embodiment, the homo-oligomers described herein (particularly in paragraphs 1-26 are one or more propylene homo-oligomers having from an Mn of from 1500 to 11,000 g/mol, and a meso diad content ranging from 45 to 98%, alternately 50 to 95%, alternately 60 to 90%, preferably the homo-oligomers have a Tm of up to 145°C, alternately from 50 to 145°C, alternately from 80 to 140°C. In an alternate embodiment, the homo-oligomers described herein
15 (particularly in paragraphs 1-26 above) are one or more of propylene homo-oligomers having an Mn of from 1500 to 11,000 g/mol, and a ratio of meso diads to racemic diads of 1:1 or less.

[00126] Meso and racemic diad content (and other propylene microstructures) are determined by ¹³CNMR according to the procedure described at page 38, paragraph [0613] to [0615] of US 2008/0045638).

20 **[00127]** In another embodiment, the oligomer described herein (particularly in paragraphs 1-26 above) is one or more of 1) propylene homo-oligomer having an meso diad content of 50% or more and an Mn of about 2500 g/mol; 2) propylene homo-oligomer having an Mn of about 5000 g/mol and an meso diad content of 50%; 3) propylene homo-oligomer having an Mn of about 10,000 g/mol and an isotacticity of about meso diad content of 50%; 4) propylene homo-oligomer having an Mn of
25 about 1000 g/mol and a ratio of meso diads to racemic diads of between 1.2:1 and 0.8/1.0 ; and 5) propylene homo-oligomer having an Mn of about 2000 g/mol and a ratio of meso diads to racemic diads of between 1.2:1 and 0.8:1.0.

[00128] In a preferred embodiment, the co-oligomers described herein (particularly in paragraphs 1-26 above) are one or more propylene co-oligomers having from an Mn of from 1500 to 11,000
30 g/mol, and a meso diad content ranging from 45 to 98%, alternately 50 to 95%, alternately 60 to 90%, preferably the co-oligomers have a Tm of up to 145°C, alternately from 50 to 145°C, alternately from 80 to 140°C.

EXAMPLES

[00129] The foregoing discussion can be further described with reference to the following non-
35 limiting examples.

Product Characterization

[00130] Products were characterized by ^1H NMR and ^{13}C NMR as follows:

 ^{13}C NMR

[00131] ^{13}C NMR data was collected at 120°C in a 10 mm probe using a Varian spectrometer with a ^1H Hydrogen frequency of at least 400 MHz. A 90 degree pulse, an acquisition time adjusted to give a digital resolution between 0.1 and 0.12 Hz, at least a 10 second pulse acquisition delay time with continuous broadband proton decoupling using swept square wave modulation without gating was employed during the entire acquisition period. The spectra were acquired using time averaging to provide a signal to noise level adequate to measure the signals of interest. Samples were dissolved in tetrachloroethane- d_2 at concentrations between 10 to 15 wt% prior to being inserted into the spectrometer magnet.

[00132] Prior to data analysis spectra were referenced by setting the chemical shift of the $(-\text{CH}_2-)_n$ signal where $n > 6$ to 29.9 ppm.

[00133] Chain ends for quantization were identified using the signals shown in the table below. N-butyl and n-propyl were not reported due to their low abundance (less than 5%) relative to the chain ends shown in the table below.

Chain End	^{13}C NMR Chemical Shift
P~i-Bu	23.5 to 25.5 and 25.8 to 26.3 ppm
E~i-Bu	39.5 to 40.2 ppm
P~Vinyl	41.5 to 43 ppm
E~Vinyl	33.9 to 34.4 ppm

 ^1H NMR

[00134] ^1H NMR data was collected at either room temperature or 120°C (for purposes of the claims, 120°C shall be used) in a 5 mm probe using a Varian spectrometer with a ^1H Hydrogen frequency of at least 500 MHz. Data was recorded using a maximum pulse width of 45°, 8 seconds between pulses and signal averaging 120 transients. Spectral signals were integrated and the number of unsaturation types per 1000 carbons was calculated by multiplying the different groups by 1000 and dividing the result by the total number of carbons.

[00135] The chemical shift regions for the olefin types are defined to be between the following spectral regions.

Unsaturation Type	Region (ppm)	Number of hydrogens per structure
Vinyl	4.95-5.10	2
Vinylidene	4.70-4.84	2
Vinylene	5.31-5.55	2
Trisubstituted	5.11-5.30	1

[00136] The populations of olefin unsaturations found in the products by ^1H NMR are summarized in Table 3. In this table, the vinyl population, as a percentage of total unsaturation, is

provided as well, along with the number average molecular weight calculated by assuming one unsaturation per chain and degree of polymerization, or average number of propylene units per chain. For the propylene oligomer products, the % vinyl ranges from ~0 (comparative examples A and B catalysts) to as high as ~98% (F). Regardless of activator, the less sterically encumbered A, B catalysts (comparative examples) did not produce significant vinyl populations, and the metallocenes D, G and H also produce products with low allylic vinyl content (10 to 42%). In the case of E, the activator appears to impact the chain termination pathway. In the case of F runs, high allylic vinyl populations were attained with both 1 and 4 activators, although allylic vinyl population decreased modestly with increasing polymerization temperature. Temperature played a role in the % vinyl for E but less so for F. Where impact was observed, it was opposite to using bridged, chiral metallocenes.

[00137] Glass Transition Temperature (T_g) was measured by DSC as described above. Viscosity was measured at 35°C using a Brookfield viscometer. Refractive Index was measured at 25°C with 589 nm Na line.

Materials

The following metallocenes were used:

A = bis(1-methyl,3-n-butylcyclopentadienyl)zirconium dimethyl;

B = dimethylsilyl bis(4,5,6,7-tetrahydroindenyl) zirconium dimethyl;

C = dimethylsilyl bis(indenyl) hafnium dimethyl;

D = (tetramethylcyclopentadienyl)(1,3-dimethylindenyl)zirconium dimethyl;

E = (tetramethylcyclopentadienyl)(1,3-dimethylindenyl)hafnium dimethyl;

F = (pentamethylcyclopentadienyl)(1,3-dimethylindenyl)hafnium dimethyl;

G = (tetramethylcyclopentadienyl)(1-isopropylindenyl) hafnium dimethyl;

H = (tetramethylcyclopentadienyl)(1-isopropyl,3-n-propylindenyl) hafnium dimethyl; and

J = dimethylsilyl bis(2-methyl,4-phenylindenyl)zirconium dimethyl.

[00138] Several ionic activators and one supported ionic activator were used to activate the metallocenes. The ionic activators used were:

1 = dimethylanilinium perfluorotetraphenylborate,

2 = 4-tert-butylanilinium bis(pentafluorophenyl)bis(perfluoro-2-naphthyl)borate,

3 = 4-tert-butylanilinium (pentafluorophenyl)tris(perfluoro-2-naphthyl)borate,

4 = dimethylanilinium tetrakis(perfluoro-2-naphthyl)borate,

5 = dimethylanilinium tetrakis(3,5 (pentafluorophenyl)perfluorophenyl)borate); and

6 = tris-perfluorophenyl boron.

[00139] Catalyst Compound Synthesis: Typical dry-box procedures for synthesis of air-sensitive compounds were followed. Solvents were purchased from Aldrich and dried over 2A sieves. Indene was purchased from Aldrich and pentamethylcyclopentadiene was purchased from Norquay.

Metallocenes A, B and C were purchased from Boulder scientific or Albemarle. The activators were purchased from Albemarle or Grace Davison.

Catalyst F: $(\text{CpMe}_5)(1,3\text{-Me}_2\text{C}_9\text{H}_5)\text{HfMe}_2$

[00140] LiC_9H_7 was generated in Et_2O (-35°C) by the reaction of 29 g indene (0.25 mol) with 1 equivalent of $n\text{-BuLi}$ (10 M, hexane) added slowly. LiC_9H_7 was isolated by reduction of the ether solution, addition of hexane and filtration over a medium glass frit. The product was washed with additional hexane (2 x 40 mL). LiC_9H_7 was dissolved in Et_2O , cooled to -35°C and reacted with excess MeI (0.375 mol, 47.6 g). After 2 hours the reaction mixture was warmed to ambient temperature. $1\text{-MeC}_9\text{H}_7$ was isolated as a colorless liquid by aqueous work-up and ether extractions.

Similarly $1,3\text{-Me}_2\text{C}_9\text{H}_6$ was synthesized by lithiation of MeC_9H_7 , methylation with MeI and aqueous work-up. $[\text{Li}][1,3\text{-Me}_2\text{C}_9\text{H}_5]$ was synthesized by reaction of $1,3\text{-Me}_2\text{C}_9\text{H}_6$ in hexane with excess $n\text{BuLi}$ (1.1 equiv) for 12 hours. The white solid was filtered and washed with additional hexane and dried in vacuo to yield pure $[\text{Li}][1,3\text{-Me}_2\text{C}_9\text{H}_5]$, **B** (14.5 g). ^1H NMR (THF-d_8 , 300 MHz) δ ppm; 7.25-7.10 (m, C_6H_4 , 2H), 6.45-6.30, C_6H_4 , 2H), 6.10 (s, 2-indenyl proton, 1H), 2.35 (s, $1,3\text{Me}_2\text{C}_9\text{H}_5$, 6 H).

[00141] $\text{CpMe}_5\text{HfCl}_3$ (Crowther, D.; Baenziger, N.; Jordan, R.; J. Journal of the American Chemical Society (1991), 113(4), 1455-1457) (10.4 g) was reacted with $[\text{Li}][1,3\text{-Me}_2\text{C}_9\text{H}_5]$ (3.7 g, 24.8 mmol) in Et_2O (100 ml) for 12 hours. The yellow product was collected by filtration over a glass frit and dried to yield crude $(\text{CpMe}_5)(1,3\text{-Me}_2\text{C}_9\text{H}_5)\text{HfCl}_2$ (8.6 g) as a mixture with LiCl .

[00142] ^1H NMR (CD_2Cl_2 , 300 MHz) δ ppm; 7.58-7.11 (m, C_6H_4), 6.17 (s, 2-indenyl proton), 2.32 (s, $1,3\text{Me}_2\text{C}_9\text{H}_5$), 2.09 (s, CpMe_5).

[00143] Crude $(\text{CpMe}_5)(1,3\text{-Me}_2\text{C}_9\text{H}_5)\text{HfCl}_2$ (2.5 g) was slurried in toluene (100 ml) and reacted with MeMgI (4.2 g, 2.1 equiv, 3.0 M in Et_2O). The reaction mixture was heated to 80°C for 3 hours. After cooling the volatiles were removed in vacuo to yield a solid which was extracted with hexane (4 x 40 mL). Hexane was removed from the combined extractions to yield solid yellow $(\text{CpMe}_5)(1,3\text{-Me}_2\text{C}_9\text{H}_5)\text{HfMe}_2$, **E** (1.6 g). ^1H NMR (C_6D_6 , 300 MHz) δ ppm; 7.55-7.48 (m, C_6H_4 , 2H), 7.20-7.16 (m, C_9H_5 , 3H), 2.00 (s, $1,3\text{Me}_2\text{C}_9\text{H}_5$, 6H), 1.76 (s, CpMe_5 , 15H), -0.95 (s, Hf-Me , 6H).

Catalyst D: $(\text{CpMe}_4)(1,3\text{-Me}_2\text{C}_9\text{H}_5)\text{ZrMe}_2$

[00144] ZrCl_4 (36 g) was slurried in CH_2Cl_2 (200 mL) and then reacted with Me_2S (19.2 g) for 1 hour. $\text{CpMe}_4\text{HSiMe}_3$ (34 g) was added slowly to the reaction mixture. Yellow solid began to precipitate after several hours and was filtered to yield a first crop of 21.3 g of light yellow solid product. $(\text{CpMe}_4\text{H})\text{ZrCl}_3(\text{SMe}_2)_x$ ^1H NMR (CD_2Cl_2 , 300 MHz) δ ppm; 6.05 (s, CpMe_4H), 2.6 (br s, MeS), 2.27 (s, CpMe_4), 2.20 (s, CpMe_4).

[00145] $(\text{CpMe}_4\text{H})\text{ZrCl}_3$ (15.0 g) was slurried in Et_2O (250 mL) and reacted with $[\text{Li}][1,3\text{-Me}_2\text{C}_9\text{H}_5]$ (7.5 g) for 16 hours. The reaction product was filtered over a glass frit, washed with

CH₂Cl₂ and dried in vacuo. All the solid product (ca 22 g) was slurried in Et₂O (200 mL) and reacted with MeMgI (38 g 3 M in Et₂O). After 4 hours dimethoxyethane (6.8 g) was added and the reaction mixture filtered. Additional Et₂O was used to extract the solid residue. The filtrates were reduced and cooled to -35°C. An off-white solid product was filtered and dried in vacuo (14.8 g).

[00146] ¹H NMR (CD₂Cl₂, 500 MHz) δ ppm; 7.35, 7.05 (m, C₉H₅), 5.51 (s, C₉H₅), 4.83 (s, CpMe₄H), 2.17 (s, Me₂C₉H₅), 1.79, 1.70 (s, CpMe₄H), -1.31 ZrMe.

Catalyst E: (CpMe₄)(1,3-Me₂C₉H₅)HfMe₂

[00147] HfCl₄ (31 g) was slurried in CH₂Cl₂ (200 mL) and reacted slowly with CpMe₄HSiMe₃ for several hours. The reaction mixture was filtered, reduced in volume and hexane (80 mL) was added. The filtrate was cooled to -35°C. The off-white product was collected and dried in vacuo. (CpMe₄H)HfCl₃ (8.0 g) was dissolved in Et₂O (150 mL) and reacted with [Li][1,3-Me₂C₉H₅] (2.8 g). After 1 hour the volatiles were removed and the crude reaction mixture extracted with CH₂Cl₂ (2 X 60 mL). The filtrate was reduced in vacuo to a light yellow solid product (7.2 g). All (CpMe₄)(1,3-Me₂C₉H₅)HfCl₂ (7.2 g) was slurried in toluene (200 mL) and reacted with 2 equivalents of MeMgBr (3 M in Et₂O). The reaction mixture was heated to 90°C for 6 hours. The mixture was cooled to room temperature and dimethoxyethane (3 mL) was added. The volatiles were removed, the residue extracted with CH₂Cl₂ and the filtrates were reduced in vacuo. The product was collected after cooling to -35 °C (2.85 g). (CpMe₄)(1,3-Me₂C₉H₅)HfMe₂ ¹H NMR (CD₂Cl₂, 500 MHz) δ ppm; 7.35, 7.06 (m, C₉H₅), 5.50 (s, C₉H₅), 4.89 (s, CpMe₄H), 2.18 (s, Me₂C₉H₅), 1.79, 1.76 (s, CpMe₄H), -1.49 HfMe.

Catalyst H:(tetramethylcyclopentadienyl)(1-isopropyl, 3-propyl-C₉H₆)HfMe₂

[00148] 1-isopropyl, 3-propyl-C₉H₆ was synthesized by reaction of 1-isopropylindenyl lithium with propyl bromide in Et₂O. The lithium salt is synthesized from BuLi in Et₂O. [Li][1-isopropyl, 3-propyl -C₉H₅] (2.1 g) was dissolved in Et₂O (60 mL) and reacted with (CpMe₄H)HfCl₃ (4.0 g). MeMgI (2 equivalents) were added to the reaction mixture, 60 mL toluene added and the reaction was heated to 90°C. After 2 hours the reaction was cooled, volatiles removed and the dimethyl product extracted with hexane. The product was obtained as an amber oil (3.8 g). ¹H NMR (C₆D₆, 300 MHz) δ ppm; 7.48 (d), another doublet partially obscured under solvent 7.02 (m), 5.53 (s), 4.72 (s), 3.25 (p), 2.72 (m), 2.31 (m), 2.83, 2.77, 2.74, 2.73 (s), 1.22 (d), 1.07 (d), -0.73(s, Hf-Me), -1.29 (s, Hf-Me).

Catalyst G: (CpMe₄)(1-*i*C₃H₇-C₉H₅)HfMe₂

[00149] 1-Isopropylindenyl lithium (Bradley et al, OM, 2004, 23, 5332) (2.0 g) was slurried in Et₂O (100 mL) and reacted with (CpMe₄H)HfCl₃ (5.0 g) for 12 hours. The solid product was filtered and washed with hexane (3.7 g). (CpMe₄)(1-*i*C₃H₇-C₉H₅)HfCl₂ ¹H NMR (C₆D₆, 300 MHz) δ ppm; 7.55, 7.41 (d), 6.95 (p), 6.22 (d), 5.51 (d), 4.96 (s), 3.72 (p), 1.93, 1.92, 1.83, 1.64 (s), 1.34, 1.11 (d).

[00150] The dichloride was slurried in toluene (50 mL) and reacted with 2 equivalents of MeMgI (3 M in Et₂O). The reaction was heated to 90°C for 2 hours and then cooled. The volatiles were removed. The crude mixture was extracted with hexane (2 x 40 mL), filtered and filtrate reduced to solid product in vacuo (3.1 g). ¹H NMR (C₆D₆, 300 MHz) δ ppm; -0.52, -1.46 Hf-Me.

- 5 [00151] TEAL-SiO₂: SiO₂ Davison 948 calcined at 600°C was slurried in hexane (30 mL) and reacted with Triethylaluminum (10 mL, 1.9 M in toluene) for 12 hours. The solid was filtered and washed with hexane (2 x 20 mL). After drying in vacuo the yield was 10.75 g TEAL-SiO₂.

Catalyst I:

- 10 [00152] TEAL-SiO₂ (2.0 g) was slurried in toluene (30 mL) and reacted with Triphenylcarbonium tetrakis(perfluorophenyl) borate (142 mg, Grace Davison) for 10 minutes. Metallocene E (56 mg) was added as a solution in toluene (5 mL) to the slurry and allowed to react for 12 hours. The supported catalyst was filtered, washed with hexane and dried in vacuo.

Catalyst K:

- 15 [00153] Similar to Catalyst I, Metallocene E was supported as described above except that 3.8 g TEAL-SiO₂, 215 mg of ionic activator 1, and 114 mg of metallocene E were used.

Polymerizations

- 20 [00154] Propylene oligomer batch or continuous polymerizations were carried out for this study using a 2L stirred autoclave reactor are described in Table 1. Catalyst solutions were prepared in a dry nitrogen purged Vacuum Atmospheres dry box by adding nearly equimolar (typically 1.00:1.05) quantities of metallocene and activator to 4 mL dry toluene in a 10 mL glass vial. The mixture was stirred for several minutes and then transferred to a clean, oven dried catalyst tube. An example of the basic polymerization procedure follows: 2 mL of 25 wt% tri-n-octyl-aluminum (0.037 g Al) in hexanes as scavenger and 100 mL propylene were added to the reactor. Next the reactor was heated to the selected polymerization temperature and catalyst/activator was flushed from the catalyst tube
- 25 into the reactor with 100 mL propylene. Additional propylene was optionally added for a total of up to 1000 mL. In some cases, hydrogen was also added from a ballast tank (see Table 2A). Hydrogen partial pressure was as high as 50 psig at the start of the run. Polymerization was carried out for 10 to 60 minutes, and then the reactor was cooled, depressurized, and opened. At this point the collected product typically contained some residual monomer. The residual monomer concentration in the
- 30 product was initially reduced by "weathering." In many cases the sample was heated in the oven under nitrogen purge or for a short time with applied vacuum. Some of the lowest molecular weight oligomer product may be lost along with the residual monomer. In some cases, residual monomer is still detected in the product in ¹H NMR spectras recorded at 30°C (but is not detected when spectra are recorded at 120°C). In the Tables below Polig means propylene oligomer, EP means propylene-

ethylene oligomer, T_p means polymerization temperature, P-time means polymerization time, Cat means catalyst, Act means activator, DP means degree of polymerization.

Table 1: Summary of Propylene Polymerizations

Example	Product	Cat	Act	Cat/Act (mg/mg)	Tp (° C)	P-time (min)	Yield (g)	Additional C3**
1#	Polig	A	4	30/60	90	10	25	***
2#	Polig	B	4	10/25	90	7	110	***
3#	Polig	A	4	30/60	140	10	25	***
4#	Polig	C	4	10/25	140	8	160	***
5#	Polig	B	4	4/12	145	7	140	***
6#	Polig	B	1	6/15	152	5	47	***
7#	Polig	B	1	6/15	130	10	30	***
8	Polig	D	4	6/13.1	132	10	5.7	***
9	Polig	E	4	10/25.7	132	10	19	***
10	Polig	E	4	10/25.7	100	12	31.9	100
11	Polig	E	4	10/25.7	80	12	52.5	100
12	Polig	E	4	10/25.7	80	27	142	400
13	Polig	E	4	10/25.7	60	10	65	***
14	Polig	E	4	12/30.8	75	40	242	500
21	Polig	E	1	10/17.9	132	10	17.9	***
22	Polig	E	1	10/17.9	80	12	46.2	100
23	Polig	E	4	10/25.7	80	27	~127	300
24	Polig	D	4	10/31.5	80	10	8.9	150
26	Polig	E	6	10/11.5	80	30	0	***
25^	Polig	K(150mg)			80	30	9.8	250
28^	Polig	I(210mg)			60	30	14.9	***
27	Polig	E	6	10/11.5	132	30	0	***
30	Polig	E	5	10/45.7	80	30	162	450
31	Polig	E	2	10/23.1	80	30	112	350
32	Polig	E	3	10/25.7	80	30	112	250
36	Polig	E	1	10/17.9	45	30	130	***
37	Polig	H	4	10/25	80	30	13.2	200
38	Polig	F	4	10/25	80	30	46.2	250
39	Polig	G	4	10/22.7	80	25	70	150
40	Polig	G	4	10/22.7	100	30	55.7	70
41	Polig	G	4	10/22.7	132	30	16.2	40
42	Polig	E	4	10/25.7	38	20	~200	***
44	Polig	E	4	10/25	60	30	~75	***

45	Polig	E	4	10/25	37	30	~85	***
46	Polig	E	4	10/25	100	30	36.7	80
47	Polig	E	4	10/25	132	30	~10	***
48	Polig	E	1	10/18	60	30	~110	***
49	Polig	E	1	10/18	80	30	~70	280
50	Polig	E	4	10/25	60	180	~200	***
51	Polig	E	1	10/18	60	120	~220	***

comparative, ^ supported, **Additional propylene added, *** Continuous run using continuous propylene feed from day tank

[00155] Propylene-ethylene co-oligomerizations, carried out for this study using a 2L stirred autoclave reactor, are described in Table 2. Catalyst solutions were prepared in a dry nitrogen purged Vacuum Atmospheres dry box by adding nearly equimolar (typically 1.00:1.05) quantities of metallocene and activator to 4 mL dry toluene in a 10 mL glass vial. The mixture was stirred for several minutes and then transferred to a clean, oven dried catalyst tube. An example of the basic polymerization procedure follows: 2 mL of 25 wt% tri-n-octyl-aluminum in hexanes as scavenger and 300 mL propylene were added to the reactor. Next the reactor was heated to appropriate polymerization temperature and catalyst/activator was flushed from the catalyst tube into the reactor with an additional 300 mL propylene. Ethylene was then added continuously throughout the reaction at partial pressures from less than 5 psi up to 220 psi. After a pre-determined reaction time, the reactor was cooled, depressurized, and opened. At this point the collected product typically contained some residual monomer. The residual monomer concentration in the product was initially reduced by “weathering.” In many cases the sample was heated in the oven under nitrogen purge or for a short time with applied vacuum. Some of the lowest molecular weight oligomer product may be lost along with the residual monomer. Note that catalyst productivities are 28 to 678 times higher than the productivities reported by in *Macromolecules* 2008 41, 559-567.

Table 2 Summary of Propylene-Ethylene Copolymerizations

Example	Catalyst/ Activator	Mole metallocene ^a	T _p , °C	Psig C ₂	Time, min	Yield, g	Productivity, g/mmol/hr
33	E/4	2.13E-05	65	20	10	320	90,122
35	E/4	4.26E-06	60	40	20	127	89,526
52	F/4	8.26E-06	60	40	20	240	87,297
53	F/4	8.26E-06	65	30	10	128	92,838
54	F/4	4.13E-06	60	20	10	178	258,206
55	F/1	2.06E-06	58	< 5	30	95	92,055
56	F/1	2.06E-06	70	< 5	30	87	84,303
57	F/1	6.19E-06	70	10	60	80	12,920
58	F/1	8.26E-06	68	30	10	158	114,597
59	F/1	4.13E-06	65	50	10	95	137,806
60	F/1	2.07E-06	55	220	10	108	313,329
61	F/1	4.15E-06	65	50	5	46	133,455

^a in all cases, slight molar excess (~5-10 mol%) of activator used with metallocene.

Table 2A: Propylene Polymerizations with Catalyst F in the Presence of Hydrogen

Ex	Act	Cat/Activator (mg/mg)	H ₂ , psi	Tp. (°C)	Time (min)	Yield (g)	Productivity g/mmol/hr
62	4	10 / 25	7	80	10	342	39768
63	4	5 / 12.5	7	27	60	348	13489
64	4	4 / 10	7	60	30	225	21803
65	4	4.5 / 11.25	7	40	45	428	24579
66	1	5 / 9	7	29	50	525	33915
67	1	2 / 3.5	7	60	60	165	22841
68	1	6 / 10.4	7	45	30	487	45375
69	1	2 / 3.5	7	40	10	1.5	2180
70	1	2 / 3.5	50	40	5	2.3	6689
71	1	4 / 7	7	50	10	140	101740
72	1	4 / 7	22	45	10	202	146770
73	1	4 / 7	50	42	5	30	43622
74	1	4 / 7	50	47	30	325	78731

5

Table 3: Characterization Data for Propylene Oligomers

Example	% Vinyls*	DP*	Mn*	Tg (°C)	Viscosity at 35°C (cps)	Refractive Index
1	3.35	12.55	526.91			
2	5.5	107.5	4516			

3	1.50	6.57	275.92			
4	28.7	86.1	3618			
5	12.6	24.2	1017			
6	1.94	6.54	274.51			
7	1.64	6.93	291.18			
8	14.19	8.23	345.51			
9	25.03	4.34	182.43			1.4240
10	41.47	6.89	289.26		3.5	
11	57.17	8.95	375.94			
12	55.74	9.01	378.28		16.0	
13	73.30	26.97	1132.69	-37.3		
14	69.63	14.40	604.75			
21	30.75	3.54	148.48			
22	54.24	7.80	327.72		37.3	1.4489
23	60.88	8.46	355.15			1.4534
24	24.72	46.04	1933.70	-56.9		
25	54.11	9.05	379.92			
28	63.3	17.48	734.1			
29	16.1	45.8	1923			
30	55.52	8.52	357.69			
31	57.49	8.54	358.70			
32	60.45	9.33	391.83			
36	62.37	68.17	2862.99	-16.7		
37	10.68	8.07	338.90			
38	97.20	4.62	194.04			1.4252
39	42.16	7.61	319.42			
40	27.06	4.68	196.63			1.4298
41	15.14	3.59	150.81			
42	74.12	106.5	4472.84			
44	97.48	7.12	299.02			
45	97.61	24.12	1013.02			
46	95.02	4.31	181.21			1.4367
47	88.73	3.79	159.25			
48	97.49	8.52	357.87			
49	97.85	4.68	196.41			1.4205
50	96.24	8.14	341.96			
51	97.13	8.24	346.28			1.4422
62	97.1	6.31	265			

63	96.5	22.49	945			
64	96.7	6.55	275			
65	98.2	13.59	570			
66	97.2	19.97	838			
67	98.0	6.21	261			
68	97.4	10.31	433			
71	98.0	6.79	285.4			
72	98.2	7.52	315.7			
73	96.7	10.56	443.5			
74	97.4	9.07	380.8			

% Vinyls = % allyl chain ends, * ¹H NMR, IBCE = isobutyl chain end.

Table 3A GPC-DRI(PP standard)

Ex.	H ₂ , psi	¹ H NMR	GPC-DRI (PP Std)		
			M _N	M _w	M _z
2	0	4516	3245	9600	21306
4	0	3617	3262	9584	22496
5	0	1017	576	2745	12604
13	0	1133	811	7546	675,306
24	0	1934	360	12,359	614,945
33	0	1283	947	3,703	10,279
35	0	4546	4,080	19,065	313,648
36	0	2863	2,075	13,793	1,541,001
42	0	4473	3,410	26,362	180,129
45	0	1013.02	504	2,409	9,196
63	0	945	468	1,736	4,143
64	7	275	106	265	611
65	7	570	255	850	1,883
66	7	838	389	1,810	4,557
67	7	261	98	198	431
68	7	433	183	538	1,142
71	7	285.4	134	395	1,676
72	50	315.7	153	443	1,600
73	7	443.5	102	288	1,143
74	22	380.8	156	564	1,440
52	0	773	378	2,277	22,624
53	0	929	466	9,804	53,617
54	0	795	315	3,577	38,176
55	0	974	651	3,290	23,906

56	0	490	294	1,292	9,395
57	0	112	490	5,208	31,162
58	0	1071	501	6,709	65,024
59	0	1580	633	11,053	118,559
60	0	4861	3,519	71,123	433,478
61	0	1877	900	16,764	348,185

Table 4: Properties of Propylene-Ethylene Copolymers

Sample	Mole fraction propylene in product*	Wt fraction propylene in product*	Tg (°C)	% vinyls*	DP*	Mn*
33	-	-	-45.6	82.5	30.6	1283
35	0.555	0.652	-53.1	84.1	108.2	4545
52	0.629	0.718	-88	95.9	18.4	773
53	0.447	0.578		97.2	22.1	929
54	0.501	0.606		96.4	18.9	795
55	0.428	0.529	-83	95.9	23.2	974
56	0.611	0.702		94.6	11.7	490
57	0.434	0.535		94.9	26.8	1124
58	0.378	0.472		94.8	25.5	1071
59	0.351	0.447		96.5	37.6	1580
60	0.124	0.176		76.4	115.7	4861
61	0.247	0.329		99.1	44.7	1877

* Calculated from ^1H NMR % Vinyls = % allyl chain ends

[00156] Examples 35 and 52-61 were characterized by ^{13}C NMR as described above then compared to the data in *Macromolecules* 2008 41, 559-567.

Table 5: Allyl chain ends in Propylene-Ethylene Co-oligomers

Source	Wt% ethylene	Mol% ethylene	% allyl chain ends
M-Tab 1†	0.0	0.00	100
M-Tab 1†	21.4	29.0	65.0
M-Tab 1†	29.9	39.0	60.0
M-Tab 1†	51.0	61.0	43.0
Coates Tab 1†	54.2	64.0	42.0
35	34.8	44.5	84.1
52	28.2	37.1	95.9
53	42.2	55.3	97.2
54	39.4	49.9	96.4
55	47.1	57.2	95.9

56	29.8	38.9	94.6
57	46.5	56.6	94.9
58	52.8	62.2	94.8
59	55.3	64.9	96.5
60*	82.4	87.6	76.4*
61	67.1	75.3	99.1

M-Tab is table 1 of † *Macromolecules* 2008 41, 559-567 * 10C exotherm

Table 6: percent Chain End Microstructures from ^{13}C NMR

Sample	Saturated End Groups *		Unsaturated End Groups		Init / Term
	IB-P	IB-E	Vinyl-P	Vinyl-E	
52	71.8	28.2	71.7	28.3	1.31
53	64.5	35.5	64.1	35.9	1.32
55	48.6	51.4	61.8	38.2	1.16
56	62.4	37.6	65.6	34.4	1.03

[00157] Saturated chain end microstructure analysis reveals the surprising result that propylene is nearly always the first monomer inserted following β -Methyl elimination or transfer involving a growing chain and/or incoming monomer, even in polymers containing up to 52 mol% ethylene.

Comparative Examples

[00158] Activator 7 is triphenylcarbonium perfluorotetraphenylborate and Activator 8 is dimethylanilinium perfluorotetranaphthylborate.

[00159] Polymerizations with catalyst J and Activators 1, 7 and 8 are carried out in the reactor described below at temperatures ranging from 70 to 130°C. Inlet propylene feed concentration is 3.5 to 4 M. Residence time for all runs is 5 min. Tri(n-octyl)aluminum (TNOAL) is used throughout as scavenger. Molar ratio of TNOAL to metallocene is ~20. The polymerizations are performed in a liquid filled, single-stage continuous reactor using mixed metallocene catalyst systems. The reactor is a 0.5-liter stainless steel autoclave reactor and is equipped with a stirrer, a water cooling/steam heating element with a temperature controller, and a pressure controller. Solvents, propylene, and comonomers (such as butene and hexene), if present, are first purified by passing through a three-column purification system. The purification system consists of an Oxiclear column (Model # RGP-R1-500 from Labeledar) followed by a 5A and a 3A molecular sieve columns. Purification columns were regenerated periodically whenever there is evidence of lower activity of polymerization. Both the 3A and 5A molecular sieve columns were regenerated in-house under nitrogen at a set temperature of 260°C and 315°C, respectively. The molecular sieve material was purchased from Aldrich. Oxiclear column was regenerated in the original manufacture. Purified ethylene from in-house supply is fed into the manifold then the reactor through a Brookfield mass flow controller. The ethylene is delivered as a gas solubilized in the chilled solvent/monomer mixture. The purified solvents and

monomers are then chilled to about -15°C by passing through a chiller before fed into the reactor through a manifold. Solvent and monomers are mixed in the manifold and fed into reactor through a single tube. All liquid flow rates are measured using Brooksfield mass flow meters or Micro-Motion Coriolis-type flow meters. The polymerization conditions, % conversion of feed, catalyst productivity and characterization data are listed in the table below and Figure 3.

Ex.	Cat	Act	Tp, $^{\circ}\text{C}$	Tm, $^{\circ}\text{C}$	ΔH_f , J/g	%Conv ersion*	Productivity $\times 10^6$ g/mol/ min	Vinyl/ 1000C	Vinylidene/ 1000C	Vinylene/ 1000C	Mn x 1000 ^1H NMR	Mn x 1000 GPC
C1	J	1	125	131.93	82.65	94.07	46.5	----	----	----	----	----
C2	J	1	120	134.32	87.26	95.68	47.3	0.93	1.14	0	6.76	6.69
C3	J	1	115	136.91	84.17	98.11	48.6	0.51	0.82	0.09	9.86	9.82
C4	J	1	110	140.77	90.01	98.79	48.9	0.78	1.21	0.11	6.67	9.36
C5	J	1	105	142.31	92.33	100.61	46.9	----	----	----	----	----
C6	J	1	100	145.07	97.75	100.71	66.2	----	----	----	----	----
C7	J	1	95	146.07	96.40	100.64	66.2	0.24	0.43	0.08	18.7	19.74
C8	J	1	90	148.15	103.70	100.39	66.0	0.21	0.28	0.15	18.9	32.11
C9	J	7	130	127.14	78.58	65.68	1.83	0.99	1.11	0.01	6.1	6.0
C10	J	7	120	132.64	84.16	67.36	32.4					
C11	J	7	110	138.27	91.6	70.14	33.3	0.46	0.40	0.01	14.4	9.0
C12	J	7	100	140.83	127.15	72.61	34.6					
C13	J	7	90	145.42	95.89	73.54	36.3	0.17	0.35	0.00	23.7	25.0
C14	J	7	80	151.24	103.60	73.57	36.3					
C15	J	8	130	132.33	89.6	57.93	28.6	0.78	0.47	0.03	10.5	8.7
C16	J	8	120	137.18	87.8	60.79	30.0					
C17	J	8	110	143.44	96.72	62.04	30.6	0.37	0.19	0.00	23.7	24.3
C18	J	8	100	146.0	100.70	62.46	30.8					
C19	J	8	90	152.85	93.78	63.43	31.3	0.25	0.22	0.01	29.2	56.6

Functionalization

Example A

10 [00160] In separate runs, each of the (co)polymers prepared in the Examples above and pulverized

maleic is charged at a ratio of 1.6 moles of maleic anhydride to one mole of (co)polymer under dry nitrogen and at atmospheric pressure to a 100 ml pressure reactor equipped with a stirrer and a thermocouple and heated by means of an electric heating mantle. The reaction mixture is heated to 70°C, after which the reactor is gently purged by bubbling dry nitrogen through the liquid reaction mixture for 15 min. The purging is then terminated and the reactor sealed. The reactor temperature is then raised to a temperature of 220°C and is maintained at that temperature for 6 hours, while stirring. The reaction is then terminated by cooling the reaction mixture to about 60°C, after which the liquid mixture is transferred to a glass beaker. Unreacted maleic anhydride is stripped off by passing dry nitrogen gas through the liquid at 140°C. The liquid product so prepared in each run is expected to contain (co)polymer functionalized with succinic acid.

Example B

[00161] In separate runs, dispersant materials are prepared utilizing liquid products as prepared in Example A. The succinic acid anhydride substituted polymers are dissolved in an equal amount by weight of mineral oil (S150NL). To the polymer solution is added tetraethylene pentamine (TEPA), and the mixture is heated to 140°C under nitrogen while stirring for about 2 to 4 hours. The molar ratio of total polymer to polyamine in terms of succinic acid equivalents to TEPA charged is 2 to 1.

Example C: Preparation of a Mannich Base Dispersant Additive

Alkylation of the Phenol

[00162] In separate runs, about 50 grams of each of the (co)polymers prepared in the Examples above are dissolved in 100 ml of chlorobenzene and added to a solution containing about 10 gram of phenol in 300 ml of chlorobenzene. While stirring at room temperature under nitrogen, 0.5 g of BF₃ gas is bubbled into the charged solution, and the reaction mixture is stirred while the temperature is increased to 50°C for about one hour. The reaction mixture is then neutralized with gaseous ammonia until a neutral pH is obtained. The solution is filtered and the filtrate is heated to 150°C to distill off the solvent and excess phenol.

Mannich Base Condensation

[00163] To a 500 ml round-bottomed reaction flask is charged 25 grams of S150NL mineral oil in which is dissolved 25 grams of (co)polymer substituted phenol as just prepared. 0.61 g of 1,6-hexanediamine and 0.35 g of formaldehyde are then added to the flask at 30°C under nitrogen. The mixture is heated to 115°C and kept at that temperature for 1 hour, after which the temperature of the reaction mixture is raised to 130°C and maintained at that temperature for 45 min, all the while sweeping the reaction flask with dry nitrogen gas. The stripped reaction mixture is then cooled to room temperature, diluted with 100 ml of heptane, and filtered. The filtrate is then stripped at 130°C with dry nitrogen gas to remove heptane.

EXAMPLE 9

Example C: Oxidized (Co)polymer

[00164] In separate runs, 1500-ml glass reactor equipped with gas inlet and outlet tubes, a thermometer, and a stirrer is charged with 800 grams of (co)polymer as prepared in the examples
5 above. The temperature is raised to 200°C while stirring the (co)polymer. Dry air is bubbled through the (co)polymer via the inlet tube for 6 hours, all the while maintaining the temperature at 200°C. At the end of 6 hours, the air flow is terminated, and nitrogen is bubbled through the copolymer while cooling the reactor to room temperature.

Preparation of a Nitrogen-Containing Dispersant from Oxidized EB Copolymer

10 [00165] A nitrogen-containing dispersant material is prepared utilizing oxidized (co)polymer product as prepared above. The oxidized (co)polymer is dissolved in an equal amount by weight of S150NL mineral oil. To the polymer solution is added tetraethylene pentamine (TEPA), and the mixture is heated to 140°C under nitrogen while stirring for about 2 to 4 hours. The molar ratio of total polymer to polyamine in terms of equivalents of carboxyl groups in the oxidized EB copolymer
15 to TEPA charged is 2 to 1.

[00166] All documents described herein are incorporated by reference herein, including any priority documents and/or testing procedures to the extent they are not inconsistent with this text. As is apparent from the foregoing general description and the specific embodiments, while forms of the invention have been illustrated and described, various modifications can be made without departing
20 from the spirit and scope of the invention. Accordingly, it is not intended that the invention be limited thereby. Likewise, the term "comprising" is considered synonymous with the term "including" for purposes of Australian law.

CLAIMS

What is claimed is:

1. A functionalized co-oligomer comprising the reaction product of 1) a heteroatom containing group, and 2) a co-oligomer having an Mn of 300 to 30,000 g/mol (measured by ^1H NMR) and
5 comprising 10 to 90 mol% propylene and 10 to 90 mol% of ethylene, wherein the oligomer has at least X% allyl chain ends (relative to total unsaturations) prior to functionalization, where: 1) $X = (-0.94(\text{mol\% ethylene incorporated}) + 100)$, when 10 to 60 mol% ethylene is present in the co-oligomer, and 2) $X = 45$, when greater than 60 and less than 70 mol% ethylene is present in the co-oligomer, and 3) $X = (1.83 * (\text{mol\% ethylene incorporated}) - 83)$, when 70 to 90 mol% ethylene is
10 present in the co-oligomer, where the heteroatom containing group comprises where the functional group comprises one or more heteroatoms selected from the group consisting of P, O, S, N, Br, Cl, F, I and or B, and the functionalized co-oligomer has 0.75 to 1.10 functional groups per chain.
2. The functionalized co-oligomer of claim 1 wherein the co-oligomer has more than 90% allyl chain ends (relative to total unsaturations) prior to functionalization.
- 15 3. The functionalized co-oligomer of claim 1 wherein the co-oligomer comprises from 15 to 95 wt% ethylene and has more than 80% allyl chain ends (relative to total unsaturations) prior to functionalization.
4. The functionalized co-oligomer of claim 1 wherein the co-oligomer comprises from 30 to 95 wt% ethylene and has more than 70% allyl chain ends (relative to total unsaturations) prior to
20 functionalization.
5. The functionalized co-oligomer of claim 1 wherein the co-oligomer comprises from 30 to 95 wt% ethylene and has more than 90% allyl chain ends (relative to total unsaturations) prior to functionalization.
6. The functionalized co-oligomer of claim 1, wherein $F + VI^* + VE^* \geq (0.50(VI + VE))$,
25 wherein VI is the number of vinyl groups/1000 Carbons and VE is number of vinylidene groups/1000 Carbons (VE^*) for the unfunctionalized oligomer, VI^* is the number of vinyl groups/1000 Carbons and VE^* is the number of vinylidene groups/1000 carbons for the functionalized oligomer, and F is the number of functional groups per 1000 carbons.
7. The functionalized co-oligomer of claim 1, wherein the functionalized co-oligomer has an Mn
30 of about 500 to about 7,500 g/mol, an Mw of 1,000 to about 20,000 g/mol, and an Mz of about 1400 to about 150,000 g/mol.
8. A functionalized propylene oligomer, comprising the reaction product of 1) a heteroatom containing group and 2) an oligomer comprising more than 90 mol% propylene and less than 10 mol% ethylene wherein the oligomer has: at least 93% allyl chain ends, a number average molecular
35 weight (Mn) of about 500 to about 20,000 g/mol, an isobutyl chain end to allylic vinyl group ratio of

0.8:1 to 1.35:1.0, and less than 100 ppm aluminum, where the heteroatom containing group comprises one or more heteroatoms selected from the group consisting of P, O, S, N, Br, Cl, F, I and or B, and the functionalized oligomer has 0.75 to 1.10 functional groups per chain.

9. A functionalized propylene oligomer, comprising: the reaction product of 1) a heteroatom containing group, and 2) an oligomer comprising at least 50 mol% propylene and from 10 to 50 mol% ethylene, wherein the oligomer has: at least 90% allyl chain ends, an Mn of about 150 to about 10,000 g/mol, and an isobutyl chain end to allylic vinyl group ratio of 0.8:1 to 1.2:1.0, wherein monomers having four or more carbon atoms are present at from 0 to 3 mol%, where the heteroatom containing group comprises one or more heteroatoms selected from the group consisting of P, O, S, N, Br, Cl, F, I and or B, and the functionalized co-oligomer has 0.75 to 1.10 functional groups per chain.

10. A functionalized propylene oligomer, comprising: the reaction product of 1) a functional group, and 2) an oligomer comprising at least 50 mol% propylene, from 0.1 to 45 mol% ethylene, and from 0.1 to 5 mol% C₄ to C₁₂ olefin, wherein the oligomer has: at least 90% allyl chain ends, an Mn of about 150 to about 10,000 g/mol, and an isobutyl chain end to allylic vinyl group ratio of 0.8:1 to 1.35:1.0, where the heteroatom containing group comprises one or more heteroatoms selected from the group consisting of P, O, S, N, Br, Cl, F, I and or B, and the functionalized co-oligomer has 0.75 to 1.10 functional groups per chain.

11. A functionalized propylene oligomer, comprising: the reaction product of 1) a heteroatom containing group, and 2) an oligomer comprising at least 50 mol% propylene, from 0.1 to 45 wt% ethylene, and from 0.1 to 5 mol% diene, wherein the oligomer has: at least 90% allyl chain ends, an Mn of about 150 to about 10,000 g/mol, and an isobutyl chain end to allylic vinyl group ratio of 0.7:1 to 1.35:1.0, where the heteroatom containing group comprises one or more heteroatoms selected from the group consisting of P, O, S, N, Br, Cl, F, I and or B, and the functionalized co-oligomer has 0.75 to 1.10 functional groups per chain.

12. A functionalized homo-oligomer, comprising the reaction product of 1) a heteroatom containing group and 2) a homo-oligomer of propylene, wherein the oligomer has: at least 93% allyl chain ends, an Mn of about 500 to about 20,000 g/mol, an isobutyl chain end to allylic vinyl group ratio of 0.8:1 to 1.2:1.0, and less than 1400 ppm aluminum, where the heteroatom containing group comprises one or more heteroatoms selected from the group consisting of P, O, S, N, Br, Cl, F, I and or B, and the functionalized co-oligomer has 0.75 to 1.10 functional groups per chain.

13. The functionalized co-oligomer of claim 1, wherein $F + VI^* + VE^* \geq (0.80(VI + VE))$, wherein VI is the number of vinyl groups/1000 carbons and VE is number of vinylidene groups/1000 carbons for the unfunctionalized oligomer, VI* is the number of vinyl groups/1000 carbons and VE* is the number of vinylidene groups/1000 carbons for the functionalized oligomer, and F is the number of functional groups per 1000 carbons.

14. The functionalized oligomer of any of the above claims, wherein the oligomer is a liquid at 25°C.

15. The functionalized oligomer of any of claims 1-14 wherein the heteroatom containing group comprises sulfonates, amines, aldehydes, alcohols, or acids.

16. The functionalized oligomer of any of claims 1-14 wherein the heteroatom containing group comprises an epoxide, succinic acid, maleic acid or maleic anhydride.


17. The functionalized oligomer of any of claims 1-14 wherein the heteroatom containing group comprises one or more of acids, esters, anhydrides, acid-esters, oxycarbonyls, carbonyls, formyls, formylcarbonyls, hydroxyls, and acetyl halides.


18. The functionalized oligomer of any of claims 1-17 wherein the functionalized oligomer has an Mn that is up to 15% greater than the Mn of the starting (co)oligomer.

19. The functionalized oligomer of any of claims 1-17 wherein $F + VI^* + VE^* \geq (0.85(VI + VE))$, wherein VI is the number of vinyl groups/1000 carbons and VE is number of vinylidene groups/1000 carbons for the unfunctionalized oligomer, VI* is the number of vinyl groups/1000 carbons and VE* is the number of vinylidene groups/1000 carbons for the functionalized oligomer, and F is the number of functional groups per 1000 carbons.

20. A process to make the functionalized co-oligomer of any of the above claims, comprising 1) a first homogenous process for making a propylene co-oligomer, said first process having productivity of at least 4500 g/mmol/hr, wherein the first process comprises:

contacting, at a temperature of from 35°C to 150°C, propylene, 0.1 to 70 mol% ethylene and from 0 to about 5 wt% hydrogen in the presence of a catalyst system comprising an activator and at least one metallocene compound represented by at least one of the formulae:





where:

Hf is hafnium;

each X is, independently, selected from the group consisting of hydrocarbyl radicals having from 1 to 20 carbon atoms, hydrides, amides, alkoxides, sulfides, phosphides, halogens, dienes, amines, phosphines, ethers, and a combination thereof, (two X's may form a part of a fused ring or a ring system;

each Q is, independently carbon or a heteroatom;

each R¹ is, independently, a C₁ to C₈ alkyl group, R¹ may be the same or different as R²;

each R² is, independently, a C₁ to C₈ alkyl group;

each R³ is, independently, hydrogen, or a substituted or unsubstituted hydrocarbyl group having from 1 to 8 carbon atoms, provided however that at least three R³ groups are not hydrogen;

each R⁴ is, independently, hydrogen or a substituted or unsubstituted hydrocarbyl group, a heteroatom or heteroatom containing group;

R⁵ is hydrogen or a C₁ to C₈ alkyl group;

R⁶ is hydrogen or a C₁ to C₈ alkyl group;

each R⁷ is, independently, hydrogen, or a C₁ to C₈ alkyl group, provided however that at least seven R⁷ groups are not hydrogen;

N is nitrogen;

T is a bridge;


each R^a is, independently, hydrogen, halogen or a C₁ to C₂₀ hydrocarbyl, and two R^a can form a cyclic structure including aromatic, partially saturated, or saturated cyclic or fused ring system;

and further provided that any two adjacent R groups may form a fused ring or multicenter fused ring system where the rings may be aromatic, partially saturated or saturated, and

2) a second functionalizing process comprising contacting the co-oligomer produced in the first process with a heteroatom containing group.

21. A process to make a functionalized homo-oligomer, comprising 1) a first homogenous process for making a propylene homo-oligomer, said first process having productivity of at least 4500 g/mmol/hour, wherein the first process comprises:

5 0 to about 5 wt% hydrogen in the presence of a catalyst system comprising an activator and at least one metallocene compound represented by the formulae:



10 where

Hf is hafnium;

each X is, independently, selected from the group consisting of hydrocarbyl radicals having from 1 to 20 carbon atoms, hydrides, amides, alkoxides, sulfides, phosphides, halogens, dienes, amines, phosphines, ethers, and a combination thereof, (two X's may form a part of a fused ring or a ring system;

each Q is, independently carbon or a heteroatom;

each R¹ is, independently, a C₁ to C₈ alkyl group, R¹ may be the same or different as R²;

each R² is, independently, a C₁ to C₈ alkyl group;

20 each R³ is, independently, hydrogen, or a substituted or unsubstituted hydrocarbyl group having from 1 to 8 carbon atoms, provided however that: 1) all five R³ groups are methyl, or 2) four R³ groups are not hydrogen and at least one R³ group is a C₂ to C₈ substituted or unsubstituted hydrocarbyl;

each R⁴ is, independently, hydrogen or a substituted or unsubstituted hydrocarbyl group, a heteroatom or heteroatom containing group;

R⁵ is hydrogen or a C₁ to C₈ alkyl group;

R⁶ is hydrogen or a C₁ to C₈ alkyl group;

each R⁷ is, independently, hydrogen, or a C₁ to C₈ alkyl group, provided however that at least seven R⁷ groups are not hydrogen;

N is nitrogen;

5 T is a bridge;

each R^a, is independently, hydrogen, halogen or a C₁ to C₂₀ hydrocarbyl, and two R^a can form a cyclic structure including aromatic, partially saturated, or saturated cyclic or fused ring system;

and further provided that any two adjacent R groups may form a fused ring or multicenter fused ring system where the rings may be aromatic, partially saturated or saturated, and

10 2) a second functionalizing process comprising contacting the homo-oligomer produced in the first process with a heteroatom containing group.

22. The process of claim 20 or 21 where in the heteroatom containing group comprises one or more heteroatoms selected from the group consisting of P, O, S, N, Br, Cl, F, I and or B.

15 23. The process of claim 20, 21 or 22, wherein the activator comprises one or more non-coordinating anions.

24. The process of any of claims 20 to 23 wherein the catalyst system comprises one or more of

(pentamethylcyclopentadienyl)(1,3 dimethylindenyl) hafnium dimethyl,

(pentamethylcyclopentadienyl)(1,3 dimethylindenyl) hafnium dichloride,

(1,3-Dimethylindenyl)(pentamethylcyclopentadienyl) hafnium dimethyl,

20 (1,3,4,7-Tetramethylindenyl)(pentamethylcyclopentadienyl) hafniumdimethyl,

(1,3-Dimethylindenyl)(tetramethylcyclopentadienyl) hafniumdimethyl,

(1,3-Diethylindenyl)(pentamethylcyclopentadienyl) hafniumdimethyl,

(1,3-Dipropylindenyl)(pentamethylcyclopentadienyl) hafniumdimethyl,

(1-Methyl,3-propylindenyl)(pentamethylcyclopentadienyl) hafniumdimethyl,

25 (1,3-Dimethylindenyl)(tetramethylpropylcyclopentadienyl) hafniumdimethyl,

(1,2,3-Trimethylindenyl)(pentamethylcyclopentadienyl) hafniumdimethyl,

(1,3-Dimethylbenzindenyl)(pentamethylcyclopentadienyl) hafniumdimethyl,

(2,7-Bis t-butylfluorenyl)(pentamethylcyclopentadienyl) hafniumdimethyl,

(9-Methylfluorenyl)(pentamethylcyclopentadienyl) hafniumdimethyl,

30 (2,7,9-Trimethylfluorenyl)(pentamethylcyclopentadienyl) hafniumdimethyl,

μ-Dihydrosilyl-bis(tetramethylcyclopentadienyl)Hafniumdimethyl,

μ-Dimethylsilyl(tetramethylcyclopentadienyl)(3-propyltrimethylcyclopentadienyl) hafniumdimethyl,

μ-Dicyclopropylsilyl(bis tetramethylcyclopentadienyl)hafnium dimethyl.

(1,3-Dimethylindenyl)(pentamethylcyclopentadienyl) hafniumdihalide,

35 (1,3,4,7-Tetramethylindenyl)(pentamethylcyclopentadienyl) hafniumdihalide,

- (1,3-Dimethylindenyl)(tetramethylcyclopentadienyl) hafniumdihalide,
 (1,3-Diethylindenyl)(pentamethylcyclopentadienyl) hafniumdihalide,
 (1,3-Dipropylindenyl)(pentamethylcyclopentadienyl) hafniumdihalide,
 (1-Methyl,3-propyllindenyl)(pentamethylcyclopentadienyl) hafniumdihalide,
 5 (1,3-Dimethylindenyl)(tetramethylpropylcyclopentadienyl) hafniumdihalide,
 (1,2,3-Trimethylindenyl)(pentamethylcyclopentadienyl) hafniumdihalide,
 (1,3-Dimethylbenzindenyl)(pentamethylcyclopentadienyl) hafniumdihalide,
 (2,7-Bis t-butylfluorenyl)(pentamethylcyclopentadienyl) hafniumdihalide,
 (9-Methylfluorenyl)(pentamethylcyclopentadienyl) hafniumdihalide,
 10 (2,7,9-Trimethylfluorenyl)(pentamethylcyclopentadienyl) hafniumdihalide,
 μ -Dihydrosilyl-bis(tetramethylcyclopentadienyl)Hafniumdimethyl,
 μ -Dimethylsilyl(tetramethylcyclopentadienyl)(3-propyltrimethylcyclopentadienyl) hafniumdihalide,
 and
 μ -Dicyclopropylsilyl(bis tetramethylcyclopentadienyl)hafnium dihalide.
- 15 25. The process of claim 20 to 24 wherein $F + VI^* + VE^* \geq (0.80(VI + VE))$, wherein VI is the number of vinyl groups/1000 carbons and VE is number of vinylidene groups/1000 Carbons for the unfunctionalized oligomer, VI* is the number of vinyl groups/1000 carbons and VE* is the number of vinylidene groups/1000 carbons for the functionalized oligomer, and F is the number of functional groups per 1000 carbons.