

METHOD AND APPARATUS FOR MAKING CRYSTALLINE POLYMERIC
PELLETS AND GRANULES

RELATED APPLICATION

5 This application is entitled to and hereby
claims the priority of co-pending U.S. provisional
application Serial No. 60/684,556, filed May 26,
2005.

10 FIELD OF THE INVENTION

 The present invention generally relates to
a method and apparatus for underwater pelletizing and
subsequent drying of polymer pellets with an
increased level of crystallinity. More specifically,
15 the present invention relates to a method and
apparatus for pelletizing polyesters, polyamides,
polycarbonates, thermoplastic polyurethanes, and
their respective copolymers, underwater with
subsequent drying of those pellets and granules in a
20 manner such that crystallization of those pellets or
granules is self-initiated. The pelletization and
drying process described herein produces pellets and
granules having a desired level of crystallinity
rather than an amorphous structure.

25 The present invention expands upon the
disclosures of pending U.S. applications, Serial Nos.
10/717,630 and 10/954,349, filed November 21, 2003
and October 1, 2004, respectively, which are owned by
Gala Industries, Inc. of Eagle Rock, Virginia
30 (hereinafter Gala), the assignee of the present
invention and application. The disclosures of the
aforesaid pending U.S. applications are expressly
incorporated in this application by reference as if
fully set forth herein and the aforesaid applications
35 are hereinafter referred to as "the Gala
applications".

BACKGROUND OF THE INVENTION

The following U.S. patents and published patent applications include disclosures which may be relevant to the present invention and are expressly incorporated by reference in this application as if fully set forth herein:

	<u>Number</u>	<u>Inventors</u>
	5,563,209	Schumann et al
10	6,706,824	Pfaendner et al
	5,648,032	Nelson et al
	6,762,275	Rule et al
	6,790,499	Andrews et al
	6,344,539	Palmer
15	6,518,391	McCloskey et al
	5,663,281	Brugel
	6,455,664	Patel et al
	6,740,377	Pecorini et al
	5,750,644	Duh
20	6,121,410	Gruber et al
	6,277,951	Gruber et al
	4,064,112	Rothe et al
	4,161,578	Herron
	5,412,063	Duh et al
25	5,532,335	Kimball et al
	5,708,124	Al Ghatta et al
	5,714,571	Al Ghatta et al
	5,744,571	Hilbert et al
	5,744,572	Schumann et al
30	6,113,997	Massey et al
	6,159,406	Shelby et al
	6,358,578	Otto et al
	6,403,762	Duh
	5,864,001	Masse et al
35	6,534,617	Batt et al
	6,538,075	Krech et al
	2005/0049391	Rule et al

2005/0056961 Bonner

SUMMARY OF THE INVENTION

The present invention is directed to a
5 pelletizing system that produces polymeric pellets
underwater that retain sufficient latent heat to
self-initiate the crystallization process and
ultimately provide sufficient crystalline structure
without requirement for an additional heating step
10 for the polymeric pellets and granules prior to
additional processing. The Gala applications have
demonstrated the effectiveness of this elevated heat
condition on poly(ethylene terephthalate) or PET and
copolymers made therefrom. It has been discovered
15 that other polymers which can be crystallized when
subjected to analogous elevated heat conditions
benefit from the reduction of the residence time of
the pellets and granules in the water slurry, leaving
sufficient heat in the pellets and granules during
20 the drying stage to allow crystallization to initiate
within the pellets and granules. These polymers fall
into the broad category of polymers identified herein
as "crystallizing polymers".

To accomplish the self-initiated crystallization,
25 it has been found that the pellets must be separated
from the water as quickly as possible with
significant increase in the speed with which they
flow from the exit of the underwater pelletizer and
into and through the drying apparatus. Such pellets
30 exit the dryer retaining much of their latent heat
and can be transported on conventional vibrating
conveyors or similar vibratory or other handling
equipment such that with the additional time the
desired crystallinity is achieved. Storage of the hot
35 pellets in conventional heat retaining containers or
heat insulating containers is included in the instant
invention that provide time to complete the desired

level of crystallization. The desired crystallization is at least sufficient to avoid agglomeration of the pellets and granules when subjected to additional processing.

5 The separation of the pellets and granules from the water and subsequent increase of the pellet speed to the drying apparatus is accomplished in accordance with the same general procedures and apparatus disclosed for PET and copolymers in the Gala
10 applications. Once the cut pellets and granules leave the underwater pelletizer water box in the water slurry, air or other suitable inert gas is injected into the transport pipe leading from the water box to the drying apparatus. The injected air serves to
15 aspirate the water into vapor effectively separating it from the pellets and granules and further increases the speed of transport of the pellets to and ultimately through the dryer. This increase in transport speed is sufficiently rapid to allow the
20 pellet to remain at a temperature hot enough to initiate the crystallization process inside the pellets and granules which may be amorphous upon exiting the centrifugal dryer. Other conventional methods of drying the pellet with comparable
25 efficiency may be employed by one skilled in the art and are included herein by reference.

To achieve aspiration of the water and increase the transport speed from the exit of the pelletizer waterbox to the dryer, the air injected must be at a
30 very high velocity. In particular, the volume of the injected air should preferably be at least 100 cubic meters per hour based on injection through a valve into a 1.5 inch diameter pipe. This flow volume will vary in accordance with throughput volume, drying
35 efficiency, and pipe diameter as will be understood by one skilled in the art. Nitrogen or other inert gas may be used instead of air. Other methods

providing comparable separation of the liquid water from the pellets with acceleration of the pellet to and through the dryer may be employed by one skilled in the art and are included herein by reference.

5 The rate of the air injection into the slurry piping is preferably regulated through use of a ball valve or other valve mechanism located after the air injection point. Regulation through this valve mechanism allows more control of the residence time
10 for the pellets and granules in the transport pipe and drying apparatus and serves to improve the aspiration of the pellet/water slurry. Vibration is reduced or eliminated in the transport pipe by use of the valve mechanism after the air injection point as
15 well.

Regulation of the air injection provides the necessary control to reduce the transport time from the exit of the pelletizer waterbox through the dryer allowing the pellets to retain significant latent
20 heat inside the pellets. Larger diameter pellets do not lose the heat as quickly as do smaller diameter pellets and therefore can be transported at lower velocity than the smaller pellets. Comparable results are achieved by increasing the air injection velocity
25 as pellet diameter decreases as will be understood by one skilled in the art. Reduction of the residence time between the pelletizer waterbox and the dryer exit leaves sufficient heat in the pellets to achieve the desired crystallization. The retention of heat
30 inside the pellet is enhanced through use of a heat-retaining vibrating conveyor following pellet release from the dryer and/or through the use of conventional storage containers or heat insulating containers.

Transportation times on the vibrating conveyor
35 are disclosed in the Gala applications to be effective from 20 to 90 seconds, and have been found to be particularly effective from 30 to 60 seconds.

This time frame should be effective for the polymers herein described. Crystallization of 30% or greater, preferably 35% or greater, and most preferably 40% or greater, may be achieved by the process described
5 herein. Variation of the residence times for polymer and polymer blends may be adjusted as needed to optimize results for the particular formulation and desired level of crystallinity as will be understood by one skilled in the art. Additional heating steps
10 are eliminated through use of the process described herein.

Accordingly, it is an object of the present invention to provide a method and apparatus for processing crystallizing polymers in an underwater
15 pelletizing system which can produce crystallization in the polymer pellets that exit from the dryer.

It is another object of the present invention to provide a method and apparatus for producing crystallization in crystallizing polymer pellets
20 utilizing an underwater pelletizing system without the necessity of an expensive secondary heating stage to convert amorphous polymer pellets to crystalline polymer pellets.

It is a further object of the present invention
25 to provide a method and apparatus for the underwater pelletizing of crystallizing polymers in which an inert gas is injected into the water and pellet slurry exiting the pelletizer to produce a water vapor mist form of slurry handling, thereby providing
30 better heat retention in the transported pellets.

A still further object of the present invention is to provide a method and apparatus for underwater pelletizing of crystallizing polymers in accordance with the preceding object in which the pellets are
35 rapidly transported through the equipment through the injection of air at a flow rate of at least 100 m³/hour, to about 175 m³/hour or more, so that the

residence time of the pellets before exiting the dryer is sufficiently reduced to generate crystallization on the order of 30% - 40% of total (100%) crystallization.

5 It is yet another object of the present invention to provide a method and apparatus for producing crystallizing polymer pellets using an underwater pelletizing system in which the pellets exiting the dryer have sufficient heat remaining inside the
10 pellets for at least 35% total crystallization of the pellets to occur without subsequent heating.

 It is still a further object of the present invention to provide an underwater pelletizing method and apparatus for producing crystallizing polymer
15 pellets in which the residence time of the pellets from the time of extrusion at the die face until exit from the centrifugal dryer is reduced to less than about one second by gas injection into the slurry line from the pelletizer to the dryer.

20 A still further object of the present invention is to provide an underwater pelletizing method and apparatus for producing crystallizing polymer pellets in accordance with the preceding object in which the residence time is regulated using a valve mechanism
25 for improved pressurization of the water vapor mist downstream of the valve in the slurry line.

 It is another object of the present invention to provide an underwater pelletizing system in which the hot pellets exiting the dryer are carried on a
30 vibrating conveyor or other vibrating or handling equipment to achieve virtually uniform crystallization throughout a given output pellet volume.

 Yet a further object of the present invention is
35 to expand the scope of the polymers and copolymers for which the apparatus and method of the Gala

applications can achieve polymer self-initiated crystallization.

These together with other objects and advantages which will become subsequently apparent reside in the details of construction and operation of the invention as more fully hereinafter described and claimed, reference being had to the accompanying drawings forming a part hereof, wherein like numerals refer to like parts throughout.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a schematic illustration of an underwater pelletizing system, including an underwater pelletizer and centrifugal dryer manufactured and sold by Gala with air injection and vibrating conveyor in accordance with the present invention.

Figure 2a is a schematic illustration of the side view of the vibrating conveyor of Figure 1.

Figure 2b is a schematic illustration of the end view of the vibrating conveyor of Figure 1.

Figure 3 illustrates the components of the underwater pelletizing system shown in Figure 1 during a bypass mode when the process line has been shut down.

Figure 4 is a schematic illustration showing the method and apparatus for air or other inert gas injection into the slurry line from the pelletizer to the dryer in accordance with the present invention.

Figure 5 is a schematic illustration showing a preferred method and apparatus for inert gas injection into the slurry line from the pelletizer to the dryer including an expanded view of the ball valve in the slurry line.

Figure 6 is a schematic illustration showing an underwater pelletizing system including

crystallization and dryer marketed and sold by Gala for use with thermoplastic polyurethane processing.

Figure 7 is a schematic illustration of the crystallization portion of the system shown in Figure 6.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Preferred embodiments of the invention are explained in detail. It is to be understood that the invention is not limited in its scope to the details of construction, arrangement of the components, or chemical components set forth in the description which follows or as illustrated in the drawings. The embodiments of the invention are capable of being practiced or carried out in various ways and are contained within the scope of the invention.

Descriptions of the embodiments which follow utilize terminology included for clarification and are intended to be understood in the broadest meaning including all technical equivalents by those skilled in the art. The polymer components set forth in this invention provide those of ordinary skill in the art with detail as to the breadth of the method as disclosed and is not intended to limit the scope of the invention.

Polyesters which qualify as crystallizing polymers for the present invention are of the general structural formula

(OR.sub.1.O).sub.x. [(C=O)R.sub.2.(C=O)].sub.y and/or
[(C=O)R.sub.1.O].sub.x. [(C=O)R.sub.2.O].sub.y.

R.sub.1 and R.sub.2 herein described include aliphatic, cycloaliphatic, aromatic and pendant substituted moieties including but not limited to halogens, nitro functionalities, alkyl and aryl groups, and can be the same or different. More preferably, polyesters herein described include poly(ethylene terephthalate) or PET,

poly(trimethylene terephthalate) or PTT,
poly(butylene terephthalate) or PBT, poly(ethylene
naphthalate) or PEN, polylactide or PLA, and
poly(alpha-hydroxyalkanoates) or PHA.

5 Polyamides which qualify as crystallizing
polymers for the present invention are of the general
structural formula

$[N(H,R)R_{\text{sub.1}}N(H,R)]_{\text{sub.x}}[(C=O)R_{\text{sub.2}}(C=O)]_{\text{sub.y}}$ and/or

10 $[(C=O)R_{\text{sub.1}}N(H,R)]_{\text{sub.x}}[(C=O)R_{\text{sub.2}}N(H,R)]_{\text{sub.y}}$. $R_{\text{sub.1}}$ and $R_{\text{sub.2}}$ herein described include
aliphatic, cycloaliphatic, aromatic and pendant
substituted moieties including but not limited to
halogens, nitro functionalities, alkyl and aryl
15 groups and can be the same or different. R herein
described includes but is not limited to aliphatic,
cycloaliphatic, and aromatic moieties. More
preferably, polyamides include polytetramethylene
adipamide or nylon 4,6, polyhexamethylene adipamide
20 or nylon 6,6, polyhexamethylene sebacamide or nylon
6,10, poly(hexamethylenediamine-co-dodecanedioic
acid) or nylon 6,12, polycaprolactam or nylon 6,
polyheptanolactam or nylon 7, polyundecanolactam or
nylon 11, and polydodecanolactam or nylon 12.

25 Polycarbonates which qualify as crystallizing
polymers for the present invention are of the general
structural formula

$[(C=O)OR_{\text{sub.1}}O]_{\text{sub.x}}[(C=O)OR_{\text{sub.2}}O]_{\text{sub.y}}$.

$R_{\text{sub.1}}$ and $R_{\text{sub.2}}$ herein described include
30 aliphatic, cycloaliphatic, aromatic and pendant
substituted moieties including but not limited to
halogens, nitro functionalities, alkyl and aryl
groups and can be the same or different. More
preferably, polycarbonates include bisphenol and
35 substituted bisphenol carbonates where bisphenol is
of the structural formula $HOPhC(CH_{\text{sub.3}})_{\text{sub.2}}PhOH$
or $HOPhC(CH_{\text{sub.3}})(CH_{\text{sub.2}}CH_{\text{sub.3}})PhOH$ where Ph

describes the phenyl ring and substituents include but are not limited to alkyl, cycloalkyl, aryl, halogen, and nitro functionalities.

Polyurethanes which qualify as crystallizing
5 polymers for the present invention are of the general structural formula
$$[(C=O)OR_{1.1}N(H,R)]_{x}[(C=O)OR_{2.2}N(H,R)]_{y}$$

R_{1.1} and R_{2.2} herein described include aliphatic, cycloaliphatic, aromatic and pendant
10 substituted moieties including but not limited to halogens, nitro functionalities, alkyl and aryl groups and can be the same or different. R herein described includes but is not limited to aliphatic, cycloaliphatic, and aromatic moieties. More
15 preferably, polyurethanes include polyether polyurethane and/or polyester polyurethane copolymers including methylenebis (phenylisocyanate).

Additional polyesters and copolymers not previously disclosed, polyamides and copolymers,
20 polycarbonates and copolymers, and polyurethanes and copolymers which qualify as crystallizing polymers for the present invention may be comprised of at least one diol including ethylene glycol, 1,2-propylene glycol, 1,3-propylene glycol, 1,3-butenediol, 1,4-butenediol, 1,5-pentanediol, 1,3-hexanediol, 1,6-hexanediol, neopentyl glycol, decamethylene glycol, dodecamethylene glycol, 2-butyl-1,3-propanediol, 2,2-dimethyl-1,3-propanediol, 2,2-diethyl-1,3-propanediol, 2-ethyl-2-isobutyl-1,3-
25 propanediol, 2-methyl-1,4-pentanediol, 3-methyl-2,4-pentanediol, 3-methyl-1,5-pentanediol, 2,2,4-trimethyl-1,3-pentanediol, 2-ethyl-1,3-hexanediol, 2,2,4-trimethyl-1,6-hexanediol, 1,2-cyclohexanediol, 1,4-cyclohexanediol, 1,2-cyclohexane dimethanol, 1,3-cyclohexane dimethanol, 1,4-cyclohexane dimethanol,
35 cyclohexane dimethanol, 1,4-cyclohexane dimethanol, diethylene glycol, triethylene glycol, polyethylene glycol, dipropylene glycol, tripropylene glycol,

polypropylene glycol, polytetramethylene glycol, catechol, hydroquinone, isosorbide, 1,4-bis (hydroxymethyl)-benzene, 1,4-bis(hydroxyethoxy)benzene, 2,2-bis(4-hydroxyphenyl)propane and isomers thereof.

Other polyesters and copolymers, polyamides and copolymers, polycarbonates and copolymers, and polyurethanes and copolymers which qualify as crystallizing polymers for the present invention may be comprised of at least one lactone or hydroxyacid including butyrolactone, caprolactone, lactic acid, glycolic acid, 2-hydroxyethoxyacetic acid, 3-hydroxypropoxy-acetic acid, and 3-hydroxybutyric acid.

Still other polyesters and copolymers, polyamides and copolymers, polycarbonates and copolymers, and polyurethanes and copolymers which qualify as crystallizing polymers for the present invention may be comprised of at least one diacid including phthalic acid, isophthalic acid, terephthalic acid, naphthalene-2,6-dicarboxylic acid and isomers, stilbene dicarboxylic acid, 1,3-cyclohexanedicarboxylic acid, diphenyldicarboxylic acids, succinic acid, glutaric acid, adipic acid, azelaic acid, sebacic acid, fumaric acid, pimelic acid, undecanedioic acid, octadecanedioic acid, and cyclohexanediacetic acid.

Further polyesters and copolymers, polyamides and copolymers, polycarbonates and copolymers, and polyurethanes and copolymers which qualify as crystallizing polymers for the present invention may be comprised of at least one diester including dimethyl or diethyl phthalate, dimethyl or diethyl isophthalate, dimethyl or diethyl terephthalate, dimethyl naphthalene-2,6-dicarboxylate and isomers.

Yet other polyamides and copolymers, polyesters and copolymers, polycarbonates and copolymers, and

polyurethanes and copolymers which qualify as crystallizing polymers for the present invention may be comprised of diamines including 1,3-propanediamine, 1,4-butanediamine, 1,5-pentanediamine, 1,6-hexanediamine, 1,8-octanediamine, 1,10-decanediamine, 1,12-dodecanediamine, 1,16-hexadecanediamine, phenylenediamine, 4,4'-diaminodiphenylether, 4,4'-diaminodiphenylmethane, 2,2-dimethyl-1,5-pentanediamine, 2,2,4-trimethyl-1,5-pentanediamine, and 2,2,4-trimethyl-1,6-hexanediamine.

Still further polyamides and copolymers, polyesters and copolymers, polycarbonates and copolymers, and polyurethanes and copolymers which qualify as crystallizing polymers for the present invention may be comprised of at least one lactam or amino acid including propiolactam, pyrrolidinone, caprolactam, heptanolactam, caprylactam, nonanolactam, decanolactam, undecanolactam and dodecanolactam.

And other polyurethanes and copolymers, polyesters and copolymers, polyamides and copolymers, and polycarbonates and copolymers which qualify as crystallizing polymers for the present invention may be comprised of at least one isocyanate including 4,4'-diphenylmethane diisocyanate and isomers, toluene diisocyanate, isophorone diisocyanate, hexamethylene-diisocyanate, ethylene diisocyanate, 4,4'-methylenebis (phenylisocyanate) and isomers, xylylene diisocyanate and isomers, tetramethyl xylylene diisocyanate, 1,5-naphthalene-diisocyanate, 1,4-cyclohexyl diisocyanate, diphenylmethane-3,3'-dimethoxy-4,4'-diisocyanate, 1,6-hexanediisocyanate, 1,6-diisocyanato-2,2,4,4-tetramethylhexane, 1,3-bis (isocyanatomethyl)cyclohexane, and 1,10-decanediisocyanate.

An underwater pelletizing system for use in connection with the present invention is shown schematically in Figure 1. The underwater pelletizing system is designated generally by reference number 10 and includes an underwater pelletizer 12, such as a Gala underwater pelletizer, with cutter hub and blades 14 exposed in the separated view from the waterbox 16 and die plate 18.

In the underwater pelletizing system 10, the polymers to be processed are fed from above using a polymer vat or hopper 160 (see Figure 6) typically into an extruder 155 and undergoes shear and heat to melt the polymer. Polyesters and polyamides are typically extruded from about 200°C to about 300°C. Hot melt adhesive formulations are typically extruded from about 100°C to about 200°C. Polycarbonates are typically extruded from about 225°C to about 350°C and polyurethanes typically are extruded from about 175°C to about 300°C. The polymer melt is fed into the screen changer 20 (see Figure 1) to remove any solid particles or extraneous material. The melt continues to feed through the gear pump 22 which provides a smooth and controlled flow rate into the polymer diverter valve 24 and into the die holes in the die plate 18. The strands of polymer melt formed by extrusion through the die holes enter into the waterbox 16 and are cut by the rotating cutter hub and blades 14 to form the desired pellets or granules. This process as described herein is exemplary in nature and other configurations achieving the desired polymer flow as are readily understood by someone skilled in the art and/or as otherwise defined in accordance with prior art are included within the scope of the invention.

Prior art has demonstrated the numerous modifications and additives to the extrusion process which are useful in reducing the degradation of the

extrudate thermally or oxidatively. Among these adaptations are included vacuum removal of byproducts and excess monomers, hydrolysis reduction, control of catalytic depolymerization, inhibition of
5 polymerization catalysts, end-group protection, molecular weight enhancement, polymer chain extension, and use of inert gas purges.

Water enters the waterbox 16 through pipe 26 and rapidly removes the pellets so formed from the die
10 face to form a pellet and water slurry. The process water circulated through the pelletizer waterbox as included in this invention is not limited herein and may contain additives, cosolvents, and processing aids as needed to facilitate pelletization, prevent
15 agglomeration, and/or maintain transport flow as will be understood by those skilled in the art. The pellet water slurry so formed exits the waterbox through pipe 28 and is conveyed toward the dryer 32 through slurry line 30.

20 In accordance with this invention, air is injected into the system slurry line 30 at point 70, preferably adjacent to the exit from the waterbox 16 and near the beginning of the slurry line 30. This preferred site 70 for air injection facilitates the
25 transport of the pellets by increasing the transport rate and facilitating the aspiration of the water in the slurry, thus allowing the pellets and granules to retain sufficient latent heat to effect the desired crystallization. High velocity air is conveniently
30 and economically injected into the slurry line 30 at point 70 using conventional compressed air lines typically available at manufacturing facilities, such as with a pneumatic compressor. Other inert gas including but not limited to nitrogen in accordance
35 with this invention may be used to convey the pellets at a high velocity as described. This high velocity air or inert gas flow is achieved using the

compressed gas producing a volume of flow of at least 100 meters.^{sup.3}/hour using a standard ball valve for regulation of a pressure of at least 8 bar into the slurry line 30 which is standard pipe diameter, preferably 1.5 inch pipe diameter.

To those skilled in the art, flow rates and pipe diameters can vary according to the throughput volume, level of crystallinity desired, and the size of the pellets and granules. The high velocity air or inert gas effectively contacts the pellet water slurry generating water vapor by aspiration, and disperses the pellets throughout the slurry line propagating those pellets at increased velocity into the dryer 32, preferably at a rate of less than one second from the waterbox 16 to the dryer exit 34. The high velocity aspiration produces a mixture of pellets in an air/gas mixture which may approach 98-99% by volume of air in the gaseous mixture.

Figure 5 shows a preferred arrangement for air injection into the slurry line. The water/pellet slurry exits the pelletizer waterbox 102 into the slurry line 106 (Figure 4) through the sight glass 112 past the angle elbow 114 where the compressed air is injected from the valve 120 through the angled slurry line 116 and past the enlarged elbow 118 through the dryer entrance 110 and into the dryer 108. It is preferred that the air injection into the angled elbow 114 is in line with the axis of the slurry line 116 providing the maximum effect of that air injection on the pellet/water slurry resulting in constant aspiration of the mixture.

The angle formed between the vertical axis of slurry line 116 and the longitudinal axis of said slurry line 116 can vary from 0° to 90° or more as required by the variance in the height of the pelletizer 102 relative to the height of the entrance 110 to the dryer 108. This difference in height may

be due to the physical positioning of the dryer 108 in relation to the pelletizer 102 or may be a consequence of the difference in the sizes of the dryer and pelletizer. The preferred angle range is
5 from 30° to 60° with the more preferred angle being 45°. The enlarged elbow 118 into the dryer entrance 110 facilitates the transition of the high velocity aspirated pellet/water slurry from the incoming slurry line 116 into the entrance of the dryer 110
10 and reduces the velocity of the pellet slurry into the dryer 108.

The preferred position of the equipment, as shown in Figure 5, allows transport of the pellets from the pelletizer 102 to the exit of the dryer 108 in
15 approximately one second which minimizes loss of heat inside the pellet. This is further optimized by insertion of a second valve mechanism, or more preferred a second ball valve 150, after the air injection port 120. This additional ball valve allows
20 better regulation of the residence time of the pellets in the slurry line 116 and reduces any vibration that may occur in the slurry line. The second ball valve allows additional pressurization of the air injected into the chamber and improves the
25 aspiration of the water from the pellet/water slurry. This becomes especially important as the size of the pellets and granules decrease in size.

The pellets are ejected through the exit 126 of the dryer 108 and are preferably directed toward a
30 vibratory unit, such as a vibrating conveyor 84 illustrated schematically in Figures 2a and 2b. The agitation which results from the vibratory action of the vibrating conveyor 84 allows heat to be transferred between the pellets as they come in
35 contact with other pellets and the components of the vibrating conveyor. This promotes better uniformity of temperature and results in improved and more

uniform crystallinity of those pellets and granules. Agitation alleviates the tendency for pellets to adhere to each other and/or to the components of the vibrating conveyor as a consequence of the increased
5 pellet temperature.

The residence time of the pellets and granules on the vibrating conveyor contributes to the desired degree of crystallization to be achieved. The larger the pellet the longer the residence time is expected
10 to be. The residence time is typically about 20 seconds to about 120 seconds or longer, preferably from 30 seconds to 60 seconds, and more preferably about 40 seconds, to allow the pellets to crystallize to the desired degree and to allow the pellets to
15 cool for handling. The larger pellets will retain more heat inside and crystallize more quickly than would be expected for smaller pellets. Conversely, the larger the pellet size, the longer the residence time required for the pellet to cool for handling
20 purposes. The desired temperature of the pellet for final packaging is typically lower than would be required for further processing. It is generally observed that temperatures below the crystallization temperature, $T_{sub.c}$, of the pellet is sufficient for
25 additional processing while temperatures below the glass transition temperature, $T_{sub.g}$, are appropriate for packaging. Values obtained by differential scanning calorimetry as measured in the cooling mode are good indicators of the temperatures
30 as identified herein.

Other methods of cooling or methods in addition to a vibrating conveyor can be used to allow the pellets exiting the dryer to have sufficient time to crystallize and subsequently cool for handling. For
35 example, an alternative route for the current invention is the pellet crystallization system (PCS), marketed by Gala. The Gala PCS is illustrated in

Figures 6 and 7. The Gala PCS provides additional crystallization and cooling by passing the pellet and water slurry through the inlet valve 201 into the agglomerate catcher 202 through the tank inlet valve 5 205 and into a tank fitted with an agitator represented as 206 in Figure 7. After the initial water-fill through the water-fill valve 204 the pellet/water slurry is introduced alternately into the three separate tanks allowing additional time for 10 the cooling and crystallization with agitation to prevent agglomeration of the pellets or granules. Details of the actual process are described in product literature and brief discussion is included here for purposes of illustration. The cooled pellet 15 slurry exits the appropriate tank through the drain valve 207 and is transported through the transport pipe 210 via the process pump 209 to the dryer 32 through the dryer inlet 33 in Figure 1 as detailed above.

20 As an alternative, the Gala PCS can be attached in sequence after the drier 108 or after the vibrating conveyor 84 allowing additional crystallization of the pellets to be achieved. As disclosed above, water including processing additives 25 and cosolvents are contained within the scope of the process. The temperature of the water or water-containing solutions can be controlled in one, two, or all three tanks and may be the same or different in each of the tanks to confer greater crystallinity. 30 As the degree of crystallization increases the crystallization temperature increases and the processing temperature can be increased to effect an even greater degree of crystallinity. As has been demonstrated historically, increased crystallinity 35 confers improved properties on most polymers and conditions may be optimized according to the necessary gains in those desirable properties.

Pellets and granules from the dryer 108 or the vibrating conveyor 84 can be packaged or stored as required. They may also be transferred to solid state polycondensation or solid state polymerization, identified herein as "SSP" and has been detailed extensively in the prior art. Use of agitation with cocurrent or countercurrent flow of inert gas, preferably nitrogen gas, at elevated temperatures is a common component of the SSP process. This process requires enhanced crystallization as provided by the current invention to avoid agglomeration of the pellets and granules at the temperatures required for proper operation of the SSP process. The increased molecular weight which results from the SSP process allows clear, amorphous polymers to be obtained. Applications and uses are well-disclosed in prior art. It is beyond the scope of this application to describe the processing conditions for the various polymers contained herein as appropriate to SSP.

While the present invention has been described specifically with respect to numerous crystallizing polymers, other such crystallizing polymers, presently known or to be discovered in the future can be processed in accordance with the present invention. Accordingly, it is not intended that the present invention be limited to any particular crystallizing polymer or group of crystallizing polymers but the invention is intended to encompass all crystallizing polymers.

WHAT IS CLAIMED

1. A method for processing crystallizing polymers into pellets using an apparatus including an underwater pelletizer and a dryer, said method
5 comprising:
 - extruding strands of a crystallizing polymer through a die plate for cutting in said underwater pelletizer;
 - 10 cutting the polymer strands into pellets in a cutting chamber of said pelletizer;
 - transporting said pellets out of said cutting chamber to said dryer as a water and pellet slurry; and
 - 15 injecting a high velocity gas into said water and pellet slurry to generate a water vapor mist and enhance the speed of the pellets into and out of said dryer, with said pellets retaining sufficient internal heat upon exiting said dryer for crystallization of said pellets.
- 20 2. The method as claimed in claim 1 wherein said pellets exiting said dryer are handled to avoid agglomeration.
3. The method as claimed in claim 2 wherein said pellets exiting said dryer are agitated to avoid
25 agglomeration and to achieve a desired crystallinity from the retained internal heat.
4. The method as claimed in claim 1 wherein said pellets exit said dryer at a mean temperature above about 135°C, preferably above about 145°C.
- 30 5. The method as claimed in claim 1 wherein the crystallization of said pellets is 30% or greater, preferably 35% or greater, and most preferably 40% or greater.
6. The method as claimed in claim 1 wherein
35 said step of transporting said pellets out of said pelletizer to said dryer includes transporting said

slurry upwardly at an angle from the vertical between 30° and 60°, preferably about 45°.

7. The method as claimed in claim 1 wherein said pressurized gas is air.

5 8. The method as claimed in claim 1 wherein said gas is injected substantially in alignment with a flow direction of said water and pellet slurry.

9. The method as claimed in claim 1 wherein said high velocity gas is injected at a flow rate of
10 at least about 100 cubic meters per hour at a pressure of about 8 bar.

10. The method as claimed in claim 1 wherein said vapor mist has a gas component of about 98% by volume.

15 11. The method of claim 1 wherein the gas injected into said slurry increases pellet flow speed from the pelletizer to an exit of said dryer to a rate of less than about one second.

12. The method of claim 1 wherein
20 crystallization of said pellets occurs using only said internal heat retained from extrusion and in an absence of any secondary heating step while passing through said apparatus.

13. A method for processing crystallizing
25 polymers into pellets, which comprises:

extruding a crystallizing polymer into strands;

cutting the extruded strands into pellets in a water stream;

30 transporting said pellets in said water stream as a water and pellet slurry;

injecting an inert gas at a high velocity into said pellet and water slurry such that said pellets retain sufficient heat for crystallization of
35 said polymer without the application of external heat; and

drying and agitating said pellets to achieve a desired crystallinity from the retained heat.

14. The method of claim 13 wherein said desired crystallinity is 30% or greater, preferably 35% or greater, and most preferably 40% or greater.

15. The method of claim 13 wherein the gas injected into said slurry increases pellet flow speed from a pelletizer at said step of cutting to a dryer exit to a rate of less than about one second.

10 16. The method of claim 13 wherein said polymer is selected from the group consisting of polyesters and copolymers, polyamides and copolymers, polycarbonates and copolymers, and polyurethanes and copolymers.

15 17. A method for processing crystallizing polymers into crystallized pellets using an apparatus having an underwater pelletizer and a centrifugal dryer, said method comprising:

20 cutting strands of a crystallizing polymer into pellets in the underwater pelletizer;

transporting said pellets out of said pelletizer as a water and pellet slurry; and

25 introducing a high velocity inert gas into said water and pellet slurry to enhance the speed of said pellets through said centrifugal dryer located downstream of said gas introduction, said pellets exiting said dryer with sufficient internal heat for crystallization of said pellets.

30 18. The method of claim 17 wherein the gas introduced into said slurry increases a speed of pellet flow from said pelletizer to an exit of said dryer to a rate of less than about one second.

35 19. The method of claim 17 wherein said step of introducing a high velocity gas includes injecting said gas at a flow rate of at least about 100 cubic meters per hour at a pressure of about 8 bar.

20. The method of claim 17 wherein said injected gas produces a water vapor mist having a gas component of about 98% by volume.

21. The method of claim 17 wherein
5 crystallization of said pellets occurs using only said internal heat retained from extrusion and in an absence of any secondary heating step while passing through said apparatus.

22. The method of claim 17 wherein said polymer
10 is selected from the group consisting of polyesters and copolymers, polyamides and copolymers, polycarbonates and copolymers, and polyurethanes and copolymers.

23. The method as claimed in claim 17 wherein
15 said pellets exiting said dryer are handled to avoid agglomeration.

24. The method as claimed in claim 23 wherein
said pellets exiting said dryer are agitated to avoid agglomeration and to achieve a desired crystallinity
20 from the retained internal heat.

25. An apparatus for processing crystallizing polymers into pellets which comprises an underwater pelletizer to cut strands of a crystallizing polymer extruded into said pelletizer into pellets, piping to
25 introduce water into said pelletizer, a slurry line to transport a water and pellet slurry out of said pelletizer and to a dryer for drying said pellets, and an injector to introduce a pellet speed expediter into said water and pellet slurry to enhance the
30 speed of said pellets through said processing apparatus with said pellets exiting said dryer with sufficient internal heat to initiate crystallization of said pellets.

26. The apparatus as claimed in claim 25 wherein
35 the pellet speed expediter is an inert gas moving at a flow rate of about 100 to about 175m³/hour.

27. The apparatus as claimed in claim 25 and further comprising an agitating unit for receiving said pellets exiting said dryer to avoid agglomeration and to achieve a desired crystallinity
5 for said pellets.

28. The apparatus as claimed in claim 25 wherein said apparatus further comprises one or more heat insulating containers for receiving said pellets out of said dryer to achieve a desired crystallization of
10 said pellets.

29. The apparatus as claimed in claim 25 wherein a portion of said slurry line is generally vertical and another portion is angled upwardly at an angle between 30° and 60° from vertical, preferably about
15 45°.

30. The apparatus as claimed in claim 25 wherein said slurry line includes an elbow and a straight portion and said gas injector introduces said inert gas at said elbow substantially in alignment with a
20 longitudinal axis of said straight portion.

31. The apparatus as claimed in claim 25 wherein said slurry line includes an exit end with an enlarged diameter before entry into said centrifugal dryer.

25 32. The apparatus as claimed in claim 25 wherein said slurry line includes a generally vertical section from said pelletizer, a generally angled straight section from said generally vertical section, and an enlarged section at an outer end of
30 said generally angled straight section to reduce slurry velocity of said pellets entering said dryer.