PCT WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 : H01L 21/02

A2

(11) International Publication Number: WO 99/62108

(43) International Publication Date: 2 December 1999 (02.12.99)

(21) International Application Number: PCT/IB99/00835

(22) International Filing Date: 10 May 1999 (10.05.99)

(30) Priority Data:
98401232.8 22 May 1998 (22.05.98) EP

(71) Applicant *(for all designated States except US)*: APPLIED MATERIALS, INC. [US/US]; 3050 Bowers Avenue, Santa Clara, CA 95054 (US).

(72) Inventors; and
(75) Inventors/Applicants *(for US only)*: GEIGER, Fabrice [FR/FR]; 29, avenue de la Plaine Fleurie, F-38240 Meylan (FR). GAILLARD, Frédéric [FR/FR]; Rue des Tallifardières, F-38800 Voiron (FR).

(74) Agents: BERNADICOU, Michael, A. et al.; Blakely, Sokoloff, Taylor & Zafman LLP, 7th floor, 12400 Wilshire Boulevard, Los Angeles, CA 90025 (US).

(81) Designated States: JP, KR, SG, US.

Published
Without international search report and to be republished upon receipt of that report.

(54) Title: METHODS FOR FORMING SELF-PLANARIZED DIELECTRIC LAYER FOR SHALLOW TRENCH ISOLATION

(57) Abstract

A method for depositing a trench oxide filling layer (300) on a trenched substrate (224) utilizes the surface sensitivity of dielectric materials such as O_3/TEOS. Such materials have different deposition rates on differently constituted surfaces at different levels on the trenched substrate (224) so that the surface profile of the deposited layer (300) is substantially self-planarized. Depositing the dielectric material on a silicon trench (228) produces a high quality filling layer, and cleaning the trench (228) prior to deposition can increase the quality. After deposition, an oxidizing anneal can be performed to grow a thermal oxide (308) at the trench surfaces and densify the dielectric material. A chemical mechanical polish can be used to remove the excess oxide material above an etch stop layer (226) of the substrate (224) which can be formed of LPCVD nitride or CVD anti-reflective coating.

