

- 1 -

FIBRE TREATMENTField of the invention

This invention is concerned with methods of improving the visual appearance of lyocell fabrics.

5 It is known that man-made cellulose fibre can be made by extrusion of a solution of cellulose in a suitable solvent into a coagulating bath. One example of such a process is described in US-A-4,246,221, the contents of which are incorporated herein by way of reference.

10 Cellulose is dissolved in a solvent such as an aqueous tertiary amine N-oxide, for example N-methylmorpholine N-oxide. The resulting solution is then extruded through a suitable die into an aqueous bath to produce an assembly of filaments which is washed in water to remove the solvent and

15 is subsequently dried. This process is referred to as "solvent-spinning", and the cellulose fibre produced thereby is referred to as "solvent-spun" cellulose fibre or as lyocell fibre. Lyocell fibre is to be distinguished from cellulose fibre made by other known processes, which rely on

20 the formation of a soluble chemical derivative of cellulose and its subsequent decomposition to regenerate the cellulose, for example the viscose process.

As used herein, the term "lyocell fibre" means a cellulose fibre obtained by an organic solvent spinning

25 process, wherein the organic solvent essentially comprises a mixture of organic chemicals and water, and wherein solvent spinning involves dissolving cellulose in the organic solvent to form a solution which is spun into fibre without formation of a derivative of the cellulose. As used

30 herein, the terms "solvent-spun cellulose fibre" and "lyocell fibre" are synonymous. As used herein, the term "lyocell yarn" means a yarn which contains lyocell fibre, alone or in blend with other type(s) of fibre. As used herein, the term "lyocell fabric" means a fabric woven or

- 2 -

knitted from yarns, at least some of which are lyocell yarns.

Fibres may exhibit a tendency to fibrillate, particularly when subjected to mechanical stress in the wet state. Fibrillation occurs when fibre structure breaks down in the longitudinal direction so that fine fibrils become partially detached from the fibre, giving a hairy appearance to the fibre and to fabric containing it, for example woven or knitted fabric. Dyed fabric containing fibrillated fibre tends to have a "frosted" visual appearance, which may be aesthetically undesirable. Such fibrillation is believed to be caused by mechanical abrasion of the fibres during treatment in a wet and swollen state. Wet treatment processes such as dyeing processes inevitably subject fibres to mechanical abrasion. Higher temperatures and longer times of treatment generally tend to produce greater degrees of fibrillation. Lyocell fibres appear to be particularly sensitive to such abrasion in comparison with other types of cellulose fibre, in particular cotton which has an inherently very low fibrillation tendency.

It is an object of the present invention to provide dyed lyocell fabric which does not exhibit a "frosted" appearance and which does not develop such a "frosted" appearance after repeated laundering. This improvement is referred to hereinafter as improving the colour properties of the lyocell fabric. This term "colour properties" is to be distinguished from the terms "uniform dyeability" and "level dyeing" commonly used in the art. In general, the levelness of dyeing of a fabric does not change on repeated laundering. Cotton is a natural fibre, and its dyeability varies from fibre to fibre. In contrast, lyocell fibres are made by a controlled manufacturing process and exhibit uniform dyeability. Cotton does not fibrillate, and so its colour properties do not change during processing or laundering. The colour properties of known lyocell fabric may change depending on the type of treatment to which it is

- 3 -

subjected. For example, repeated laundering commonly induces fibrillation and worsens the colour properties of lyocell fabric, whereas enzyme (cellulase) treatment removes fibrils and generally improves the colour properties of the fabric.

Background art

It has been known for many years to subject cotton fibres, in particular in the form of yarn or fabric, to the process known as mercerisation. Mercerisation consists in treating the fibres with a strong alkali, usually aqueous sodium hydroxide, followed by washing with water and dilute acid to remove the alkali and drying. Cotton yarn and fabric may be held under tension during the treatment with alkali. The reasons for mercerising are to obtain (1) increased colour yield on dyeing or printing, (2) improved easy-care properties, (3) improved fibre lustre (when the cotton is held under tension during mercerising), and (4) more uniform dyeability. Cotton fibres are coated with mineral waxes and pectins which are removed by this treatment with aqueous alkali. Removal of these impurities increases the absorbency and dye receptiveness of the cotton fibres. If cotton contains a high proportion of thin-walled immature fibres, mercerising swells these fibres and makes them dye more like maturer fibres, thereby promoting uniform dyeing.

It is well known that man-made cellulose fibres such as viscose rayon and cuprammonium rayon fibres have naturally high dye receptiveness and lustre, generally higher than that of cotton. It is also well-known that such rayon fibres do not contain non-cellulosic waxy impurities. It is further well known that such rayon fibres are much less resistant than cotton to the action of sodium hydroxide. When rayon fibre is mercerised using 10 to 30 percent by weight aqueous sodium hydroxide, as might be used for cotton, the fibre becomes harsh and brittle, loses lustre

- 4 -

and may partially dissolve in the mercerising liquor. When rayon fabric soaked with such strong solutions of sodium hydroxide is washed with water, it becomes very swollen and loses nearly all its strength, with the result that the fabric becomes very liable to mechanical damage.

Disclosure of the invention

According to the invention a method of improving the colour properties of lyocell fibre consists in mercerising the fibre.

10 The lyocell fibre may be subjected to mercerisation in the form of staple fibre, tow, continuous filaments, spun yarn or lyocell fabric. Mercerisation of lyocell fabric may be preferred.

A typical mercerisation process for cotton yarn or
15 fabric includes the steps of:

(1) wetting the cotton with a solution of caustic soda (10 to 30, often 20 to 25, per cent by weight sodium hydroxide in water) at ambient or slightly elevated temperature, for example at up to about
20 35°C;

(1a) optionally washing with water;

(2) souring with dilute aqueous acid (for example up to 3, preferably 1 to 3, per cent by weight of an inorganic acid such as sulphuric acid or
25 hydrochloric acid or an organic acid such as acetic acid);

(3) washing one or more times with water to remove the acid; the final wash may optionally contain a slightly alkaline softener to neutralise the last
30 traces of acid; and

- 5 -

- (4) drying the cotton, for example in an air dryer for 15 to 20 minutes at about 120°C or other conventional manner.

Similar conditions and equipment are appropriate for 5 lyocell fibre.

It is highly surprising that lyocell fibre, which is a man-made cellulose fibre, can satisfactorily be treated with strong alkali in a mercerisation process. Other man-made cellulose fibres, for example viscose rayon and cuprammonium 10 rayon fibre, suffer severe damage under such conditions.

Lyocell fibre treated according to the method of the invention may subsequently be dyed using known dyestuffs for cellulose in known manner. Dyed lyocell fabric containing fibre treated by the method of the invention has good colour 15 properties and retains good colour properties on repeated laundering. In particular, such fabric has a much less "frosted" appearance than fabric subjected to the same processing steps but with omission of the mercerising treatment of the invention.

20 Procedures are known in which lyocell fibre is treated with a variety of chemical reagents, for example cross-linking agents, thereby reducing the degree of fibrillation and/or the tendency to fibrillation of the fibre. Such procedures generally cause an improvement in the colour 25 properties of the fibre. However, such known procedures may suffer from the disadvantage that the improvement thereby produced may not be permanent. The colour properties of the fibre may for example deteriorate during repeated laundering. Furthermore, such known procedures may impair 30 the dyeability or physical properties of the fibre. The method of the invention has advantages over such known procedures in that the improvement in colour properties thereby obtained remains through repeated laundering cycles; that the mercerised fibre has good dyeability; and that the

- 6 -

mercerised fibre has good physical properties. In particular, lyocell fabric containing lyocell fibre treated by the method of the invention exhibits the characteristic attractive drape and soft hand associated with lyocell 5 fabrics.

The reason for the improvement in the colour properties afforded by the invention is not fully understood. Unmercerised and mercerised samples of lyocell fabric appear very similar under the microscope, in particular in their 10 degree of fibrillation, provided that they have otherwise been treated in the same way.

Lyocell fibre or fabric, particularly fabric, treated by the method of the invention may subsequently be treated with an aqueous solution of a cellulase enzyme to remove 15 fibrils from the fabric in known manner. Many cellulase preparations suitable for the treatment of cellulosic fabrics are available commercially. Mercerisation generally hardens the handle of cellulosic fabrics. It has surprisingly been found that cellulase treatment softens the 20 handle of mercerised lyocell fabric to an unexpectedly large extent.

The degree of fibrillation of lyocell fibres and fabrics may be assessed by the following test method:-

Test Method (Assessment of Fibrillation)

25 There is no universally accepted standard for assessment of fibrillation, and the following method was used to assess Fibrillation Index (F.I.). Samples of fibre were arranged into a series showing increasing degrees of fibrillation. A standard length of fibre from each sample 30 was then measured and the number of fibrils (fine hairy spurs extending from the main body of the fibre) along the standard length was counted. The length of each fibril was measured, and an arbitrary number, being the number of

- 7 -

fibrils multiplied by the average length of each fibril, was determined for each fibre. The fibre exhibiting the highest value of this product was identified as being the most fibrillated fibre and was assigned an arbitrary 5 Fibrillation Index of 10. A wholly unfibrillated fibre was assigned a Fibrillation Index of zero, and the remaining fibres were evenly ranged from 0 to 10 based on the microscopically measured arbitrary numbers.

The measured fibres were then used to form a standard 10 graded scale. To determine the Fibrillation Index for any other sample of fibre, five or ten fibres were visually compared under the microscope with the standard graded fibres. The visually determined numbers for each fibre were then averaged to give a Fibrillation Index for the sample 15 under test. It will be appreciated that visual determination and averaging is many times quicker than measurement, and it has been found that skilled fibre technologists are consistent in their rating of fibres.

Fibrillation Index of fabrics can be assessed on fibres 20 drawn from the surface of the fabric. Woven and knitted fabrics having F.I. of more than about 2.0 to 2.5 are normally found to exhibit an unsightly appearance.

The invention is illustrated by the following Examples, in which parts and proportions are by weight unless 25 otherwise specified:-

Example 1

A piece of 2x1 twill fabric (190 g/m²) woven from 100% Tencel 20 tex yarn (fibre 1.7 dtex) was prepared in open width by scouring with sodium carbonate and an anionic 30 detergent at 90°C and can-drying at 140°C. (Tencel is a Trade Mark of Courtaulds Fibres (Holdings) Limited for lyocell.) For mercerising, it was immersed in 14% aqueous sodium hydroxide at ambient temperature for 45 seconds, and

- 8 -

mangled to give 70% add-on. The fabric was rinsed in water at 95°C, neutralised in water containing 1 ml/l acetic acid, rinsed again and dried.

This treated (mercerised) fabric was dyed together with an untreated piece in a rotary laboratory dyeing machine using a bath containing 4% Procion Blue HE-GN (Procion is a Trade Mark of Zeneca plc), 80 g/l Glaubers salt and 20 g/l soda ash at 80°C. The treated fabric dyed to a deeper shade than the untreated piece.

10 The two pieces of fabric were then washed at 60°C and tumble-dried a total of five times. The appearance of the treated piece was considerably less frosty than that of the untreated control piece. Under the microscope, the fibrils in the treated sample appeared shorter than those in the control and appeared to be stuck to the main part of the fibre.

Samples of fibre were removed from the pieces of fabric and their F.I. assessed by the Test Method described above. The F.I. of fibres from the untreated control and the treated fabric were 5.2 and 3.1 respectively. The appearance of the mercerised fabric was satisfactory despite its relatively high F.I.

Example 2

A piece of Tencel fabric as used in Example 1 was treated (mercerised) and dyed as in Example 1, except that a 25% solution of sodium hydroxide was used. The treated piece and an untreated control piece were washed a single time, after which fibrillation was observed to be more evident in the untreated piece. The two pieces of fabric were then immersed in an aqueous solution containing 3 ml/l Primafast 100 (a cellulase preparation available from Genencor) (Primafast is a Trade Mark) at pH 5.0 for 60 minutes at 55°C to remove fibrils, rinsed and dried. The two

- 9 -

pieces were then laundered five times in the manner described in Example 1. The F.I. of fibres removed from both pieces of fabric was 2.0. Nevertheless, the visual appearance of the treated piece was much cleaner and less
5 frosted than that of the untreated control. The handle of both samples was very soft, with a "peach-skin" touch. The handle of the mercerised and cellulase-treated sample was markedly softer than that of a sample which had not been treated with cellulase.

- 10 -

CLAIMS

1. A method of improving the colour properties of lyocell fibre, characterised in that it includes the step of mercerising the fibre.
- 5 2. A method according to claim 1, characterised in that the lyocell fibre is present in a lyocell fabric.
3. A method according to claim 1 or claim 2, characterised in that the lyocell fibre is subsequently treated with a solution of a cellulase enzyme.
- 10 4. A method according to any preceding claim, characterised in that the lyocell fibre is subsequently dyed.

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification⁶ : D06M 11/40, 16/00, D06P 1/673	A1	(11) International Publication Number: WO 95/24524 (43) International Publication Date: 14 September 1995 (14.09.95)
(21) International Application Number: PCT/GB95/00484 (22) International Filing Date: 6 March 1995 (06.03.95) (30) Priority Data: 9404510.1 9 March 1994 (09.03.94) GB (71) Applicant (for all designated States except US): COUR- TAULDS FIBRES (HOLDINGS) LIMITED [GB/GB]; 50 George Street, London W1A 2BB (GB). (72) Inventor; and (75) Inventor/Applicant (for US only): TAYLOR, James, Martin [GB/GB]; 146 Field Lane, Alveston, Derby DE24 0GW (GB). (74) Agent: HALE, Stephen, Geoffrey; J.Y. & G.W. Johnson, Furnival House, 14-18 High Holborn, London WC1V 6DE (GB).		(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN, MW, MX, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TT, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ, UG). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i> <i>RTMP's copy.</i>
(54) Title: FIBRE TREATMENT ✓ (57) Abstract The colour properties (i.e. freedom from a frosted visual appearance, especially in dyed form) of lyocell fibre, in particular in fabric form, can be improved by mercerising the fabric. The hand of the mercerised fabric can be softened to a marked degree by treatment with a cellulase enzyme.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

96 11234-7