

5 **A process for monitoring the operation of hydrodeoxygena-**
 tion of a feedstock

 The present invention belongs within the field of hydropro-
 cessing units, more specifically hydroprocessing units for
10 the treatment of renewable feedstocks.

 Environmental concerns about global warming and climatic
 changes are the main drivers in the search of alternative
 renewable energy sources to maintain the current increasing
15 level of energy use. Although different forms of renewable
 energy (solar, wind etc.) will increasingly contribute to
 the energy supply, it is expected that liquid transporta-
 tion fuels will remain pivotal in the transportation sector
 for decades to come. Currently, such transportation fuels
20 are mainly derived from crude oil, and although electric
 and fuel-cell powered vehicles are getting a growing share
 of the passenger vehicle market, liquid transportation
 fuels derived from crude oil remain important for heavy
 duty road, rail and marine transport as well as in aviation
25 where electrification is not feasible. Liquid hydrocarbon-
 based fuels can in principle be obtained from renewable en-
 ergy sources such as electricity, e.g. by converting elec-
 tricity to hydrogen by electrolysis of water and then using
 it to reduce CO₂. The problem of these solar fuels technol-
30 ogies is that they are still in their infancy, which ex-
 plains the incentive to use natural gas (the cleanest burn-
 ing fossil fuel) and renewable biomass as feedstocks in the
 transition to a low-carbon economy.

Hydrotreating, hydrocracking and hydroisomerization processes share many common features, so they are often discussed together as "hydroprocessing". Most hydroprocessing units employ specialized catalysts. As the name implies, they all consume hydrogen. Important chemical reactions include hydrodesulfurization (HDS), hydrodenitrogenation (HDN), hydrodeoxygenation (HDO), the saturation of olefins and aromatics, the conversion of large hydrocarbon molecules into smaller hydrocarbons (hydrocracking) and the isomerization of hydrocarbons (hydroisomerization).

Hydrocarbons may be produced from oxygenated hydrocarbons, such as triglycerides, fatty acids, resin acids, ketones, aldehydes or alcohols, where said oxygenates originate from one or more of a biological source, a gasification process, a pyrolysis process, Fischer-Tropsch synthesis, methanol based synthesis or a further synthesis process. In this process, the raw oxygenate feedstock is subjected to hydrodeoxygenation (HDO). Chemically, HDO removes oxygen from the feedstock molecules in the presence of gaseous hydrogen and an HDO catalyst and rejects it in the form of water, CO and CO₂.

In a process for hydrogenation of a feedstock comprising oxygenates, it is desirable to be able to determine the need for replacement of a material that is catalytically active in hydrotreatment. This is because catalyst deactivation in connection with hydrotreating of renewable fuels happens in another way than in fossil fuel hydrotreating, and in connection with split injection of the feedstock it may be desirable to have a protection bed arranged in the

bottom of the hydrotreater to ensure that the dewaxing catalyst is not poisoned by impurities and/or oxygen.

5 As regards split injection of the feedstock, the feedstock can be injected in multiple beds, but preferably no feedstock is injected into the protection bed.

10 So the idea underlying the present invention is to arrange a protection bed in connection with the HDO reactor. For most plant designs, the bed will be arranged in the bottom of the HDO reactor. However, it can also be arranged in a separate reactor between the HDO reactor and the dewaxing reactor.

15 More specifically, the present invention relates to a process for monitoring the operation of hydrodeoxygenation of a feedstock, comprising the steps of

20 - directing the feedstock to contact a material catalytically active in hydrotreatment,

- monitoring the temperature in multiple locations of said catalytically active material, and

25 - providing an indication in a means for process monitoring when the difference between the temperature in a first location of said catalytically active material and the temperature in a second location of said catalytically active material is above a specified threshold value, optionally
30 for a specified time of operation,

wherein the difference between the temperature in said

first location of said catalytically active material and the temperature in said second location of said catalytically active material is below said specified threshold value during an initial time of operation.

5

The means for process monitoring is preferably a control room screen, but the indication in the process monitoring may also be triggering a local or remote warning to review the performance of the catalytically active material.

10

The specified threshold may either be defined as an absolute difference in temperature, or be defined as a relative value, compared to the difference in temperature from the inlet of said catalytically active material to the outlet of said catalytically active material, also known as the exotherm of the process.

15

20

The absolute threshold value may be 10°C, 20°C or 40°C. The effect of the threshold being 10°C, 20°C or 40°C is related to a balance between sensitivity and risk of false alarm.

25

When a moderate temperature increase of 10°C is seen over a catalytically active material assumed to be in excess, and thus not expected to show temperature increase, this will typically be an early indication of the upstream material having insufficient activity. When a higher temperature increase of 20°C or 40°C the warning is closer in time to the required time of action.

30

The relative threshold may be a more robust measure, especially in the case of varying feedstocks, showing different exotherms. The exotherm in the processes in question may be

from 40°C or 80°C to 150°C or 200°C, such that the exotherm is sufficient for being an indicator of the activity of the catalytically active material while not being too excessive for operation. The relative threshold will typically be
5 10%, 20% or 40% of the actual or time weighted exotherm. In this respect the exotherm is typically regarded as the difference in temperature from reactor inlet to reactor outlet, and the temperature difference is typically measured across a reactor catalyst bed.

10 Preferably the feedstock comprises one or more oxygenates selected from the group consisting of triglycerides, fatty acids, resin acids, ketones, aldehydes and alcohols, said oxygenates originating from one or more of a biological
15 source, a gasification process, a pyrolysis process, a Fischer-Tropsch synthesis, a methanol-based synthesis or a further synthesis process. Such a process is a process being viable for receiving a wide range of feedstocks, especially of renewable origin.

20 The feedstock preferably originates from vegetables, plastics, plants, algae, animals, fish, vegetable oil refining, domestic waste, sewage sludge or industrial organic waste, such as tall oil or black liquor.

25 While the invention primarily is targeted at hydroprocessing of feedstocks consisting of 100 % renewables, the same challenges are present for co-processing mixtures of fossil and renewable feedstocks.

30 Generally, it is possible to hydroprocess feedstock mixtures containing up to about 10 % renewables without having

to revamp the hydroprocessing unit, but co-processing operation with 20% or 50% renewables may also be attractive.

5 The material that is catalytically active in hydrotreatment preferably consists of one or more catalyst layers designed specifically for fixed-bed hydrodeoxygenation purposes.

10 This way, the dewaxing reactor and the dewaxing catalyst will both be protected, which leads to a longer lifetime of the dewaxing catalyst. The protection bed also protects the dewaxing catalyst against organic sulfur and nitrogen. Furthermore, the protection bed enables hydroprocessing of feedstocks with a high content of nitrogen and sulfur. The protection bed, in addition, can be seen as a warning measure to the operator, because when the exotherm in this bed (the difference in temperature from bed inlet to outlet) starts to rise, it means that the beds on top of the protection bed have lost their activity.

20 Thus, in a process for hydrogenation of a feedstock comprising oxygenates, the invention relates to a method for determining the need for replacement of a material that is catalytically active in hydrotreatment. The process comprises the steps of directing the feedstock to contact a material catalytically active in hydrotreatment and monitoring the temperature in multiple locations of said material, wherein replacement of the material is determined as needed when the increase in temperature over an amount of the material exceeds a pre-defined limit.

30

Regarding prior art, US 9.938.469 B2 relates generally to

processes and systems for the hydrodeoxygenation of an oxygenate feedstock that increases the conversion of oxygenates to hydrocarbons while avoiding any detrimental effects resulting from increasing the severity of the oxygenation reaction. The systems comprise a catalyst-containing reactor, a first and a second separator, a distillation apparatus configured to separate solvents from unreacted oxygenates and a conduit to return the unreacted oxygenates to the reactor.

In US 9.523.041 B2, a method is described which involves reducing a pressure drop across a hydroprocessing reactor having a reactor feed and producing a hydroprocessing product, where the reactor feed includes a bio-oil feed and a hydrocarbon diluent. The step of reducing the pressure drop comprises stopping or substantially reducing the bio-oil feed supplied to the reactor and supplying the hydrocarbon diluent to the reactor.

Catalysts, methods and reactor systems for converting oxygenated hydrocarbons to various oxygenated compounds are described in US 2015/0183701. The oxygenated compounds are e.g. cyclic ethers, monooxygenates, dioxygenates, ketones, aldehydes, carboxylic acids and alcohols produced from oxygenated hydrocarbons, such as carbohydrates, sugars, sugar alcohols, sugar degradation products and the like, using catalysts containing Group VIII metals. The oxygenated compounds produced are useful in the production of chemicals, liquid fuels and other products. None of these prior art documents mention the possibility of - or the need for - arranging a protection bed in the bottom of a hydrodeoxygenation reactor.

Within the field of the invention, the standard solution has so far been (1) not to use a protection bed in the HDO reactor and (2) to use fewer catalyst beds altogether with no warning before breakthrough to the dewaxing catalyst, which is very selective towards isomerization. This has meant that the end of run state of the catalyst in the HDO reactor was realized with very short notice, thus hindering any planned scheduling of catalyst exchange. The impact of this is that the reactor will have to run with a deactivated catalyst, which will lead to a decrease in capacity and/or a yield loss.

The Applicant has recently launched a series of dewaxing catalysts that are true isomerization catalysts: TK-910 D-wax, TK-920 D-wax, TK-930 D-wax and TK-940 D-wax. Other relevant catalysts are Applicant's TK-928 and TK-939, specifically designed for improvement of cold flow properties.

By using an extra bed of catalysts as protection bed in the bottom of the HDO reactor or in a separate reactor between the HDO reactor and the dewaxing reactor, the following effects and advantages are obtained:

- a longer lifetime of the dewaxing catalyst,
- a better operability, and
- a warning before breakthrough to the dewaxing catalyst.

In addition, feedstocks with high contents of nitrogen and sulfur can be handled.

Further, there is a safety issue in connection with letting oxygen compounds slip to the dewaxing catalyst. The oxygen compounds will result in a very high exotherm, which is unacceptable for the dewaxing catalyst due to the risk of temperature excursions, since the dewaxing catalyst is a zeolite-containing catalyst. Thus, the dT over the dewaxing temperature should be kept low in order to minimize this risk.

The problem with the very high exotherm can be counteracted by recycling part of the outlet from the HDO reactor to the inlet thereof and/or adding a "diluent" gas not containing oxygen to the inlet of the HDO reactor.

Experimental

Experiments have shown in more detail how - during a cycle with renewables - the exotherm over time moves down through the catalytic bed. These experiments used a bed consisting of five consecutive catalyst layers as follows:

layer 1: 3/16" Ring
layer 2: 1/8" Ring
layer 3: TK-339 1/10" QL
layer 4: TK-341 1/10" QL
layer 5: TK-569 1/16" TL

where the TK-339 and TK-341 catalysts are designed for fixed-bed hydrodeoxygenation (HDO) purposes, while the TK-569 catalyst provides high hydrodenitrogenation (HDN) and hydrodesulfurization (HDS) activity.

This catalytic bed received a fresh feed stream. By specifically watching the behavior of the exotherm (% dT) as a function of the number of run days for bed no. 1, it was
5 seen that, in the beginning, most of the reactions take place in layers 1, 2 and 3. But already after 50 run days, the dT above these layers begin to decrease and move to layer 4 as TK-339 starts to deactivate. Around run day 120, the dT above layer 4 begins to decrease, while it begins to
10 increase in layer 5.

At the start of run (SOR), approximately 50 % of the dT is happening in the HDO and HDN layer, and the hydrogenation activity of the P guard starts to deactivate after around
15 100 run days. The HDO catalyst starts to deactivate after 130 run days, and more than 50 % of the dT has moved to layer 5 (HDO/HDN) after 220 run days.

At the end of run (EOR) after 500 run days, almost all of
20 the reactions take place in the last layer, i.e. layer 5. Furthermore, it is seen that approximately 45% of the dT is happening in the TK-341 or TK-569 layers at the start of run (SOR). After 50 run days, TK-339 starts to deactivate, and TK-341 starts to deactivate after 120 run days, having
25 no more activity left after one year of catalyst life.

The TK-339 has no more activity left after 175 run days, and more than 50% of the dT has moved to the TK-569 layer after 200 run days.

30

In another experiment with four beds, it was observed that around day 360, dT begins to decrease in beds 1 and 2, i.e.

the two beds receiving a fresh renewable feed stream, while the dT increases in bed 3 (which bed, in this experiment, serves as the protection bed).

5 In the figure, a simplified run is shown, only including dT of bed 1 and bed 3. At (a), fresh renewable feed is injected into beds 1 and 2, which do all the renewable reactions. At EOR, shown as (b), 50 % of the exotherm is now happening in bed 3, i.e. the protection bed, meaning that
10 this bed is now doing a significant part of the HDO reactions.