

RUBBER COMPOSITION AND GOLF BALL COMPRISING IT

1. Field of the Invention

This invention relates to a rubber composition having improved mechanical properties, particularly an excellent compressive strength.

This invention also relates to a golf ball which comprises the rubber composition mentioned above and has excellent durability, bounce impact elasticity (flight characteristics) and excellent feeling upon hitting.

This invention further relates to a rubber composition particularly suitable for a cover layer of golf ball.

2. Description of the Prior Art

Rubber compositions, unlike plastics, exhibit viscoelasticity and, by the virtue of this property, have found their utility in a wide variety of fields such as civil engineering, machine industry, electrical industry and chemical industry. In recent years, rubber compositions have been required to possess high hardness, high elasticity, high strength, extremely high compressive strength and excellent wear, resistance to meet diversified needs by the same token that high-strength plastics had been developed. Further, those rubber composition are in most cases required to possess at least two of such highly improved properties simultaneously.

Golf balls, for example, are required to ensure the flight stability, long flight distance characteristics and the like. The rubber compositions used in golf balls, therefore, are

required to have well controlled properties such as bounce impact elasticity, compressive strength and hardness, and various rubber compositions having improved properties have been proposed.

5 For example, a golf ball composed of a composition containing metal salt monomers of an α, β -monoethylenically unsaturated carboxylic acid has been proposed. In this type of golf ball, the monomers had been grafted on the main chain of the rubber component
10 of polybutadiene in the presence of a free radical initiator to function as a co-cross-linking agent, and thereby hardness is imparted to the ball. However, sufficient durability and bounce impact elasticity have not been obtained with such a golf ball. The hardness
15 of a golf ball can be controlled by the amount of the cross-linking agent; however, an increased amount of the cross-linking agent would cause a decline of the bounce impact elasticity.

For the purpose of the improvement of hardness and
20 wear resistance of rubber compositions, various compositions incorporated with finely divided inorganic material have also been proposed; however, a decrease of the elasticity and decrease of the compression fracture strength are inevitably caused without
25 exception. The incorporation of long staple fibers has been proved to be effective for enhancing the strength of the composition; however, the incorporation of such fibers impairs the surface smoothness and also fails to produce any significant improvement in elasticity and
30 hardness.

Based on the technical concept of those conventional methods mentioned above, the use of fine fibers in a rubber composition was naturally supposed; however, they exhibit poor wettability to a rubber
35 material to cause slippage between their surfaces and the rubber material. Because of the slippage, it is

difficult to obtain the desired properties in such composite material, though the fine fibers can be dispersed uniformly in a given rubber composition. Therefore, providing a suitable surface treatment of the fibers has often remained as a problem to be solved. It is well known that hydrolyzable silyl compounds are effective surface treating agents, but the compound(s) must be selected to suit the particular kind of rubber component used in the composition and the surface treatment with the compound(s) requires highly advanced skill.

We have already found that a sulfur-containing silyl compound possesses an excellent affinity to rubber components and serves as an excellent agent for the surface treatment mentioned above. However, heretofore such sulfur-containing silyl compounds have been invariably directed to sulfur vulcanizing systems, and it has been believed that the sulfur-containing silyl compound can not be used for non-sulfur vulcanizing systems since it has been supposed that the non-sulfur vulcanization would be inhibited with the sulfur-containing silyl compound judging from its vulcanization mechanism.

An object of the invention is to provide a high-performance rubber composition having high elasticity, high strength and high compression property, and vulcanizable with a non-sulfur type vulcanizing agent.

Another object of the invention is to provide a golf ball which has excellent durability, bounce impact elasticity and hardness and which can give excellent feeling upon hitting with a golf club and a long flight distance.

Yet another object of the invention is to provide a rubber composition suitable for molding a cover layer of a golf ball, which has an excellent durability, bounce impact elasticity and hardness and which can

give an excellent feeling upon hitting and a long flight distance when used in a golf ball.

The first aspect of the invention provides a rubber composition comprising at least one natural
5 and/or synthetic component(s), fine inorganic fibers, as hereinafter defined subjected to a surface treatment with a surface treating agent and a non-sulfur type vulcanizing agent. The rubber composition may further comprise a cross-linking monomer.

10 The second aspect of the invention provides a golf ball comprising the rubber composition mentioned above. The golf ball of the present invention includes:

- a) a solid golf ball made solely of the rubber composition mentioned above,
- 15 b) a two-piece golf ball which comprises a core of elastic rubber and a cover layer of a hard elastomer, wherein the core and/or the cover layer are/is composed of the rubber composition mentioned above,
- c) a three-piece golf ball which comprises a core of
20 elastic rubber, an intermediate layer of elastic rubber and a cover layer of hard elastomer, wherein at least one of the core, the intermediate layer and the cover layer is(are) composed of the rubber composition mentioned above, and
- 25 d) a thread wound golf ball which comprises a spherical core, an intermediate layer formed by winding an elastic thread on the spherical core with high tension and a cover layer, wherein the

core and/or the cover layer are/is composed of the rubber composition mentioned above.

The third aspect of the invention provides a rubber composition for a cover layer of a golf ball, which comprises at least one natural and/or synthetic rubber component(s) and alkali metal titanate fibers subjected to a surface treatment with a surface treating agent.

As the rubber component of the composition of the invention, any of the various known rubbers can be used. Examples of the rubber component include natural rubber (NR), isoprene rubber (IR), styrene-butadiene rubber (SBR), nitrile rubber (NBR), butadiene rubber (BR), chloroprene rubber (CR), butyl rubber (IIR), acrylic rubber (AR), urethane rubber (UR), silicone rubber (SiR), fluorocarbon rubber (FR), ethylene-propylene rubber (EPR), chlorosulphonated polyethylene (CSM), ethylene-vinyl acetate rubber (EVA), chlorinated polyethylene (CPE), polyisobutylene (PIB), alfin rubber (AL), polyester rubber (ESR), epichlorohydrin rubber (ECR), chlorinated isobutylene-isoprene rubber (CIR), nitrile-isobutylene rubber (NIR), ionomer resin, trans-polyisoprene resin and the like.

The rubber component preferably contains at least 30 % by weight of polybutadiene of cis-1,4-configuration, because the hardness and bounce impact elasticity of the composition containing such rubber component are particularly improved. Though it is not unclear why this improvement is caused, it is supposed that the reinforcing effect efficiently utilizing the shape of the fine fibers contained in the composition is obtained

due to the reaction of the sulfur component of the surface treating agent with polybutadiene of cis-1,4-configuration. This theory is supported by the fact that a greater improvement of hardness and bounce of impact elasticity can be obtained in the compositions utilizing such sulfur-containing surface treating agent than those utilizing a conventional surface treating agent containing no sulfur component, for example, alkoxysilane type surface treating agent such as methyltrimethoxysilane, methyltriethoxysilane, γ -glycidoxypropyltrimethoxysilane and γ -aminopropyltriethoxysilane.

When the rubber composition of the present invention is used as a hard elastomer of the surface cover layer in a multi-layer golf-ball such as two-piece golf ball, three-piece golf ball, thread wound golf ball and the like, the rubber component is preferably ionomer resin or trans-polyisoprene resin from the viewpoint of the high elasticity and wear resistance.

As an example of the ionomer resin, it can be mentioned an ionic copolymer which is obtained by reacting a copolymer of an α -olefin represented by the general formula of $R-CH=CH_2$ wherein R represents an alkyl group having 1 to 8 carbon atoms and an α,β -unsaturated carboxylic acid having 3 to 8 carbon atoms with a metal compound.

Examples of the α -olefin mentioned above include ethylene, propylene, butene-1, pentene-1, hexene-1, heptene-1, 3-methylbutene-1, 4-methylpentene-1 and the like. Though α -olefins having larger numbers of carbon atoms than those mentioned above may be used in the present invention, they are unsuitable for the practical use because of their unavailability. These α -olefins may be used alone or in any combination thereof.

The content of the α -olefins in the copolymer is preferably at least 50 molar %, particularly at least 80 molar % from the view point of the moldability and physical properties of the composition.

Examples of α, β -unsaturated carboxylic acid^s having 3 to 8 carbon atoms include acrylic acid, methacrylic acid, ethacrylic acid, itaconic acid, maleic acid, fumaric acid; monoester^s of dicarboxylic acid such as monomethyl maleate and monoethyl fumarate; and anhydride^s of dicarboxylic acid such as maleic anhydride, but it is not limited to those specific examples. These α, β -unsaturated carboxylic acids may be used alone or in any combination thereof. The content of α, β -unsaturated carboxylic acid in the copolymer is preferably in the range of 0.5 to 25 mole %, particularly in the range of 1 to 10 mole %. Further, the copolymer may contain any monomer component other than the α -olefin and α, β -unsaturated carboxylic acid, which is copolymerizable with the α -olefin and α, β -unsaturated carboxylic acid to replace a part of the α -olefin. Examples of such^a monomer include styrene, vinyl chloride, vinyl acetate, acrylonitrile vinyl methyl ether and the like.

The copolymer composed of the α -olefin and the α, β -unsaturated carboxylic acid is not limited to those obtained by directly copolymerizing a mixture of the monomers, and it also includes those obtained by graft polymerization where the α, β -unsaturated carboxylic acid monomers are grafted on a base polymer produced from the α -olefin.

The ionic copolymer can be obtained by reacting the copolymer obtained as above with a metal compound generating metal ions to neutralize the copolymer.

Examples of metal ion suitable for the preparation of the ionic copolymer include those of the metals of Group I and Group II of the periodic table, i.e., Na, K, Li, Cs, Cu, Ag, Be, Mg, Ca, Sr, Ba, Zn, Cd and Hg, and they can be used alone or in any combination thereof. Owing to the employment of those metal ions, cross-linkings are advantageously formed during the formation of the ionic copolymer. Among those metal ions cited above, Na and Zn are particularly preferable from the viewpoint of the melt workability of the copolymer and the physical properties exhibited in the solid state of the copolymer. The amount of the ion to be used or the degree of the neutralization of the copolymer can not be specifically fixed, because they are variable depending on the desired properties in the solid state and ^{the} melting property of the ionic copolymer. In order to significantly change the properties of the copolymer in the solid state, the amount of the ion is preferably enough to neutralize at least 10 % of the carboxyl groups in the copolymer, and the neutralization can be generally effected up to about 90 % of the carboxyl groups in the copolymer. The degree of neutralization for optimizing the physical properties of the copolymer also can ^{be} not specifically fixed, because the optimum properties are variable depending on the use for which the copolymer is intended and further because the physical properties of the ionic copolymer are variable depending on the amount of the carboxylic group in the copolymer, the molecular weight of the copolymer and the like. However, it is generally preferable to neutralize at least 50 % of the carboxyl groups in the copolymer.

The metal ions mentioned above can be obtained by dissolving a metal compound generating such ions, for example, an inorganic

metal compound such as sodium hydroxide and sodium carbonate and an organic metal compound such as sodium methoxide, sodium formate and sodium acetate in water or an organic solvent such as methanol.

5 The method for the production of the ionic copolymer from the aforementioned copolymer and the metal ion is not particularly limited, and any conventional method can be used for the production.

10 The molecular weight of the ionic copolymer can be conveniently expressed with the melt index (MI), which serves as a criterion of the metal viscosity and is described in ASTM D 1238. The MI of the ionic copolymer is advantageously in the range of 0.1 to 100 g/10 minutes (190°C), particularly in the range of 0.5
15 to 20 g/10 minutes (190°C). The ionic copolymer of which MI is approximately in the range of 0.1 to 100 g/10 minutes has excellent melt workability and exhibits high toughness, suitable elasticity and flexibility in the solid state.

20 The trans-polyisoprene resin which may be used in the present invention occurs as a main component of natural resin such as balata and gutta-percha obtainable from natural plants and it has a molecular configuration of trans-1,4-polyisoprene. As a typical
25 commercially available product of the resin, Kuraray Trans-Polyisoprene TP-301, Kuraray Isoprene Chemical Co., Ltd. can be mentioned.

30 The term "fine inorganic fibers" in the present invention refers to inorganic fibers having an average length of 1 μ m to 1 mm, preferably 5 to 300 μ m, and an aspect ratio of 5 to 1000, preferably 10 to 300. The fine inorganic fibers having an average length and aspect ratio in the range defined above


exhibit an excellent reinforcing property and uniform dispersibility, and thereby they can produce an uniform strength distribution of the composition. As the fine inorganic fibers of the present invention, inorganic whiskers are particularly preferred. Examples of the fine inorganic fibers include alumina fibers, silicic acid fibers, titania fibers, magnesium silicate fibers, calcium silicate fibers, calcium sulfate fibers, silicon carbide fibers, titanium carbide fibers, boron carbide fibers, boron nitride fibers, titanium nitride fibers, carbon nitride fibers, carbon boride fibers, silicon boride fibers, titanium boride fibers, sodium titanate fibers, potassium titanate fibers, lithium titanate fibers, calcium titanate fibers, magnesium titanate fibers, barium titanate fibers and the like. Among those fine inorganic fibers exemplified above, the potassium titanate fibers are particularly preferable material, because they exhibit an excellent reinforcing effect and heat resistance, permit the coloration of a desired hue owing to the outstanding whiteness thereof, ensure the easy production of fine fibers of uniform length and show uniform dispersibility in the composite material.

The term "potassium titanate fibers" in the present invention refers to single crystal fibers represented by the formula: $K_2O \cdot nTiO_2$ or by the general formula: $K_2O \cdot nTiO_2 \cdot 1/2H_2O$ wherein n is an integer of 2 to 8. Examples of the potassium titanate fibers include potassium tetratitanate fibers, potassium hexatitanate fibers and potassium octatitanate fibers. These potassium titanate fibers can be used alone or in any combination thereof. The potassium titanate fibers preferably possess an average fiber diameter in the range of 0.1 to 2 μm , average fiber

length in the range of 5 to 100 μm and aspect ratio in the range of 10 to 200. The average fiber diameter and the average fiber length are determined by measuring the values of each fiber by means of a scanning electron microscope and calculating the average of those values of at least 10 fibers per each of at least five fields of the view. The aspect ratio is obtained by dividing the average fiber length by the average fiber diameter.

As the surface treating agent for the fine inorganic fibers of the invention, sulfur-containing silane compounds such as a silane compound bearing^a/mercapto group and a sulfide compound bearing^a/silyl group can be mentioned.

Typical examples of the silane compound bearing^a/mercapto group mentioned above are those compound^s represented by the general formula:



wherein each R^1 independently represents a substituted or unsubstituted divalent hydrocarbon group of 2 to 6 carbon atoms, each R^2 independently represents a substituted or unsubstituted monovalent hydrocarbon group, each X independently represents a hydrolyzable group, a is an integer of from 1 to 3, and b is an integer of from 0 to 2 with proviso of $1 \leq (a+b) \leq 3$.

Examples of R^1 include ethylene group, trimethylene group, tetramethylene group, pentamethylene group, hexamethylene group and the like. Among the examples mentioned above, R^1 is preferably^{an}/ethylene group or trimethylene group, particularly^a / trimethylene group.


Examples of R^2 include an alkyl group such as^a/methyl group, ethyl group, propyl group, butyl group, pentyl group, hexyl

group, octyl group, decyl group, dodecyl group and octadecyl group; alkenyl group such as vinyl group and allyl group; aryl group such as phenyl group and tolyl group; aralkyl group such as benzyl group, β -phenylethyl group and β -phenylpropyl group; and substituted hydrocarbon group such as β -cyanoethyl group, γ -chloropropyl group, 3,3,3-trifluoropropyl group and chlorophenyl group. The group of R_2 is selected depending on the kind of the rubber component and the purpose to which the product is intended. The group of R^2 of a long chain alkyl is suitable for a rubber component containing no aromatic ring, R^2 of aryl group or aralkyl group is suitable for a rubber component containing aromatic rings and R^2 of a substituted hydrocarbon group is suitable for a rubber component containing substituents such as halogen atoms or nitrile groups.

The symbol X represents a hydrolyzable group bonding to a silicon atom. Examples of the group X include an alkoxy group such as methoxy group, ethoxy group, propoxy group and butoxy group; alkoxyalkoxy group such as β -methoxyethoxy group, β -ethoxyethoxy group and β -butoxyethoxy group; enoxy group such as isopropenyloxy group; ketoximato group such as dimethyl ketoximato group and methylethyl ketoximato group; amino group such as diethylamino group and dibutylamino group; aminooxy group such as diethylaminooxy group; acyloxy group such as acetoxy group and octanoyloxy group; and amide group such as N-methylacetamide group. The group X is preferably selected from lower alkoxy groups of 1 to 4 carbon atoms from the view point of the reactivity with the surface of fine inorganic fibers, and methoxy group is most preferable because of its outstanding reactivity.

The symbol a denotes an integer of from 1 to 3, preferably less than 2 in average, and b denotes an integer of from 0 to 2, preferably not more than 1 in average. If the value of a and b are unduly large, the number of the hydrolyzable groups become small and thereby the reactivity of the compound with the inorganic fibers is lowered. If the value of a is unduly small, the effect of the mercapto group on the rubber component is lowered. Accordingly, ^{the} silane compound bearing mercapto group is preferably controlled such that the average value of a is 1 and that the average value of b is less than 1.

Typical examples of the sulfide compound bearing silyl group are those compounds represented by the following general formula;



wherein each R^3 independently represents a substituted or unsubstituted monovalent hydrocarbon group, each R^4 independently represents a substituted or unsubstituted hydrocarbon group of 2 to 4 carbon atoms, each Y independently represents a hydrolyzable group, c is an integer of from 0 to 2 and n is an integer of from 1 to 6.

Examples of R^3 include alkyl group such as methyl group, ethyl group, propyl group, butyl group, pentyl group, hexyl group, octyl group, decyl group, dodecyl group and octadecyl group; alkenyl group such as vinyl group and allyl group; aryl group such as phenyl group and tolyl group; aralkyl group such as benzyl group, β -phenylethyl group and β -phenylpropyl group; and substituted hydrocarbon group such as β -cyanoethyl group, γ -chloropropyl group, 3,3,3-trifluoropropyl group and chlorophenyl group. The group of R^3 is selected depending on the

kind of the rubber component and the purpose to which the product is intended. The group of R^3 of a long chain alkyl is suitable for a rubber component containing no aromatic ring, R^3 of aryl group or aralkyl group is suitable for a rubber component containing aromatic rings and R^3 of a substituted hydrocarbon group is suitable for a rubber component containing substituents such as halogen atoms or nitrile groups.

Examples of R^4 include ethylene group, trimethylene group, tetramethylene group, pentamethylene group, hexamethylene group and the like. Among the examples mentioned above, R_4 is preferably ethylene group or trimethylene group, particularly trimethylene group.

The symbol Y represents a hydrolyzable group bonding to the silicon atom. Examples of the group Y include an alkoxy group such as methoxy group, ethoxy group, propoxy group and butoxy group; alkoxyalkoxy group such as β -methoxyethoxy group, β -ethoxyethoxy group and β -butoxyethoxy group; enoxy group such as isopropenyloxy group; ketoximato group such as dimethyl ketoximato group and methylethyl ketoximato group; amino group such as diethylamino group and dibutylamino group; aminooxy group such as diethylaminooxy group; acyloxy group such as acetoxy group and octanoyloxy group; and amide group such as N-methylacetamide group. The group Y is preferably selected from lower alkoxy groups of 1 to 4 carbon atoms from the view point of the reactivity with the surface of fine inorganic fibers, and propoxy group is particularly preferable because the compound having propoxy groups as the group of Y can be easily synthesized and ~~have~~^{has} good stability.

The symbol c denotes an integer of from 0 to 2. The sulfide

compound bearing silyl group represented by the formula II preferably contains at least one, preferably two, of the hydrolyzable groups reactive to the surface of the inorganic fibers. Therefore, the value of $\bar{c}$ is preferably less than 2 ^{on} ~~in~~ average. The symbol $\bar{n}$ denotes an integer of from 1 to 6, and the average value of $\bar{n}$ is preferably 2 to 4 from the viewpoint of the ease of synthesis, affinity for the rubber and inability to inhibit the vulcanization of the compound.

Those surface treating agents defined above can be used alone or in any combination thereof.

In the present invention, the fine inorganic fibers are treated with ^{the} ~~a~~forementioned surface treating agent. The amount of the surface treating agent is preferably in the range of about 0.05 % to 10 % by weight based on the amount of the fibers. So long as the amount is in this range, the surface treating agent sufficiently improves the surface property of the fine inorganic fibers, and consequently the physical properties of the rubber composition are improved without inhibiting the subsequent vulcanization.

The treatment with the surface treating agent can be effected according to any of the conventional methods. For example, the treatment can be carried out by spraying the surface treating agent or ^a ~~the~~ dilution of the surface treating agent on the fine inorganic fibers, or mixing the agent with the fibers homogeneously, or impregnating the fibers with the agent to deposit the agent on the surface of the fibers uniformly. Then, the agent on the fibers ^{is} ~~are~~ dried by heating or hydrolyzed to be immobilized on the fibers as a uniform coating.

The surface treating agent used in the invention contains a

sulfur atom in the molecular structure. Hitherto, such compounds, particularly those containing a sulfur atom in a terminal mercapto group have been known to cause inhibition of the vulcanization utilizing a peroxide type vulcanizing agent and impair the physical properties of rubber. However, it was found that the surface treating agent manifested the surface treating effect such that the rubber composition has a sufficient hardness and compressive strength with uniform vulcanization, i.e., without any inhibition of the vulcanization. In the rubber composition, the rubber component adheres to the inorganic fibers strongly and the slippage at the interface between the fibrous filler and the rubber matrix is suppressed, the slippage being recognized to cause the deterioration of the physical properties of the rubber composition as described above.

As the cross-linking monomer which may be used in the present invention, unsaturated carboxylic acids, salts thereof and other unsaturated vinyl compounds may be used. Examples of the unsaturated carboxylic acid include acrylic acid, methacrylic acid, 2-acetoaminoacrylic acid, β,β -dimethacrylic acid, ethacrylic acid, α -chloroacrylic acid, cinnamic acid, acotinic acid, 2-ethyl-3-propylacrylic acid, crotonic acid, aminocrotonic acid, acidophoshydroxyethyl(meth) acrylate, β -acryloxypropionic acid, 2-butene-1,4-dicarboxylic acid, sorbic acid, acetylcarboxylic acid, N-butylmaleamidic acid, fumaric acid, maleic acid, chloromaleic acid, di-n-butylmaleamidic acid, N,N-dimethylmaleamidic acid, N-ethylmaleamidic acid, N-phenyl-maleamidic acid, dichrolomaleic acid, dihydroxymaleic acid, allylarsonic acid, chloroendeic acid, itaconic acid, benzoyl-acrylic acid and the like. Examples of the other unsaturated

vinyl compound include vinyl compound^s such as vinyl acetate, vinyl propionate, vinyl caproate, styrene, vinyltoluene and divinylbenzene; alkyl ester^s of acrylic acid such as alkyl acrylate and alkyl methacrylate; (meth)acrylic acid derivatives such as (meth)acrylonitrile, (meth)acrylamide and glycidyl (meth)acrylate; and triallylisocyanurate. Among those compound^s mentioned above, it is particularly preferable to select the cross-linking monomer from the group of acrylic acid, methacrylic acid, cinnamic acid, acotinic acid, crotonic acid, itaconic acid and benzoylacrylic acid. Those compounds can be used alone or in any combination thereof.

The metal salts of the unsaturated carboxylic acid^s mentioned above can be also used as the cross-linking monomer of the present invention. Examples of the metal for those metal salts include lithium, sodium, potassium, strontium, zinc, magnesium, calcium, barium, cadmium, lead, zirconium, beryllium, copper, aluminium, tin, iron, antimony, bismuth, molybdenum, tungsten, nickel and the like, and they can be used alone or in any combination thereof. Metal salt^s of metal ion^s having a valency of at least 2 ^{are} ~~is~~ particularly preferable since they enhance the cross-linking efficiency. Calcium, zinc, magnesium and zirconium are particularly preferred because of their availability and low toxicity. Those metals may be incorporated into the composition either by using the metal salts of the unsaturated carboxylic acid obtained by the reaction of the metallic compound and the unsaturated carboxylic acid, or by adding the unsaturated carboxylic acid and the metallic compound such as metal oxide, metal hydroxide, metal carbonate and the like separately into the rubber component and reacting them in

the mixture system to form metal salts of the unsaturated carboxylic acid. The amount of the cross-linking monomer used in the rubber composition of the present invention is not particularly limited, however, it is preferable to incorporate 0.1 to 50 parts by weight, particularly 1 to 15 parts by weight of the cross-linking agent based on 100 parts by weight of the rubber component to facilitate the control of hardness and bounce impact elasticity of the composition.

Examples of the non-sulfur type vulcanizing agent used in the present invention include metal oxide such as magnesium oxide, lead oxide and zinc oxide; cross-linking resin such as phenol resin, melamine formaldehyde resin, urethane resin polyester resin, polyamide resin and epoxy resin; low molecular weight compound and modified compound of those resins; and organic peroxide such as diacetyl peroxide, dibenzoyl peroxide, dicapryl peroxide, di(p-chlorobenzoyl) peroxide, didecanoyl peroxide, di(2,4-dichlorobenzoyl) peroxide, diisobutyl peroxide, diisononanoyl peroxide, dilauroyl peroxide, dipelargonyl peroxide, dipropynyl peroxide, di(β -carboxypropinoyl) peroxide, methyl ethyl ketone peroxide, cyclohexanone peroxide, dihydroxy-dimethyl-dioxacyclopentane, t-butyl peroxide, t-butylperoxy(2-ethylhexanoate), t-butylperoxyisobutylate, O,O-t-butyl-O-isopropylmonoperoxy carbonate, t-butylperoxy-pivalate, dimethyl-di(benzoylperoxy)hexane, t-butylperoxy(2-ethylbutylate), di-t-butyl peroxide, dicumyl peroxide, dimethyl-bis(t-butylperoxy)hexane, t-butyl hydroperoxide, cumyl hydroperoxide, bis(t-butylperoxy)trimethylcyclohexane and n-butyl-bis(t-butylperoxy)valerate and the like. Among those non-sulfur type vulcanizing agent mentioned above, dicumyl

peroxide, cumyl hydroperoxide, t-butyl peroxide, dibutyl peroxide, bis(t-butylperoxy)trimethylcyclohexane and n-butyl-bis(t-butylperoxy)valerate are particularly preferred because those vulcanizing agent^s can proceed the vulcanization uniformly as favored by the relation between the vulcanizing temperature and the half-life. Those non-sulfur type vulcanizing agent can be used alone or in any combination thereof. The amount of the vulcanizing agent used in the rubber composition may be variable depending on factors such as the type of rubber, the purpose of the rubber composition, and the like; however, it is usually preferable to use it in an amount of 0.1 to 15 weight % of the rubber component.

The rubber composition of the present invention may be incorporated with various known additives, for example, vulcanization accelerator, vulcanization retarder, antioxidant, plasticizer, peptizer, tackifier, antitack agent, sponging agent, dispersant, dusting agent, mold release agent, solvent, softening agent and the like. Additionally, various inorganic fillers for reinforcing the material and any desired pigment and dye for coloring the composition may be also incorporated in the rubber composition. Examples of the inorganic filler include clayish powders of carbon black, magnesium carbonate, zinc oxide, calcium carbonate, barium sulfate, aluminium hydroxide, aluminium oxide, silica powder, titanium dioxide, mica, talc, clay, diatomaceous earth, kaolin and the like. The rubber composition of the present invention may also contain any of ^{the} organic modifiers conventionally used, and examples of such organic modifier include cumarone-indene resin, phenol resin, polystyrene resin, acrylic resin, polyamide resin, epoxy resin, urethane resin,

polyolefin resin and the like. Further, the rubber composition of the invention may include long fiber reinforcing material, for example, inorganic fibers such as glass fibers, carbon fibers, metal fibers, quartz fibers and ceramic fibers, and organic fibers such as nylon fibers, vinylon fibers, polyester fibers, aromatic polyamide fibers, polyimide fibers and aromatic polyether amide fibers.

The rubber composition of the invention can be produced by kneading one or more rubber components with the fine inorganic fibers of which surfaces are treated with the surface treating agent, the non-sulfur type vulcanizing agent, and optionally with cross-linking monomers, various additives and auxiliaries by a conventional method. The vulcanization of the rubber composition according to the present invention can be also carried out in a conventional manner, and the vulcanization is preferably carried out at a temperature of from 80°C to 180°C for 5 to 60 minutes,

The mixing ratio of each component is not specifically limited and can be varied depending on the kind of rubber component used in the composition and the purpose for which the composition is intended to be used. As concerns the amount of the surface treated fine inorganic fibers, it is preferable to incorporate 2 to 100 parts by weight, particularly 10 to 50 parts by weight of the surface treated fine inorganic fibers into 100 weight parts of the rubber component. When the content of the fibers is less than the lower limit of the range, it becomes difficult to obtain a sufficient strength of the composition though it has a sufficient flexibility, and when the content of the fibers exceeds the upper limit of the range, the composition becomes unsuitable for practical use because it gets excessive

hardness and poor elongation ratio while the strength is enhanced.

The rubber composition according to the present invention can be used for various purposes, for example, industrial materials such as rubber rollers, sporting goods such as golf balls, baseballs, shoe soles and many applications in other fields such as electronic device industry, telecommunication device industry and chemical industry.

10 In the case where the rubber composition is used in the production of a golf ball, the rubber composition may include a weight adjusting agent.

15 The solid golf ball of the present invention is prepared by molding the rubber composition of the present invention, which has been kneaded and vulcanised as described above, in the shape of a golf ball.

20 The two-piece golf ball of the present invention can be produced by covering a core of an elastic rubber with a layer of hard elastomer and molding the resultant composite in the shape of a golf ball having desired surface characteristics such as dimples, wherein the core and/or the cover are/is composed of the rubber composition of the present invention.

25 The three-piece golf ball of the present invention can be produced by covering a core of an elastic rubber with an intermediate layer, molding the intermediate layer, vulcanizing the resultant composite, then covering the intermediate layer with a cover layer, 30 molding the resultant composite in the shape of a golf ball and optionally further vulcanizing the molded golf ball, wherein at least one of the core, the intermediate layer and cover layer is(are) composed of the rubber composition of the present invention. The 35 three-piece golf ball of the present invention can be produced by a single molding process, that is, by covering the core with the intermediate layer and the

cover layer successively, then molding and vulcanizing the resultant composite.

The thread wound golf ball of the present invention can be produced by winding a core of elastic rubber with an elastic thread in a conventional manner, covering the thread wound core with hard elastomer and molding the resultant composite in the shape of a golf ball having desired surface characteristics such as dimples. Any known elastic thread can be employed for the preparation, and examples of elastic thread include a thread produced by a known process for the preparation of rubber thread utilizing a rubber material such as natural rubber (NR), polyisoprene rubber (IR) and a blend material of these rubber materials.

When the elastic rubber or the hard elastomer used in the golf ball of the invention is not composed of the rubber composition of the invention, ^{it} ~~they~~ may be composed of any of known rubber materials conventionally used. Particularly, ionomer resin and trans-polyisoprene resin, which are also described hereinbefore as a rubber component used in the rubber composition of the invention, can be suitably used as the material for the hard elastomer of the cover layer.

The golf ball according to the present invention may be treated on its surface with a conventional coating agent.

The golf ball cover composition of the present invention can be obtained by mixing the rubber component mentioned hereinbefore and alkali metal titanate fibers mentioned hereinbefore as the fine inorganic fiber material in a conventional kneader. By covering a golf ball core with the golf ball cover composition according to the invention and molding the

resultant composite, for example, by means of an injection molding machine, a golf ball having an excellent bounce impact elasticity can be obtained.

5 As the rubber component of the golf ball cover composition of the present invention, ionomer resin and trans-polyisoprene resin, which are described above, are particularly preferable since they permit a high elasticity and good wear resistance of the composition.

Examples

10 Now, the present invention will be described more specifically with reference to working examples and comparative experiments hereafter; however, it should be noted that the present invention is not intended to be restricted within those specific examples.

15 In the attached tables, *1, *2 and *3 denote products of Japan Synthetic Rubber Co., Ltd. marketed under product codes of "BR-11", "STEREON 720" and "IR-2200", respectively, *4 denotes a product of Seido Kagaku marketed under the product code "Zinc White No. 20 3" and *5 denotes a product of Nippon Silica Co., Ltd. marketed under the trade name "Nipseal VN 3AQ".

The potassium titanate fine fibers (untreated) were obtained from Otsuka Chemical Co., Ltd. as a commercially available product under the trade name 25 "Tismo D" (The word "Tismo" is a Trade Mark).

The surface treated fibers A were obtained by treating Tismo D with 1 % of bis(3-triethoxysilylpropyl)tetrasulfide.

30 The surface treated fibers B were obtained by treating Tismo D with 1 % of γ -mercaptopropyltrimethoxysilane.

The surface treated fibers C were obtained by treating

Tismo D with 1 % of γ -mercaptopropyltriethoxysilane.

The surface treated fibers D were obtained by treating Tismo D with 1 % of bis(3-trimethoxysilylpropyl)tetrasulfide.

The surface treated fibers E were obtained by treating Tismo D with 1 % of γ -glycidoxypropyltrimethoxysilane.

The surface treated fibers F were obtained by treating Tismo D with 1 % of bis(mercaptopropyl)tetramethylsiloxane.

The surface treated fibers G were obtained by treating Tismo D with 1 % of bis(3-trimethoxysilylpropyl)disulfide.

The surface treated fibers H were obtained by treating silicon carbide whiskers produced by Tokai Carbon Co., Ltd. and marketed under a trade name of "Tokawhisker" with 1 % of γ -mercaptopropylethoxysilane.

The surface treated fibers I were obtained by treating Tokawhisker with 1 % of bis(3-trimethoxysilylpropyl)tetrasulfide.

The durability index of a given sample was determined by cyclically exerting a compression enough to produce a deformation of 10 mm on the sample and taking count of the number of compression cycles upto the rupture of the sample, and reported as a relative value based on the durability index of Example 1 taken as 100. The bounce impact elasticity was determined by allowing a given sample to fall from a height of 120 cm in an atmosphere kept at 20°C and measuring the height to which the sample bounced according to the specification of JIS (Japan Industrial Standard) S 7005. The compression was evaluated as the strength exhibited by a given sample compressed 2.54 mm in diameter.

Examples 1 to 18 and Comparative Experiments 1 to 7

All of the ingredients, of which formulating ratios are

indicated in Table 1 in parts by weight and each column corresponds to each Example or Comparative Experiment (the same shall apply hereafter), excepting a vulcanizing agent were introduced in a kneader and kneaded for 10 minutes at 60 to 100°C, then the resultant mass was cooled to 60°C to 70°C and admixed with the vulcanizing agent to form a rubber composition of the present invention. The composition was kneaded and vulcanized in a test mold for 30 minutes at 150 ± 5°C to form a test piece, which was subjected to measurements of the tensile strength and tear strength. The same procedure as described above was repeated for each Example and Comparative Experiment.

The results are also shown in Table 1.

Examples 19 to 36 and Comparative Experiments 8 to 14

Rubber compositions were produced by repeating the procedure of Examples 1 to 18 excepting that the formulating ratios indicated in Table 2 were used, and the properties of the obtained compositions were tested.

The results are also shown in Table 2.

Examples 37 to 56 and Comparative Experiments 15 to 21

All of the ingredients of which formulating ratios are indicated in Table 3 excepting the vulcanizing agent were introduced into a kneader and kneaded for 10 minutes at a temperature of 60°C to 100°C, then cooled to a temperature of 60°C to 70°C and admixed with the vulcanizing agent. The density of the resultant mass was adjusted to form a golf ball of 45 g in weight and vulcanized in a conventional golf ball mold for 30 minutes at 150 ± 5°C to produce a solid golf ball, of which bounce impact elasticity, durability, compression and feeling upon hitting were measured and tested. The same procedure as described above was repeated for each Example and Comparative Experiment.

The results are also shown in Table 3.

Examples 57 to 63 and Comparative Experiments 22 to 27

Solid golf balls were produced by repeating the procedure of Examples 37 to 56, excepting that the formulating ratios indicated in Table 4 were used, and the properties of the obtained balls were tested.

The results are also shown in Table 4.

Examples 64 to 72 and Comparative Experiments 28 and 29

Solid golf balls were produced by repeated the procedure of Examples 37 to 56, excepting that the formulating ratios indicated in Table 5 were used, and properties of the obtained balls were tested.

The results are also shown in Table 5.

Examples 73 to 82 and Comparative Experiments 30 to 33

Solid golf balls were produced by repeating the procedure of Examples 37 to 56, excepting that the formulating ratios indicated in Table 6 were used, and properties of the obtained balls were tested.

The results are also shown in Table 6.

Examples 83 to 86 and Comparative Experiments 34 to 39

All of the ingredients of which formulating ratios are indicated in Table 7 excepting the vulcanizing agent were introduced into a kneader and kneaded for 10 minutes at a temperature of 60°C to 100°C, then cooled to a temperature of 60°C to 70°C and admixed with the vulcanizing agent. The resultant mass was vulcanized in a metal mold for a golf ball core for 30 minutes at 150 ± 5°C to produce a golf ball core. The thus obtained

core was covered with a composition prepared by mixing 100 parts of ionomer resin and 10 parts of titanium oxide such that the ball weighed 45 g and injection molded by means of ^{an} injection molding machine to form a two-piece golf ball. The same procedure as described above was repeated for each Example and Comparative Experiment. The bounce impact elasticity, durability, compression and feeling upon hitting of the obtained golf balls were measured and tested.

The results are also shown in Table 7.

Examples 87 to 90

Two-piece golf balls were produced by repeating the procedure of Examples 83 to 86, excepting that the formulating ratios of the cores indicated in Table 8 were used and that a hard elastomer obtained by mixing 100 parts of ionomer resin and potassium titanate fibers (surface treated fibers A) was used as the cover layer.

The properties of the obtained balls were tested, and the results are also shown in Table 8.

Examples 91 to 96

Two-piece golf balls were produced by repeating the procedure of Examples 83 to 86, excepting that the formulating ratios of the cores indicated in Table 9 were used, and the properties of the obtained balls were tested.

The results are also shown in Table 9.

Examples 97 to 100

Two-piece golf balls were produced by repeating the procedure of Examples 91 to 96, excepting that the formulating ratios of the cores indicated in Table 10 were used and that a hard elastomer obtained by mixing 100 parts of ionomer resin and

potassium titanate fibers (surface treated fibers A) was used as the cover layer.

The properties of the obtained balls were tested, and the results are also shown in Table 10.

Examples 101 to 116

Two-piece golf balls were produced by covering the same golf ball cores as Example 92 with the covering compositions of which formulating ratios are shown in Table 11; and the properties of the obtained balls were tested.

The results are also shown in Table 11.

Examples 117 to 127

Two-piece golf balls were produced by covering golf ball cores of which formulating ratios are shown in Table 12 with the same cover layers as Examples 103, 107 and 104, which were used for Examples 117 to 119, Examples 120 to 123 and Examples 124 to 127, respectively.

The properties of the obtained balls were tested and the results are also shown in Table 12.

Examples 128 to 136 and Comparative Experiments 40 to 41

Three-piece golf balls were produced by utilizing cores of which formulating ratios are shown in Table 13, and an intermediate layer and a cover layer of which formulating ratios are shown below.

The properties of the obtained balls were tested, and the results are also shown in Table 13.

Intermediate layer:	Examples	Comparative Experiments
Rubber (BR)	100	100
Zinc acrylate	15	-
Zinc oxide	10	15
Aerosolizable silica	10	30
Dicumyl peroxide	5	5
Antioxidant	4	4
Stearic acid	2	2
Surface treated fibers A	20	-

Cover layer:

Ionomer resin	100
Titanium dioxide	10

Examples 137 to 142 and Comparative Experiments 42 to 47

Three-piece golf balls were produced by utilizing cores of which formulating ratios are shown in Table 14, and an intermediate layer and a cover layer of which formulating ratios are shown below.

The properties of the obtained balls were tested, and the results are also shown in Table 14.

Intermediate layer:	Examples	Comparative Experiments
Rubber (BR)	100	100
Zinc acrylate	15	10
Zinc oxide	10	15
Aerosolizable silica	10	40
Dicumyl peroxide	5	5
Antioxidant	4	5
Stearic acid	2	2
Surface treated fibers A	20	-

Cover layer:

Ionomer resin	100
Titanium dioxide	10

Examples 143 to 146

Three-piece golf balls were produced by repeating the procedure of Examples 137 to 142 excepting that the formulating ratios of cores indicated in table 15 were used and that a hard elastomer prepared by mixing 100 parts of ionomer resin with 10 parts of the surface treated fibers A was used as the cover layer.

The properties of the obtained balls were tested, and the results are also shown in Table 15.

Comparative Experiments 48 to 51

Three-piece golf balls were produced by repeating the procedure of Comparative Experiments 42 to 47 excepting that the formulating ratios of cores indicated in Table 15 were used, and the properties of the obtained balls were tested.

The results are also shown in Table 15.

Examples 147 to 150 and Comparative Experiments 52 to 55

Three-piece golf balls were produced by repeating the procedure of Examples 143 to 146 and Comparative Experiments 48 to 51 excepting that the formulating ratios of cores indicated in Table 16 were used, and the properties of the obtained balls were tested.

The results are also shown in Table 16.

Example 151 to 161

Three-piece golf balls were produced by utilizing the same cores and intermediate layer as used in Example 138, and the cover layers of which formulating ratios are indicated in Table 17.

The properties of the obtained balls were tested and the results are also shown in Table 17.

Examples 162 to 172

Three-piece golf balls were produced by utilizing cores of which formulating ratios are indicated in Table 18. The same cover layers as Examples 153, 157 and 154 were used for Examples 162 to 164, Examples 165 to 168 and Examples 169 to 172, respectively. The intermediate layers of the compositions A and B indicated below and the same intermediate layer as Example 128 were used for examples 162 to 164, Examples 165 to 167 and Examples 168 to 172, respectively.

The properties of the obtained balls were tested and the results are also shown in Table 18.

Intermediate layers:	A	B
Rubber (BR)	100	100
Zinc acrylate	-	20
Calcium acrylate	20	-
Zinc oxide	10	15
Aerosolizable silica	-	15
Aerosolizable titanium dioxide	10	-
Dicumyl peroxide	5	5
Antioxidant	4	4
Stearic acid	2	2
Surface treated fibers A	30	-
Surface treated fibers B	-	30

Examples 173 to 178 and Comparative Experiments 56 to 61

All of the ingredients indicated in Table 19 except for the vulcanizing agent were introduced into a kneader and kneaded at the temperature of 60°C to 100°C for 10 minutes. The contents of the kneader were cooled to 60°C to 70°C, then ~~added~~^{admixed} with the vulcanizing agent, adjusted in weight and further kneaded. The resultant mass was vulcanized in a conventional mold for a golf ball core at 150°C ± 5°C for 30 minutes to produce a spherical core. The core thus obtained was wound with an elastic thread, which was a NR-based rubber thread and also used in the following Examples. The resultant thread wound core was covered with a composition obtained by blending 100 parts of ionomer with 10 parts of titanium oxide and injection molded to produce a thread wound golf ball of 45 g in weight. The same procedure^d was repeated for each Example and Comparative Experiment.

The obtained golf balls were tested for bounce impact

elasticity, durability, compression and feeling upon hitting, and the results are also shown in Table 19.

Example 179 to 182

Thread wound golf balls were produced by repeating the procedure of Examples 173 to 178 excepting that cover layers of hard elastomer obtained by blending 100 parts of ionomer resin with 10 parts of the surface treated fibers A and cores of which formulating ratios are indicated in Table 20 were used.

The properties of the obtained balls were tested, and the results are also shown in Table 20.

Examples 183 to 188 and Comparative Experiments 62 to 67

Thread wound golf balls were produced by repeating the procedure of Examples 173 to 178 excepting that cores of which formulating ratios are indicated in Table 21 were used, and the properties of the obtained balls were tested.

The results are also shown in Table 21.

Example 189 to 192

Thread wound golf balls were produced by repeating the procedure of Example 183 to 188 excepting that cores of which formulating ratios are indicated in Table 22 were used and that cover layers of hard elastomer obtained by blending 100 parts of ionomer resin with 10 parts of the surface treated fibers A were used.

The properties of the obtained balls were tested and the results are also shown in Table 22.

Examples 193 to 203

Thread wound golf balls were produced by covering the same thread wound cores as Example 184 with cover layers of which formulating ratios are shown in Table 23.

The properties of the obtained balls were tested and the results are also shown in Table 23.

Examples 204 to 214

Thread wound golf balls were produced by utilizing cores of which formulating ratios are indicated in Table 24. The same cover layers as Examples 195, 199 and 196 were used for Examples 204 to 206, Examples 207 to 210 and Examples 211 to 214, respectively.

The properties of the obtained balls were tested and the results are also shown in Table 24.

Examples 215 to 224

In a kneader, 100 parts of rubber (BR *1), 10 parts of zinc acrylate, 15 parts of zinc oxide (*2) and 15 parts of potassium titanate fibers (untreated) were blended at 60°C to 100°C for 10 minutes. Then, the contents of the kneader were cooled to 60°C 70°C, mixed with 5 parts of dicumyl peroxide, adjusted in weight, and further kneaded. The resultant mass was vulcanized in a conventional mold for golf ball at 150°C $\pm$ 5°C for 30 minutes to produce a golf ball core. The resultant core was covered with a layer of which formulating ratio is indicated in Table 25 to form a two-piece golf ball. The same procedure was repeated for each Example.

The properties of the obtained balls were tested and the results are also shown in Table 25.

Example 225 to 230

Two-piece golf balls were produced by repeating the procedure of Examples 215 to 224 excepting that cores of which formulating ratios are indicated in Table 26 were used and that a hard elastomer obtained by blending 100 parts of ionomer resin

with 10 parts of the surface treated fibers A was used as the cover layers.

The properties of the obtained balls were tested and the results are also shown in Table 26.

Comparative Experiments 68 to 75

Two-piece golf balls were produced by repeating the procedure of Example 215 to 224 excepting that cover layers of which formulating ratios are indicated in Table 27 were used.

The properties of the obtained balls were tested and the results are shown in Table 27.

Examples 231 to 240 and Comparative Experiments 76 to 83

In a kneader, 100 parts of rubber (BR *1), 10 parts of zinc acrylate, 15 parts of zinc oxide (*2), 4 parts of an antioxidant, 2 parts of stearic acid and 15 parts of potassium titanate fibers (untreated) were kneaded at 60°C to 100°C for 10 minutes. Then, the contents of the kneader were cooled to 60°C to 70°C, mixed with 5 parts of dicumyl peroxide, adjusted in weight and further kneaded. The resultant mass was vulcanized in a conventional mold for golf ball core at 150°C ± 5°C for 30 minutes to form a golf ball core. Three-piece golf ball was produced by utilizing the above-obtained core, intermediate layer of the same composition as the core and cover layer of which formulating ratio is indicated in Table 28 or Table 29. The same procedure was repeated for each Example and Comparative Experiment.

The properties of the obtained balls were tested and the results are shown in Table 28 and Table 29.

Examples 241 to 250 and Comparative Experiments 84 to 91

In a kneader, 100 parts of rubber (BR *1), 10 parts of zinc acrylate, 15 parts of zinc oxide (*2), 10 parts of aerosolizable

silica (*3) and 15 parts of potassium titanate fibers (untreated) were kneaded at 60°C to 100°C for 10 minutes. Then, the contents of the kneader were cooled to 60°C to 70°C, mixed with 5 parts of dicumyl peroxide, adjusted in weight and further kneaded. The resultant mass was vulcanized in a conventional mold for golf ball core at 150°C $\pm$ 5°C for 30 minutes to form a golf ball core. The core was wound with the elastic thread, then covered with cover layer of which formulating ratio is indicated in Table 30 or Table 31 and injection molded by means of ^{an} injection machine to produce a thread wound golf ball of 45 g in weight. The same procedure was repeated for each Example and Comparative Experiment.

The properties of the obtained balls were tested and the results are shown in Table 30 and Table 31.

Table 1

	Examples				Comparative Experiments						
	1	2	3	4	1	2	3	4	5	6	7
Rubber (BR) *1	100	100	100	100	100	100	100	100	100	100	100
Zinc oxide *4	15	15	15	15	15	15	15	15	15	15	15
Aerosolizable silica *5	20	20	20	20	50	30	20	20	20	20	20
Dicumyl peroxide	5	5	5	5	5	5	5	5	5	5	-
Sulfur	-	-	-	-	-	-	-	-	-	-	5
Antioxidant	4	4	4	4	4	4	4	4	4	4	4
Stearic acid	2	2	2	2	2	2	2	2	2	2	2
Potassium titanate fibers (untreated)	-	-	-	-	-	-	30	10	-	-	-
Surface treated fibers											
A	30	10	-	-	-	-	-	-	-	-	-
B	-	-	30	10	-	-	-	-	-	-	-
E	-	-	-	-	-	-	-	-	30	10	30
Tensile strength (kgf/cm ²)	198	187	189	172	104	98	132	128	137	131	138
Tear strength (kgf/cm ²)	93	81	85	78	24	21	46	43	60	52	63

Table 1 (Cont.)

	Examples													
	5	6	7	8	9	10	11	12	13	14	15	16	17	18
Rubber														
BR *1	-	50	-	-	100	100	100	100	30	100	100	100	100	100
SBR *2	100	50	50	-	-	-	-	-	70	-	-	-	-	-
IR *3	-	-	50	100	-	-	-	-	-	-	-	-	-	-
Zinc oxide *4	15	10	10	10	15	10	5	10	15	10	15	15	15	15
Aerosolizable silica *5	25	20	10	10	-	-	-	-	10	-	10	10	10	10
Aerosolizable titanium dioxide	-	-	-	-	10	15	10	10	-	15	-	-	-	-
Dicumyl peroxide	5	5	-	-	5	5	5	-	-	-	-	-	-	-
n-Butyl-bis(t-butyl- peroxy)valerate	-	-	5	5	-	-	-	5	5	5	5	5	5	5
Antioxidant	4	4	4	4	4	4	4	4	4	4	4	4	4	4
Stearic acid	2	2	2	2	2	2	2	2	2	2	2	2	2	2
Surface treated fibers														
A	20	20	-	-	-	-	5	-	-	-	20	25	-	-
B	-	-	25	25	-	-	-	5	10	10	-	-	-	-
C	-	-	-	-	20	-	-	-	-	-	-	-	-	-
D	-	-	-	-	-	30	-	-	-	-	-	-	-	-
H	-	-	-	-	-	-	-	-	-	-	-	-	20	-
I	-	-	-	-	-	-	-	-	-	-	-	-	-	20
Tensile strength (kgf/cm ²)	164	163	157	154	152	156	143	141	152	154	166	169	148	140
Tear strength (kgf/cm ²)	74	72	71	68	67	71	59	57	62	63	76	82	54	56

Table 2

	Examples				Comparative Experiments						
	19	20	21	22	8	9	10	11	12	13	14
Rubber (BR) *1	100	100	100	100	100	100	100	100	100	100	100
Zinc acrylate	10	10	10	10	10	10	10	10	10	10	10
Zinc oxide *4	10	10	10	10	10	10	10	10	10	10	10
Aerosolizable silica *5	20	20	20	20	50	30	20	20	20	20	20
Dicumyl peroxide	3	3	3	3	3	3	3	3	3	3	-
Sulfur	-	-	-	-	-	-	-	-	-	-	3
Antioxidant	2	2	2	2	2	2	2	2	2	2	2
Stearic acid	2	2	2	2	2	2	2	2	2	2	2
Potassium titanate fibers (untreated)	-	-	-	-	-	-	30	10	-	-	-
Surface treated fibers											
A	30	10	-	-	-	-	-	-	-	-	30
B	-	-	30	10	-	-	-	-	-	-	-
E	-	-	-	-	-	-	-	-	30	10	-
Tensile strength (kgf/cm ²)	211	203	205	241	128	121	138	133	141	139	136
Tear strength (kgf/cm ²)	94	82	87	80	41	32	43	39	43	40	38

Table 2 (Cont.)

	Examples														
	23	24	25	26	27	28	29	30	31	32	33	34	35	36	
Rubber															
BR *1	-	50	-	-	100	100	100	100	30	100	100	100	100	100	
SBR *2	100	50	50	100	-	-	-	-	70	-	-	-	-	-	
IR *3	-	-	50	-	-	-	-	-	-	-	-	-	-	-	
Acrylic acid	-	-	-	-	-	-	-	5	10	15	-	-	-	-	
Zinc acrylate	10	-	-	-	15	20	25	-	-	-	15	15	15	15	
Carcium methacrylate	-	15	20	20	-	-	-	-	-	-	-	-	-	-	
Zinc oxide *4	15	10	10	10	15	10	5	10	15	10	15	15	15	15	
Aerosolizable silica *5	25	20	10	10	-	-	-	-	10	-	10	10	15	15	
Aerosolizable titanium dioxide	-	-	-	-	10	15	10	10	-	15	-	-	-	-	
Dicumyl peroxide	5	5	-	-	5	5	5	-	-	-	-	-	-	-	
n-butyl-bis(t-butyl-peroxy)valerate	-	-	5	5	-	-	-	5	5	5	5	5	5	5	
Antioxidant	4	4	4	4	4	4	4	4	4	4	4	4	4	4	
Stearic acid	2	2	2	2	2	2	2	2	2	2	2	2	2	2	
Surface treated fibers															
A	20	20	-	-	-	30	5	-	-	-	20	25	-	-	
B	-	-	25	25	-	-	-	-	10	10	-	-	-	-	
H	-	-	-	-	-	-	-	5	-	-	-	-	20	-	
I	-	-	-	-	20	-	-	-	-	-	-	-	-	20	
Tensile strength (kgf/cm ²)	174	172	168	165	190	192	162	161	176	178	189	191	170	172	
Tear strength (kgf/cm ²)	79	83	81	72	87	89	69	58	62	64	87	89	78	81	

Table 3

	Examples				Comparative Experiments						
	37	38	39	40	15	16	17	18	19	20	21
Rubber (BR) *1	100	100	100	100	100	100	100	100	100	100	100
Zinc oxide *4	15	15	15	15	15	15	15	15	15	15	15
Aerosolizable titanium dioxide	10	10	10	10	50	30	20	20	20	20	20
Dicumyl peroxide	-	-	-	-	5	5	5	5	5	5	-
n-Butyl-bis(t-butylperoxy) valerate	5	5	5	5	-	-	-	-	-	-	-
Sulfur	-	-	-	-	-	-	-	-	-	-	5
Antioxidant	4	4	4	4	4	4	4	4	4	4	4
Stearic acid	2	2	2	2	2	2	2	2	2	2	2
Potassium titanate fibers (untreated)	-	-	-	-	-	-	30	10	-	-	-
Surface treated fibers											
A	20	25	-	-	-	-	-	-	-	-	-
C	-	-	20	-	-	-	-	-	-	-	-
D	-	-	-	30	-	-	-	-	-	-	-
E	-	-	-	-	-	-	-	-	30	10	30
Durability index	100	100	101	101	30	34	38	37	39	37	34
Bounce impact elasticity	78	82	81	82	62	64	68	65	65	63	64
Compression	76	78	76	78	63	60	59	58	57	58	58
Feeling upon hitting**	E	E	E	E	B	B	B	B	B	B	B

** E: Excellent, B: Bad

Table 3 (Cont.)

	Examples															
	41	42	43	44	45	46	47	48	49	50	51	52	53	54	55	56
Rubber																
BR *1	100	100	100	100	-	50	-	-	100	100	100	100	30	100	100	100
SBR *2	-	-	-	-	100	50	50	100	-	-	-	-	70	-	-	-
IR *3	-	-	-	-	-	-	50	-	-	-	-	-	-	-	-	-
Zinc oxide *4	15	15	15	15	15	10	10	10	15	10	5	10	15	10	15	15
Aerosolizable silica *5	20	20	20	20	25	20	10	10	-	-	-	-	10	-	-	-
Aerosolizable titanium dioxide	-	-	-	-	-	-	-	-	10	15	10	10	-	15	-	-
Dicumyl peroxide	5	5	5	5	5	5	-	-	5	5	5	-	-	-	5	5
n-Butyl-bis(t-butylperoxy) valerate	-	-	-	-	-	-	5	5	-	-	-	5	5	5	-	-
Antioxidant	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4
Stearic acid	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2
Surface treated fibers																
A	30	10	-	-	20	20	-	-	-	30	5	-	-	-	-	-
B	-	-	30	10	-	-	25	25	-	-	-	-	10	10	-	-
D	-	-	-	-	-	-	-	-	20	-	-	5	-	-	-	-
F	-	-	-	-	-	-	-	-	-	-	-	-	-	-	20	-
G	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	20
Durability index	106	102	104	100	101	102	100	49	50	50	49	50	50	50	122	120
Bounce impact elasticity	82	80	81	78	78	80	76	74	80	82	76	72	74	73	95	90
Compression	81	72	81	71	78	79	75	76	78	79	73	73	74	74	95	93
Feeling upon hitting**	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E

** E: Excellent

Table 4

	Examples							Comparative Experiments					
	57	58	59	60	61	62	63	22	23	24	25	26	27
Rubber													
BR *1	100	80	60	40	20	-	-	100	100	100	40	-	-
SBR *2	-	20	40	60	80	100	-	-	-	-	60	-	-
IR *3	-	-	-	-	-	-	100	-	-	-	-	100	100
Zinc acrylate	8	8	8	8	10	10	10	8	8	8	10	10	10
Zinc oxide *4	15	15	15	15	15	15	15	15	15	15	15	15	15
Aerosolizable silica *5	20	20	20	20	20	20	20	50	20	20	20	20	20
Dicumyl peroxide	5	5	5	5	5	5	5	5	5	5	5	5	5
Antioxidant	4	4	4	4	4	4	4	4	4	4	4	4	4
Stearic acid	2	2	2	2	2	2	2	2	2	2	2	2	2
Potassium titanate fibers (untreated)	-	-	-	-	-	-	-	-	30	-	30	30	30
Surface treated fibers													
A	30	30	30	30	30	30	30	-	-	-	-	-	-
E	-	-	-	-	-	-	-	-	-	30	-	-	-
Durability index	106	111	115	119	120	122	118	36	39	31	39	39	39
Bounce impact elasticity	98	93	91	90	86	84	89	72	80	65	62	63	63
Compression	97	95	94	93	93	96	93	81	81	57	59	60	60
Feeling upon hitting**	E	E	E	E	E	E	E	B	B	B	B	B	B

** E: Excellent, B: Bad

Table 5

	Examples									Comparative Experiments	
	64	65	66	67	68	69	70	71	72	28	29
Rubber (BR) *1	100	100	100	100	100	100	100	100	100	100	100
Zinc acrylate	1	10	15	20	25	30	50	8	8	-	100
Zinc oxide *4	10	10	10	10	10	10	10	15	15	10	10
Aerosolizable silica *5	15	15	15	15	15	15	15	-	-	15	15
Dicumyl peroxide	5	5	5	5	5	5	5	5	5	5	5
Antioxidant	4	4	4	4	4	4	4	4	4	4	4
Stearic acid	2	2	2	2	2	2	2	2	2	2	2
Surface treated fibers											
A	20	20	20	20	20	20	20	-	-	20	20
F	-	-	-	-	-	-	-	20	-	-	-
G	-	-	-	-	-	-	-	-	20	-	-
Durability index	102	105	103	104	101	99	94	123	124	38	37
Bounce impact elasticity	95	96	95	92	89	87	86	93	91	81	67
Compression	88	90	91	93	96	101	112	93	94	80	57
Feeling upon hitting**	E	E	E	E	E	E	E	E	E	E	B

** E: Excellent, B: Bad

Table 6

	Examples										Comparative Experiments			
	73	74	75	76	77	78	79	80	81	82	30	31	32	33
Rubber														
BR *1	100	50	-	-	100	100	100	100	30	100	100	100	-	-
SBR *2	-	50	50	100	-	-	-	-	70	-	-	-	100	100
IR *3	-	-	50	-	-	-	-	-	-	-	-	-	-	-
Acrylic acid	-	-	-	-	1	-	-	5	10	15	-	-	-	-
Zinc acrylate	10	-	-	-	15	20	25	-	-	-	10	-	-	10
Carcium methacrylate	-	15	20	20	-	-	-	-	-	-	-	-	-	-
Zinc oxide *4	15	10	10	10	15	10	5	10	15	10	15	15	15	15
Aerosolizable silica *5	25	20	10	10	-	-	-	-	10	-	-	-	-	-
Aerosolizable titanium dioxide	-	-	-	-	10	15	10	10	-	15	25	40	30	25
Dicumyl peroxide	5	5	-	-	5	5	5	-	-	-	-	-	-	-
n-Butyl-bis(t-butyl-peroxy)valerate	-	-	5	5	-	-	-	5	5	5	5	5	5	5
Antioxidant	4	4	4	4	4	4	4	4	4	4	4	4	4	4
Stearic acid	2	2	2	2	2	2	2	2	2	2	2	2	2	2
Potassium titanate fibers (untreated)	-	-	-	-	-	-	-	-	-	-	20	-	-	20
Surface treated fibers														
A	20	20	-	-	20	30	5	-	-	-	-	-	-	-
B	-	-	25	25	-	-	-	5	-	-	-	-	-	-
C	-	-	-	-	-	-	-	-	10	-	-	-	-	-
D	-	-	-	-	-	-	-	-	-	10	-	-	-	-
Durability index	103	111	112	120	123	127	110	97	97	98	39	38	41	37
Bounce impact elasticity	95	93	90	88	94	94	87	89	90	88	81	80	78	72
Compression	96	95	94	91	93	92	86	88	92	86	79	81	78	71
Feeling upon hitting**	E	E	E	E	E	E	E	E	E	E	B	B	B	B

** E: Excellent, B: Bad

Table 7
Formulating Ratios of Cores

	Examples				Comparative Experiments					
	83	84	85	86	34	35	36	37	38	39
Rubber (BR) *1	100	100	100	100	100	100	100	100	100	100
Zinc oxide *4	15	15	15	15	15	15	15	15	15	15
Aerosolizable silica *5	10	10	10	10	10	10	10	10	10	30
Dicumyl peroxide	5	5	5	5	5	5	5	5	5	5
Antioxidant	4	4	4	4	4	4	4	4	4	4
Stearic acid	2	2	2	2	2	2	2	2	2	2
Potassium titanate fibers (untreated)	-	-	-	-	10	15	20	25	-	-
Surface treated fibers										
A	10	15	20	25	-	-	-	-	-	-
E	-	-	-	-	-	-	-	-	20	-
Durability index	110	125	129	134	46	47	47	48	47	45
Bounce impact elasticity	99	101	101	103	86	87	87	86	91	84
Compression	107	109	112	116	93	94	93	95	92	89
Feeling upon hitting**	E	E	E	E	B	B	B	B	B	B

** E: Excellent, B: Bad

Table 8
Formulating Ratios of Cores

	Examples			
	87	88	89	90
Rubber (BR) *1	100	100	100	100
Zinc oxide *4	15	15	15	15
Aerosolizable silica *5	10	10	10	10
Dicumyl peroxide	5	5	5	5
Antioxidant	4	4	4	4
Stearic acid	2	2	2	2
Surface treated fibers A	10	15	20	25
Durability index	118	131	134	138
Bounce impact elasticity	101	103	103	106
Compression	108	111	111	119
Feeling upon hitting**	E	E	E	E

** E: Excellent

Table 9
Formulating Ratios of Cores

	Examples					
	91	92	93	94	95	96
Rubber (BR) *1	100	100	100	100	100	100
Zinc acrylate	10	10	10	10	10	8
Zinc oxide *4	15	15	15	15	10	10
Aerosolizable silica *5	10	10	10	10	-	-
Dicumyl peroxide	5	5	5	5	5	-
n-Butyl-bis(t-butylperoxy)- valerate	-	-	-	-	-	5
Antioxidant	4	4	4	4	4	4
Stearic acid	2	2	2	2	2	2
Surface treated fibers						
A	10	15	20	25	-	-
F	-	-	-	-	30	-
G	-	-	-	-	-	30
Durability index	122	138	142	146	136	133
Bounce impact elasticity	105	106	106	107	105	104
Compression	120	121	123	123	123	121
Feeling upon hitting**	E	E	E	E	E	E

** E: Excellent

Table 10
Formulating Ratios of Cores

	Examples			
	97	98	99	100
Rubber (BR) *1	100	100	100	100
Zinc acrylate	10	10	10	10
Zinc oxide *4	15	15	15	15
Aerosolizable silica *5	10	10	10	10
Dicumyl peroxide	5	5	5	5
Antioxidant	4	4	4	4
Stearic acid	2	2	2	2
Surface treated fibers A	10	15	20	25
Durability index	127	142	148	151
Bounce impact elasticity	106	108	108	109
Compression	122	123	124	126
Feeling upon hitting**	E	E	E	E

** E: Excellent

Table 11

Formulating Ratios of Cover Layers

**** E: Excellent**

[illegible]

Table 12

	Examples										
	117	118	119	120	121	122	123	124	125	126	127
Rubber											
BR *1	100	100	30	-	-	10	100	50	10	20	-
SBR *2	-	-	70	100	-	90	-	50	90	80	50
IR *3	-	-	-	-	100	-	-	-	-	-	50
Acrylic acid	-	-	-	20	-	-	-	-	-	-	-
Zinc acrylate	20	25	10	-	-	10	-	-	-	-	-
Carcium methacrylate	-	-	-	-	25	-	-	-	-	-	-
Zinc oxide *4	10	5	15	10	5	15	15	15	15	15	20
Aerosolizable silica *5	-	-	10	15	10	10	10	-	-	-	-
Aerosolizable titanium dioxide	15	10	-	-	-	-	-	10	10	10	15
Dicumyl peroxide	5	5	-	5	5	5	-	5	5	5	5
n-Butyl-bis(t-butyl- peroxy)valerate	-	-	5	-	-	-	5	-	-	-	-
Antioxidant	4	4	4	4	4	4	4	4	4	4	4
Stearic acid	2	2	2	2	2	2	2	2	2	2	2
Surface treated fibers											
A	30	-	-	-	-	25	-	-	20	-	20
B	-	5	-	-	15	-	20	-	-	20	-
C	-	-	10	-	-	-	-	25	-	-	-
D	-	-	-	15	-	-	-	-	-	-	-
Durability index	158	142	144	121	128	136	132	148	149	148	149
Bounce impact elasticity	108	102	101	94	90	96	102	101	102	100	103
Compression	128	109	106	102	101	103	106	118	121	121	122
Feeling upon hitting**	E	E	E	E	E	E	E	E	E	E	E

** E: Excellent

Table 13
Formulating Ratios of Cores

	Examples									Comparative Experiments	
	128	129	130	131	132	133	134	135	136	40	41
Rubber (BR) *1	100	100	100	100	100	100	100	100	100	100	100
Zinc oxide *4	15	15	15	15	15	15	15	15	15	15	15
Aerosolizable silica *5	10	10	10	10	10	10	10	10	30	15	15
Dicumyl peroxide	5	5	5	5	5	5	5	5	5	5	5
Antioxidant	4	4	4	4	4	4	4	4	4	4	4
Stearic acid	2	2	2	2	2	2	2	2	2	2	2
Potassium titanate fibers (untreated)	-	-	-	-	10	15	20	-	-	20	-
Surface treated fibers											
A	10	15	20	25	-	-	-	-	-	-	-
E	-	-	-	-	-	-	-	20	-	-	20
Durability index	110	123	128	132	91	93	95	90	88	48	49
Bounce impact elasticity	102	103	103	104	103	104	104	103	99	97	98
Compression	107	108	109	109	101	102	102	98	99	88	90
Feeling upon hitting**	E	E	E	E	E	E	E	E	E	B	B

** E: Excellent, B: Bad

Table 14
Formulating Ratios of Cores

	Examples						Comparative Experiments					
	137	138	139	140	141	142	42	43	44	45	46	47
Rubber (BR) *1	100	100	100	100	100	100	100	100	100	100	100	100
Acrylic acid	-	-	-	-	8	8	-	-	-	-	-	-
Zinc acrylate	10	10	10	10	-	-	10	10	10	10	10	10
Zinc oxide *4	15	15	15	15	10	10	15	15	15	15	15	15
Aerosolizable silica *5	10	10	10	10	-	-	10	10	10	10	10	30
Dicumyl peroxide	5	5	5	5	-	-	5	5	5	5	5	5
n-Butyl-bis(t-butyl- peroxy)valerate	-	-	-	-	5	5	-	-	-	-	-	-
Antioxidant	4	4	4	4	4	4	4	4	4	4	4	4
Stearic acid	2	2	2	2	2	2	2	2	2	2	2	2
Pottasium titanate fibers (untreated)	-	-	-	-	-	-	10	15	20	25	-	-
Surface treated fibers												
A	10	15	20	25	-	-	-	-	-	-	-	-
E	-	-	-	-	-	-	-	-	-	-	20	-
F	-	-	-	-	30	-	-	-	-	-	-	-
G	-	-	-	-	-	30	-	-	-	-	-	-
Durability index	123	140	144	148	136	133	52	52	52	53	52	49
Bounce impact elasticity	105	107	107	108	104	103	92	92	93	94	92	86
Compression	121	123	125	125	111	115	110	113	113	114	108	106
Feeling upon hitting**	E	E	E	E	E	E	B	B	B	B	B	B

** E: Excellent, B: Bad

Table 15
Formulating Ratios of Cores

	Examples				Comparative Experiments			
	143	144	145	146	48	49	50	51
Rubber (BR) *1	100	100	100	100	100	100	100	100
Zinc acrylate	10	10	10	10	10	10	10	10
Zinc oxide *4	15	15	15	15	15	15	15	15
Aerosolizable silica *5	10	10	10	10	20	25	30	35
Dicumyl peroxide	5	5	5	5	5	5	5	5
Antioxidant	4	4	4	4	4	4	4	4
Stearic acid	2	2	2	2	2	2	2	2
Surface treated fibers A	10	15	20	25	-	-	-	-
Durability index	124	134	141	145	50	50	50	51
Bounce impact elasticity	103	104	105	105	82	83	82	82
Compression	109	110	111	112	110	112	111	112
Feeling upon hitting**	E	E	E	E	B	B	B	B

** E: Excellent, B: Bad

Table 16
Formulating Ratios of Cores

	Examples				Comparative Experiments			
	147	148	149	150	52	53	54	55
Rubber (BR) *1	100	100	100	100	100	100	100	100
Zinc oxide *4	15	15	15	15	15	15	15	15
Aerosolizable silica *5	10	10	10	10	20	25	30	35
Dicumyl peroxide	5	5	5	5	5	5	5	5
Antioxidant	4	4	4	4	4	4	4	4
Stearic acid	2	2	2	2	2	2	2	2
Surface treated fibers A	10	15	20	25	-	-	-	-
Durability index	117	130	134	138	51	51	51	52
Bounce impact elasticity	103	103	104	105	85	86	85	86
Compression	108	109	110	110	111	109	112	112
Feeling upon hitting**	E	E	E	E	B	B	B	B

** E: Excellent, B: Bad

Table 17
Formulating Ratios of Cover Layers

	Examples										
	151	152	153	154	155	156	157	158	159	160	161
Ionomer resin	100	100	100	100	100	-	-	-	-	-	-
Trans-polyisoprene resin	-	-	-	-	-	100	100	100	100	-	-
Rubber (BR) *1	-	-	-	-	-	-	-	-	-	100	100
Zinc oxide *4	-	-	-	-	-	-	-	-	-	10	10
Zinc acrylate	-	-	-	-	-	-	-	-	-	10	-
Sulfur	-	-	-	-	-	1	1	1	1	-	-
Vulcanization accelerator	-	-	-	-	-	15	15	15	15	-	-
Titanium dioxide	20	-	-	-	-	-	-	-	-	-	-
Dicumyl peroxide	-	-	-	-	-	-	-	-	-	5	5
Antioxidant	-	-	-	-	-	-	-	-	-	4	5
Stearic acid	-	-	-	-	-	-	-	-	-	2	2
Potassium titanate fibers (untreated)	-	20	-	-	-	-	-	-	-	-	-
Surface treated fibers											
A	-	-	20	-	-	-	-	-	-	-	-
B	-	-	-	30	-	10	-	-	-	-	-
C	-	-	-	-	-	-	20	-	-	20	-
D	-	-	-	-	-	-	-	30	-	-	30
E	-	-	-	-	20	-	-	-	20	-	-
Durability index	138	142	151	149	129	121	123	128	112	121	122
Bounce impact elasticity	106	109	110	107	104	107	108	108	103	108	108
Compression	122	122	124	125	122	107	106	107	106	121	122
Feeling upon hitting**	E	E	E	E	E	E	E	E	E	E	E

** E: Excellent

Table 18

	Examples										
	162	163	164	165	166	167	168	169	170	171	172
Rubber											
BR *1	100	100	30	-	-	10	100	50	10	20	-
SBR *2	-	-	70	100	-	90	-	50	90	80	50
IR *3	-	-	-	-	100	-	-	-	-	-	50
Acrylic acid	-	-	-	20	-	-	-	-	-	-	-
Zinc acrylate	20	25	10	-	-	10	-	-	-	-	-
Carcium methacrylate	-	-	-	-	25	-	-	-	-	-	-
Zinc oxide *4	10	5	15	10	5	15	15	15	15	15	20
Aerosolizable silica *5	-	-	10	15	10	10	10	-	-	-	-
Aerosolizable titanium dioxide	15	10	-	-	-	-	-	10	10	10	15
Dicumyl peroxide	5	5	-	5	5	5	-	5	5	5	5
n-Butyl-bis(t-butyl-peroxy)valerate	-	-	5	-	-	-	5	-	-	-	-
Antioxidant	4	4	4	4	4	4	4	4	4	4	4
Stearic acid	2	2	2	2	2	2	2	2	2	2	2
Surface treated fibers											
A	15	-	-	-	-	25	-	-	20	-	20
B	-	5	-	-	15	-	20	-	-	20	-
C	-	-	10	-	-	-	-	25	-	-	-
D	-	-	-	15	-	-	-	-	-	-	-
Durability index	157	144	146	122	127	134	130	147	150	150	148
Bounce impact elasticity	108	103	102	96	98	106	102	102	109	110	109
Compression	127	107	109	107	109	104	110	117	120	120	121
Feeling upon hitting**	E	E	E	E	E	E	E	E	E	E	E

** E: Excellent

Table 19
Formulating Ratios of Spherical Cores

	Examples						Comparative Experiments					
	173	174	175	176	177	178	56	57	58	59	60	61
Rubber (BR) *1	100	100	100	100	100	100	100	100	100	100	100	100
Zinc oxide *4	15	15	15	15	15	15	15	15	15	15	15	15
Aerosolizable silica *5	10	10	10	10	-	-	10	10	10	10	10	30
Dicumyl peroxide	5	5	5	5	5	5	5	5	5	5	5	5
Antioxidant	4	4	4	4	4	4	4	4	4	4	4	4
Stearic acid	2	2	2	2	2	2	2	2	2	2	2	2
Pottasium titanate fibers (untreated)	-	-	-	-	-	-	10	15	20	25	-	-
Surface treated fibers												
A	10	15	20	25	-	-	-	-	-	-	-	-
E	-	-	-	-	-	-	-	-	-	-	20	-
F	-	-	-	-	20	-	-	-	-	-	-	-
G	-	-	-	-	-	20	-	-	-	-	-	-
Durability index	105	118	119	121	123	124	50	50	51	51	49	48
Bounce impact elasticity	89	89	90	91	91	90	81	82	82	83	80	80
Compression	101	101	102	104	100	101	72	73	73	74	73	72
Feeling upon hitting**	E	E	E	E	E	E	B	B	B	B	B	B

** E: Excellent, B: Bad

Table 20
Formulating Ratios of Cores

	Examples			
	179	180	181	182
Rubber (BR) *1	100	100	100	100
Zinc oxide *4	15	15	15	15
Aerosolizable silica *5	10	10	10	10
Dicumyl peroxide	5	5	5	5
Antioxidant	4	4	4	4
Stearic acid	2	2	2	2
Surface treated fibers A	10	15	20	25
Durability index	115	117	119	120
Bounce impact elasticity	92	93	93	94
Compression	103	104	104	105
Feeling upon hitting**	E	E	E	E

** E: Excellent

Table 21
Formulating Ratios of Spherical Cores

	Examples						Comparative Experiments					
	183	184	185	186	187	188	62	63	64	65	66	67
Rubber (BR) *1	100	100	100	100	100	100	100	100	100	100	100	100
Zinc acrylate	10	10	10	10	8	8	10	10	10	10	10	10
Zinc oxide *4	15	15	15	15	15	15	15	15	15	15	15	15
Aerosolizable silica *5	10	10	10	10	-	-	10	10	10	10	10	30
Dicumyl peroxide	5	5	5	5	5	5	5	5	5	5	5	5
Antioxidant	4	4	4	4	4	4	4	4	4	4	4	4
Stearic acid	2	2	2	2	2	2	2	2	2	2	2	2
Pottasium titanate fibers (untreated)	-	-	-	-	-	-	10	15	20	25	-	-
Surface treated fibers												
A	10	15	20	25	-	-	-	-	-	-	-	-
E	-	-	-	-	-	-	-	-	-	-	20	-
F	-	-	-	-	20	-	-	-	-	-	-	-
G	-	-	-	-	-	20	-	-	-	-	-	-
Durability index	117	119	121	122	124	123	54	54	54	54	53	50
Bounce impact elasticity	93	94	94	95	94	94	82	82	83	84	82	81
Compression	104	105	106	106	105	104	81	82	82	83	83	79
Feeling upon hitting**	E	E	E	E	E	E	B	B	B	B	B	B

** E: Excellent, B: Bad

Table 22
Formulating Ratios of Spherical Cores

	Examples			
	189	190	191	192
Rubber (BR) *1	100	100	100	100
Zinc acrylate	10	10	10	10
Zinc oxide *4	15	15	15	15
Aerosolizable silica *5	10	10	10	10
Dicumyl peroxide	5	5	5	5
Antioxidant	4	4	4	4
Stearic acid	2	2	2	2
Surface treated fibers A	10	15	20	25
Durability index	126	127	129	131
Bounce impact elasticity	101	102	103	106
Compression	104	106	106	108
Feeling upon hitting**	E	E	E	E

** E: Excellent

Table 23
Formulating Ratios of Cover Layers

	Examples										
	193	194	195	196	197	198	199	200	201	202	203
Ionomer resin	100	100	100	100	100	-	-	-	-	-	-
Trans-polyisoprene resin	-	-	-	-	-	100	100	100	100	-	-
Rubber (BR) *1	-	-	-	-	-	-	-	-	-	100	100
Zinc oxide *4	-	-	-	-	-	-	-	-	-	15	15
Zinc acrylate	-	-	-	-	-	-	-	-	-	8	8
Sulfur	-	-	-	-	-	1	1	1	1	-	-
Vulcanization accelerator	-	-	-	-	-	15	15	15	15	-	-
Titanium dioxide	20	-	-	-	-	-	-	-	-	-	-
Dicumyl peroxide	-	-	-	-	-	-	-	-	-	5	5
Antioxidant	-	-	-	-	-	-	-	-	-	4	4
Stearic acid	-	-	-	-	-	-	-	-	-	2	2
Potassium titanate fibers (untreated)	-	20	-	-	-	-	-	-	-	-	-
Surface treated fibers											
A	-	-	20	-	-	-	-	-	-	20	-
B	-	-	-	30	-	10	-	-	-	-	20
C	-	-	-	-	-	-	20	-	-	-	-
D	-	-	-	-	-	-	-	30	-	-	-
E	-	-	-	-	20	-	-	-	20	-	-
Durability index	109	111	132	131	115	117	119	122	107	126	124
Bounce impact elasticity	84	86	106	106	104	106	107	107	102	103	107
Compression	84	101	102	101	100	107	105	106	106	101	103
Feeling upon hitting**	E	E	E	E	E	E	E	E	E	E	E

** E: Excellent

Table 24

	Examples										
	204	205	206	207	208	209	210	211	212	213	214
Rubber											
BR *1	100	100	30	-	-	10	100	50	10	20	-
SBR *2	-	-	70	100	-	90	-	50	90	80	50
IR *3	-	-	-	-	100	-	-	-	-	-	50
Acrylic acid	-	-	-	20	-	-	-	-	-	-	-
Zinc acrylate	20	25	10	-	-	10	-	-	-	-	-
Carcium methacrylate	-	-	-	-	25	-	-	-	-	-	-
Zinc oxide *4	10	5	15	10	5	15	15	15	15	15	20
Aerosolizable silica *5	-	-	10	15	10	10	10	-	-	-	-
Aerosolizable titanium dioxide	15	10	-	-	-	-	-	10	10	10	15
Dicumyl peroxide	5	5	-	5	5	5	-	5	5	5	5
n-Butyl-bis(t-butyl- peroxy)valerate	-	-	5	-	-	-	5	-	-	-	-
Antioxidant	4	4	4	4	4	4	4	4	4	4	4
Stearic acid	2	2	2	2	2	2	2	2	2	2	2
Surface treated fibers											
A	30	-	-	-	-	25	-	-	20	-	20
B	-	5	-	-	15	-	20	-	-	20	-
C	-	-	10	-	-	-	-	25	-	-	-
D	-	-	-	15	-	-	-	-	-	-	-
Durability index	135	124	126	120	123	128	126	141	146	144	144
Bounce impact elasticity	106	99	101	107	107	108	108	108	107	107	105
Compression	102	101	102	106	106	107	107	108	108	107	109
Feeling upon hitting**	E	E	E	E	E	E	E	E	E	E	E

** E: Excellent

Table 25
Formulating Ratios of Cover Layers

	Examples									
	215	216	217	218	219	220	221	222	223	224
Ionomer resin	100	100	100	100	100	-	-	-	-	-
Trans-polyisoprene resin	-	-	-	-	-	100	100	100	-	-
Rubber (BR) *1	-	-	-	-	-	-	-	-	100	100
Zinc oxide *4	-	-	-	-	-	-	-	-	10	10
Zinc acrylate	-	-	-	-	-	-	-	-	9	9
Sulfur	-	-	-	-	-	1	1	1	-	-
Vulcanization accelerator	-	-	-	-	-	15	15	15	-	-
Dicumyl peroxide	-	-	-	-	-	-	-	-	5	5
Antioxidant	-	-	-	-	-	-	-	-	4	4
Stearic acid	-	-	-	-	-	-	-	-	2	2
Surface treated fibers										
A	20	-	-	-	30	-	-	10	-	-
B	-	20	-	-	-	-	10	-	-	-
C	-	-	20	-	-	10	-	-	20	-
D	-	-	-	20	-	-	-	-	-	20
Durability index	103	104	105	106	108	104	107	110	106	108
Bounce impact elasticity	115	116	117	118	117	116	118	119	100	101
Compression	123	124	128	126	122	120	122	124	121	119
Feeling upon hitting**	E	E	E	E	E	E	E	E	E	E

** E: Excellent

Table 26
Formulating Ratios of Cores

	Examples					
	225	226	227	228	229	230
Rubber (BR) *1	100	100	100	100	100	100
Zinc acrylate	10	10	10	10	10	10
Zinc oxide *4	15	15	15	15	15	15
Aerosolizable silica *5	10	10	10	10	10	30
Dicumyl peroxide	5	5	5	5	5	5
Antioxidant	4	4	4	4	4	4
Stearic acid	2	2	2	2	2	2
Potassium titanate fibers (untreated)	10	15	20	25	-	-
Surface treated fibers E	-	-	-	-	20	-
Durability index	99	99	98	98	96	97
Bounce impact elasticity	97	98	101	101	98	99
Compression	111	108	109	108	108	106
Feeling upon hitting**	G	G	G	G	G	G

** G: Good

Table 27
Formulating Ratios of Cover Layers

	Comparative Experiments							
	68	69	70	71	72	73	74	75
Ionomer resin	100	100	100	100	100	-	-	-
Trans-polyisoprene resin	-	-	-	-	-	100	100	100
Sulfur	-	-	-	-	-	1	1	1
Vulcanization accelerator	-	-	-	-	-	15	15	15
Titanium dioxide	20	-	30	-	-	30	-	10
Potassium titanate fibers (untreated)	-	20	-	30	-	-	30	-
Surface treated fibers E	-	-	-	-	30	-	-	-
Durability index	93	95	94	96	97	85	87	81
Bounce impact elasticity	90	92	96	94	95	90	91	88
Compression	108	110	112	111	111	108	107	105
Feeling upon hitting**	B	B	B	B	B	B	B	B

** B: Bad

Table 28
Formulating Ratios of Cover Layers

	Examples									
	231	232	233	234	235	236	237	238	239	240
Ionomer resin	100	100	100	100	100	-	-	-	-	-
Trans-polyisoprene resin	-	-	-	-	-	100	100	100	-	-
Rubber (BR) *1	-	-	-	-	-	-	-	-	100	100
Zinc oxide *4	-	-	-	-	-	-	-	-	10	10
Zinc acrylate	-	-	-	-	-	-	-	-	9	9
Sulfur	-	-	-	-	-	1	1	1	-	-
Vulcanization accelerator	-	-	-	-	-	15	15	15	-	-
Dicumyl peroxide	-	-	-	-	-	-	-	-	5	5
Antioxidant	-	-	-	-	-	-	-	-	4	4
Stearic acid	-	-	-	-	-	-	-	-	2	2
Surface treated fibers										
A	20	-	-	-	30	-	-	10	-	-
B	-	20	-	-	-	-	10	-	-	-
C	-	-	20	-	-	10	-	-	-	-
D	-	-	-	20	-	-	-	-	-	-
E	-	-	-	-	-	-	-	-	20	-
F	-	-	-	-	-	-	-	-	-	20
Durability index	107	105	106	107	107	104	106	105	106	107
Bounce impact elasticity	117	116	116	116	115	110	108	109	109	108
Compression	124	122	123	123	122	121	122	123	121	120
Feeling upon hitting**	E	E	E	E	E	E	E	E	E	E

** E: Excellent

Table 29
Formulating Ratios of Cover Layers

	Comparative Experiments							
	76	77	78	79	80	81	82	83
Ionomer resin	100	100	100	100	100	-	-	-
Trans-polyisoprene resin	-	-	-	-	-	100	100	100
Sulfur	-	-	-	-	-	1	1	1
Vulcanization accelerator	-	-	-	-	-	15	15	15
Titanium dioxide	20	-	30	-	-	30	-	20
Potassium titanate fibers (untreated)	-	20	-	30	-	-	30	-
Surface treated fibers E	-	-	-	-	30	-	-	-
Durability index	94	96	95	97	95	85	88	83
Bounce impact elasticity	89	91	90	92	91	90	92	90
Compression	109	111	113	113	112	108	107	103
Feeling upon hitting**	B	B	B	B	B	B	B	B

** B: Bad

Table 30
Formulating Ratios of Cover Layers

	Examples									
	241	242	243	244	245	246	247	248	249	250
Ionomer resin	100	100	100	100	100	-	-	-	-	-
Trans-polyisoprene resin	-	-	-	-	-	100	100	100	-	-
Rubber (BR) *1	-	-	-	-	-	-	-	-	100	100
Zinc oxide *4	-	-	-	-	-	-	-	-	10	10
Zinc acrylate	-	-	-	-	-	-	-	-	9	9
Sulfur	-	-	-	-	-	1	1	1	-	-
Vulcanization accelerator	-	-	-	-	-	15	15	15	-	-
Dicumyl peroxide	-	-	-	-	-	-	-	-	5	5
Antioxidant	-	-	-	-	-	-	-	-	4	4
Stearic acid	-	-	-	-	-	-	-	-	2	2
Surface treated fibers										
A	20	-	-	-	30	-	-	-	20	-
B	-	20	-	-	-	-	-	10	-	20
C	-	-	20	-	-	-	10	-	-	-
D	-	-	-	20	-	10	-	-	-	-
Durability index	103	101	101	102	108	102	101	100	105	106
Bounce impact elasticity	109	108	108	109	108	99	100	99	100	99
Compression	123	124	124	125	128	122	123	121	121	122
Feeling upon hitting**	E	E	E	E	E	E	E	E	E	E

** E: Excellent

Table 31
Formulating Ratios of Cover Layers

	Comparative Experiments							
	84	85	86	87	88	89	90	91
Ionomer resin	100	100	100	100	100	-	-	-
Trans-polyisoprene resin	-	-	-	-	-	100	100	100
Sulfur	-	-	-	-	-	1	1	1
Vulcanization accelerator	-	-	-	-	-	15	15	15
Titanium dioxide	20	-	30	-	-	30	-	20
Potassium titanate fibers (untreated)	-	20	-	30	-	-	30	-
Surface treated fibers E	-	-	-	-	30	-	-	-
Durability index	81	82	81	83	75	76	77	73
Bounce impact elasticity	82	82	83	84	84	85	86	81
Compression	101	102	102	101	98	97	96	95
Feeling upon hitting**	B	B	B	B	B	B	B	B

** B: Bad

Claims

1. A rubber composition comprising at least one natural and/or synthetic rubber component(s), fine inorganic fibers, as hereinbefore defined, subjected to a surface treatment with a surface treating agent and a non-sulfur type vulcanizing agent.


2. A rubber composition according to claim 1, wherein the composition further comprises a cross-linking monomer.

3. A rubber composition according to claim 1 or 2, wherein the fine inorganic fibers are alkali metal titanate fibers.

4. A rubber composition according to any preceding claim, wherein the surface treating agent is a sulfur-containing silane compound.


5. A rubber composition according to claim 4, wherein the surface treating agent is at least one compound selected from mercapto group-bearing silane compounds and silyl group-bearing sulfide compounds.

6. A rubber composition according to claim 5, wherein the mercapto group-bearing silane compound is represented by the formula I:



wherein each R^1 independently represents a substituted or unsubstituted divalent hydrocarbon group of 2 to 6 carbon atoms, each R^2 independently represents a substituted or unsubstituted monovalent hydrocarbon group, each X independently represents a hydrolyzable group, a is an integer of from 1 to 3, and b is an integer of from 0 to 2 with proviso of $1 \leq (a+b) \leq 3$.

7. A rubber composition according to claim 5, wherein the silyl group-bearing sulfide compound is represented by the formula II:



wherein each R^3 independently represents a substituted or



unsubstituted monovalent hydrocarbon group, each R^4 independently represents a substituted or unsubstituted hydrocarbon group of 2 to 4 carbon atoms, each Y independently represents a hydrolyzable group, c is an integer of from 0 to 2 and n is an integer of from 1 to 6.

8. A rubber composition according to any preceding claim, which comprises a cross-linking monomer which is an unsaturated carboxylic acid, salt thereof or unsaturated vinyl compound.

9. A rubber composition according to any preceding claim, whose rubber component contains at least 30% by weight of cis-1,4-polybutadiene.

10. A solid golf ball which is composed of a rubber composition as defined in any one of the preceding claims.

11. A two-piece golf ball comprising a core of elastic rubber and a cover layer of a hard elastomer, wherein the core and/or the cover layer are/is composed of a rubber composition as claimed in any one of claims 1 to 8.

12. A two-piece golf ball according to claim 11, whose core is composed of a said rubber composition.

13. A two-piece golf ball according to claim 11, whose cover layer is composed of a said rubber composition.

14. A two-piece golf ball according to claim 11, 12 or 13, wherein the cover layer is formed of a said rubber composition whose rubber component is an ionomer resin.

15. A two-piece golf ball according to claim 11, 12 or 13, wherein the cover layer is formed of a said rubber composition whose rubber component is a trans-polyisoprene resin.

16. A two-piece golf ball according to any one of



claims 11 to 15, which comprises a said rubber composition whose rubber component contains at least 30% by weight of cis-1,4-polybutadiene.

5 17. A three-piece golf ball comprising a core of elastic rubber, an intermediate layer of elastic rubber and a cover layer of hard elastomer, wherein at least one of the core, the intermediate layer and the cover layer is(are) composed of a rubber composition as claimed in any one of claims 1 to 8.

10 18. A three-piece golf ball according to claim 17, wherein the core is composed of a said rubber composition.

15 19. A three-piece golf ball according to claim 17, wherein the intermediate layer is composed of a said rubber composition.

20. A three-piece golf ball according to claim 17, wherein the cover layer is composed of a said rubber composition.

20 21. A three-piece golf ball according to any one of claims 17 to 20, wherein the cover layer is formed of a said rubber composition whose rubber component is an ionomer resin.

25 22. A three-piece golf ball according to any one of claims 17 to 20, wherein the cover layer is formed of a said rubber composition whose rubber component is a trans-polyisprene resin.

30 23. A three-piece golf ball according to any one of claims 17 to 22, which comprises a said rubber composition whose rubber component contains at least 30% by weight of cis-1,4-polybutadiene.

35 24. A thread wound golf ball comprising a spherical core of elastic rubber, an intermediate layer formed by winding elastic thread with high tension on the spherical core and a cover layer of hard elastomer, wherein the core and/or the cover layer are/is composed of a rubber composition as claimed in any one of claims



8
1 to 2.

25. A thread wound golf ball according to claim 24, wherein the core is composed of a said rubber composition.

5 26. A thread wound golf ball according to claim 24, wherein the cover layer is composed of a said rubber composition.

27. A thread wound golf ball according to claim 24, 25 or 26, wherein the cover layer is formed of a
10 said rubber composition whose rubber component is an ionomer resin.

28. A thread wound golf ball according to claim 24, 25 or 26, wherein the cover layer is formed of a
15 said rubber composition whose rubber component is a trans-polyisoprene.

29. A thread wound golf ball according to any one of claims 24 to 28 which comprises a said rubber composition whose rubber component contains at least 30% by weight of cis-1,4-polybutadiene.

20 30. A golf ball as claimed in any one of claims 10 to 29, wherein the rubber composition further comprises a weight adjusting agent.

31. A rubber composition for a cover layer of a golf ball, wherein the composition comprises at least
25 one natural and/or synthetic rubber component(s) and alkali metal titanate fibers subjected to a surface treatment with a surface treating agent.

32. A rubber composition for a golf ball cover layer according to claim 31, wherein the surface
30 treating agent is a sulfur-containing silane compound.

33. A rubber composition for a golf ball cover layer according to claim 31 or 32, wherein the surface treating agent is at least one compound selected from mercapto group-bearing silane compounds and silyl
35 group-bearing sulfide compounds.

34. A rubber composition for a golf ball cover



layer, according to claim 31, 32 or 33, wherein the rubber component is composed of ionomer resin.

35. A rubber composition for a golf ball cover layer according to claim 31, 32 or 33, wherein the

5 rubber



1 component is composed of trans-polyisoprene resin.

36. A rubber composition as claimed in claim 1,
substantially as described in any one of the foregoing
Examples 1-100, 117-131, 135, 137-150, 162-192, 204-214
5 and 229.

37. A rubber composition as claimed in claim 31,
substantially as described in any one of the foregoing
Examples 87, 103-116, 153-161, 195-203, 215-224 and
231-250.

10 38. A one-piece golf ball, substantially as
described in any one of the foregoing Examples 37-82.

39. A two-piece golf ball, substantially as
described in any one of the foregoing Examples 83-127 and
215-230.

15 40. A three-piece golf ball, substantially as
described in any one of the foregoing Examples 128-172
and 231-240.

41. A thread-wound golf ball, substantially as
described in any one of the foregoing Examples 173-214
20 and 241-250.

25

PATENTS ACT 1977
SPECIFICATION NO. 2206889B

REMARKS ON ATTACHED

The following corrections were allowed under Section 117
on 4 July 1991

Heading (72) Inventor(s)

delete Syoki Yuki insert Syoji Yuki

THE PATENT OFFICE
19 JULY 1991

76

