7. A glass article, comprising:

a glass sheet with a front face having a width and a height, a back face opposite the front face, and a thickness between the front face and back face forming four edges around the front and back faces,

wherein the glass sheet comprises:

between about 72.82 mol % to about 82.03 mol% SiO_2,

between about 0 mol% to about 4.8 mol% Al_2O_3,

between about 0 mol% to about 2.77 mol% B_2O_3,

between about 0 mol% to about 9.28 mol% Na_2O,

between about 0.58 mol% to about 10.58 mol% K_2O,

between about 0 mol% to about 2.93 mol% ZnO,

between about 3.1 mol% to about 10.58 mol% MgO,

between about 0 mol% to about 4.82 mol% CaO,

between about 0 mol% to about 1.59 mol% SrO,

between about 0 mol% to about 3 mol% BaO, and

between about 0.08 mol% to about 0.15 mol% SnO_2.

8. The glass article of Claim 7, wherein the glass sheet is substantially free of Al_2O_3, B_2O_3, Na_2O, CaO, SrO, or BaO, and combinations thereof.

9. The glass article of Claim 7, wherein the glass has a color shift < 0.005.

10. The glass article of Claim 7, wherein the glass has a strain temperature between about 512 °C and 653 °C, an annealing temperature between about 564 °C and 721 °C, a softening temperature between about 795 °C and 1013 °C,

a CTE between about 64 x 10-7/ °C to about 77 x 10-7/ °C, or a density between about 2.34 gm/cc @ 20 C and about 2.56 gm/cc @ 20 C.

11. The glass article of Claim 7, wherein the glass article is a light guide plate.

12. The glass article of Claim 11, wherein the thickness of the plate is between about 0.2 mm and about 8 mm.

13. The glass article of Claim 7, wherein the glass comprises less than 1 ppm each of Co, Ni, and Cr.

14. The glass article of Claim 7, wherein the transmittance at 450 nm with at least 500 mm in length is greater than or equal to 85%, the transmittance at 550 nm with at least 500 mm in length is greater than or equal to 90%, or the transmittance at 630 nm with at least 500 mm in length is greater than or equal to 85%, and combinations thereof.

15. The glass article of Claim 7, wherein the glass sheet is chemically strengthened.

16. The glass article of Claim 15, wherein the glass comprises between 0.1 mol% to no more than about 3.0 mol% of one or combination of any of ZnO, TiO_2, V_2O_3, Nb_2O_5, MnO, ZrO_2, As_2O_3, SnO_2, MoO_3, Sb_2O_3, and CeO_2.

17. A glass article, comprising:

a glass sheet with a front face having a width and a height, a back face opposite the front face, and a thickness between the front face and back face forming four edges around the front and back faces,

wherein the glass sheet is substantially free of Al_2O_3 and B_2O_3 and comprises greater than about 80 mol % SiO_2, and

wherein the glass has a color shift < 0.005.

18. The glass article of Claim 17, wherein the glass sheet comprises:

between about 8 mol% to about 11 mol% K_2O,

between about 0.01 mol% to about 4 mol% ZnO,

between about 6 mol% to about 10 mol% MgO, and

between about 0.01 mol% to about 0.11 mol% SnO_2.

19. A glass article, comprising:

a glass sheet with a front face having a width and a height, a back face opposite the front face, and a thickness between the front face and back face forming four edges around the front and back faces,

wherein the glass sheet is substantially free of Al_2O_3, B_2O_3, Na_2O, CaO, SrO, and BaO, and

wherein the glass has a color shift < 0.005.

20. The glass article of Claim 19, wherein the glass sheet comprises greater than about 80 mol % SiO_2.

21. The glass article of Claim 19, wherein the glass sheet comprises:

between about 8 mol% to about 11 mol% K_2O,

between about 0.01 mol% to about 4 mol% ZnO,

between about 6 mol% to about 10 mol% MgO, and

between about 0.01 mol% to about 0.11 mol% SnO_2.