

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
28 August 2003 (28.08.2003)

PCT

(10) International Publication Number
WO 03/070994 A2

- (51) International Patent Classification⁷: **C22C**
- (21) International Application Number: PCT/US03/04204
- (22) International Filing Date: 11 February 2003 (11.02.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
10/078,020 15 February 2002 (15.02.2002) US
- (71) Applicant: **INTERNATIONAL BUSINESS MACHINES CORPORATION** [US/US]; New Orchard Road, Armonk, NY 10504 (US).
- (72) Inventors: **CHOI, Won, K.**; 35 Stewart Place #202, Mount Kisco, NY 10549 (US). **GOLDSMITH, Charles, C.**; 3 Scott Court, Poughkeepsie, NY 12601 (US). **GOSSELIN, Timothy, A.**; 29 Rebeca Drive, Apalachin, NY 13732 (US). **HENDERSON, Donald, W.**; 20 Woodlane Road, Ithaca, NY 14850 (US). **KANG, Sung, K.**; 36 Mayberry Road, Chappaqua, NY 10514 (US). **PUTTLITZ, Karl, Sr.**; 21 Central Avenue, Wappingers Falls, NY 12590 (US). **SHIH, Da-Yuan**; 16 Vervalen Drive, Poughkeepsie, NY 12603 (US).
- (74) Agent: **CIOFFI, James, J.**; International Business Machines Corporation, Dept. 18G, Bldg. 300/482, 2070 Route 52, Hopewell Junction, NY 12533 (US).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZM, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
— *without international search report and to be republished upon receipt of that report*
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: LEAD-FREE TIN-SILVER-COPPER ALLOY SOLDER COMPOSITION

(57) Abstract: A solder composition and associated method of formation. The solder composition comprises a substantially lead-free alloy that includes tin (Sn), silver (Ag), and copper. The tin has a weight percent concentration in the alloy of at least about 90 %. The silver has a weight percent concentration X in the alloy. X is sufficiently small that formation of Ag₃Sn plates is substantially suppressed when the alloy in a liquefied state is being solidified by being cooled to a lower temperature at which the solid Sn phase is nucleated. This lower temperature corresponds to an undercooling δT relative to the eutectic melting temperature of the alloy. Alternatively, X may be about 4.0 % or less, wherein the liquefied alloy is cooled at a cooling rate that is high enough to substantially suppress Ag₃Sn plate formation in the alloy. The copper has a weight percent concentration in the alloy not exceeding about 1.5 %.



WO 03/070994 A2