

CATALYST AND PREPOLYMER USED FOR THE PREPARATION OF POLYOLEFINS

The present invention relates to a solid catalyst suitable for (co-)polymerizing olefins, especially ethylene, the solid catalyst being obtainable by contacting a particular magnesium chloride support with a zirconium metallocene. It also relates to the use of
5 the catalyst as such or else in the form of a prepolymer in a heterogeneous process of polymerization or copolymerization of olefins, especially ethylene.

It is known that it is possible to manufacture polyolefins in the presence of a catalyst system comprising a catalyst based on a
10 zirconium metallocene and a cocatalyst consisting of an organoaluminium compound, especially an aluminoxane. However, this catalyst is preferably employed in a homogeneous process such as in solution in a liquid hydrocarbon and is not suited to heterogeneous processes of polymerization in suspension in aliphatic hydrocarbons
15 or in gaseous phase.

According to US Patent No. 4,659,685, it is also known to manufacture polyolefins with the aid of a catalyst system comprising a solid catalyst consisting of a zirconium metallocene deposited on a support such as a refractory oxide or a magnesium chloride.
20 However, the catalysts thus obtained have a broad particle size distribution and consist of particles having no well-defined shape. Furthermore, they generally produce polyolefins with relatively broad molecular weight distribution.

For a number of years attempts have been made to develop a
25 high-activity solid catalyst comprising a zirconium metallocene for



a heterogeneous process of the (co-)polymerization of olefins especially ethylene. In particular, a solid catalyst whose support can receive a large quantity of zirconium has been sought. Attempts have been made, furthermore, to develop a catalyst suited to the heterogeneous processes of polymerization of olefins in suspension in an aliphatic hydrocarbon or in gaseous phase, processes in which it is important to be able to control the size, the particle size distribution and the morphology of the catalyst particles at the same time. It has also been shown to be important that any solid catalyst should be able to withstand the growth stresses during the polymerization, especially in the initial stage of a gas phase polymerization. We have found that the growth stresses with zirconium metallocene catalysts are generally much greater than those of a catalyst based on a titanium or vanadium chloride which is less active in olefin polymerization. It is also desirable that the solid catalyst be capable of producing an ethylene polymer or an ethylene copolymer with an easily controllable average molecular and a narrow molecular weight distribution, so as to enable this polymer or copolymer to be shaped using injection and moulding.

It has now been found that it is possible to prepare a solid catalyst with high activity in the (co-)polymerization of olefins, prepared by contacting a relatively high amount of a zirconium metallocene with a magnesium chloride support. In particular, this catalyst is in the form of spheroidal particles which are suited to the heterogeneous polymerizations of olefins in suspension or in gaseous phase and which are capable of withstanding the enormous growth stresses during the polymerization.

The present invention relates therefore to a solid catalyst suitable for a heterogeneous process for polymerizing one or more olefins, in particular ethylene, the solid catalyst being prepared by contacting a zirconium metallocene with a magnesium chloride support, characterized in that the solid catalyst is obtainable by a process comprising:

- (1) a first stage, wherein a solid support (A) containing from 80 to 99.5 mol% of magnesium dichloride and from 0.5 to 20 mol% of



at least one organic electron-donor compound, D1, free from labile hydrogen, the solid support (A) being in the form of spheroidal particles with a mass-average diameter, D_m , of 10 to 100 microns and a particle size distribution, such that the
5 ratio of D_m to the number-average diameter, D_n , of the particles is not higher than 3, preferably not higher than 2.5 and especially not higher than 2, is brought into contact with at least one electron-donor compound, D2, containing labile hydrogen,

10 (2) then, a second stage, wherein the solid support resulting from the first stage is brought into contact with a zirconium metallocene (B) optionally with an organoaluminium compound (C), preferably an aluminoxane. The contact of the solid support resulting from the first step with (B) and optionally
15 (C) may be performed in various ways, for instance by contacting the solid support resulting from the first step with (B) followed by (C) or vice versa.

In the process for the preparation of the catalyst, a particular magnesium chloride support (A) is used, containing an
20 organic electron-donor compound, D1, in a relatively large quantity. The support comprises from 80 to 99.5 mol% preferably from 80 to 95 mol% and especially from 80 to 90 mol% of magnesium dichloride and from 0.5 to 20 mol% preferably from 5 to 20 mol% and especially from 10 to 20 mol% of the compound D1.

25 The support, which is based essentially on magnesium dichloride, may additionally contain a chlorine containing aluminium derivative, such as aluminium trichloride, as well as optionally a magnesium chloride containing Mg-C bonds. The quantity of the chlorine containing aluminium derivative may be lower than or equal
30 to 30 mol%, preferably 20 mol% or less relative to the magnesium dichloride such as 1 to 20 mol%. The quantity of Mg-C bond may be lower than or equal to 5 mol%, preferably 1 mol% or less relative to the magnesium dichloride. Especially, the support contains substantially no Mg-C bond.

35 The organic electron-donor compound, D1, is generally known as



a Lewis base and must be free from labile hydrogen. It cannot, for example, be chosen from water, alcohols or phenols. It has an ability to complex magnesium dichloride. It is advantageously chosen from ethers, esters, thioethers, sulphones, sulphoxides, secondary
 5 amides, tertiary amines, tertiary phosphines and phosphoramides. Electron-donor compounds of low complexing power, such as cyclic or non-cyclic ethers, are preferred.

The organic electron-donor compound, D1, is advantageously distributed homogeneously throughout the support particle, forming a
 10 homogeneous composition of magnesium dichloride and compound D1. Consequently, a support of this kind cannot normally be prepared merely by bringing anhydrous magnesium dichloride particles into contact with the compound D1. For this reason it is recommended that the support be prepared by precipitation of magnesium dichloride in
 15 the presence of the compound D1.

The support (A) consists of particles whose specific surface area (BET) may be from 20 to 100 m²/g, preferably from 30 to 60 m²/g. It consists of spheroidal particles which have a
 20 substantially spherical shape, e.g. in which the ratio D/d of the particles is close to 1, D and d being the major axis and the minor axis of the particles respectively. The ratio D/d is generally lower than or equal to 1.5, preferably 1.3 or less, such as 1 to 1.5, or 1 to 1.3.

The particles of the support (A) have a mass-average diameter
 25 of 10 to 100 microns, preferably of 15 to 70 and especially 20 to 50 microns. They have a very narrow particle size distribution, such that the ratio D_m/D_n of the mass-average diameter, D_m, to the number-average diameter, D_n, is not higher than 3, preferably not higher than 2.5 and especially not higher than 2, such as 1 to 3, or
 30 1 to 2.5, or 1 to 2 and especially 1.1 to 1.5. Preferably, there is a virtually total absence of particles of diameter greater than 1.5 x D_m or smaller than 0.6 x D_m; the particle size distribution is usually such that more than 90% by weight of the particles of the same single batch have a particle size in the range D_m ± 10%.

35 The support may, in particular, be prepared by reacting a



dialkylmagnesium compound with an organic chlorine compound in the presence of the electron-donor compound, D1, acting as a complexing agent and not as a reactant in this preparation. For this reason in this production process, the compound D1 cannot be chosen from
 5 electron-donor compounds capable of reacting with organomagnesium compounds e.g. from esters. The dialkylmagnesium compound chosen may be a product of formula R_1MgR_2 in which R_1 and R_2 are identical or different alkyl radicals containing from 2 to 12 carbon atoms, and which is soluble in the hydrocarbon medium in which the
 10 preparation of the support will preferably be carried out. The organic chlorine compound which is chosen is an alkyl chloride of formula R_3Cl in which R_3 is a secondary or, preferably, tertiary alkyl radical, preferably containing from 3 to 12 carbon atoms. It is preferred to employ, as electron-donor compound, D1, an ether of
 15 formula R_8OR_9 in which R_8 and R_9 are identical or different alkyl radicals, especially containing from 1 to 12 carbon atoms.

The various reactants used for the preparation of the support (A) can be used with:

- a molar ratio R_3Cl/R_1MgR_2 of from 1.5 to 2.5, preferably
 20 from 1.9 to 2.3, and
- a molar ratio D_1/R_1MgR_2 of from 0.1 to 1.2, preferably from 0.3 to 0.8.


The reaction between R_1MgR_2 and R_3Cl in the presence of the electron-donor compound D1 is a precipitation which takes place in
 25 an inert liquid medium, e.g. a liquid hydrocarbon, with stirring preferably at a temperature of 0 to 100°C. To obtain an excellent support, in particular one with a large quantity of the electron-donor compound, D1, it is recommended to perform the precipitation reaction at a relatively low temperature ranging from
 30 10 to 50°C, preferably from 15 to 35°C. Preferably, the precipitation reaction should proceed extremely slowly, over a period of at least 10 hours e.g. 10 to 50 hours, preferably a period ranging from 10 to 24 hours, so as to permit a suitable formation of the solid product, in particular the
 35 insertion of a large quantity of compound D1 and its uniform



dispersion in the support.

The first stage of the catalyst preparation may consist in bringing the support (A) into contact with an electron-donor compound containing labile hydrogen, D2, e.g. an alcohol, a phenol, a primary amide, a primary or secondary amine, a primary or secondary phosphine. D2 is preferably chosen from alcohols and phenols. It is preferred to employ an alcohol containing from 1 to 12 carbon atoms, in particular ethanol, propanol, n-butanol, n-pentanol or n-hexanol. The compound D2 generally has a complexing power for magnesium chloride which is higher than that of the compound D1.

From 0.05 to 3 moles, preferably from 0.1 to 1 mole of compound D2 can be used per mole of magnesium of the support (A). If the amount of D2 used is too high, the support gets more fragile. The contact of the compound D2 with the support (A) may be brought about at 0 to 100°C, preferably 0 to 70°C. It is preferably brought about with agitation e.g. stirring in an aliphatic or aromatic liquid hydrocarbon such as n-hexane or toluene, over a period which can range from 10 minutes to 5 hours. In practice, the contact can be brought about in various ways, for example by slow addition of the compound D2 to the support (A) in a suspension in a liquid hydrocarbon under a continuous agitation. It is generally found that most of the compound D2 used in this stage becomes fixed in the support without appreciably modifying the morphology of the support. Only the specific surface area of the support is increased and helps to deposit in the support a relatively high amount of zirconium which is strongly bound to the support. Thus treated with the compound D2, the support may be washed one or more times with the aid of a hydrocarbon before proceeding to the next stage. The solid product resulting from the first stage may have the general formula:



wherein D1 and D2 denote the above-mentioned electron-donor compounds, x is a number ranging from 0.0005 to 0.15, especially from 0.001 to 0.1 and y is a number ranging from 0.05 to 3,




particularly from 0.1 to 1.

The second stage of the catalyst preparation consists in bringing the support treated with the compound D2 into contact with a zirconium metallocene (B). In particular, the zirconium
 5 metallocene is a metallocene containing a tetravalent zirconium, with at least one Zr-C bond which is a covalent or pi-bonded one. It is also called zirconocene, which preferably corresponds to the general formula



10 in which R_4 denotes a cycloalkadienyl radical or cycloalkadienyl radical substituted by at least one alkyl radical e.g. of 1 to 6 carbon atoms, such as methyl or ethyl, or by at least one alkoxy radical e.g. of 1 to 6 carbon atoms, or a fused ring cycloalkadienyl group e.g. of 7 to 14 carbon atoms such as indenyl or
 15 tetrahydroindenyl, and each of R_5 , R_6 and R_7 being identical or different denotes a cycloalkadienyl radical, a cycloalkadienyl radical substituted by at least one alkyl or alkoxy group e.g. of 1 to 6 carbon atoms, such as methyl ethyl, methoxy, ethoxy, propoxy or butoxy, an aryl radical e.g. an aromatic hydrocarbyl group such as
 20 one of 6 to 19 carbon atoms such as phenyl, an alkyl radical e.g. of 1 to 6 carbon atoms such as methyl or ethyl, a cycloalkyl radical e.g. of 5 to 7 carbon atoms such as cyclohexyl, an aralkyl radical e.g. of 7 to 19 carbon atoms such as aromatic hydrocarbyl alkyl such as benzyl, a halogen atom e.g. chlorine or bromine, an alkoxy
 25 radical e.g. of 1 to 12 carbon atoms such as methoxy, ethoxy, propoxy or butoxy, or a hydrogen atom. Provided that when R_5 represents a cycloalkadienyl radical or a substituted cycloalkadienyl radical, or a fused ring cycloalkadienyl group, R_4 and R_5 may be bonded to each other either directly or via a lower
 30 alkylene group e.g. of 1 to 4 carbon atoms. The cycloalkadienyl radical is preferably one with a conjugated C_5 ring diene group, such as a cyclopentadienyl. Examples of suitable radicals for R_4 , R_5 , R_6 or R_7 may contain 6 to 22 carbon atoms and preferably are methylcyclopentadienyl, ethylcyclopentadienyl,
 35 dimethylcyclopentadienyl, indenyl, ethylenebisindenyl or



tetrahydroindenyl radical.

The zirconium metallocene may, in particular, be chosen from bis(cyclopentadienyl) methylchlorozirconium, bis(cyclopentadienyl)dichlorozirconium and
 5 bis(4,5,6,7-tetrahydroindenyl)ethylenedichlorozirconium.

Preferably, the zirconium metallocene also comprises at least one Zr-X bond, wherein X represents a halogen atom e.g. a chlorine or bromine atom, or an alkoxy group e.g. of 1 to 12 carbon atoms.

During the second stage the support may be preferably brought
 10 into contact with the organoaluminium compound (C), preferably the aluminoxane, because the compound (C) helps to deposit in the support a relatively high amount of zirconium which is then strongly bound to the support. The compound (C) may be a trialkylaluminium, e.g. trimethylaluminium, or triethylaluminium, or an alkylaluminium
 15 hydride, an alkylaluminium alkoxide, or an alkylaluminium halide, e.g. diethylaluminium chloride, or preferably an aluminoxane. The aluminoxane may be either a linear aluminoxane corresponding to the general formula



20 in which each R denotes an alkyl radical e.g. of 1 to 6 carbon atoms, such as methyl or ethyl, and n is a number ranging from 2 to 40, preferably from 10 to 20, or a cyclic aluminoxane corresponding to the general formula



in which R and n are as defined above. The aluminoxane is preferably a methylaluminoxane.

In the second stage the support resulting from the first stage may be employed in the form of a suspension in an aliphatic or,
 30 preferably, aromatic hydrocarbon.

The zirconium metallocene (B) may be used in the form of a solution, especially in an aromatic hydrocarbon such as toluene. The concentration of the solution may be from 0.1 to 50 millimoles of zirconium per litre. The organoaluminium compound (C) which is
 35 preferably an aluminoxane may also be in the form of a solution in a



hydrocarbon, especially an aromatic hydrocarbon such as toluene, at a concentration which may go up to 30% by weight of aluminium.

The contact of the support resulting from the first stage with the zirconium metallocene (B) may be brought about in various ways. It is possible, for example, to add the support to a solution of (B), or the reverse. The contact is preferably brought about in the presence of the compound (C), preferably the aluminoxane. In this case, a solution of the zirconium metallocene (B) and a solution of the compound (C) can be added to the support either simultaneously or especially as a previously prepared mixture. It is also possible to add the support to the mixture of these two solutions.

The contact may also be brought about by successively adding to the support a solution of the zirconium metallocene (B) and then a solution of the compound (C). It is also possible to add successively to the support a mixture of the solution of (B) with a part of the solution of (C), and then the remainder of the solution of (C).

The contact may also be brought about by first of all adding a solution of (C) to the support, and then a solution of (B). It is also possible to add to the support first of all a mixture of the solution of (C) with a part of the solution of (B), and then the remainder of the solution of (B). These successive additions can be carried out by being sequenced immediately one after the other or else by being separated by periods ranging from a few minutes to a few hours, preferably from 10 minutes to 5 hours.

In all cases it is preferable that the contact be brought about with agitation e.g. stirring, for a total period ranging from 5 minutes to 10 hours, preferably from 10 minutes to 5 hours. During the contact, the addition of a component may be very fast or slow and uniform over a period ranging from 5 minutes to 5 hours. The temperature can be from 0°C to the boiling temperature of the hydrocarbon solvent employed in the solutions, and is preferably from 0°C to 110°C. When the preparation of the catalyst is carried out in the presence of the compound (C) preferably the aluminoxane, and when the latter is used separately from the zirconium



metallocene (B), the contact of the support with (C) may be brought about at a temperature other than that at which the support is brought into contact with (B).


5 The quantities of the components used during the second stage may be such that:

- the molar ratio of the quantity of Zr of the zirconium metallocene (B) to that of the Mg of the support is from 0.001 to 1, preferably from 0.005 to 0.5, and more particularly from 0.01 to 0.1,
- 10 - the molar ratio of the quantity of Al of the compound (C) to that of Zr of the zirconium metallocene (B) is from 0 to 1,000, preferably from 1 to 500, especially from 5 to 200.

15 In particular, the quantity of the zirconium metallocene (B) used during the second stage may be such that the molar ratio of the quantity of Zr to that of the compound D2 used in the first stage is from 0.01 to 2, preferably from 0.05 to 1.

The second stage of the catalyst preparation may be carried out in the presence of an organic electron donor compound, free from labile hydrogen, added when the components are brought into contact, it being possible for this electron-donor compound to be identical to or different from the compound D1 present in the support employed. It may additionally be chosen from organic silicon compounds such as a silane compound having the general formula
 25 $R^{10}_{4-n}Si(OR^{11})_n$ wherein R^{10} and R^{11} being identical or different denote an alkyl, cycloalkyl, aralkyl, or aryl, radical e.g. of 1 to 19 carbon atoms and n is a number from 1 to 4; the silane compound may be the cyclohexylmethyldimethoxy silane.

The catalyst is obtained in the form of a solid which can be
 30 isolated by removing the hydrocarbon solvent(s) employed during the preparation. The solvent(s) may, for example, be evaporated off at atmospheric pressure or a lower pressure. The solid catalyst may also be washed with a liquid hydrocarbon, preferably an aliphatic hydrocarbon such as n-hexane or n-heptane. The catalyst is in the
 35 form of spheroidal particles whose morphology, size and particle




size distribution are substantially identical with those of the solid support (A) employed for preparing the catalyst and are otherwise described above.

5 It has surprisingly been found that the catalyst may comprise relatively large quantities of zirconium. It is thought that this surprising result is due to the fact that the solid magnesium chloride support employed is of a particular nature. It comprises, in particular, an electron-donor compound D1 free from labile hydrogen, which is dispersed homogeneously in the support and
10 initially present in the support in a relatively large quantity, this support having then been subjected to a treatment with an electron-donor compound containing labile hydrogen, D2.

The solid catalyst may be employed directly in a (co)-polymerization of olefin, e.g. C₂ to C₈ alpha-olefin, such as
15 ethylene or propylene, preferably ethylene, in the presence of a cocatalyst chosen from the organometallic compounds of a metal belonging to group II or III of the Periodic Classification of the elements. In particular, the cocatalyst may be one or more organoaluminium compounds such as a trialkylaluminium, an
20 organoaluminium hydride, an organoaluminium alkoxide or an organoaluminium halide, e.g. with each alkyl group of 1 to 10 carbon atoms, such as trimethylaluminium, triethylaluminium, tri-n-hexylaluminium, tri-n-octylaluminium, or diethylaluminium chloride, but preferably an aluminosilane corresponding to the general
25 formula mentioned above. The aluminosilane employed as cocatalyst during the polymerization may be identical to or different from that which is optionally employed in the catalyst preparation. The aluminosilane may be employed mixed with an organoaluminium compound such as that described above, e.g. a trialkylaluminium such as
30 trimethylaluminium. The quantity of cocatalyst employed in polymerization is such that the molar ratio of the quantity of metal in the cocatalyst to that of zirconium in the catalyst is between 1 and 10,000, preferably between 10 and 1,000.

The solid catalyst may be employed as such in polymerization or
35 preferably in the form of a prepolymer of olefins. A



prepolymerization step is a preferred method in a heterogeneous process for polymerizing olefins by means of the present catalyst, because the zirconium metallocene of the catalyst is more strongly fixed in the support than a non-prepolymerized catalyst and it is less capable of being extracted from the catalyst and producing fine particles of polymer during the polymerisation. Another advantage of transforming the present catalyst into a prepolymer is the improvement of the quality of the polymers obtained therefrom, in particular a polymer powder with a better morphology, higher bulk density and improved flowing properties.

The prepolymer is obtained by bringing the solid catalyst into contact with at least one olefin, e.g. C₂ to C₈ alpha-olefin, such as ethylene or propylene, preferably ethylene or a mixture of ethylene and at least one alpha-olefin containing from 3 to 8 carbon atoms. The prepolymerization may be performed in a slurry in a liquid hydrocarbon or in a gas phase, at a temperature from 0 to 100°C, preferably from 20 to 90°C, especially from 50 to 80°C, and under a total pressure from 0.1 to 5 MPa. The prepolymerization may be performed in the presence of a cocatalyst, such as that described above, either by adding to the prepolymerization medium the cocatalyst, preferably an aluminosilicate or a mixture of an aluminosilicate with an organoaluminium compound such as a trialkylaluminium, or by using the catalyst containing a sufficient quantity of the organoaluminium compound (C) preferably an aluminosilicate, or by a combination of the two methods, in such a way that the total atomic ratio of Al/Zr in the prepolymerization medium is from 10 to 1000, preferably from 50 to 500. The cocatalyst added to the prepolymerization medium, if any, may be identical or different from that employed during the polymerization. The prepolymerization may be stopped when the prepolymer contains from 0.1 to 500, preferably from 10 to 400 g of polyolefin per millimole of zirconium.

The prepolymer constitutes a further aspect of the invention and preferably consists of particles of polyethylene or copolymer of ethylene with up to 10% by weight of at least one C₃ to C₈ alpha-olefin, and comprises an active zirconium metallocene catalyst



for a further (co-)polymerization of olefins, essentially comprising atoms of zirconium, magnesium, chlorine and aluminium and being preferably free from refractory oxide, such as alumina or silica, the prepolymer containing from 0.1 to 500, preferably from 10 to 400 g of polyethylene or copolymer of ethylene per millimole of zirconium, and having an atomic ratio of Al/Zr from 10 to 1000, preferably from 50 to 500. Advantageously the prepolymer may consist of spheroidal particles, having a mass-average diameter, D_m , from 10 to 500 preferably from 30 to 300 and especially from 50 to 250 microns and a narrow particle size distribution such that the ratio of D_m to the number-average diameter D_n of the particles is not higher than 3, preferably not higher than 2.5 and especially not higher than 2.

The catalyst or the prepolymer is particularly suitable for a heterogeneous polymerization process, either in suspension in a saturated aliphatic hydrocarbon or in gaseous phase in a fluidized bed, under a total pressure of 0.1 to 5 MPa and at a temperature of 10 to 110°C, in the presence of a cocatalyst, such as that described above, preferably an organoaluminium compound and especially an aluminoxane or a mixture of a trialkylaluminium with an aluminoxane, such as that described above, in a quantity such that the total atomic ratio of Al/Zr in the (co-)polymerization medium is from 10 to 1000, preferably from 50 to 500. The catalyst or the prepolymer is preferably used in a gaseous phase polymerization process, such as in a fluidized bed, because the polymers or copolymers of ethylene thus obtained generally consist of powders having improved flowing properties and higher bulk density in comparison with those obtained in a slurry process.

The polymers or copolymers of ethylene obtainable according to the present invention, preferably in a gaseous phase (co-)polymerization process, constitutes a further aspect of the invention and may have a density from 0.89 to 0.965 g/cm³, a melt index (measured according to ASTM D 1238 condition E) from 0.01 to 50, preferably from 0.1 to 20 g/10 minutes, a molecular weight distribution (expressed by M_w/M_n) from 2 to 5, preferably from 2 to

4, catalyst residues free from refractory oxide, such as silica or alumina, essentially consisting of atoms of magnesium, chlorine, aluminium and zirconium, the quantity of zirconium being 0.5 to 20, preferably from 1 to 10, especially from 1 to 5 (ppm) parts per million by weight, and a level of ethylenic unsaturation not higher than 0.6, e.g. 0.1 to 0.6 and preferably from 0.3 to 0.5 per 1000 carbon atoms, in particular a level of vinyl unsaturation not higher than 0.5 e.g. 0.1 to 0.5, preferably from 0.2 to 0.4 per 1000 carbon atoms, and a level of vinylidene unsaturation not higher than 0.2 e.g. 0.01 to 0.2 and, preferably from 0.05 to 0.1 per 1000 carbon atoms. The copolymer of ethylene may contain up to 30% by weight, e.g. from about 0.1 to 25% by weight preferably from 5 to 25% by weight of at least one C3 to C8 alpha-olefin e.g. propylene, butene-1, hexene-1, methyl-4-pentene-1 or octene-1. Advantageously, the polymers or copolymers of ethylene are in the form of a powder having a bulk density from 0.3 to 0.55, preferably from 0.35 to 0.5 g/cm³, and preferably consisting of spheroidal particles, having a mass-average diameter, D_m, from 150 to 1000, preferably from 300 to 800 microns and a narrow particle size distribution such that the ratio of D_m to the number-average diameter D_n of the particles is not higher than 3, preferably not higher than 2.5 and especially not higher than 2.

When the weight average molecular weight, M_w, of the polymers or copolymers of ethylene is from 10⁵ to 3 x 10⁵, the molecular weight distribution (expressed by M_w/M_n) is very narrow, particularly in the range from 2 to 4, preferably from 2 to 3.5. Method of determining the mass-average (D_m) and number-average (D_n) diameters of particles.

The mass-average (D_m) and number-average (D_n) diameters of the support or catalyst particles are measured on the basis of microscopic observations, by means of the Optomax image analyser (Micro-Measurements Ltd, Great Britain). The principle of the measurement consists in obtaining, from the experimental study of a population of particles using optical microscopy, a frequency table which gives the number (n_i) of particles belonging to each class (i)



of diameters, each class (i) being characterized by an intermediate diameter (di) included within the limits of the said class.

According to the approved French Standard NF X 11-630 of June 1981, Dm and Dn are given by the following formulae:

$$\begin{aligned} \text{mass-average diameter: } D_m &= \frac{\sum n_i(d_i)^3 d_i}{\sum n_i(d_i)^3} \\ \text{number-average diameter: } D_n &= \frac{\sum n_i \cdot d_i}{\sum n_i} \end{aligned}$$

The ratio Dm/Dn characterizes the particle size distribution; it is sometimes called "width of the particle size distribution". The measurement using the Optomax image analyser is carried out by means of an inverted microscope which permits the examination of the suspensions of support or catalyst particles with a magnification of between 16 and 200 times. A television camera picks up the images given by the inverted microscope and transmits them to a computer which analyses the images received line by line and point by point on each line, in order to determine the particle dimensions or diameters, and then to classify them.

Measurement of the molecular weight distribution.

The molecular weight distribution of a (co)polymer is calculated according to the ratio of the weight-average molecular weight, Mw, to the number-average molecular weight, Mn, of the (co)polymer, from a molecular weight distribution curve obtained by means of a "Waters"(Trademark) model "150" (R) gel permeation chromatograph (High Temperature Size Exclusion Chromatograph), the operating conditions being the following:

- solvent: 1,2,4-trichlorobenzene
- solvent flow rate: 1 ml/minute
- three "Shodex" (R) (Trademark) model "AT 80 M S " columns
- temperature: 150°C
- sample concentration: 0.1% by weight
- injection volume: 500 microlitres
- detection by a refractometer integral with the



chromatograph

- calibration using a high density polyethylene sold by BP Chemicals S.N.C. under the trade name "Rigidex 6070EA": $M_w = 65,000$ and $M_w/M_n = 4$ and a high density polyethylene which has : $M_w = 210,000$ and $M_w/M_n = 17.5$.

The following nonlimiting examples illustrate the invention.

Example 1

a) Preparation of a support

10.2 litres of a mixture containing 10 moles of dibutylmagnesium in n-hexane, followed by 6.45 litres of n-hexane and finally 1 litre of diisoamyl ether were introduced in the course of a first stage under nitrogen, at room temperature (25°C), into a 30-litre stainless steel reactor equipped with a stirrer rotating at a speed of 600 revolutions per minute and a jacket. In a second stage, where the speed of the stirrer was maintained at 600 revolutions per minute and the reaction temperature at 25°C, 2.4 l of tert-butyl chloride were added to the mixture thus obtained, at a constant flow rate during 12 hours. At the end of this period the reaction mixture was maintained at 25°C for 3 hours. The precipitate obtained was washed with 15 litres of n-hexane at 25°C. The solid product obtained constituted the magnesium dichloride support, containing 0.12 moles of diisoamyl ether and less than 0.0001 mole of Mg-C bond per mole of magnesium dichloride. When examined with a microscope, the support was in the shape of spheroidal particles which had a mass-average diameter of 35 microns and an extremely narrow particle size distribution, such that the D_m/D_n ratio of the particles was equal to 1.4.

The specific surface of the support was approximately 45 m^2/g (BET).

b) Preparation of a catalyst

285 ml of an n-hexane suspension of the previously prepared support containing 100 millimoles of magnesium were introduced at 25°C under nitrogen atmosphere into a glass reactor with a capacity of 1 litre, equipped with a stirrer



rotating at 350 revolutions per minute and with a heating and cooling system, followed by 20 millimoles of n-butanol. The mixture was kept stirred at 25°C for 1 hour. At the end of this period the support is washed twice, each with 200 ml of n-hexane at 25°C.

A 100 ml n-hexane suspension of the previously washed support, containing 100 millimoles of magnesium, was kept at 25°C under a nitrogen atmosphere in the same reactor. 100 ml of a solution of bis(cyclopentadienyl)dichlorozirconium (Cp_2ZrCl_2) in toluene containing 5 millimoles of Zr were then introduced into the reactor at 25°C, with stirring. The reactor was then heated to 70°C and the mixture was then kept stirred at 70°C for 2 hours. At the end of this period the reactor was cooled to 50°C and the catalyst thus obtained was washed four times, each with 200 ml of n-hexane at 50°C and then twice, each with 200 ml of n-hexane at 25°C, while cooling the reactor to 25°C. A solid catalyst which was ready for use was obtained in the form of spheroidal particles which had $D_m = 35$ microns and a D_m/D_n ratio = 1.4. It contained the elements Zr and Mg in a molar ratio $\text{Zr/Mg} = 0.0113$

c) Polymerization of ethylene in suspension in n-hexane

500 ml of n-hexane were introduced under a nitrogen atmosphere into a stainless steel reactor with a capacity of 2 litres, equipped with a stirrer rotating at 350 revolutions/minute and with a heating and cooling system. The reactor was heated to 70°C and a quantity of previously prepared catalyst was introduced into it, corresponding to 0.0025 millimoles of zirconium and 25 milliatoms of aluminium as methylaluminoxane (MAO) in solution at a concentration of 30% by weight in toluene, the solution of (MAO) being sold by Schering company (Germany). A volume of 50 ml of hydrogen, measured under normal conditions, was then introduced into the reactor, followed by ethylene at a steady flow rate of 60 g/h during 75 minutes. At the end of this period the polymerization was stopped and after the n-hexane had been removed a



polyethylene powder was recovered, which had a melt index of 3.9 g/10 minutes, measured at 190°C under a 2.16 kg weight. The Mw/Mn ratio of the polyethylene, measured by GPC, was 2.3.

Example 2

5 a) Preparation of a support

This was exactly identical with that of Example 1.

b) Preparation of a catalyst

10 The preparation was carried out exactly as in Example 1, apart from maintaining the reactor at 25°C and the mixture stirred at 25°C for 2 hours after the introduction of the zirconium compound in the reactor. The catalyst thus obtained was then washed six times, each with 200 ml of n-hexane at 25°C. A solid catalyst which was ready for use was obtained in the form of spheroidal particles which had $D_m = 35$ microns and
15 a D_m/D_n ratio = 1.4. It contained the elements Zr, and Mg in a molar ratio $Zr/Mg = 0.01$.

c) Polymerization of ethylene in suspension in n-hexane

A polymerization was carried out exactly as in Example 1, apart from using the previously prepared catalyst.
20 A polyethylene powder was recovered, which had a melt index of 2g/10 minutes measured at 190°C under a 2.16 kg weight. The Mw/Mn ratio of the polyethylene, measured by GPC, was 2.3.

Example 3

a) Preparation of a support

25 This was exactly identical with that of Example 1.

b) Preparation of a catalyst

30 100 ml of a suspension in n-hexane of the previously prepared support containing 100 millimoles of magnesium were introduced at 25°C under nitrogen atmosphere into a glass reactor with a capacity of 1 litre equipped with a stirrer rotating at 350 revolutions per minute and with a heating and cooling system, followed slowly by 100 millimoles of n-butanol over 2 hours. At the end of this period the support was washed once with 500 ml of n-hexane at 25°C.

35 A 100 ml n-hexane suspension of the previously washed



support, containing 100 millimoles of magnesium was kept at 25°C under nitrogen atmosphere in the same reactor. 14 ml of a solution of (MAO) in toluene, containing 25 milliatoms of aluminium were then introduced at 25°C into the reactor with stirring. The reactor was heated to 70°C and the mixture was kept stirred at 70°C for 2 hours. The reactor was cooled to 50°C and the solid obtained was washed four times, each with 200 ml of n-hexane at 50°C and then twice, each with 200 ml of n-hexane at 25°C, while the reactor was cooled to 25°C. 100 ml of a solution of (Cp₂ZrCl₂) in toluene, containing 5 millimoles of zirconium, were then introduced into the reactor at 25°C with stirring. The reactor was heated to 70°C and the mixture was kept stirred at 70°C for 2 hours. The reactor was cooled to 50°C and the solid catalyst obtained was washed four times, each with 200 ml of n-hexane at 50°C and then twice, each with 200 ml of n-hexane at 25°C while the reactor was cooled to 25°C.

A solid catalyst which was ready for use was obtained, containing the elements Zr, Mg and Al and the butoxy radical in the following molar ratios:

$$\text{Zr/Mg} = 0.0111$$

$$\text{Al/Zr} = 9$$

$$\text{Butoxy/Mg} = 0.88$$

c) Polymerization of ethylene in suspension in n-hexane

The polymerization was carried out exactly as in Example 1, apart from using the previously prepared catalyst.

A polyethylene powder was obtained which had a melt index of 6.8 g/10 minutes measured at 190°C under 2.16 kg. The Mw/Mn ratio of the polyethylene was 2.1.


30 Example 4

a) Preparation of a support

This was exactly identical with that of Example 1.

b) Preparation of a catalyst

100 ml of a toluene suspension of the previously prepared support containing 100 millimoles of magnesium were introduced



at 25°C under nitrogen atmosphere into a glass reactor with a capacity of 1 litre, equipped with a stirrer rotating at 350 revolutions per minute and with a heating and cooling system, followed by 20 millimoles of n-butanol. The mixture was kept stirred at 25°C for 1 hour. At the end of this period the support was washed twice, each with 100 ml of toluene at 25°C.

A 100 ml toluene suspension of the previously washed support, containing 100 millimoles of magnesium, was kept at 25°C in the same reactor under nitrogen atmosphere. 250 ml of a mixture in toluene containing 10 millimoles of (Cp₂ZrCl₂) and 250 milliatoms of aluminium as (MAO) in solution at a concentration of 30% by weight in toluene had been previously prepared in a separate vessel under nitrogen atmosphere, by contacting (Cp₂ZrCl₂) and (MAO) with stirring at 25°C for 1 hour. The mixture was then introduced into the reactor at 25°C with stirring. The reactor was heated to 70°C and the mixture was kept stirred at 70°C for 2 hours. At the end of this period, the catalyst thus obtained was washed ten times, each with 200 ml of n-hexane at 70°C. A solid catalyst which was ready for use was obtained in the form of spheroidal particles which had D_m = 35 microns and a D_m/D_n ratio = 1.4. It contained the elements Zr, Mg and Al in the following molar ratios:

$$\text{Zr/Mg} = 0.04$$

$$\text{Al/Zr} = 0.16$$

c) Preparation of a prepolymer

Into a 5 litre stainless steel reactor equipped with a stirrer rotating at 500 revolutions/minute were introduced under nitrogen 2 litres of n-hexane which were heated to 70°C, then a mixture consisting of 260 milliatoms of aluminium as (MAO) in solution at a concentration of 30% by weight in toluene and a quantity of previously prepared catalyst corresponding to 1.3 milliatoms of zirconium. Ethylene was then introduced into the reactor at a uniform rate of 133 g/h for 90 minutes. At the end of this period, the reactor was



cooled at ambient temperature (20°C) and the content of the reactor was transferred to a rotary evaporator and the solvent was evaporated off under reduced pressure at a temperature of 60°C. A prepolymer was thus obtained and stored under nitrogen. It contained 153 g of polyethylene per millimole of zirconium and the atomic ratio Al/Zr was 200. It consisted of spheroidal particles having $D_m = 90$ microns and a particle size distribution such that the ratio $D_m/D_n = 1.5$.

d) Gas phase polymerization of ethylene

A powder charge of 800 g of a polyethylene originating from a preceding polymerization and which had been stored under nitrogen, was introduced into a fluidized bed reactor having a diameter of 18 cm. The reactor was heated to 80°C and ethylene was introduced into it, so as to obtain a pressure of 1.0 MPa. Ethylene passed upwardly through the bed with a fluidization speed of 30 cm/sec.

25 g of the previously prepared prepolymer were introduced into the fluidized bed reactor and the temperature in the bed was kept at 80°C during 8 hours. A polyethylene powder was thus prepared, having a density of 0.95 g/cm³, a melt index (ASTM D 1238 condition E) of 0.1 g/10 minutes, a molecular weight distribution such that $M_w/M_n = 2.5$, a zirconium content of 5 (ppm) parts per million by weight, a level of vinyl unsaturation of 0.4 per 1000 carbon atoms and a level of vinylidene unsaturation of 0.1 per 1000 carbon atoms. The powder consisted of spheroidal particles, having $D_m = 400$ microns and a ratio $D_m/D_n = 1.5$. It had a bulk density of 0.45 g/cm³.

Example 5

a) Preparation of a support

This was exactly identical with that of Example 1.

b) Preparation of a catalyst

The preparation was carried out exactly as in Example 4, apart from preparing 250 ml of a mixture in toluene containing 5 millimoles of (Cp₂ZrCl₂) and 125 milliatoms of aluminium as



(MAO) in solution at a concentration of 30% by weight in toluene, and apart from introducing the mixture into the reactor.

5 A solid catalyst was obtained in the form of spheroidal particles which had $D_m = 35$ microns and a D_m/D_n ratio = 1.4. It contained the elements Zr, Mg and Al in the following molar ratios:

$$\text{Zr/Mg} = 0.05$$

$$\text{Al/Zr} = 0.14$$

10 c) Preparation of a prepolymer

The preparation was carried out exactly as in Example 4, apart from using the previously prepared catalyst.

d) Gas phase polymerization of ethylene

15 The polymerization was carried out exactly as in Example 4, apart from using the previously prepared prepolymer.

A polyethylene powder was thus prepared, having a density of 0.947 g/cm^3 , a melt index (ASTM D 1238 condition E) of 0.1 g/10 minutes, a molecular weight distribution such that $M_w/M_n = 2.6$, and a zirconium content of 4 ppm. The powder consisted of
20 spheroidal particles, having $D_m = 450$ microns and a ratio $D_m/D_n = 1.6$. It had a bulk density of 0.46 g/cm^3 .

Example 6

a) Preparation of a support

This was exactly identical with that of Example 1.

25 b) Preparation of a catalyst

The preparation was carried out exactly as in Example 5, apart from maintaining the reactor at 25°C and the mixture stirred at 25°C for 2 hours after the introduction into the reactor of the mixture containing (Cp_2ZrCl_2) and (MAO).

30 A solid catalyst was obtained in the form of spheroidal particles which had $D_m = 35$ microns and a D_m/D_n ratio = 1.5. It contained the elements Zr, Mg and Al in the following molar ratios:

$$\text{Zr/Mg} = 0.034$$

35 $\text{Al/Zr} = 0.15$



c) Preparation of a prepolymer

The preparation was carried out exactly as in Example 4, apart from using the previously prepared catalyst.

d) Gas phase polymerization of ethylene

5 The polymerization was carried out exactly as in Example 4, apart from using the previously prepared prepolymer.

A polyethylene powder was thus prepared, having a density of 0.946 g/cm³, a melt index (ASTM D 1238 condition E) of 0.2 g/10 minutes, a molecular weight distribution such that Mw/Mn = 10 2.5 and a zirconium content of 5 ppm. The powder consisted of spheroidal particles, having Dm = 400 microns and a ratio Dm/Dn = 1.7. It had a bulk density of 0.46 g/cm³.

15

20

25

30

35





CLAIMS

1. Solid catalyst suitable for a heterogeneous process for polymerizing one or more olefins, the solid catalyst being prepared by contacting a zirconium metallocene with a magnesium chloride support, characterized in that the solid catalyst is obtainable by a process comprising:
- 5
- (1) a first stage, wherein a solid support (A) containing from 80 to 99.5 mol% of magnesium dichloride and from 0.5 to 20 mol% of at least one organic electron-donor compound, D1, free from labile hydrogen, the solid support (A) being in the form of
- 10 spheroidal particles with a mass-average diameter, D_m , of 10 to 100 microns and a particle size distribution, such that the ratio of D_m to the number-average diameter, D_n , of the particles is not higher than 3, is brought into contact with at least one electron-donor compound, D2, containing labile
- 15 hydrogen,
- (2) then, a second stage, wherein the support resulting from the first stage is brought into contact with a zirconium metallocene (B), optionally with an organoaluminium compound (C), preferably an aluminoxane.
- 20
2. Solid catalyst according to Claim 1, characterized in that the organic electron-donor compound, D1, free from labile hydrogen is chosen from ethers, esters, thioethers, sulphones, sulfoxides, secondary amides, tertiary amines, tertiary phosphines and phosphoramides.
- 25
3. Solid catalyst according to Claim 1, characterized in that the





electron-donor compound, D2, containing labile hydrogen is chosen from alcohols, phenols, primary amides, primary or secondary amines and primary or secondary phosphines.

4. Process for preparing the solid catalyst according to any of
5 Claims 1 to 3, characterized in that:

- in the first stage, the compound D2 is used in an amount such that the molar ratio of the quantity of D2 to that of magnesium is from 0.05 to 3, and
- in the second stage, the amounts of the components used are
10 such that the molar ratio of the quantity of Zr of (B) to that of Mg is from 0.001 to 1, and the molar ratio of the quantity of Al of (C) to that of Zr of (B) is from 0 to 1000.

5. Prepolymer particles characterized in that they comprise (i) a
15 polyethylene or a copolymer of ethylene with up to 10% by weight of at least one C3 to C8 alpha-olefin and (ii) an active catalyst for a further (co-)polymerization of olefins essentially containing atoms of zirconium, magnesium, chlorine and aluminium, and comprising an organoaluminium compound as cocatalyst and the solid catalyst according to any of Claims 1 to 3, or prepared according to Claim 4,
20 in a quantity such that the prepolymer contains from 0.1 to 500 g of polyethylene or copolymer of ethylene per millimole of zirconium and the atomic ratio Al/Zr is from 10 to 1000.

6. Prepolymer particles according to Claim 5, characterized in that they consist of spheroidal particles, having a mass-average
25 diameter, Dm, from 20 to 500 microns and a particle size distribution such that the ratio of Dm to the number-average diameter, Dn, of the particles is not higher than 3.

7. Process for preparing the prepolymer particles according to Claim 5 or 6, characterized in that the solid catalyst according to
30 any of Claims 1 to 3 or prepared by a process according to Claim 4 is contacted with ethylene or a mixture of ethylene and at least one C3 to C8 alpha-olefin in a liquid hydrocarbon slurry or in a gas phase, at a temperature from 0 to 100°C, under a total pressure from 0.1 to 5 MPa, in the presence of an organoaluminium compound in a
35 quantity such that atomic ratio Al/Zr is from 10 to 1000.





8. Process for polymerizing ethylene or copolymerizing ethylene with at least one C3 to C8 alpha-olefin, characterized in that the solid catalyst according to any of Claims 1 to 3 or prepared according to Claim 4, or the prepolymer particles according to Claim 5 or 6 or prepared according to Claim 7, are contacted with ethylene or a mixture of ethylene with at least one C3 or C8 alpha-olefin, at a temperature of 10 to 110°C, under a total pressure of 0.1 to 5 MPa, in the presence of an organoaluminium compound, in a quantity such that the atomic ratio Al/Zr is from 10 to 1000.
9. Polymer or copolymer powder obtainable by the process according to Claim 7 or 8, comprising (i) a polyethylene or a copolymer of ethylene with up to 30% by weight of at least one C3 to C8 alpha-olefin, having a density from 0.89 to 0.965 g/cm³, a melt index (ASTM D 1238 condition E) from 0.01 to 50g/10 minutes, a molecular weight distribution from 2 to 5 and a level of ethylenic unsaturation not higher than 0.6 per 1000 carbon atoms and (ii) catalyst residues essentially consisting of atoms of magnesium, chlorine, aluminium and zirconium, the quantity of zirconium being from 0.5 to 20 parts per million by weight, the said powder having a bulk density from 0.3 to 0.55 g/cm³.
10. Polymer or copolymer powder according to Claim 9, characterized in that it consists of spheroidal particles, having a mass-average diameter, D_m, from 150 to 1000 microns and a particles size distribution such that the ratio of D_m to the number-average diameter, D_n, of the particles is not higher than 3.

30

35

