

Title: Method for Manufacture of a Multi-layer Pipe

The present invention relates to a method for manufacture of a multi-layer pipe. Multi-layer pipes are preferably used when high demands exist against corrosion or abrasion.

Corrosion-resistant pressure vessels or pressure lines can be produced in a more cost-effective way than solid versions of corresponding materials when multi-layer pipes are used. This is achieved by load distribution on a thin, corrosion-resistant internal layer (e.g. stainless and acid-resistant steel) and a high-strength and pressure-proof external layer (e.g. fine-grained structural steel). Steel consumption can be considerably decreased as a result and a large part of the remaining steel consumption can be shifted to more cost-effective materials.

In certain grades, abrasion-resistant pipelines can only be manufactured when being executed as a multi-layer pipe (for instance with mechanical bonding, see below), since materials (e.g. high-strength steels with high hardness) can be used as an internal layer which for itself cannot be processed into pipes or only under great difficulties.

Other material combinations are possible in a great diversity but basically the combination possibilities of materials are restricted in this context only by the processing methods eligible in each case.

When creating the pipe sheathing, there are two possibilities

- **metallurgical** bonding over the entire surface (requiring cladmed plates as initial semi-finished product), and
- merely **mechanical** bonding (for instance friction bonding) between internal and external pipe - preferably internal and external plates and their welding on the plate edges -.

Manufacture of such multi-layer pipes is done as follows in Prior Art :
Such a method is already known from the JP-A-60111791.

For multi-layer pipes with metallurgical bonding between the layers - for instance multi-layer pipes out of metal plates, preferably steel plates - a clad composite plate made out of two different (steel) materials is used as an initial semi-finished product. The multi-layer pipe is then manufactured as follows:

- 5 - At first the composite plate is produced by roll-bonding or explosion cladding,
- then pipe forming is made in accordance with usual methods such as for example by means of a bending roller or a bending press and
- subsequently welding occurs with the outer wall of the multi-layer pipe being executed in accordance with the usual pipe welding methods pursuant to the material used and inner wall welding occurring as deposition welding likewise
- 10 pursuant to the material.

The disadvantage of this procedure according to Prior Art is on the one hand the high cost of the initial semi-finished product and thus also of the final product, but on the other hand also insufficient availability of the initial semi-finished product, because

15 production capacities are very restricted for it on a world-wide basis. Thus, as far as is known to the applicant and the inventor, only a few installations exist for the production of roll-bonded multi-layer plates, for instance in Austria and in Japan, but for example, not a single one in the Federal Republic of Germany. Neither installations for explosion

20 cladding do hardly exist as far as is known to the inventor and the applicant. For example, at Dynamit Nobel at Burbach, Federal Republic of Germany, one of a few of such plants exists. The production engineering used for it is also a great problem and therefore expensive and intricate taking into consideration in addition that it is only available for very small production lots, anyhow.

25 Moreover, the number of materials, which can be processed in this way, is restricted. Thus, for example, certain abrasion-resistant steels cannot be used as an internal layer, if they can hardly be welded or not welded at all due to their high carbon content.

30 In the case of multi-layer pipes with mechanical bonding, several - preferably two - finished pipes are used as an initial semi-finished product. The process will be explained below by way of an example with two pipes (in the event of more layers, the explanations have to be understood accordingly):

- two finished pipes are manufactured in close fit and moved into each other without friction with the external pipe requiring a higher yield point than the internal pipe
- 5 - by expansion (mechanically - for example, by means of an expansion die - or by fluid pressure with the pipes placed into each other being pressed into a die comprising the external pipe) the internal pipe is pressed into the external pipe by elastic expansion of the external pipe. After the expansion forces are omitted, the external pipe places itself non-positively around the internal pipe due to the higher elastic resiliency
- 10 - finally the two materials are welded on their faces.

The disadvantage of this process of Prior Art is that the external pipe must have a higher yield point than the internal pipe, since otherwise the elastic resiliency of the external pipe causing the non-positive connection with the internal pipe and therefore
15 being necessary, is missing. This is particularly disadvantageous, because high-strength materials - for instance, especially high-strength steels - as they are especially advantageous preferably for abrasion-resistant pipelines inside the pipe, have high or even very high yield points, and are therefore unsuitable for this manufacturing process.

20 It is therefore the object of the present invention to provide on the basis of the State of the Art a method for manufacture of a multi-layer pipe, which on the one hand tries and avoids the above mentioned disadvantages and thus not requiring roll-bonded and/or explosion cladded semi-finished products but which on the other hand is neither
25 subject to the restrictions involved in manufacture of multi-layer pipes according to the State of the Art with frictionally engaged mechanical bonding of layers among each other.

This object is met according to the invention by a method for manufacture of a multi-layer pipe according to claim 1. Further preferred embodiments can be found in the
30 dependent claims.

According to the present invention, application of roll-bonded and/or explosion cladded semi-finished products can be avoided by pressing the respective material layer acting as an internal pipe already during pipe forming in the bending roller and/or the bending machine, usually necessary for final shaping, non-positively into the material layer
5 acting as an external pipe so that it is frictionally maintained in the respective external pipe without the necessity to expand the multi-layer pipe and thus running into the disadvantages already mentioned. It is pointed out that in some cases, however, final forming or shaping is already possible in the bending roller alone, for example, in the event of shorter bending rollers which can include the function of end forming of the
10 pipe. In that cases a bending machine is not included in the method according to the invention.

If in this text a connection alongside an edge or alongside a (preferably only imaginary) line is mentioned, any type of connection alongside the edge or line is meant, whether
15 this connection exists alongside the entire edge or line or only in sections alongside the edge or line or only in individual spots (such as for example spot welding), for example in two spots - preferably at the end spots of the edge or line - or even only in an individual spot on the edge or on the line.

20 In a preferred embodiment of the method for manufacture of a multi-layer pipe by means of a bending roller according to the present invention,

- the first connection between the material layers is created by connecting them alongside one of the longitudinal or transverse edges of the material layer resting on the other material layer, and
- 25 - at least one other connection occurs between the material layers after a definite shaping progress alongside the second longitudinal or transverse edge of the material layer resting on the other material layer.

The at least one other connection between the material layers can, for example, be
30 created after a shaping progress between 50 % and less than 100 %.

In another, especially preferred embodiment of the method for manufacture of a double-layer pipe as a multi-layer pipe with an external pipe and an internal pipe by

means of a bending roller according to the present invention, the shaping progress occurs after the at least one other connection between the material layers is made - called F_{for} here and indicated in parts per cent - preferably approximately as follows :

$$F_{for} = \left(1 - \frac{\frac{\sigma_I}{E} \cdot (DA - 2 \cdot SA - SI) \cdot \pi \cdot (Z_s + 1)}{(DA - SA) \cdot \pi - (DA - 2 \cdot SA - SI) \cdot \pi} \right) \cdot 100$$

- 5 with DA being the external diameter of the external pipe in mm,
 SA being the wall thickness of the external pipe in mm,
 SI being the wall thickness of the internal pipe in mm,
 s_I being the yield point of the internal pipe in N/mm²
 Z_s being the upsetting allowance indicated in parts per cent
 10 and
 E being the Young's modulus in N/mm².

The above mentioned expression results from the following relations:

The length of the neutral fibre of the external pipe - here called L_{nfa} - is:

$$15 \quad L_{nfa} = (DA - SA) \cdot \pi$$

The length of the neutral fibre of the internal pipe - here called L_{nfi} - is:

$$L_{nfi} = (DA - 2 \cdot SA - SI) \cdot \pi$$

Shifting of the free plate edge at 100 % degree of shaping of the pipe - here called L_{fv} - is then:

$$20 \quad L_{fv} = L_{nfa} - L_{nfi}$$

The degree of upsetting of the internal pipe in order to reach the upsetting limit - here called ε_{st} - results as follows:

$$\varepsilon_{st} = \frac{\sigma_I}{E}$$

and the length of upsetting in order to reach the upsetting limit results as :

$$25 \quad L_{st} = \varepsilon_{st} \cdot L_{nfi} \cdot (Z_s + 1)$$

The shaping progress during which further connection between the material layers takes place - here called F_{for} - is then (indicated as a value between 0 and 1) approximately:

$$F_{for} = 1 - \frac{L_{st}}{L_{fv}}$$

5 and indicated in parts per cent :

$$F_{for} = \left(1 - \frac{L_{st}}{L_{fv}} \right) \cdot 100 .$$

If this expression is resolved with:

- 10 DA being the external diameter of the external pipe in mm,
 SA being the wall thickness of the external pipe in mm,
 SI being the wall thickness of the internal pipe in mm,
 s_I being the yield point of the internal pipe in N/mm²
 Z_s being the upsetting allowance indicated in parts per cent
 and
 E being the Young's modulus in N/mm²

15 one gets the expression for the shaping progress already specified at the beginning where the further connection takes place between the materials - here called F_{for} - and indicated in parts per cent. The upsetting allowance takes into account production inaccuracy in locating the at least one other material layer connection and compensates it in such a way that the intended force of pressure of the internal pipe
 20 against the external pipe is at least achieved.

Some examples are intended to illustrate this with the minimum and maximum as well as the typical example referring to the percentage degree of shaping at which the at least one other connection between the material layers occurs:

Given are:		eventual minimum	typical example	eventual maximum
	unit	ex. 1	ex. 2	ex. 3
DA (external diameter of external pipe)	mm	406	762	2500
SA (wall thickness of the external pipe)	mm	25	20	12
SI (wall thickness of the internal pipe)	mm	10	3	1
s_I (yield point of internal pipe)	N/mm ²	100	350	480

Z _s (upsetting allowance)	(%)	0%	50%	15%
E (Young's modulus)	N/mm ²	210,000	210,000	210,000

Table 1: Examples for Determination of the Shaping Progress for one other Connection of the Material Layers

The searched quantities are then as follows:

For the examples given in table 1, the following results for the searched quantities:			eventual minimum	typical example	eventual maximum
		unit	ex. 1	ex. 2	ex. 3
length of the neutral fibre of the external pipe:	$L_{nfa} = (DA - SA) \cdot \pi$	mm	1,196.9	2,331.1	7,816.3
length of the neutral fibre of the internal pipe:	$L_{nfi} = (DA - 2 \cdot SA - SI) \cdot \pi$	mm	1,087.0	2,258.8	7,775.4
shifting of the free plate edge at 100 % shaping:	$L_{fv} = L_{nfa} - L_{nfi}$	mm	110.0	72.3	40.8
degree of upsetting of the internal pipe in order to achieve the upsetting limit:	$\epsilon_{st} = s_l / E$	(%)	0.05%	0.17%	0.23%
length of upsetting in order to achieve the upsetting limit:	$L_{st} = \epsilon_{st} \cdot L_{nfi} \cdot Z_s$	mm	0.52	5.65	20.44
required degree of shaping for the at least one other connection, for example for locating the second plate edge:	$F_{for} = 1 - L_{st} / L_{fv}$	(%)	99.5%	92.2%	50.0%

5 Table 2: Searched Quantities for the Examples for Determination of the Shaping Progress for another Connection of the Material Layers from Table 1

Another preferred embodiment of the method for manufacture of a multi-layer pipe by means of a bending roller according to the present invention is characterised in that at least one of the material layers comprises more than one element positioned above, preferably more than one plate. The elements positioned above can be positioned with their longitudinal edge in parallel to the material layer below but this must not be the case. Thus it is also possible that they are positioned transversely to it with their longitudinal edge.

15

If the elements are with their longitudinal edge in parallel - preferably approximately parallel - to the longitudinal edge of the material layer below, the first connection between the material layers is preferably created by the elements, preferably plates,

after their positioning on top alongside their joining location, which at the same time constitutes each a longitudinal edge of the elements, preferably plates, of the material layer on top, being connected with the material layers below, preferably the plate below.

5

This method is particularly suitable for the manufacture of multi-layer pipes according to the present invention having large diameters, preferably greater than 610 mm (24"), where often the width of available internal layer material strips, preferably steel strips (steel plates), is not sufficient, in order to produce an entire internal layer for such large
10 pipes. If even two strips are not sufficient, the procedure can be continued at will: in that case three or even more elements, preferably plates, are positioned.

In the method for manufacture of a multi-layer pipe by means of a bending roller according to the present invention, the multi-layer pipe is preferably closed by welding
15 of the external pipe alongside the pipe seam and a deposition welding of the internal pipe in order to produce the multi-layer pipe body.

Also, the material layers can be connected on the pipe faces, for example to prevent that humidity penetrates between the material layers which are metallurgical not
20 connected over the entire surface.

A preferred application of the method according to the present invention is the manufacture of inventive double-layer pipes, although the invention is not restricted to it. Also three-, four-layer pipes and pipes with even more layers can generally be
25 produced according to the present invention which is far more difficult in Prior Art or even not possible at all.

In another especially preferred embodiment of the present invention, plates, preferably metal plates, and more preferably, steel plates, are used as material layers or elements
30 of the material layer.

Also, in the method for manufacture of a multi-layer pipe by means of a bending roller according to the present invention, preferably at least one of the connections of the

material layers is made as a welding, which is particularly suitable for the metal plates, preferably steel plates, mentioned above.

5 The multi-layer pipe obtained according to the inventive method, can be formed in particular such that a material layer positioned inside has a higher yield point or proof stress (see below) compared with the outer material layer with at least one material layer comprising preferably a metal plate, and more preferably, a steel plate.

10 An especially preferred embodiment of a multi-layer pipe obtained according to the present invention is characterised in that the multi-layer pipe is formed as a double-layer pipe exhibiting two steel plate material layers with the steel plate, which acts as an internal pipe, having a high up to a very high carbon content and thus is at least not necessarily weldable any more.

15 The multi-layer pipes obtained in such a way according to the present invention are different from those of Prior Art in a variety of ways but without these differences having to become evident all at the same time in one multi-layer pipe according to the present invention which could be identified accordingly. Rather these difference can also occur in different combinations among each other but need not do so necessarily.

20 Thus according to the present invention it is on the one hand not necessary to use clad plates (with the disadvantages, already discussed at the beginning, of long delivery times and limited availability as well as high prices), on the other hand nevertheless multi-layer pipes - especially double-layer pipes out of steel plate material
25 layers - with a high yield point of the material of the respective internal pipe and simultaneous low yield point of the material of the respective external pipe can be manufactured, which is necessary, for example, for such applications of multi-layer pipes requiring a possibly high abrasion resistance of the internal pipe, since high abrasion resistance normally coincides also with a high hardness which in turn
30 coincides with a high yield point. Such multi-layer pipes having an internal pipe made out of a material with a higher or the same yield point than the respective external pipe but which have nevertheless no metallurgical connection of adjacent layers over the entire surface, cannot be manufactured according to Prior Art. They do not exist until now. But they become possible due to the present invention. It must be pointed out that

in the event of a not very distinct yield point - for example, in cases of only increased plastic deformation - the proof stress will be substituted for the yield point as the amount of stress of a plastic permanent expansion under a certain impact of force.

- 5 Independent of it, also multi-layer pipes can be manufactured by means of the method according to the present invention, without using expensive and hardly available, clad plates (mechanically connected over the entire surface), in almost any large diameters, which is not possible according to Prior Art, since here the necessary expansion is limited by the dimensions of the expansion die used, or by a die
- 10 necessary for uniform shaping in the case of a hydraulic expansion force impact which encloses the multi-layer pipe to be manufactured. Compared with this the inventive roll bending process permits multi-layer pipes, which are not subject to such predetermined limitations, since the bending roller, which intervenes for shaping purposes always only in one location of the pipe radius of curvature, does not limit the diameter of the
- 15 inventive multi-layer pipe. Thus in particular also multi-layer pipes without clad plates can be manufactured which exceed - and preferably exceed by far - the limit of the present State of the Art of a diameter of approx. 610 mm (24").

- The present invention permits manufacture of multi-layer pipes with partial internal
- 20 layer at all, i.e. an internal pipe forming a graduated circle in cross-section, for example in the form of a channel insert at the pipe base which is likewise not possible in Prior Art until now.

- In this connection it should be mentioned that according to method of the present
- 25 invention of course also pipes in only very small quantities, especially also individual pipes, can be economically manufactured, which in Prior Art on the one hand is impeded by the intricate cladding and the minimum production lots necessary for it, and on the other hand by the especially set up tools and appliances required for expansion.

- 30 Below, non-limitative embodiments will be discussed by means of the drawings, in which

Fig. 1 is a perspective plan view of two material layers, to be combined into a multi-layer pipe, put onto each other,

- 5 Fig. 2 is a perspective plan view of two material layers, to be combined into a multi-layer pipe, put onto each other, with a first connection, preferably welding, between the material layers, approximately alongside an (imaginary) line parallel to one of the longitudinal edges of the material layer positioned above.
- 10 Fig. 3 is a perspective plan view of two material layers, to be combined into a multi-layer pipe, put onto each other, with one of the material layers comprising two elements - preferably plates - placed in longitudinal pipe direction,
- 15 Fig. 3a is another perspective plan view of two material layers, to be combined into a multi-layer pipe, put onto each other, with one of the material layers, namely the material layer placed above, constituting a plurality of elements - preferably plates - placed in circumferential pipe direction,
- 20 Fig. 4 is a perspective plan view of two material layers, to be combined into a multi-layer pipe, put onto each other, with one of the material layers comprising more than one, namely two elements here - preferably plates - placed above, and a first connection was created here between the material layers by connecting - preferably welding - the elements with the material layer below, after their positioning alongside their joining location, which at the same time constitutes each a longitudinal edge of the elements of the material layer placed above,
- 25 Fig. 5 a perspective view from a front into a multi-layer pipe according to the present invention during the inventive manufacturing process, namely in the process step where the thus formed multi-layer material is shaped into a pipe by means of the bending roller (not shown here) with a constant friction-tight connection being created between the material layers as a result of the pressure of the rollers from the top and from the bottom, and during shaping, the portions of the material layers, which can still shift freely against each other, shifting freely to each other in accordance with the shaping progress due to the different bend radii of internal pipe and external pipe,
- 30

Fig. 6 a perspective view from a front into a multi-layer pipe according to the present invention during the inventive manufacturing process, namely in the process step where after a definite shaping progress at least one other connection between the material layers is created by connecting the material layer positioned on top in at least one other position to each other,

Fig. 7 a perspective cross-section of a finished multi-layer pipe according to the present invention with internal and external layer,

Fig. 8 a perspective cross-section of a multi-layer pipe with internal and external layer with detailed view in the area of the weld seam,

Fig. 1 shows a perspective plan view of two material layers **1, 2**, to be combined into a multi-layer pipe, put onto each other.

Fig. 2 shows a perspective plan view of two material layers, to be combined into a multi-layer pipe, put onto each other, with a first connection **3a** and **3b** - preferably welding (namely in the points **3a** and **3b**) - between the material layers **1, 2**, approximately alongside an (imaginary) line parallel to a longitudinal edge **4** of the material layer positioned above **1**.

Fig. 3 is a perspective plan view of two material layers **1a, 1b, 2**, to be combined into a multi-layer pipe, put onto each other, with one of the material layers here, namely the material layer placed above, comprising two elements **1a, 1b** - preferably plates - placed in longitudinal pipe direction.

Fig. 3a is another perspective plan view of two material layers **1a, 1b, ..., 1n, 2**, to be combined into a multi-layer pipe, put onto each other, with one of the material layers here, namely the material layer placed above, constituting a plurality, namely a finite number - here called **n** - of elements **1a, 1b 1n** - preferably plates - placed in circumferential pipe direction. The fact that it may be any number of **n** elements **1a, 1b, ..., 1n** placed above, is specified in the drawing by a dotted line **11**.

The elements placed above **1a, 1b 1n** are here placed with their longitudinal edge **4** transversely to the longitudinal edge of the material layer **2** placed below, whereas with their respective transverse edge **4a** they are here placed parallel to the longitudinal edge of the material layer **2** placed below. Also, the respective first
5 connections **3a₁, 3a₂, 3b₁, 3b₂, 3n₁, 3n₂** provided in this arrangement of the elements **1a, 1b 1n** placed onto material layer **2** can be seen here.

Fig. 4 shows a perspective plan view of two material layers **1a, 1b, 2**, to be combined into a multi-layer pipe, put onto each other, with one of the material layers comprising
10 more than one, namely two elements **1a, 1b** here - preferably plates - placed above, and a first connection **3** was created here between the material layers by connecting, preferably welding, the elements **1a, 1b** with the material layer **2** below, after their positioning alongside their joining location, which at the same time constitutes each a longitudinal edge of the elements **1a, 1b** of the material layer placed above. Here, this
15 connection **3** was made alongside the joining location and at the same time longitudinal edge by a closed connection **3**, preferably welding, extending over the entire length of the joining location and at the same time longitudinal edge. In particular a connection in sections, preferably, welding, is possible.

20 Fig. 5 shows a perspective view from a front into a multi-layer pipe **5** according to the present invention during the inventive manufacturing process, namely in the process step where the thus formed multi-layer material is shaped into pipe **5** by means of the bending roller (not shown here) with a constant friction-tight connection being created between the material layers **1, 2** as a result of the pressure of the rollers from the top
25 and from the bottom, and during shaping, the portions **1c** against **2a**, as well as **1d** against **2b** of the material layers, which can still shift freely against each other, shifting freely to each other in accordance with the shaping progress due to the different bend radii of internal pipe **1** and external pipe **2**. The first connection **3a, 3b** between the two material layers **1, 2** was made here already in two points **3a, 3b** which are located
30 alongside an (imaginary) line parallel to a longitudinal edge of the internal pipe **2**, which is forming - namely at the end points there. But in the area of this first connection **3a** and **3b** of the material layers **1, 2**, these, due to their connection **3a** and **3b** with each other, can now no longer shift against each other but remain immobilised or held in position against each other here.

Fig. 6 shows a perspective view from a front into a multi-layer pipe **5** according to the present invention during the inventive manufacturing process, namely in the process step where after a definite shaping progress at least one other connection - two other connections here - **6a** and **6b**, here formed as a continuous or partial weld seam, between the material layers **1**, **2** was created by connecting the material layer **1** positioned on top in at least one other position - in two other positions here - to each other. Subsequently the multi-layer pipe **5** can then be finish-shaped (not shown) by means of the bending roller and/or bending machine, with the material layers shifting no more against each other now during this finish-shaping due to the other connections **6a** and **6b**, so that as a result, the material layer **1**, **1c**, **1d** acting as an internal pipe is pressed non-positively into the material layer **2**, **2a**, **2b** acting as an external pipe.

Fig. 7 shows a perspective cross-section of a finished multi-layer pipe **5** according to the present invention with internal layer (also called internal pipe, internal pipeline, internal plate etc.) **1** and external layer (also called external pipe, external pipeline, base plate etc.) **2** with the multi-layer pipe **5** having been closed by means of welding **7** of the external pipe **2** alongside a pipe seam **8** and deposition welding **9** of the internal pipe **1**.

Fig. 8 shows a perspective cross-section of a multi-layer pipe according to Fig. 7 with internal layer **1** and external layer **2** in detailed view in the area of the two weld seams **7**, **9**.

Claims

1. A method for manufacture of a multi-layer pipe (5) by means of a bending roller, where

- individual material layers (1, 2) to be combined into the multi-layer pipe (5) are put onto each other,
- subsequently a first connection (3, 3a and 3b, 3a₁ and 3a₂, 3b₁ and 3b₂, 3n₁ and 3n₂) between the material layers (1, 2) is created by connecting them to each other,

characterised in that

- the thus formed multi-layer material is shaped into a pipe (5) by means of the bending roller with a constant friction-tight connection being created between the material layers (1, 2) as a result of the pressure of the rollers from the top and from the bottom, and during shaping, the portions (1c, 1d, 2a, 2b) of the material layers (1, 2), which can still shift freely against other, shifting freely to each other in accordance with the shaping progress due to the different bend radii of internal pipe (1) and external pipe (2)
- after a definite shaping progress at least one other connection (6a, 6b) is created between the material layers (1, 2) by connecting them to each other in at least one other position, and
- the multi-layer pipe (5) is then finish-shaped by means of the bending roller and/or bending machine, with the material layers (1, 2) shifting no more against each other now during this finish-shaping, so that as a result, the material layer (1) acting as an internal pipe is pressed non-positively into the material layer (2) acting as an external pipe.

2. A method for manufacture of a multi-layer pipe (5) by means of a bending roller according to claim 1, characterised in that the material layer (1) acting as an internal pipe constitutes a graduated circle in cross-section in the finished multi-layer pipe (5).

3. A method for manufacture of a multi-layer pipe (5) by means of a bending roller according to claim 2, characterised in that the material layer (1) acting as an internal pipe that constitutes a graduated circle in cross-section in the finished multi-layer pipe (5) forms a channel at the base of the multi-layer pipe.
- 5
4. A method for manufacture of a multi-layer pipe (5) by means of a bending roller according to claim 1, 2 or 3, characterised in that first connection between the material layers (1, 2) is created by connecting them to each other approximately alongside a longitudinal edge (4) or transverse edge (4a) of the material layer positioned above (1) or approximately alongside a line parallel to it.
- 10
5. A method for manufacture of a multi-layer pipe (5) by means of a bending roller according to any one of claims 1 - 4, characterised in that the at least one other connection (6a, 6b) between the material layers (1, 2) occurs after a definite shaping progress approximately alongside a second longitudinal edge (4) or transverse edge (4a) of the material layer above (1, 1a, 1b, 1n), or approximately alongside a line parallel to it.
- 15
6. A method for manufacture of a multi-layer pipe (5) by means of a bending roller according to any one of claims 1 - 5, characterised in that
- 20
- the first connection between the material layers (1, 2) is created by connecting them to each other alongside one of the longitudinal edges (4) or transverse edges (4a) of the material layer (1) above, and
 - the at least one other connection (6a, 6b) occurs between the material layers (1, 2) after a definite shaping progress alongside the second longitudinal edge or transverse edge of the material layer (1) above.
- 25
7. A method for manufacture of a multi-layer pipe (5) by means of a bending roller according to any one of claims 1 - 6, characterised in that the at least one other connection (6a, 6b) between the material layers (1, 2) is created after a shaping progress between 50 % and less than 100 %.
- 30

8. A method for manufacture of a double-layer pipe (5) as a multi-layer pipe with an external pipe (2) and an internal pipe (1) by means of a bending roller according to any one of claims 1 - 6, characterised in that the at least one other connection (6a, 6b) between the material layers (1, 2) is created after a shaping progress of approximately F_{for} (indicated in parts per cent) with F_{for} resulting as follows :

$$F_{for} = \left(1 - \frac{\frac{\sigma_l}{E} \cdot (DA - 2 \cdot SA - SI) \cdot \pi \cdot (Z_s + 1)}{(DA - SA) \cdot \pi - (DA - 2 \cdot SA - SI) \cdot \pi} \right) \cdot 100$$

- with DA being the external diameter of the external pipe in mm,
 SA being the wall thickness of the external pipe in mm,
 SI being the wall thickness of the internal pipe in mm,
 σ_l being the yield point of the internal pipe in N/mm²
 Z_s being the upsetting allowance indicated in parts per cent
 and
 E being the Young's modulus in N/mm².

9. A method for manufacture of a multi-layer pipe (5) by means of a bending roller according to any one of the preceding claims 1 - 8, characterised in that at least one of the material layers (1, 2) comprises more than one element (1a, 1b, 1n) positioned above.

10. A method for manufacture of a multi-layer pipe (5) by means of a bending roller according to claim 9, characterised in that the elements are placed with their longitudinal edge approximately parallel to the longitudinal edge of the material layer below, and the first connection (3) between the material layers (1, 2) is created by the elements (1a, 1b) after their positioning on top alongside their joining location, which at the same time constitutes each a longitudinal edge of the elements of the material layer (1a, 1b) on top, being connected with the material layer below.

11. A method for manufacture of a multi-layer pipe (5) by means of a bending roller according to any one of the preceding claims 1 - 10, characterised in that the

multi-layer pipe (5) is closed by means of welding (7) of the external pipe (2) alongside the pipe seam (8) and deposition welding (9) of the internal pipe (1).

- 5 12. A method for manufacture of a multi-layer pipe (5) by means of a bending roller according to any one of the preceding claims 1 - 11, characterised in that the material layers (1, 2) are connected at the pipe front (5).
- 10 13. A method for manufacture of a multi-layer pipe (5) by means of a bending roller according to any one of the preceding claims 1 - 12, characterised in that as a multi-layer pipe (5) a double-layer pipe is manufactured.
- 15 14. A method for manufacture of a multi-layer pipe (5) by means of a bending roller according to any one of the preceding claims 1 - 13, characterised in that plates are used as a material layer (1, 2) or elements (1a, 1b, 1n) of the material layer (1).
- 20 15. A method for manufacture of a multi-layer pipe (5) by means of a bending roller according to any one of the preceding claims 1 - 14, characterised in that at least one of the connections (3, 3a and 3b, 3a₁ and 3a₂, 3b₁ and 3b₂, 3n₁ and 3n₂, 6a, 6b) of the material layers (1, 2) is performed as a welding.