

Description

FIELD OF THE INVENTION

5 The present invention relates to an improved process for producing polytetramethylene ether glycol from tetrahydrofuran using a catalyst which is a fluorinated resin containing both sulfonic acid groups and carboxylic acid groups or a blend of fluorinated resin containing sulfonic acid groups and a fluorinated resin containing carboxylic acid groups. An important aspect of the present invention involves activating the sulfonic acid groups containing fluorinated resin prior to its use as catalyst. This activation involves a partial
 10 dehydration of the catalyst to contain from not more than 1,000 to 2,000 ppm (0.1 to 0.2 wt%) water. Further, the catalytic resin may be blended with one or more other resins to control its catalytic activity.

BACKGROUND OF THE INVENTION

15 Poly(tetramethylene ether) glycol (PTMEG) is a commodity in the chemical industry, widely used in the manufacture of block copolymers in combination with polyfunctional urethanes and polyesters such as polybutylene terephthalate. It is commonly prepared by reaction of tetrahydrofuran (THF) with a strong acid catalyst such as fluorosulfonic acid and then quenching and hydrolyzing the product with water.

While this process has proved to be quite satisfactory, it is not as efficient as desired because the acid
 20 catalyst cannot be recovered and reused again. Moreover, disposal of the spent acid is a problem because of its toxicity and corrosiveness.

U.S. Patent 4,120,903 describes the preparation of PTMEG by the polymerization of THF using, as catalysts, perfluorinated ion-exchange polymers with pendant sulfonic acid groups (PFIEP-SO₃H) which have a low enough solubility to allow easy separation from the product, thus permitting their reuse. A
 25 method for avoiding the disposal problem traditionally associated with the strong acid catalyst was therefore possible based on the reaction equations (1) through (4) of U.S. 4,120,903, Column 1, where P-SO₃H has the same meaning as PFIEP-SO₃H herein. The PFIEP-SO₃H catalyst is further described by F. J. WALLER and R. W. Van Scoyoc, CHEMTECH, July, 1987, pages 438-441.

There are two drawbacks to implementation of this technology, however, in that (1) the polymerization is
 30 sensitive to moisture necessitating that both the catalyst and the THF be specially dried before use and (2) the PTMEG made using this process had a number average molecular weight 10,000 or greater.

One approach to circumvent these drawbacks by Heinson et al using the PFIEP-SO₃H catalyst of U.S. 4,120,903 above is disclosed in U.S. 4,163,115. This patent discloses maintaining an anhydrous reaction environment by carrying out the polymerization of tetrahydrofuran in the presence of an acylium ion
 35 precursor, i.e. a carboxylic acid anhydride such as acetic anhydride and optionally the corresponding carboxylic acid. Esters of the PTMEG were formed with facile control of molecular weight in the desired commercial range or up to very high molecular weights. Recovery of the PTMEG, however, required saponification or methanolysis, and thereby diminishing the advantages of this process.

An insoluble catalyst, less sensitive to moisture in the polymerization system, and which could yield
 40 commercial grade PTMEG in the desired molecular weight ranges of 250 to 4,000 would have a distinct advantage.

The present invention is an improvement in the process for PTMEG manufacture within the commercially important molecular weight range of 250 to 4,000 in which THF containing the amount of water usually found in commercial polymerization-grade material, and an insoluble catalyst are brought together under
 45 conditions suitable for polymerization. After the desired polymerization has taken place, the catalyst may be separated from the bulk of the reaction mass for reuse and the PTMEG isolated by the usual methods. Part of the water introduced into the system either with the catalyst or the THF, acts as the chain terminator for the polymerization and, as such, is consumed. The catalyst of this invention is a blend of a perfluorinated ion exchange polymer containing pendant sulfonic acid groups (PFIEP-SO₃H) with a perfluorinated ion
 50 exchange polymer containing pendant carboxylic acid groups (PFIEP-CO₂H). The PFIEP-SO₃H/PFIEP-CO₂H may be used as is or it may be further blended with other, inert polymers before use. Ordinarily, these catalysts would not yield commercial grade PTMEG in the desired molecular weight range from 250 to 4,000 largely due to the poor access of the active sulfonic acid end groups to THF. The accessibility is considerably improved by swelling the catalyst in THF after activation by partial dehydration through (1)
 55 heating to 90°C or (2) by leaching the catalyst with dry THF or (3) drying the catalyst using a dehydrating agent like trimethyl orthoformate or (4) by distilling off the water contained in the catalyst or through any combination of the above methods.

SUMMARY OF THE INVENTION


The catalyst of this invention is a blend of perfluorinated ion exchange polymers containing pendant sulfonic acid groups (PFIEP-SO₃H) with a perfluorinated ion exchange polymer containing pendant carboxylic acid groups (PFIEP-CO₂H). Activating this catalyst is an extremely important step in preparing the desired low molecular weight PTMEG. The activity of the catalyst is improved sufficiently by partial dehydration by either (1) heating to 90°C for a period of time sufficient to reduce water content to a critical level, (2) leaching the catalyst with dry THF, or (3) drying the catalyst using a dehydrating agent, trimethyl orthoformate for example, or (4) by distilling off the water contained in the catalyst or through any combination of the above methods.

The polymerization process may be run either batchwise or continuously. Water input is monitored since it is a chain terminating agent and its levels affect the molecular weight of the product PTMEG. After the reaction mass is removed from the reactor, the unreacted THF and catalyst are removed by conventional means to yield the PTMEG product.

DETAILED DESCRIPTION OF THE INVENTION

The catalyst of this invention is a blend of PFIEP-SO₃H and PFIEP-CO₂H formed by blending a melt-fabricable first polymer having sulfonyl functional groups and a melt-fabricable second polymer having carboxylic functional groups, hydrolyzing the functional groups to ionizable functional groups, and finally, if base has been used for the hydrolysis, acidifying the ionizable functional groups to the corresponding sulfonic and carboxylic acid groups.

The melt-fabricable first polymer having sulfonyl functional groups is typically a polymer having a fluorinated hydrocarbon backbone chain to which are attached the functional groups or pendant side chains which in turn carry the functional groups. The pendant side chains can contain, for example,




groups, wherein R_f is F, Cl, or a C-1 to C-10 perfluoroalkyl radical and n is an integer from 1 to 5. Ordinarily, the functional group in the side chains of the polymer will be present in terminal




groups where R_f and n have the meanings defined above. Examples of fluorinated polymers of this kind are disclosed in U.S. Patents 3,282,875, 3,560,568, 3,718,627, 4,417,969 and 4,610,762.

The melt-fabricable second polymer having carboxylic functional groups is typically a polymer having a fluorinated hydrocarbon backbone chain to which are attached the functional groups or pendant side chains which carry the functional groups. The pendant side chains can contain, for example,



groups, wherein Z is F or CF₃, m is 1 to 12, and W is -COOR, -CF₂COOR or -CN, wherein R is lower alkyl. Ordinarily, the functional group in the side chains of the polymer will be present in terminal



groups. Examples of fluorinated polymers of this kind are disclosed in British Patent No. 1,145,445 and U.S. Patent 3,506,635.

The first and second polymers are then blended as described for example in U.S. Patent 4,176,217, Col. 7, lines 43-55 and Example 1. The resulting blend is then extruded into film or pellet form, hydrolyzed with base, and then acidified to give a blend of PFIEP-SO₃H and PFIEP-CO₂H. Techniques for hydrolyzing and subsequently acidifying the ionizable functional groups of these polymers are described in U.S. Patent 4,176,215, Col. 9 lines 25-45 and Example 1.

The catalysts of this invention can be used as is or blended with one or more inert polymers prepared from ethylenically unsaturated monomers. Examples of such monomers are ethylene, styrene, vinyl chloride, vinyl fluoride, vinylidene fluoride, chlorotrifluoroethylene, vinyl ethers, perfluoroalkyl vinyl ethers, tetrafluoroethylene, hexafluoropropylene, or combinations thereof. The solid blends of the polymers of this invention, containing preferably about 20 to 80% of the inert diluent polymer, can be prepared by techniques familiar in the art. Powders, granules or pellets of the individual polymers can first be mixed together. Such a mixture is then subjected to heat and pressure by various means, such as pressing, extruding in a screw extruder, or working on a roll mill or rubber mill. To insure formation of an intimate uniform blend, the steps can be repeated two or more times. For example, pressed films can be flaked or cut into small pieces and repressed into film. Extruded polymer can be chopped into pellets as it is extruded, and then re-extruded. Powders for blending can be made by grinding in a mill; cold grinding in a freezer mill is also a useful technique.

A suitable catalyst for use in this invention is a blend of 40-95% PFIEP-SO₃H and 60-5% PFIEP-CO₂H. The preferred catalyst is a blend of 70-95% PFIEP-SO₃H and 30-5% PFIEP-CO₂H. The PFIEP-CO₂H component can also be replaced with an inert filler like polytetrafluoroethylene, polychlorotrifluoroethylene or copolymers of either of these with hexafluoropropylene or a perfluoroalkyl vinyl ether wherein the alkyl groups contain from 1 to 6 carbon atoms, or any combination thereof.

Catalyst activation is an extremely important step in preparing the desired low molecular weight PTMEG. Unactivated catalyst, when used for polymerizing THF, usually results in production of PTMEG having molecular weight greater than 10,000. The catalyst can be activated by any one or a combination of the following methods:

(1) The catalyst is first dried in an oven at about ~100°C for about 8 hours under reduced pressure ranging between 0.1-100 mm mercury. The catalyst is then mixed with THF containing 50 to 300 ppm water and the slurry heated under nitrogen pressure at 85°C or higher for at least three hours. The preferred range of activation temperatures is 85-150°C and the hold-up time should be at least 3 hours. This type of activation is useful because THF does not polymerize under these conditions. It is thermodynamically impossible to polymerize THF at temperatures greater than 85°C. One plausible explanation for catalyst activation is the fact that the bulk of water present in the system is vaporized at these temperatures thereby dehydrating the catalyst. (2) The catalyst is leached with dry THF (water concentration <100 ppm) several times at temperatures ranging between 0 and 90°C. Each time the catalyst is leached with THF, the water concentration in the catalyst decreases. The most active catalyst is produced by leaching with THF until water concentration in THF is reduced to below 100 ppm. The estimated water concentration in the leached catalyst is about ~2000 ppm. (3) The catalyst is dried in an oven at 140-180°C in a vacuum oven maintained at 0.1-10 mm mercury in the presence of trimethyl orthoformate (TMOF). The ratio of trimethyl orthoformate to the catalyst ranges between 0.5-50 by weight. The trimethyl orthoformate reacts with water present in the catalyst to produce methyl formate and methanol both of which are highly volatile. The catalyst is treated in several stages with TMOF, (Total amount of TMOF used is 0.5-50 times the amount of catalyst). The catalyst is then dried under the same conditions as above in a vacuum oven for 8 hours to ensure the unreacted TMOF along with the volatile reaction product are removed. The water concentration in the dehydrated catalyst is about 1000-2000 ppm. The dehydrated catalyst is cooled and ready to use for polymerizing THF. (4) The catalyst is dried by distilling off the water in the presence of THF. The wet catalyst is mixed with THF and the THF/water mixture distilled off either by heating at the normal boiling point of the solution at atmospheric pressure or by vacuum distillation at lower temperatures ranging between 0°-60°C. The amount of THF distilled and used in this process ranges from 10 to 20 times the weight of the catalyst, depending on

initial moisture content of the catalyst. The catalyst contains from 1000 to 2000 ppm of residual water following this treatment and is active enough to be used as is without further activation.

The THF used for polymerization can be any of those commercially available for polymerization. Its water content usually varies between 10 and 1000 ppm. The peroxide content is normally less than 0.002% by weight. The THF may optionally contain an oxidation inhibitor such as butylated hydroxytoluene to prevent formation of undesirable color or excess peroxides. The type and concentration of the inhibitor have little or no effect on the polymerization.

The water contained in the system of this invention acts as the chain terminator for the polymerization and, as such, its concentration is important since it has an effect on the number-average molecular weight of the product PTMEG. The less water present the higher the average molecular weight. The more water present, the lower the molecular weight. If too much water is present the propagation rate is very slow. For these reasons, attention must be given to the water content of the system. Water enters the system either with the THF or the catalyst. As stated above, polymerization-grade THF usually contains about 0.001 to 0.1% water. The catalyst also contains water presumably as tightly held hydrates of the strongly acidic sulfonic acid groups. Even after the catalyst has been vacuum dried under stringent conditions, it is estimated that it still may contain up to about 0.2% water by weight. During reaction, water is removed from the system by being consumed as the chain terminator. Because of the above factors, it may be necessary, as processing proceeds and equilibrium conditions are approached, to adjust the water content of the THF being fed to the reactor system to maintain a relatively steady molecular weight in the desired range, from batch to batch.

The process of this invention can be run batchwise or continuously:

When run batchwise, a closed reaction vessel purged with a slow flow of dry nitrogen and fitted with an agitator is charged with THF and about 5 to 45%, preferably about 25 to 40%, by weight of the THF, of catalyst which has been activated by one or several combinations of the activation methods described above. The reaction mass is then held, with stirring or agitation, at a temperature ranging from ambient to the boiling point of THF, preferably at 0° to 65°C. If higher temperatures are desired, the reaction can be run under pressure. When the desired degree of polymerization has been reached, generally after 2 to 60 hours, the catalyst can be removed by filtration, centrifugation or decantation, and again dried, if necessary, before reuse.

The progress of the polymerization can be monitored by periodic sampling and analysis by, for example, gel permeation chromatography or by determination of the hydroxyl number.

When run continuously, the THF containing small amounts of chain-terminating water, and optionally the catalyst, also containing small amounts of water, are continuously fed into a reactor at rates which provide the requisite concentrations and suitable residence time, and product and excess reactants are continuously removed. Preferably, the catalyst is charged initially and is held in the reaction zone by suitable screens or filters, and can remain in continuous use. Reactor hold-up-times used in the continuous system range from 4 to 40 hours, operating at temperatures ranging from 5° to 70°C, using a feed rate to the reactor of 0.1 to 1.0 g THF per g of catalyst per hour.

After the reaction mass is withdrawn from the reactor, whether the reactor be batch or continuous, the unreacted THF and catalyst are recovered for recycle by conventional techniques to yield the PTMEG product.

If the catalyst loses its activity over a period of time it may be reactivated by one or several methods of activation outlined above.

Examples of batch and continuous polymerization experiments follow.

EXAMPLE 1

(a) A batch of pelletized (approximately 0.2 mm diameter x 0.5 mm long cylindrical) ion exchange resin blend designated NR-55 containing 78% PFIEP-SO₃H and 22% PFIEP-CO₂H by weight was activated by leaching with THF repeatedly until the water content of the THF was <80 mcg (micrograms water/mL THF). Leaching was carried out at 20°C and the activated catalyst was kept soaked in THF for 5 hours.

(b) A 45 g portion of the virgin catalyst as prepared in (a) above and 90.0 g THF were added to a glassware batch reactor, and heated to 85°C for 14 hours to initiate the polymerization. The reactor was then cooled to 2°C to allow propagation. After 1 hour at 2°C there was 7.0% conversion to PTMEG with a number average molecular weight (M_n) of 550. At the end of 2nd hour the conversion reached 8.2% at M_n 911. At the end of the 3rd hour conversion increased to 10.6% at M_n 933. After 4 hours and 14.05% conversion to M_n 940, the water concentration had increased to 99 mcg.

The catalyst was rinsed with dry THF, 0.15 g water was added to the reactor, and on the next day Recycle 1 of the same catalyst charge with 90 g new THF was started after heating to 85 °C for 4.5 hours to reinitiate the polymerization.

The above data are reported in the following TABLE 1 extended through four recycles of the same catalyst charge:

TABLE 1

PERFORMANCE OF RESIN CATALYST IN POLYMERIZATION OF THF TO PTMEG			
CATALYST	INITIATION °C/hrs.	PROPIGATION °C/End hr/Conv./M _n	WATER CONC. mcg, and TREATMENT AT END
Virgin	85/14.0	2/1st hr/ 7.0%/ 550 2nd hr/ 8.2%/ 911 3rd hr/10.6%/ 933 4th hr/14.0%/ 940	99 mcg Rinsed THF. Added 0.15g water.
Recycle 2	85/11.0	2/2nd hr/ 2.0%/250	571 mcg High H ₂ O/low Mn. Rinsed dry THF.
Recycle 3	85/18.0	2/1st hr/ 7.0%/866 2nd hr/13.32/864 3rd hr/16.9%/882 4th hr/23.3%/896 5th hr/27.0%/936 6th hr/30.0%/949 7th hr/ 2% /350	395 mcg Product lost after 6th hr. Rinsed dry THF.
Recycle 4	85/14.0	2/1st hr/ 7.5%/890 2nd hr/14.5%/905	Terminated

EXAMPLE 2

Another sample of 78% PFIEP-SO₃H, 22% PFIEP-CO₂H as used in EXAMPLE 1 (a) above was acid treated and repeatedly rinsed with THF until the water concentration was 92 mcg. This virgin catalyst (39 g) and 77.0 g of dry THF were charged to the batch reactor and heated to 85 °C for 20.0 hours to initiate the polymerization. Next, the reactor and its contents were cooled to 2 °C for the propagation step of the reaction. After the 1st hour, 2.0% conversion to PTMEG with M_n 2300 was found; after the 2nd hour, 7.9% conversion and M_n 2300 were measured; and after the 3rd hour, 6.0% conversion and M_n 2227.

EXAMPLE 3

A 31.0 g sample of 78% PFIEP-SO₃H, 22% PFIEP-CO₂H catalyst as used in EXAMPLES 1 (a) and 2 above was soaked in water, dried at 20 °C, and leached with dry THF. The virgin catalyst was added to 63.4 g THF, heated to 85 °C for 19.5 hours to initiate the polymerization, and cooled to 7 °C for propagation.

After 1 hour, 10.0% conversion to PTMEG of 1400 M_n resulted.

EXAMPLE 4

- 5 2.0 g portion of 78% PFIEP-SO₃H, 22% PFIEP-CO₂H catalyst as used in the above EXAMPLES was leached with dry THF until its water content was 111 mcg. The virgin catalyst and 64.0 g of THF were heated to 86 °C for 12.0 hours to initiate the polymerization and cooled to 54 °C for propagation. Results are reported in the following TABLE 2:

10 **TABLE 2**
PERFORMANCE OF RESIN CATALYSTS IN
POLYMERIZATION OF THF TO PTMEG

CATALYST	INITIATION °C/hrs.	PROPAGATION °C/End hr/Conv./ M_n	WATER CONC. mcg, AND TREATMENT AT END

Virgin	86/12.0	54/1st hr/ 2.3%/2800 2nd hr/ 5.1%/2800 3rd hr/ 4.0%/2800	Catalyst rinsed THF
Recycle 1	85/12.0	53/1st hr/ 7.8%/2800 2nd hr/10.7%/2800	Catalyst rinsed THF
Recycle 2	85/ 3.5	54/1st hr/ 2.6%/2800 2nd hr/ 5.0%/2800	Catalyst rinsed THF
Recycle 3	85/12.0	54/1st hr/ 8.7%/2800 2nd hr/ 7.7%/2800	204 mcg Catalyst rinsed THF
Recycle 4	85/ 4.5	54/1st hr/ 4.0%/2300	Catalyst rinsed THF
Recycle 5	85/12.0	54/1st hr/ 6.0%/2500	120 mcg Catalyst rinsed THF
Recycle 6	85/12.0	55/No data collected	Catalyst rinsed THF
Recycle 7	85/12.0	55/No data collected	Catalyst rinsed THF
Recycle 8	85/12.0	55/1st hr/4.6%/2500	245 mcg Catalyst rinsed THF

5	Recycle 9	85/12.0	60/added 0.5 g 1,4- butane diol 1st hr/ 3.4%/2000 4th hr/10.8%/1400	Catalyst rinsed THF
10	Recycle 10	85/12.0	60/1.5 hr/9.8%/1400 8th hr/9.8%/1400	Catalyst rinsed THF
15	Recycle 11	85/12.0	56/1st hr/12.3%/2300 7th hr/13.3%/2300	Catalyst rinsed THF
20	Recycle 12	85/12.0	55/1st hr/11.5%/2500	115 mcg Catalyst rinsed THF
25	Recycle 13	85/12.0	55/0.5th hr/14.5%/2800 1st hr/18.2%/ 2800	Added 0.5g 1,4-butane diol. Catalyst rinsed THF
30	Recycle 14	85/18.0	65/1st hr/6.0%/2050 3rd hr/6.0%/2050	119 mcg Catalyst rinsed THF
35	Recycle 15	85/ 4.0	65/0.5th hr/5.3%/2000 1st hr/6.6%/2000	NO THF CATALYST RINSE
40	Recycle 16	85/12.0	65/1st hr/5.8%/2050 50/2nd hr/4.9%/2000	128 mcg Catalyst rinsed THF
45	Recycle 17	85/15.0	55/1st hr/4.8%/2500 2nd hr/3.9%/2500	Catalyst rinsed THF
50	Recycle 18	90/12.0	60/0.5th hr/10.62%/2500 1st hr/16.8%/2500 2nd hr/18.0%/2500	113 mcg Catalyst rinsed THF
	Recycle 19	120/12.0	60/ Catalyst charred by lack of agitation at 120°C for 12hrs. Reaction terminated.	

EXAMPLES 5 through 8 used a catalyst made from a blend of 80% by weight PFIEP-SO₃H and 20% PFIEP-CO₂H. The PFIEP-SO₃H precursor resin used had a melt index of 11. EXAMPLES 5 through 7 were normal particle size: 0.1 diameter x 0.5 mm long cylindrical pellets. The particle size of the catalyst used in EXAMPLE 8 was reduced by approximately one-half. The catalyst of EXAMPLE 9 was made from a blend of 80% by weight PFIEP-SO₃H and 20% fluorinated ethylene propylene polymer (FEP) of the normal

particle size, and dried by extraction with THF in the usual manner.

The catalyst for EXAMPLES 5 and 6 started with 70.0 g of resin leached with dry THF at 45° to 50°C several times until the water concentration in the THF was 166 mcg. The catalyst slurry was divided into approximately equal portions containing 35 g of catalyst and 70 g of THF. The same 35:70 weight ratio of Catalyst to THF was also maintained in EXAMPLE 7. The ratio varied from 35:100 to 35:72-76 for EXAMPLE 8, and was 32:65 in EXAMPLE 9.

In EXAMPLE 5 the catalyst slurry was charged to a glass reactor; in EXAMPLE 6 the reactor was made of steel.

In EXAMPLES 7 and 8 the catalyst was prepared by acid exchange followed by rinsing with dry THF at 21°C until water in the THF was 74 mcg.

15

20

25

30

35

40

45

50

55

Performance of these catalysts in polymerization of THF to PTMEG is reported in TABLE 3 below.

TABLE 3
RESIN CATALYST PERFORMANCE IN
POLYMERIZATION OF THF TO PTMEG

<u>CATALYST</u>	<u>INITIATION</u> <u>°C/hrs.</u>	<u>PROPAGATION</u> <u>°C/End</u> <u>hr/CONV/M_n</u>	<u>WATER CONC.</u> <u>AT END, mcg</u>
EXAMPLE 5 (Glass Reactor)			
Virgin	90/12.0	Heater to constant temperature bath failed; incomplete initiation.	
Recycle 1	90/ 2.0	63/ 1st hr/1.8%/2200 2nd hr/2.2%/2200	164 mcg
EXAMPLE 6 (Steel Reactor)			
Virgin	90/12.0	Heater to constant temperature bath failed; incomplete initiation.	
Recycle 1	90/ 2.0	63/ 1st hr/ 7.5%/2450 1.5th hr/10.5%/2500 2.3rd hr/11.0%/2500 19th hr/10.5%/2780	153 mcg Catalyst rinsed THF
Recycle 2	90/ 4.5	65/ 1st hr/4.4%/3040 1.5th hr/ 5.0%/2891 20th hr/15% /2882	Catalyst rinsed THF
Recycle 3	90/36.0	60/ 2nd hr/ 5% /2891 3rd hr/ 4% /2852	122 mcg Catalyst rinsed THF
Recycle 4	90/14.0	60/ 1st hr/11% /2800 2nd hr/22% /2852	119 mcg Catalyst rinsed THF Added 2 g CF ₃ CO ₂ H.
Recycle 5	90/ 4.0	62/ 1st hr/ 2%/1300	175 mcg Catalyst rinsed THF
Recycle 6	90/12.0	67/1st hr/ 5%/1300 2nd hr/13.6%/1300 3rd hr/13.5%/1300	See foot-note (1). Catalyst rinsed THF

Recycle 7 90/12.0 60/1st hr/ 5% /1300 See foot-
2nd hr/11% /1300 note (2).
Catalyst
rinsed THF

Recycle 8 90/12.0 60/1st hr/4.5%/1300 See foot-
2nd hr/ 6.9%/1384 note (3).
3rd hr/ 7.0%/1300
5th hr/ 4.5%/1300 Reaction
stopped.

Footnotes: (1) Agitation lost during INITIATION.
(2) No agitation during INITIATION or
PROPAGATION.
(3) No agitation during INITIATION.

EXAMPLE 7

Virgin 85/3.0 8/1st hr/ 2.0%/3000 Catalyst
rinsed THF

Recycle 1 85/16.0 7/1st hr/ 1.5%/low M_n
2nd hr/ 6.5%/ " "
4.5th hr/ 2.0%/ " " Catalysts
rinsed THF

Recycle 2 85/16.0 7-23/2nd hr/2.5%/3000 Catalyst
7th hr/4.0%/3000 rinsed THF

Recycle 3 85/16 7-9/1st hr/6.0%/3000 Reaction
stopped

EXAMPLE 8

Virgin 86/16.0 6/1st hr/ 1.%/low M_n 200 mcg
30/5th hr/ 2.5%/ " " Catalyst
rinsed THF

Recycle 1 86/19.0 6/1st hr/ 7%/3200 114 mcg
2.5 hr/10%/3200
3.5 hr/ 8%/3200 Catalyst
rinsed THF

Recycle 2 86/ 4.0 8/ 1st hr/ 7%/3200 121 mcg
Catalyst
rinsed THF
Added
0.01g
water.

Recycle 3 86/13.0 6/0.5 hr/3.0%/3000 143 mcg
1.0 hr/4.6%/3000 Catalyst
rinsed THF

Recycle 4 86/17.0 6/0.5hr/16.0%/3200 114 mcg
1.2 hr/14.0%/3200 Reaction
stopped.

EXAMPLE 9

Virgin 85/16.0 51/0.5 hr/4.8%/low M_n 231 mcg
1.5 hr/6.5%/ " " Catalyst
4.0 hr /7.3%/ " " rinsed THF

Recycle 1 86/18.0 56/0.5th hr/7.2%/2350 81 mcg
1st hr/ 7.8%/ 2350 Catalyst
3rd hr/ 7.2%/ 2350 rinsed THF
5th hr/ 9.7%/ 2350

Recycle 2 86/17.0 54/0.5 hr/26%/3200 131 mcg
Catalyst
rinsed THF
Added
0.025
g water.

Recycle 3 86/4.0 56/0.5 hr/17%/3200 Catalyst
rinsed THF
Added
0.049
g water.

Recycle 4 86/2.5 59/0.5 hr/6.5%/3000 149 mcg
Reaction
Terminated

EXAMPLE 10

Continuous Operation: Feed Rate of
 THF = 0.9 mL/Minute
 Catalyst: 120.13 g of 70% PFIEP-SO₃H/30% PFIEP-CO₂H

Elapsed Cumulative Time, Hours	Water Content of THF, mcg	Conversion To PTMEG, % by Weight	Number Average Molecular Weight, M _n	moles of PTMEG
---	------------------------------------	---	--	-------------------

Reactor Temperature = 65°C

0	530	0	0	0
24	580	1.60	800	0.0104
41	630	1.50	717	0.0181
47	630	1.13	749	0.0201
65	491	2.70	792	0.0334
72	500	2.20	815	0.0375
88	606	3.20	880	0.0501
96	935	3.20	904	0.0562
117	---	4.00	940	0.0755
144	658	4.00	1088	0.0969
162	539	4.00	1004	0.1124
167	539	5.15	1028	0.1178
187	409	8.90	1200	0.1498
191	409	7.40	1112	0.1555
210	409	11.90	1080	0.2007
214	409	15.10	1587	0.2089
234	376	13.90	1572	0.2471
238	604	8.00	1575	0.2515
239	604	7.00	2124	0.2522
257	657	9.80	1956	0.2717

Reactor temperature was 68°C at 257 hours. Reactor temperature dropped to 61°C by 262 hours and maintained at that temperature until hour 689 at termination of run.


262	657	9.80	2058	0.2768
304	550	9.00	2948	0.3045
334	518	7.00	3203	0.3187
355	578	11.75	1931	0.3463
359	578	13.40	2003	0.3521
383	---	11.00	2641	0.3737
402	349	12.30	3561	0.3879
407	447	14.07	3819	0.3919
450	---	0.03	9918	0.3919
501	---	14.80	4636	0.4271
521	---	3.80	2786	0.4330
525	---	3.90	3113	0.4341
545	---	6.00	3500	0.4415
549	---	12.80	2760	0.4455
570	---	47.10	3416	0.5080
689	---	1.20	3480	0.5169




Claims

1. A polymeric acidic catalyst consisting of a blend of a perfluorinated ion exchange polymer having pendant sulfonic acid groups with a perfluorinated ion exchange polymer having pendant carboxylic acid groups, the catalyst being formed by hydrolyzing and then acidifying, if necessary,

a) melt-fabricable polymer having sulfonyl functional groups, typically a polymer having a fluorinated hydrocarbon backbone chain to which are attached the functional groups or pendant side chains which in turn carry the functional groups, the pendant side chains containing, for example,




groups, wherein R_f is F, Cl, or a C-1 to C-10 perfluoroalkyl radical, and n is an integer from 1 to 5 with the functional group in the side chains of the polymer present in terminal




groups, and

b) a melt-fabricable polymer having carboxylic functional groups, typically a polymer having a fluorinated hydrocarbon backbone chain to which are attached the functional groups or pendant side chains which carry the functional groups, the pendant side chains containing,



groups, wherein Z is F or CF_3 , m is 1 to 12, and W is $-\text{COOR}$, or $-\text{CF}_2\text{COOR}$, where R is lower alkyl with the functional groups in the side chains of the polymer present in terminal



groups; and

c) melt blending 40-95 percent of the melt-fabricable polymer from a) above with 80-5 percent of the melt-fabricatable polymer from b) above, and up to 80 percent of an inert filler selected from polytetrafluoroethylene, polychlorotrifluoroethylene or copolymers of tetrafluoroethylene or chlorotrifluoroethylene with one or more of hexafluoropropylene or a perfluoroalkyl vinyl ether wherein the alkyl group contains from 1 to 6 carbon atoms or any combination thereof; pelletizing the resulting polymer, and

d) converting the pelletized melt-fabricable polymer from c) by hydrolyzing and then acidifying, if necessary followed by reducing the water content of the polymer to 1,000 to 2,000 parts per million.

2. An polymeric acidic resin catalyst according to Claim 1 wherein the catalyst water content is reduced to from 1,000 to 2,000 ppm by oven drying the catalyst at about 90°C for about 8 hours under pressure between 0.1-100 mm Hg (absolute), followed by mixing the catalyst with tetrahydrofuran containing from 50 to 300 ppm water and heating under nitrogen at between 85° to 150°C for at least three hours under conditions that prevent polymerization of tetrahydrofuran.



3. A polymeric acid catalyst of Claim 1 wherein the catalyst water content is reduced to from 1,000 to 2,000 ppm by repeated leaching of the catalyst with dry tetrahydrofuran containing less than 100 ppm water at temperatures ranging from 0° to 90°C, until the water concentration in the leachant tetrahydrofuran is reduced to below 100 ppm and the residual water concentration in the leached catalyst is 1,000 to 2,000 ppm.
4. A polymeric acid resin catalyst of Claim 1 wherein the catalyst water content is reduced to 1,000 to 2,000 ppm by oven drying the catalyst at 140°-180°C under a pressure of 0.1-10 mm Hg (absolute) in the presence of 0.5 to 50 parts of trimethyl orthoformate per part of catalyst to convert water in the catalyst to methyl formate, followed by further heating the catalyst under vacuum in an oven for at least 8 hours to volatilise out the last traces of trimethyl orthoformate and methyl formate and the residual water concentration in the catalyst is 1,000 to 2,000 ppm.
5. A polymeric acid resin catalyst of Claim 1 wherein the catalyst water content is reduced to 1,000 to 2,000 ppm by extractive distillation of water from the catalyst in the presence of 10 to 20 parts tetrahydrofuran per part of catalyst by weight, whereby wet catalyst is mixed with tetrahydrofuran and the tetrahydrofuran/water mixture or azeotrope is distilled off to yield a catalyst with residual moisture remaining in the catalyst ranging from 1,000 to 2,000 ppm.
6. A batch process for the manufacture of poly(tetramethylene ether) glycols of number average molecular weight 250 to 4,000 by polymerization of tetrahydrofuran containing 10 to 300 ppm water in the presence of 5 to 45 percent, based on the weight of tetrahydrofuran, of pelleted perfluorinated ion exchange resin catalyst of Claim 1, said process being carried out with stirring or agitation at a temperature from 0° to 65°C for a period of time of 2 to 60 hours until the desired degree of polymerization has been reached, followed by removal of the product poly(tetramethylene ether) glycol from the catalyst and recovery of the catalyst.
7. The process of Claim 6 wherein the moisture content of the catalyst, prior to use, has been reduced to 1,000 to 2,000 ppm by oven drying the catalyst at about 90°C for about 8 hours under a pressure between 0.1-100 mm Hg (absolute) followed by mixing with tetrahydrofuran containing from 50 to 300 ppm water and heating under nitrogen at a pressure of from 0.1 to 10 mm Hg at between 85° to 150°C for at least 3 hours under conditions that prevent polymerization of tetrahydrofuran.
8. The process of Claim 6 wherein the moisture content of the catalyst, prior to use, has been reduced to from 1,000 to 2,000 ppm by repeated leaching of the catalyst with dry tetrahydrofuran containing less than 100 ppm water at temperatures ranging from 0° to 90°C until the water concentration in the leachant tetrahydrofuran is reduced to below 100 ppm and the residual water content in the leached catalyst is 1,000 to 2,000 ppm.
9. The process of Claim 6 wherein the moisture content of the catalyst, prior to use, has been reduced to from 1,000 to 2,000 ppm by oven drying the catalyst at 140° to 180°C under a pressure of 0.1 to 10 mm Hg (absolute) in the presence of 0.5 to 50 parts of trimethyl formate per part of catalyst to convert water in the catalyst to methyl formate, followed by further heating of the catalyst under vacuum in an oven for at least 8 hours to volatilize out the last traces of trimethyl orthoformate and methyl formate and the residual content of water in the catalyst is from 1,000 to 2,000 ppm.
10. The process of Claim 6 wherein the moisture of the catalyst, prior to use, has been reduced to 1,000 to 2,000 ppm by extractive distillation of water from the catalyst in the presence of 10 to 20 parts tetrahydrofuran per part of catalyst by weight, whereby wet catalyst is mixed with tetrahydrofuran and the tetrahydrofuran/water mixture or azeotrope is distilled off to yield a catalyst with residual moisture remaining in the catalyst ranging from 1,000 to 2,000 ppm.
11. A continuous process for the manufacture of poly(tetramethylene ether) glycols of number average molecular weight 250 to 4,000 by feeding 0.1 to 1.0 g per hour of tetrahydrofuran, per gram of the pelleted perfluorinated ion exchange resin of Claim 1 held in the reaction zone by suitable means, said tetrahydrofuran containing less than 1,000 ppm water for a hold-up time of from 4 to 40 hours, operating at temperatures ranging from 5° to 70°C, followed by recovery of the effluent and further processing under reduced pressure to remove excess tetrahydrofuran and traces of volatiles from the




product poly(tetramethylene ether) glycol.


12. The process of Claim 11 wherein the moisture content of the catalyst, prior to use, has been reduced to from 1,000 to 2,000 ppm by oven drying the catalyst at above 100°C for about 8 hours under a pressure between 0.1-100 mm Hg (absolute) followed by mixing with tetrahydrofuran containing from 50 to 300 ppm water and heating under nitrogen at a pressure from 0.1 to 10 mm Hg (absolute) for at least 3 hours under conditions that prevent polymerization of tetrahydrofuran.
13. The process of Claim 11 wherein the moisture content of the catalyst, prior to use, has been reduced from 1,000 to 2,000 ppm by repeated leaching of the catalyst with dry tetrahydrofuran containing less than 100 ppm water at temperatures ranging from 0° to 90°C until the water concentration in the leachant tetrahydrofuran is reduced to below 100 ppm and the residual water content in the catalyst is from 1,000 to 2,000 ppm.
14. The process of Claim 11 wherein the moisture content of the catalyst, prior to use, has been reduced to from 1,000 to 2,000 ppm by oven drying the catalyst at 140° to 180°C under a pressure of 0.1 to 10 mm Hg (absolute) in the presence of 0.5 to 50 parts of trimethyl formate per part of catalyst to convert water in the catalyst to methyl formate, followed by further heating of the catalyst under vacuum in an oven for at least 8 hours to volatilize out the last traces of trimethyl orthoformate and methyl formate and the residual water content in the catalyst is from 1,000 to 2,000 ppm.
15. The process of Claim 11 wherein the moisture content of the catalyst, prior to use, has been reduced to 1,000 to 2,000 ppm by extractive distillation of water from the catalyst in the presence of 10 to 20 parts of tetrahydrofuran per part of catalyst by weight, whereby wet catalyst is mixed with tetrahydrofuran and the azeotrope of the tetrahydrofuran/water mixture is distilled off to yield catalyst with residual moisture remaining in the catalyst ranging from 1,000 to 2,000 ppm.

Patentansprüche

1. Polymerer saurer Katalysator, bestehend aus einer Mischung eines perfluorierten Ionenaustauscher-Polymeren mit angehängten Sulfonsäuregruppen mit einem perfluorierten Ionenaustauscher-Polymer mit angehängten Carbonsäuregruppen, wobei der Katalysator gebildet wird durch Hydrolyse und anschließendes Ansäuern, sofern notwendig,
- a) eines schmelzverarbeitbaren Polymeren mit sulfonylfunktionellen Gruppen, typischerweise einem Polymer mit einer fluorierten Kohlenwasserstoff-Hauptkette, an die die funktionellen Gruppen oder die angehängten Seitenketten angeknüpft sind, die ihrerseits die funktionellen Gruppen tragen, wobei die angehängten Seitenketten beispielsweise folgende Gruppen enthalten




- worin R_f für F, Cl oder einen C-1- bis C-10-Perfluoralkylrest steht und n eine ganze Zahl von 1 bis 5 bedeutet, wobei die funktionellen Gruppen in den Seitenketten des Polymeren in den terminalen Gruppen




- vorhanden sind, und
- b) eines schmelzverarbeitbaren Polymeren mit carboxyfunktionellen Gruppen, typischerweise einem Polymer, das eine fluorierte Kohlenwasserstoff-Hauptkette aufweist, an die die funktionellen Gruppen oder die angehängten Seitenketten, die die funktionellen Gruppen tragen, angeknüpft sind; wobei die



angehängten Seitenketten die folgenden Gruppen enthalten,



worin Z für F oder CF_3 steht, m 1 bis 12 bedeutet, und W -COOR oder $-\text{CF}_2\text{COOR}$ bedeutet, worin R für Niedrigalkyl steht, wobei die funktionellen Gruppen in den Seitenketten des Polymeren in den endständigen Gruppen



vorhanden sind, und

c) Schmelzvermischen von 40 bis 95 % des schmelzverarbeitbaren Polymeren aus a), vorstehend, 60-5 % des schmelzverarbeitbaren Polymeren aus b), vorstehend, und bis zu 80 % eines inerten Füllstoffes, ausgewählt aus Polytetrafluorethylen, Polychlortrifluorethylen oder aus Copolymeren von Tetrafluorethylen oder Chlortrifluorethylen mit einem oder mehreren von Hexafluorpropylen oder einem Perfluoralkylvinylether, worin die Alkylgruppe 1 bis 6 Kohlenstoffatome enthält, oder von irgendeiner Kombination davon, Pelletisieren des resultierenden Polymeren, und

d) Umwandeln des pelletisierten schmelzverarbeitbaren Polymeren aus c) durch Hydrolyse und anschließendes Ansäuern, sofern notwendig, worauf die Verringerung des Wassergehaltes des Polymeren auf 1 000 bis 2 000 Teile pro Million erfolgt.

2. Saurer Harzkatalysator nach Anspruch 1, worin der Wassergehalt des Katalysators auf 1 000 bis 2 000 ppm verringert wird, indem der Katalysator in einem Ofen bei etwa 90 °C für etwa 8 Stunden unter einem Druck zwischen 0,1 bis 100 mmHg (absolut) getrocknet wird, worauf das Vermischen des Katalysators mit Tetrahydrofuran, das 50 bis 300 ppm Wasser enthält, und das Erhitzen unter Stickstoff zwischen 85 ° bis 150 °C für wenigstens 3 Stunden unter Bedingungen, die die Polymerisation von Tetrahydrofuran verhindern, erfolgen.

3. Polymerer saurer Katalysator nach Anspruch 1, bei dem der Wassergehalt des Katalysators auf 1 000 bis 2 000 ppm verringert wird, indem der Katalysator wiederholt mit trockenem Tetrahydrofuran, das weniger als 100 ppm Wasser enthält, bei Temperaturen im Bereich von 0 bis 90 °C ausgelaugt wird, bis sich die Wasserkonzentration in dem Auslauge-Tetrahydrofuran auf unter 100 ppm verringert und die Restwasserkonzentration in dem ausgelaugten Katalysator 1 000 bis 2 000 ppm beträgt.

4. Polymerer saurer Harzkatalysator nach Anspruch 1, bei dem der Katalysator-Wassergehalt auf 1 000 bis 2 000 ppm verringert wird, indem der Katalysator bei 140-180 °C unter einem Druck von 0,1-10 mmHg (absolut) in Gegenwart von 0,5 bis 50 Teilen Trimethylorthoformiat pro Teil Katalysator erhitzt wird, um das Wasser in dem Katalysator zu Methylformiat umzuwandeln, worauf noch das Erhitzen des Katalysators unter Vakuum in einem Ofen für wenigstens 8 Stunden erfolgt, um die letzten Spuren von Trimethylorthoformiat und Methylformiat zu verflüchtigen, so daß die Restwasserkonzentration in dem Katalysator 1 000 bis 2 000 beträgt.

5. Polymerer saurer Harzkatalysator nach Anspruch 1, bei dem der Katalysator-Wassergehalt auf 1 000 bis 2 000 ppm verringert wird, indem das Wasser extraktiv aus dem Katalysator in Gegenwart von 10 bis 20 Teilen Tetrahydrofuran pro Gewichtsteil Katalysator abdestilliert wird, wobei nasser Katalysator mit Tetrahydrofuran gemischt und das Gemisch aus Tetrahydrofuran/Wasser oder das Azeotrop abdestilliert wird, so daß sich ein Katalysator mit einer in dem Katalysator verbleibenden Restfeuchtigkeit im Bereich von 1 000 bis 2 000 ppm ergibt.

6. Batchverfahren zur Herstellung von Poly(tetramethylenether)-glycolen mit einem Zahlenmittelmolekulargewicht von 250 bis 4 000 durch Polymerisation von Tetrahydrofuran, das 10 bis 3 000 ppm Wasser



- enthält, in Gegenwart von 5 bis 45 %, bezogen auf das Gewicht von Tetrahydrofuran, von pelletisiertem perfluoriertem Ionenaustauscher-Harzkatalysator nach Anspruch 1, wobei das genannte Verfahren unter Schütteln oder Rühren bei einer Temperatur von 0 bis 65 °C für die Zeitdauer von 2 bis 60 Stunden durchgeführt wird, bis der gewünschte Polymerisationsgrad erreicht worden ist, worauf die Entfernung des Poly(tetramethylenether)-glycol-Produkts aus dem Katalysator und die Rückgewinnung des Katalysators erfolgen.
7. Verfahren nach Anspruch 6, bei dem der Feuchtigkeitsgehalt des Katalysators vor der Verwendung auf 1 000 bis 2 000 ppm verringert worden ist, indem der Katalysator bei etwa 90 °C für etwa 8 Stunden unter einem Druck zwischen 0,1-100 mmHg (absolut) in einem Ofen getrocknet und anschließend mit Tetrahydrofuran, das 50-300 ppm Wasser enthält, vermischt worden ist und unter Stickstoff bei einem Druck von 0,1 bis 10 mmHg zwischen 85 bis 150 °C für wenigstens 3 Stunden unter Bedingungen, die die Polymerisation von Tetrahydrofuran verhindern, erhitzt worden ist.
8. Verfahren nach Anspruch 6, bei dem der Feuchtigkeitsgehalt des Katalysators vor der Verwendung auf 1 000 bis 2 000 ppm verringert worden ist, indem der Katalysator wiederholt mit trockenem Tetrahydrofuran, das weniger als 100 ppm Wasser enthält, bei Temperaturen im Bereich von 0 ° bis 90 °C ausgelaugt worden ist, bis die Wasserkonzentration in dem Auslauge-Tetrahydrofuran unter 100 ppm verringert worden ist und der Restwassergehalt in dem ausgelaugten Katalysator 1 000 bis 2 000 ppm beträgt.
9. Verfahren nach Anspruch 6, bei dem der Feuchtigkeitsgehalt des Katalysators vor der Verwendung auf 1 000 bis 2 000 ppm verringert worden ist, indem der Katalysator in einem Ofen bei 140 ° bis 180 °C unter einem Druck von 0,1-10 mmHg (absolut) in Gegenwart von 0,5-50 Teilen Trimethylformiat auf ein Teil Katalysator getrocknet worden ist, um das Wasser in dem Katalysator zu Methylformiat umzuwandeln, gefolgt von weiterem Erhitzen des Katalysators unter Vakuum in einem Ofen für wenigstens 8 Stunden, um die letzten Spuren von Trimethylorthoformiat und Methylformiat zu verflüchtigen, so daß der Restwassergehalt in dem Katalysator 1 000 bis 2 000 ppm beträgt.
10. Verfahren nach Anspruch 6, bei dem die Feuchtigkeit des Katalysators vor der Verwendung auf 1 000 bis 2 000 ppm durch extraktive Destillation des Wassers aus dem Katalysator in Gegenwart von 10 bis 20 Teilen Tetrahydrofuran auf 1 Gewichtsteil Katalysator verringert worden ist, wobei der nasse Katalysator mit Tetrahydrofuran vermischt und das Tetrahydrofuran/Wassergemisch oder Azeotrop abdestilliert wird, so daß sich ein Katalysator mit einer in dem Katalysator verbleibenden Restfeuchtigkeit im Bereich von 1 000 bis 2 000 ppm ergibt.
11. Kontinuierliches Verfahren zur Herstellung von Poly(tetramethylether)-glycolen mit einem Zahlenmittelmolekulargewicht von 250 bis 4 000, indem pro Stunde 0,1 bis 1,0 g Tetrahydrofuran auf 1 g des pelletisierten perfluorierten Ionenaustauscherharzes nach Anspruch 1, das durch geeignete Mittel in der Reaktionszone gehalten wird, für eine Verweilzeit von 4 bis 40 Stunden eingeleitet wird, wobei das genannte Tetrahydrofuran weniger als 1 000 ppm Wasser enthält und wobei bei Temperaturen im Bereich von 5 ° bis 70 °C gearbeitet wird und anschließend der Überlauf gewonnen und unter reduziertem Druck weiterverarbeitet wird, um überschüssiges Tetrahydrofuran und Spuren von flüchtigen Bestandteilen aus dem Poly(tetramethylenether)-glycol-Produkt zu entfernen.
12. Verfahren nach Anspruch 11, bei dem der Feuchtigkeitsgehalt des Katalysators vor der Verwendung auf 1 000 bis 2 000 ppm verringert worden ist, indem der Katalysator im Ofen bei über 100 °C für etwa 8 Stunden unter einem Druck zwischen 0,1 bis 100 mmHg (absolut) getrocknet und anschließend mit Tetrahydrofuran, das 50 bis 300 ppm Wasser enthält, vermischt worden ist und indem unter Stickstoff bei einem Druck von 0,1 bis 10 mmHg (absolut) für wenigstens 3 Stunden unter Bedingungen erhitzt wurde, die die Polymerisation von Tetrahydrofuran verhindern.
13. Verfahren nach Anspruch 11, bei dem der Feuchtigkeitsgehalt des Katalysators vor der Verwendung auf 1 000 bis 2 000 ppm verringert worden ist, indem der Katalysator wiederholt mit trockenem Tetrahydrofuran, das weniger als 100 ppm Wasser enthält, bei Temperaturen im Bereich von 0 ° bis 90 °C ausgelaugt worden ist, bis sich die Wasserkonzentration in dem Auslauge-Tetrahydrofuran auf unter 100 ppm verringert hat und der Restwassergehalt in dem Katalysator 1 000 bis 2 000 ppm beträgt.




14. Verfahren nach Anspruch 11, bei dem der Feuchtigkeitsgehalt des Katalysators vor der Verwendung auf 1 000 bis 2 000 ppm verringert worden ist, indem der Katalysator bei 140-180 °C unter einem Druck von 0,1-10 mmHg (absolut) in Gegenwart von 0,5 bis 50 Teilen Trimethylorthoformiat pro Teil Katalysator in einem Ofen getrocknet worden ist, um das Wasser in dem Katalysator zu Methylformiat umzuwandeln, gefolgt von weiterem Erhitzen des Katalysators unter Vakuum in einem Ofen für wenigstens 8 Stunden, um die letzten Spuren von Trimethylorthoformiat und Methylformiat zu verflüchtigen, so daß der Restwassergehalt in dem Katalysator 1 000 bis 2 000 ppm beträgt.

15. Verfahren nach Anspruch 11, bei dem der Feuchtigkeitsgehalt des Katalysators vor der Verwendung auf 1 000 bis 2 000 ppm durch extraktive Destillation des Wassers aus dem Katalysator in Gegenwart von 10 bis 20 Teilen Tetrahydrofuran auf 1 Gewichtsteil Katalysator verringert worden ist, wobei der nasse Katalysator mit Tetrahydrofuran vermischt und das Azeotrop aus dem Tetrahydrofuran/Wassergemisch abdestilliert wird, so daß sich ein Katalysator mit einer in dem Katalysator verbleibenden Restfeuchtigkeit im Bereich von 1 000 bis 2 000 ppm ergibt.


Revendications

1. Un catalyseur acide polymère constitué d'un mélange d'un polymère d'échange d'ions perfluoré comportant des groupes acides sulfoniques pendants avec un polymère d'échange d'ions comportant des groupes acides carboxyliques pendants, le catalyseur étant formé en hydrolysant puis acidifiant, si nécessaire,


a) un polymère travaillable à l'état fondu comportant des groupes fonctionnels sulfonyles, typiquement constitué par un polymère ayant une chaîne squelettale hydrocarbonée fluorée à laquelle sont attachés les groupes fonctionnels ou des chaînes latérales pendantes qui portent elles-mêmes les groupes fonctionnels, les chaînes latérales pendantes contenant par exemple des groupes




où R_f est un atome de fluor ou de chlore ou un radical perfluoroalkyle en C₁ à C₁₀ et n un nombre entier de valeur 1 à 5, avec présence du groupe fonctionnel des chaînes latérales du polymère dans des groupes terminaux



b) un polymère travaillable à l'état fondu comportant des groupes fonctionnels carboxyliques, typiquement constitué par un polymère ayant une chaîne squelettale hydrocarbonée fluorée à laquelle sont attachés les groupes fonctionnels ou des chaînes latérales pendantes qui portent les groupes fonctionnels, les chaînes latérales pendantes contenant des groupes



dans lesquels Z est un atome de fluor ou un groupe CF₃, m vaut 1 à 12, et W est -COOR, ou -CF₂COOR, où R est un groupe alkyle inférieur avec présence des groupes fonctionnels des chaînes latérales du polymère dans des groupes terminaux





- 5 c) en mélangeant à l'état fondu 40 à 95 pour cent du polymère travaillable à l'état fondu de a) ci-dessus avec 60 à 5 pour cent du polymère travaillable à l'état fondu de b) ci-dessus, et jusqu'à 80 pour cent d'une charge inerte choisie parmi le polytétrafluoréthylène, le polychlorotrifluoréthylène ou des copolymères de tétrafluoréthylène et de chlorotrifluoréthylène avec un ou plusieurs représentants de l'ensemble formé par l'hexafluoropropylène et les éthers de perfluoroalkyle et de vinyle dans lesquels le groupe alkyle compte 1 à 6 atomes de carbone ou une combinaison quelconque de ceux ci ; en granulant le polymère résultant, et
- 10 d) en convertissant le polymère, granulé, travaillable à l'état fondu de c) par hydrolyse puis acidification, si nécessaire suivi d'une réduction de la teneur en eau de polymère à une valeur de 1000 à 2000 parties par million.
- 15 2. Un catalyseur résineux acide polymère selon la revendication 1 dans lequel la teneur en eau du catalyseur est réduite à une valeur de 1000 à 2000 parties par million par séchage du catalyseur en étuve à environ 90 °C pendant environ 8 heures sous une pression absolue de 0,1 à 100 mm de mercure, puis mélange du catalyseur avec du tétrahydrofurane renfermant 50 à 300 ppm d'eau et chauffage sous azote à une température comprise entre 85 et 150 °C pendant au moins 3 heures dans des conditions propres à éviter la polymérisation du tétrahydrofurane.
- 20 3. Un catalyseur acide polymère selon la revendication 1 dans lequel la teneur en eau du catalyseur est réduite à une valeur de 1000 à 2000 ppm par lessivage répété du catalyseur avec du tétrahydrofurane sec renfermant moins de 100 ppm d'eau à des températures de 0 à 90 °C jusqu'à ce que la concentration en eau du tétrahydrofurane de lessivage tombe au-dessous de 100 ppm et que la concentration en eau résiduelle du catalyseur lessivé soit de 1000 à 2000 ppm.
- 25 4. Un catalyseur résineux acide polymère de la revendication 1 dans lequel la teneur en eau du catalyseur est réduite à une valeur de 1000 à 2000 parties par million par séchage du catalyseur en étuve à 140-180 °C sous une pression absolue de 0,1 à 10 mm de mercure en présence de 0,5 à 50 parties d'orthoformiate de triméthyle par partie de catalyseur afin de convertir l'eau présente dans le catalyseur en formiate de méthyle, puis en chauffant de nouveau le catalyseur sous vide dans une
- 30 étuve pendant au moins 8 heures à l'effet de volatiliser les dernières traces d'orthoformiate de triméthyle et de formiate de méthyle et d'obtenir une concentration en eau résiduelle dans le catalyseur de 1000 à 2000 ppm.
- 35 5. Un catalyseur résineux acide polymère de la revendication 1 dans lequel la teneur en eau du catalyseur est réduite à une valeur de 1000 à 2000 ppm par distillation extractive de l'eau du catalyseur en présence de 10 à 20 parties en poids de tétrahydrofurane par partie en poids de catalyseur, de sorte que le catalyseur humide se trouve mélangé avec du tétrahydrofurane et que le mélange ou azéotrope tétrahydrofurane/eau se trouve chassé par distillation pour fournir un catalyseur dont la teneur en humidité résiduelle est de 1000 à 2000 ppm.
- 40 6. Un procédé discontinu pour la préparation de poly(tétraméthylène éther) glycols de poids moléculaire moyen en nombre de 250 à 4000 par polymérisation de tétrahydrofurane renfermant 10 à 300 ppm d'eau en présence de 5 à 45 pour cent, rapportés au poids de tétrahydrofurane, de catalyseur résineux échangeur d'ions perfluoré en granules de la revendication 1, ledit procédé étant mis en oeuvre avec
- 45 remuement ou agitation à une température de 0 à 65 °C pendant une durée de 2 à 60 heures jusqu'à ce que le degré désiré de polymérisation ait été atteint, puis élimination du produit poly(tétraméthylène éther) glycol du catalyseur et récupération du catalyseur.
- 50 7. Le procédé de la revendication 6 dans lequel la teneur en humidité du catalyseur, avant utilisation, a été réduite à une valeur de 1000 à 2000 ppm par séchage du catalyseur en étuve à environ 90 °C pendant environ 8 heures sous une pression absolue comprise entre 0,1 et 100 mm de mercure, puis mélange avec du tétrahydrofurane renfermant 50 à 300 ppm d'eau et chauffage sous azote sous une pression de 0,1 à 10 mm de mercure et à une température comprise entre 85 et 150 °C pendant au moins 3 heures dans des conditions propres à éviter la polymérisation du tétrahydrofurane.
- 55 8. Le procédé de la revendication 6 dans lequel la teneur en humidité du catalyseur, avant utilisation, a été réduite à une valeur de 1000 à 2000 ppm par lessivage répété du catalyseur avec du tétrahydrofurane sec renfermant moins de 100 ppm d'eau à des températures de 0 à 90 °C jusqu'à ce que la



concentration en eau du tétrahydrofurane de lessivage soit descendue au-dessous de 100 ppm et que la concentration en eau résiduelle du catalyseur lessivé soit de 1000 à 2000 ppm.

- 5 9. Le procédé de la revendication 6 dans lequel la teneur en humidité du catalyseur, avant utilisation, a été réduite à une valeur de 1000 à 2000 ppm par séchage du catalyseur en étuve à une température de 140 à 180 °C sous une pression absolue de 0,1 à 10 mm de mercure en présence de 0,5 à 50 parties de formiate de triméthyle par partie de catalyseur afin de convertir l'eau présente dans le catalyseur en formiate de méthyle, puis en poursuivant le chauffage du catalyseur sous vide dans une étuve pendant au moins 8 heures à l'effet de volatiliser les dernières traces d'orthoformiate de triméthyle et de formiate de méthyle, et d'obtenir une teneur en eau résiduelle du catalyseur de 1000 à 2000 ppm.
- 10 10. Le procédé de la revendication 6 dans lequel la teneur en humidité du catalyseur, avant utilisation, a été réduite à une valeur de 1000 à 2000 ppm par distillation extractive de l'eau du catalyseur en présence de 10 à 20 parties en poids de tétrahydrofurane par partie en poids de catalyseur, de sorte que le catalyseur humide se trouve mélangé avec du tétrahydrofurane et que le mélange ou azeotrope tétrahydrofurane/eau se trouve chassé par distillation pour fournir un catalyseur dont la teneur en humidité résiduelle est de 1000 à 2000 ppm.
- 20 11. Un procédé pour la préparation en continu de poly(tétraméthylène éther) glycols de poids moléculaire moyen en nombre de 250 à 4000 par envoi de 0,1 à 1,0 gramme par heure de tétrahydrofurane par gramme de la résine d'échange d'ions perfluorée en granules de la revendication 1 maintenue dans la zone de réaction par des moyens appropriés, ledit tétrahydrofurane renfermant moins de 1000 ppm d'eau pour un temps de séjour de 4 à 40 heures, travail à des températures de 5 à 70 °C, puis récupération de l'effluent et poursuite du traitement sous pression réduite à l'effet d'éliminer le tétrahydrofurane en excès et les traces de produits volatils du poly(tétraméthylène éther) glycol produit.
- 25 12. Le procédé de la revendication 11 dans lequel la teneur en humidité du catalyseur, avant utilisation, a été réduite à une valeur de 1000 à 2000 ppm par séchage du catalyseur en étuve au-dessus de 100 °C pendant environ 8 heures sous une pression absolue comprise entre 0,1 et 100 mm de mercure, puis mélange avec du tétrahydrofurane renfermant 50 à 300 ppm d'eau et chauffage sous azote sous une pression de 0,1 à 10 mm de mercure pendant au moins 3 heures dans des conditions propres à éviter la polymérisation du tétrahydrofurane.
- 30 13. Le procédé de la revendication 11 dans lequel la teneur en humidité du catalyseur, avant utilisation, a été réduite à une valeur de 1000 à 2000 ppm par lessivage répété du catalyseur avec du tétrahydrofurane sec renfermant moins de 100 ppm d'eau à des températures de 0 à 90 °C jusqu'à ce que la concentration en eau dans le tétrahydrofurane de lessivage soit descendue au-dessous de 100 ppm et que la concentration en eau résiduelle dans le catalyseur lessivé soit de 1000 à 2000 ppm.
- 40 14. Le procédé de la revendication 11 dans lequel la teneur en humidité du catalyseur, avant utilisation, a été réduite à une valeur de 1000 à 2000 ppm par séchage du catalyseur en étuve à une température de 140 à 180 °C sous une pression absolue de 0,1 à 10 mm de mercure en présence de 0,5 à 50 parties de formiate de triméthyle par partie de catalyseur afin de convertir l'eau présente dans le catalyseur en formiate de méthyle, puis en poursuivant le chauffage du catalyseur sous vide dans une étuve pendant au moins 8 heures à l'effet de volatiliser les dernières traces d'orthoformiate de triméthyle et de formiate de méthyle, et d'obtenir une teneur en eau résiduelle du catalyseur de 1000 à 2000 ppm.
- 45 15. Le procédé de la revendication 11 dans lequel la teneur en humidité du catalyseur, avant utilisation, a été réduite à une valeur de 1000 à 2000 ppm par distillation extractive de l'eau du catalyseur en présence de 10 à 20 parties en poids de tétrahydrofurane par partie en poids de catalyseur, de sorte que le catalyseur humide se trouve mélangé avec du tétrahydrofurane et que l'azeotrope tétrahydrofurane/eau se trouve chassé par distillation pour fournir un catalyseur dont la teneur en humidité résiduelle est de 1000 à 2000 ppm.
- 50 55