

Description

The present invention relates to voltage non-linear type resistors composed of zinc oxide as a main component.

It is widely known that resistors composed mainly of zinc oxide and containing small amounts of additives such as Bi_2O_3 , Sb_2O_3 , SiO_2 , Co_2O_3 , and MnO_2 exhibit excellent voltage-current non-linearity. Such resistors are used for lightning arrestors or the like. Reference is made in this respect to EP-A-24/150, which however does not discuss choice of specific phases of bismuth oxide.

In particular, when the resistor of the above type is used for a lightning arrestor and if excessive current is passed therethrough by lightning strike, current is earthed through the voltage non-linear resistor which ordinarily functions as an insulator and which acts as a conductor when a voltage greater than a rated voltage is applied thereto. As a result, accident due to the lightning strike can be prevented.

EP-A-115 149 describes control of the ratio of the β and γ phases of Bi_2O_3 , to improve life of the resistor.

As crystalline phases of the voltage non-linear resistors, bismuth phases of an α type, a β type, a γ type and a δ type as well as a pyrochlore phase exist as intergranular layers in addition to a crystalline phase of zinc oxide. However, depending upon their contents or ratios, a change rate of V_{ImA} after application of surge current increases or a change rate of a V-I characteristic increases with temperatures. In either case, the characteristic against repeated strike of lightning may be damaged. Further, when the V_{ImA} change rate is great, there is risk of thermal runaway in the case of a gapless type lightning arrestor, and follow current cannot be interrupted in the case of a gap type lightning arrestor. Further, recent investigations have revealed that depending upon the contents or the ratios of the bismuth phases of the α , β , γ , and δ phases or the pyrochlore which exist as the intergranular phase besides the crystalline phase of zinc oxide mentioned above, variations in characteristics such as a voltage non-linearity index or a leakage current ratio becomes greater, and that hygroscopicity of the resistor deteriorates.

It is an object of the present invention to overcome the above-mentioned problems, and to provide voltage non-linear resistors which exhibit good characteristic against repeated lightning strike.

It is another object of the present invention to overcome the above-mentioned problems, and to provide voltage non-linear resistors which have smaller variations and good hygroscopicity.

According to a first aspect of the present invention, a voltage non-linear resistor is provided as set out in claim 1.

According to a second aspect of the present invention, a voltage non-linear resistor is provided as set out in claim 2.

According to a third aspect of the present invention, a voltage non-linear resistor is provided as set out in claim 3.

The first aspect of the present invention has been accomplished based on the discovery that the voltage non-linear resistor of which the crystalline phase contains at least the β type crystalline phase and the δ type crystalline phase in the specified ratio range has a small change rate of V_{ImA} after application of surge and small change in the V-I characteristic with temperature, as is clear from experiments mentioned later. As a result, the voltage non-linear resistor having good surge-withstanding capability, good characteristic against repeated thunderbolt strike, and good use life with being free from thermal runaway can be obtained.

Turning now to effects obtained by each of the phases, the δ type crystalline phase mainly functions to decrease the V_{ImA} change rate after application of thunderbolt surges. It also functions to improve the surge-withstanding capability. The β type crystalline phase mainly functions to decrease the change ratio of the V-I characteristic with temperature, and its function is further improved under coexistence with the δ type crystalline phase. Only the β type crystalline phase unfavorably deteriorates the use life. Although a γ type crystalline phase improves use life, it adversely affects other characteristics than mentioned above. Thus, the γ type crystalline phase is preferably not more than 0.5 wt% at the maximum. It is preferable that no pyrochlore phase is contained.

In addition, 0.01 to 0.03 wt% of a glass frit is added in the production of the resistor. Further, it is preferable to add silicon oxide in the state of an amorphous phase, because an intergranular phase is stabilized therewith.

It is preferable that $70 \leq \beta/(\beta + \delta) \times 100 \leq 80$, because the effects attainable in the present invention becomes more conspicuous.

The second aspect of the present invention has been accomplished based on the discovery that the voltage non-linear resistor in which the crystalline phases of the bismuth oxide in the resistor include at least the α type crystalline phase, the β type crystalline phase, and the δ type crystalline phase has small

change rate of V_{ImA} after application of surge and small change rate of V-I characteristic with temperature, as is clear from experiments mentioned later. As a result, the voltage non-linear resistor which has good surge-withstanding capability, good resistance against repeated lightning strike and long use life while being free from thermal runaway can be obtained.

5 Turning now to effects of the phases, the δ phase mainly functions to decrease the V_{ImA} change rate, and also functions to improve the surge-withstanding capability. The α and β phases mainly have an effect to decrease the change rate of the V-I characteristic with temperatures. If the α phase or the β phase singly exists, the above effect is small, and the use life is shortened. If the α phase and the β phase fall outside the range in the present invention, the effect is small. Furthermore, although the γ phase prolongs the use
10 life, the phase adversely affects the other characteristics mentioned later. Thus, the γ phase is preferably not more than 0.5 wt% at the maximum. Further, it is preferable that no pyrochlore phase is contained.

In producing the resistor, 0.01 to 0.03 wt% of glass frit is preferably added. In addition, silicon oxide is preferably added in the state of an amorphous phase, because the intergranular phase is stabilized.

15 It is preferable that the contents of the α , β and δ crystalline phases satisfy the following inequalities, because the effects of the invention become more conspicuous.

$$25 \leq \frac{\alpha}{\alpha + \beta + \delta} \times 100 \leq 40,$$

20

$$40 \leq \frac{\beta}{\alpha + \beta + \delta} \times 100 \leq 50, \text{ and}$$

25

$$20 \leq \frac{\delta}{\alpha + \beta + \delta} \times 100 \leq 30,$$

30 The third aspect of the present invention has been accomplished based on the discovery that the voltage non-linear resistor in which the intergranular phase is partially made amorphous by the incorporation of bismuth into the sintered body and the content of bismuth in the amorphous phase and that in the δ - Bi_2O_3 phase are controlled to the respectively specified ranges has small variations in the characteristics such as voltage non-linearity index, the change rate of V_{ImA} after application of thunderbolt surge, limit
35 voltage ratio, and leakage current ratio as well as good hygroscopicity of the non-linear resistor, as mentioned later in Experiments.

As mentioned later, the voltage non-linear resistor can appropriately be obtained by selectively combining the kinds of and addition amounts of raw materials, final firing conditions, cooling rate and thermally treating conditions after the final firing.

40 Use of glass frit containing silver or boron in the raw material is preferable, because the frit improves the characteristics. Boron advances the diffusion of additive components, and promote the uniformization of the characteristics over the sintered body, and the glass frit stabilizes the intergranular phase. Silver suppresses movement of ions due to charging, and stabilize the intergranular phase. As an example, borosilicate bismuth glass containing silver is preferably added. It is preferable that the addition amount of
45 the glass frit is 0.01 to 0.3 wt%, the contents of Ag_2O and B_2O_3 in the glass frit being both 10 to 30 wt%. Further, it is preferable that pyrochlore which is conventionally confirmed in the intergranular phase is not contained.

For a better understanding of the invention, reference is made to the drawing, wherein:

Fig. 1 is a diagram showing a charging pattern with respect to the relationship between the leakage
50 current and time.

In order to obtain a voltage non-linear resistor composed mainly of zinc oxide, additives such as bismuth oxide, cobalt oxide, manganese oxide, antimony oxide, chromium oxide, preferably amorphous silicon oxide, nickel oxide, boron oxide, and silver oxide are mixed to a zinc oxide raw material in given mixing amounts. All of the additives and the raw material are adjusted to respectively given particle sizes. In
55 this case, silver nitrate and boric acid may be used instead of silver oxide and boron oxide, respectively. Preferably, bismuth borosilicate containing silver is used. In such a use, a given amount of an aqueous solution of polyvinyl alcohol is added to the powders of these materials. Preferably, a given amount of a solution of aluminum nitrate is added as a source of aluminum oxide. The mixing is effected by using an

emulsifying machine.

Next, a mixed slip is obtained by deairing in vacuum under a reduced pressure of preferably 200 mmHg or less. It is preferable that the content of water and the viscosity of the mixed slip are 30 to 35 wt% and 100 ± 50 cp, respectively. Then, the thus obtained mixed slip is fed to a spray drier to produce
 5 granulated powder having the average particle diameter of 50 to 150 μm , preferably 80 to 120 μm , and the water content of 0.5 to 2.0 wt%, preferably 0.9 to 1.5 wt%. Next, the granulated powder obtained is shaped in a desired shape under a shaping pressure of 800 to 1,000 kg/cm^2 in a shaping step. Thereafter, the shaped body is fired under conditions that heating and cooling are effected at a rate of 50 to 70 $^{\circ}\text{C/hr}$ (heating rate and cooling rate) in a temperature range from 800 to 1,000 $^{\circ}\text{C}$ and the shaped body is held at
 10 1,000 $^{\circ}\text{C}$ for 1 to 5 hours (a keeping time of 1 to 5 hours). It is preferable that a binder contained is removed off by heating and cooling the shaped body at a rate of 10 to 100 $^{\circ}\text{C}$ in a temperature range from 400 to 600 $^{\circ}\text{C}$ while holding it at 600 $^{\circ}\text{C}$ for a keeping time of 1 to 10 hours before calcination.

Next, an insulating covering layer is formed on a side surface of a calcined body. In the present invention, an oxide paste in which ethyl cellulose, butyl carbitol, or n-butyl acetate is added, as an organic
 15 binder, to given amounts of Bi_2O_3 , Sb_2O_3 , ZnO , and/or SiO_2 is coated onto the side surface of the calcined body in a coated thickness of 60 to 300 μm . Next, the coated body is fired under conditions that the coated body is final fired at the heating and cooling rate of 20 to 60 $^{\circ}\text{C/hr}$ in a temperature range from 1,000 to 1,300 $^{\circ}\text{C}$, preferably 1,100 to 1,250 $^{\circ}\text{C}$, while being kept at the maximum temperature for 3 to 7 hours. A
 20 glass paste in which ethyl cellulose, butyl carbitol or n-butyl acetate added, as an organic binder, to a glass powder is coated onto the insulating covering layer in a thickness of 100 to 300 μm , which is thermally treated at a heating and cooling rate of 50 to 200 $^{\circ}\text{C/hr}$ in a temperature range from 400 to 900 $^{\circ}\text{C}$ while being kept at 900 $^{\circ}\text{C}$ for a keeping time of 0.5 to 2 hours to form a glass layer.

Thereafter, opposite end faces of the thus obtained voltage non-linear resistor are polished with an abrasive #400 to 2000, such as SiC , Al_2O_3 or diamond powder by using water or oil as a polishing liquid.
 25 Next, after the polished surfaces are washed, a metalicon electrode is formed on each of the polished opposite surfaces with an aluminum metalicon, for instance, by metallizing, thereby obtaining a voltage non-linear resistor.

The crystalline phases of bismuth oxide have the following characteristics.

A great amount of the α phase is produced when the addition amount of amorphous SiO_2 is small and
 30 the cooling rate in the final firing is low. With respect to the β phase, a great amount of it is produced when the addition amount of amorphous SiO_2 is small and the cooling rate in the final firing is great. The γ phase is produced by thermal treatment after the final firing, and particularly the production thereof is conspicuous when the thermal treatment is effected at 600 to 800 $^{\circ}\text{C}$. With respect to the δ phase, a great amount of it is produced when the addition amount of amorphous SiO_2 is great and the cooling rate in the final firing is
 35 relatively small.

According to the present invention, the contents of the crystalline phases of bismuth oxides are controlled mainly based on the above criteria.

In the above-mentioned producing process, the voltage non-linear resistor according to the present invention, which include at least the β - Bi_2O_3 crystalline phase and the δ - Bi_2O_3 crystalline phase in the
 40 specified ratio range, or which includes the α - Bi_2O_3 crystalline phase, the β - Bi_2O_3 crystalline phase, and the δ - Bi_2O_3 crystalline phase in the specified ratio range in the sintered body, or which includes the δ - Bi_2O_3 crystalline phase and the amorphous phase containing bismuth in the intergranular layer of the sintered body in the specified ratio range, can be obtained by variously combining the kinds of the raw materials, the
 45 addition amounts, the final firing conditions, the cooling rate in the final firing, the thermal treatment conditions after the final firing, and the like. Thus, the voltage non-linear resistor having the good V_{IMA} change rate, the change rate of the V-I characteristic against temperatures, and/or the voltage non-linearity can be obtained.

In the following, with respect to voltage non-linear resistors falling inside or outside the scope of the present invention, various characteristics were actually measured, and results thereof will be explained.

50

(Examples)

Experiment 1

55 According to the above-mentioned method, sample Nos. 1-1 through 1-7 according to the present invention and Comparative sample Nos. 1-1 through 1-3 were prepared from a raw material consisting of 0.1 to 2.0 mol% of Bi_2O_3 , Co_3O_4 , MnO_2 , Sb_2O_3 , and Cr_2O_3 , 0.001 to 0.01 mol% of $\text{Al}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$, 0.01 to 0.3 wt% of a bismuth borosilicate glass containing silver, 0.5 to 3.0 mol% of amorphous SiO_2 , and the

balance being ZnO. Each of the samples had a diameter of 47 mm and a thickness of 22.5 mm, and a crystalline phase shown in Table 1.

With respect to the resistors thus prepared according to the invention samples and Comparative samples, temperature characteristic, V_{ImA} reduction rate, thunderbolt surge-withstanding capability, and on-off surge-withstanding capability were measured, and charge use life pattern was determined. Results are shown in Table 1. In this experiment, the temperature characteristic was determined as change rates of V_{ImA} and V_{40kA} at 150°C relative to those at 25°C, respectively. As compared with V_{ImA} and V_{40kA} at 25°C, the V_{ImA} lowers and the V_{40kA} increases at 150°C. The reduction rate of V_{ImA} was determined by values of V_{ImA} before and after applications of electric current of 30 kA in the form of 8/20 μ s electric current waves ten times. As to the thunderbolt-withstanding capability, those which were broken and not broken upon application of electric currents of 130 kA and 150 kA in the form of electric current waves of 4/10 μ s twice are shown by X and O, respectively. With respect to the on-off surge-withstanding capability, those which were broken and not broken upon applications of electric current of 800 A and 1,000 A in the form of electric current of 2 ms twenty times are shown by X and O, respectively. Further, the charge pattern was determined based on the relationship between the current and time in Fig. 1. In Fig. 1, A, B, C denote most excellent samples, good samples which were restored without being thermally runaway, and those which were thermally runaway, respectively. The amount of each of the crystalline phase was determined by an internal standard method in X-ray diffraction.

Table 1

Sample No.	Final firing rate (°C/hr)	Addition amount of amorphous SiO ₂	Thermally treating conditions		Ratio of crystalline phases (%)		Other crystalline phase	Temperature characteristic		V _{IMA} reduction rate (%)		Thunder-bolt surge-withstanding capability		Switching surge-withstanding capability		Life pattern on charging
			Temperature (°C)	Cooling rate (°C/hr)	β phase	δ phase		V _{IMA} change rate (%)	V _{40kA} change rate (%)	Average	σ_{n-1}	130 kA	150 kA	800 A	1000 A	
Example	1-1	0.5	-	-	60	40	α	4.8	3.3	5.5	1.0	○	○	○	○	B
	1-2	3.0	500	60	64	36	γ	4.2	3.2	4.6	0.8	○	○	○	×	B
	1-3	1.0	-	-	71	29		3.9	2.9	3.0	0.6	○	○	○	○	B
	1-4	0.5	-	-	76	24	α	4.0	3.1	3.1	0.7	○	○	○	○	B
	1-5	1.0	-	-	80	20		3.8	2.8	3.5	0.5	○	○	○	○	B
	1-6	3.0	500	60	86	14	γ	4.6	3.8	4.4	0.8	○	×	○	○	B
	1-7	1.0	-	-	90	10		5.5	3.7	5.7	0.9	○	×	○	○	B
Comparative Example	1-1	1.0	-	-	49	51		6.5	4.9	9.9	1.9	○	×	○	×	C
	1-2	1.0	-	-	100	0		6.5	4.2	13.2	2.7	×	-	×	-	C
	1-3	1.0	750	100	0	0	γ	22.0	6.0	15.3	2.8	×	-	×	-	A

Final firing was effected at 1,200°C for 5 hours for all the samples (heating rate: 40°C/hr)

It is clear from the results in Table 1 that the resistors containing at least the β phase and the δ phase at the specific ratio according to the present invention have better temperature characteristic and V_{IMA} reduction rate as compared with Comparative Examples in addition to the other characteristics.

Although the change life pattern is not of an A type (see Fig. 1) in the present invention, there is no fear of thermal runaway. In the case of the gap-provided type lightning arrestors, there is no problem even for a B type because the element is always charged.

As understood from the above explanation, since the voltage non-linear resistor according to the present invention contains at least the β phase and the δ phase at the specific ratio, the change rate of V_{ImA} due to application of thunderbolt surge is small and change in the voltage-current characteristic relative to the temperature change is small. Thus, good resistance against repeated thunderbolts as well as good surge-withstanding capability, use life, and other characteristics can be obtained.

Experiment 2

According to the above-mentioned method, sample Nos. 2-1 through 2-9 according to the present invention and Comparative sample Nos. 2-1 through 2-10 were prepared from a raw material consisting of 0.1 to 2.0 mol% of each of Bi_2O_3 , Co_3O_4 , MnO_2 , Sb_2O_3 , Cr_2O_3 and NiO , 0.001 to 0.01 mol% of $\text{Al}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$, 0.01 to 0.3 wt% of a bismuth borosilicate glass containing silver, 1.0 to 3.0 mol% of amorphous SiO_2 , and the balance being ZnO . Each of the samples had a diameter of 47 mm and a thickness of 22.5 mm, a crystalline phase shown in Table 2, and a varistor voltage (V_{ImA}) of 200 to 230 V/mm.

With respect to resistors thus prepared as the invention samples and Comparative samples, temperature characteristic, V_{ImA} reduction rate, thunderbolt surge-withstanding capability, and switching surge-withstanding capability were measured, and charge use life pattern was determined. Results are shown in Table 2. In this experiment, the temperature characteristic was determined as change rates of V_{ImA} and $V_{40\text{kA}}$ at 150°C relative to those at 25°C , respectively. As compared with V_{ImA} and $V_{40\text{kA}}$ at 25°C , V_{ImA} lowers and $V_{40\text{kA}}$ increases at 150°C . The reduction rate of V_{ImA} was determined by values of V_{ImA} before and after applications of electric current of 30 kA in the form of 8/20 μs electric current waves ten times. As to the thunderbolt-withstanding capability, those which were broken and not broken upon application of electric current of 130 kA and 150 kA in the form of electric current waves of 4/10 μs twice are shown by X and O, respectively. With respect to the switching surge-withstanding capability, those which were broken and not broken upon application of electric current of 800 A and 1,000 A in the form of electric current waves of 2 ms twenty times are shown by X and O, respectively. Further, the charge pattern was determined based on the relationship between the leakage current and time in Fig. 1. In Fig. 1, A, B, C denote most excellent samples, good samples which were restored without being thermally runaway, and those which were thermally runaway, respectively. The amount of each of the crystalline phases was determined by an internal standard method in X-ray diffraction.

Table 2(a)

Sample No.	Final firing	Addition of amorphous SiO ₂	Thermally treating conditions		Ratio of crystalline phases (%)			Other crystalline phase	Temperature characteristic		V _{1mA} reduction rate (%)		Thunderbolt surge-withstanding capability		Switching surge-withstanding capability		Life pattern on charging
	Cooling rate (°C/hr)		Temperature (°C)	Cooling rate (°C/hr)	α phase	β phase	δ phase		V _{1mA} change rate (%)	V _{40kA} change rate (%)	Average	σ_{R-1}	130 kA	150 kA	800 A	1000 A	
2-1	50	3.0	-	-	17	48	35	-	5.2	3.2	3.2	1.0	○	○	○	×	B
2-2	20	3.0	500	60	43	27	30	Y0.5	5.9	2.1	3.2	0.9	○	×	○	×	B
2-3	60	1.0	-	-	34	55	11	-	5.1	2.0	4.1	0.6	○	○	○	×	B
2-4	30	1.0	-	-	48	33	19	-	4.9	3.1	4.9	0.7	○	×	○	○	B
2-5	60	1.5	500	60	25	60	15	Y0.5	6.2	2.5	4.8	1.0	○	×	○	×	B
2-6	60	3.0	-	-	19	42	39	-	5.5	2.4	4.4	0.8	○	○	○	×	B
2-7	50	2.0	-	-	28	49	23	-	4.0	2.9	3.9	0.5	○	○	○	○	B
2-8	40	1.5	-	-	39	40	21	-	4.5	2.1	3.7	0.6	○	○	○	○	B
2-9	40	2.0	-	-	31	39	30	-	3.9	3.5	3.5	0.5	○	○	○	○	B

Example

Table 2(b)

Sample No.	Final firing Cooling rate (°C/hr)	Addition of amorphous SiO ₂	Thermally treating conditions		Ratio of crystalline phases (%)			Other crystalline phase	Temperature characteristic		V _{1mA} reduction rate (%)		Thunderbolt surge-withstanding capability		Switching surge-withstanding capability		Life pattern on charging
			Temperature (°C)	Cooling rate (°C/hr)	α phase	β phase	δ phase		V _{1mA} change rate (%)	V _{40kA} change rate (%)	Average	σ_{n-1}	130 kA	150 kA	800 A	1000 A	
Comparative Example	2-1	80	-	-	11	59	30	-	8.3	4.3	6.2	2.0	○	×	×	-	B
	2-2	20	-	-	48	20	32	-	8.1	3.9	6.7	2.2	○	×	×	-	B
	2-3	60	-	-	41	53	6	-	7.3	4.2	7.8	2.4	×	-	×	-	C
	2-4	20	-	-	58	25	17	-	7.7	4.7	6.5	2.3	×	-	○	×	B
	2-5	100	-	-	20	68	12	-	7.6	3.3	7.1	2.0	×	-	×	-	B
	2-6	20	-	-	21	31	48	-	8.8	5.1	6.4	1.9	○	×	×	-	C
	2-7	70	-	-	43	57	-	-	10.1	4.2	8.0	2.4	×	-	×	-	C
	2-8	60	-	-	-	60	40	-	11.3	5.9	7.5	2.5	×	-	○	×	C
	2-9	15	550	60	35	-	65	Y ₆₈	16.8	5.8	8.9	2.5	○	×	×	-	B
	2-10	40	750	100	-	-	-	Y ₁₀₀	21.0	6.1	9.2	2.9	×	-	×	-	A

Final firing was effected at 1,200°C for 5 hours for all the samples (heating rate: 40°C/hr)

From the results in Table 2, it is seen that the resistors according to the present invention containing at least the α phase, the β phase and the δ phase have better temperature characteristic, V_{1mA} reduction rate, and other characteristics as compared with Comparative Examples.

Although the life pattern on charging of the resistors according to the present invention are not of the A type (best), there is no fear of thermal runaway. Since a gap-provided type lightning arrester is always

charged, no problem occurs even when it is of the B type.

As understood from the above explanation, since the voltage non-linear resistor according to the second aspect of the present invention contains at least the α phase, the β phase and the δ phase at the specific ratios, small change rate of V_{ImA} due to application of thunderbolt surge, small voltage-current characteristic relative to the temperature change, and good resistance against repeated application of surges can be obtained. Thus, good resistance against repeated thunderbolt as well as good surge-withstanding capability, use life, and other characteristics can be obtained.

Experiment 3

According to the above-mentioned method, sample Nos. 3-1 through 3-8 according to the present invention and Comparative sample Nos. 3-1 through 3-8 were prepared from a raw material consisting of 0.1 to 2.0 mol% of each of Bi_2O_3 , Co_3O_4 , MnO_2 , Sb_2O_3 , Cr_2O_3 and NiO , 0.001 to 0.01 mol% of $\text{Al}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$, 0.01 to 0.3 wt% of bismuth borosilicate glass containing silver, 1.0 to 3.0 mol% of amorphous SiO_2 , and the balance being ZnO . Each of the samples had a diameter of 47 mm and a thickness of 20 mm, and a varistor voltage (V_{ImA}) of 200 to 230 V/mm.

With respect to resistors thus prepared as the invention samples and Comparative samples, voltage non-linear index, V_{ImA} reduction rate due to application of thunderbolt surge, limit voltage ratio, and leakage current ratio were measured, and hygroscopicity of elements was examined. Results are shown in Table 3. In this experiment, the voltage non-linearity index α was determined from the ratio between V_{ImA} and $V_{100\mu\text{A}}$ according to $I = KV^\alpha$ in which I, V, and K are current, voltage, and a proportional constant, respectively. The reduction rate of V_{ImA} due to application of thunderbolt surge was determined by values of V_{ImA} before and after applications of electric current of 40 kA in the form of 4/10 μs electric current waves ten times. The limit voltage ratio was determined from the ratio between applied voltage and the varistor voltage necessary for flowing current of 10 kA in the form of 8/20 ms current waveform. The rate of the leakage current was determined from the current ratio of I_{100} hour/ I_0 hour with lapse of 100 hour charging immediately after the charging when the element was charged at the charging rate of 95% at a surrounding temperature of 130 °C. Further, the amounts of the crystalline phases and the ratios thereof were determined based on the internal standard method in the X-ray diffraction. Furthermore, hygroscopicity was determined by a 24 hour immersing process in a fluorescent beam scratch-detecting liquid under application of 200 kg/cm². In Table 3, samples which underwent impregnation and those which did not undergo impregnation are shown by X and O, respectively.

Table 3(a)

Sample No.	Final firing rate (°C/hr)	Addition of amorphous SiO ₂	Thermally treating conditions		B/A	C/A	Other crystal-line phase	Voltage non-linearity index		V _{1mA} reduction rate (%)		Limit voltage ratio V _{10kA} /V _{1mA}	Rate of leakage current		Hygroscopicity
			Temperature (°C)	Cooling rate (°C/hr)				Average	σ_{h-1}	Average	σ_{h-1}		Average	σ_{h-1}	
Example	3-1 60	1.0	900	200	0.13	0.28	α, β	45	3.3	5.5	1.0	1.7	0.68	0.11	○
	3-2 20	3.0	800	100	0.40	0.07	α	51	3.8	5.6	0.9	1.6	0.69	0.10	○
	3-3 40	2.0	850	180	0.22	0.19	γ	31	2.4	3.8	0.4	1.6	0.29	0.05	○
	3-4 50	2.0	800	150	0.29	0.10	α	39	2.2	4.2	0.5	1.6	0.61	0.09	○
	3-5 30	1.5	800	180	0.27	0.14	α, β	48	2.1	4.3	0.5	1.6	0.60	0.08	○
	3-6 50	1.0	800	200	0.25	0.18	α, β, γ	40	2.0	4.0	0.6	1.6	0.31	0.10	○
	3-7 30	3.0	850	200	0.38	0.24	α, γ	39	3.5	5.8	0.9	1.7	0.35	0.08	○
	3-8 60	2.0	900	200	0.22	0.30	β	70	3.2	5.2	1.2	1.6	0.59	0.10	○

Table 3(b)

Sample No.	Final firing Cooling rate (°C/hr)	Addition amount of amor- phous SiO ₂	Thermally treating conditions		B/A	C/A	Other crystal- line phase	Voltage non- linearity index		V _{1mA} reduction rate (%)		Limit voltage ratio V _{10kA} /V _{1mA}	Rate of leakage current		Hygro- scopicity
			Temper- ature (°C)	Cooling rate (°C/hr)				Average	σ_{n-1}	Average	σ_{n-1}		Average	σ_{n-1}	
Compar- ative Example	3-1	40	0.5	-	-	0.23	0	62	4.5	8.8	2.9	1.9	1.02	0.40	X
	3-2	60	1.0	1000	250	0.20	0.41	33	4.2	9.9	3.1	2.0	0.49	0.39	X
	3-3	20	0.5	800	100	0	0.09	55	3.9	7.7	2.8	1.9	0.78	0.38	O
	3-4	60	0.5	800	150	0	0.11	39	4.1	8.1	2.5	1.8	0.35	0.22	X
	3-5	40	1.0	800	200	0	0.13	25	4.9	7.4	2.3	1.9	0.35	0.18	O
	3-6	40	5.0	850	200	0.49	0.20	41	4.5	7.3	2.9	1.8	0.82	0.30	O
	3-7	40	2.0	750	100	0	0	33	3.8	7.5	2.5	1.9	0.41	0.25	X
	3-8	40	6.0	1000	250	0.52	0.45	45	4.4	9.8	3.2	1.8	0.55	0.45	X

Final firing was effected at 1,200°C for 5 hours for all the samples (heating rate: 40°C/hr)

Remarks) A: Total content of bismuth in sintered body
 B: Content of bismuth in δ -Bi₂O₃ crystalline phase
 C: Content of bismuth in Bi-containing amorphous phase

From the above, it is seen that Sample Nos. 3-1 through 3-8 according to the present invention which contain at least the δ -Bi₂O₃ crystalline phase and the bismuth-containing amorphous phase and in which the content of bismuth in each of the phase satisfies (1) $0.10 \leq B/A \leq 0.40$, preferably $0.2 \leq B/A \leq 0.3$ and (2) $0.05 \leq C/A \leq 0.30$, preferably $0.10 \leq C/A \leq 0.2$ have better characteristic values and fewer variations thereof as compared with Comparative Example Nos. 3-1 through 3-8 which do not satisfy one or both of the

above-mentioned requirements.

As is clear from the above explanation, according to the voltage non-linear resistor of the present invention, the intergranular phase of the sintered body is partially made amorphous, and the content of bismuth in the amorphous phase and the content of the bismuth in the δ -Bi₂O₃ phase are controlled to
 5 respectively specified values. Thus, excellent electrical properties can be obtained together with excellent hygroscopicity without suffering variations in characteristics.

Claims

- 10 1. A voltage non-linear resistor which is composed mainly of zinc oxide and contains at least bismuth oxide, antimony oxide and silicon oxide as additives, characterized in that crystalline phases of said bismuth oxide present include at least a β type crystalline phase and a δ type crystalline phase, and β and δ satisfy the following inequalities:

15
$$60 \leq \frac{\beta}{\beta + \delta} \times 100 \leq 90$$

in which β and δ are contents of the β type crystalline phase and the δ type crystalline phase,
 20 respectively.

2. A voltage non-linear resistor which is composed mainly of zinc oxide and contains at least bismuth oxide, antimony oxide and silicon oxide as additives, characterized in that crystalline phases of said bismuth oxide present include at least an α type crystalline phase, a β type crystalline phase, and a δ
 25 type crystalline phase, and α , β and δ satisfy the following inequalities:

30
$$15 \leq \frac{\alpha}{\alpha + \beta + \delta} \times 100 \leq 50,$$

$$25 \leq \frac{\beta}{\alpha + \beta + \delta} \times 100 \leq 60, \text{ and}$$

35
$$10 \leq \frac{\delta}{\alpha + \beta + \delta} \times 100 \leq 40,$$

in which α , β and δ are contents of the α type crystalline phase, the β type crystalline phase, and the δ
 40 type crystalline phase, respectively.

3. A voltage non-linear resistor which is composed mainly of zinc oxide and contains at least bismuth oxide, antimony oxide, and silicon oxide as additives, characterized in that the resistor contains at least
 45 a β -Bi₂O₃ crystalline phase and an amorphous phase containing bismuth, and the content of bismuth in said phases satisfies the following inequalities:

(1) $0.10 \leq B/A \leq 0.40$

50 (2) $0.05 \leq C/A \leq 0.30$

in which A, B and C are the total content of bismuth in a sintered body of the resistor, the content of bismuth in the δ -Bi₂O₃ type crystalline phase, and the content of bismuth in the bismuth-containing
 55 amorphous phase, respectively.

above-mentioned requirements.

As is clear from the above explanation, according to the voltage non-linear resistor of the present invention, the intergranular phase of the sintered body is partially made amorphous, and the content of bismuth in the amorphous phase and the content of the bismuth in the δ -Bi₂O₃ phase are controlled to
 5 respectively specified values. Thus, excellent electrical properties can be obtained together with excellent hygroscopicity without suffering variations in characteristics.

Claims

- 10 1. A voltage non-linear resistor which is composed mainly of zinc oxide and contains at least bismuth oxide, antimony oxide and silicon oxide as additives, characterized in that crystalline phases of said bismuth oxide present include at least a β type crystalline phase and a δ type crystalline phase, and β and δ satisfy the following inequalities:

15
$$60 \leq \frac{\beta}{\beta + \delta} \times 100 \leq 90$$

20 in which β and δ are contents of the β type crystalline phase and the δ type crystalline phase, respectively.

2. A voltage non-linear resistor which is composed mainly of zinc oxide and contains at least bismuth oxide, antimony oxide and silicon oxide as additives, characterized in that crystalline phases of said bismuth oxide present include at least an α type crystalline phase, a β type crystalline phase, and a δ
 25 type crystalline phase, and α , β and δ satisfy the following inequalities:

30
$$15 \leq \frac{\alpha}{\alpha + \beta + \delta} \times 100 \leq 50,$$

$$25 \leq \frac{\beta}{\alpha + \beta + \delta} \times 100 \leq 60, \text{ and}$$

35
$$10 \leq \frac{\delta}{\alpha + \beta + \delta} \times 100 \leq 40,$$

40 in which α , β and δ are contents of the α type crystalline phase, the β type crystalline phase, and the δ type crystalline phase, respectively.

3. A voltage non-linear resistor which is composed mainly of zinc oxide and contains at least bismuth oxide, antimony oxide, and silicon oxide as additives, characterized in that the resistor contains at least
 45 a β -Bi₂O₃ crystalline phase and an amorphous phase containing bismuth, and the content of bismuth in said phases satisfies the following inequalities:

(1) $0.10 \leq B/A \leq 0.40$

50 (2) $0.05 \leq C/A \leq 0.30$

in which A, B and C are the total content of bismuth in a sintered body of the resistor, the content of bismuth in the δ -Bi₂O₃ type crystalline phase, and the content of bismuth in the bismuth-containing amorphous phase, respectively.

55



Patentansprüche

1. Nichtlinear spannungsabhängiger Widerstand, der hauptsächlich aus Zinkoxid besteht und zumindest Wismutoxid, Antimonoxid und Siliziumoxid als Additive enthält, dadurch gekennzeichnet, daß die kristallinen Phasen des genannten vorhandenen Wismutoxids zumindest eine kristalline Phase vom β -Typ und eine kristalline Phase vom δ -Typ enthalten und β und δ den folgenden Ungleichungen entsprechen:

$$60 \leq \frac{\beta}{\beta + \delta} \times 100 \leq 90$$

worin β und δ Gehalte der kristallinen Phase vom β -Typ bzw. der kristallinen Phase vom δ -Typ sind.

2. Nichtlinear spannungsabhängiger Widerstand, der hauptsächlich aus Zinkoxid besteht und zumindest Wismutoxid, Antimonoxid und Siliziumoxid als Additive enthält, dadurch gekennzeichnet, daß die kristallinen Phasen des genannten vorhandenen Wismutoxids zumindest eine kristalline Phase vom α -Typ, eine kristalline Phase vom β -Typ und eine kristalline Phase vom δ -Typ enthalten und α , β und δ den folgenden Ungleichungen entsprechen:

$$15 \leq \frac{\alpha}{\alpha + \beta + \delta} \times 100 \leq 50,$$

$$25 \leq \frac{\beta}{\alpha + \beta + \delta} \times 100 \leq 60, \text{ und}$$

$$10 \leq \frac{\delta}{\alpha + \beta + \delta} \times 100 \leq 40,$$

worin α , β und δ Gehalte der kristallinen Phase vom α -Typ, der kristallinen Phase vom β -Typ bzw. der kristallinen Phase vom δ -Typ sind.

3. Nichtlinear spannungsabhängiger Widerstand, der hauptsächlich aus Zinkoxid besteht und zumindest Wismutoxid, Antimonoxid und Siliziumoxid als Additive enthält, dadurch gekennzeichnet, daß der Widerstand zumindest eine kristalline β - Bi_2O_3 -Phase und eine amorphe Phase enthält, die Wismut enthält, und der Gehalt an Wismut in den genannten Phasen den folgenden Ungleichungen entspricht:

$$(1) \quad 0.10 \leq B/A \leq 0.40$$

$$(2) \quad 0.05 \leq C/A \leq 0.30$$

worin A, B, und C der Gesamtgehalt an Wismut in einem Sinterkörper des Widerstands, der Wismutgehalt in der kristallinen Phase vom β - Bi_2O_3 -Typ bzw. der Wismutgehalt in der wismuthältigen amorphen Phase sind.

Revendications

1. Résistance non linéaire dépendant de la tension qui se compose principalement d'oxyde de zinc et qui contient au moins de l'oxyde de bismuth, de l'oxyde d'antimoine et de l'oxyde de silicium comme additifs, caractérisée en ce que les phases cristallines dudit oxyde de bismuth présentent comprennent au moins une phase cristalline du type β et une phase cristalline du type δ , et β et δ satisfont aux inégalités suivantes :



$$60 \leq \frac{\beta}{\beta + \delta} \times 100 \leq 90$$

5

où β et δ sont les teneurs de la phase cristalline du type β et de la phase cristalline du type δ , respectivement.

- 10 2. Résistance non linéaire dépendant de la tension qui se compose principalement d'oxyde de zinc et qui contient au moins de l'oxyde de bismuth, de l'oxyde d'antimoine et de l'oxyde de silicium comme additifs, caractérisée en ce que les phases cristallines dudit oxyde de bismuth présentent comprennent au moins une phase cristalline du type α , une phase cristalline du type β et une phase cristalline du type δ et α , β et δ satisfont aux inégalités suivantes :

15

$$15 \leq \frac{\alpha}{\alpha + \beta + \delta} \times 100 \leq 50,$$

20

$$25 \leq \frac{\beta}{\alpha + \beta + \delta} \times 100 \leq 60 \text{ et}$$

25

$$10 \leq \frac{\delta}{\alpha + \beta + \delta} \times 100 \leq 40,$$

- 30 où α , β et δ sont les teneurs de la phase cristalline du type α , de la phase cristalline du type β et de la phase cristalline du type δ , respectivement.

- 35 3. Résistance non linéaire dépendant de la tension qui se compose principalement d'oxyde de zinc et qui contient au moins de l'oxyde de bismuth, de l'oxyde d'antimoine et de l'oxyde de silicium comme additifs, caractérisée en ce que la résistance contient au moins une phase cristalline de β -Bi₂O₃ et une phase amorphe contenant du bismuth et la teneur en bismuth dans lesdites phases satisfait aux inégalités suivantes :

40

$$(1) \quad 0,10 \leq B/A \leq 0,40$$

$$(2) \quad 0,05 \leq C/A \leq 0,30$$

45

où A, B et C sont la teneur totale en bismuth dans un corps fritté de la résistance, la teneur en bismuth dans la phase cristalline du type β -Bi₂O₃ et la teneur en bismuth dans la phase amorphe contenant du bismuth, respectivement.

50

55

