

Bituminous membrane

The present invention relates to a bituminous membrane. Bituminous membranes today find widespread application in many spheres, for the purpose of repairing and protecting, for example construction components in masonry, domestic fixtures and motor vehicles. Their versatility is largely due to the fact that they adhere very well to an extremely wide range of materials, such as wood, metal, asphalt, cement and the like, not to mention the fact that they can be applied in cold conditions and can thus be used by virtually anyone.

Membranes of this type mainly comprise a bitumen-based compound in which are present thermoplastic polymers and plasticizers, in synthetic or natural form. The main problems encountered by products of this type are varied in nature: it would be advantageous for them to have satisfactory mechanical properties, which would give them strength and dimensional stability; they would also need to be protected against natural deterioration due to exposure to atmospheric agents, and lastly it would be advantageous for them to have noteworthy plastic properties in order to retain the shape acquired when they are applied.

Attempts have been made to solve these problems over the years. It was initially thought to improve the mechanical properties of these membranes by burying inside the bituminous compound, or by binding thereto, a support consisting of a film with similar mechanical properties.

Following that, the membrane was given a surface sheet of aluminium, as described in US patent No. 3,770,559, which goes towards improving its aesthetic appearance and at the same time gives it protection against ageing caused by UV rays, ozone, oxygen or any other atmospheric agent.

The obvious development arising from these shrewd approaches has resulted in the emergence of bituminous membranes comprising both an internal support which improves its mechanical properties, and a
5 surface film of aluminium, which extends its lifetime.

However, especially in the case of thin membranes, which are often used to join surfaces that are not co-planar, internal supports used have a tendency to resume their original flat shape, which
10 could lead to detachment of the membrane from one of the surfaces involved.

In many cases, in order to avoid this type of elastic behaviour, it has thus been decided to dispense with the internal reinforcing support, thus leaving the
15 aluminium film responsible for both the protective function and the enhancement of the mechanical properties of the membrane.

The result obtained is a durable product with excellent plastic behaviour but only modest mechanical
20 properties.

Alternatively, by using a process which is widespread in the food sector and in the sector of flexible wrappings, membranes have been made in which a polyethylene support is bonded to the protective
25 aluminium film rather than being inserted in the bituminous compound.

A multilayer membrane, described in US patent No. 5,096,759, was thus obtained, composed of a surface sheet of aluminium reinforced with a polyethylene
30 support, bonded thereto by a polyurethane adhesive, underneath which are, in the following order, the bituminous compound and a sheet for protecting the adhesive surface.

This product has good mechanical properties and
35 durability, but still has an elastoplastic behaviour which is unsatisfactory for the purposes for which this product is used. Actually, its elastic behaviour is substantially more pronounced than that of membranes in which the reinforcing film is inserted in the bituminous compound.

The object of the present invention is thus to eliminate the drawbacks mentioned above. The invention, as characterized by the claims, solves the problem of ensuring a satisfactory plastic behaviour.

5 One of the advantages afforded by the present invention consists essentially of the fact that even after a long period, the membrane thus produced does not have any undesired elastic recovery; in addition, it has excellent mechanical properties and durability.


10 The subject of the present invention consists of a bituminous membrane as described in the preamble of the attached Claim 1, characterized by the characterizing part of that claim.

The technical characteristics of the invention, according to the abovementioned objects, can clearly be gathered from the content of the subsequent claims and the advantages of this invention will become more clearly apparent in the detailed description which follows, which is given with reference to the attached drawings, which represent a non-limiting and purely illustrative embodiment thereof, in which:

- Figure 1 illustrates the cross-section of a membrane according to the prior art;
- Figure 2 illustrates the cross-section of a membrane according to the invention;
- Figure 3 illustrates the invention subjected to an elastic return test and the relevant apparatus;
- Figure 3a shows the profile of the test pieces subjected to the abovementioned test;
- 30 • Figures 4 to 7 illustrate, in the form of tables, the results of the test mentioned in Figures 3 and 3a.

The invention relates to a bituminous membrane.

The inventor of the present invention has carried out an analysis directed towards clarifying the reasons for which a membrane as described above, i.e. coated according to the current dictates of the art, might have the abovementioned drawback of not being able to be bent so as to perfectly fit irregular surfaces, on account of its elastic "return", and has



arrived at the conclusion that this return is caused by the elastic reaction formed by the supporting and reinforcing sheet of synthetic resin.

5 This reaction in turn arises from compression and/or tension on the outermost fibres of the film caused by the flexure imparted to the membrane to make it adhere to the said irregular surfaces. Since, as is known, the value of the flexure-derived stresses acting on the fibres depends on the distance of these fibres
10 from the neutral axis of the flexed body, the inventor set himself the aim of reducing this distance to the minimum possible value and concluded that, to this end, another film of aluminium, identical in thickness to that of the abovementioned first film, needs to be
15 applied by bonding, also to the opposite face of the film of synthetic resin, in order to ensure that the neutral axis of a section of the entire membrane lies on the median plane of this membrane: in this way, the fibres of the film of synthetic resin which are under
20 the most stress, i.e. those most distant from the neutral axis, are distant therefrom by only half the thickness of the film.

Since, in these applications, this thickness is of the order of one-twentieth of a μm , the resultants
25 of the tensile and compression stresses acting on the fibres, which give rise to the abovementioned elastic reaction, thus have such a low value, which can be contrasted with the actual weight of the membrane and/or its flexural strength, which is also dependent
30 on its profile derived from the shape of the surface onto which it is made to adhere.

A membrane is thus obtained with essentially "plastic" behaviour, with the consequent advantage of being able to be applied in a reliable manner with
35 maximum adhesion to the surfaces to be coated. (As regards their physical properties, both the sheets of aluminium and the layer of bituminous compounds have been considered as having no influence on the elasticity of the membrane).

Figure 2 shows the cross-section of a membrane 21 according to the prior art, in which a single metal film 3, generally made of aluminium, is bonded to a film of synthetic resin 2.

5 In the figure, the position of the neutral axis n-n and the maximum distance therefrom of the fibres of the film of synthetic resin 2 which are under the greatest stress, this distance being equal to half the thickness H of the entire membrane, can be seen. In
10 addition, the entire cross-section of the film of resin works under compression or under tension.

Figure 1 is a cross-section of a membrane according to the present invention, in which two films of aluminium 3,4 of equal thickness d are bonded to the
15 opposite faces of a film of synthetic resin 2 equal in thickness to that of the film of Figure 1.

Since all the films 2, 3, 4 are joined together by bonding, the neutral axis n-n is located as shown, i.e. on the median plane of the film of synthetic
20 resin 2, and the fibres of this film which are under the greatest flexural stress are at the smallest possible distance from the neutral axis n-n, equal to half the thickness S of the film of synthetic resin 2.

In addition, half of the film of synthetic
25 resin 2 is subjected to tension, and half to compression.

In this way, the result which the inventor intended to achieve is obtained.

Both figures also show the film of bituminous
30 compound, applied directly to the supporting and reinforcing film of synthetic resin 2 according to the prior art, and to the innermost film of aluminium 4 according to the present invention.

An antiadhesive protective sheet, for example a
35 siliconated sheet, not represented in the figures since it is well known to those familiar with this technological field, is usually applied to the outermost face of the film of bituminous compound.



Among the many films of synthetic resin 2 which can be used for this purpose, a preferred solution performed envisages the use of polyester, nylon 6 or polyethylene, whereas, for the bituminous compound (5), it is recommended to use a composition comprising about 75% 180/200 bitumen, about 15% SBR (styrene-butadiene-rubber: sold, for example, under the name Finaprene 411X) and about 10% plasticizers and resins, in approximately equal parts.

The inventor recommends the use of two films of aluminium 3,4 and one film of synthetic resin 2, all three having an identical thickness equal to about 20 μm .

The plasticity of the membrane thus obtained is demonstrated by laboratory test analyses carried out by a specialized institute, the results of which are attached in Figures 4 to 7.

The tests were carried out on various samples of bituminous membrane consisting of portions of aluminium film joined with syntnetic films.

For the various types of material examined, rectangular test pieces 6, 70 x 25 mm in size and with thicknesses corresponding to the type of material were prepared, half of which were cut along a direction A and the other half cut in the direction B perpendicular to the first.

Apparatus for determining the cold flexibility in accordance with the indications of UNI standard 8202, Section XV, was used to carry out the test, this apparatus including bending mandrels 7, 15, 10 and 5 mm in diameter, as well as a centesimal digital gauge with 0.1 mm definition.

After they had been conditioned at the laboratory temperature, of between 10 and 23°C, for 24 hours, the test pieces 6, placed on supports 8, were bent into a "U" shape by means of the abovementioned apparatus, using mandrels 7 of different diameter, in the manner represented schematically in Figure 3. One minute after bending, the distance "X" between the



upper arms of the test piece was measured, as indicated in Fig. 3A.

The results relating to a sample consisting of aluminium and HDPE (high density polyethylene), corresponding to the subject of US patent No. 5,096,759, were tabulated in Figure 4: as can be seen, the result obtained is relatively independent of the direction in which the test pieces were cut (A or B) and of the dimensions of the mandrel used.

The elastic return is large and the chord "X" measured is between 70 and 78% of the original length of the test piece.

Figures 5 and 6 show the results of tests on two test pieces 25 consisting of a film of aluminium and polyester: in the first case, the aluminium surface is placed in contact with the mandrel, in the second case the polyester surface is placed in contact.

With reference to the average values here also, the tests carried out with aluminium in contact with the mandrel give fairly uniform results, gradually improving as the size of the mandrel decreases, for the samples cut in the direction A.

For the samples cut in the direction B, distinctly plastic behaviour is observed using a 10 mm mandrel: indeed, in this case, the sample has a return of slightly over 50%. When the polyester surface is placed in contact with the mandrel, almost constant behaviour is observed, both in terms of the orientation of cutting of the sample and in terms of the size of the mandrel: the best result obtained in this case gives a return of about 60%.

However, it should be pointed out that even the best result obtained in these tests, achieved with a sample made of aluminium and polyester, in which the aluminium is placed in contact with the 10 mm mandrel, has only a remote possibility of application, since membranes of this type are always bended with the aluminium surface facing outwards.

Lastly, Figure 7 shows the results of the tests relating to the membrane which is the subject of the present invention: as can be seen, these results are essentially independent of the direction of cutting and
5 improve substantially as the size of the mandrel decreases, until elastic returns of between 25 and 30% are reached, which indicate its distinctly plastic behaviour.

The invention thus designed can be modified and
10 varied in many ways, all of which fall within the scope of the inventive concept. In addition, all of the details can be replaced with technically equivalent elements.

Needless to say, modifications and/or
15 improvements which nevertheless fall within the scope of the following claims can be made in practice.

Claims

1. Bituminous membrane (1) comprising a sheet (5) of a bituminous compound onto which is placed a layer composed by a film of metallic material (3) bonded to one face of a supporting and reinforcing film (2) made of synthetic resin, characterized in that on the opposite side of the supporting and reinforcing film (2) made of synthetic resin is applied, by bonding, another film (4) of metallic material with a thickness (d) equal to that of the said metal film (3) applied to the other face.
2. Membrane according to Claim 1, in which the said two films (3,4) of metallic material are made of aluminium.
3. Membrane according to either of the preceding claims, in which the said supporting and reinforcing film (2) is made of polyester.
4. Membrane according to either of Claims 1 and 2, in which the said supporting and reinforcing film (2) is made of nylon 6.
5. Membrane according to either of Claims 1 and 2, in which the said supporting and reinforcing film (2) is made of polyethylene.
6. Membrane according to any one of the preceding claims, in which the said sheet (5) of bituminous compound comprises about 75% 180/200 bitumen, about 15% SBR and about 10% plasticizers and resins.
7. Membrane according to one of the preceding claims, in which both the two said films (3,4) of metallic material and the said supporting and reinforcing film (2) made of synthetic resin have a thickness of about 20 μm .

This Sheet Has Been Replaced

