

LIQUID CRYSTAL DISPLAY CELL SPACER AND
LIQUID CRYSTAL DISPLAY CELL

TECHNICAL FIELD

The present invention relates to a liquid crystal display cell spacer with improved in coloring effect and light shielding effect and to a liquid crystal display cell with use thereof.

BACKGROUND ART

While the liquid crystal display cell has been used widely in a variety of electronic equipment such as personal computers and portable electronic devices, there has been much need for improving its performance by increasing its display contrast of images. Japanese Kokai Publication Sho-57-189117 discloses such a technology which comprises disposing two transparent electrode-carrying substrates with the respective electrodes facing each other and a liquid crystal hermetically sandwiched between said substrates, with particles of a colored spacer being dispersed on the entire surfaces of the substrates which are adjoining to the liquid crystal so as to prevent deterioration of the display contrast of images.

The liquid crystal display cell spacer for such a high-contrast liquid crystal display cell must have been colored to a deep shade. While many production methods have heretofore been proposed for the fabrication of such a liquid crystal display cell spacer, they can be roughly divided into the technology which comprises dyeing polymer particles previously manufactured and the technology which comprises dyeing polymer particles in the course of their manufacture.

The technology which comprises dyeing polymer particles previously manufactured includes the following processes. Japanese Kokai Publication Hei-1-144429 describes a process which comprises treating polymer particles with an acid and then dyeing them. Japanese Kokai Publication Hei-1-207719

discloses a process which comprises subjecting polymer particles to heat treatment at 200 to 700°C to provide flame-resistant sintered particles. Japanese Kokai Publication Hei-5-165033 discloses a process which comprises coating polymer particles with a conjugated polymer such as polyacetylene. Japanese Kokai Publication Hei-1-200227 describes a process which comprises disposing a metallic layer on the surface of crosslinked polymer particles and oxidizing the metal to the metal oxide.

Japanese Kokai Publication Hei-4-15623 discloses a process which comprises striking ultrafine black metal oxide particles into the surface layers of organic polymer particles, while Japanese Kokai Publication Hei-3-101713 discloses a process which comprises dispersing particles of a polymer containing anionic functional groups in a solution containing an oxidizing agent to let the oxidizing agent adsorbed or impregnated, adding at least one member selected from the group consisting of 5-membered heterocyclic compounds and aromatic hydrocarbons, and causing the mixture to undergo chemical oxidative polymerization. Disclosed in Japanese Kokoku Publication Hei-4-27242 is a process in which particles of a water-soluble polymer available upon polymerization of an ethylenically unsaturated sulfonic acid compound or a salt thereof are dyed with a basic dye.

Furthermore, Japanese Kokai Publication Hei-3-351639 discloses a process which comprises dyeing polymer particles comprising amino resin with an acidic dye in the presence of a solvent at high temperature, while Japanese Kokai Publication Hei-4-363331 discloses a process which comprises dispersing an oily solution of an oily dye uniformly in an aqueous medium, mixing the resulting dye emulsion with an emulsion of polymer particles so as to dye the particles.

However, this technology of coloring polymer particles prepared beforehand not only entails high production costs but also has the drawback that the performance and quality

1 characteristics of the final product cannot be easily
controlled.

5 The technology which comprises dyeing polymer particles
in the course of their manufacture includes the following and
other processes. Japanese Kokoku Publication Sho-50-33821,
Japanese Kokoku Publication Sho-56-50883, and Japanese Kokoku
Publication Hei-4-89805 disclose technologies for producing
10 liquid crystal display cell spacers in which a polymerizable
monomer is suspension-polymerized in the presence of a
pigment. However, these methods have limitations in the kind
of polymerizable monomer that can be used and in production
scale and, moreover, the incorporated pigment tends to be
15 exposed on the spacer surface with the result that the
pigment itself dissolves out upon exposure to an organic
solvent or the like or that impurities in the pigment are
liable to dissolve out.

Japanese Kokoku Publication Hei-4-59321 discloses a
process for producing a liquid crystal display cell spacer
20 which comprises mixing a lipophilicity-imparted pigment with a
monomeric component comprising a polyfunctional vinyl
compound and an lipophilic vinyl compound and subjecting the
mixture to suspension-polymerization in an aqueous medium.
This process is conducive to improvements in the
25 dispersibility of the pigment and solvent resistance but in
order to insure a substantial absence of the pigment on the
spacer surface, the vinyl compound must be subjected to a
suspension polymerization or emulsion polymerization as a
post-treatment. Since this process involves two stages of
polymerization, the production cost is high of necessity.

30 Japanese Kokai Publication Hei-7-2913 describes a process
for producing a liquid crystal display cell spacer which
comprises mixing a pigment uniformly with a (meth)
acrylonitrile-containing polyfunctional ethylenically
35 unsaturated component and subjecting the mixture to suspension
polymerization in an aqueous medium. However, this

1 technology cannot provide a liquid crystal display cell
spacer colored to a deep shade, for although it is conducive
to improvements in the dispersibility of the pigment and the
5 mechanical strength and solvent resistance of the spacer, the
impurities in the pigment tend to dissolve and diffuse into
the spacer to reduce its electrical resistance of the spacer,
so that there is a limit to the proportion of the pigment
that can be added.

10 Thus, by the technology of coloring polymer particles in
the course of manufacture thereof, too, it is difficult to
obtain a liquid crystal display cell spacer with good
coloring effect and light shielding effect and physical
properties necessary for a spacer in an expedient and
15 efficient manner.

SUMMARY OF THE INVENTION

The present invention has for its object to solve the
above problems and accordingly provide a liquid crystal
display cell spacer with improved coloring effect and light
20 shielding effect and satisfactory electrical, physical,
chemical, and optical properties and a liquid crystal display
cell with use thereof.

The present invention relates, in a first aspect, to a
liquid crystal display cell spacer comprising surface-coated
carbon black. This liquid crystal display cell spacer can be
25 advantageously applied to liquid crystal display cells.

The present invention relates, in a second aspect, to a
liquid crystal display cell spacer comprising a pigment
component comprising carbon black and at least one set of
30 organic pigments of dissimilar colors other than carbon
black. This liquid crystal display cell spacer can be
advantageously applied to liquid crystal display cells.

The present invention relates, in a third aspect, to a
liquid crystal display cell spacer comprising a pigment
35 component comprising surface-coated carbon black and at least

one set of organic pigments of dissimilar colors other than carbon black. This liquid crystal display cell spacer can be advantageously applied to liquid crystal display cell.

The present invention relates, in a fourth aspect, to a liquid crystal display cell comprising the liquid crystal display cell spacer according to said first, second, or third aspect of the invention.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a sectional view showing one embodiment of the liquid crystal display cell according to the present invention; in which the reference numeral 1 represents a transparent substrate, 2 a transparent electrode, 3 an alignment layer, 4 a transparent substrate, 5 a transparent electrode, 6 an orientation control film, 7 a substrate, 8 a spacer, 9 a substrate, 10 a sealing member, 11 nematic liquid crystals, 12 a polarizing sheet, and 13 a polarizing sheet.

DISCLOSURE OF THE INVENTION

The first aspect of the present invention relates to a liquid crystal display cell spacer comprising surface-coated carbon black.

The carbon black for use in this first aspect of the invention has a coated surface which precludes dissolution and diffusion of its impurities. By using this surface-coated carbon black, the electrical resistance of the liquid crystal display cell spacer can be prevented from reducing even if its proportion is increased and, moreover, the dispersibility of carbon black is improved so that sufficiently deep black shading of the spacer can be achieved with a smaller amount of carbon black. The coating can be applied by, for example, using a thermoplastic resin.

As used throughout this specification, the term "impurities" means the contaminants which are unavoidably contained in ordinary carbon black and, if dissolved out and

1 diffused into the liquid crystal display cell spacer, reduce
the electrical resistance of the spacer, such as sodium ion,
potassium ion, chloride ion, and sulfate ion, among others.

5 The carbon black for said surface-coated carbon black is
not particularly restricted in kind, thus including but not
limited to channel black, roll black, furnace black, and
thermal black.

10 The thermoplastic resin is not particularly restricted in
kind but includes alkyd resin, modified alkyd resin, phenolic
resin, natural resin-modified phenolic resin, maleic acid
resin, natural resin-modified maleic acid resin, fumaric acid
resin, ester gum, rosin, petroleum resin, coumarone resin,
indene resin, polyester resin, polyamide resin, polycarbonate
15 resin, polyethylene resin, epoxy resin, styrene resin, vinyl
resin, acrylic resin, chlorinated rubber, benzoguanamine
resin, urea resin, etc. These resins may be used
independently or in combination.

20 The technique for coating the surface of carbon black
with the above-mentioned thermoplastic resin is not
restricted. A typical method comprises pulverizing carbon
black in the presence of a hydrophobic medium containing said
thermoplastic resin by means of a crusher such as a ball mill
or the like. An alternative method comprises mixing an
25 aqueous dispersion of carbon black with a hydrophobic medium
containing said thermoplastic resin to prepare an emulsion and
removing water by heating. In a further alternative process,
a hydrophobic medium containing said thermoplastic resin is
heated beforehand, an aqueous dispersion of carbon black is
30 added with stirring, and the water is simultaneously distilled
off. The surface-coated carbon black thus obtained can be
precipitated by mixing the system with a lower alcohol, e.g.
ethanol or isopropyl alcohol, which is miscible with the
hydrophobic medium, and recovered by filtration or
35 decantation.

The liquid crystal display cell spacer according to the

1 first aspect of the invention can be produced by dispersing
said surface-coated carbon black uniformly in a polymerizable
monomer and subjecting the dispersion to polymerization
reaction. The method for this polymerization is not
5 particularly restricted. Thus, for example, suspension
polymerization and emulsion polymerization can be mentioned.
Particularly in order to provide a uniformly colored liquid
crystal display cell spacer, a suspension polymerization
process is preferred.

10 The suspension polymerization is carried out by
dispersing said surface-coated carbon black uniformly in said
polymerizable monomer and subjecting the dispersion to
polymerization in the presence of a polymerization initiator
in an aqueous medium.

15 There is no particular limitation on the polymerizable
monomer that can be used, thus including unsaturated
carboxylic acids such as acrylic acid, methacrylic acid,
maleic acid, maleic anhydride, fumaric acid, crotonic acid,
itaconic acid, etc.; acrylic esters such as methyl acrylate,
20 ethyl acrylate, n-propyl acrylate, isopropyl acrylate,
n-butyl acrylate, t-butyl acrylate, 2-ethylhexyl acrylate,
stearyl acrylate, etc.; methacrylic esters such as methyl
methacrylate, ethyl methacrylate, propyl methacrylate,
n-butyl methacrylate, t-butyl methacrylate, 2-ethylhexyl
25 methacrylate, lauryl methacrylate, stearyl methacrylate,
dodecyl methacrylate, glycidyl methacrylate, β -hydroxyethyl
methacrylate, hydroxymethyl methacrylate, etc.; styrenic
monomers such as styrene, vinyltoluene, α -methylstyrene,
p-methoxystyrene, t-butylstyrene, chlorostyrene, etc.; diene
30 type monomers such as butadiene, isoprene, etc.; ethylene,
vinyl chloride, vinyl acetate, vinyl propionate, acrylamide,
methacrylamide, acrylonitrile, methylolacrylamide, vinyl
stearate, acryl acetate, diallyl adipate, dimethyl itaconate,
diethyl maleate, allyl alcohol, vinylidene chloride,
35 vinylpyridine, N-vinylpyrrolidone, N-hydroxyacrylamide,

1 2-vinyl-2-oxazoline, 2-isopropenyl-2-oxazoline,
dimethylaminoethyl acrylate, glycidyl methacrylate, allyl
glycidyl ether, monomethyl fumarate, etc. These monomers can
5 be used independently or in combination and there is no
particular limitation on the kinds of monomers to be used in
combination.

In addition to the polymerizable monomer mentioned above,
one or more other crosslinking compounds can be optionally
10 employed. Among such optional monomers can be mentioned
aromatic divinyl compounds such as divinylbenzene,
divinylnaphthalene and their derivatives; diethylenically or
triethylenically unsaturated carboxylic esters such as
ethylene glycol di(meth)acrylate, diethylene glycol di(meth)
15 acrylate, triethylene glycol di(meth)acrylate,
trimethylolpropane tri(meth)acrylate, 1,3-butanediol di(meth)
acrylate, etc.; divinyl compounds such as N,N-divinylaniline,
divinyl ether, divinyl sulfide, divinyl sulfone, etc.; and
compounds each containing 3 or more vinyl groups. The
20 preferred proportion of such crosslinking compounds is 0.005
to 100 weight percent based on the combined amount of the
crosslinking compound and the polymerizable monomer.

The proportion of said polymerizable monomer per 100
parts by weight of the aqueous medium is preferably 1 to 200
25 parts by weight. If the proportion is less than 1 part by
weight, the production cannot be profitably carried out. On
the other hand, if the upper limit of 200 parts by weight is
exceeded, it will be difficult to remove the heat of
polymerization.

30 The proportion of surface-coated carbon black is
preferably 0.1 to 200 parts by weight relative to 100 parts by
weight of the polymerizable monomer. If the proportion is
smaller than 0.1 part by weight, the spacer can hardly be
colored to a deep shade. On the other hand, if the upper
35 limit of 200 parts by weight is exceeded, the mechanical
strength of the product liquid crystal display cell spacer

1 tends to be sacrificed.

In order that the surface-coated carbon black may be uniformly dispersed in said polymerizable monomer, a mechanical device such as a ball mill, bead mill, sand mill, attriter, sand grinder, nanomizer, or the like can be used with advantage. In this operation, a dispersing agent can be used to improve dispersibility of the surface-coated carbon black.

10 The dispersing agent that can be used is not particularly restricted in kind. Thus, it may be any of water-soluble polymers such as polyvinyl alcohol, starch, methylcellulose, carboxymethylcellulose, hydroxyethylcellulose, poly(sodium methacrylate), etc.; barium sulfate, calcium sulfate, aluminum sulfate, calcium carbonate, calcium phosphate, talc, clay, diatomaceous earth, metal oxide powder, etc.

The proportion of said dispersing agent is 0.01 to 20 weight % based on the polymerizable monomer component.

20 The aqueous medium that can be used is not particularly restricted in kind and may for example be an aqueous solution of a water-soluble organic compound such as polyvinyl alcohol, polyacrylic acid, polymethacrylic acid, gelatin, methylcellulose, polymethacrylamide, polyethylene glycol, polyethylene oxide monostearate, sorbitan tetraoleate, glycerin monooleate, dodecylbenzenesulfonic acid, etc., as well as water.

30 In the above aqueous medium is in a microfine fashion suspended a uniform dispersion of surface-coated carbon black in said polymerizable monomer. This suspending operation can be carried out using a homogenizer or the like.

35 The reaction temperature preferred for said suspension polymerization is 20 to 100°C. If the temperature is below 20°C the polymerization reaction rate will not be acceptably high. On the other hand, if the reaction temperature exceeds 100°C, the polymerization reaction can hardly be controlled.

The suspension polymerization time is preferably 1 to 50

1 hours. If the reaction time is less than 1 hour, the rate of
polymerization will be too low. On the other hand, a
prolonged reaction over 50 hours is unnecessary.

5 The liquid crystal display cell spacer obtained by the
above suspension polymerization reaction can be separated by
filtration, centrifugation or other known procedure. The
separated liquid crystal display cell spacer is rinsed with
water or the like and dried by heating or in vacuo.

10 The polymerization initiator that can be used in said
suspension polymerization is not particularly restricted,
thus including but not limited to azo compounds such as
2,2'-azobisisobutyronitrile, 2,2'-azobis-2,4'-
dimethylvaleronitrile, 2,2'-azobis-methylbutyronitrile,
15 2,2'-azobis-methylheptonitrile, 2,2'-azobis-2,3-
dimethylbutyronitrile, 2,2'-azobis-2,3,3-
trimethylbutyronitrile, 2,2'-azobis-2-isopropylbutyronitrile,
4,4'-azobis-4-cyanovaleric acid, dimethyl-2,2'-azobis-
isobutyrate, etc. and organic peroxides such as acetyl
20 peroxide, decanoyl peroxide, lauroyl peroxide, benzoyl
peroxide, octanoyl peroxide, orthomethoxybenzoyl peroxide,
p-chlorobenzoyl peroxide, 2,4-dichlorobenzoyl peroxide,
diisopropyl peroxydicarbonate, 2-ethylhexyl peroxydicarbonate,
acetyl cyclohexanesulfonyl peroxide, t-butyl
25 peroxyisobutyrate, t-butyl peroxyphthalate, t-butyl peroxy-2-
ethylhexanoate, di-t-butyl peroxide, t-butyl cumyl peroxide,
dicumyl peroxide, methyl ethyl ketone peroxide, cumene
hydroperoxide, t-butyl hydroperoxide, etc.

30 The amount of said polymerization initiator is 0.01 to 30
parts by weight based on 100 parts by weight of the
polymerizable monomer. If the proportion is smaller than
0.01 part by weight, the rate of polymerization reaction will
be too low. On the other hand, addition of the initiator in
excess of 30 parts by weight is unnecessary. The preferred
35 range is 0.1 to 10 parts by weight.

The preferred liquid crystal display cell spacer

1 according to the first aspect of the present invention has a
mean particle diameter of 0.5 to 500 μ m. If the mean
particle diameter is less than 0.5 μ m, the particles tend to
5 coagulate and will not be practically useful. The spacer
with a mean particle diameter exceeding 500 μ m will find
little application. The preferred range is 1 to 300 μ m.

The coefficient of variation of the particle size of the
liquid crystal display cell spacer according to the first
10 aspect of the present invention is preferably not greater than
20%. If the coefficient of variation exceeds 20%, the
particle size distribution will be too broad so that the
performance of the spacer tends to be sacrificed. More
preferably, the coefficient of variation is not greater than
15 10%. For still better results, the coefficient is not greater
than 5%.

In order to preclude dissolution and diffusion of
impurities etc. (inclusive of the pigment itself) and impart
an interfacial chemical modification to the surface of the
20 liquid crystal display cell spacer, the spacer surface may be
coated with a coating material such as a silane coupling
agent as necessary. The coating agent is preferably applied
in a monomolecular layer or as a thin polymer film.

The silane coupling agent that can be used as above is
not particularly restricted, thus including but not limited to
25 amino silane coupling agents such as γ -aminopropyltrimethoxy
silane, N- β -(aminoethyl)- γ -aminopropyltrimethoxysilane, 3-
[N-allyl-N-(2-aminoethyl)]aminopropyltrimethoxysilane, 3-(N-
allyl-N-glycidyl)aminopropyltriethoxysilane, 3-(N-allyl-N-
methacryl)aminopropyltrimethoxysilane, 3-(N,N-diglycidyl)
30 aminopropyltrimethoxysilane, etc.; amide silane coupling
agents such as N,N-bis[3-(methyldimethoxysilyl)propyl]amine,
N,N-bis[3-(trimethoxysilyl)propyl]amine, N,N-bis[3-
(methyldimethoxysilyl)propyl]ethylenediamine, N,N-bis[3-
(trimethoxysilyl)propyl]ethylenediamine, N-glycidyl-N,N-bis[3-
35 (methyldimethoxysilyl)propyl]amine, N-glycidyl-N,N-bis[3-

1 (trimethoxysilyl)propylamine, etc.; vinyl silane coupling
agents such as vinyltriethoxysilane, vinyl-tris(2-
methoxyethoxy)silane, etc.; methacrylic silane coupling agents
5 such as γ -methacryloxypropyltrimethoxysilane etc.; glycidyl
silane coupling agents such as γ -glycidoxypropyltrimethoxy-
silane etc.; and mercaptosilane coupling agents such as
 γ -mercaptopropyltrimethoxysilane etc.

10 There is no particular limitation on the method for
covering the surface of the liquid crystal display cell
spacer with said coating agent. A typical method comprises
mixing the coating agent with the liquid crystal display cell
spacer in an inorganic solvent such as water or an organic
solvent such as alcohol, heating the mixture with stirring,
15 thereafter separating the liquid crystal display cell spacer
by, for example, decantation, and finally removing the
solvent by drying in vacuo. An alternative method comprises
mixing said coating agent with the liquid crystal display
cell spacer directly and heating the mixture.

20 The liquid crystal display cell spacer according to the
first aspect of the present invention comprises a surface-
coated carbon black and, therefore, is free from the
dissolution and diffusion of any impurities in the carbon
black, with the result that not only a uniform deep black
shade but also a high solvent resistance can be obtained.
25 Furthermore, the surface-coated carbon black is suppressed in
the loss of electrical resistance and improved in
dispersibility compared with the uncoated carbon black, with
the result that it is uniformly dispersed and imparts a higher
degree of darkness to the liquid crystal display cell spacer.

30 The second aspect of the present invention relates to a
liquid crystal display cell spacer which comprises a pigment
component comprising carbon black and at least one set of
organic color pigments of dissimilar colors other than carbon
black.

35 There is no particular limitation on the kind of carbon

1 black that can be used, thus including but not limited to
acetylene black, channel black, and furnace black. In this
second aspect of the invention, a surface-treated carbon
black such as Microlith (Ciba-Geigy) can be used for improved
5 in carbon black dispersibility.

Referring to said one set of organic color pigments of
dissimilar colors other than carbon black, those organic color
pigments which are comparatively high in transparency and
high in heat resistance, weather resistance, and solvent
10 resistance are preferably used. Particularly preferred is a
set of organic color pigments which, upon admixture, give a
substantially black shade. In this second aspect of the
invention, at least one such set of organic color pigments is
used.

15 The color pigments constituting said set of organic color
pigments of dissimilar colors other than carbon black are not
restricted in kind but can for example be selected from among
azo and condensed azo organic color pigments such as
Brilliant Carmine BS, Lake Carmine FB, Brilliant Fast Scarlet,
20 Lake Red 4R, Permanent Red R, Fast Red FGR, Toluidine Maroon,
Bisazo Yellow, Fast Yellow G, Bisazo Orange, Vulcan Orange,
Pyrazolone Red, etc.; organic color pigments in the
phthalocyanine series, such as phthalocyanine Blue, Fast Sky
Blue, phthalocyanine Green, etc.; lake series organic color
25 pigments such as Lake Yellow, Rose Lake, Violet Lake, Blue
Lake, Green Lake, etc.; oxazine series organic color
pigments; and quinophthalone series organic color pigments,
among others.

30 Referring to said one set of organic color pigments of
dissimilar colors other than carbon black, two or more of the
above-mentioned color pigments can be selectively employed.

The combination of said organic color pigments
constituting said one set of organic color pigments of
dissimilar colors other than carbon black is preferably such
35 that when said at least one set of organic color pigments of

1 dissimilar colors other than carbon black is used in
conjunction with said carbon black, the maximum spectral
transmittance of the liquid crystal display cell spacer
5 according to the second aspect of the present invention over
the entire visible wavelength region from about 400 to about
700 nm is less than 3% and the total light transmittance over
the entire visible wavelength region is 0.1 to 2.5%. The
more preferred combination is such that the maximum spectral
transmittance value is less than 2.7% and the total light
10 transmittance value is 0.2 to 2.0%.

There is no particular limitation on such combination.
For example, such combinations as blue and violet pigments,
red and blue pigments, yellow, blue, and violet pigments,
green, blue, and violet pigments, and red, blue, and violet
15 pigments can be mentioned.

From the standpoints of optical transmittance and
uniformity of film surface, the organic pigments are
preferably not greater than 1 μ m in particle diameter.

20 In the pigment component, the preferred proportion of
said carbon black is 5 to 60 weight % and the preferred
proportion of said at least one set of organic color pigments
of dissimilar colors other than said carbon black is 95 to 40
weight %. If the proportion of said carbon black is less
25 than 5 weight % and the proportion of said at least one set
of organic color pigments of dissimilar colors other than
said carbon black is greater than 95 weight %, the excessive
amount of said at least one set of organic color pigments
other than said carbon black tends to detract from the
mechanical strength of the liquid crystal display cell spacer
30 according to the second aspect of the present invention.

If the proportion of said carbon black exceeds 60 weight
% and that of said at least one set of organic color pigments
of dissimilar colors other than said carbon black is less than
40 weight %, the excessive amount of carbon black leads to an
35 amplified influence of impurities dissolving and diffusing

1 out of the carbon black so that the electrical resistance of
the liquid crystal display cell spacer of the second aspect
of the invention tends to be decreased. More preferably, the
5 proportion of said carbon black is 10 to 40 weight % and that
of said at least one set of organic color pigments of
dissimilar colors other than carbon black is 90 to 60 weight
%.

10 If the pigment component consists solely of said at least
one set of organic color pigments of dissimilar colors other
than said carbon black, even if the color pigments constitute
the optimum combination for rendition of sufficient darkness,
the increased amount of said set of organic color pigments may
detract from the mechanical strength of the liquid crystal
display cell spacer.

15 Since the color component of the liquid crystal display
cell spacer of the second aspect of the invention comprises
carbon black and at least one set of organic color pigments
of dissimilar colors other than carbon black, the necessary
amount of carbon black can be smaller so that the dissolution
20 and diffusion of impurities are decreased. Moreover, the
decrease in electrical resistance can be prevented and, at
the same time, sufficient darkness and satisfactory physical
properties can be secured.

25 The liquid crystal display cell spacer according to the
second aspect of the invention can be obtained by dispersing
said pigment component comprising said carbon black and said
at least one set of organic color pigments of dissimilar
colors other than said carbon black uniformly in a
polymerizable monomer and causing the mixture to polymerize.

30 There is no particular limitation on the method of
polymerization. Thus, suspension polymerization and emulsion
polymerization can be mentioned by way of example but in order
to obtain a uniformly colored liquid crystal display cell
spacer, a suspension polymerization process is preferred.

35 The suspension polymerization process comprises

1 dispersing said pigment component uniformly in said
polymerizable monomer and causing the mixture to polymerize
in the presence of a polymerization initiator in aqueous
medium.

5 The polymerizable monomer that can be used includes the
same monomers as mentioned for the first aspect of the
invention.

10 One or more suitable crosslinking compounds can be used
in combination with said polymerizable monomer. The kind of
crosslinking compound and its proportion may be similar to
those mentioned for the first aspect of the invention.

15 The proportion of said pigment component is preferably 1
to 180 parts by weight based on 100 parts by weight of said
polymerizable monomer. If the proportion is less than 1 part
by weight, the cell spacer may hardly be colored to a deep
shade, while the mechanical strength of the spacer tends to
be sacrificed if the pigment component accounts for more than
180 parts by weight. The particularly preferred range is 3
to 160 parts by weight.

20 For dispersing said pigment component uniformly in
said polymerizable monomer, the same machine as mentioned for
the first aspect of the invention, for instance, can be
employed.

25 A dispersing agent may be added for improved
dispersibility of said pigment component. The kind of
dispersing agent and its amount may be similar to those
mentioned for the first aspect of the invention.

30 The aqueous medium may also be the same medium as
mentioned for the first aspect of the invention.

A uniform dispersion of the pigment component in the
polymerizable monomer is suspended in a microfine fashion in
said aqueous medium. This suspending operation can be
performed using a homogenizer or the like.

35 The temperature of suspension polymerization may be
similar to that mentioned for the first aspect of the

1 invention.

The polymerization time of suspension polymerization may be similar to that mentioned for the first aspect of the invention.

5 The liquid crystal display cell spacer obtained by the above suspension polymerization can be isolated by, for example, filtration or centrifugation. The isolated spacer is rinsed with water or the like and dried by heating or in vacuo.

10 The polymerization initiator and its amount may for example be similar to those mentioned for the first aspect of the invention.

15 The mean particle diameter and coefficient of variation of particle size of the liquid crystal display cell spacer according to the second aspect of the invention may be similar to those mentioned for the first aspect of the invention.

20 Where necessary, the liquid crystal display cell spacer according to the second aspect of the present invention may have been surface-coated with a coating material such as a silane coupling agent. The silane coupling agent can be selected from among the compounds mentioned for the first aspect of the invention.

25 Since the liquid crystal display cell spacer according to the second aspect of the invention contains a pigment component comprising carbon black and at least one set of organic color pigments of dissimilar colors other than carbon black, it not only assumes a deep black color despite the small proportion of the pigment component but also has satisfactory electrical resistance. Moreover, chances for contamination of the liquid crystals due to the pigment component are minimized.

30 The third aspect of the present invention is a liquid crystal display cell spacer comprising a pigment component comprising surface-coated carbon black and at least one set of organic color pigments of dissimilar colors other than carbon

35

1 black.

5 The carbon black for use in this third aspect of the invention has been surface-coated for preventing the dissolution and diffusion of impurities. The surface-coated carbon black may be selected from among those species of carbon black mentioned for the first aspect of the invention.

10 The above-mentioned set of organic color pigments of dissimilar colors other than carbon black and its proportion can be similar to those mentioned for the second aspect of the invention.

15 The liquid crystal display cell spacer according to the third aspect of the invention can be produced by using said surface-coated carbon black in otherwise the same manner as described for the liquid crystal display cell spacer according to the second aspect of the invention.

20 The mean particle diameter and coefficient of variation of particle size of the liquid crystal display cell spacer according to the third aspect of the invention are similar to those mentioned for the first aspect of the invention.

25 Where necessary, the liquid crystal display cell spacer according to the third aspect of the invention may have been covered with a coating material such as a silane coupling agent. The silane coupling agent may be selected from among the compounds mentioned for the first aspect of the invention.

30 Since the liquid crystal display cell spacer according to the third aspect of the invention contains a surface-coated carbon black, there is little dissolution and diffusion of impurities into the spacer. This effect coupled with the effect of concomitant use of at least one set of organic color pigments of dissimilar colors other than carbon black results in a black shade even if the smaller amount of carbon black is used as compared with the first and the second aspect of the invention and insures high solvent resistance, electrical resistance and mechanical strength.

35

1 The fourth aspect of the present invention is a liquid
crystal display cell incorporating said liquid crystal display
cell spacer according to the first, second, or third aspect
of the present invention.

5 The liquid crystal display cell according to the fourth
aspect of the invention gives an excellent display image
contrast without the spacer being visually recognized as
luminescent spots in the dark or black area of the image.

10 An embodiment of the liquid crystal display cell
according to the fourth aspect of the invention is now
described with reference to the accompanying drawings.

15 As shown in Fig. 1, a liquid crystal display cell A
comprises a pair of substrates 7, 9, a spacer 8, a sealing
member 10, a nematic liquid crystalline component 11, and
polarizing sheets 12, 13.

20 The spacer 8 is disposed between the substrates 7 and 9
constituting said pair for the purpose of maintaining a
predetermined gap between the substrates 7 and 9. The
sealing member 10 is disposed around said pair of substrates
7, 9. The nematic liquid crystal line component 11 is sealed
in the space between said substrates 7 and 9. The polarizing
sheets 12 and 13 are bonded to the surfaces of the substrates
7 and 9, respectively.

25 Each of the substrates 7 and 9 comprises a transparent
glass substrate 1 or 4 with a transparent electrode 2 or 5
formed upon a pattern on one side thereof and an alignment
layer 3 or 6 (e.g. a polyimide film) coated on the surface of
the transparent electrode (2 or 5)-transparent substrate (1 or
4) assembly. The alignment layer 3 or 6 has been treated to
control alignment by rubbing.

30 The spacer 8 is a liquid crystal display cell spacer
according to the first, second, or third aspect of the
invention.

1 The following examples are intended to illustrate the
present invention in further detail and should by no means be
construed as defining the scope of the invention.

5 Example 1

Preparation of a liquid crystal cell spacer

10 To a uniform mixture of 60 parts by weight of
tetramethylolmethane triacrylate, 20 parts by weight of
divinylbenzene, and 20 parts by weight of acrylonitrile was
added 12 parts by weight of polyethylene-coated carbon black
and the carbon black was uniformly dispersed by means of a
bead mill for 48 hours.

15 This colored polymerizable monomer mixture in which said
surface-coated carbon black had been dispersed was evenly
mixed with 2 parts by weight of benzoyl peroxide and the
mixture was poured in 850 parts by weight of a 3 weight %
aqueous solution of polyvinyl alcohol. After thorough
stirring, the mixture was suspended with a homogenizer so that
the diameter of droplets of the colored polymerizable monomer
would be about 3 to 10 μ m to provide a suspension.

20 This suspension was transferred to a 2-L separable flask
equipped with a thermometer, stirrer, and reflux condenser and
heated at 85°C in a nitrogen gas atmosphere with constant
stirring. This polymerization reaction was carried out for 7
hours, at the end of which time the temperature was increased
25 to 90°C and the reaction mixture was maintained at that
temperature for 3 hours to carry the polymerization reaction
to completion. This polymerization reaction mixture was
cooled and the resulting colored particles were recovered by
filtration, rinsed well with water, and dried to provide 120
30 parts by weight of colored particles containing dispersing
pigment within the size range of 3 to 10 μ m. These colored
particles were subjected to classification to provide a liquid
crystal display cell spacer with a mean particle diameter of
35 5.55 μ m and a coefficient of variation in particle size of
2.48%.

1 The degree of darkness (light transmittance) of the
liquid crystal display cell spacer thus obtained, the
concentration of impurities in the spacer, and the electrical
resistance of the spacer were evaluated by the following
5 methods. The results are presented in Table 1.

Evaluation Methods

(1) Degree of darkness

10 A mixture of the polymerizable monomer of the same
composition as that of the above liquid crystal display cell
spacer and the color component was polymerized to prepare a 1
mm-thick wafer. The spectral transmittance of this wafer was
measured over the entire visible wavelength range of 400 to
700 nm with a spectrophotometer and the maximum value was
regarded as the degree of darkness of the liquid crystal
15 display cell spacer.

(2) The concentrations of impurities in the liquid crystal display cell spacer

20 Ten (10) grams of the liquid crystal display cell spacer
obtained was put in 330 ml of a solvent mixture
(water/isopropyl alcohol = 7/3, v/v) with stirring and the
mixture was allowed to stand at room temperature for one week
(with stirring once a day). The mixture was allowed to stand
without agitation in the final 2-day period to let the liquid
crystal display cell spacer settle. The supernatant was
25 recovered with a filter paper (0.2 μ m thick), concentrated
to 30 ml, and analyzed. The analyses for sodium and
potassium ions were carried out with Jarrell-Ash SPQ8000
atomic absorption spectrophotometer. The analyses for
chloride and sulfate ions were carried out with Dionex 2010I
30 ion chromatographic analyzer.

(3) Electrical resistance of the liquid crystal display cell spacer

35 Using Toa Dempa Ultra Megohmmeter SM-8210, the liquid
crystal display cell spacer was filled into the accessory
liquid sample electrode and the electrical resistance of the

1 liquid crystal display cell spacer was measured according to
the instruction manual for liquid samples.

Fabrication of a TN liquid crystal display cell

5 In order to evaluate the performance of a liquid crystal
display device incorporating the liquid crystal display cell
spacer obtained, a TN liquid crystal display cell of the
normally black display mode, which facilitates assessment of
the light shielding effect of spacers, was fabricated. The
10 light shielding effect of the spacer or the effect on cell gap
formation as evaluated using this test liquid crystal display
cell is translatable to the effect obtainable with an STN or
other liquid crystal display cell, so that the results of
evaluation are not exclusively valid for TN liquid crystal
15 display cells but valid for all kinds of liquid crystal
display cells.

A transparent electrically conductive indium oxide-tin
oxide film was formed in a thickness of about 500 Angstrom
units on a 0.7 mm-thick glass sheet by the low-temperature
sputtering technique and a predetermined electrode pattern was
20 formed by photolithography. Then, the surface was coated
with an alignment material and heated to obtain an alignment
layer. This glass sheet was cut to 5 cm x 12.5 cm to provide
glass substrates for a liquid crystal display cell.

25 The peripheral edge of the glass substrate obtained was
then printed with a glass fiber spacer-mixed epoxy adhesive
in a breadth of 1 mm by the screen printing technique.

After this glass substrate was set in a horizontal
position, the liquid crystal display cell spacer was scattered
over with the aid of pressurized nitrogen gas and allowed to
30 fall uniformly on the glass substrate. The scattering time
was adjusted so that the density of the liquid crystal display
cell spacer particles on the glass substrate would be about
150 particles/mm².

35 After another glass substrate was superimposed on the
liquid crystal display cell spacer-scattered glass substrate,

a load of 1 kg/cm² was applied uniformly on the whole glass substrate by means of a press. At the same time, the assembly was heated at a temperature of 160 °C for 20 minutes to cure the peripheral epoxy adhesive.

After a vacuum was established in the fabricated cell by aspiration, the liquid crystal was injected from a bore formed in a part of the peripheral seal and the injection bore was closed up under a subatmospheric intracellular pressure of 0.6 atmosphere. The cell was then heated to a predetermined temperature for liquid crystal realignment to provide a finished liquid crystal display cell.

The measured gap between the top and bottom substrates of this liquid crystal display cell was 5.38 μ m.

Evaluation methods

(1) Unevenness of color of the TN liquid crystal display cell

Polarizing sheets were set on either surface of the liquid crystal display cell so that the color of the reflecting light of the light projected against the TN liquid crystal display cell would be olive. The olive color was uniform all over without unevenness.

The following evaluation criteria were used.

◎ : no color unevenness

○ : a practically acceptable degree of color unevenness

× : a practically unacceptable degree of color unevenness

(2) The light shielding effect of the cell spacer in the TN

liquid crystal display cell

The polarizing sheets bonded to the liquid crystal display cell were set to the TN normally black mode and the assembly was observed under a transmission microscope at x 200 magnification.

With the drive voltage OFF, the darkness in the center of the spacer and the darkness of the spacer-free liquid crystal area were compared visually by using a panel of 10 assessors.

1 The evaluation was © when the number of assessors who
judged that the darkness in the center of the spacer was
deeper or equivalent accounted for 80% or more of the panel,
5 ○ when it accounted for 70 to 80%, △ when it accounted for
50 to 70%, and × when it accounted for less than 50%.

 The mean cell gap values and the results of evaluation of
color unevenness and light shielding effect are shown in
Table 1.

10 Examples 2 to 4

 Except that the compositions shown in Table 1 were used,
liquid crystal display cell spacers and cells were fabricated
and evaluated in the same manner as in Example 1. The results
are shown in Table 1.

15 Comparative Example 1

 Except that uncoated carbon black was used and the
composition shown in Table 1 was used, a liquid crystal
display cell spacer and a liquid crystal display cell were
fabricated and evaluated in the same manner as in Example 1.

 The results are shown in Table 1.

20 Comparative Example 2

 Except that the composition shown in Table 1 was used
with omission of carbon black, a liquid crystal display cell
spacer and a liquid crystal display cell were fabricated and
evaluated as in Example 1. The results are shown in Table 1.

25

30

35

Table 1

			Examples				Comparative Examples	
			1	2	3	4	1	2
Composition (weight part)	Polymerizable monomer	Tetramethyloimethane triacrylate	60	60	60	—	60	60
		Divinylbenzene	20	20	20	50	20	20
		Acrylonitrile	20	20	20	—	20	20
		Ethylene glycol dimethacrylate	—	—	—	50	—	—
	Carbon	Surface-coated carbon black	12	6	18	12	—	—
		Carbon black	—	—	—	—	30	—
Quality and performance parameters	Spacer quality	Mean particle size (μm)	5.55	3.59	7.42	4.55	6.05	5.78
		Coefficient of variation of particle size (%)	2.48	2.66	2.85	2.89	3.71	4.11
		Degree of darkness (spectral transmittance) (%)	2.6	3.0	2.2	2.5	1.5	75.7
		Electrical resistance ($\Omega \cdot \text{cm}$)	10^{11}	10^{11}	10^{13}	10^{11}	$<10^9$	10^{11}
	Levels of impurities	Sodium ion (ppm)	0.02	0.01	0.03	0.02	0.1	0.03
		Potassium ion (ppm)	0.04	0.03	0.05	0.03	0.1	0.05
		Chloride ion (ppm)	0.1	0.1	0.2	0.1	0.9	0.3
		Sulfate ion (ppm)	0.5	0.4	0.7	0.6	1.5	0.5
	Cell quality	Mean cell gap (μm)	5.38	3.38	7.03	4.00	5.63	5.65
		Evenness of color	⊙	⊙	⊙	⊙	×	⊙
		Light shielding effect	⊙	○	⊙	⊙	×	×

Example 5

Preparation of a liquid crystal display cell spacer

To a uniform mixture of 60 parts by weight of tetramethyloimethane triacrylate, 20 parts by weight of divinylbenzene, and 20 parts by weight of acrylonitrile was added 12 parts by weight of carbon black, 6 parts by weight of Phthalocyanine Blue (blue pigment), and 6 parts by weight of Dioxane Violet (violet pigment) as the black pigment component and the black pigment component was evenly dispersed by means of a bead mill for 48 hours.

This colored polymerizable monomer mixture in which said black pigment component had been dispersed was evenly mixed with 2 parts by weight of benzoyl peroxide and the mixture was

1 poured in 850 parts by weight of a 3 weight % aqueous
solution of polyvinyl alcohol. After thorough stirring, the
mixture was suspended with a homogenizer so that the diameter
5 of droplets of the colored monomer would be about 3 to 10 μ m
to provide a suspension.

This suspension was transferred to a 2-L separable flask
equipped with a thermometer, stirrer, and reflux condenser and
heated to 85°C in a nitrogen gas atmosphere with constant
10 stirring. This polymerization reaction was carried out for 7
hours, at the end of which time the temperature was raised to
90°C and the reaction mixture was maintained at that
temperature for 3 hours to carry the polymerization reaction
to completion. This polymerization reaction mixture was
15 cooled and the resulting colored particles were recovered by
filtration, rinsed well with water, and dried to provide 120
parts by weight of colored particles containing dispersing
pigment within the size range of 3 to 10 μ m. Colored
particles obtained were subjected to classification to provide
20 a liquid crystal display cell spacer with a mean particle
diameter of 6.45 μ m and a coefficient of variation in
particle size of 2.88%.

The liquid crystal display cell spacer thus obtained was
evaluated in the same manner as in Example 1, and a liquid
25 crystal display cell was fabricated and evaluated in the same
manner as in Example 1. The results are presented in Table 2.

Examples 6 to 8 and Comparative Examples 3 and 4

Except that the compositions shown in Table 2 were used,
30 liquid crystal display cell spacers and cells were fabricated
and evaluated in the same manner as in Example 5. The results
are shown in Table 2.

Table 2

			Examples				Comparative Examples	
			5	6	7	8	3	4
Composition (weight part)	Polymerizable monomer	Tetramethylolethane triacrylate	60	60	60	—	60	60
		Divinylbenzene	20	20	20	50	20	20
		Acrylonitrile	20	20	20	—	20	20
		Ethylene glycol dimethacrylate	—	—	—	50	—	—
	Carbon	Surface-coated carbon black	—	—	—	—	—	—
		Carbon black	12	10	20	25	30	—
	Pigment	Phthalocyanine blue	6	10	5	10	—	15
		Dioxazine violet	6	10	5	10	—	5
		Isindoline yellow	—	10	—	—	—	—
		Quinacridone red	—	—	15	—	—	20
Quality and performance parameters	Spacer quality	Mean particle size (μm)	6.45	4.17	8.63	5.29	7.03	6.72
		Coefficient of variation of particle size (%)	2.88	3.10	2.75	2.58	3.54	4.05
		Degree of darkness (spectral transmittance) (%)	2.5	2.8	2.0	1.7	1.6	76.4
		Electrical resistance ($\Omega \cdot \text{cm}$)	10^{11}	10^{11}	10^{11}	10^{11}	$< 10^{11}$	10^{11}
	Levels of impurities	Sodium ion (ppm)	0.02	0.02	0.03	0.02	0.1	0.03
		Potassium ion (ppm)	0.05	0.02	0.03	0.02	0.1	0.03
		Chloride ion (ppm)	0.1	0.2	0.2	0.2	0.8	0.3
		Sulfate ion (ppm)	0.5	0.3	0.3	0.4	1.2	0.4
	Cell quality	Mean cell gap (μm)	6.04	3.61	8.22	4.87	6.81	6.32
		Evenness of color	◎	◎	○	○	×	×
		Light shielding effect	◎	◎	◎	○	△	×

Examples 9 and 10

Except that the surface-coated carbon black of Example 1 and the compositions shown in Table 3 were used, liquid crystal display cell spacers and cells were fabricated and evaluated in the same manner as in Example 5. The results are shown in Table 3.

Table 3

			Examples	
			9	10
Composition (weight part)	Polymerizable monomer	Tetramethylolethane triacrylate	50	50
		Divinylbenzene	30	30
		Acrylonitrile	10	10
	Carbon	Surface-coated carbon black	6	10
		Carbon black	—	—
	Pigment	Phthalocyanine blue	7	15
		Dioxazine violet	7	5
		Isoindoline yellow	7	5
		Quinacridone red	7	20
Quality and performance parameters	Spacer quality	Mean particle size (μm)	6.8	4.9
		Coefficient of variation of particle size (%)	2.94	3.6
		Degree of darkness (spectral transmittance) (%)	2.9	2.7
		Electrical resistance ($\Omega \cdot \text{cm}$)	10^{14}	10^{14}
	Levels of impurities	Sodium ion (ppm)	0.02	0.03
		Potassium ion (ppm)	0.02	0.01
		Chloride ion (ppm)	0.2	0.2
		Sulfate ion (ppm)	0.4	0.5
	Cell quality	Mean cell gap (μm)	6.49	4.66
		Evenness of color	◎	○
		Light shielding effect	○	◎

INDUSTRIAL APPLICABILITY

Its construction having been described hereinabove, the liquid crystal display cell spacer of the present invention is very satisfactory in coloring effect and light shielding effect and has optimal electrical, physical, chemical, and optical properties. The liquid crystal display cell in incorporating this cell spacer shows a good display contrast of the image with the spacer not visualized as luminescent points in the dark area of the image.



CLAIMS

1. A liquid crystal display cell spacer comprising surface-coated carbon black.

2. A liquid crystal display cell spacer comprising a pigment component comprising carbon black and at least one set of organic pigments of dissimilar colors other than carbon black.

3. A liquid crystal display cell spacer comprising a pigment component comprising surface-coated carbon black and at least one set of organic pigments of dissimilar colors other than carbon black.

4. A liquid crystal display cell comprising a liquid crystal display cell spacer according to Claim 1, 2, or 3.

This Sheet Has Been Replaced



1

ABSTRACT

5 The present invention relates to a liquid crystal display
cell spacer with improved in coloring effect and light
shielding effect and optimal electrical, physical, chemical,
and optical properties and a liquid crystal display cell with
use thereof. A liquid crystal display cell spacer
10 comprising surface-coated carbon black; a liquid crystal
display cell spacer comprising a pigment component comprising
carbon black and at least one set of organic pigments of
dissimilar colors other than carbon black; and a liquid
crystal display cell spacer comprising a pigment component
15 comprising surface-coated carbon black and at least one set of
organic pigments of dissimilar colors other than carbon
black. A liquid crystal display cell with use any of above
liquid crystal display cell spacers.

20


25

30

35

DRAWING

Fig. 1





CLAIMS

1. (Amended) A liquid crystal display cell spacer comprising surface-coated carbon black with dispersing uniformly.
2. A liquid crystal display cell spacer comprising a pigment component comprising carbon black and at least one set of organic pigments of dissimilar colors other than carbon black.
3. A liquid crystal display cell spacer comprising a pigment component comprising surface-coated carbon black and at least one set of organic pigments of dissimilar colors other than carbon black.
4. A liquid crystal display cell comprising a liquid crystal display cell spacer according to Claim 1, 2, or 3.

